

Mimbres Pottery. Production and Distribution

Robert J. Speakman

ADVERTIMENT. La consulta d'aquesta tesi queda condicionada a l'acceptació de les següents condicions d'ús: La difusió d'aquesta tesi per mitjà del servei TDX (www.tdx.cat) i a través del Dipòsit Digital de la UB (diposit.ub.edu) ha estat autoritzada pels titulars dels drets de propietat intel·lectual únicament per a usos privats emmarcats en activitats d'investigació i docència. No s'autoritza la seva reproducció amb finalitats de lucre ni la seva difusió i posada a disposició des d'un lloc aliè al servei TDX ni al Dipòsit Digital de la UB. No s'autoritza la presentació del seu contingut en una finestra o marc aliè a TDX o al Dipòsit Digital de la UB (framing). Aquesta reserva de drets afecta tant al resum de presentació de la tesi com als seus continguts. En la utilització o cita de parts de la tesi és obligat indicar el nom de la persona autora.

ADVERTENCIA. La consulta de esta tesis queda condicionada a la aceptación de las siguientes condiciones de uso: La difusión de esta tesis por medio del servicio TDR (www.tdx.cat) y a través del Repositorio Digital de la UB (diposit.ub.edu) ha sido autorizada por los titulares de los derechos de propiedad intelectual únicamente para usos privados enmarcados en actividades de investigación y docencia. No se autoriza su reproducción con finalidades de lucro ni su difusión y puesta a disposición desde un sitio ajeno al servicio TDR o al Repositorio Digital de la UB. No se autoriza reserva de derechos afecta tanto al resumen de presentación de la tesis como a sus contenidos. En la utilización o cita de partes de la tesis es obligado indicar el nombre de la persona autora.

WARNING. On having consulted this thesis you're accepting the following use conditions: Spreading this thesis by the TDX (**www.tdx.cat**) service and by the UB Digital Repository (**diposit.ub.edu**) has been authorized by the titular of the intellectual property rights only for private uses placed in investigation and teaching activities. Reproduction with lucrative aims is not authorized nor its spreading and availability from a site foreign to the TDX service or to the UB Digital Repository. Introducing its content in a window or frame foreign to the TDX service or to the UB Digital Repository is not authorized (framing). Those rights affect to the presentation summary of the thesis as well as to its contents. In the using or citation of parts of the thesis it's obliged to indicate the name of the author.

Departament de Prehistòria, Història Antiga i Arqueologia

Programa de Doctorat:

Universitat de Barcelona

Societat i Cultura

Mimbres Pottery Production and Distribution

Robert J. Speakman

2013

Tesi Doctoral dirigida per:

Dr. Jaume Buxeda i Garrigós Professor Agregat d'Arqueologia

Abstract

Mimbres-Mogollon people inhabited areas of southwestern New Mexico from approximately A.D. 200–1150, with settlements located primarily in the Gila, Mimbres, and Rio Grande Valleys and immediate adjacent areas. Among the most recognizable of Mimbres cultural traits is the production of a white-slipped brown-paste ceramic decorated with bold, black, geometric designs. By about A.D. 1000, Mimbres pottery came to be more elaborately decorated with finely executed geometric designs; in some cases, vessels were decorated with naturalistic motifs of animals, humans, plants, and anthropomorphized figures. This research project examines the production and distribution of Mimbres-Mogollon pottery using instrumental neutron activation analysis (INAA, NAA) to identify pottery production sites and the movement of pottery throughout the Mimbres and adjacent regions of the American Southwest.

Since publication of Gilman et al.'s (1994) seminal study of Mimbres pottery from the American Southwest using NAA, dozens of research projects involving the analyses of Mimbres-Mogollon and Jornada-Mogollon pottery have occurred. Projects have ranged in scale from small (<30) to large (e.g., 100–200 samples). These combined efforts have resulted to date in the analyses of thousands of Mimbres-Mogollon and Jornada-Mogollon ceramics and clays. Very little of this research has been formally published, and until now there has been no comprehensive analysis and interpretation that includes most/all extant NAA data.

In addition to hundreds of recent NAA analyses conducted for this project, most extant data generated for earlier Mimbres NAA projects are

incorporated into this study. In total, the dataset includes more the 3,600 NAA analyses of pottery and clays obtained from several hundred archaeological sites in Arizona, New Mexico, Texas, and northern Mexico.

Research discussed herein provides—from a chemical perspective—the most accurate and comprehensive interpretation of Mimbres pottery production and distribution to date. Statistical analysis of the NAA dataset resulted in the identification of 35 distinct pottery groups. This finding is in contrast to most previous studies that only identified on average four to six compositional groups. Knowledge of the true group structure allows for a more accurate reconstruction of Mimbres pottery production and distribution and allows for examinations of temporal changes. Ultimately, this research will serve as a basis for archaeologists seeking to examine a broad range of topics related to Mimbres social organization and interaction, gender, and ideology.

Resumen

Els integrants de la cultura Mimbres-Mogollón habitaven zones del sud-oest de Nou Mèxic des d'aproximadament el 200-1150 dC, en assentaments ubicats principalment a les valls de Gila, Mimbres i de Río Grande i les zones adjacents immediates. Entre el trets culturals més característics de la societat Mimbres hi ha la producció d'una ceràmica de pasta marró i d'engalba blanca decorada amb audaços dissenys negres i figures geomètriques. Cap a l'any 1000 dC, la ceràmica Mimbres va arribar a ser més elaborada, decorada amb dissenys geomètrics finament executats. En alguns casos, les peces estaven decorades amb motius naturalistes d'animals, éssers humans, plantes i figures antropomorfiques. Aquest projecte d'investigació analitza la producció i distribució de la ceràmica Mimbres-Mogollon utilitzant l'anàlisi per activació neutrònica instrumental (INAA, NAA), tècnica d'anàlisi química emprada per identificar els llocs de producció de ceràmica i el moviment de la ceràmica a través de les regions de Mimbres i les regions adjacents del sud-oest dels Estats Units.

Des de la publicació de Gilman et al. (1994) i el seu estudi acadèmic de la ceràmica Mimbres del sud-oest americà a partir de NAA, s'han produït desenes de projectes de recerca que impliquen l'anàlisi de ceràmiques i argiles de Mimbres-Mogollón i Jornada-Mogollon. Els projectes han oscil·lat en escala des de petits projectes (<30) a grans projectes (per exemple, de 100 a 200 mostres). Tots aquests esforços s'han traduït fins ara en l'anàlisi de milers de ceràmiques i argiles de Mimbres-Mogollón i Jornada-Mogollón. Molt poca d'aquesta investigació ha estat publicada oficialment, i fins ara no hi ha hagut una anàlisi exhaustiva i d'interpretació que inclogui la majoria o totes les dades de NAA existents.

A més dels centenars de les darreres anàlisis realitzades per NAA per aquest projecte, les dades existents generades en anteriors projectes per NAA sobre ceràmiques de Mimbres s'han incorporat en aquest estudi. En total, el conjunt de dades inclou més de 3.600 anàlisis per NAA de ceràmica i argiles obtingudes a centenars de llocs arqueològics d'Arizona, de Nou Mèxic, de Texas i del nord de Mèxic.

La investigació descrita aquí ofereix, des de la perspectiva de la química i l'arqueologia, la interpretació més precisa i completa a dia d'avui de la producció de la ceràmica Mimbres i de la seva distribució. L'anàlisi estadística del conjunt de dades de NAA ha resultat en la identificació de 35 grups diferents de ceràmica. Aquesta troballa contrasta amb la majoria dels estudis anteriors, els quals només van identificar de mitjana de quatre a sis grups composicionals. El coneixement de l'estructura dels grups químics permet una reconstrucció més precisa de la producció i distribució de la ceràmica de la cultura Mimbres, així com també proporciona una important eina per avaluar els canvis culturals i temporals. En última instància, aquesta investigació servirà com a base per als arqueòlegs que busquen examinar una àmplia gamma de temes relacionats amb l'organització cultural de Mimbres i la seva interacció social, el gènere i la ideologia.

Acknowledgements

I conducted my first NAA project at the MURR Archaeometry Laboratory 1997. At that time, I knew very little about chemistry or physics, but I became hooked on this aspect of archaeological science almost immediately. A year later, Mike Glascock hired me on at the Archaeometry Laboratory as a graduate student and promoted me into a full-time staff position in 1999. My initial exposure to NAA, which happened simply because I was in the right place at the right time, sparked an interest in archaeological science that launched me into a very different career trajectory than I had previously envisioned or even considered. I am grateful to Mike Glascock who has served as my mentor, teacher, collaborator, colleague, advisor, and friend over the past 15 years. Likewise, I am grateful for the educational and training opportunities that I received at MURR between 1997 and 2006.

This dissertation project, in large part, is Darrell Creel's vision, and without him, there is no way that this dissertation could have come together in its present form. In 2004, Darrell and I began talking seriously about combining the extant Mimbres NAA data from the Texas A&M and Smithsonian-NIST laboratories with the NAA data from MURR. Early on, I recognized this would be challenging process, but that it would make a great contribution to the archaeology of the Mimbres region and decided to take the project on as dissertation project. In hindsight, if I had fully appreciated just how challenging the interpretation of this dataset would eventually become, I probably never would have attempted this particular dissertation project. Throughout all aspects of this research, Darrell freely shared information, was always there to provide logistical support, and answered my numerous questions. As this research progressed, Darrell arranged for the analyses of new samples to fill in the largest of the gaps in the coverage of the database. He also tracked down descriptive data for many of the Texas A&M samples and identified and corrected numerous issues in the database. Darrell constantly pushed me on the identification of the compositional groups, questioned

these groups, and served as a sounding board for my ideas. Darrell also read and commented on numerous drafts of this dissertation—a task that I greatly appreciate.

This dissertation project represents a collaborative effort involving numerous individuals and organizations who have shared data developed for their various NAA projects over the past 20 years. I especially want to thank Myles Miller who was a tremendous source of information throughout this process and provided much information and advice as I was working with the data. I also thank the individuals who contributed samples and/or NAA data used in this study. This includes Robbie Brewington, Shari Chandler, Tim Church, Andy Cloud, Darrell Creel, Eleanor Dahlin, Kathryn Donoho, Pat Gilman, Thomas Gruber, Michelle Hegmon, Deb Huntley, Jane Kelly, Nancy Kenmotsu, Meade Kermer, Karl Laumbach, Ken Lawrence, Stephen Lekson, Chris Lowry, Mike Mallouf, Valli Powell-Marti, Mike Quigg, Holly Meier, Lori Reed, Barbara Roth, Bernard Schriever, Harry Shafer, Debra Taylor, Matthew Taliaferro, Chris Turnbow, and Kristina Wyckof. I also extend thanks to the Peabody Museum, Harvard University, Western New Mexico University Museum, Arizona State Museum, and University of Arkansas Museum for allowing their collections to be sampled and analyzed by NAA. I apologize in advance to anyone who I may have inadvertently omitted.

INAA analyses conducted at the University of Missouri Research Reactor were supported, in part, by various NSF grants awarded to the Archaeometry Lab at MURR. These include NSF grants 1110973, 0802757, 0504015. Other direct support came from the University of Texas—Austin, the University of Missouri, and the Smithsonian Institution. Additionally, all the researchers mentioned above had various state and federal funding sources that supported their excavations and the analytical costs of their specific samples.

The scientists who run the NAA programs at the MURR, the Smithsonian, and Texas A&M are among the best in their fields. I thank Mike Glascock, Ron Bishop, and

Dennis James for their efforts. I also thank Ron Bishop for providing me with access to Pat Gilman's original NAA data and for providing me with Pat's archived ceramic samples so that I could conduct additional NAA analyses to generate data for the short-lived elements. I thank Dennis James for answering numerous questions regarding the Texas A&M data. I also thank Hector Neff (who was at MURR until 2002) for patiently working with me and training me on the interpretation of NAA data generated for pottery and clays.

Javier G. Iñañez has been a good friend and colleague for many years. Javier was instrumental in helping me apply to the Doctoral Program at UB and spent countless hours navigating the bureaucratic processes on my behalf to ensure that all of my paperwork was in order. I also am grateful to Javier for introducing me to Jaume Buxeda i Garrigós and the University of Barcelona (UB). I am also grateful to Jaume Dantí i Riu, Marisol Madrid i Fernández, and Jaume Buxeda i Garrigós for their assistance throughout this process.

Steven Shackley read earlier drafts of my dissertation and provided a much appreciated perspective on the geological processes of southwest New Mexico. His comments and insights are greatly appreciated.

In addition to Mike Glascock and Darrell Creel, the other members of my dissertation committee have been a tremendous source of assistance. I am especially grateful to Jaume Buxeda i Garrigós for accepting me as his Ph.D. student at the University of Barcelona and for all of the assistance that he has provided.

This dissertation is dedicated to LuElla Parks Speakman whose love, encouragement, and support made this all possible. Now that I'm finally done with my dissertation, I look forward doing things that we always postponed because I wasn't finished yet. I love you, Lu!

Table of Contents

Chapte	er 1: Introduction and Background	
	Introduction	1
	Mimbres Mogollon Background	1
	Research Background	7
	Overview of the Ceramic Sample	11
	Summary	17
Chapte	er 2: Previous NAA Research in the Mimbres & Jornada Regions	
	Overview of Previous NAA Research	19
	Gilman et al. 1994	23
	James et al. 1995	26
	Brewington et al. 1996	28
	Brewington and Shafer 1999	31
	Shafer 2001; James 2001	33
	Powell 2000; Powell-Marti and James 2006	35
	Chandler 2000	39
	Dahlin 2003	40
	Dahlin et al. 2007	44
	MURR (Neff & Speakman)	45
	Schriever (2008)	48
-	er 3: Instrumental Neutron Activation Analysis (INAA) and aches to Interpreting Compositional Data	
	Overview of INAA	52
	INAA Sample Preparation at MURR	53
	INAA Sample Preparation at Texas A&M	55
	INAA Sample Preparation at the Smithsonian Institution	56
	Irradiation and Gamma-Ray Spectroscopy at MURR	56
	Irradiation and Gamma-Ray Spectroscopy at Texas A&M	58
	Irradiation and Gamma-Ray Spectroscopy at the Smithsonian Institution	59
	Approaches to Interpreting Chemical Data	62

Chapter 4: Group Structure and Interpretation of INAA Data	
4.1. Identification of Macro Groups	71
4.2. Macro Group A	78
Mimbres-01	84
Mimbres-03	87
Mimbres-7A and 7B	89
Mimbres-10	91
Mimbres-13	93
4.3. Macro Group B	95
Macro Group B-1 Compositional Groups	
Mimbres-04A, B, and C	110
Mimbres-05A, B, and C	117
Mimbres-09	124
Macro Group B-2 Compositional Groups	
Mimbres-02A	125
Mimbres-02B	127
Mimbres-02C	128
Mimbres-08	130
Mimbres-11	132
4.4. Macro Group C	134
Macro Group C-1 Compositional Groups	
Mimbres-21	151
Mimbres-22	153
Mimbres-23	155
Mimbres-24	157
Mimbres-27	159
Mimbres-28	159
Macro Group C-2 Compositional Groups	
Mimbres-41	161
Mimbres-42	163
Mimbres-43	165
Mimbres-44	165
Mimbres-46	167
Mimbres-47	167
Mimbres-48	169
Mimbres-49A	169
Mimbres-49B	172

4.5. Macro Group D

173

Chapter 5: Discussion of Results and Conclusions

Introduction	177
Summary of Compositional Groups	178
Broad Scale Temporal Change in Pottery Production	184
Mimbres-01 Temporal Change	188
Mimbres-02A, Mimbres-08, and Mimbres-11 Temporal Change	191
Mimbres-03 Temporal Change	191
Mimbres-04A Temporal Change	192
Mimbres-49A and Mimbres 4C Temporal Change	193
Mimbres-5A Temporal Change	193
Mimbres-21 Temporal Change	194
Mimbres-22 Temporal Change	194
Mimbres-24 Temporal Change	194
Classic Period Pottery Production—Specialized or Not?	197
Recommendations for Future Research	199
Re-Evaluation of Previous Research Questions	200
Targeted Sampling	200
Raw Material Survey and Analysis.	201
Petrographic Studies	202
Conclusions	204
References Cited	209
Appendix A: Macro Group A Mahalanobis Distance Calculations and PCA Scores	218
Appendix B: Macro Group B Mahalanobis Distance Calculations and PCA Scores	199 200 200 201 202 204 209 A Scores 218 A Scores 232 A Scores 271
Appendix C: Macro Group C Mahalanobis Distance Calculations and PCA Scores	271
Appendix D: Macro Group D Mahalanobis Distance Calculations	299
Appendix E: NAA data and Descriptive Information	313

List of Tables

Table 1.1. General Mimbres-Mogollon cultural sequence.	6
Table 3.1 Radioactive isotopes and gamma-ray energies used for INAA at the MURR and Texas A&M laboratories.	60
Table 3.2 Radioactive isotopes and gamma-ray energies used for INAA at the Smithsonian Institution.	61
Table 4.3.1. Mahalanobis Distance (M.D.) probabilities for clay samples projected against Mimbres-04C.	116
Table 4.3.2. Mahalanobis Distance (M.D.) probabilities for clay samples projected against Mimbres-05A.	119
Table 4.3.3. Mahalanobis Distance (M.D.) probabilities for clay samples projected against Mimbres-05B.	122
Table 4.4.1. Mahalanobis Distance (M.D.) probabilities for clay samples projected against Mimbres-41.	162
Table 4.4.2. Mahalanobis Distance (M.D.) probabilities for clay samples projected against Mimbres-49A.	171
Table 5.1. Summary of compositional Groups, presumed production locale, and ceramic types associated with each group.	180
Table 5.2. Counts and frequencies for Three Circle R/W and Mimbres B/W Styles I— III pottery assigned to the 14 largest compositional groups	186
Table A1. Macro Group A Mahalanobis distance calculations and posterior classification.	219
Table A2. Macro Group A Mahalanobis distance calculations for specimens projected against two or more groups .	227
Table A3. Principal component analysis for Macro Group A pottery (R-Q factor analysis based on variance-covariance matrix).	229
Table B1. Macro Group B-1 Mahalanobis distance calculations for specimens projected against two or more groups.	233
Table B2. Macro Group B1 Mahalanobis distance calculations for specimens projected against two or more groups.	247
Table B3. Macro Group B-2 Mahalanobis distance calculations for specimens projected against two or more groups.	248
Table B4. Macro Group B2 Mahalanobis distance calculations for specimens projected against two or more groups.	257
Table B5. Mahalanobis distance calculations for unassigned specimens projected against Macro Group B compositional groups.	258
Table B6. Principal component analysis for Macro Group A pottery (R-Q factor analysis based on variance-covariance matrix).	268

Table C1. Macro Group C-1 Mahalanobis distance calculations for specimens projected against two or more groups.	272
Table C2. Macro Group C-1 Mahalanobis distance calculations for specimens projected against two or more groups.	278
Table C3. Macro Group C-2 Mahalanobis distance calculations for specimens projected against two or more groups.	281
Table C4. Macro Group C-2 Mahalanobis distance calculations for specimens projected against two or more groups.	285
Table C5. Principal component analysis for Macro Group C-1 pottery (R-Q factor analysis based on variance-covariance matrix).	290
Table C6. Principal component analysis for Macro Group C-2a pottery (R-Q factor analysis based on variance-covariance matrix).	293
Table C7. Principal component analysis for Macro Group C-2b pottery (R-Q factor analysis based on variance-covariance matrix).	296
Table D1. Macro Group B1 Mahalanobis distance calculations for specimens projected against two or more groups.	300
Table E1. NAA data and descriptive information.	314

List of Figures

Figure 1.1. Map of the American Southwest ca. AD 1100 showing the approximate geographical extent of Mimbres and other Southwestern cultural groups	3
Figure 1.2. Examples of Classic Period Mimbres Black-on-white pottery decorated with naturalistic motifs	5
Figure 1.3. Map of southern Arizona, southern New Mexico, and northern Mexico showing the locations of sites with Mimbres-Mogollon pottery included in this study	13
Figure 1.4. Map of southwest New Mexico showing the locations of sites with Mimbres-Mogollon pottery included in this study	14
Figure 1.5. Bar chart showing numbers of analyzed samples by ceramic type/category	15
Figure 1.6. Histogram showing the frequency of sites relative to the numbers of analyzed Mimbres-Mogollon pottery	16
Figure 2.1. Example of Mimbres B/W bowl decorated with an anthropomorphic design	21
Figure 2.2. Plot of canonical (discriminant) 1 versus canonical (discriminant) 2 for the 117-specimen Mimbres NAA study conducted by Gilman et al. (1994)	25
Figure 2.3. Plot of Principal Component 1 versus Principal Component 2 for the 200+ specimen Mimbres NAA study conducted by James et al. (1995)	27
Figure 2.4. Discriminant Analysis plot showing groups defined by Brewington et al. (1996)	30
Figure 2.5. Discriminant Analysis plot showing groups defined by Brewington and Shafer (1999)	32
Figure 2.6. Principal component analysis plot showing groups reported in Shafer (2001)	34
Figure 2.7. Discriminant Analysis plot showing groups reported in Shafer (2001)	35
Figure 2.8. Principal Component plot (PC1 versus PC2) showing groups defined by Powell (2000)	37
Figure 2.9. Regional level discriminant analysis of samples included in Dahlin (2003).	43
Figure 2.10. Site level discriminant analysis of samples included in Dahlin (2003).	43
Figure 2.11. Plot of discriminant analysis scores for pottery included in Dahlin et al. (2007).	45

Figure 2.12. Plot of tantalum and chromium base-10 logged concentrations showing the separation of Groups 1 and 2 in Schriever's NAA dataset.	50
Figure 2.13. Plot of chromium and cesium base-10 logged concentrations showing the separation of Groups 3–7 in Schriever's NAA dataset.	51
Figure 3.1. Diagram illustrating the process of neutron capture by a target nucleus followed by the emission of gamma rays.	52
Figure 3.2. The University of Missouri Research Reactor.	55
Figure 4.1.1. Alma Rough wide-mouthed jar (modified seed jar form) from the Power Site (LA 121210).	73
Figure 4.1.2. Plot of thorium and dysprosium showing separation of Macro Group A from Macro Group B.	74
Figure 4.1.3. Plot of thorium and iron showing separation of Macro Group B from Macro Group C.	75
Figure 4.1.4. Plot of thorium and tantalum showing separation of Macro Groups A, C, and D.	76
Figure 4.1.5. Plot of tantalum and iron showing separation of Macro Group B from Macro Group C.	77
Figure 4.2.1. Biplot of principal components 1 and 2 derived from PCA of the variance-covariance matrix for Macro Group A pottery.	79
Figure 4.2.2. Plot of principal components 1 and 2 derived from PCA of the variance-covariance matrix for Macro Group A pottery.	80
Figure 4.2.3. Biplot of principal components 1 and 4 derived from PCA of the variance-covariance matrix for Macro Group A pottery.	81
Figure 4.2.4. Plot of principal components 1 and 4 derived from PCA of the variance-covariance matrix for Macro Group A pottery.	82
Figure 4.2.5. Plot of chromium and cesium base-10 logged concentrations showing separation of Macro Group A pottery.	83
Figure 4.2.6. Graduated symbol distribution map for Mimbres-01 pottery.	86
Figure 4.2.7. Graduated symbol distribution map for Mimbres-03 pottery.	88
Figure 4.2.8. Graduated symbol distribution map for Mimbres-07A pottery.	90
Figure 4.2.9. Graduated symbol distribution map for Mimbres-10 pottery.	92
Figure 4.2.10. Map showing the site distribution for Mimbres-13 pottery.	94
Figure 4.3.1. Plot of principal components 1 and 2 derived from PCA of the variance-covariance matrix for Macro Group B pottery.	98

Figure 4.3.2. Biplot of principal components 1 and 2 derived from PCA of the variance-covariance matrix for Macro Group B pottery.	99
Figure 4.3.3. Plot of principal components 1 and 2 derived from PCA of the variance-covariance matrix for Macro Group B pottery showing unassigned pottery specimens.	100
Figure 4.3.4. Plot of principal components 1 and 2 derived from PCA of the variance-covariance matrix for Macro Group B pottery showing Group B clay specimens.	101
Figure 4.3.5. Plot of chromium and ytterbium base-10 logged concentrations showing Macro Group B-1 pottery.	102
Figure 4.3.6. Plot of samarium and europium base-10 logged concentrations showing separation of Mimbres-04 and Mimbres-09 pottery.	103
Figure 4.3.7. Plot of ytterbium and chromium base-10 logged concentrations showing separation of Mimbres-04 and Mimbres-05 pottery.	104
Figure 4.3.8. Plot of chromium and thorium base-10 logged concentrations showing separation of Mimbres-04 pottery into three subgroups designated 4A, 4b, and 4C.	105
Figure 4.3.9. Plot of chromium and thorium base-10 logged concentrations showing separation of Mimbres-05 pottery into three subgroups designated 5A, 5b, and 5C.	106
Figure 4.3.10. Plot of zirconium and hafnium base-10 logged concentrations showing the separation of Mimbres-05B and Mimbres-05C pottery.	107
Figure 4.3.11. Plot of Canonical Discriminant 1 and 2 showing separation of all B-1 pottery groups.	108
Figure 4.3.12. Plot of cesium and chromium base-10 logged concentrations showing separation of pottery groups assigned to Macro Group B-2.	109
Figure 4.3.13. Graduated symbol distribution map for Mimbres-04A pottery.	112
Figure 4.3.14. Graduated symbol distribution map for Mimbres-04B pottery.	114
Figure 4.3.15. Graduated symbol distribution map for Mimbres-04C pottery.	117
Figure 4.3.17. Graduated symbol distribution map for Mimbres-05B pottery.	119
Figure 4.3.18. Map showing the location of the Gobernadora site.	121
Figure 4.3.19. Graduated symbol distribution map for Mimbres-09 pottery.	124
Figure 4.3.20. Graduated symbol distribution map for Mimbres-02A pottery.	126
Figure 4.3.21. Graduated symbol distribution map for Mimbres-02B pottery.	128

Figure 4.3.22. Graduated symbol distribution map for Mimbres-02C pottery.	129
Figure 4.3.23. Graduated symbol distribution map for Mimbres-08 pottery.	131
Figure 4.3.24. Graduated symbol distribution map for Mimbres-11 pottery.	133
Figure 4.4.1. Plot of cesium and titanium base-10 logged concentrations showing separation of Macro Groups C-1 and C-2.	136
Figure 4.4.2. Plot of cesium and titanium base-10 logged concentrations showing Macro Group C clays projected against 90% confidence ellipses for groups C-1 and C-2.	137
Figure 4.4.3. Biplot of principal components 1 and 2 derived from PCA of the correlation matrix for Macro Group C-1 pottery.	138
Figure 4.4.4. Plot of principal components 1 and 2 derived from PCA of the correlation matrix for Macro Group C-1 pottery showing unassigned pottery specimens.	139
Figure 4.4.5. Plot of scandium and cerium base-10 logged concentrations showing Macro Group C-1 pottery groups Mimbres-21, -22, and -28.	140
Figure 4.4.6. Plot of samarium and uranium base-10 logged concentrations showing Macro Group C-1 pottery groups Mimbres-23, -24, and -27.	141
Figure 4.4.7. Plot of manganese and iron base-10 logged concentrations showing Macro Group C-1 pottery groups Mimbres-21 and Mimbres-24.	142
Figure 4.4.8. Plot of chromium and zirconium base-10 logged concentrations showing separation of Macro Group C-2 subgroups.	143
Figure 4.4.9. Plot of chromium and zirconium base-10 logged concentrations showing unassigned specimens relative to Macro Group C-2 subgroups.	144
Figure 4.4.10. Plot of chromium and zirconium base-10 logged concentrations showing separation of Macro Group C-2 subgroups.	145
Figure 4.4.11. Biplot of principal components 1 and 2 derived from PCA of the correlation matrix for Macro Group C-2a pottery.	146
Figure 4.4.12. Plot of europium and iron base-10 logged concentrations showing separation of Mimbres-46 and Mimbres-49B from Mimbres-42 and Mimbres-49A.	147
Figure 4.4.13. Plot of thorium and scandium base-10 logged concentrations showing separation of Mimbres-42 from Mimbres-49A.	148
Figure 4.4.14. Biplot of principal components 1 and 2 derived from PCA of the variance-covariance matrix for Macro Group C-2b pottery.	149
Figure 4.4.15. Plot of manganese and scandium base-10 logged concentrations showing separation of Macro Group C-2b pottery.	150

Figure 4.4.16. Graduated symbol distribution map for Mimbres-21 pottery.	152
Figure 4.4.17. Graduated symbol distribution map for Mimbres-22 pottery.	154
Figure 4.4.18. Graduated symbol distribution map for Mimbres-23 pottery.	156
Figure 4.4.19. Graduated symbol distribution map for Mimbres-24 pottery.	158
Figure 4.4.20. Map showing the locations of sites associated with Mimbres-27 and Mimbres-28 compositional groups.	160
Figure 4.4.21. Graduated symbol distribution map for Mimbres-41 pottery.	162
Figure 4.4.22. Graduated symbol distribution map for Mimbres-42 pottery.	164
Figure 4.4.23. Graduated symbol distribution map for Mimbres-44 pottery.	166
Figure 4.4.24. Graduated symbol distribution map for Mimbres-47 pottery.	168
Figure 4.4.25. Graduated symbol distribution map for Mimbres-49A pottery.	171
Figure 4.4.26. Map with site locations for pottery assigned to Mimbres-49B.	172
Figure 4.5.1. Plot of chromium and ytterbium base-10 logged concentrations showing the El Paso Core, El Paso-2, and El Paso Loop 375 groups.	175
Figure 4.5.2. Map showing site locations for pottery assigned to the El Paso Loop 375 group.	176
Figure 5.1. Example of Classic Period Mimbres Polychrome bowl decorated with a macaw motif.	176
Figure 5.2. Map showing the distribution of compositional groups identified in this study relative to their assumed production areas.	182
Figure 5.3. Map showing the distribution of Mimbres Valley and Arenas Valley (Treasure Hill) and Cameron Creek compositional groups identified in this study relative to their production areas.	183
Figure 5.4. Bar chart showing frequencies of Three Circle R/W and Mimbres B/W Styles I–III for the 14 largest compositional groups.	187
Figure 5.5. Map showing the distribution of Mimbres B/W Style II pottery assigned to the Mimbres-01 group.	190
Figure 5.6. Maps showing the distribution of pottery production during the Late Pithouse and Classic Periods.	196
Figure 5.7. Map showing the distribution of clays analyzed by INAA	203

Chapter 1

Introduction and Background

Introduction

In this dissertation, I examine Mimbres-Mogollon pottery production and distribution using instrumental neutron activation analysis (INAA, NAA) to identify pottery production sites and the movement of pottery throughout the Mimbres Valley and adjacent regions. In addition to hundreds of recent analyses conducted for this project (in collaboration with Darrell Creel and others), I incorporate, where possible, extant data generated for earlier Mimbres INAA projects. In total, the dissertation dataset draws on more than 2,900 analyses of Mimbres-Mogollon pottery and approximately 160 clays. I also include for comparative purposes approximately 600 Jornada-Mogollon ceramics manufactured in and around El Paso, Texas. In total, the dataset includes more the 3,600 INAA samples. The Mimbres-Mogollon dataset includes pottery from 165 archaeological sites across Arizona, New Mexico, Texas, and northern Mexico. To date more than 35 compositional groups have been identified.

Mimbres-Mogollon Background

Mimbres-Mogollon people inhabited areas of southwestern New Mexico from approximately A.D. 200–1150, with settlements located primarily in the Gila, Mimbres, and Rio Grande Valleys and immediate adjacent areas (Figure 1.1). The Mimbres represent one of several branches of the Mogollon tradition and are one of four major cultural traditions defined for the American Southwest—the others being the Hohokam, Anasazi

(now referred to as Ancestral Puebloan) and Patayan. Mogollon people, recognizable by shared ceramic traditions and settlement patterns, appear to have developed out of the earlier Archaic traditions of the region. Beginning in the Late Archaic period (1500 B.C. – A.D. 200), it appears that similar developmental trends, including the acquisition and refinement of agriculture and pottery technologies, occur relatively contemporaneously across the Mogollon region and the southern American Southwest. Mimbres sites begin to emerge around A.D. 200 with the Early Pithouse period and extend into the late A.D. 1100s with the Terminal Classic period within the Mimbres Valley (Hegmon 2002) and into the A.D. 1200s in the Rio Grande Valley (termed the Postclassic or Reorganization phase) (Hegmon et al. 1998). However, it is not until about A.D. 700 that the Mimbres culture reliably can be distinguished from other Mogollon cultural expressions (Anyon 1984).




Figure 1.1. Map of the American Southwest ca. A.D. 1100 showing the approximate geographical extent of Mimbres and other Southwestern cultural groups.

The development of the Mimbres into a distinct cultural tradition is marked by changes in architecture, settlement patterns, an increased dependence on agriculture (maize, cotton, beans, and squash), and the manufacture of stylistically unique decorated pottery. The Mimbres Classic period (ca. A.D. 1000–1130) is the height of Mimbres culture. During this period, Mimbres people aggregated in large, closely spaced masonry-constructed surface pueblo communities. The largest concentrations of these villages were in the Mimbres Valley. A generalized cultural sequence for the Mimbres-Mogollon is provided in Table 1.1 along with pottery types and architectural traits.

Most recognizable of all Mimbres traits is the development of a white-slipped pottery decorated with black geometric designs. By about AD 900, some pottery vessels depicted humans and animals; but during the Classic period, the ceramics became elaborately painted, many of which included naturalistic motifs of animals, humans, plants, and anthropomorphized figures (Figure 1.2). Many scenes depict aspects of everyday life and the natural environment. Pots decorated with these elaborate motifs represent a relatively small percentage of Mimbres ceramic assemblages, but they epitomize Classic Mimbres culture and reveal aspects of Mimbres culture and ideology that could not otherwise be gleaned from the archaeological record.



Figure 1.2. Examples of Classic Period Mimbres Black-on-white pottery decorated with naturalistic motifs. Images are courtesy of the Smithsonian Institution.

Table 1.1. General Mimbres-Mogollon cultural sequence. (Compiled from Anyon et al. 1981; Dahlin 2003; Hegmon et al. 1998; Hegmon 2002; Schriever 2008)

Period	Phase	Dates (A.D.)	Areas	Architecture	Pottery
Early Pithouse	Cumbre	200–550	NW Mogollon and Mimbres regions	Circular and oval pit structures	Plainware
	Georgetown	550-650	NW Mogollon and Mimbres regions	Circular and D- shaped pit structures	Plainware and Redware
onse	San Francisco	650-800	NW Mogollon and Mimbres regions	Rounded rectangular pit structures	Plainware, Redware, Alma Neck Banded, Mogollon R/B
Late Pithouse	Three Circle	750/800– 900	NW Mogollon and Mimbres regions	Rectangular and square pit structures	Plainware, Redware, Three Circle Corrugated and R/W, Style I B/W
	Late Three Circle	900-1000	NW Mogollon and Mimbres regions	Rectangular and square pit structures	Addition of Style II B/W
	Classic	1000– 1130/1150	Entire Mimbres region	Masonry surface structures	Plainware, Redware, Corrugated, Style III B/W
Classic	Terminal Classic	1130– 1180	Lower Mimbres Valley	Masonry surface structures	Addition of El Paso Poly,
	Mimbres Reorganization	1150– early 1200s	E. Mimbres/Rio Grande Valley	Masonry surface structures	Chupadero B/W, Tularosa, Playas Red and other Chihuahuan
Postclassic	Black Mountain	1180– 1300	S. Mimbres region and south	Adobe surface structures	El Paso Poly, Chupadero B/W, Playas Red and other Chihuahuan
Po	Cliff	1300– 1450	W. Mimbres and S. Arizona	Adobe surface structures	Gila Poly, Chupadero B/W, Chihuahuan

Abbreviations: B/W: Black-on-white; R/W: Red-on-white, R/B: Red-on-brown, Poly: Polychrome

Research Background

Since publication of Gilman et al.'s (1994) seminal study using instrumental neutron activation analysis (INAA) of Mimbres pottery from the American Southwest, dozens of research projects involving the analyses of Mimbres-Mogollon and Jornada-Mogollon pottery have been conducted at Texas A&M and the University of Missouri Research Reactor Center (MURR). Projects have ranged in scale from small CRM (cultural resource management) projects involving the analyses of relatively few samples to larger more complex research projects initiated by Mimbres scholars. These efforts have resulted to date in the analyses of more than 3000 Mimbres-Mogollon ceramics and clays and more than 1000 Jornada-Mogollon ceramics and clays. Very little of this research has been published, and until now there has been no comprehensive analysis and interpretation that includes most extant data (a review of earlier INAA studies is provided in Chapter 2).

Early investigations of Mimbres pottery using petrographic methods (Rugge 1976) provided some tentative information regarding the exchange of Mimbres ceramics. Rugge's initial work with Mimbres painted and corrugated pottery (Rugge 1976) identified two types of temper used to produce Mimbres pottery. He determined that temper for painted wares was derived exclusively from volcanic rocks and that corrugated pottery either contained volcanic rock or plutonic rock (e.g., granite) tempers. Based on his knowledge of the Mimbres Valley, Rugge proposed that the geologic source for the granitic tempers was in the Cooks range in the southeastern part of the Mimbres Valley. Furthermore, given the morphology of the granitic temper, Rugge argued that the material was being procured directly from the source, rather than secondary alluvial deposits.

By 1988, Rugge had been involved in several additional petrographic projects involving Mimbres pottery (e.g., Rugge 1985a, 1985b, 1988). Rugge's data suggested extensive interregional exchange of Mimbres ceramics and that pottery production exclusive to the Mimbres Valley could be ruled out. Although the petrographic conclusions were not clear-cut in the sense that specific Mimbres pottery production locales could confidently be identified, Rugge's work was significant in that he was the first to recognize on the basis of mineralogical diversity of Mimbres-series pottery, that this pottery was widely produced, not only in the Mimbres Valley, but also the Rio Grande Valley and perhaps the Jornada-Mogollon region.

The early petrographic work served as a catalyst for developing ideas related to Mimbres pottery production and exchange. However, because Mimbres B/W (Black-on-white) pottery tends to be tempered with broadly similar sedimentary, igneous, or alluvial materials, archaeologists had not been able to effectively use petrographic approaches to confidently identify pottery production locales (Gilman et al. 1994:698) and by extension develop and rigorously test models of interaction and exchange. The occurrence of Mimbres pottery over a large geographic area (from the Guadalupe Mountains in southeast New Mexico, across west Texas, west to the Hohokam heartland in central Arizona, and south into Chihuahua), was perceived by many archaeologists to result from pottery produced in the Mimbres Valley being moved via "down-the-line" trade or centralized redistribution mechanisms (e.g., Robinson 1980; see also discussions in Gilman et al. 1994; Rugge 1988). Not satisfied with the scale at which pottery production and distribution could be examined using petrographic

approaches, archaeologists, Pat Gilman (Oklahoma University) and Harry Shafer (Texas A&M University) and their students began to employ INAA as a means to address this complicated topic (see Chapter 2).

Although there was a general interest in identifying pottery production locales to examine trade, there also was an interest in studying the naturalistic images found on Mimbres B/W pottery. In the late 1970s, Catherine LeBlanc (see Minnis 1985) examined the distribution of design motifs on Mimbres pottery and found that certain styles, such as bowls containing bighorn sheep motifs clustered at Swarts Ruin and that the horny toad motif seemed to predominate at the Baca site. Furthermore, LeBlanc found, that when these designs were examined across all sites in her study, design and distance (from the presumed point of origin) were inversely correlated thereby suggesting that pots with specific design elements were moving through an organized exchange network. However, design similarities on pots do not necessarily indicate a common point of origin—this idea requires additional data, such as petrography, INAA, or other analytical approach to substantiate. Ultimately such a database did not exist at the time of LeBlanc's work and these ideas have largely remained untested. Vallie Sue Powell-Marti (Powell 2000, Powell-Marti and James 2006) further examined this issue using a combined NAA and iconographic approach to develop ideas regarding preferred exchange directions/partners and the transmission of iconographically-borne social ideology. Ultimately, however, there are issues with Powell-Marti's interpretation of the NAA group structure which calls into question conclusions regarding trade networks (see Chapter 2).

The iconographic designs on Mimbres pottery have been further examined by Stephen LeBlanc who has proposed the possibility of identifying the work of individual potters via examination of design motifs and who also has argued that there were few potters at any time in any given village (LeBlanc 2004, 2006, 2010). In other words, production of painted pottery was specialized and therefore had higher prestige/value because these pots were produced by a limited number of specialists at any given time. This idea is contrast to Shafer (2003) who has proposed that most/all Mimbres women produced pottery. LeBlanc correctly acknowledges there are certain independent of lines of evidence that could be used to support the idea of pottery specialization. Foremost is the notion that if pottery production is specialized, bowls made by the same artist should originate from the same source (LeBlanc 2006:143)—that is they should have similar geochemical fingerprints. In contrast to LeBlanc, if pottery with specific iconographic design motifs are not limited to a few chemical groups, but instead appear to have been made in many locations, then we can hypothesize that the widespread distribution of specific motifs can be explained, in part, as participation in a common ideology or transmission of shared information across the Mimbres region.

Overall, the studies mentioned above, those discussed in Chapter 2, and data presented herein can be used to examine numerous topics related to Mimbres social organization and pottery production at various levels ranging from broad-scale change and distribution to finer intra-and inter-site levels. First and foremost, however, it is critical that one have more than a casual understanding of where pots are being produced and where these pots are ultimately being moved. INAA provides the level of resolution necessary to conduct such research, but the studies

conducted to date represent mere fragments of a much larger puzzle. With the benefit of a large dataset that includes most extant data, we begin to see a more complex view of Mimbres pottery production and social interaction and can now see that pottery production appears to have changed through time in terms of who produced it and where, and that as pottery production changed, so too did social interaction networks.

Overview of the Ceramic Sample

As indicated above, this study includes INAA data for more than 2,900 Mimbres-Mogollon and related ceramics and about 160 clays. The sample originates from 165 sites in New Mexico, Texas, Arizona, and northern Mexico. Figure 1.3 shows the locations of the 165 sites; Figure 1.4 is an enlarged view of the previous figure showing the names and locations of sites in southwest New Mexico and the El Paso, Texas area.

Although the Mimbres-Mogollon dataset is substantial, the sample is inherently biased. This is due in part to the varied nature of the research questions being addressed by previous researchers.

Consequently, many important Mimbres sites (and geographic areas) are not represented at all and many sites are underrepresented. Additionally, later period ceramics, such as Mimbres B/W Style III dominate the dataset, whereas earlier pottery such as San Francisco Red, Alma (all types), and Three Circle (all types) are considerably underrepresented (Figure 1.5). When one examines the numbers of samples per site as a histogram (Figure 1.6), it is evident that the sample is negatively skewed, that is to say that most sites have only had a few samples analyzed by INAA. There are 15 sites that can be considered to be well represented in

that they have more than 60 analyzed samples—admittedly an argument could be made that in some cases 20 samples is sufficient.

Approximately 650 samples originate from "whole" vessels. This includes about 200 samples from the Swarts site (SWR prefixes) and about 450 specimens from multiple Mimbres Valley sites (MVP prefixes). There are a few mostly intact or whole vessels scattered throughout the dataset, but by and large most of the INAA sample originates from small sherds of pottery—sometimes with limited contextual information beyond the site name which further hinders interpretation of the data. The importance of the "whole" vessel samples is that most contain painted design elements that when combined with the NAA data should provide information regarding the origin and distribution of some decorated pottery particularly with respect to design variation and patterning at both the site and regional levels. This specific avenue of research is well beyond the scope of this project, but the research implications are considerable.




Figure 1.3. Map of southern Arizona, southern New Mexico, and northern Mexico showing the locations of sites with Mimbres-Mogollon pottery included in this study. Black dots represent sites with fewer than 20 analyzed samples, blue dots denote sites with 20–40 analyzed samples and green dots indicate sites with more than 40 analyzed samples. Sites containing only Jornada Brownwares are not depicted in this map (but all sites in the El Paso area that have Mimbres pottery also have substantial quantities of Jornada pottery).




Figure 1.4. Map of southwest New Mexico showing the locations of sites with Mimbres-Mogollon pottery included in this study. Black dots represent sites with fewer than 20 analyzed samples, blue dots denote sites with 20–40 analyzed samples and green dots indicate sites with more than 40 analyzed samples. Sites containing only Jornada Brownwares are not depicted in this map (but all sites in the El Paso area that have Mimbres pottery also have substantial quantities of Jornada pottery).




Figure 1.5. Bar chart showing numbers of analyzed samples by ceramic type/category (ca. 3600 analyses).




Figure 1.6. Histogram showing the frequency of sites relative to the numbers of analyzed Mimbres-Mogollon pottery. Sites containing only Jornada Brownwares are not included in this summary.

Summary

In order to discuss anthropological issues that are guided by insights from ceramic compositional data, one must first have a firm understanding of the inherent structure of the compositional data—only then is it possible to move from chemical groups to anthropological interpretation. If the true structure of the dataset is masked (by use of inappropriate statistics and/or by failing to take into account extant data), then the resulting anthropological interpretations will be limited and/or inherently flawed. I argue that, in the case of Mimbres pottery, these issues have resulted in biased, incomplete, inaccurate, and/or erroneous interpretations of Mimbres pottery production and distribution, as well as other aspects of Mimbres social dynamics. Most researchers fail to realize that interpretation of Mimbres compositional data has been less than optimal, and unfortunately continue to cite these studies as if they are infallible.

My dissertation research differs from Gilman et al. (1994) and subsequent studies in that it is a synthesis that includes most extant data, and it provides the most accurate interpretations of Mimbres pottery production and distribution to date. I stress that my classification of this large and complex dataset is not perfect, but I contend that my study is the most accurate reflection of reality. Gilman et al.'s study was excellent given the limitations of a small sample, and it remains today a seminal/historical reference because they demonstrated the viability of INAA for identifying non-Mimbres valley pottery production. However my dissertation research indicates a substantially different scenario than previous studies given that I have identified ca. 35 Mimbres series chemical groups (and another 10-15 Jornada groups). Unlike many of the earlier studies (see Chapter 2), I do not force the

creation (or separation) of groups using less than optimal statistical approaches (see Chapters 2 and 3). Knowledge of a more precise group structure will allow archaeologists to reconstruct Mimbres pottery production and its distribution across the landscape. Ultimately, this research will form the basis for addressing numerous anthropological questions, such as social organization and interaction, gender, ideology, and provide insights into daily life.

Chapter 2

Previous NAA Research in the Mimbres & Jornada Regions

Overview of Previous NAA Research

Most early NAA work involving Mimbres pottery was conducted at Texas A&M in the early-to-mid 1990s by nuclear chemist Dennis James in collaboration with archaeologist Harry Shafer and students Robbie Brewington, Holly Meier, and Eleanor Dahlin. Under this program, more than 1100 Mimbres, Jornada, and related pottery and clays were analyzed. By the early-2000s, the Texas A&M Mimbres NAA project had run its course. Although several papers describing various aspects of the data were published, a full reporting of all of the data never occurred. Results for various aspects of the Texas A&M research have been summarized in James et al. (1995), Shafer (2003), and Dahlin (2003; Dahlin et al. 2007). A 1995 report at the Ninth Jornada/Mogollon Conference (Brewington et al. 1997) and subsequent 1996 Society for American Archaeology meeting presentation by Brewington et al. (1996) provided a glimpse of some of the Texas A&M results (Brewington et al. 1996) and an overview of the progress to date for their substantive effort (Brewington et al. 1997). Despite the magnitude of the Texas A&M program, it appears that researchers did not build upon earlier phases of the research. For example groups and data that formed the basis for James et al. (1995) do not appear to have been used in subsequent research reported in Brewington et al. (1996, 1997), Brewington and Shafer (1999), Dahlin (2003), Shafer (2001, 2003), or by University of Oklahoma graduate student Valli Powell-Marti (Powell 2000; Powell-Marti and James 2006). Instead each project began anew with group

formation and identification processes. With the exception of Dahlin (Dahlin 2003; Dahlin et al. 2007), who included some NAA data for samples analyzed for Brewington and Meier, extant data do not appear to have been included routinely in interpretations of new NAA results.

In the mid-1990's, archaeologist Myles Miller initiated an NAA research project complementary to that of the Texas A&M program. In 1995, Miller began submitting samples to MURR as the start of a long-term program of study of Mimbres and Jornada pottery, primarily from the El Paso area, that continues today (Miller et al. 1997; 2005; 2007). Most of this research has been, and continues to be, in support of contract archaeology projects on Fort Bliss located north of El Paso. Miller's efforts to date have resulted in the analysis of more than 500 ceramics and clays.

At about the same time that Miller began to analyze Mimbres and Jornada pottery samples from the Jornada region, archaeologist Darrell Creel (University of Texas—Austin), who had been collaborating on various aspects of the Texas A&M NAA research, initiated a separate project at MURR that focused initially on Post Classic period (e.g., Black Mountain phase) pottery from the Mimbres region (Creel et al. 2002). This program, rapidly expanded in early-to-mid 2000's to include the analyses of Mimbres pottery from all time periods, as well as ceramic imports from adjacent areas including the Jornada, Chihuahua, and the Chupadero areas. To date Creel and colleagues (Chris Turnbow, Nancy Kenmotsu, Steven LeBlanc, and others) have analyzed more than 1500 ceramics by NAA at MURR (e.g., Figure 2.1).




Figure 2.1. Example of Mimbres B/W bowl decorated with an anthropomorphic design. Photo courtesy of the Smithsonian Institution's National Museum of Natural History.

Catalog number A326294.

Over the past eight years, Pat Gilman and students at Oklahoma University, have submitted Mimbres pottery samples to MURR for analysis. Many of the ceramics have originated from sites in eastern Arizona and sites south of the Mimbres Valley (Cedar Mountains and Cooke Range). The analyses of ceramics from these peripheral areas have proven important for understanding Mimbres pottery production and circulation outside of the Mimbres Valley. In addition, one of Gilman's recent students, Bernard Schriever (2008), initiated a large-scale study of pottery and clays from the sites of Wind Mountain, Galaz, and Old Town.

Of particular interest is that Schriever selected samples that spanned earlier time periods which significantly increased the NAA sample for earlier ceramics types (Three Circle Red-on-white, Mimbres B/W Style I, Mimbres B/W Style II, and Mogollon Red-on-brown). More importantly though, Schriever included in his analysis more than 50 clays and also conducted microprobe analyses on a sample of the ceramics to characterize the mineral constituents. In total, recent NAA research by the University of Oklahoma group has resulted in the analysis of about 400 pottery and clay samples.

In addition to samples analyzed at MURR for Creel and Miller, dozens of contract archaeology projects (CRM) have occurred in which Mimbres, Jornada, and other related pottery have been analyzed at MURR. The majority of these projects have been relatively small in scale, ranging from 10-20 samples. One exception, however, was a large project initiated by Lori Reed (Animas Ceramic Consulting) and Western Cultural Resource Management for the AT&T Nexgen/Core Fiber Optic project. The analyses included approximately 500 Mimbres and Jornada ceramics and a handful of Chupadero and other miscellaneous types. This research was unique in that the Mimbres-series ceramics were primarily from earlier time periods (Alma), and most of the sample originated from smaller sites in west Texas and southwestern New Mexico that previously had not been studied by NAA. The analyses of the Alma and Jornada pottery resulted in the identification of several new compositional groups. In total about 800 contract archaeology related Mimbres and Jornada pottery samples have been analyzed by NAA at MURR. Few, if any, of these projects have been formally published.

Gilman et al. 1994

Gilman et al. (1994) published the first NAA-based study of Mimbres pottery. Their sample included 117 sherds from six sites: Powers Ranch (n = 14), Cameron Creek (n = 25), Mattocks (n = 26), Galaz (n = 9), NAN (n = 20), and Old Town (n = 23). The primary objective of this pilot study was to assess the compositional variability of Mimbres Style III B/W pottery with the idea that the number of chemical groups identified by NAA would serve as an indicator of the potential number of sources and/or production locales for Mimbres pottery.

Petrographic observations of Classic period and earlier Mimbres pottery has suggested that some Mimbres pottery possibly was produced in the Rio Grande Valley and Hueco Bolson areas which are east of the Mimbres Valley (Miller 1990; Rugge 1985a, 1985b, 1986, 1988; Stoltman 1996). Based on these limited studies, Rugge (1986) suggested that as many as 6 production locales were represented in his sample of 9 sherds from the Hueco Bolson. Likewise, similar studies of Mimbres pottery by Hill (1991) in the San Andres Mountains (White Sands Missile Range) and Stoltman (1996) at the Wind Mountain site located west of the Mimbres Valley indicated that multiple production locales existed. However, because Mimbres B/W pottery tends to be tempered with broadly similar sedimentary, igneous, or alluvial materials, archaeologists had not been able to use petrographic approaches to identify specific pottery production locales (Gilman et al. 1994:698)¹. In principal, given the wide diversity in tempers used to manufacture Mimbres pottery, petrography should be highly useful in forming compositional groups, evaluating existing groups, and identifying pottery productions areas. However,

1

¹ Although technically true, petrographic studies to date have focused on relatively small sample sizes. A large-scale study that combines petrography of Mimbres pottery with regional raw material surveys and which includes samples analyzed by INAA would help address many lingering questions.

small sample sizes in these petrographic studies have hampered such efforts. On the bases of the extant petrographic studies, Gilman et al. decided to employ NAA, primarily because of the ease with which large numbers of samples could be processed, but also because the NAA data, once generated, could easily serve as the basis for subsequent intra- and inter- regional studies of Mimbres pottery production.

The results of Gilman et al.'s study were significant on several fronts. First and foremost the NAA data conclusively refuted the idea that Mimbres pottery production and distribution was controlled only by people living in the Mimbres Valley—also referred to as the heartland model. Secondly, Gilman et al. proposed (based on the available NAA data) that the distribution of pottery suggested a model in which pottery was produced locally at Mimbres sites throughout the region and that little exchange of pottery occurred. With the benefit of several thousands of additional analyses we now know that this is not the case—Mimbres pottery was widely produced and exchanged (see Chapters 4 and 5).

Given that a full table of group assignments and sample identification numbers were never published, and because the chemical groups defined by Gilman and colleagues are depicted in discriminant space, it is not possible to reconstruct their groups. However, it appears that pottery assigned to the Powers Ranch group (Figure 2.2) is more or less comparable to the Mimbres-05A group identified in the current study. This group appears to reflect pottery production along or near the Gila River, probably between Safford, Arizona and Cliff, New Mexico. Mimbres-05A is clearly different from other Gila River groups (e.g., Mimbres-03, 05B, 21, 22). However, given what we know about the

challenges of identifying pottery production in large drainage systems (e.g., Cogswell 1998), it is quite possible that Mimbres-05A could represent a chemical signature for Gila River clays across very large geographic area that extends 100's of kilometers along the Gila River from the West Fork area into Eastern Arizona.




Figure 2.2. Plot of canonical (discriminant) 1 versus canonical (discriminant) 2 for the 117-specimen Mimbres NAA study conducted by Gilman et al. (1994) showing the 5 compositional groups identified.

Reproduced from Gilman et al. (1994:702; Figure 4).

James et al. 1995

James et al. (1995) published results for more than 200 Mimbres and Jornada ceramics. Data for this study were generated at the Texas A&M reactor and it appears that this is the only Mimbres pottery study to originate from the Texas A&M laboratory that examined (and published) their data using more traditional pattern recognition techniques, such as principal component analysis. The authors identified 6 compositional groups designated Group 1–6 (Figure 2.3) which are discussed below.

Group 1 was described as a chemically distinct group of 21 ceramics comprised of undifferentiated Cibola whitewares and Mimbres B/W pottery from the West Fork site located along the Gila River, just north of the Mimbres Valley. Specimens assigned to this group form the basis for the Mimbres-03 group in the present study.

Group 2 comprised a diverse set of 28 Mimbres B/W pottery, corrugated jars, and smudged bowls from West Fork (n = 15), NAN (n = 9), Old Town (n = 1), Treasure Hill (n = 2), and sites in the El Paso area (n = 1). Based on the numbers of samples from West Fork, James et al. argued that this group originated along the Upper Gila despite its apparent ceramic diversity. In the present study samples in this group have been reassigned to multiple compositional groups.

Group 3 included the majority of the Mimbres polychrome pottery from the NAN and Old Town sites, one sherd from West Fork, and 12 sherds recovered from sites in the El Paso area. In total 54 samples were assigned to this group. Based on the predominance of pottery from Old Town and NAN that were assigned to this group, the authors proposed a

Mimbres Valley origin. In the present study samples in this group have been reassigned to multiple compositional groups.




Figure 2.3. Plot of Principal Component 1 versus Principal Component 2 for the 200+ specimen Mimbres NAA study conducted by James et al. (1995) showing the 6 compositional groups identified. Figure reproduced from James et al. (1995:114; Figure 1).

Group 4 was a chemically distinct group of 7 Mimbres B/W sherds from Old Town (n = 4) and sites in the El Paso area (n = 3). Given that Mimbres pottery production was (and is) not generally expected to have been produced in the Jornada region, the authors proposed a Mimbres Valley origin for this group. Specimens assigned to this group form the

basis for the Mimbres-01 group in the present study—a group believed to represent pottery production east of the Mimbres Valley in the Rio Grande Valley—not the Mimbres Valley.

All pottery assigned to Group 5 was comprised of El Paso and Jornada *style* ceramics (e.g., El Paso Polychrome, Jornada bichrome, and El Paso brownwares). Pottery assigned to this group forms the basis for the El Paso Core group in the current study which is believed to represent pottery production in the El Paso, Texas/Hueco Bolson area (e.g., the Jornada Region).

Group 6 comprised the remaining West Fork site smudged and corrugated samples (n = 18) that were not assigned to Group 2 and a single Mimbres polychrome sherd recovered from NAN. As with Group 2, pottery assigned to this group was believed to represent pottery production in Upper Gila area. In the present study, however, Group 6 pottery corresponds to the Mimbres-05B group—but, the single Mimbres polychrome sample from NAN is now assigned to Mimbres Group 11.

Brewington et al. 1996

Brewington et al. (1996) conducted an NAA study on Mimbres B/W Style III ceramics and clay samples from 18 sites including: NAN Ruin, NAN-6, NAN-15, Agape Acres, Old Town, Treasure Hill, Cameron Creek, M&M Brown #1, Rock House, Saige-McFarland, Shelley/Woodrow, West Fork, and Red Rock #2. Additional samples were obtained from sites in the Jornada region (Gobernadora and Ojasen) and several sites in the San Simon Valley in eastern Arizona. In total their sample included 230

Mimbres B/W Style III sherds, 25 Mimbres Polychrome samples, 33 whitewares, and 35 clays.

Interpretation of their NAA data was as follows. Principal components analysis was initially conducted on the 323-specimen dataset. Scores derived from the first 6 principal components were then used as input data for a hierarchical cluster analysis algorithm. Groups identified via the cluster analysis were subsequently refined using discriminant analysis. In total, Brewington et al. identified 11 chemical groups, two of which they argued were directly sourced using the clay samples. Twenty samples were not assigned to any of the groups.

Given that the NAA data and corresponding group assignments were never published, it is not possible to reconstruct the original compositional groups that Brewington et al. identified. Certainly there do appear to be some valid groups identified in this study. For example, the most chemically distinct group identified was the West Fork white wares group Figure 2.4). This group contained 23 samples of which 87% originated from West Fork ruin. This group clearly corresponds with James et al.'s (1995) Group 6 pottery which also is equivalent to Mimbres Group 3 in the current study.




Figure 2.4. Discriminant Analysis plot showing groups defined by Brewington et al. (1996). From Brewington et al. 1996; Figure 2.

Brewington and Shafer 1999

As a follow up on their earlier NAA research (e.g., Brewington et al. 1996), Brewington and Shafer (1999) analyzed an additional 209 pottery and clay samples from 14 sites in the Mimbres Valley, Upper Gila River, and Jornada regions. Sample types included El Paso Brownwares, Mimbres B/W, Mimbres Polychrome, Mimbres Corrugated, and Gila Whitewares. A primary objective of this study was to ascertain whether Mimbres B/W pottery was produced in the Jornada region.

Statistical manipulation and interpretation of compositional groups was identical to those reported in the earlier study (Brewington et al. 1996). In brief, scores derived from the first 6 principal components were used as input data for a hierarchical cluster analysis routine. Groups identified via the cluster analysis were subsequently refined using discriminant analysis. In total, Brewington and Shafer identified 6 groups—one upper Gila group, four Mimbres Valley groups, and one group comprised entirely of El Paso Brownware pottery (Figure 2.5). All Mimbres pottery obtained from sites in the Jornada were assigned to Mimbres Valley groups. Nine samples were not assigned.

The authors used their NAA results to refute Carmichael's (1986) and Rugge's (1988) conclusions (based on petrographic observations) that some Mimbres B/W pottery found in the Jornada area either originated in the Rio Grande Valley or was produced in the Jornada area and argued for support of LeBlanc and Whalen's (1980) hypothesis that Mimbres B/W pottery was traded into the Jornada from the Mimbres core area (e.g., Mimbres Valley). As is shown later in this dissertation (see Chapters 4 and 5), Mimbres B/W pottery found in Jornada sites originates from numerous production locales within the Mimbres Valley and

adjacent areas, including the Rio Grande Valley. Additionally, there is some tantalizing support for limited Mimbres B/W pottery production in the Jornada region. Consequently, it is possible that Carmichael (1986) and Rugge (1998) were partly correct—at least some of the Mimbres B/W pottery from sites in the Jornada did originate in the Rio Grande Valley. Likewise, LeBlanc and Whalen's hypothesis of a Mimbres Valley origin(s) for Mimbres B/W pottery found in the Jornada is partly correct, but not entirely.

Canonical Discriminant Functions




Figure 2.5. Discriminant Analysis plot showing groups defined by Brewington and Shafer (1999). From Brewington and Shafer (1999:194; Figure 90).

Shafer 2001; James 2001

As part of the Loop 375 road construction project in El Paso, Texas (Dering et al. 2001), a sample of 157 sherds were analyzed by NAA by Harry Shafer and Dennis James. The sample was comprised of 141 El Paso Brownware ceramics, two Playas Red, 10 intrusive ceramics (8 Gila Polychrome and two unknown), and four undifferentiated (i.e., unknown typology) sherds. In addition, the study included five sherds from David Hill's earlier petrographic study of Loop 375 pottery (Hill 1988, 1993) and 18 sherds from Robinson's (2001) petrographic study.

Statistical manipulation and interpretation of compositional groups was identical to those reported in earlier studies (e.g., Brewington et al. 1996). In brief, initial groups were defined using a hierarchical cluster algorithm, then subjected to principal components analysis, and subsequently refined using discriminant analysis. In total, five groups were identified—Groups 1, 2, and 5 comprised all of the assigned Jornada Brownwares (Figures 2.6–2.7). Group 3 comprised the intrusive pottery samples, probably from New Mexico. Group 4 contained four analyses of three samples of Chihuahuan pottery. Six samples were not assigned.

The NAA results are interesting in that multiple Jornada compositional groups were identified and that the petrographic analyses support the NAA compositional groups. In this particular study, correspondence of groups with those identified in my current study of Mimbres and Jornada pottery is quite good (see discussion of Macro Group D): Group 1 corresponds to the El Paso Core group, Group 2 is equivalent to the El Paso Loop 375 group, and Group 5 is comparable to El Paso Group 2. One issue, however, is that two Playas Red samples were assigned to Group 1—these sherds do not have membership in this

group and instead belong to group known as Playas Red subgroup 2 (see Creel et al. 2002). Whether or not these samples represent pottery production in the Jornada region is up for debate, but Playas Red subgroup 2 and the El Paso Core group are chemically distinct from one another. A forthcoming dissertation by Matthew Taliaferro (UT-Austin, Taliaferro n.d.) will address Playas pottery production.




Figure 2.6. Principal component analysis plot showing groups reported in Shafer (2001). After Shafer (2001:349; Figure 8:10).




Figure 2.7. Discriminant Analysis plot showing groups reported in Shafer (2001). After Shafer (2001:350; Figure 8:12).

Powell 2000; Powell-Marti and James 2006

Powell-Marti (Powell 2000; Powell-Marti and James 2006) analyzed a sample of 152 Mimbres B/W sherds that formed the basis for her dissertation which focused on the identification of patterning in Mimbres pottery (chemical, decorative, and iconographic) as a means for understanding temporal changes in social group formation. The ultimate goal of this study was a reconstruction of Mimbres social organization. The underlying assumption of this research was that groups/alliances within Mimbres society would exhibit a greater degree of importation-exportation of vessels between or among group members than between or among other nonmember villages (Powell-Marti and James 2006). In

other words, groups/alliances among villages could be reconstructed via ceramic consumption and exchange patterns revealed by NAA.

Additionally, Powell-Marti hypothesized that membership in groups/alliances could be substantiated via ceramic iconographic similarities (Powell-Marti and James 2006).

Ceramics analyzed for Powell-Marti's study were obtained from the sites of Galaz, Old Town, NAN, Saige-McFarland, and Cameron Creek and were analyzed at Texas A&M. Powell-Marti's statistical evaluation of the NAA data consisted of the use of cluster analysis to produce a dendrogram based on a dissimilarity measure from which five groups were identified (Figure 2.8). Principal component analysis of logtransformed data was subsequently used to visualize the five groups. The hypothetical provenance of the groups was then determined via the criterion of abundance, i.e., the site with the highest percentage of sherds in a given group was assumed to be point of origin. The distribution of the groups was as follows: Group 1 (n = 60), Galaz; Group 2 (n = 22), Old Town; Group 3 (n = 13), NAN; Group 4 (n = 34), Saige-McFarland; Group 5 (n = 11), Cameron Creek. On the basis of these assignments Powell-Marti argued for specific patterns of importation/exportation of vessels across three time periods Early (ca. AD 970-1060), Middle (ca. AD 1060-1110), and Late (ca. AD 1110-1140).




Figure 2.8. Principal Component plot (PC1 versus PC2) showing groups defined by Powell (2000). Reproduced from Powell (2000:128; Figure 9).

Unfortunately the statistical manipulation of the data and subsequent group assignments were inappropriate for this dataset. Cluster analysis procedures are primarily exploratory techniques that perform variably depending on the elements included in the dataset and the scaling procedures, similarity measures, and clustering algorithm used (Neff 2002). The resulting solutions must always be examined using other ordination techniques (e.g., PCA, bivariate plots, discriminant analysis) and validated using a statistical procedure, such as Mahalanobis distance. As Neff (2002:28) points out "under no circumstances should the search for structure in a compositional dataset end with the application of some preferred cluster solution". It is obvious from inspection of Powell-Marti's PCA plot (Figure 2.8) that the defined groups lack any structure from which archaeologically meaningful interpretations can be derived. Consequently, hypotheses forwarded by

Powell-Marti (Powell 2000; Powell-Marti and James 2006) concerning the movement of pottery are likely invalid. Reexamination of the data generated for Powell-Marti's study indicates that the 152-sample dataset can be assigned to at least 17 discrete groups (note that some samples are unassigned and that a handful of samples are not included in the present study because it was not possible to link Powell-Marti's descriptive information with the NAA data). Powell-Marti's Group 5 is comparable to James et al.'s (1995) Group 4 and the current study's Mimbres Group 1, a group believed to represent pottery production east of the Mimbres Valley near the Rio Grande River—not Cameron Creek. Powell-Marti's Group 3 roughly corresponds to the current study's Mimbres Group 8 which is believed to represent pottery production, probably at the Mattocks site. Group 4 is somewhat similar to the current study's Mimbres Group 21 and is therefore in general agreement with a Saige-McFarland origin. It is not clear how Groups 1 and 2 relate to groups identified in the current study given that a final list of group assignments was not published in Powell-Marti's dissertation (Powell 2000) or subsequent publication (Powell-Marti 2006). It is important to underscore that although the data interpretation for this project appears to be inadequate by conventional standards, the actual NAA data are of the highest quality and comparable with other Mimbres-related data generated at the Texas A&M and MURR laboratories.

Chandler 2000

As the core of a M.A. Thesis, Shari Chandler (UT-Austin) analyzed 108 Three Circle Phase (and later) ceramics from the Old Town (Chandler 2000). The analyses were conducted at MURR and sample analyses and data interpretation followed standards MURR protocols (see Chapter 3). Pottery was assigned to 8 compositional groups by Neff. These groups were subsequently reevaluated by Myles Miller who reassigned the specimens to 16 groups. By 2000, Miller had amassed a fairly large dataset of Mimbres and Jornada pottery from which he had identified about 30 compositional groups. Miller's group reassignments highlighted an inherent flaw in the MURR-defined compositional groups—specifically with respect to the Main Playas Red group and Mimbres groups 4 and 5—an issue that is discussed in a section below. The bottom line here, is that Chandler's thesis, with the benefit of Miller's group assignments, as a whole, represents what is probably the most accurate assignment of Mimbres NAA data to date.

One of the more significant findings of this study was that more than 50% of the pottery analyzed appeared to have originated from sites outside of the Lower Mimbres Valley. This finding was contrary to many of the earlier NAA studies of Mimbres pottery which documented little movement of pottery. However, as Chandler correctly pointed out, the identification of discreet compositional groups does not necessarily mean that the ceramics have been sourced to a specific site(s) or regions, but only that groups have been identified. Recognizing the interpretative limitations of her dataset, Chandler called for increased sampling of clays and pottery from sites throughout the Mimbres area. More importantly she recognized that extant data from all of the NAA labs should be compiled and rigorously examined as this would provide the most

reliable approach for identifying ceramic provenance so that archaeologists could begin to expand theories of Mimbres social interaction (Chandler 2000:46).

Dahlin 2003

For her MA thesis (Dahlin 2003), Eleanor Dahlin examined a NAA dataset comprised of 278 Classic Period Mimbres pottery and clay samples obtained from sites in the Mimbres Valley (Elk Ridge, NAN Ranch Ruin, NAN-15, Pruitt Ranch, and NAN Ranch Windmill Draw), the Gila River Valley (Red Rock, Saige-McFarland, Shelley/ Woodrow, and West Fork), and the Rio Grande region (Ronnie Pueblo, Las Animas Village, Buckaroo), Cameron Creek (west of the Mimbres Valley), and two Avilas Canyon sites: LA 44997 and LA 450000. The dataset included 105 new analyses and a selection of 183 samples previously reported by James et al. (1995) and Brewington et al. (1996). All NAA analyses for this project were conducted at Texas A&M. Also included in this study were 5 Chupadero B/W and 5 Gila polychrome samples—presumably non-local imports—that were included to demonstrate that pottery of both types was not manufactured from clays used to produce Mimbres pottery. In total the sample consisted of 141 bowls, 118 jars, and 29 clay samples.

Dahlin's research was focused on four hypotheses: (1) bowls moved throughout the Mimbres system more often than jars; (2) vessel movement among sites within a given region exceeded vessel movement between regions; (3) Mimbres people produced pottery at the village level in all regions; and, (4) elites did not control ceramic vessel distribution (Dahlin 2003:58). Based on the interpretation of the NAA data, Dahlin concluded that sufficient evidence existed to support the

first three hypotheses. Based on the limited numbers of samples that she perceived to be imports to NAN Ranch, Dahlin found limited support for the fourth hypothesis.

Dahlin's method for assigning pottery to compositional groups varied significantly from the approaches used in the current study (and previous Texas A&M studies). In most studies, compositional groups are formed based on chemical similarities and dissimilarities; groups are then explored and validated using any number of approaches, such as bivariate projections of the data, principal components analysis, and Mahalanobis distance probabilities. In contrast to the norm, Dahlin constructed groups at the site and regional levels (Figures 2.9–2.10). Discriminant analysis in combination with *p* scores and Mahalanobis distance probabilities were then used to identify misclassified sherds and refine compositional groups. Misclassified samples were subsequently interpreted as imports from one of the other regions and/or sites included in the study.

Discriminant analysis is designed to calculate the best means of separating groups identified by the analyst (Neff 2002). When discriminant analysis is conducted on groups defined solely on the basis of archaeological context, as in the case of Dahlin, there is potential to subsume so much compositional variability that a broad range of the analyzed pottery will appear to qualify as Mimbres Valley, Gila River Valley, and/or Rio Grande region (or whatever sites are used as the basis for the construction of the groups). Certainly, archaeological context is a reasonable starting point for identifying source-related groups, but these are hypotheses that must be tested and should not be the end of the analysis (i.e., Neff et al. 2002) At one level, the classification of ceramics

into three regional groups may seem reasonable, if we assume that Mimbres pottery only was produced in three regions and if we assume that ceramics are chemically more similar within a given region than they are between regions. However, this is not the case—there are an unknown number of Mimbres-related ceramic compositional groups, many of which are produced outside of the regions identified by Dahlin. At present count there are more than 35 Mimbres and Jornada compositional groups and hundreds of unassigned samples that potentially represent dozens of other compositional groups/production locales. By constraining the analysis to three regions and/or a handful of sites, Dahlin effectively created groups that have limited interpretive value—as was the case with Powell-Marti (Powell 2000; Powell-Marti and James 2006). To illustrate this point, we can refer to the non-Mimbres pottery included in Dahlin's study. She states:

The Chupadero B/W and Gila Polychrome sherds from the NAN Ranch Windmill Draw site were classified into the Mimbres region at the regional level of analysis. It is probable that these pieces were manufactured from Mimbres region clays, but at which site remains unknown Dahlin (2003:79).

My reexamination of Dahlin's data clearly shows that the five Chupadero samples can be assigned to Chupadero ceramic compositional groups that are firmly tied to the Capitan Mountains located more than 100 miles northeast of the Mimbres Valley (see Clark 2006). The misclassification of the five Chupadero pottery samples clearly underscores some of the pitfalls associated with using discriminant analysis as the primary means to construct compositional groups.




Figure 2.9. Regional level discriminant analysis of samples included in Dahlin (2003). Reproduced from Dahlin 2003:64.




Figure 2.10. Site level discriminant analysis of samples included in Dahlin (2003). Reproduced from Dahlin 2003:69.

Dahlin et al. 2007

Dahlin's M.A. thesis ultimately was published in 2007 (Dahlin et al. 2007). In this paper, however, the data were reevaluated using the approach more commonly used by Texas A&M (e.g., Brewington et al. 1996). Statistical manipulation and interpretation of compositional groups the application of a hierarchical cluster analysis algorithm. Groups identified via the cluster analysis were subsequently refined using discriminant analysis. This approach resulted in the identification of 6 compositional groups (Figure 2.11).

Based on their reevaluation of NAA data, the authors concluded that distribution patterns revealed significant movement of vessels among the Mimbres, Gila and Rio Grande regions and that distribution patterns were somewhat similar from village to village, indicating little likelihood of a dominant trading partner or elite entity which controlled ceramic distribution (Dahlin et al. 2007:465). Ultimately, however, this study suffered the same problems that most of the other cluster analysis and discrimination-based interpretations—inherent variation was masked and too few compositional groups were identified.




Figure 2.11. Plot of discriminant analysis scores for pottery included in Dahlin et al. (2007). Reproduced from Dahlin et al. (2007:463).

MURR (Neff & Speakman)

From about 1988 until mid-2002, Hector Neff oversaw the reporting of NAA ceramic data from the Archaeometry Laboratory at MURR. During this time, Neff reported data for thousands of analyses of ceramics from the American Southwest, including numerous reports for Lori Reed, Darrell Creel, and other archaeologists working in the Mimbres and Jornada regions. One of the earliest Mimbres projects involving Neff

concerned the analysis and interpretation of data reported in Creel et al. (2002), a project that was concerned primarily with Black Mountain Phase ceramics from the Mimbres and Jornada regions. This early research led to the identification of what is referred to as the Main Playas Red group and two Playas Red subgroups (1 and 2). As originally defined the Main Playas Red group contained only pottery classified as Playas Red. However, as the ceramic database for Mimbres-series pottery increased, five additional Mimbres groups were defined (Groups 1-5) as well as the El Paso Core group, and a handful of smaller groups. At some point it was recognized that Groups 4 and 5, when combined, were equivalent to the Main Playas Red group. Consequently, when samples could not be assigned to either Mimbres-4 or Mimbres-5 (because of low Mahalanobis distance probabilities of membership in either group, or because of high probabilities in both groups), they were assigned to the Main Playas Red group. As membership in MPR increased, so did the compositional heterogeneity of this group (and Mimbres-5). But, given what we knew about Mimbres pottery production from the MURR-based NAA studies, this classification scheme seemed appropriate.

Following the departure of Hector Neff from MURR in 2002, I assumed responsibility for reporting the ceramic results from the various NAA projects undertaken at the Archaeometry Laboratory. I continued to use and refine groups identified by Neff. Problems with the Main Playas Red group became evident by 2004. In early 2003, William (Andy) Cloud submitted 34 ceramics and four clays from the Millington and Arroyo de la Presa sites located in Presidio County, Texas (several hundred miles south of El Paso, Texas). Pottery types submitted for analysis included El Paso Polychrome and Jornada Brownwares, a generic group referred to as undifferentiated Chihuahuan Brownwares, and several local wares, i.e.,

Capote, Chinati, Conchos. Most of the pottery fit into a local chronology that spanned approximately 500 years, including the La Junta phase (ca. 1200-1450 CE; El Paso Polychrome samples), the Concepcion phase (ca. 1500-1683 CE; Capote types and Chinati types) and the Conchos phase (ca. 1683-1760 CE; Conchos types).

Based on the NAA data generated for that project, Enrique Rodríguez-Alegría (a postdoctoral student) assigned the pottery to four compositional groups. As expected the El Paso Polychrome and Jornada Brownware pottery could be assigned to the El Paso core group. The four undifferentiated Chihuahuan Brownware samples formed a second group and four samples designated Capote-1 formed a third small group (see Rodríguez-Alegría et al. 2005). The fourth group of sherds contained 18 samples of Capote and Chinati pottery. Based on Mahalanobis distance probabilities, these samples were assigned to the Main Playas Red group and Mimbres-5. This was completely unexpected, but given the numbers and types of samples assigned to the main Playas Red group, it was not out of the realm of possibility—but it did raise questions about the interpretative value of the Main Playas Red group.

A major breakthrough regarding the Mimbres dataset occurred around 2004–2005. About that time, Darrell Creel, who had been leading an effort compile extant Mimbres-related NAA data provided all extant Texas A&M data to me. When the MURR and Texas A&M data were combined, it became inherently clear that the 4 or 5 Mimbres pottery group structure that we had routinely been reporting at MURR only told part of the story. Furthermore, examination of the larger dataset confirmed that the Main Playas Red group was not a valid analytical construct—at least for Mimbres pottery.

Since 2004, Darrell Creel and I have devoted significant effort to expanding the Mimbres NAA database. Creel has led this effort and has devoted significant time and resources in straightening out the database, obtaining new samples, and coordinating our efforts with other archaeologists. My role has been primarily in defining and refining groups within this large corpus of data. Specimens that were previously assigned to Mimbres-4 and Mimbres-5 have been reassigned in the current study to newly defined groups (Mimbres-08, 11, 4A, 4B, 4C, 5A, 5B, and all the groups designated with a 20 or 40 series prefix). This dissertation is the culmination of a decade of research with this dataset. In the following chapters I describe the laboratory analyses, approaches to compositional group identification, and the individual groups themselves.

Schriever (2008)

Before concluding this discussion of previous NAA work, there is one final dataset to discuss. In 2006, Beau Schriever submitted 225 pottery samples and 56 clays to MURR for NAA analysis. The sample was obtained from three sites: Galaz, Old Town, and Wind Mountain. Seventy-five sherds were analyzed from each site—15 Mogollon R/B, 15 Three Circle R/W, 15 Mimbres B/W Style I, 15 Mimbres B/W Style II, and 15 Mimbres B/W Style III. This project was significant on several fronts—it included samples from a large Mimbres site (Wind Mountain) that had not been sampled previously, it included many early ceramic types that were vastly underrepresented in the larger database, and Schriever included 56 clays in the analysis. In addition to the NAA data, Schriever also conducted petrographic analyses via electron microprobe on a

subset of the NAA sample and identified about 30 different petrographic groups. In this dissertation, I have referred heavily to Schriever's petrographic groups as there is a relatively high correspondence among his groups and the NAA groups I have defined. Unfortunately, the NAA groups defined for Schriever's dissertation were done without comparison to the larger extant dataset. Consequently, there is little agreement between the NAA groups reported in Schriever's dissertation and the groups discussed herein (Figures 2.12–2.13).




Figure 2.12. Plot of tantalum and chromium base-10 logged concentrations showing the separation of Ferguson's Groups 1 and 2 in Schriever's NAA dataset. From Ferguson and Glascock (2007, Figure 1).




Figure 2.13. Plot of chromium and cesium base-10 logged concentrations showing the separation of Ferguson's Groups 3–7 in Schriever's NAA dataset. "+" symbols represent unassigned specimens.

From Ferguson and Glascock (2007, Figure 2).

Chapter 3

Instrumental Neutron Activation Analysis (INAA) and Approaches to Interpreting Compositional Data

Overview of INAA

Instrumental Neutron Activation Analysis (INAA, NAA) is a sensitive analytical technique in which a sample is subjected to a neutron flux that results in the production of radioactive nuclides. As these radioactive nuclides decay, they emit gamma rays with characteristic energies for each nuclide (Figure 3.1). Comparison of the intensity of these gamma rays with those emitted by a standard permit a quantitative measure of the concentrations of the various nuclides. NAA has widely been applied to almost every conceivable field of scientific and/or technical interest. For many elements and applications, NAA offers sensitivities, in many cases, that are superior to those attainable by other methods, on the order of parts per billion or better.




Figure 3.1. Diagram illustrating the process of neutron capture by a target nucleus followed by the emission of gamma rays. Figure courtesy of M.D. Glascock.

Since the first applications of NAA to archaeological materials in the 1950's (e.g., Sayre and Dodson 1957), the advantages of this analytical technique over other chemical characterization techniques were quickly recognized by researchers. These include: (1) ease of sample and standard preparation; (2) determination of the concentrations of multiple elements in a bulk sample; (3) many elemental determinations with high analytical precision; and (4) good interlaboratory comparability. Prior to the development of NAA, most chemical studies of archaeological materials, particularly ceramics, centered around wet chemistry or emission spectrometry. NAA rapidly replaced these analytical techniques as the "true" bulk sample technique of choice, and in the ensuing decades NAA emerged as one of the most powerful and widely applied analytical techniques for chemical characterization and provenance-based research of ceramics, obsidian, chert, flint, basalt, glass, metals, and other archaeological and historical materials (Glascock et al. 2007).

INAA Sample Preparation at MURR

Most pottery samples were prepared for INAA using procedures standard at MURR¹. Fragments of about 1cm² were removed from each sample and abraded using a silicon carbide burr in order to remove glaze, slip, paint, and adhering soil, thereby reducing the risk of measuring contamination. The samples were washed in deionized water and allowed to dry in the laboratory. Once dry, the individual sherds were ground to

¹ The following descriptions of MURR pottery sample preparation procedures and statistical analyses of data is based on "boiler plate" text that was developed at MURR in the late 1980s and early 1990s by Hector Neff. It has been revised and expanded through the years by Neff, Michael Glascock, Speakman, and others and has been published in various forms in at least 100 theses, dissertations, and peer-reviewed publications.

powder in an agate mortar to homogenize the samples. Archival samples were retained from each sherd (when possible) for future research.

Given that much of the recent analytical effort by Creel and colleagues has focused on the analysis of intact (or mostly intact) museum specimens, the procedure described above was modified to minimize damage to the vessels—specifically for samples with SWR and MVP prefixes. For ceramic pots a silicon carbide abrader (i.e., a Dremel bit) or a tungsten carbide drill was used to remove the outer white-slipped surfaces on the bottoms of the vessels. The bit was then cleaned and used to abrade, onto laboratory weighing paper, approximately 300—500 mg of ceramic powder. The powdered material was then transferred to glass screw-cap vials and shipped to MURR for analysis.

Two analytical samples were prepared from each ceramic specimen. Portions of approximately 150 mg of powder were weighed into clean high-density polyethylene vials used for short irradiations at MURR. At the same time, 200 mg of each sample were weighed into clean high-purity quartz vials used for long irradiations. Individual sample weights were recorded to the nearest 0.01 mg using an analytical balance. Both vials were sealed prior to irradiation. Along with the unknown samples, Standards made from National Institute of Standards and Technology (NIST) certified standard reference materials of SRM-1633a or SRM-1633b (coal fly ash) and SRM-688 (basalt rock) were similarly prepared, as were quality control samples (e.g., standards treated as unknowns) of SRM-278 (obsidian rock) and Ohio Red Clay (a standard developed for in-house applications).




Figure 3.2. The University of Missouri Research Reactor. Photo R.J. Speakman

INAA Sample Preparation at Texas A&M

INAA sample preparation at Texas A&M is described in James et al. (2007). As a first step, the outer surfaces of the sherds are removed with a rotary tool using a silicon carbide bit followed by washing with deionized water, air drying, grinding in a diamonite mortar and pestle and finally oven drying. This procedure results in a fine powder of several hundred milligrams from which approximately 100 mg is weighed and

packaged into pre-cleaned polyethylene vials for irradiation. National Institute of Standards and Technology (NIST) standard reference material, coal fly ash (SRM 1633a) is used as a calibration standard and Ohio Red clay is analyzed for quality control. NIST SRM 688 basalt is sometimes used to aid with quality control and for standardization of calcium in the samples.

INAA Sample Preparation at the Smithsonian Institution

As described by Blackman and Bishop (2007), sample preparation of pottery for INAA at the Smithsonian Institution involves cleaning the area to be sampled with a tungsten carbide burring tool followed by drilling into the sherd with a tungsten carbide bit. The powder from the drilling is collected on weighing paper and stored in clean glass screw top vials. The weighing paper is used once and discarded and the burring tool and drill bit are cleaned with acetone or ethanol after each sample. All samples are dried at 110° C for 24 hours to remove adhered water and allowed to cool to ambient temperature and stored in a desiccator before weighing. Nominal 80 to 100 mg sub-samples are weighed into polyethylene 0.4 ml micro centrifuge tubes and sealed. NIST SRM 1633a and a check standard, typically Ohio Red clay are similarly prepared.

Irradiation and Gamma-Ray Spectroscopy at MURR

Neutron activation analysis of ceramics at MURR, which consists of two irradiations and a total of three gamma counts, constitutes a superset of the procedures used at most other NAA laboratories (Glascock 1992; Neff 1992, 2000). As discussed in detail by Glascock (1992), a short irradiation is carried out through the pneumatic tube irradiation system. Samples in the polyvials are sequentially irradiated,

two at a time, for five seconds at a neutron flux of 8 x 10^{13} cm $^{-2}$ s $^{-1}$. The 720-second count yields gamma spectra containing peaks for nine shortlived elements: aluminum (Al), barium (Ba), calcium (Ca), dysprosium (Dy), potassium (K), manganese (Mn), sodium (Na), titanium (Ti), and vanadium (V). The samples are encapsulated in quartz vials and are subjected to a 24-hour irradiation at a neutron flux of 5 x 10¹³ cm⁻² s⁻¹. This long irradiation is analogous to the single irradiation utilized at most other laboratories. After the long irradiation, samples decay for seven days, and then are counted for 1,800 seconds (the "middle count") on a high-resolution germanium detector coupled to an automatic sample changer. The middle count yields determinations of seven medium halflife elements, namely arsenic (As), lanthanum (La), lutetium (Lu), neodymium (Nd), samarium (Sm), uranium (U), and ytterbium (Yb). After an additional three- or four-week decay, a final count of 8,500 seconds is carried out on each sample. The latter measurement yields the following 17 long half-life elements: cerium (Ce), cobalt (Co), chromium (Cr), cesium (Cs), europium (Eu), iron (Fe), hafnium (Hf), nickel (Ni), rubidium (Rb), antimony (Sb), scandium (Sc), strontium (Sr), tantalum (Ta), terbium (Tb), thorium (Th), zinc (Zn), and zirconium (Zr). Refer to Table 3.1 for a list of radioactive isotopes and gamma-ray energies used in instrumental neutron activation analysis at MURR.

Element concentrations were determined using the standard-comparator method in which the elemental abundances of the unknown samples (i.e., the pottery and clays) were determined by ratioing the measured activities per unit weight of the unknown sample to those measured for a reference standard (SRM-1633a, SRM-278, SRM-688) with known concentrations. The element concentration data from the three measurements are tabulated in parts per million using the EXCEL

spreadsheet program. Descriptive data for the sample was appended to the concentration spreadsheet. Data also are archived in the MURR ceramic database.

Irradiation and Gamma-Ray Spectroscopy at Texas A&M

Details of irradiation and gamma-ray spectroscopy at Texas A&M are described in detail in James et al. (2007). In brief, samples and standards are subjected to two irradiations and three gamma counts. Short-lived elements of interest are determined via a 30-second irradiation followed by a 20-minute decay and a 500-second count. Elements determined in this count includes: Al, Ca, Dy, Mn, Ti, and V. A 14-hour irradiation in a reactor rotisserie position allows the measurement of isotopes with longer half-lives. Following irradiation and a decay of 1-week a 2000 second is performed to quantify As, K, La, Lu, Na, Sm, U and Yb. A 3-hour count is performed after 1-month to quantify Ba, Ce, Cs, Cr, Co, Eu, Hf, Fe, Nd, Ni, Rb, Sb, Sc, Sr, Ta, Tb, Th, Zn, and Zr. The nominal flux available for all these irradiations is 1 x 10¹³ n cm⁻² s⁻¹. Gamma spectroscopy instrumentation includes three high resolution (<1.8 keV FWHM at 1332 keV) high-purity germanium detectors interfaced via digital pulse processing either to a PC running Canberra Industries GeniePC software (for short counts) or to an alpha-based multichannel acquisition system also from Canberra which runs under an open-VMS operating system (for the longer counts). Refer to Table 3.1 for a list of radioactive isotopes and gamma-ray energies used in instrumental neutron activation analysis at Texas A&M.

Element concentrations are determined using the standardcomparator method in which the elemental abundances of the unknown samples (i.e., the pottery and clays) are determined by ratioing the measured activities per unit weight of the unknown sample to those measured for a reference standard (SRM-1633aSRM-688) with known concentrations.

Irradiation and Gamma-Ray Spectroscopy at the Smithsonian Institution

As detailed by Blackman and Bishop (2007) 18 unknown samples, 2 aliquots of the standard, NIST SRM 1633, and a check standard are pneumatically introduced into the Center for Neutron Research's 20 MW research reactor at the National Institute for Standards and Technology in Gaithersburg, Maryland. Samples are irradiated for 4 hours at a neutron flux of 7.7 x 10¹³ cm⁻² s⁻¹. Samples and standards are allowed to decay for six days and each is then counted for one hour and five minutes real time using hyper-pure Ge detectors and associated electronics. Following the first count, the samples decay for an additional three weeks before a second count of two hours and 10 minutes real time is made of each sample using a second sample changer and gamma detection system (Table 3.2).

Elements with half-lives of less than 12 hours are not routinely quantified due to physical considerations and the labor intensive nature of the analysis. Consequently, archived powders from the Gilman et al. (1994) project were reanalyzed at MURR for short-lived elements using procedures described above.

Table 3.1 Radioactive isotopes and gamma-ray energies used for INAA at the MURR and Texas A&M laboratories.

Element	Nuclide	Gamma Ray Energy (KeV)	Half Life	Count
Al	Al-28	1779	2.24 minutes	short
Ва	Ba-139	496	84.63 minutes	short
Ca	Ca-49	3084	8.72 minutes	short
Dy	Dy-165	95	2.33 hours	short
K	K -42	1525	12.40 hours	short
Mn	Mn-56	847	2.58 hours	short
Na	Na-24	1369	14.96 hours	short
Ti	Ti-51	320	5.76 minutes	short
V	V-52	1434	3.75 minutes	short
As	As-76	559	26.32 hours	mid
La	La- 140	1596	40.28 hours	mid
Lu	Lu- 177	208	6.74 days	mid
Nd	Nd-147	91	11.10 days	mid
Sm	Sm-153	103	46.80 hours	mid
U	Np-239	106	2.34 days	mid
Yb	Yb-175	396	4.21 days	mid
Ce	Ce-141	145	32.50 days	long
Со	Co-60	1333	5.27 years	long
Cr	Cr-51	320	27.7 days	long
Cs	Cs-134	796	2.06 years	long
Eu	Eu-152	1408	13.54 years	long
Fe	Fe-59	1099	44.50 days	long
Hf	Hf-181	482	42.40 days	long
Ni	Co-58	811	70.86 days	long
Rb	Rb-86	1077	18.66 days	long
Sb	Sb-124	1691	60.2 days	long
Sc	Sc-46	889	83.81 days	long
Sr	Sr-85	514	64.84 days	long
Та	Ta-182	1221	114.5 days	long
Tb	Tb-160	879	72.3 days	long
Th	Pa-233	312	27.0 days	long
Zn	Zn-65	1116	243.9 days	long
Zr	Zr-95	757	64.02 days	long

Table 3.2 Radioactive isotopes and gamma-ray energies used for INAA at the Smithsonian Institution (Modified from Blackman and Bishop 2007).

Element	Nuclide	Gamma Ray Energy (KeV)	Half Life	Count
As	As-76	559	26.32 hours	1
Ва	Ba-131	496	11.50 days	1
Ca	Ca-47	1297	4.53 days	1
K	K -42	1525	12.40 hours	1
La	La-140	1596	40.28 hours	1
Lu	Lu-177	208	6.74 days	1
Na	Na-24	1369	14.96 hours	1
Sb	Sb-122	564	2.72 days	1
Sm	Sm-153	103	46.80 hours	1
U	Np-239	106	2.34days	1
Yb	Yb-175	396	4.21days	1
Ce	Ce-141	145	32.50 days	2
Со	Co-60	1173 & 1333	5.27 years	2
Cr	Cr-51	320	27.69 days	2
Cs	Cs-134	796	2.06 years	2
Eu	Eu-152	1408	12.70 years	2
Fe	Fe-59	1099 & 1292	44.50 days	2
Hf	Hf-181	482	42.40 days	2
Nd	Nd-147	91	11.10 days	2
Rb	Rb-86	1077	18.66 days	2
Sc	Sc-46	889	83.82 days	2
Se	Se-75	265	119.78 days	2
Sr	Sr-85	514	64.86 days	2
Та	Ta-182	1221	115.10 days	2
Tb	Tb-160	879	72.10 days	2
Th	Pa-233	312	27.40 days	2
Zn	Zn-65	1115	243.80 days	2
Zr	Zr-95	757	64.02 days	2

Approaches to Interpreting Chemical Data

The analyses at MURR described above produced elemental concentration values for 32 or 33 elements in most of the analyzed samples. Data for Ni in most samples was below detection limits (as is the norm for most New World ceramic analyses) and was removed from consideration during the statistical analysis. In addition, several elements, although measured by NAA, are measured with high analytical error. With small datasets, this error does not generally present a problem. However, with large datasets, especially datasets generated at multiple laboratories, this error can mask compositional groups and adversely affect the statistical evaluation of the data. Consequently, the element Tb was removed from consideration in this study. The element Co has been identified as contaminant in other studies of Mimbres pottery and was removed from consideration in the evaluation of data generated for this study. Finally, because the Texas A&M facility does not consistently measure and/or report numbers for Sr, Ca, and K these elements also were not considered in the current study. Statistical analysis was subsequently carried out on base-10 logarithms of concentrations on the remaining 27 elements. Use of log concentrations rather than raw data compensates for differences in magnitude between the major elements, such as calcium, on one hand and trace elements, such as the rare earth or lanthanide elements (REEs). Transformation to base-10 logarithms also yields a more normal distribution for many trace elements.

The interpretation of compositional data obtained from the analysis of archaeological materials is discussed in detail in numerous publications (e.g., Baxter and Buck 2000; Bieber et al. 1975; Bishop and Neff 1989; Buxeda i Garrigós and Kilikoglou 2003; Glascock 1992;

Harbottle 1976; Neff 2000) and will only be summarized here. The main goal of data analysis is to identify distinct chemically homogeneous groups within the analytical sample. Based on the provenance postulate of Weigand et al. (1977), different chemical groups may be assumed to represent geographically restricted sources. For lithic materials such as obsidian, basalt, and cryptocrystalline silicates (e.g., chert, flint, or jasper), raw material samples are frequently collected from known outcrops or secondary deposits and the compositional data obtained on the samples is used to define the source localities or boundaries. The locations of sources also can be inferred by comparing unknown specimens (e.g., ceramic artifacts) to knowns (i.e., clay samples) (e.g., Neff 2000) or by indirect methods such as the "criterion of abundance" (Bishop et al. 1992) or by arguments based on geological and sedimentological characteristics (e.g., Steponaitis et al. 1996). The ubiquity of ceramic raw materials usually makes it impossible to sample all potential "sources" intensively enough to create groups of knowns to which unknowns can be compared. Lithic sources tend to be more localized and compositionally homogeneous in the case of obsidian or compositionally heterogeneous as is the case for most cryptocrystalline silicates (cherts, flints, and jaspers).

Compositional groups can be viewed as "centers of mass" in the compositional hyperspace described by the measured elemental data. Groups are characterized by the locations of their centroids and the unique relationships (i.e., correlations) between the elements. Decisions about whether to assign a specimen to a particular compositional group are based on the overall probability that the measured concentrations for the specimen could have been obtained from that group.

Initial hypotheses about source-related subgroups in the compositional data can be derived from non-compositional information (e.g., archaeological context, decorative attributes, etc.) or from application of various pattern-recognition techniques to the multivariate chemical data. Some of the pattern recognition techniques that have been used to investigate archaeological data sets are cluster analysis (CA), principal components analysis (PCA), and discriminant analysis (DA). Each of the techniques has advantages and disadvantages which may depend upon the types and quantity of data available for interpretation.

The variables (measured elements) in archaeological and geological data sets are often correlated and frequently large in number. This makes handling and interpreting patterns within the data difficult.

Therefore, it is often useful to transform the original variables into a smaller set of uncorrelated variables in order to make data interpretation easier. Of the above-mentioned pattern recognition techniques, PCA is a technique that transforms the data from the original correlated variables into uncorrelated variables most easily.

PCA creates a new set of reference axes arranged in decreasing order of variance subsumed. The individual PCs are linear combinations of the original variables. The data can be displayed on combinations of the new axes, just as they can be displayed on the original elemental concentration axes. PCA can be used in a pure pattern-recognition mode, i.e., to search for subgroups in an undifferentiated data set, or in a more evaluative mode, i.e., to assess the coherence of hypothetical groups suggested by other criteria. Generally, compositional differences between specimens can be expected to be larger for specimens in different groups than for specimens in the same group, and this implies

that groups should be detectable as distinct areas of high point density on plots of the first few components.

It is well known that PCA of chemical data is scale dependent (Mardia et al. 1979), and analyses tend to be dominated by those elements or isotopes for which the concentrations are relatively large. As a result, standardization methods are common to most statistical packages. A common approach is to transform the data into logarithms (e.g., base 10). As an initial step in the data interpretation discussed herein, the data are transformed into log concentrations to compensate for differences in scale between major elements such as Al, Ca and Fe, and trace elements, such as the rare-earth elements (REEs). An additional advantage of the transformation is that it appears to produce more nearly normal distributions for the trace elements.

A frequently exploited strength of PCA, discussed by Baxter (1992), Baxter and Buck (2002), and Neff (1994, 2002), is that it can be applied as a simultaneous R- and Q-mode technique, with both variables (elements) and objects (individual analyzed samples) displayed on the same set of principal component reference axes. A plot using the first two principal components as axes is usually the best possible two-dimensional representation of the correlation or variance-covariance structure within the data set. Small angles between the vectors from the origin to variable coordinates indicate strong positive correlation; angles at 90 degrees indicate no correlation; and angles close to 180 degrees indicate strong negative correlation. Likewise, a plot of sample coordinates on these same axes will be the best two-dimensional representation of Euclidean relations among the samples in log-concentration space (if the PCA was based on the variance-covariance

matrix) or standardized log-concentration space (if the PCA was based on the correlation matrix). Displaying both objects and variables on the same plot makes it possible to observe the contributions of specific elements to group separation and to the distinctive shapes of the various groups. Such a plot is commonly referred to as a "biplot" in reference to the simultaneous plotting of objects and variables. The variable interrelationships inferred from a biplot can be verified directly by inspecting bivariate elemental concentration plots.

Whether a group can be discriminated easily from other groups can be evaluated visually in two dimensions or statistically in multiple dimensions. A metric known as the Mahalanobis distance (or generalized distance) makes it possible to describe the separation between groups or between individual samples and groups on multiple dimensions. The Mahalanobis distance of a specimen from a group centroid (Bieber et al. 1976, Bishop and Neff 1989) is defined by:

$$D_{y,X}^2 = [y - \overline{X}]^t I_x [y - \overline{X}]$$

where y is the 1 x m array of logged elemental concentrations for the specimen of interest, X is the n x m data matrix of logged concentrations for the group to which the point is being compared with \overline{X} being it 1 x m centroid, and I_X is the inverse of the m x m variance-covariance matrix of group X. Because Mahalanobis distance takes into account variances and covariances in the multivariate group it is analogous to expressing distance from a univariate mean in standard deviation units. Like standard deviation units, Mahalanobis distances can be converted into probabilities of group membership for individual specimens. For relatively small sample sizes, it is appropriate to base probabilities on

Hotelling's T^2 , which is the multivariate extension of the univariate Student's T.

Mahalanobis distance-based probabilities can and do fluctuate dramatically depending upon whether or not each specimen is assumed to be a member of the group to which it is being compared—this is especially true for small groups. Harbottle (1976) calls this phenomenon "stretchability" in reference to the tendency of an included specimen to stretch the group in the direction of its own location in elemental concentration space. This problem can be circumvented by crossvalidation, that is, by removing each specimen from its presumed group before calculating its own probability of membership (Baxter 1994; Leese and Main 1994). This is a conservative approach to group evaluation that may sometimes exclude true group members.

Small sample and group sizes place further constraints on the use of Mahalanobis distance: with more elements than samples, the group variance-covariance matrix is singular thus rendering calculation of I_X (and D^2 itself) impossible. Therefore, the dimensionality of the groups must somehow be reduced. One approach would be to eliminate elements considered irrelevant or redundant. The problem with this approach is that the investigator's preconceptions about which elements should be discriminate may not be valid. It also squanders the main advantage of multielement analysis, namely the capability to measure a large number of elements. An alternative approach is to calculate Mahalanobis distances with the scores on principal components extracted from the variance-covariance or correlation matrix for the complete data set. This approach entails only the assumption, entirely reasonable in light of the above discussion of PCA, that most group-

separating differences should be visible on the first several PCs. Unless a data set is extremely complex, containing numerous distinct groups, using enough components to subsume at least 90% of the total variance in the data can be generally assumed to yield Mahalanobis distances that approximate Mahalanobis distances in full elemental concentration space.

Mahalanobis distance calculations also are quite useful for handling missing data (Sayre 1975). When many specimens are analyzed for a large number of elements, it is almost certain that a few element concentrations will be missed for some of the specimens. This occurs most frequently when the concentration for an element is near the detection limit. Rather than eliminate the specimen or the element from consideration, it is possible to substitute a missing value by replacing it with a value that minimizes the Mahalanobis distance for the specimen from the group centroid. Thus, those few specimens which are missing a single concentration value can still be used in group calculations.

A final discussion point in this section concerns the use of discriminant analysis. Discriminant analysis has widely been used to facilitate the construction of compositional groups in previous Mimbres studies (e.g., Brewington et al. 1996; Dahlin 2003). The underlying assumption in discriminant analysis is that the number of possible groups is known beforehand using *a priori* regional information (e.g., site level provenience, ceramic type, etc.). Linear combinations of the original chemical data are then calculated. Which plotted, these scores display the best possible separation of the assumed groups. Such an approach is, generally speaking, appropriate when compositional variability among groups is well established. However, when chemical variability is subtle

among groups, which is oftentimes the case with ceramic compositional data, subgroups are masked and samples that would otherwise be unassigned or even outliers to the dataset are not obvious.

In Chapter 2, I provided an overview of previous Mimbres studies and illustrate plots of data that resulted from these studies. As one examines these figures, there is a very clear and recurring theme in that 5 to 8 compositional groups typically are identified in most of these earlier studies. The identification of these groups is based, in part, on an inherent bias in the dataset. Specifically, more than 50% of 4000+ specimen dataset is dominated by pottery from about 15 sites, most of which are located in the Mimbres Valley. With each successive study that occurred, there was a general trend to ignore (or not incorporate) extant data. Initial starting groups were typically defined based on site-level provenience and/or through the application of some preferred clustering algorithm with a cut-off of 4-8 groups. These initial groups were then subjected to discriminant analysis and further refined to account for misassigned samples (e.g., imports). Compositional groups were subsequently attributed to a given site (or group of sites) based on the criterion of abundance. That is to say that the site(s) that contributed the largest number of samples to a given compositional group is assumed to be the point of origin for that particular group.

Unfortunately Mimbres pottery group assignments are not that straightforward or simplistic. In this reanalysis of the entire Mimbres region dataset, I have identified more than 35 Mimbres-series compositional groups. With the benefit of the larger dataset, it has been possible to reassign samples in datasets that were previously assigned to only 5 or 6 groups to 12–20 different compositional groups. Many of the

newly identified groups can confidently be attributed to specific sites and/production zones throughout the Mimbres region. Many compositional groups, however, cannot confidently be attributed. This issue is discussed in greater detail in Chapters 4 and 5. What is important, here, is to underscore the fact that clustering algorithms and discriminant analysis have not been used to construct or identify compositional groups in the current study. Instead I have taken an approach in which segments of the dataset are separated from the dataset using key discriminating elements (e.g., Th, Ta, Dy, and Fe) to create, so-called "Macro Groups". This has resulted in the identification of smaller more manageable groups of samples that can then be further subdivided using traditional pattern recognition and exploratory data techniques discussed above.

Chapter 4

Group Structure and Interpretation of INAA Data

4.1. Identification of Macro Groups

As discussed in earlier chapters, there have been more that 4000 analyses of Mimbres (e.g., Figure 4.1.1), Jornada, and related pottery and clays since the early 1990's. Although numerous researchers have explored the dynamics of Mimbres pottery production from a chemical perspective, none have attempted to incorporate all, or even most, of the extant data under the umbrella of a single interpretative framework until now.

Analysis of large and complex datasets is not without challenges. It is virtually impossible to work with and interpret a large dataset without having some means to partition the data into smaller more manageable groups. In the earlier interpretations of the Mimbres data generated at MURR in the late 1990's and early 2000's, groups were shown to be distinct, by Hector Neff, on the basis of thorium, cesium, tantalum, and a few other key elements¹. Typically thorium and tantalum could be used to effectively separate Mimbres from Jornada pottery produced in the Hueco Bolson (the area in and around El Paso, Texas) and thorium and cesium could be used to discriminate Mimbres groups 1, 2, 3, 4 and 5².

¹ Although James et al. (1995) did not publish eigenvalues or loading scores for their PCA analysis of 200+ specimen Mimbres dataset, I observe similar patterns. When PCA analysis is conducted on their dataset, Group 4 expresses enrichment in Cs relative to Groups 2, 3, 5, and 6. Group 1 is enriched in Th relative to Groups 2, 3, 5, and 6.

² Neff's Groups 1, 2, and 3 are essentially unchanged in the current study. Neff's Group 4 is somewhat similar to the Group 4 (a, b, and c) in the present study, but also included ceramics assigned to Groups 8 and 11. When combined, Neff's Groups 4 and 5 formed the basis for the Main Playas Red group. Neff's Group 5 bears no similarity to Group 5 in the current study.

Given that thorium has been repeatedly demonstrated to be such a critical element for discriminating the major Mimbres compositional groups, it made sense to continue to use thorium to partition the entire dataset into smaller more manageable units. In the current study, Mimbres and other related pottery and clays are divided into three macro groups designated A, B, and C. Generally speaking, pottery assigned to Macro Group A has thorium concentrations higher than 30 ppm. Macro Group B has thorium concentrations that range from ca. 12–30 ppm thorium. Finally Macro Group C contains specimens that have less than ca. 12 ppm thorium. Separation of the three macro groups is illustrated in Figures 4.1.2 and 4.1.3.

Jornada Mogollon pottery is generally assigned to Macro Group D. Effective separation of the Macro Group D from Macro Groups A and C can be illustrated in a bivariate projection of thorium and tantalum (Figure 4.1.4). Separation of Macro Group D from Macro Group B is possible using the elements thorium and hafnium (Figure 4.1.5). There are few samples from Macro Group B however that overlap with macro Group D. Examination of data for these samples indicates they primarily are samples analyzed for Gilman et al.'s (1994) study. As discussed above, powdered material for analysis of these samples was obtained by drilling the ceramics with tungsten-carbide drill bits. The drilling resulted in cobalt contamination of the samples, and to a certain extent, tantalum contamination (cobalt and tantalum are used in the production of tungsten carbide tools). Because the tantalum enrichment only affected a small number of the samples analyzed for this project, and because tantalum is an important discriminating element for separation of pottery from the Jornada region from pottery produced throughout the Mimbres region, the decision was made to not remove tantalum from the dataset.



Figure 4.1.1. Alma Rough wide-mouthed jar (modified seed jar form) from the Power Site (LA 121210). INAA sample number ANIOO5. Photograph courtesy of Lori Reed.




Figure 4.1.2. Bivariate plot of thorium and dysprosium showing separation of Macro Group A from Macro Group B.




Figure 4.1.3. Bivariate plot of thorium and iron showing separation of Macro Group B from Macro Group C.




Figure 4.1.4. Bivariate plot of thorium and tantalum showing separation of Macro Groups A, C, and D.




Figure 4.1.5. Bivariate plot of tantalum and iron showing separation of Macro Group B from Macro Group C.

4.2. Macro Group A

Macro Group A comprises approximately 485 pottery samples assigned to six compositional groups designated Mimbres-01 (n = 193), Mimbres-03 (n = 103), Mimbres-07A (n = 49), and Mimbres-07B (n = 7), Mimbres-10 (n = 102), AND Mimbres-13 (n = 4). Twenty-eight samples are unassigned. Unambiguous separation of these groups is readily possible in multivariate space (PCA) and using element projections. Figures 4.2.1–4.2.5 illustrates the group structure for Macro Group A. Mahalanobis distance probabilities and PCA scores are provided in Appendix A.

Figures 4.2.1-4.2.4 are plots derived from PCA of the variancecovariance matrix for Macro Group A pottery. Ellipses are drawn at the 90% confidence interval. Figure 4.2.1 is a biplot of principal components 1 and 2 that illustrates the basic compositional group structure for Macro Group A pottery. Pottery assigned to Mimbres-01 expresses enrichment in Cs, Sb, and U relative to the other groups. Mimbres-03 tends to be enriched in Mn and Rb. The remaining four groups tend to be enriched first row transition metals and lanthanide group elements relative to Mimbres-01 and Mimbres-03. Figure 4.2.2 is a plot of principal components 1 and 2, but without the vectors drawn. In this figure it is shown that Mimbres-13 has some compositional overlap with Mimbres-10 and that Mimbres-07A and -07B exhibit marginal separation. A plot of principal components 1 and 4 (Figures 4.2.3–4.2.4), however, indicates separation of the groups from one another is possible. A bivariate plot of Cr and Cs concentrations (Figure 4.2.5) show unambiguous separation of the six compositional groups identified in Macro Group A.




Figure 4.2.1. Biplot of principal components 1 and 2 derived from PCA of the variance-covariance matrix for Macro Group A pottery. Ellipses are drawn at the 90% confidence interval.




Figure 4.2.2. Plot of principal components 1 and 2 derived from PCA of the variance-covariance matrix for Macro Group A pottery. Ellipses are drawn at the 90% confidence interval.




Figure 4.2.3. Biplot of principal components 1 and 4 derived from PCA of the variance-covariance matrix for Macro Group A pottery. Ellipses are drawn at the 90% confidence interval.




Figure 4.2.4. Plot of principal components 1 and 4 derived from PCA of the variance-covariance matrix for Macro Group A pottery. Ellipses are drawn at the 90% confidence interval.




Figure 4.2.5. Plot of chromium and cesium base-10 logged concentrations showing separation of Macro Group A pottery. Ellipses are drawn at the 90% confidence interval.

Mimbres-01 Pottery assigned to this group occurs at 37 sites throughout the Mimbres and Jornada regions and at one site in Chihuahua. This chemical group consists almost entirely of Style III sherds ca. (88%). A few samples are classified as Style II (ca. 5%); the remaining are either Mimbres Style Indeterminate, corrugated, or Mimbres polychrome specimens. No clay samples are members of this group despite the fact that several clays from the Eastern Mimbres segments of the Rio Grande Valley area (EMAP) have been analyzed. On the basis of electron microprobe work, Schriever (2008:116) classified four samples assigned to this group (BAS067, 071, 214, and 221) as being comprised of a:

...fine grained mature sediment in which there are few altered rhyolite fragments and in which most of the mineral grains are altered and exhibit weathering. Rhyolite fragments are considerably altered with plagioclase and alkali feldspars exhibiting zones of alteration grading toward end-members, muscovite probably replacing biotite, and the groundmass altering to microcrystalline quartz. These phases compose the majority of the paste, indicating that rhyolite is the parent material. Small inclusions of calcite are also present in the paste. It is unclear whether the paste derives from a highly weathered rhyolite or one that was altered through some other process such as the deposition of pyroclastic material into a body of water or hydrothermal activity. Regardless, the homogeneity of the paste indicates that the material is from either a primary or residual formation (Schriever 2008:121).

Chemically the Mimbres-01 is one of three very distinct groups (the others being Mimbres-03 and Mimbres-02A) that consistently has been recognized in most previous INAA studies (e.g., Miller et al. 1997 [Group

3]; Creel and Hudler 2004 [Group 2]. Miller (2005) notes this group also is marked by distinctive production and design attributes, including a much higher incidence of exterior slips, red-painted (oxidized) designs, and also has distinctive temper attributes.

The distribution of pottery, by site, is depicted in Figure 4.2.61. For purposes of this specific figure, Mimbres-01 pottery from a site in Chihuahua is not displayed on the map (instead refer to Figure 1.3). Based on the distribution of sites containing relatively higher percentages of pottery, we can safely assume that the production area for the Mimbres-01 group is somewhere in the Eastern Mimbres area (EMAP) and thus seems to represent a significant Mimbres production group outside of the Mimbres Valley. The Mimbres-01 group comprises 65% or more of the pottery from three EMAP sites (Flying Fish, Las Animas Village, and Lizard Terrace). Relatively higher percentages of Mimbres-01 pottery are found at sites in the Rio Alamosa area (Victorio, Montoya, and Kelly Canyon) and at sites further south in the Jornada region. Mimbres-01 pottery is found in lower relative abundance at sites throughout the Mimbres Valley and elsewhere.

¹ All graduated symbol distribution maps were created using ArcMap 10. In all cases, sites with fewer than 10 analyzed samples are displayed as blue symbols. Graduated symbols are based on the ArcMap Equal Interval algorithm for 5 classes. Graduated symbol sizes in each map are scaled from a size of 10 to 50 points. Input data for the Equal Interval Algorithm is expressed as a percentage of the number of samples, from a given site, that are assigned to the group in question, relative to the total number of analyzed samples from that site. Pottery classified as Jornada Mogollon wares (e.g., El Paso polychrome, El Paso Brown, El Paso Bichrome) are not included in the site totals.




Figure 4.2.6. Graduated symbol distribution map for Mimbres-01 pottery.

Larger symbol sizes represent sites with proportionally higher percentages of pottery assigned to the Mimbres-01 group. Sites with fewer than 10 samples are represented by blue dots. Samples from sites in Chihuahua are not displayed in this figure.

Mimbres-03 is represented by 103 samples that originate from 14 sites. Considerable confusion exists in the classification of ceramics assigned to this group. This stems from the fact that Mimbres Black-on-white pottery is by definition a white-slipped brown-paste ceramic. Pottery assigned to Mimbres-03 typically (but not always) is made from an unslipped light-colored paste, but decorated with design elements that are reminiscent of traditional Mimbres B/w pottery. Consequently it has been classified by different researchers as "Indeterminate Whiteware", Whiteware (not Mimbres), "Cibola Paste, Mimbres design", Cibola, and Mimbres B/W Style I, II, and III. This group also includes one Tularosa B/w and one Alma Plain specimen.

The distribution of Mimbres-03 pottery, by site, is depicted in Figure 4.2.7—a graduated symbol distribution map. Like the Mimbres-01 compositional group, the Mimbres-03 group is one of three distinct groups consistently recognized in INAA studies of Mimbres pottery. Despite the fact that no clays can be assigned to this group, the Upper Gila region (Gila Forks) is assumed to be the point of origin for pottery assigned to this group, on the basis of its high occurrence at sites in the Upper Gila.




Figure 4.2.7. Graduated symbol distribution map for Mimbres-03 pottery.

Larger symbol sizes represent sites with proportionally higher percentages of pottery assigned to the Mimbres-03 group. Sites with fewer than 10 samples are represented by blue dots.

Mimbres-07A and Mimbres-07B groups are recognizable by their higher rare earth element profiles. Forty-nine samples are assigned to group 7A and seven are assigned to group 7B. Both groups are chemically very similar and group separation is marginal. Additionally, a number of samples assigned to Mimbres-07A exhibit higher cerium (ca. 200 ppm versus 400 ppm) and other rare earth element concentrations relative to other samples in this group. It is possible that with additional sampling that a third group might be defined.

Pottery assigned to the Mimbres-07A group primarily is classified as Alma Plain, Rough, or Smudged (n = 45); this group also includes one Mimbres Red, one Reserve, and two plain specimens. Forty-six of the samples originate from sites in the Deming area (LA129562, LA54814, and LA59652); the remaining three samples originate from three different sites in the Animas Valley.

Six of seven specimens assigned to Mimbres-07B are classified as Alma Plain or Alma Rough; the remaining sample is classified as Mimbres Red (which probably more appropriately should be classified as San Francisco Red). All samples assigned to this group originate from two sites in the Deming area (LA129562 and LA59652).

Given the proximity of the Deming sites to one another, the number of samples assigned to these two groups, and the chemical similarity between the two groups, it seems apparent that samples assigned to these groups were produced locally at sites in the Deming area. There have not been any clay samples analyzed from the Deming thus far, and none of the clays in the database can be assigned to this group.

The distribution of Mimbres-07A pottery, by site, is depicted in Figure 4.2.8. Given that only two sites are represented in the Mimbres-07B group, a distribution map was not created since the small sample size would skew the results; site locations for Mimbres-07B pottery are shown the map constructed for Mimbres-07A pottery (Figure 4.2.8).




Figure 4.2.8. Graduated symbol distribution map for Mimbres-07A pottery. Larger symbol sizes represent sites with proportionally higher percentages of pottery assigned to the Mimbres-07A group. Sites with fewer than 10 samples are represented by blue dots.

Most **Mimbres-10** pottery can be classified as utilitarian ware. Ceramics in this group (N= 102) are predominantly classified as Mimbres corrugated (ca. 35%), misc. corrugated (ca. 16%), and Alma Plain and Alma Rough (ca. 20%). The group also includes two Mimbres B/w Style III samples and one Style I sherd; six Playas Red specimens also are assigned to this group.

From a chemical perspective this group is chemically heterogeneous. A single clay sample (ANIO10) has a 35% probability of membership in this group. According to Lori Reed (Reed n.d.), ANIO10 is a residual granitic-derived clay composed of quartz, plagioclase, potassium feldspar, and granitic lithic fragments (which is consistent with the Precambrian-aged basement rock for much of this region). The high probability of membership for ANIO10 in the Mimbres-10 group would seem to suggest that pottery assigned to this group was produced at or near the Power and Beargrass sites in the Burro Mountains. Certainly this is the case for some of the pottery assigned to this group specifically samples with an ANI prefix. However, it does not seem plausible that the Burro Mountains are the point source for all of the pottery assigned to this group. It is more likely this group represents the use of chemically similar clays (i.e., granitic-parent material) over a broad geographic region. With sufficient sampling, it eventually may be possible to separate the Burro Mountain pottery from the Mimbres-10 group on the basis of antimony and manganese concentrations. Likewise additional sampling may define separate groups for the Cedar Mountains and the Cooke Range. The distribution of Mimbres-10 pottery, by site, is depicted in Figure 4.2.9.




Figure 4.2.9. Graduated symbol distribution map for Mimbres-10 pottery.

Larger symbol sizes represent sites with proportionally higher percentages of pottery assigned to the Mimbres-10 group. Sites with fewer than 10 samples are represented by blue dots. Clay sample ANI010 is denoted by the red star.

Mimbres-13 pottery consists of 4 samples of Mimbres B/W Style II, III, and II/III sherds from sites in the Jornada region—Los Tules (n=2), Diablo 1 (n=1), and North Hills I (n=1). This group is not only chemically distinct from other Mimbres pottery groups, but also distinct from compositional groups identified for the Jornada region (Macro Group D).

Figure 4.2.10 shows the site locations for the four samples assigned to this group. Currently, the best guess is that this group represents a small, relatively isolated production of Mimbres pottery in the Jornada region. One possibility is that this group represents pottery production at the Los Tules site which when excavated had a lot of Mimbres pottery and Mimbres-style pithouse dwellings and is arguably a Mimbres site, or at least a site that had some Mimbres residents.

Alternatively, this group could represent pottery production in the Las Cruces/Mesilla areas—pottery from which has not yet been the subject of INAA.




Figure 4.2.10. Map showing the site distribution for Mimbres-13 pottery.

4.3. Macro Group B

Macro Group B contains about 1700 pottery and clay samples that are assigned to 12 compositional groups. This large group of pottery can be divided further into two subgroups designated Macro Group B-1 and Macro Group B-2 based on patterning observed in various element projects of the data, but notably in PCA space (see Figure 4.3.1). Macro Group B-1 includes: Mimbres-04A, Mimbres-04B, Mimbres-04C, Mimbres-05A, Mimbres-05B, Mimbres-05C, and Mimbres-09. Macro Group B-2 includes Mimbres-02A, Mimbres-02B, Mimbres-02C, Mimbres-08, and Mimbres-11. Approximately 30% of the pottery in Macro Group B is unassigned. Unambiguous separation of groups is readily possible in multivariate space (PCA) and using element projections—notably B-2 pottery is enriched in Cs relative to B-1 groups. Figures 4.3.1–4.3.12 illustrates the group structure for Macro Group B. Mahalanobis distance probabilities for group membership and PCA scores are provided in Appendix B.

Figures 4.3.1–4.3.4 are plots derived from PCA of the variance-covariance matrix for Macro Group B pottery. Ellipses are drawn at the 90% confidence interval. Figure 4.3.1 illustrates the basic group structure for Macro Group B. The dashed line in this figure delineates groups assigned to Macro Group B-1 and Macro Group B-2. Pottery assigned to subgroup B-2 expresses enrichment in Cs, Rb, Th, and Sb (Figure 4.3.2). Within Macro B-1, Mimbres-05 expresses enrichment in first row transition metals and rare earth elements, relative to Mimbres-04 and Mimbres-09. Figure 4.3.3 projects the unassigned samples relative to the 90% confidence ellipses for the B-1 and B-2 compositional groups.

Figure 4.3.4 projects Marco Group B clays against the 90% confidence ellipses for the compositional groups. Of particular note here is that relatively few clays plot with groups in assigned to Macro Group B-2, and those that do—generally—cannot assigned with a high degree of confidence to their corresponding group using Mahalanobis distance probabilities. The most likely explanation is the addition of non-plastics (tempers) to the clays used to produce Macro Group B-2.

A plot of Cr and Yb concentrations illustrates the basic group structure for pottery assigned to Macro Group B-1 (Figure 4.3.5). Marginal separation exists for the Mimbres-04 and -05 groups (see also Figure 4.3.7), but it is Yb and to a lesser extent Sm and Dy that allow these groups to be separated from one another. A plot of Sm and Eu shows unambiguous separation of Mimbres-09 from Mimbres-04 (Figure 4.3.6).

Mimbres-04 can be subdivided into three groups, designated 04A, 04B, and 04C, on the basis Cr and Th concentrations (Figure 4.3.8). Distinctions among these groups are marginal and likely reflect subtle chemical variation within geologically similar clays and tempers in the Middle Mimbres Valley used to produce pottery assigned to these groups. Although separation of group 4 pottery is marginal, it does none-the-less appear to represent geographically distinct signatures for pottery production (see below).

Mimbres-05, likewise, can be further divided into two large groups (05A and 05B) and one small group (05C) on the basis of Cr and Th (Figure 4.3.9) and Hf and Zr (Figure 4.3.10).

Given that Macro Group B-1 pottery exhibits subtle chemical, as opposed to Macro Group A pottery (refer to previous discussion) and Macro Group B-2 pottery, a plot showing unambiguous separation of the seven compositional groups is not possible using a single principal components plot or bi(tri)variate elemental plot. It is possible, however, to show good visual separation of the seven compositional groups using discriminant analysis (Figure 4.3.11). However, to reiterate a point made in Chapter 3, discriminant analysis was not used create these groups, but rather it is used solely for illustrative purposes.

In contrast to Macro Group B-1, groups assigned to Macro Group B-2 can be shown to be discrete in a single plot using Cs and Cr (Figure 4.3.12). The groups identified in Macro Group B-1 are believed to represent pottery production in the Mimbres Valley (as with the Mimbres-04 groups), but as mentioned above, use of different tempers is likely what is driving the major differences among compositional groups.

In the sections below, I discuss individual compositional groups.




Figure 4.3.1. Plot of principal components 1 and 2 derived from PCA of the variance-covariance matrix for Macro Group B pottery. Ellipses are drawn at the 90% confidence interval. The dashed line delineates groups assigned to Macro Group B-1 and Macro Group B-2.




Figure 4.3.2. Biplot of principal components 1 and 2 derived from PCA of the variance-covariance matrix for Macro Group B pottery. Ellipses are drawn at the 90% confidence interval.




Figure 4.3.3. Plot of principal components 1 and 2 derived from PCA of the variance-covariance matrix for Macro Group B pottery showing unassigned pottery specimens.




Figure 4.3.4. Plot of principal components 1 and 2 derived from PCA of the variance-covariance matrix for Macro Group B pottery showing Group B clay specimens projected against 90% confidence ellipses for Macro Group B reference groups.




Figure 4.3.5. Bivariate plot of chromium and ytterbium base-10 logged concentrations showing Macro Group B-1 pottery. Ellipses are drawn at the 90% confidence interval.




Figure 4.3.6. Bivariate plot of samarium and europium base-10 logged concentrations showing separation of Mimbres-04 and Mimbres-09 pottery. Ellipses are drawn at the 90% confidence interval.




Figure 4.3.7. Bivariate plot of ytterbium and chromium base-10 logged concentrations showing separation of Mimbres-04 and Mimbres-05 pottery. Ellipses are drawn at the 90% confidence interval.




Figure 4.3.8. Bivariate plot of chromium and thorium base-10 logged concentrations showing separation of Mimbres-04 pottery into three subgroups designated 04A, 04b, and 04C. Ellipses are drawn at the 90% confidence interval.




Figure 4.3.9. Bivariate plot of chromium and thorium base-10 logged concentrations showing separation of Mimbres-05 pottery into three subgroups designated 05A, 05b, and 05C. Ellipses are drawn at the 90% confidence interval.




Figure 4.3.10. Bivariate plot of zirconium and hafnium base-10 logged concentrations showing the separation of Mimbres-05B and Mimbres-05C pottery. Ellipses are drawn at the 90% confidence interval.




Figure 4.3.11. Bivariate plot of Canonical Discriminant 1 and 2 showing separation of all B-1 pottery groups. Ellipses are drawn at the 90% confidence interval.




Figure 4.3.12. Bivariate plot of cesium and chromium base-10 logged concentrations showing the separation of all pottery groups assigned to Macro Group B-2. Ellipses are drawn at the 90% confidence interval.

Macro Group B-1 Compositional Groups

The identification of distinct Mimbres Valley pottery groups has been problematic since the first INAA studies of Mimbres pottery (e.g., Gilman et al. 1994; James et al. 1995). At one point in time, Mimbres-04, as Hector Neff originally defined the group at MURR in the early 2000's, subsumed the majority of what I now refer to as Groups 04A, 04B, 04C, 08, 09, and 11, and also some samples assigned to Mimbres-05A and 05B. With the additional INAA analyses of hundreds of Mimbres pottery specimens over the past several years, and also the benefit of looking at these groups from the perspective of a combined dataset (e.g., the inclusion of the Texas A&M and Smithsonian-NIST data), it is now possible to recognize and statistically validate multiple previously unknown groups. A few of these groups are highly distinctive, such as Mimbres-02A, 08, and 11. In contrast, distinctions among Mimbres-04A, 04B, and 04C are marginal given the subtle chemical variation present in these groups (e.g., temper/clay mixing). The following is a discussion of each of the Macro Group B-1 pottery groups.

Mimbres-04A, B, and C.

The identification of distinct subgroups within the large Mimbres-04 group analytically has been fairly challenging given that chemical distinctions among these groups are subtle. Mahalanobis distance probabilities oftentimes indicate membership in one or more of the subgroups. Schriever (2008) had similar problems identifying subgroups from a mineralogical perspective. He states:

While this group contains rhyolites of various textures, these do not provide a means to discriminate groups because it is not uncommon for rhyolite deposits to exhibit such variation [and because they are ubiquitous throughout the region].

Further, there is little difference in feldspar populations
between the samples [because they were produced from the
same basement materials at approximately the same time].

Although the samples in this group are closely grouped, the
INAA analysis places members of this group into three
different compositional groups that probably relate to the
minor mineral assemblage. The discrimination of INAA groups
is based on trace elements that are associated with minor
minerals the presence or absence of which in the INAA
sample could be significant (Schriever 2008:324).

Mimbres-04A contains approximately 280 samples from 43 sites throughout the Mimbres, Jornada, and adjacent regions. Most pottery assigned to this group (ca. 75%) is classified as Mimbres B/W Style III; approximately 9% of the pottery assigned to this group is Mimbres B/W Style II pottery of which more half originates from the Galaz site. Mimbres B/W Style I pottery represents approximately 3% of pottery assigned this group (n = 9). Interestingly of the 9 Mimbres B/W Style I samples, 6 originate from sites outside the Mimbres Valley; within the Mimbres Valley two specimens originate from Galaz and one is from Swarts. Corrugated pottery represents about 7% of this group and the remaining samples are variants of Reserve, Three Circle, and Alma.

The distribution of Mimbres-04A pottery, by site, is depicted in Figure 4.3.13. Most pottery assigned to this group is confined to the Mimbres Valley and immediate surrounding area and also the Jornada region. Avilas Canyon Village in the Eastern Mimbres/Rio Grande

drainage has a higher overall percentage of pottery, but given the relatively low overall occurrence of Mimbres-04A pottery in the Eastern Mimbres relative to sites in the Mimbres Valley, it is not likely that this pottery originates from sites in the Rio Grande drainage. Additionally, given that most Mimbres B/W Style I and II pottery assigned to this group originates from Galaz and given that 22% of the total analyzed sample of Galaz pottery (n = 130) is assigned to this group, Galaz seems to be the most likely production center for Mimbres-04A pottery.




Figure 4.3.13. Graduated symbol distribution map for Mimbres-04A pottery. Larger symbol sizes represent sites with proportionally higher percentages of pottery assigned to the Mimbres-04A group. Sites with fewer than 10 samples are represented by blue dots.

Mimbres-04B contains 129 samples from 38 sites. More than 88% of pottery assigned to this group is Mimbres B/W Style III (n = 105) or Mimbres Polychrome (n = 10); the remaining pottery types includes Mimbres B/W Style I, II, or II/III, Mimbres Plain, and Mimbres Corrugated. There is a single Three Circle R/W specimen (from Old Town) assigned to this group.

As with Mimbres-04A, Mimbres-04B also is assumed to represent pottery production in the Mimbres valley. The distribution of Mimbres-04A pottery, by site, is depicted in Figure 4.3.14. Most pottery assigned to this group is confined to sites within the Mimbres Valley and immediate surrounding area. Given that the site with the highest occurrence of Mimbres-04B is the Perrault site (25% which is 12% higher than the next two highest sites—Goforth and Pruitt Ranch), it seems likely that Perrault is the point of origin for pottery assigned to this group. One caveat, however, is that to date only 24 pottery vessels have been analyzed from Perrault; a more robust sample that includes both pottery and raw materials is needed to substantiate this finding.




Figure 4.3.14. Graduated symbol distribution map for Mimbres-04B pottery. Larger symbol sizes represent sites with proportionally higher percentages of pottery assigned to the Mimbres-04B group. Sites with fewer than 10 samples are represented by blue dots.

Mimbres-04C contains 119 pottery samples from 29 sites. Unlike Mimbres-04A and 04B which contain primarily later period pottery (e.g., Style III), Mimbres-04C is comprised primarily of earlier ceramic types. With this particular group, Mimbres B/W Style III pottery represents only about 18% (n = 22) of the total. In contrast, more than 27% of pottery in Mimbres-04C is classified as Mimbres B/W Style I (n = 33); 18% is classified as Mimbres B/W Style II (n = 22); and 18% is classified as Alma (n = 6), Three Circle (n = 9), and Mogollon Red-on-brown (n = 8)—all earlier pottery types. The remaining pottery assigned to this group is classified as plain, corrugated, or other miscellaneous pottery types.

The distribution of Mimbres-04C pottery, by site, is depicted in Figure 4.3.15. Most pottery assigned to this group is confined to the Mimbres Valley and immediate surrounding area and also the Jornada region. Based on the distribution of pottery assigned to this group and its chemical similarities with Mimbres-04A and 04B, it is assumed that this compositional group represents a primarily earlier pottery production in the Mimbres Valley. Furthermore, the distribution patterns would seem to suggest that the Harris Site area [there are several moderate/large pithouse and Classic sites in the immediate vicinity] is the point of origin for pottery assigned to this group. However, only 18 samples have been analyzed to date from this site. Clearly additional sampling is needed. Additionally of interest is that only one is Mimbres B/W Style III pottery specimen is represented in the Jornada region sample; the remaining samples are Mimbres B/W Style I, I/II, or II.

Two clay samples exceed 1% Mahalanobis distance probability of having membership in the Mimbres-04C group (Table 4.3.1). One is a sample of potter's clay from Swarts (SWR213; M.D. = 2.87%); the second

is a piece of burned adobe from NAN (BRE224A; M.D. = 1.71%). In both cases, these probabilities are too low to confidently argue for production of Mimbres-04C pottery at Swarts or NAN. Additionally, the pottery samples from these sites would not support such an argument. Only 3% of the 210 samples from Swarts can be assigned to this group—relative to the much higher percentages for the Harris, Galaz, and Gonzales sites. Likewise, only 2% of the pottery from NAN is assigned to this group. It is likely that a raw clay material survey in and around the Harris site would yield clays with much higher probabilities of group membership—to date such a study has not been undertaken.

Table 4.3.1. Mahalanobis Distance (M.D.) probabilities for clay samples projected against Mimbres-04C.

I.D.	M.D.	Material	Site Name	Site No.
BRE224A	1.7	Clay-Burned Adobe	NAN	LA 002465
SWR213	2.9	Clay-Potters	Swarts	LA 001691




Figure 4.3.15. Graduated symbol distribution map for Mimbres-04C pottery. Larger symbol sizes represent sites with proportionally higher percentages of pottery assigned to the Mimbres-04C group. Sites with fewer than 10 samples are represented by blue dots.

Mimbres-05A, B, and C.

Mimbres-05¹ was first identified, in its present form, in the mid-2000's during a project for Chris Turnbow involving the analyses of Mimbres and Mimbres-related pottery from the Upper Gila River. As the number of analyses increased from Upper Gila River, and as extant

¹ Mimbres-05 as discussed herein is completely different from the Mimbres-05 group identified by Hector Neff at MURR and used to classify Mimbres pottery from the mid-1990's through the mid-2000's. MURR's Group 5 comprised pottery that has been subdivided into various Macro-Group C compositional groups.

datasets were incorporated into MURR database (e.g., Gilman et al. 1994 and various Texas A&M datasets), it became apparent that at least two compositional groups were present and Mimbres-05 subsequently was divided into groups 05A and 05B. More recently a third smaller group (05C) has been identified.

Mimbres-05A contains 98 pottery samples from 36 sites. Most pottery assigned to this group originates from sites along the Gila River and its tributaries. Its occurs in highest percentages at Dutch Ruin in western New Mexico and the Powers Ranch site in eastern Arizona. Many of the samples assigned to the Powers Ranch compositional group by Gilman et al. (1994) also are assigned to this group. Ceramic types assigned to this group are fairly diverse. Approximately 25% (n = 25) of the ceramics are classified as Mimbres Style III, 12% are Style II, and 13% are Style I. A majority of the remaining pottery is undifferentiated brown/plain pottery much of which is post-A.D. 1300 in age.

The distribution of Mimbres-05A pottery, by site, is depicted in Figure 4.3.16. Two clay samples exceed 1% probability of membership in this group (Table 4.3.2). One sample (BRE214) is from the West Fork site and this same sample actually has higher probabilities of membership in Mimbres-05B (see below). The second clay sample (RLB075) is from Lake Roberts Vista and has a relative low probability of membership. Unfortunately, very few clays have been sampled from the vicinity of the Gila River. Thus while these two clays do have probabilities of membership in Mimbres-05A, it is likely, especially based on the distribution of this group, that (1) the actual origin is further west near Dutch Ruin and/or Powers Ranch and/or (2) that widespread

compositional similarity in Gila River alluvium exists from the West Fork area into eastern Arizona.

Table 4.3.2. Mahalanobis Distance (M.D.) probabilities for clay samples projected against Mimbres-05A.

I.D.	M.D.	Material	Site Name	Site No.	
BRE214	17.9	Clay	West Fork	LA 008675	
RLB075	3.4	Clay	Lake Roberts Vista	LA 071877	




Figure 4.3.16. Graduated symbol distribution map for Mimbres-05A pottery. Larger symbol sizes represent sites with proportionally higher percentages of pottery assigned to the Mimbres-05A group. Sites with fewer than 10 samples are represented by blue dots. Clays exceeding 1% probability of membership in this group are denoted by red stars.

Mimbres-05B contains 73 pottery samples of which about 74% originate from sites along the upper Gila River. Unlike Mimbres-05A which contained approximately 50% black-on-white painted pottery, black-on-white pottery (Mimbres B/W Style I, II, and III) comprises only 10% of the samples assigned to this group. The remaining samples are Alma (23%, n = 17), Reserve (16%, n = 12), Three Circle R/W (5%, n = 4), and a variety of corrugated, smudged, and undifferentiated brown ware pottery.

The distribution of Mimbres-05B pottery, by site, is depicted in Figure 4.3.17. A total of 13 clay samples exceed 1% probability of membership in this group (Table 4.3.3). A majority of these clays are from the West Fork and TJ Ruin locales along the upper Gila and membership probabilities for the samples is consistent with the pottery distribution for this group—hence it is evident that Mimbres-05B pottery production likely was centered around the West Fork site. However, there are multiple clays from Wind Mountain, and a few from the Lower and Middle Mimbres Valley that also exceed 1% probability of membership in this group. One sample—a clay from Quaternary fan deposits—in the Middle Mimbres Valley (BAS246)—exceeds 31% probability of membership in this group and this membership probability is higher than any of the clays from the West Fork locale. In this particular case, I argue that Mimbres-05B is clearly an Upper Gila River production given the distribution of pottery and the clays. The high probability associated with clay sample BAS246 (and the others), however, raises the question of what exactly is the chemical variability of clays in the greater Mimbres region and whether or not a single clay sample with high (or even moderate) membership probabilities is sufficient for linking ceramic compositional groups to specific geographic locales within this region.




Figure 4.3.17. Graduated symbol distribution map for Mimbres-05B pottery. Larger symbol sizes represent sites with proportionally higher percentages of pottery assigned to the Mimbres-05B group. Sites with fewer than 10 samples are represented by blue dots. Clays exceeding 1% probability of membership in this group are denoted by red stars.

Table 4.3.3. Mahalanobis Distance (M.D.) probabilities for clay samples projected against Mimbres-05B.

I.D.	M.D.	Material	Site Name	Site No.
BAS226	1.2	Clay sample (fired)	Wind Mountain	LA 127260
BAS227	2.0	Clay sample (fired)	Wind Mountain	LA 127260
BAS228	1.2	Clay sample (fired)	Wind Mountain	LA 127260
BAS229	3.4	Clay sample (fired)	Wind Mountain	LA 127260
BAS246	31.6	Clay, Quaternary fan deposits	Galaz Locality	N/A
BAS249	3.3	Clay, tuffaceous sandstone	Galaz Locality	N/A
BRE145	21.2	Clay Sample	West Fork	LA 008675
BRE148	2.0	Clay Sample	West Fork	LA 008675
BRE214	11.6	Clay Sample	West Fork	LA 008675
BRE220	1.7	Clay Sample	West Fork	LA 008675
BRE221	1.8	Clay Sample	West Fork	LA 008675
BRE223	8.9	Clay Sample	TJ Ruin Locality	N/A
OT047	1.7	Clay Sample	Old Town	LA 001113

Mimbres-05C consists of 4 Mimbres corrugated jars from the Gobernadora site in the Jornada region (Figure 4.3.18). This compositional group is unique to the Gobernadora site. It would, however, suggest that at least some Mimbres-style corrugated pottery was produced in the Jornada region. Another possibility is that this group originates somewhere else, maybe the Silver City area, and that this is simply sampling bias given that there are almost no analyzed samples from the Silver City area which was fairly densely populated. Additionally, few samples have analyzed from the greater Burro Mountains which also was densely populated and heavily wooded and that the distribution may reflect some unrecognized trading relationship between people at Gobernadora and those in the production area.




Figure 4.3.18. Map showing the location of the Gobernadora site which is the only site containing pottery assigned to Mimbres-05C.

Mimbres-09 is comprised of 21 samples. Mimbres B/W Style III pottery consists of 73% of the sample (n = 16); the remaining samples include one Mimbres B/W Style I, 2 Style II, and 2 Style II/III ceramics. The distribution of Mimbres-09 pottery, by site, is depicted in Figure 4.3.19. Based on the distribution of pottery assigned to this group it appears that production may be centered near the XSX and Main Diamond B sites along the upper Gila River. There are no clays that confidently can be attributed to this group.




Figure 4.3.19. Graduated symbol distribution map for Mimbres-09 pottery. Larger symbol sizes represent sites with proportionally higher percentages of pottery assigned to the Mimbres-09 group. Sites with fewer than 10 samples are represented by blue dots.

Macro Group B-2 Compositional Groups

Macro Group B-2 compositional groups include Mimbres-02A, Mimbres-02B, Mimbres-02C, Mimbres-08, and Mimbres-11.

Mimbres-02A is among the most widely distributed of all the Mimbres pottery groups and contains about 245 specimens. It occurs in high abundance at sites in the lower and middle Mimbres Valley, and pottery assigned to this group is the most common of the Mimbres Valley produced pottery found in sites throughout the Jornada region.

Additionally, Mimbres pottery assigned to this group is found at sites in Mexican ca. 350 km south of El Paso, Texas as well as sites, such as San Simon Wash located approximately 130 km southwest of Tucson, Arizona (or ca. 400 km from the Mimbres Valley). Chemically, this group is as distinct as Mimbres groups 1 and 3. Schriever examined a single sherd assigned to this group. He states:

The single sherd in this group contains altered rhyolite and differs from most other samples primarily in having a dominant population of more potassic alkali feldspars. The rocks and minerals in this sherd probably derive from the type of magma that gives rise to porpheric copper alteration-George Morgan personal communication 2008. (Schriever 2008:324).

The distribution of Mimbres-02A pottery, by site, is depicted in Figure 4.3.20. There are no clays that confidently can be attributed to this group, and based on the distribution of pottery it appears that the production site for this pottery is Swarts. Interestingly, very little pottery

assigned to this group is moving north up the Mimbres Valley; but it is found in large proportions at sites in the lower Mimbres Valley and is well represented at sites in the Jornada region.




Figure 4.3.20. Graduated symbol distribution map for Mimbres-02A pottery. Larger symbol sizes represent sites with proportionally higher percentages of pottery assigned to the Mimbres-02A group. Sites with fewer than 10 samples are represented by blue dots. Not shown are distant sites in southern Arizona, Texas, and Mexico.

Mimbres-02B is a small but well-defined compositional group represented by 20 sherds/vessels from 10 sites. All but 5 of the samples are classified as Mimbres B/W Style III; the remaining samples are classified as Mimbres B/W Style indeterminate and it is suspected that these samples also are Mimbres B/W Style III pottery. Chemically, this group is virtually identical to Mimbres-02A, with the exception that pottery assigned to this group has higher correlated cesium and rubidium concentrations.

The distribution of Mimbres-02B pottery, by site, is depicted in Figure 4.3.21. There are no clays that confidently can be attributed to this group, and based on the distribution of pottery and its similarity with Mimbres-02A, it appears that the production site for this pottery is Swarts.



Figure 4.3.21. Graduated symbol distribution map for Mimbres-02B pottery. Larger symbol sizes represent sites with proportionally higher percentages of pottery assigned to the Mimbres-02B group.

Mimbres-02C is a small but well-defined compositional group represented by 10 sherds/vessels from 8 sites. All but 2 of the samples are classified as Mimbres B/W Style III; the remaining samples are classified as Mimbres B/W Style indeterminate and it is suspected that they also are Style III pottery. Chemically, this group is virtually identical to Mimbres-02A, but with lower concentrations of first row transition metals (e.g., Sc, Ti, V, Cr, Fe) and slightly higher thorium.

The distribution of Mimbres-02C pottery, by site, is depicted in Figure 4.3.22. There are no clays that confidently can be attributed to this group, and based on the distribution of pottery and its compositional similarity with Mimbres-02A, it appears that the production site for this pottery is Swarts.




Figure 4.3.22. Graduated symbol distribution map for Mimbres-02C pottery. Larger symbol sizes represent sites with proportionally higher percentages of pottery assigned to the Mimbres-02C group.

Mimbres-08 contains 85 samples from 27 sites. The distribution of this pottery primarily is confined to the Mimbres Valley. It occurs in highest abundance at sites in the upper Mimbres Valley, but it is widely distributed throughout the Mimbres Valley and adjacent areas. More than 90% of the pottery (n = 77) is Mimbres B/W Style III; 2 are Mimbres B/W Style indeterminate, one is Mimbres corrugated, 2 are Mimbres Polychrome, and 3 are classified as Mimbres B/W Style III. Like the Mimbres-02 groups, Mimbres-08 appears to represent late Mimbres pottery production. Schriever examined a single sherd (BAS148) assigned to this group. He notes the temper contains all rhyolites—some of which are pumice, some very potassic, and some altered with recrystallized quartz and/or exsolving alkali feldspar and/or oxides (Schriever 2008:315).

The distribution of Mimbres-08 pottery, by site, is depicted in Figure 4.3.23. There are no clays that confidently can be attributed to this group, and based on the distribution of pottery assigned to this group it appears that the production site for this group is in the upper Mimbres Valley, probably at the Mattocks site.




Figure 4.3.23. Graduated symbol distribution map for Mimbres-08 pottery. Larger symbol sizes represent sites with proportionally higher percentages of pottery assigned to the Mimbres-08 group. Sites with fewer than 10 samples are represented by blue dots.

Mimbres-11 is represented by 84 samples from 27 sites. The distribution of this pottery primarily is confined to the Mimbres Valley. It occurs in highest abundance at sites in the Middle Mimbres Valley but is widely distributed throughout the Mimbres Valley and adjacent areas. Approximately 70% of the pottery (n = 59) is classified as Mimbres B/W Style III; four samples are Mimbres polychrome, 5 are Mimbres B/W Style indeterminate, 15 are Mimbres B/W Style II or II/III, and one sample is classified as Mimbres B/W Style I.

Schriever analyzed one sample assigned to Mimbres-11 by electron microprobe for his dissertation (Schriever 2008). He notes that the sample (BAS136) is:

Similar to BAS141. Although there are a few trachyite phonolite fragments, the vast majority of rock fragments are rhyolitic glass altering to microcrystaline quartz. Most glass fragments [are] highly altered. But enough are transitional allowing the link to be made between the glass and the high-silica microcrystaline quartz fragments in the sample. It is possible that the hypabyssal rhyolite, which is composed of quartz and k-feldspar, is also an alteration product of the glass. The matrix is very spongy and some grains appear melted into matrix, suggesting the sample was fired hot (Schriever 2008:314).

The distribution of Mimbres-11 pottery, by site, is depicted in Figure 4.3.24. There are no clays that confidently can be attributed to this group, and based on the distribution of pottery assigned to this group it appears that the production site for this group is in the middle-to-lower Mimbres Valley—probably between Perrault and Pruitt Ranch. The highest site sample percentage is at Perrault, but the current data

are insufficient for a more confident identification of production locale.

For the time being, I feel this group is best classified as a Middle

Mimbres Valley production at a yet to be determined site.




Figure 4.3.24. Graduated symbol distribution map for Mimbres-11 pottery. Larger symbol sizes represent sites with proportionally higher percentages of pottery assigned to the Mimbres-11 group. Sites with fewer than 10 samples are represented by blue dots.

4.4. Macro Group C

Macro Group C contains approximately 730 pottery and clay samples that are assigned to 15 compositional groups. This large group of pottery can be divided further into two subgroups designated Macro Group C-1 and Macro Group C-2 based on patterning observed in various element projects of the data, notably cesium concentrations (see Figure 4.4.1). Macro Group C-1 includes: Mimbres-21, Mimbres-22, Mimbres-23, Mimbres-24, Mimbres-27, and Mimbres-28. Macro Group C-2 includes Mimbres-41, Mimbres-42, Mimbres-43, Mimbres-44, Mimbres-46, Mimbres-47, Mimbres-48, Mimbres-49A, and Mimbres-49B. Approximately 20% (ca. 140 specimens) of the pottery in Macro Group C is unassigned. Figures 4.4.1-4.4.15 illustrates the group structure for Macro Group C. Mahalanobis distance probabilities for group membership and PCA scores are listed in Appendix C. Clay samples assigned to Macro Group C are shown in Figure 4.4.2. Clays assigned to specific compositional groups are discussed in the various sections below.

Figures 4.4.3–4.4.4 are plots derived from PCA of the variance-covariance matrix for Macro Group C-1 pottery which contains almost 400 specimens. Ellipses are drawn at the 90% confidence interval. Figure 4.4.3 illustrates the basic group structure for Macro Group C-1; unassigned C-1 pottery specimens are depicted in Figure 4.4.4.

A plot of scandium and cerium concentrations illustrates the basic group structure for pottery assigned to the Mimbres-21, Mimbres-22, and Mimbres-28 groups (Figure 4.4.5). Marginal separation exists between the Mimbres-21 and Mimbres-22 groups, but they are nonetheless sufficiently distinct. A plot of samarium and uranium readily

discriminates the Mimbres-23, Mimbres-24, and Mimbres-27 groups (Figure 4.4.6). Finally a plot of manganese and iron (Figure 4.4.7) shows discrimination of Mimbres-21 from Mimbres-24.

Identification of individual composition groups in Macro Group C-2 is somewhat more complicated than Macro Group C-1. As with the other Macro Groups, C-2 groups were identified using a combination of PCA and bivariate plots and validated using Mahalanobis distance probabilities. This resulted in the identification of 9 compositional groups within the 330+ specimen dataset. For purposes of illustrating groups assigned to Macro Group C-2, pottery is separated into three subgroups designated a, b, and c on the basis of inherent clustering in chromium concentrations (Figures 4.4.8-4.4.10). Macro Group C-2a contains four groups designated Mimbres-42, Mimbres-46, Mimbres-49A, and Mimbres-49B that are shown to be discreet in PCA and bivariate element projections (Figures 4.4.11-4.4.13). Group C-2b contains four groups: Mimbres-41, Mimbres-43, Mimbres-44, and Mimbres-47 that also can be shown to be discreet in multivariate space and in bivariate element projections (Figures 4.4.14-4.4.15). C-2c contains a single group designated Mimbres-48 (e.g., Figure 4.4.10).

In the sections below, I discuss individual compositional groups.




Figure 4.4.1. Bivariate plot of cesium and titanium base-10 logged concentrations showing separation of Macro Groups C-1 and C-2. Ellipses are drawn at the 90% confidence interval.




Figure 4.4.2. Bivariate plot of cesium and titanium base-10 logged concentrations showing Macro Group C clays projected against 90% confidence ellipses for groups C-1 and C-2.




Figure 4.4.3. Biplot of principal components 1 and 2 derived from PCA of the correlation matrix for Macro Group C-1 pottery. Ellipses are drawn at the 90% confidence interval.




Figure 4.4.4. Plot of principal components 1 and 2 derived from PCA of the correlation matrix for Macro Group C-1 pottery showing unassigned pottery specimens.




Figure 4.4.5. Bivariate plot of scandium and cerium base-10 logged concentrations showing Macro Group C-1 pottery groups Mimbres-21, -22, and -28. Ellipses are drawn at the 90% confidence interval.




Figure 4.4.6. Bivariate plot of samarium and uranium base-10 logged concentrations showing Macro Group C-1 pottery groups Mimbres-23, -24, and -27. Ellipses are drawn at the 90% confidence interval.




Figure 4.4.7. Bivariate plot of manganese and iron base-10 logged concentrations showing Macro Group C-1 pottery groups Mimbres-21 and Mimbres-24. Ellipses are drawn at the 90% confidence interval.




Figure 4.4.8. Bivariate plot of chromium and zirconium base-10 logged concentrations showing separation of Macro Group C-2 subgroups.

Ellipses are drawn at the 90% confidence interval.




Figure 4.4.9. Bivariate plot of chromium and zirconium base-10 logged concentrations showing unassigned specimens relative to Macro Group C-2 subgroups. Ellipses are drawn at the 90% confidence interval.




Figure 4.4.10. Bivariate plot of chromium and zirconium base-10 logged concentrations showing separation of Macro Group C-2 subgroups.

Ellipses are drawn at the 90% confidence interval.




Figure 4.4.11. Biplot of principal components 1 and 2 derived from PCA of the correlation matrix for Macro Group C-2a pottery. Ellipses are drawn at the 90% confidence interval.




Figure 4.4.12. Bivariate plot of europium and iron base-10 logged concentrations showing separation of Mimbres-46 and Mimbres-49B from Mimbres-42 and Mimbres-49A. Ellipses are drawn at the 90% confidence interval.




Figure 4.4.13. Bivariate plot of thorium and scandium base-10 logged concentrations showing separation of Mimbres-42 from Mimbres-49A.

Ellipses are drawn at the 90% confidence interval.




Figure 4.4.14. Biplot of principal components 1 and 2 derived from PCA of the variance-covariance matrix for Macro Group C-2b pottery. Ellipses are drawn at the 90% confidence interval.




Figure 4.4.15. Bivariate plot of manganese and scandium base-10 logged concentrations showing separation of Macro Group C-2b pottery. Ellipses are drawn at the 90% confidence interval.

Macro Group C-1 Compositional Groups

Mimbres-21 contains 182 samples from 41 sites. More than 53% of pottery assigned to this group is Mimbres Style III (n = 97) or Mimbres Polychrome (n = 1). Approximately 34% of pottery assigned to this group is Mimbres B/W Style II (n = 63). Mimbres B/W Style I comprises 5% of the sample (n = 11). One Three Circle R/W specimen (from XSX site) is assigned to this group. The remaining samples are Mimbres B/W style indeterminate (n = 4); Mimbres B/W style II/III (n = 4), or Mimbres B/W style I/II (n = 1).

On the basis of electron microprobe work, Schriever (2008:115) placed several samples assigned to this group (BAS120, 122, 124, and 204) into his "Zeolite" group. He describes most rock fragments as having a sedimentary appearance—composed primarily of crazed quartz with clay but often also containing authogenic albite crystals that have orthoclase inclusions with minor amounts of sodic tracyte, rhyolite, basalt, and trachy-andesite rock fragments (Schriever 2008:312).

The distribution of Mimbres-21 pottery, by site, is depicted in Figure 4.4.16. Based on the distribution of pottery assigned to this group it appears that the point of origin for pottery assigned to this group is the Woodrow site along the Gila River. A moderate amount of pottery from Woodrow occurs at the nearby Saige-McFarland site and at the Powers Ranch site further downstream. Minor amounts of pottery assigned to this group are distributed throughout the Mimbres area. There are no clays that confidently can be attributed to this group.




Figure 4.4.16. Graduated symbol distribution map for Mimbres-21 pottery. Larger symbol sizes represent sites with proportionally higher percentages of pottery assigned to the Mimbres-21 group. Sites with fewer than 10 samples are represented by blue dots.

Mimbres-22 contains 35 pottery samples from 16 sites. Mimbres B/W Style III represents 57% (n = 20) of the sample; 14% of the pottery Mimbres B/W Style II, and about 6% of the pottery is classified as Mimbres B/W style I. The remaining pottery (n=8) is classified as Cibola B/W or unslipped B/W. As discussed in the section on Mimbres-03 pottery, this pottery is an unslipped and has a light-colored paste in contrast to Mimbres which is a white-slipped brown ware.

The distribution of Mimbres-22 pottery, by site, is depicted in Figure 4.4.17. Based on the distribution of pottery assigned to this group it appears that the point of origin for pottery assigned to this group is clearly somewhere along the Gila River. Given that this composition group is so distinct from Mimbres-03 which represents pottery production in the Gila Forks area, and given the chemical similarity of this group to Mimbres-21 pottery (which is assumed to represent pottery production at the Woodrow site), it appears that this compositional group represents limited pottery production in the vicinity of the Saige-McFarland site.




Figure 4.4.17. Graduated symbol distribution map for Mimbres-22 pottery. Larger symbol sizes represent sites with proportionally higher percentages of pottery assigned to the Mimbres-22 group. Sites with fewer than 10 samples are represented by blue dots.

Mimbres-23 contains 30 pottery samples from 14 sites. This group is dominated by Mimbres Style III B/W pottery which represents 80% (n = 24) of the specimens assigned to this group. Mimbres Style B/W II pottery comprises 13% (n = 4) of the specimens; one sample is classified as Mimbres B/W Style II/III. Finally, one sample lacks descriptive information (from the Calderon site in Chihuahua, Mexico), but is assumed to be Mimbres B/W Style III pottery.

The distribution of Mimbres-23 pottery, by site, is depicted in Figure 4.4.18. Based on the distribution of pottery assigned to this group it appears that the point of origin for pottery assigned to this group is either the southern Rio Grande Valley or the Jornada region. Given that this compositional group is so distinct from other Jornada region compositional groups, it appears that the Rio Vista site is the production locale for this pottery. Interestingly this group is primarily found at sites in the Rio Grande and Jornada regions with no occurrence at sites in the Mimbres Valley.




Figure 4.4.18. Graduated symbol distribution map for Mimbres-23 pottery. Larger symbol sizes represent sites with proportionally higher percentages of pottery assigned to the Mimbres-23 group. Sites with fewer than 10 samples are represented by blue dots. One sample from the Calderon site in Chihuahua, Mexico (ca. 350 km south of El Paso, Texas) is not shown.

Mimbres-24 contains 74 pottery samples from 17 sites. This group is dominated by earlier ceramic types. Mogollon R/B accounts almost 38% (n = 28) of the specimens assigned to this group. Three Circle R/W accounts for almost 26% (n = 19) of the samples. Mimbres B/W Style I represents almost 18% (n = 13) of the pottery assigned to this group. There is one sample each of San Francisco Red, Alma Plain, and Mimbres B/W Style I/II; two each of Mimbres B/W Style II and Mimbres B/W Style indeterminate; and 7 Mimbres B/W Style III (ca. 9.5%).

On the basis of electron microprobe work, Schriever (2008:115) placed samples (e.g., BAS040, 041, 088, 090, 098, 162) assigned to this group into his "Mixed 2" volcanic rock group. He describes this group as having:

...very similar rock fragment and feldspar populations. All include rhyolite and trachyte/trachyandesite/trachy-basalt. The distinguishing trait of this group is that the samples include a normal rhyolite population and a very sodic rhyolite from which the albite in the sample derives. The differences in trachytic rock fragments among samples could relate to sampling errors and chemical variation in the source rock (Schriever 2008:336).

The distribution of Mimbres-24 pottery, by site, is depicted in Figure 4.4.19. Based on the distribution of pottery assigned to this group it appears that the point of origin for pottery assigned to this group the Wind Mountain site and/or adjacent vicinity. One item of interest is that none of the Mimbres B/W Style III sherds assigned to this group were found at sites in the Mimbres Valley—five are from sites along the Gila

River, one is from eastern Arizona, and one is from the Sapillo Creek area (Gatton Park).




Figure 4.4.19. Graduated symbol distribution map for Mimbres-24 pottery. Larger symbol sizes represent sites with proportionally higher percentages of pottery assigned to the Mimbres-24 group. Sites with fewer than 10 samples are represented by blue dots.

Mimbres-27 contains six Mimbres B/W samples from two sites in the Cedar Mountains—Otto and the Snake (n = 5) and the adjacent Indian Wells Field Site (n = 1). The group contains two samples each of Mimbres B/W Style I, II, and III. It is assumed that this compositional group represents local Mimbres pottery production in the Cedar Mountains. Figure 4.4.20 shows the locations of the sites associated with this group.

Mimbres-28 contains four Mimbres B/W Style I specimens from the Victorio site in Rio Alamosa drainage. This chemical signature is unique to the Victorio site, but is different from other Rio Alamosa pottery. It is currently assumed to be an import from an unknown area. Figure 4.4.20 shows the locations of the Victorio site.




Figure 4.4.20. Map showing the locations of sites associated with Mimbres-27 and Mimbres-28 compositional groups.

Macro Group C-2 Compositional Groups

Mimbres-41 contains 47 pottery and six clay samples from 11 sites. Ceramic types assigned to this group are diverse. Mimbres B/W style II accounts for about 40% of the sample (n = 19). Mimbres B/W style II represents about 15% of the sample (n = 7). Mimbres B/W style III is present, but only accounts for about 11% of the sample. The remaining type include Alma (n = 5), Three Circle (n = 4), Reserve (n = 1), San Francisco Red (n = 2), and other miscellaneous ceramic types (n = 6). Six clay samples from NAN that were analyzed for Eleanor Dahlin's M.A. thesis have high probabilities of membership in this group.

On the basis of electron microprobe work, Schriever (2008:115) placed samples (BAS179 and BAS210) in his "Rhyolite 2" group. He describes this group as having:

Dominant feldspar populations Kf 60-70+orthoclase, An 10-30. The sherds in this group contain primarily rhyolite fragments with a few presumably altered volcanic rock fragments that have the composition of rhyolite but which include An 50-70 plagioclase. Oddly, the plagioclase in both samples are well preserved while the many of the alkali feldspars exhibit alteration or replacement by albite (Schriever 2008:325).

The distribution of Mimbres-41 pottery, by site, is depicted in Figure 4.4.21. Fortunately clay samples from NAN can confidently be assigned to this group—otherwise it would appear that Old Town, NAN, and Harris have more-or-less equal chances of being the point of origin for this group.

Table 4.4.1. Mahalanobis Distance (M.D.) probabilities for clay samples projected against Mimbres-41.

I.D.	M.D.	Material	Site Name	Site No.
ED-083	39.26	Clay	NAN	LA 002465
ED-084	8.56	Clay	NAN	LA 002465
ED-085	5.80	Clay	NAN	LA 002465
ED-086	3.39	Clay	NAN	LA 002465
ED-087	18.72	Clay	NAN	LA 002465
ED-088	3.94	Clay	NAN	LA 002465




Figure 4.4.21. Graduated symbol distribution map for Mimbres-41 pottery. Larger symbol sizes represent sites with proportionally higher percentages of pottery assigned to the Mimbres-41 group. Sites with fewer than 10 samples are represented by blue dots. Clay samples from NAN are denoted by the red star.

Mimbres-42 contains 18 pottery samples from 11 sites. Mimbres B/W style III comprises 50% of the pottery assigned to this group. There are three samples each of Mimbres B/W style II, Mimbres B/W style II/III, and Mimbres B/W style indeterminate.

The distribution of Mimbres-42 pottery, by site, is depicted in Figure 4.4.22. Although the Flying Fish site appears to be the likely point of origin for this group, overall the percentages of pottery from each site are fairly low. Given that the majority of pottery assigned to this group is clustered at sites in the Mimbres Valley, it seems probable that this group represents a fairly restricted Mimbres B/W pottery production at a yet to be determined site in the Lower Mimbres Valley.




Figure 4.4.22. Graduated symbol distribution map for Mimbres-42 pottery. Larger symbol sizes represent sites with proportionally higher percentages of pottery assigned to the Mimbres-42 group. Sites with fewer than 10 samples are represented by blue dots.

Mimbres-43 is comprised of three Mimbres Polychrome samples from the Treasure Hill site and one Mimbres B/W Style III sample from Cameron Creek. Both sites are geographically close to one another. Although there are no clays associated with this compositional, it is one of two groups that are assumed to represent pottery production (the other being Mimbres-44). The locations of the two sites are shown in Figure 4.4.23 which shows the distribution of pottery assigned to Mimbres-44.

Mimbres-44 is comprised of nine specimens from five sites.

Ceramic types include: two Mimbres Polychrome, three Mimbres B/W

Style III, one Mimbres B/W Style II, two Mimbres B/W Style I, and one

Mimbres B/W Style indeterminate. The distribution of Mimbres-44

pottery, by site, is depicted in Figure 4.4.23. This relatively small group is assumed to represent limited pottery production at or near the Cameron Creek site.




Figure 4.4.23. Graduated symbol distribution map for Mimbres-44 pottery. Larger symbol sizes represent sites with proportionally higher percentages of pottery assigned to the Mimbres-44 group.

<u>Mimbres-46</u> is comprised of four specimens from three sites—two samples from Old Town and one each from Galaz and the Indian Wells Field Site. Ceramic types assigned to this group include Three Circle R/W (n = 3) and Mogollon R/B. Given the low number of samples assigned to this group, the production area is uncertain, but Old Town seems to be the most likely point of origin.

Mimbres-47 contains 33 pottery specimens from 12 sites. The group is dominated by utilitarian ceramics, such as corrugated (n = 18), Alma Rough and Plain (n = 9), undifferentiated brown ware (n = 2), and one undifferentiated Chihuahuan "indented" sherd. Only three specimens have painted designs—two of which are Mimbres B/W Style I the remaining sample is classified as Three Circle R/W.

The distribution of Mimbres-47 pottery, by site, is depicted in Figure 4.4.24. Although the Ojasen site appears to be well represented, it is unlikely that the Jornada area is the point of origin for this group given that the chemical composition is entirely different from any Jornada area groups (e.g., Macro Group D) and specifically the Ojasen area. Based on types represented, mostly Mimbres Corrugated, it is doubtful that the Jornada is the production area. Interestingly the Mimbres Corrugated specimens in this group are from NAN, Eby, Pruitt, and Old Town, plus Ojasen, and not from higher up the Mimbres valley. It seems likely that this group reflects corrugated pottery production at NAN and looks chemically similar to Mimbres-41 because of the use of different tempers for these vessels which predominantly used for cooking.




Figure 4.4.24. Graduated symbol distribution map for Mimbres-47 pottery. Larger symbol sizes represent sites with proportionally higher percentages of pottery assigned to the Mimbres-47 group. Sites with fewer than 10 samples are represented by blue dots.

Mimbres-48 contains seven samples from two sites in the Deming area—LA 059652 and the adjacent site of LA 129562 (refer to Figure 4.4.24 for location of LA 059652). Six of the samples are classified as Alma and the remaining sample is classified as Mimbres Red (or more appropriately San Francisco Red). The production locale for this group is uncertain. Given that Mimbres-07a and Mimbres-07b have high probability of originating from these two sites, it seems likely that this group represents imports to the Deming area from a yet to be identified area.

Mimbres-49A contains 133 samples and 8 clays from 37 sites.

Ceramic types assigned to this group range from the earliest part of the Mimbres-Mogollon sequence up through the post Classic Period. Most pottery, ca. 35% (n = 46) assigned to this group is Classified as Mimbres B/W Style III. Mimbres B/W Style I and Mimbres B/W Style II comprise about 22% of the sample (11 specimens of each). Other types include Alma and Three Circle, (n = 9), Gila Polychrome, Playas, Reserve, and Tularosa and other miscellaneous type (a complete list is in Appendix E). Of interest here is that this group includes quite a variety of types that span the entire Mimbres-Mogollon sequence.

On the basis of electron microprobe work, Schriever (2008:115) placed samples (BAS121 and BAS169) in his "Mixed 5" volcanic rock group. He describes this group as having:

...similar rock fragment and feldspar populations. Rhyolite most prevalent rock type. But, many dacite to trachytes also present. Also, there are many altered volcanic rock fragments, some unidentifiable (Schriever 2008:325).

The distribution of Mimbres-49A pottery, by site, is depicted in Figure 4.4.25. It is clear that the highest distribution of pottery assigned to this group are the upper Mimbres Valley sites of Elk Ridge, Mitchell, Harris, Ranger Station, and Lake Roberts Vista (just north of the Mimbres Valley in the Sapillo Creek area). Four clay samples from the Elk Ridge site also have high probability of membership in the group indicating that the probable point of origin for this group is the Upper Mimbres Valley at or near the Elk Ridge site. Additionally, given that this is the only group that appears to be associated with pottery production at Elk Ridge, it is assumed that this group represents, in part, the Elk Ridge groups identified in previous INAA studies (see Chapter 2). Unfortunately, as clear cut as this may seem there are two clay samples from NAN and two clays from the vicinity of Old Town that also have high probabilities of membership in this group (Table 4.4.2).

An exhaustive effort was made to subdivide Mimbres 49A so that (1) the non-Elk Ridge clays could be shown to be different or (2) that there were indeed two discreet groups present with one representing pottery production in the Upper Valley and a second group that would represent pottery production elsewhere (e.g., near NAN or Old Town). Unfortunately it is not possible to further subdivide this group. I am confident that most pottery assigned to this group does in fact represent pottery production in the Upper Mimbres Valley. However, given that a few clays from NAN and the vicinity of Old Town have high probabilities of membership, it seems likely that a few samples assigned to this group may derive from other parts of the Mimbres Valley.

Table 4.4.2. Mahalanobis Distance (M.D.) probabilities for clay samples projected against Mimbres-49A.

1.1	D. M	.D. Ma	terial	Site Na	ame	Site No.
НМ	096 83	.39	Clay	Elk Ri	dge	LA 078963
НМ	097 86	.25	Clay	Elk Ri	dge	LA 078963
НМ	098 87	.86	Clay	Elk Ri	dge	LA 078963
НМ	099 96	.61	Clay	Elk Ri	dge	LA 078963
ОТ	165 83	.43	Clay N,	/A (near O	ld Town)	N/A
ОТ	166 59	.29	Clay N,	/A (near O	ld Town)	N/A
RLB	078 23	.46	Clay	NAN	N	LA 002465
RLB	083 18	.02	Clay	NAN	N	LA 002465




Figure 4.4.25. Graduated symbol distribution map for Mimbres-49A pottery. Larger symbol sizes represent sites with proportionally higher percentages of pottery assigned to the Mimbres-49A group. Sites with fewer than 10 samples are represented by blue dots. Clay sample locations are designated by red stars.

<u>Mimbres-49B</u> is represented by five sherds from five different sites. The group includes one Mimbres Corrugated, one Alma Plain, one Mimbres B/W Style III, and two Mimbres B/W Style I. From a chemical perspective, this group is very similar to Mimbres-49A, but has slightly higher rare-earth-element concentrations. Given the chemical similarity to the Mimbres-49A group, it is probable that this group also has origins in the upper Mimbres Valley at or near the Elk Ridge Site. Figure 4.4.26 shows the site locations for pottery assigned to this group.




Figure 4.4.26. Map showing site locations for pottery assigned to Mimbres-49B.

4.5. Macro Group D

Macro Group D contains more than 800 pottery and clay samples that are assigned to more than 15 compositional groups—the three largest of which I refer to as the EI Paso Core (n>480), EI Paso-2 (n = 45), and EI Paso Loop 375 (n = 81). More than 95% of pottery samples assigned to this group are classified as Jornada Brownwares—primarily EI Paso Polychromes and bichromes. Samples in this group form the basis of a long-term research project coordinated, in large part, by Myles Miller and colleagues. Because these ceramics are only indirectly related to the Mimbres series ceramics discussed in earlier sections and given that Miller has yet to publish these data (publication is in progress), the Jornada pottery groups are not discussed in detail in this dissertation. Furthermore, it is important to underscore that my group designations have no bearing on group names that Miller may be using to describe these groups and that it is possible that the EI Paso core group may actually represent 2 or more discreet compositional groups.

The three largest Jornada compositional groups, El Paso Core, El Paso-2, and El Paso Loop 375 represent pottery production in the immediate vicinity of El Paso, Texas. Jornada pottery assigned to El Paso Core and El Paso-2 groups are widely distributed throughout the entire Jornada region, the Mimbres Valley, and adjacent regions of west Texas, southwest New Mexico, southeastern Arizona, Chihuahua (Mexico). In contrast, pottery assigned to the El Paso Loop 375 group is very geographically restricted and only known to occur at a handful of sites north and east of downtown El Paso. The majority of samples assigned to this group (ca. 90%) originate from a cluster of sites about 15 km NE of downtown El Paso that were impacted by of construction of Loop 375 around the northeast side of El Paso (see Dering et al. 2001). Ceramics

assigned to this group are distinct chemically, i.e., Shafer's (2001) INAA Cluster 2 and by petrography, i.e., Robinson's (2001) Petrographic Group 1. From a purely chemical perspective this group is very distinct from other Jornada groups in that it has higher relative concentrations of lutetium, ytterbium, and dysprosium.

Of the several thousand Mimbres-series ceramics analyzed by INAA, only one sample can be shown unequivocally to have been produced in the vicinity of El Paso, Texas (but recall that Mimbres Group 13 also is suspected to be a Jornada-derived group). This sample, designated ANIO46, is a Mimbres B/W Style Indeterminate from site 41EPO1676. It has a Mahalanobis distance probability of ca. 80% and consistently plots in multivariate and bivariate projections of the data. Figure 4.5.1 is a bivariate plot showing Mimbres B/W sample ANIO46 relative to the El Paso Core, El Paso-2, and El Paso Loop 375 groups. Figure 4.5.2 is a map showing site locations for pottery assigned to the El Paso Loop 375 group.

Mahalanobis distance probabilities for Macro Group D pottery are provided in Appendix D.




Figure 4.5.1. Bivariate plot of chromium and ytterbium base-10 logged concentrations showing Mimbres B/W specimen ANI046 relative to the El Paso Core, El Paso-2, and El Paso Loop 375 groups. Ellipses are drawn at the 90% confidence interval.




Figure 4.5.2. Map showing site locations for pottery assigned to the El Paso Loop 375 group (blue dots) and the location of site 41EP01676 from which Mimbres B/W specimen ANI046 (red star) originates.

Chapter 5

Discussion of Results and Conclusions

Introduction

As shown in detail in Chapter 4, identifying the production of Mimbres-series pottery is much more complex than previous studies have suggested (see Chapter 2). With the benefit of this large NAA dataset that includes approximately 2900 Mimbres-Mogollon and related ceramics and about 160 clays and an additional 600 ceramics from the Jornada-Mogollon region we begin to observe a much more detailed picture of Mimbres pottery production and its distribution across the landscape. However, simply identifying and statistically validating large numbers of compositional groups and/or demonstrating that a given compositional group occurs across a broad geographic area is only part of the process. In order to be informative and useful to the archaeologist, these groups must be linked to production sites or production zones in order to provide information that can be used to reconstruct prehistoric social processes. In the previous chapter, I outlined how compositional groups were constructed for this study, provided figures showing the distribution of pottery assigned to these groups, and offered suggestions as to where these groups likely originated given their distribution and where possible, linking groups to geologic clay samples. In the following sections, I summarize these compositional groups, discuss some of the broad-scale temporal changes and implications that are observed, and provide recommendations and thoughts for future research directions.

Summary of Compositional Groups

Table 5.1 provides a summary of the compositional groups discussed in the previous chapter. This table includes the presumed point of origin for these groups, the primary ceramic type(s) associated with individual compositional groups, and whether or not clay samples can be assigned to these groups. Given that most groups cannot be firmly linked to geologic clays, the attribution of compositional groups to specific sites is based in large part on information detailed in the pottery distribution maps discussed in Chapter 4. I attempt to qualify the degree of certainty to which compositional groups are linked to specific sites in the table column "Confidence" using four categories. High confidence indicates relative certainty that a given compositional group originated from a given site(s). Medium confidence indicates the compositional group probably originated from the designated, site(s) but we are less certain about this. In the case of a few groups we are unsure about their origin, but there is some suggestion that the pottery may have been produced at the site indicated in the table—these groups are designated as low confidence. Finally, "unknown" refers to compositional groups for which we currently have no idea as to where they were produced.

In Figure 5.2, I map the distribution of the compositional groups identified in this study. The boundaries of these groups are varied and reflect general ideas about where pottery assigned to specific groups was produced. These boundaries are admittedly subjective, but are based in large part on data discussed in Chapter 4. Additional research involving the analyses of raw materials will help to refine these boundaries further. Nonetheless, I believe that in general this map reflects a reasonably accurate scenario for pottery production across the Mimbres

region. Figure 5.3, is similar to Figure 5.2, but focusses on Mimbres Valley pottery groups.



Figure 5.1. Example of Classic Period Mimbres Polychrome bowl decorated with a macaw motif. Image courtesy of the Smithsonian Institution.

Table 5. 1. Summary of compositional Groups, presumed production locale, and ceramic types associated with each group.

Chem. Group	Macro	Origin	Ceramic Types	Confidence	Clays
Mimbres-01	Α	Rio Grande Valley	Mimbres B/W Style III	high	No
Mimbres-02A	B-2	Mimbres Valley (Middle)-Swarts	Mimbres B/W Style III	high	No
Mimbres-02B	B-2	Mimbres Valley (Middle)-Swarts	Mimbres B/W Style III	high	No
Mimbres-02C	B-2	Mimbres Valley (Middle)-Swarts	Mimbres B/W Style III	high	No
Mimbres-03	Α	Gila River Forks	Mimbres design w/"Cibola" Paste	high	No
Mimbres-04A	B-1	Mimbres Valley (Upper)-Galaz	Mimbres B/W Style III	high	No
Mimbres-04B	B-1	Mimbres Valley (Middle)-Perrault	Mimbres B/W Style III	medium	No
Mimbres-04C	B-1	Mimbres Valley (Upper)-Harris/ Gonzales	Mimbres B/W Style II and Earlier	high	No
Mimbres-05A	B-1	Gila River Valley- Powers Ranch to Gila Cliff	Mimbres B/W Style I-III and Post Classic types	medium	Yes
Mimbres-05B	B-1	Gila River Forks (TJ Ruin area)	Alma, Reserve, and plain/corrugated	medium	Yes
Mimbres-05C	B-1	Uncertain (could be Jornada, but seems unlikely)	Corrugated	unknown	No
Mimbres-07A	А	Deming Plain, LA 59652 area	Alma	medium	No
Mimbres-07B	A	Deming Plain, LA 59652 area	Alma	medium	No
Mimbres-08	B-2	Mimbres Valley (Upper)-Mattocks	Mimbres B/W Style III	medium	No
Mimbres-09	B-1	Gila River Forks (XSX or Main Diamond B)	Mimbres B/W Style III	low	No
Mimbres-10	A	Burro Mountains- Power Site area	Corrugated and Alma	medium	Yes
Mimbres-11	B-2	Mimbres Valley (Middle)-unknown site	Mimbres B/W Style III	medium	No
Mimbres-13	A	Rio Grande Valley	Mimbres B/W Style III	medium	No
Mimbres-21	C-1	Gila River Valley- Woodrow	Mimbres B/W Style III and II	high	No

Table 5. 1 (continued). Summary of compositional Groups, presumed production locale, and ceramic types associated with each group.

Chem. Group	Macro	Origin	Ceramic Types	Confidence	Clays
Mimbres-22	C-1	Gila River Valley-Saige- McFarland	Mimbres B/W Style III and II	medium	No
Mimbres-23	C-1	Rio Grande Valley-Rio Vista	Mimbres B/W Style III	medium	No
Mimbres-24	C-1	Burro Mountains/Gila River Valley-Wind Mountain	Mogollon R/B, Three Circle, Mimbres B/W Style I	medium	Yes
Mimbres-27	C-1	Cedar Mountains-Otto and the Snake	Mimbres B/W Style I-III	medium	No
Mimbres-28	C-1	Uncertain	Mimbres B/W Style I	unknown	No
Mimbres-41	C-2b	Mimbres Valley (Middle)-NAN	Mimbres B/W Style II and I	high	Yes
Mimbres-42	C-2a	Mimbres Valley (Lower or Middle)-unknown	Mimbres B/W Style III and II	unknown	No
Mimbres-43	C-2b	Arenas Valley-Treasure Hill	Mimbres B/W Style III	medium	No
Mimbres-44	C-2b	Cameron Creek- Cameron Creek	Mimbres B/W Style III	low	No
Mimbres-46	C-2a	Mimbres Valley (Lower) Old Town?	Mogollon R/B and Three Circle	low	No
Mimbres-47	C-2b	Mimbres Valley (Middle)-NAN	Corrugated and Alma	medium	No
Mimbres-48	C-2c	Deming Plain, LA 59652 area	Alma	medium	No
Mimbres-49A	C-2a	Mimbres Valley (Upper)-Elk Ridge	Entire ceramic sequence	high	Yes
Mimbres-49B	C-2a	Mimbres Valley (Upper)-Elk Ridge	Mimbres B/W Style I	medium	No
El Paso Core	D	Jornada-El Paso vicinity	El Paso and Jornada Brownwares	high	No
El Paso Group- 2	D	Jornada-El Paso vicinity	El Paso and Jornada Brownwares	high	No
El Paso Loop 375	D	Jornada-El Paso vicinity northeast	El Paso and Jornada Brownwares	high	No




Figure 5.2. Map showing the distribution of compositional groups identified in this study relative to their assumed production areas. See Figure 5.3 for an enlarged view of Mimbres Valley production locales.




Figure 5.3. Map showing the distribution of Mimbres Valley and Arenas

Valley (Treasure Hill) and Cameron Creek compositional groups identified in this study relative to their production areas.

Broad Scale Temporal Changes in Pottery Production

One of the interesting findings regarding the Mimbres INAA dataset involves the examination of broad temporal changes in pottery production for the compositional groups described in the preceding chapter. This type of examination is something that would not been possible with the earlier INAA projects given the relatively small numbers of samples analyzed for any given project and the general focus on Classic period ceramics (e.g., Mimbres B/W Style III).

For the purposes of this discussion, the examination of temporal change among the compositional groups is directed toward the Mimbres series painted ceramics. Specifically I focus on pottery classified as Three Circle R/W (n = 52), Mimbres B/W Style I (n = 180), Mimbres B/W Style II (n = 284), and Mimbres B/W Style III (n = 1467). No pottery classified as Mimbres B/W Style I/II or Mimbres B/W Style II/III is included in this particular examination because of their low occurrence and the fact that many archaeologists do not use these transitional groups when assigning pottery types. Finally, ceramics classified as Mimbres Polychrome are included in counts for Mimbres B/W Style III.

Typically when one might examine temporal change, frequencies would be calculated by taking, for example, Mimbres Group 1 and calculating the percentage distribution of Three Circle R/W and Mimbres B/W Styles I–III within that specific group. However, because the sample is so heavily biased toward Mimbres Style III, there would almost always appear to be an increase through time because of disproportionally greater sampling for the later ceramic types. An alternative approach for calculating frequencies was therefore employed. I took each of the four ceramic types (Three Circle R/W and Mimbres B/W Style I–III) and

calculated independently the percentages of each type (e.g., Style I) assigned to each compositional group (unassigned specimens of each type also were included in the calculations). Smaller compositional groups (e.g., Mimbres-02B, 02C, 23, etc.) either have too few samples or are exclusively Mimbres B/W Style III and therefore are not considered herein. Likewise, unassigned samples are uninformative given that we have no means of knowing where they were produced or how many discreet production locales are represented among the unassigned samples. Therefore, only the 14 major groups containing higher quantities of Mimbres painted pottery (Mimbres-01, 02A, 4A, 4B, 4C, 5A, 8, 11, 21, 24, and 49A) are discussed in this section.

A bar chart showing frequencies of Three Circle R/W and Mimbres B/W Styles I–III for the 14 largest compositional groups containing these pottery types is provided below (Figure 5.4) Data used to create this Figure are provided in Table 5.2. Based on the data presented in Table 5.2 and Figure 5.4, it is apparent that clear temporal changes in pottery production occur. These changes are discussed below.

Table 5.2. Counts and frequencies for Three Circle R/W and Mimbres B/W Styles I–III pottery assigned to the 14 largest compositional groups containing these types. Unassigned specimens and samples assigned to other groups are included in the calculations.

Chemical Group	Three Ci	rcle R/W	Mimbres B	/W Style I	Mimbres B	/W Style II	Mimbres B/	W Style III
	Count	%	Count	%	Count	%	Count	%
(1) EMAP	-	-	-	-	7	2.5	186	12.7
(2A) Swarts	-	-	1	0.6	11	3.9	201	14.3
(3) Gila Forks	-	-	9	5.0	10	3.5	12	0.8
(4A) Galaz	1	1.9	9	5.0	23	8.1	209	14.2
(4B) Perrault	1	1.9	4	2.2	2	0.7	106	7.2
(4C) Harris	7	13.5	34	18.9	20	7.0	23	1.6
(5A) Gila/Cliff	3	5.8	13	7.2	12	4.2	26	1.8
(8) Mattocks	-	-	-	-	2	0.7	78	5.3
(11) Unknown	-	-	-	-	9	3.2	60	4.1
(21) Woodrow	1	1.9	10	5.6	61	21.5	97	6.6
(22) Saige-McFarland	-	-	2	1.1	5	1.8	20	1.4
(24) Wind Mountain	19	36.5	13	7.2	2	0.7	7	0.5
(41) NAN	1	1.9	7	3.9	18	6.3	5	0.3
(49A) Elk Ridge	2	3.8	15	8.3	14	4.9	46	3.1
Other Group	8	15.4	17	9.4	13	4.6	84	5.7
Unassigned	9	17.3	46	25.6	<i>75</i>	26.4	307	20.9
Total	52	100.0	180	100.0	284	100.0	1467	100.5




Figure 5.4. Bar chart showing frequencies of Three Circle R/W and Mimbres B/W Styles I–III for the 14 largest compositional groups containing these pottery types.

For Mimbres-01, which is assumed to represent the manufacture of pottery in the Eastern Mimbres area, production seems to begin during the Late Three Circle phase (ca. A.D. 900–1000) and dramatically increases during the Classic and Mimbres Reorganization Periods (ca. A.D. 1000 to the early 1200s). The significant increase observed for Mimbres B/W Style III pottery is in part a consequence of sampling bias in the larger data set. Specifically, all Mimbres B/W pottery analyzed from the Eastern Mimbres sites was Style III pottery and no earlier pottery types have been analyzed from sites in this area.

Archaeological data for the Eastern Mimbres area, however, supports the observed increase in pottery production through time. Hegmon et al. (1998) have argued that as the Mimbres Valley began to be depopulated during the late Classic Period, there was an influx of people into the Eastern Mimbres area (cf. Shafer 2003). Likewise, we know from archaeological research in the Eastern Mimbres area (Nelson 1984, Karen Schollmeyer personal communication to D. Creel) that evidence for earlier occupations exists below the Classic period Mimbres sites, but not at the density that is observed in the Mimbres Valley and elsewhere. Hence in this example, the archaeological data and the changes observed in the frequencies derived from the compositional data are in agreement.

Although no Mimbres B/W Style II pottery has been analyzed from sites in the Eastern Mimbres area, 7 examples of this pottery type are assigned to the Mimbres-01 group. These samples originate from the San Andres Mountains to the east (n = 2), the Lower Rio Grande (n = 2), Elk Ridge (n = 2) in the upper Mimbres Valley, and Old Town (n = 1) in the lower Mimbres Valley (Figure 5.5). Whereas the actual number of Mimbres B/W Style II samples assigned to this compositional group is

quite small, there are several interesting observations that can be made regarding the earlier occupation in the Eastern Mimbres area. First, the NAA data demonstrate that Late Pithouse period people in the Eastern Mimbres area were interacting, albeit at a small scale, with Jornada people along the lower Rio Grande River and the western margins of the San Andres Mountains. The two samples from Elk Ridge, which is situated toward the very upper end of the Mimbres Valley and single specimen from Old Town at the very lower end of the Mimbres Valley demonstrates that there was limited interaction between people in the Eastern Mimbres and the Mimbres Valley, and that these interactions may have been limited to sites at the extreme ends of the valley given that no other Mimbres Valley sites appear to contain this pottery.




Figure 5.5. Map showing the distribution of Mimbres B/W Style II pottery assigned to the Mimbres-01 group relative to the production area for this pottery.

Similar diachronic changes are observed for pottery produced at Swarts (Mimbres-02A), Mattocks (Mimbres-08), and Mimbres-11 (production site seems to be located in the middle Mimbres Valley). These sites, which are located in the middle and upper parts of the Mimbres Valley, show clear increases through time in pottery production. Additionally, Swarts appears to be one of two primary production centers for Mimbres B/W Style III pottery in the Mimbres Valley—14.3% of all Style III pottery (n = 1467) analyzed can be attributed to Swarts.

As discussed in Chapter 4.1, considerable confusion exists regarding the classification of pottery assigned to Mimbres-03. This stems from the fact that Mimbres Black-on-white pottery is by definition a white-slipped brown-paste ceramic. Pottery assigned to Mimbres-03 typically is made from an unslipped light-colored paste, but decorated with design elements that are reminiscent of traditional Mimbres B/w pottery. Consequently it has been classified by different researchers as "Indeterminate Whiteware", Whiteware (not Mimbres), "Cibola Paste, Mimbres design", Cibola, Mimbres Style I, II, and III, etc. In many respects, it may not be fair to discuss temporal change given the issues with the typology of pottery assigned to this group and since pottery classified as "Whiteware" (Cibola or otherwise) was not included in the tallies used to produce Table 5.2 and Figure 5.4.

Despite the issues regarding typology, there does seem to be a decrease in pottery production through time for Mimbres-series pottery assigned to this group. I believe this trend is accurate. In Robbie Brewington's analyses of pottery from the West Fork site (samples designated with a TAM prefix), she refers to pottery as both undifferentiated Whitewares and also as white-slipped Brownwares

(information derived from descriptive information for INAA data provided by Texas A&M). Clearly, Brewington recognized the typological issues, and interestingly samples comprising both descriptive types are assigned to the Mimbres-03 group. Brewington further indicates that several of the "Whitewares" have design elements similar to Mimbres B/W Styles I and II, but does not indicate that any are similar to Mimbres B/W Style III. Thus, we can infer that Brewington believed most of the Whitewares were likely earlier. Additionally, most of Mimbres pottery analyzed by Brewington (the white-slipped Brownwares) assigned to this group also are classified as Mimbres B/W Style I and II. This means that if we only consider pottery analyzed by Brewington, we still see the same pattern of a decrease in pottery production through time.

As a final note on this group, it worth mentioning that it appears that people living in the Gila Forks area were producing two distinct pottery types—a white ware and a white-slipped Brownware—and were decorating both types with typical Mimbres-style designs. This is a topic that should be investigated further.

Mimbres-series pottery assigned to Mimbres-04A is attributed to the Galaz site located in the upper Mimbres Valley. Galaz was perhaps the largest of all the Mimbres Valley sites, and as such, produced large amounts of pottery throughout the entire Mimbres-Mogollon sequence. Galaz exhibits a clear increase through time in pottery production. In the Mimbres Valley, it is the largest producer of Mimbres B/W Style II pottery and one of two primary production centers for Mimbres B/W Style III (in the Mimbres Valley)—14.2% of all Style III pottery (n = 1467) analyzed can be attributed to Galaz.

Mimbres-049A (Elk Ridge) and Mimbres-04C (Harris Site) have almost identical temporal trends—pottery production peaks with Mimbres B/W Style I and then decreases through time.

I have attributed pottery assigned to Mimbres-04C as having originated from the Harris site. Lekson (2006) has republished multiple tree-ring dates from the site (ca. A.D. 600–875) which suggests the site primarily dates to the Late Pithouse period. These dates are in agreement with the temporal trends observed with the painted ceramics. Having said that, only 18 pottery samples have been analyzed from Harris, but 28% of the analyzed sample is assigned to Mimbres-04C. Two nearby sites also have high percentages of pottery assigned to this group—Galaz (ca. 20%) and Gonzales (ca. 22%). Given that Mimbres-04A is believed to represent pottery production at Galaz, we can probably rule out Galaz as the origin for this group. The Gonzales site, is similar to Harris in that relatively few samples have been analyzed from it (n = 15), but unlike Harris, relatively little is known about this site. The Gonzales site was briefly recorded by Nels Nelson in 1920 and again by the Mimbres Foundation in the 1970s, but has never been the subject of professional archaeological excavation and is now totally destroyed.

Mimbres-05A believed to represent pottery production along a broad segment of the Gila River between Powers Ranch in eastern Arizona and the Cliff region in western New Mexico. This group exhibits a temporal trend similar to that observed in the Gila Forks area (Mimbres-03) in that there a general decrease in production of Mimbres-series pottery through time.

Mimbres-21 originates from the Woodrow site located along the Gila River north of Cliff, New Mexico. Pottery production at Woodrow appears to increase through time. In Figure 5.4, a notably large spike occurs in production of Mimbres B/W Style II pottery. This increase could be in part attributable to sample bias in the larger dataset, but there was a large Late Pithouse period occupation at the site and it may have well been a major ceramic producer. A large number Mimbres B/W Style II specimens analyzed for Schriever's (2008) dissertation project at Wind Mountain were assigned to the Mimbres-21 group. Because pottery from Wind Mountain represents the largest sample of non-Mimbres Valley derived Style II pottery, the percentages for Woodrow are probably slightly skewed, but given that a major portion of the Mimbres B/W Style II pottery from NAN originates from this site, the data seem to suggest that Woodrow was a major source of pottery during the Late Pithouse period.

No clear temporal trends are observed for **Mimbres-22** pottery, which is believed to represent pottery production at Saige-McFarland.

Wind Mountain (Mimbres-24) shows a clear decrease through time in pottery production. Three Circle R/W dominates the early part of the sequence, but this is likely a result of sample bias similar to that discussed for Mimbres-21. Even with this bias, however, the observed decrease through time is likely real. Of the nearly 15,000 Three Circle R/W and Mimbres B/W Style I–III pottery sherds from Wind Mountain, almost 80% are Three Circle R/W and Mimbres B/W style I–II; the remaining 20% are Mimbres B/W Style III (Woosley and McIntyre 1996).

Unlike other Mimbres Valley production sites, **Mimbres-41** (NAN) shows a very interesting pattern—pottery production increases through time, peaks with Mimbres B/W Style II, and then falls off. NAN does have a significant Classic period occupation, thus it is not simply a case of NAN being abandoned during the Classic Period. Likewise, it is not a sampling issue. More than 250 Mimbres-series ceramics have been analyzed from NAN, this includes about 140 Mimbres Style III B/W specimens (or ca. 10% of the total Mimbres B/W Style III sample). In other words, we should see clear evidence for fairly large scale Classic period pottery production at NAN—it simply does not seem to exist. Only five Mimbres B/W Style III bowls (out of more than 1500 analyzed to date) can be attributed to NAN.

If we examine pottery production in the Mimbres Valley during the Late Pithouse Period (e.g., Three Circle R/W and Mimbres Style I and II), we observe that pottery is being produced throughout the entire Mimbres Valley. In contrast, during the Classic Period there is no real evidence for pottery production in the lower Mimbres Valley and only minimal evidence for pottery production at NAN. Instead it appears that sites from NAN down river to Old Town, all of which had significant Classic Period occupations, were obtaining most/all of their pottery from elsewhere. Figure 5.6 illustrates differences observed in Mimbres Valley pottery production during the Late Pithouse and Classic Periods.




Figure 5.6. Maps showing the distribution of pottery production during the Late Pithouse and Classic Periods. Dashed lines indicate ephemeral Classic Period pottery production at NAN (Mimbres-41), Harris (Mimbres-04C, and the Lower Mimbres Valley (Mimbres-42). Refer to Table 5.2.

Classic Period Pottery Production—Specialized or Not?

In Chapter 1, I discussed two competing ideas regarding Classic Period Mimbres B/W pottery production. Shafer (2003) has proposed that most, if not all, Mimbres women produced painted pottery, and he contends that the distribution of similar, but not identical designs and a lack of standardization within any one pottery style is indicative of a large number of Mimbres potters at any given site at any given time. In contrast, LeBlanc (2004, 2010) has argued that Classic Period production was a specialized activity practiced by a few potters at any time in any given village. LeBlanc also has acknowledged that independent lines of evidence can be developed to support ideas regarding pottery specialization. This includes not only stylistic analysis of design motifs, but also the identification of the sources of pottery via NAA or other means.

Until recently, most NAA analyses of Mimbres-series pottery was conducted on small pot sherds. As a result, the use of stylistic information in conjunction with NAA data, has not been possible. Powell-Marti (Powell 2000) attempted to address this topic in her Ph.D. dissertation, but was largely unsuccessful due to the limited interpretative value of her specific INAA dataset. During the past several years, Darrell Creel's INAA research on Mimbres pottery has focused almost exclusively on whole or nearly intact Mimbres vessels. This effort got underway in the early 2000's with the analyses of about 200 pots from Swarts Ruin. In the past few years an additional 450 intact pots have been analyzed, and currently there is a significant effort underway to analyze by INAA an additional 800–1000 whole pots. When completed, this massive undertaking will allow stylistic information to be merged directly with NAA data. Ultimately, this effort will facilitate a highly

detailed assessment of whether or not pottery production is a specialized activity or one that is practiced by numerous individuals throughout the Mimbres area. The groups identified and discussed in this dissertation will greatly aid in that effort.

Based on preliminary data, there is good evidence that certain design motifs originate from the same production site and are likely produced by the same potter (e.g., Creel and Speakman 2012). In other cases, however, design elements exist on some pots that one might reasonably argue were painted by the same potter, but NAA data indicates these pots originated from multiple sites.

There are large numbers of Mimbres painted pottery samples that remain unassigned (22% of samples in Table 5.2 are unassigned). The fact that these samples are unassigned suggests that many more production sites exist and that we simply have not analyzed enough specimens from sites that would allow us to identify/define compositional groups. In part this is due to the fact that NAA efforts to date have tended to focus on the larger sites in the Mimbres Valley. Samples from numerous other sites, within the Mimbres Valley and throughout the Mimbres region have yet to be sampled. Additionally, in some cases sites have been completely destroyed through looting and it will not be possible to obtain samples. I conservatively estimate that an additional 20 Mimbresseries compositional groups ultimately will be identified as the NAA sample increases. It is unlikely that any additional large groups will be identified given the NAA analyses to date, but the occurrence of small compositional groups will nonetheless inform our understanding of Mimbres pottery production.

With respect to the question of specialized pottery production, or not, the current NAA data would seem to support aspects of both LeBlanc's and Shafer's ideas. Clearly the NAA data do suggest a common point of origin for some of the stylistic groups that have been identified. In other cases, it appears that similar design motifs occur on pottery produced at multiple sites throughout the Mimbres region. The large numbers of unassigned pottery specimens would seem to support Shafer's ideas regarding pottery production (at least at some level) being an activity that is undertaken by numerous individuals in the Mimbres region.

Recommendations for Future Research

One of the challenges in working with this dataset is that it is a compilation of many different research projects. At a basic level, all of the earlier projects had an underlying of goal of identifying production, but the broader research questions being addressed varied from project to project. Additionally, interpretations regarding the origin of compositional groups varied considerably, and even in cases where similar groups were identified across different projects (such as Mimbres-01 and 03), a lack of standardized group names precluded researchers from comparing groups across differ studies. As additional NAA-based research continues in the Mimbres Region, it is critical that groups identified and discussed herein continue to be used as a baseline for the interpretation of new data rather creating new groups as has been the norm for most previous studies. Obviously as additional NAA data are generated, compositional groups will be reevaluated and refined, new groups will be identified, and the proposed origins of some groups may change. These changes are inevitable, but the underlying group structure presented herein should form the basis for guiding these decisions rather than simply creating random new compositional groups and/or names for groups that already exist.

Re-evaluation of Previous Research Questions

At this point, it would highly beneficial for researchers to reevaluate their earlier research questions using the group structure identified herein. This would allow Pat Gilman, for example, who has been investigating Mimbres pottery production in the peripheral areas of eastern Arizona and at areas south of the Mimbres Valley to discuss trade and interaction at the same level as a researcher working within the Mimbres Valley or perhaps the Upper Gila River. If most researchers could be convinced to undertake this task, it would be possible to create a significant synthesis of Mimbres pottery production and distribution throughout the greater Mimbres region and would allow patterns observed and specific research questions to be discussed in similar terms.

Targeted Sampling

As discussed previously (see Figure 1.5), the Mimbres dataset is heavily biased toward the analysis of Mimbres B/W Style III. To date only three projects have placed significant emphasis on the analyses of earlier ceramic types—one for Lori Reed which focused primarily on Alma pottery, a second project initiated by Bernard Schriever focused on earlier painted ceramics, and Darrell Creel has analyzed large numbers of earlier ceramics from NAN. New projects need to be initiated that focus on earlier ceramic types. In doing so, we will gain a much better understanding of earlier Mimbres pottery production and social interaction—specifically how social relationships changed, or not, among different sites leading up to the Classic Period.

Approximately 50% (ca. 1450 specimens) of the analyzed sample of Mimbres-series pottery is derived from 9 sites: Old Town, NAN, Swarts, Galaz, Pruitt Ranch, West Fork, Eby, Elk Ridge, and LA 059652. Pottery from dozens of other sites, both large and small, have yet to be analyzed or are poorly represented in the dataset. Much of Darrell Creel's recent research has focused on filling in these gaps, such that we now have a reasonable number of samples from sites such as, Pruitt Ranch and Eby and a few samples from Gonzalez and Harris. It is critical that future research be focused on sites not well represented in the database. It is from such analyses that we will likely be able to create new groups that include some existing unassigned samples as well as refine our thoughts about the origins of some existing groups.

Raw Material Survey and Analysis.

The INAA database for clays and tempers is severely limited. As mentioned previously, approximately 160 geological clays are included in this study, but very few of the clays can be linked confidently to specific compositional groups. Clays that have been sampled originate primarily from sites in the lower and middle Mimbres Valley, the eastern Mimbres area, and the Wind Mountain locale (Figure 5.7). Clays from large areas surrounding the Mimbres Valley have yet to be sampled and analyzed by INAA. We have good reason to believe that pottery production occurs in these areas, and in many cases I have argued (see Chapter 4 and discussion above) that certain compositional groups originate from specific sites despite the fact that that we cannot firmly link these groups to the sites. It is abundantly clear that a large-scale regional study of clays needs to occur.

Additionally, no chemical analyses of non-clay inclusions (temper) have occurred to date. As the various petrographic studies have demonstrated (e.g., Rugge 1976, 1985a, 1985b, 1988; Stoltman 1996, Schreiver 2008) Mimbres series pottery is tempered with a diverse range of volcanic rocks, granites, and/or sand. The intentional addition of these materials, by Mimbres potters, to the clays effectively serves to enrich and/or dilute elements measured by INAA. The result is that chemical composition of the finished product (the pottery) is altered in such a manner that the clays cannot effectively be linked to the compositional groups. The inclusion of possible tempers in future studies of Mimbres pottery will permit the clay data to be mathematically mixed in various proportions so that pottery reference groups can firmly be linked to geologic sources (both clays and temper). Such analyses, in conjunction with traditional petrographic analyses, will be critical to our ability to firmly link chemical groups to specific pottery production locales.

Petrographic Studies

Petrographic studies to date have demonstrated wide variability occurs in Mimbres pottery tempers (both naturally occurring and intentionally added). A major benefit of petrography is that physical differences, such as paste texture and mineral inclusions can provide information relating to raw material selection and ceramic paste preparation beyond the bulk chemical data provided by NAA. In this dissertation, it was determined that petrographic groups defined by Schriever (2008) were correlated with the NAA groups. Future efforts can and should continue to involve petrography to help guide research directed at identifying the origins of tempers used in production of Mimbres pottery.




Figure 5.7. Map showing the distribution of clays analyzed by INAA.

Conclusions

In this dissertation, I have examined Mimbres-Mogollon pottery production and distribution using NAA. The underlying goal of this research was to identify valid compositional groups that could be used to examine pottery production sites and the movement of pottery throughout the Mimbres Valley and adjacent regions. In addition to hundreds of recent analyses conducted for this project (in collaboration with Darrell Creel and others), I have incorporated, where possible, extant data generated for earlier Mimbres NAA projects (see Chapter 2). In total, the NAA dataset includes about 2900 analyses of Mimbres-Mogollon pottery samples and approximately 160 clays from 165 archaeological sites across Arizona, New Mexico, Texas, and northern Mexico. An additional 600 Jornada-Mogollon pottery samples were included for comparative purposes.

A major component of this research was to construct robust and statically valid compositional groups. Given the relatively large numbers of samples in the database and the complex compositional variability, I partitioned the dataset into 6 macro groups (A, B1, B2, C1, C2, and D) using elements (e.g., Cs, Dy, Fe, Th, Ta) that, in earlier MURR NAA research, had proven valuable for discriminating major Mimbres compositional groups. When viewed from the perspective of the larger dataset, I observed that the partitioning of these groups followed natural breaks in the compositional continuum for Mimbres and Jornada pottery (Chapter 4.1).

With the dataset subdivided into smaller and more manageable macro groups, I then used principal components analysis in combination with inspection of element projections of the NAA data to identify

compositional groups. The validity of these groups subsequently was assessed using Mahalanobis distance probabilities. This approach resulted in the identification of about 35 compositional groups. The process of group formation that I employed was significantly different from earlier studies that typically used a preferred clustering algorithm followed by discriminant analysis to force the creation of groups.

Whereas I have identified approximately 35 compositional groups in this study, earlier researchers typically identified four to six groups for any given project. The lower numbers of groups identified by earlier researchers stems not only from smaller datasets but also from a combination of less than optimal use of statistical approaches and pattern recognition techniques, and also the fact that most of the earlier research failed to successively build on earlier related NAA projects.

Consequently, interpretations based on earlier INAA research involving Mimbres pottery, for the most part, cannot be considered valid.

Following the identification of compositional groups, I created graduated-symbol distribution maps using ArcMap 10 software to examine the distribution of pottery across the landscape. Given that most compositional groups could not be linked to specific clays, the distribution maps greatly aided in determining the possible origin(s) of pottery and by extension its movement via trade and/or social mechanisms. This novel approach for examining ceramic distribution patterns has applications for other provenance-based studies of cultural materials.

An examination of Three Circle R/W and Mimbres B/W Styles I-III assigned to the 14 largest compositional groups showed significant temporal changes in the distribution of pottery through time. These

changes reflect the varied and dynamic nature of social interaction in the Mimbres region and will serve as reference for researchers attempting to understand social processes that are reflected through the movement of pottery across the landscape. When these patterns are examined in conjunction with stylistic data, it is expected that major questions regarding whether or not Mimbres pottery production was a specialized activity will ultimately be answered. However, as stated above, evidence exists for both specialized and generalized production of pottery.

Although many researchers have questioned whether or not Mimbres pottery was produced in the Jornada region, this question has not been satisfactorily addressed until now. Based on the NAA data, there is clear evidence, albeit limited, that some Mimbres B/W pottery was produced in the Jornada region. This includes one sample firmly tied to the Loop 375 group which originates northeast of El Paso, TX. Additionally, two compositional groups (Mimbres-13 and Mimbres-23) are believed to have been produced in the Rio Grande Valley and perhaps even the Jornada Region.

Minimal evidence exists for Classic period pottery production at NAN and at Mimbres Valley sites down river from NAN. Additionally, at the nearby sites of Cameron Creek and Treasure Hill (located to the west) there is very little evidence of Classic Period pottery productions (see Chapter 4). Given that the analyzed sample of Mimbres B/W Style III pottery from these sites is more than adequate, these patterns appear to be real, rather than sample bias.

Numerous avenues for future research have been suggested above.

These include:

- The reevaluation of earlier research questions, by the original researchers, in light of the compositional group structure discussed herein.
- Targeted sampling of underrepresented pottery types.
- Targeted sampling of sites not included in this study.
- The initiation of a major raw material survey that includes the analysis of both clays and tempers.
- Increased sampling of whole or mostly intact pots given that
 the decorative elements will aid in addressing "big picture"
 questions regarding craft specialization and social
 stratification within Mimbres society.

As I have outlined in Chapter 2, the analyses of a few hundred samples did not adequately explain Mimbres pottery production given the relative size of the Mimbres region, the geological variability, and the large numbers of sites potentially producing pottery. With the benefit of this the substantial NAA dataset that was developed over a 20 year period, we are just now beginning to appreciate the full value of NAA for studying Mimbres pottery production and distribution. In hindsight, the limitations of previous studies are readily apparent—in all cases the analyses of only a few hundred samples precluded recognition of the full range of potential production sites (i.e., compositional groups) that exist in the Mimbres region. Although numerous questions related to Mimbres pottery production remain to be examined, I have outlined approaches in this dissertation that I hope will guide future research concerning Mimbres pottery. As this research progresses, new groups will be formed and in some cases samples will be reassigned to other groups. But in general, the compositional group structure described herein is not likely to change very much. It is critical that future research in the

Mimbres area, and for that matter anywhere else, build upon the earlier research. Extant data may have been generated with very different research questions in mind, but such data still have tremendous analytical value; one of the great benefits of NAA is that data from multiple labs can usually be corrected and incorporated with new INAA data.

References Cited

Anyon, R.

1984 *Mogollon Settlement Patters and Communal Architecture*. M.A. thesis, Department of Anthropology, University of New Mexico, Albuquerque.

Anyon, R., P. A. Gilman, and S. A. LeBlanc

1981 A Reevaluation of the Mogollon-Mimbres Archaeological Sequence. *Kiva* 46:209–225.

Baxter, M. J.

1992 Archaeological uses of the Biplot—A Neglected Technique? In *Computer Applications and Quantitative Methods in Archaeology, 1991*, edited by G. Lock and J. Moffett. BAR International Series S577, pp. 141–148. Tempvs Reparatvm, Archaeological and Historical Associates, Oxford.

1994 Exploratory Multivariate Analysis in Archaeology. Edinburgh University Press, Edinburgh.

Baxter, M. J. and C. E. Buck

2000 Data Handling and Statistical Analysis. In *Modern Analytical Methods in Art and Archaeology*, edited by E. Ciliberto and G. Spoto, pp. 681–746. John Wiley and Sons, Inc., New York.

Bieber, A. M. Jr., D. W. Brooks, G. Harbottle, and E. V. Sayre

1976 Application of Multivariate Techniques to Analytical Data on Aegean Ceramics. *Archaeometry* 18:59–74.

Bishop, R. L. and H. Neff

1989 Compositional Data Analysis in Archaeology. In *Archaeological Chemistry IV*, edited by R. O. Allen, pp. 576–586. Advances in Chemistry Series 220, American Chemical Society, Washington, D.C.

Bishop, R. L., R. L. Rands, and G. R. Holley

1992 Ceramic Compositional Analysis in Archaeological Perspective. In *Advances in Archaeological Method and Theory*, vol. 5, pp. 275–330. Academic Press, New York.

Blackman, M. J. and Bishop, R. L.

The Smithsonian-NIST partnership: The Application of Instrumental Neutron Activation Analysis to Archaeology. *Archaeometry*, 49(2): 321–341.

Brewington, R. L., and H. J. Shafer

The Ceramic Assemblages of Ojasen and Gobernadora. In Archaeology of the Ojasen (41EP289) and Gobernadora (41EP321) Sites, El Paso County, Texas, edited by H. J. Shafer, J. E. Dockall, and R. L. Brewington, pp. 149–197. Reports of Investigations 2, Center for Ecological Archaeology, Texas A&M University, College Station; Report 13, Archeology Studies Program, Environmental Affairs Division, Texas Department of Transportation, Austin.

Brewington, R. L., H. J. Shafer, and W. D. James

- 1996 Production and Distribution of Mimbres Black-on-white Ceramics: Evidence from Instrumental Neutron Activation Analysis (INAA). Paper presented at the 61st Annual Meeting of the Society for American Archaeology, New Orleans, Louisiana.
- Continuing Neutron Activation Analysis of Mimbres Ceramics: A Progress Report.
 Proceedings of the Ninth Jornada-Mogollon Conference, edited by R. P. Mauldin,
 J. D. Leach, and S. Ruth, pp. 127–130. Centro de Investigaciones Arqueologicas,
 Publications in Archaeology No. 12 and The University of Texas at El Paso.

Buxeda i Garrigós, J., and V. Kilikoglou

2003 Total Variation as a Measure of Variability in Chemical Data Sets. In *Patterns and Process: A Festschrift in Honor of Dr. Edward V. Sayre*, edited by L. Van Zelst, pp. 185–198. Smithsonian Center for Materials Research and Education, Suitland, Maryland.

Carmichael, D. C.

1986 Archaeological Settlement Patterns in the Southern Tularosa Basin. El Paso Centennial Museum Publications in Anthropology No. 10. University of Texas, El Paso.

Chandler, S. L.

2000 Sourcing Three Circle Phase Ceramics from Old Town (LA 113), Luna County, New Mexico. M.A. thesis, Department of Sociology and Anthropology, New Mexico State University, Las Cruces.

Clark, Tiffany C.

2006 Production, Exchange, and Social Identity: A Study of Chupadero Black-on-white Pottery. Ph.D. dissertation, Department of Anthropology, Arizona State University, Tempe.

Cogswell, J. W.

1998 *Ceramic Studies in the Missouri Bootheel.* Ph.D. dissertation, Department of Anthropology, University of Missouri–Columbia.

- Creel, D., and R. J. Speakman
- The Mimbres Vessel Project: An Update on the Neutron Activation Analysis Effort. Paper presented at the 17th Mogollon Conference, Silver City, New Mexico, October 4–6, 2012.
- Creel, D., M. Williams, H. Neff, and M. D. Glascock
- 2002 Black Mountain Phase Ceramics and Implications for Manufacture and Exchange Patterns. In *Ceramic Production and Circulation in the Greater Southwest: Source Determination by INAA and Complementary Mineralogical Investigations*, edited by Donna M. Glowacki and Hector Neff, pp. 37–46. Monograph 44, Cotsen Institute of Archaeology, University of California, Los Angeles.

Dahlin, E. S.

2003 INAA and Distribution Patterns of Classic Mimbres Black-on-white Vessels during the Classic Period. M.A. thesis, Department of Anthropology, Texas A&M University, College Station.

Dahlin, E. S., D. L. Carlson, W. D. James, and H. J. Shafer

2007 Distribution Patterns of Mimbres Ceramics using INAA and Multivariate Statistical Methods *Journal of Radioanalytical and Nuclear Chemistry*, 271:461–466.

Dering, P., H. J. Shafer, and R. P. Lyle (editors)

2001 The El Paso Loop 375 Archaeological Project: Phase II Testing and Phase III Mitigation. Report No. 28, Texas Department of Environmental Affairs Division Archaeological Studies Program, Austin, and Reports of Investigations No. 3, Center for Ecological Archaeology, Texas A&M University, College Station.

Ferguson, J. R., and M. D. Glascock

2007 Instrumental Neutron Activation Analysis of Mimbres Pottery from Three Sites in Southwestern New Mexico. Report on File, Archaeometry Laboratory, University of Missouri Research Reactor, Columbia.

Gilman, P. A., V. Canouts, and R. L. Bishop

1994 The Production and Distribution of Classic Mimbres Black-on-white Pottery. *American Antiquity* 59:695–709.

Glascock, M. D.

1992 Characterization of Archaeological Ceramics at MURR by Neutron Activation Analysis and Multivariate Statistics. In *Chemical Characterization of Ceramic Pastes in Archaeology*, edited by H. Neff, pp. 11–26. Prehistory Press, Madison, Wisconsin.

Glascock, M. D., R. J. Speakman, and H. Neff

2007 Archaeometry at the University of Missouri Research Reactor and the Provenance of Obsidian Artifacts in Eastern North America. *Archaeometry* 49:343–357.

Harbottle, G.

1976 Activation Analysis in Archaeology. *Radiochemistry* 3:33–72. The Chemical Society, London.

Hegmon, M.

2002 Recent Issues in the Archaeology of the Mimbres Region of the North American Southwest. *Journal of Archaeological Research* 10:307–357.

Hegmon, M., M. C. Nelson, and S. M. Ruth.

1998 Abandonment and Reorganization in the Mimbres Region of the American Southwest. *American Anthropologist* 100:148–162.

Hensler, K. N., Reed, Lori S., and R. J. Speakman

2005 Looking at the Mimbres Valley from the West. In *Proceedings of the 13th Mogollon Conference (2004)*, edited by L. Ludeman, pp. 364–379. Western New Mexico University Museum, Silver City, New Mexico.

Hill. D. V.

- 1988 Petrographic Analysis of Loop 375 Ceramics (Phase II). In *Loop 375*Archaeological Project Fort Bliss Maneuver Area I, El Paso, Texas: An Interim

 Report for Phase II Testing and Phase III Recommendations for Data Recovery, by

 T. C. O'Laughlin, V. L. Scarborough, T. B. Graves, and D. Martin. Appendix H.

 Department of Sociology and Anthropology, The University of Texas at El Paso. El Paso, Texas.
- 1991 Petrographic Analysis of Mimbres Phase Ceramics from the San Andres Mountains. In *Mountains of Sunlit Silence: White Sands Missile Range Sample Inventory, Survey of the Southern San Andres Mountains of New Mexico*, by Human Systems Research, Tularosa, New Mexico. Report submitted to White Sands Missile Range, U.S. Department of the Army.
- 1993 Ceramics. In Phase II Additional Testing Loop 375 Archaeological Project El Paso County, Texas, by T. C. O'Laughlin and D. L. Martin. *The Artifact* 31:110–121.

James, D. W.

2001 Instrumental Neutron Activation Analysis. In *The El Paso Loop 375 Archaeological Project: Phase II Testing and Phase III Mitigation*, edited by P. Dering, H. J. Shafer, and R. P. Lyle, pp. 344–348. Report No. 28, Texas Department of Environmental Affairs Division Archaeological Studies Program, Austin, and Reports of

Investigations No. 3, Center for Ecological Archaeology, Texas A&M University, College Station.

James, W. D., R. L. Brewington, H. J. Shafer

1995 Compositional Analysis of American Southwestern Ceramics by Neutron Activation Analysis. *Journal of Radioanalytical and Nuclear Chemistry* 192:109–116.

James, W. D., E. S. Dahlin, and D. L. Carlson

2005 Chemical Compositional Studies of Archaeological Artifacts: Comparison of LA-ICP-MS to INAA Measurements. *Journal of Radioanalytical and Nuclear Chemistry* 263:697–702.

James, W. D., M. R. Raulerson, and P. R. Johnson

2007 Archaeometry at Texas A&M University: Characterization of Samoan Basalts. *Archaeometry* 49:395–402.

LeBlanc, S. A.

2004 Painted by a Distant Hand: Mimbres Pottery from the American Southwest. Peabody Museum Press, Harvard University, Cambridge.

2006 Who Made Mimbres Bowls? Implications of Recognizing Individual Artists for Craft Specialization and Social Networks. In *Mimbres Society*, edited by V. S. Powell-Marti and P. A. Gilman, pp. 109–150. The University of Arizona Press, Tucson.

2010 The Painters of the Pots. In *Mimbres Lives and Landscapes*, edited by M.C. Nelson and M. Hegmon, pp. 74–81. School for Advanced Research Press, Santa Fe.

LeBlanc, S. A., and M. E. Whalen (editors)

1980 An Archaeological Synthesis of Southcentral and Southwestern New Mexico.
Office of Contract Archaeology, University of New Mexico, Albuquerque.

Leese, M. N. and P. L. Main

1994 The Efficient Computation of Unbiased Mahalanobis Distances and their Interpretation in Archaeometry. *Archaeometry* 36:307–316.

Lekson, S. H.

2006 Archaeology of the Mimbres Region, Southwestern New Mexico, U.S.A. BAR International Series 1466. Archaeopress, Oxford.

Lynott, M. J., H. Neff, J. E. Price, J. W. Cogswell, and M. D. Glascock

2000 Inferences about Prehistoric Ceramics and People in Southeast Missouri: Results of Ceramic Compositional Analysis. *American Antiquity* 65:103–126.

Mardia, K. V., J. T. Kent and J. M. Bibby 1979 *Multivariate Analysis*. Academic Press, London.

Miller, M. R. III

- 1990 The Southern Jornada Mogollon Transitional Period: Excavations in the North Hills Subdivision, El Paso County, Texas. Report No. 100. Batcho and Kauffman Associates, Las Cruces, New Mexico. Submitted to International City Developers, El Paso, Texas.
- 2005 Peripheral Basins and Ephemeral Polities: INAA of Mimbres Black-on-White Ceramics and Insights into Mimbres and Jornada Mogollon Social Relationships. Paper presented at the 70th Annual Meeting of the Society for American Archaeology, Salt Lake City, Utah.

Miller, M. R. III, H. Neff, and M. D. Glascock

1997 Production and Distribution of Mimbres Whiteware and El Paso Brownware in the Jornada Mogollon Region of West Texas and Southern New Mexico. Paper presented at the 62nd Annual Meeting of the Society for American Archaeology, Nashville, Tennessee.

Miller, M. R. III, Robert J. Speakman, H. Neff, and M. D. Glascock

2007 Peripheral Basins and Ephemeral Polities: INAA of Mimbres Black-on-White Ceramics and Insights into Mimbres and Jornada Mogollon Social Relationships. Paper presented at the 15th Biennial Jornada Mogollon Conference, El Paso Museum of Archaeology, El Paso, Texas.

Neff, H.

- 1992 Introduction. In *Chemical Characterization of Ceramic Pastes in Archaeology*, edited by H. Neff, pp. 1–10. Prehistory Press, Madison, Wisconsin.
- 1994 RQ-mode Principal Components Analysis of Ceramic Compositional Data. *Archaeometry* 36:115–130.
- 2000 Neutron Activation Analysis for Provenance Determination in Archaeology. In *Modern Analytical Methods in Art and Archaeology*, edited by E. Ciliberto and G. Spoto, pp. 81–134. John Wiley and Sons, Inc., New York.

- Quantitative Techniques for Analyzing Ceramic Compositional Data. In *Ceramic Source Determination in the Greater Southwest*, edited by D. M. Glowacki and H. Neff, pp. 15–36. Monograph 44, Cotsen Institute of Archaeology, UCLA, Los Angeles.
- Neff, H, J. E. Blomster, M. D. Glascock, R. L. Bishop, M. J. Blackman, M. D. Coe, G. L. Cowgill, R. A. Diehl, S. Houston, A. A. Joyce, C. P. Lipo, B. L. Stark, and M. Winter
 2006a Methodological Issues in the Provenance Investigation of Early Formative Mesoamerican Ceramics. *Latin American Antiquity* 17:54–76.
- 2006b Smokescreens in the Provenance Investigation of Early Formative Mesoamerican Ceramics. *Latin American Antiquity* 17:104–118.

Neff, H., R. L. Bishop, and E. V. Sayre

1988 A Simulation Approach to the Problem of Tempering in Compositional Studies of Archaeological Ceramics. *Journal of Archaeological Science* 15:159–172.

Nelson, M.C. (editor)

1984 Ladder Ranch Research Project: A Report of the First Season. Technical Series of the Maxwell Museum of Anthropology No. 1, University of New Mexico, Albuquerque.

Powell, V. S.

2000 Iconography and Group Formation during the Late Pithouse and Classic Periods of the Mimbres Society, A.D. 970–1140. Ph.D. dissertation, Department of Anthropology, University of Oklahoma, Norman.

Powell-Marti, V. S., and W. D. James

2006 Ceramic Iconography and Social Asymmetry in the Classic Mimbres Heartland, AD 970–1140. In *Mimbres Society*, edited by V. S. Powell-Marti and P. A. Gilman, pp. 151–173. University of Arizona Press, Tucson.

Reed, L.

n.d. A Sourcing Study of Early Pithouse Period Ceramics and Raw Materials in the Burro Mountains, Southwestern New Mexico. Manuscript in possession of R.J. Speakman.

Robinson, D. G.

1980 Mogollon Ceramic Production and Exchange in the Middle San Francisco River Valley, Southwestern New Mexico. Unpublished M.A. Thesis, Department of Anthropology, University of Texas, Austin.

2001 Loop 375 Archaeological Project: Petrographic Analysis. In *The El Paso Loop 375 Archaeological Project: Phase II Testing and Phase III Mitigation*, edited by P. Dering, H. J. Shafer, and R. P. Lyle, pp. 338–342. Report No. 28, Texas Department of Environmental Affairs Division Archaeological Studies Program, Austin, and Reports of Investigations No. 3, Center for Ecological Archaeology, Texas A&M University, College Station.

Rugge, D. R.

- 1976 A Petrographic Study of Ceramics from the Mimbres River Valley, New Mexico.
 Report part of Mimbres Foundation files housed at the Maxwell Museum of
 Anthropology, University of New Mexico, Albuquerque.
- 1985a Petrographic Analysis of Ceramic Technology. In *Archaeological Testing at the Fairchild Site (LA 45732), Otero County, New Mexico*, by R. Anyon, pp. 121–135. Office of Contract Archaeology, University of New Mexico, Albuquerque.
- 1985b Petrographic Analysis of Mimbres Series Ceramics from the Ft. Bliss Military Reservation, Texas and New Mexico. Report on file, Fort Bliss Environmental Protection Office, Fort Bliss, Texas.
- 1988 Petrographic Studies. In *The Border Star 85 Survey: Toward an Archaeology of Landscapes*, edited by T. J. Seaman, W. H. Dolemen, and R. C. Chapman, pp. 185–190. Office of Contract Archaeology, University of New Mexico, Albuquerque.

Sayre, E. V.

1975 Brookhaven Procedures for Statistical Analyses of Multivariate Archaeometric Data. Brookhaven National Laboratory Report BNL-23128. New York.

Sayre, E. V., and R.W. Dodson

1957 Neutron Activation Study of Mediterranean Potsherds, *American Journal of Archaeology*, 61, 35–41.

Schriever, B. A.

2008 Informal Identity and the Mimbres Phenomenon: Investigating Regional Identity and Archaeological Cultures in the Mimbres Mogollon. Ph.D. dissertation, Department of Anthropology, University of Oklahoma, Norman.

Shafer, H. J.

- 2001 INAA Results. In *The El Paso Loop 375 Archaeological Project: Phase II Testing and Phase III Mitigation*, edited by P. Dering, H. J. Shafer, and R. P. Lyle, pp. 348–355. Report No. 28, Texas Department of Environmental Affairs Division Archaeological Studies Program, Austin, and Reports of Investigations No. 3, Center for Ecological Archaeology, Texas A&M University, College Station.
- 2003 *Mimbres Archaeology at NAN Ranch*. University of New Mexico Press, Albuquerque.

Steponaitis, V., M. J. Blackman, and H. Neff

1996 Large-Scale Compositional Patterns in the Chemical Composition of Mississippian Pottery. *American Antiquity* 61:555–572.

Stoltman, J. B.

1996 Petrographic Observations of Selected Sherds from Wind Mountain. In *Mimbres Mogollon Archaeology*, edited by A. I. Woosley and A. J. McIntyre, pp.367–371. University of New Mexico Press, Albuquerque.

Taliaferro, M.

n.d. The Black Mountain Phase Occupation at the Old Town Ruin: an Examination of Social and Technological Organization in the Mimbres Valley of Southwestern New Mexico ca. A.D. 1150-1300. Ph.D. dissertation, Department of Anthropology, University of Texas, Austin.

Weigand, P. C., G. Harbottle, and E. V. Sayre

1977 Turquoise Sources and Source Analysis: Mesoamerica and the Southwestern U.S.A. In *Exchange Systems in Prehistory*, edited by T. K. Earle and J. E. Ericson, pp. 15–34. Academic Press, New York.

Woosley, A. I., and A. J. McIntyre (editors)

1996 Mimbres Mogollon Archaeology: Charles Di Peso's Excavations at Wind Mountain. University of New Mexico Press, Albuquerque.

Annondiv A
Appendix A:
Macro Group A Mahalanobis Distance Calculations and PCA Scores

Table A1. Macro Group A Mahalanobis distance calculations and posterior classification.

Groups Evaluated:

Mimbres-01 (M01)

Mimbres-03 (M03)

Mimbres-07A (M07A)

Mimbres-10 (M10)

Variables used:

As, La, Lu, Nd, Sm, U, Yb, Ce, Cr, Cs, Eu, Fe, Hf, Rb, Sb, Sc, Ta, Th, Zn, Zr, Al, Ba, Dy, Mn, Na, Ti, V

The following sp	ecimens are assigned	to group Mimbres	-01.		
ID. NO.	M01	M03	M07A	M10	Assigned Group
BAS067	2.42	0.00	0.00	0.00	M01
BAS071	81.27	0.00	0.00	0.00	M01
BAS074	94.54	0.00	0.00	0.00	M01
BAS214	85.92	0.00	0.00	0.00	M01
BAS221	6.77	0.00	0.00	0.00	M01
BAS225	94.57	0.00	0.00	0.00	M01
BRE058	51.67	0.00	0.00	0.00	M01
BRE093	30.48	0.00	0.00	0.00	M01
BRE094	0.15	0.00	0.00	0.00	M01
BRE098	0.56	0.00	0.00	0.00	M01
CAP176	57.82	0.00	0.00	0.00	M01
CAP180	99.39	0.00	0.00	0.00	M01
CAP181	95.03	0.00	0.00	0.00	M01
CAP182	26.15	0.00	0.00	0.00	M01
CAP183	53.00	0.00	0.00	0.00	M01
CAP184	79.64	0.00	0.00	0.00	M01
CAP185	97.70	0.00	0.00	0.00	M01
CAP186	95.58	0.00	0.00	0.00	M01
CAP187	68.51	0.00	0.00	0.00	M01
CAP190	5.06	0.00	0.00	0.00	M01
CAP192	97.76	0.00	0.00	0.00	M01
CAP194	85.60	0.00	0.00	0.00	M01
CAP195	95.98	0.00	0.00	0.00	M01
CAP196	67.38	0.00	0.00	0.00	M01
CAP197	9.30	0.00	0.00	0.00	M01
CAP203	93.86	0.00	0.00	0.00	M01
CAP204	56.29	0.00	0.00	0.00	M01
ED-022	5.49	0.00	0.00	0.00	M01
ED-036	92.84	0.00	0.00	0.00	M01
ED-044	76.56	0.00	0.00	0.00	M01
ED-045	3.91	0.00	0.00	0.00	M01
ED-046	27.59	0.00	0.00	0.00	M01
ED-047	98.44	0.00	0.00	0.00	M01
ED-048	76.46	0.00	0.00	0.00	M01
ED-049	55.97	0.00	0.00	0.00	M01
ED-050	46.22	0.00	0.00	0.00	M01
ED-072	83.06	0.00	0.00	0.00	M01
ED-077	9.15	0.00	0.00	0.00	M01
HM021	39.04	0.00	0.00	0.00	M01
HM047	62.18	0.00	0.00	0.00	M01
HM054	89.21	0.00	0.00	0.00	M01
HM070	97.19	0.00	0.00	0.00	M01
HM071	33.27	0.00	0.00	0.00	M01
HM073	99.79	0.00	0.00	0.00	M01
HM080	63.75	0.00	0.00	0.00	M01

HM084	98.93	0.00	0.00	0.00	M01
HM086	1.17	0.00	0.00	0.00	M01
HM090	75.84	0.00	0.00	0.00	M01
HM092	83.47	0.00	0.00	0.00	M01
HM095	12.72	0.00	0.00	0.00	M01
JAM124	90.94	0.00	0.00	0.00	M01
JHK004	4.21	0.00	0.00	0.00	M01
LOA038	38.09	0.00	0.00	0.00	M01
LOA191	83.36	0.00	0.00	0.00	M01
MPC005	1.40	0.00	0.00	0.00	M01
MPM016	0.75	0.00	0.00	0.00	M01
MPM023	8.75	0.00	0.00	0.00	M01
MPM026	2.33	0.00	0.00	0.00	M01
MPN022	1.22	0.00	0.00	0.00	M01
MPT003	0.38	0.00	0.00	0.00	M01
MRM004	4.00	0.00	0.00	0.00	M01
MRM008	95.30	0.00	0.00	0.00	M01
MRM010	12.13	0.00	0.00	0.00	M01
MRM037	96.87	0.00	0.00	0.00	M01
MRM051	2.20	0.00	0.00	0.00	M01
MRM055	99.81	0.00	0.00	0.00	M01
MRM056	99.81	0.00	0.00	0.00	M01
MRM058	93.55	0.00	0.00	0.00	M01
MRM063	79.37	0.00	0.00	0.00	M01
MRM064	84.00	0.00	0.00	0.00	M01
MRM077	99.14	0.00	0.00	0.00	M01
MRM083	85.26	0.00	0.00	0.00	M01
MRM086	69.55	0.00	0.00	0.00	M01
MRM093	55.87	0.00	0.00	0.00	M01
MRM115	49.07	0.00	0.00	0.00	M01
MRM124	30.16	0.00	0.00	0.00	M01
MRM126	31.69	0.00	0.00	0.00	M01
MRM130	78.71	0.00	0.00	0.00	M01
MRM131	75.51	0.00	0.00	0.00	M01
MRM138	31.14	0.00	0.00	0.00	M01
MRM139	29.22	0.00	0.00	0.00	M01
MRM140	95.41	0.00	0.00	0.00	M01
MRM169	9.88	0.00	0.00	0.00	M01
MRM170	56.75	0.00	0.00	0.00	M01
MRM173	28.09	0.00	0.00	0.00	M01
MRM215	6.75	0.00	0.00	0.00	M01
MRM217	5.47	0.00	0.00	0.00	M01
MRM218	68.87	0.00	0.00	0.00	M01
MRM221	38.31	0.00	0.00	0.00	M01
MRM226	98.22	0.00	0.00	0.00	M01
MRM229	79.48	0.00	0.00	0.00	M01
MRM233	19.02	0.00	0.00	0.00	M01
MRM235	14.66	0.00	0.00	0.00	M01
MRM239	19.19	0.00	0.00	0.00	M01
MRM245	67.05	0.00	0.00	0.00	M01
MRM258	69.15	0.00	0.00	0.00	M01
MRM259	98.44	0.00	0.00	0.00	M01
MRM264	98.01	0.00	0.00	0.00	M01
MRM267	72.69	0.00	0.00	0.00	M01
MVP0013	29.61	0.00	0.00	0.00	M01
MVP0015	57.18	0.00	0.00	0.00	M01
MVP0023	26.77	0.00	0.00	0.00	M01
MVP0031	99.63	0.00	0.00	0.00	M01
5051	33.03	5.00	5.00	5.55	

	07.00				
MVP0060	85.90	0.00	0.00	0.00	M01
MVP0070	0.19	0.00	0.00	0.00	M01
MVP0072	7.51	0.00	0.00	0.00	M01
MVP0079	4.71	0.00	0.00	0.00	M01
MVP0117	1.94	0.00	0.00	0.00	M01
MVP0122	65.85	0.00	0.00	0.00	M01
MVP0126	66.31	0.00	0.00	0.00	M01
MVP0153	1.02	0.00	0.00	0.00	M01
MVP0192	20.58	0.00	0.00	0.00	M01
MVP0226	5.88	0.00	0.00	0.00	M01
MVP0248	8.18	0.00	0.00	0.00	M01
OK029	17.54	0.00	0.00	0.00	M01
OK065	93.33	0.00	0.00	0.00	M01
OK070	35.49	0.00	0.00	0.00	M01
OK075	37.79	0.00	0.00	0.00	M01
OK076	39.23	0.00	0.00	0.00	M01
OK078	50.07	0.00	0.00	0.00	M01
OK082	47.03	0.00	0.00	0.00	M01
OK090	94.27	0.00	0.00	0.00	M01
OK093	30.46	0.00	0.00	0.00	M01
OK095	61.17	0.00	0.00	0.00	M01
OK123	2.52	0.00	0.00	0.00	M01
OT100	58.94	0.00	0.00	0.00	M01
OT115	34.81	0.00	0.00	0.00	M01
OT133	49.35	0.00	0.00	0.00	M01
OT137	91.68	0.00	0.00	0.00	M01
OT143	89.57	0.00	0.00	0.00	M01
OT145	35.82	0.00	0.00	0.00	M01
OT146	78.99	0.00	0.00	0.00	M01
OT489	99.87	0.00	0.00	0.00	M01
OT491	68.02	0.00	0.00	0.00	M01
OT492	99.53	0.00	0.00	0.00	M01
OT493	38.99	0.00	0.00	0.00	M01
OT495	89.31	0.00	0.00	0.00	M01
OT496	71.64	0.00	0.00	0.00	M01
OT497	99.02	0.00	0.00	0.00	M01
OT500	43.24	0.00	0.00	0.00	M01
OT501	99.74	0.00	0.00	0.00	M01
OT502	99.71	0.00	0.00	0.00	M01
OT507	20.38	0.00	0.00	0.00	M01
OT508	2.03	0.00	0.00	0.00	M01
OT517	58.29	0.00	0.00	0.00	M01
OT518	21.52	0.00	0.00	0.00	M01
RLB094	54.90	0.00	0.00	0.00	M01
RLB107	96.65	0.00	0.00	0.00	M01
RLB116	1.27	0.00	0.00	0.00	M01
RLB141	7.46	0.00	0.00	0.00	M01
RLB203	0.07	0.00	0.00	0.00	M01
RLB203	15.95	0.00	0.00	0.00	M01
RLB248	52.07	0.00	0.00	0.00	M01
RLB249	26.44	0.00	0.00	0.00	M01
SWC031	70.63	0.00	0.00	0.00	M01
SWC041	7.63	0.00	0.00	0.00	M01
SWC050	9.59	0.00	0.00	0.00	M01
SWR008	15.29	0.00	0.00	0.00	M01
SWR017	97.86	0.00	0.00	0.00	M01
SWR023	67.27	0.00	0.00	0.00	M01
SWR026	93.42	0.00	0.00	0.00	M01

SWR061	87.69	0.00	0.00	0.00	M01
SWR083	0.09	0.00	0.00	0.00	M01
SWR134	87.17	0.00	0.00	0.00	M01
SWR139	0.91	0.00	0.00	0.00	M01
SWR147	41.39	0.00	0.00	0.00	M01
SWR187	1.48	0.00	0.00	0.00	M01
TAM116	3.50	0.00	0.00	0.00	M01
TAM117	10.44	0.00	0.00	0.00	M01
TAM208	3.40	0.00	0.00	0.00	M01
TAM236	56.07	0.00	0.00	0.00	M01
TAM239	0.53	0.00	0.00	0.00	M01
TAM240	9.20	0.00	0.00	0.00	M01
UT00454	95.88	0.00	0.00	0.00	M01
UT00466	55.38	0.00	0.00	0.00	M01
UT00775	42.15	0.00	0.00	0.00	M01
0100773	42.13	0.00	0.00	0.00	IVIOI
The following	specimens are assigned	to group Mimbres-	03.		
ID. NO.	M01	M03	M07A	M10	Assigned Group
ATT421	0.00	99.52	0.00	0.00	M03
ATT439	0.00	74.81	0.00	0.00	M03
BRE011	0.00	0.87	0.00	0.00	M03
BRE012	0.00	0.56	0.00	0.00	M03
BRE013	0.00	18.91	0.00	0.00	M03
BRE051	0.00	1.08	0.00	0.00	M03
BRE077	0.00	48.36	0.00	0.00	M03
BRE077	0.00	74.82	0.00	0.00	M03
BRE080A	0.00	15.06	0.00	0.00	M03
BRE081	0.00	49.02	0.00	0.00	M03
BRE083	0.00	14.84	0.00	0.00	M03
BRE084	0.00	4.43	0.00	0.00	M03
BRE085	0.00	45.79	0.00	0.00	M03
CAP166	0.00	2.70	0.00	0.00	M03
ED-026	0.00	61.36	0.00	0.00	M03
ED-094	0.00	8.61	0.00	0.00	M03
ED-095	0.00	65.72	0.00	0.00	M03
ED-097	0.00	45.13	0.00	0.00	M03
ED-099	0.00	25.70	0.00	0.00	M03
ED-104	0.00	6.01	0.00	0.00	M03
ED-105	0.00	16.04	0.00	0.00	M03
ED-107	0.00	58.83	0.00	0.00	M03
HM009	0.00	23.19	0.00	0.00	M03
HM051	0.00	52.28	0.00	0.00	M03
HM055	0.00	78.93	0.00	0.00	M03
HM078	0.00	10.74	0.00	0.00	M03
KCW002	0.00	55.17	0.00	0.00	M03
LOA008	0.00	86.37	0.00	0.00	M03
LOA009	0.00	90.26	0.00	0.00	M03
LOA015	0.00	34.21	0.00	0.00	M03
LOA021	0.00	98.06	0.00	0.00	M03
LOA025	0.00	19.78	0.00	0.00	M03
LOA063	0.00	81.36	0.00	0.00	M03
LOA064	0.00	88.98	0.00	0.00	M03
LOA065	0.00	51.99	0.00	0.00	M03
LOA066	0.00	25.60	0.00	0.00	M03
LOA067	0.00	51.28	0.00	0.00	M03
LOA068	0.00	89.14	0.00	0.00	M03
LOA069	0.00	33.72	0.00	0.00	M03
LOA073	0.00	95.96	0.00	0.00	M03
	- · - -			- · · · -	30

LOA074	0.00	99.64	0.00	0.00	M03
LOA098	0.00	52.13	0.00	0.00	M03
LOA099	0.00	59.79	0.00	0.00	M03
LOA166	0.00	92.98	0.00	0.00	M03
LOA167	0.00	15.10	0.00	0.00	M03
LOA170	0.00	58.37	0.00	0.00	M03
LOA172	0.00	87.61	0.00	0.00	M03
LOA192	0.00	97.84	0.00	0.00	M03
LOA193	0.00	91.21	0.00	0.00	M03
LOA194	0.00	7.49	0.00	0.00	M03
LOA195	0.00	23.64	0.00	0.00	M03
LOA196	0.00	90.73	0.00	0.00	M03
LOA197	0.00	96.64	0.00	0.00	M03
LOA199	0.00	79.91	0.00	0.00	M03
LOA200	0.00	67.02	0.00	0.00	M03
LOA201	0.00	7.76	0.00	0.00	M03
LOA202	0.00	92.78	0.00	0.00	M03
LOA203	0.00	85.45	0.00	0.00	M03
LOA204	0.00	32.30	0.00	0.00	M03
LOA212	0.00	97.31	0.00	0.00	M03
LOA213	0.00	72.18	0.00	0.00	M03
MPT007	0.00	4.73	0.00	0.00	M03
MRM150	0.00	64.52	0.00	0.00	M03
MRM193	0.00	57.11	0.00	0.00	M03
MRM207	0.00	69.09	0.00	0.00	M03
MRM208	0.00	47.02	0.00	0.00	M03
MRM211	0.00	96.39	0.00	0.00	M03
MVP0103	0.00	44.20	0.00	0.00	M03
OT195	0.00	0.90	0.00	0.00	M03
OT196	0.00	94.89	0.00	0.00	M03
OT197	0.00	49.20	0.00	0.00	M03
OT198	0.00	32.02	0.00	0.00	M03
OT199	0.00	47.67	0.00	0.00	M03
OT200	0.00	94.50	0.00	0.00	M03
OT230	0.00	63.83	0.00	0.00	M03
OT231	0.00	21.09	0.00	0.00	M03
OT232	0.00	94.65	0.00	0.00	M03
OT233	0.00	5.24	0.00	0.00	M03
OT234	0.00	0.72	0.00	0.00	M03
OT243	0.00	91.47	0.00	0.00	M03
OT544	0.00	68.41	0.00	0.00	M03
RLB028	0.00	7.99	0.00	0.00	M03
SWR180	0.00	1.33	0.00	0.00	M03
TAM056	0.00	91.96	0.00	0.00	M03
TAM059	0.00	88.80	0.00	0.00	M03
TAM060	0.00	49.64	0.00	0.00	M03
TAM063	0.00	97.22	0.00	0.00	M03
TAM064	0.00	21.62	0.00	0.00	M03
TAM066	0.00	61.23	0.00	0.00	M03
TAM074	0.00	94.05	0.00	0.00	M03
TAM076	0.00	91.78	0.00	0.00	M03
TAM077	0.00	9.84	0.00	0.00	M03
TAM078	0.00	17.34	0.00	0.00	M03
TAM079	0.00	40.20	0.00	0.00	M03
TAM080	0.00	20.76	0.00	0.00	M03
TAM081	0.00	93.27	0.00	0.00	M03
TAM082	0.00	3.79	0.00	0.00	M03
TAM083	0.00	87.44	0.00	0.00	M03

TAM084	0.00	14.12	0.00	0.00	M03
TAM085	0.00	74.45	0.00	0.00	M03
TAM086	0.00	2.67	0.00	0.00	M03
TAM087	0.00	73.52	0.00	0.00	M03
TAM088	0.00	1.32	0.00	0.00	M03
TAM089	0.00	35.23	0.00	0.00	M03
The following spe	ecimens are assigned	to group Mimbres-	-07A.		
ID. NO.	M01	M03	M07A	M10	Assigned Group
ATT356	0.00	0.00	30.59	0.12	M07A
ATT360	0.00	0.00	0.32	0.00	M07A
ATT363	0.00	0.00	70.05	0.17	M07A
ATT364	0.00	0.00	85.68	0.56	M07A
ATT365	0.00	0.00	18.87	0.01	M07A
ATT368	0.00	0.00	64.82	0.05	M07A
ATT369	0.00	0.00	90.68	0.87	M07A
ATT370	0.00	0.00	91.17	0.39	M07A
ATT371	0.00	0.00	19.59	1.17	M07A
ATT372	0.00	0.00	72.53	0.08	M07A
ATT376	0.00	0.00	29.30	0.01	M07A
ATT378	0.00	0.00	85.70	0.00	M07A
ATT432	0.00	0.00	45.24	1.10	M07A
ATT433	0.00	0.00	34.92	0.00	M07A
ATT435	0.00	0.00	24.30	0.00	M07A
ATT436	0.00	0.00	23.11	0.47	M07A
ATT437	0.00	0.00	1.17	0.02	M07A
ATT453	0.00	0.00	59.75	0.01	M07A
ATT455	0.00	0.00	25.08	0.00	M07A
ATT456	0.00	0.00	14.31	0.04	M07A
ATT458	0.00	0.00	51.69	0.01	M07A
ATT459	0.00	0.00	34.51	0.00	M07A
ATT462	0.00	0.00	74.46	0.00	M07A
ATT464	0.00	0.00	54.27	0.00	M07A
ATT466	0.00	0.00	98.29	0.00	M07A
ATT469	0.00	0.00	56.77	0.00	M07A
ATT470	0.00	0.00	47.55	0.00	M07A
ATT472	0.00	0.00	95.93	0.00	M07A
ATT474	0.00	0.00	89.48	0.00	M07A
ATT476	0.00	0.00	88.06	0.01	M07A
ATT478	0.00	0.00	98.63	0.00	M07A
ATT483	0.00	0.00	97.82	0.00	M07A
ATT484	0.00	0.00	10.28	0.00	M07A
ATT485	0.00	0.00	29.21	0.00	M07A
ATT486	0.00	0.00	64.67	0.00	M07A
ATT488	0.00	0.00	0.46	0.00	M07A
ATT490	0.00	0.00	89.58	0.00	M07A
ATT491	0.00	0.00	34.91	0.00	M07A
ATT494	0.00	0.00	47.17	0.00	M07A
ATT496	0.00	0.00	31.06	0.05	M07A
ATT501	0.00	0.00	76.23	0.03	M07A
KCW006	0.00	0.00	22.28	0.00	M07A M07A
KCW008	0.00	0.00	24.03	2.19	M07A
KCW010	0.00	0.00	24.03	0.00	M07A
VCAAOTO	0.00	0.00	2.03	0.00	IVIU/A

The following specimens are assigned to group Mimbres-10.										
ID. NO.	M01	M03	M07A	M10	Assigned Group					
ANI002	0.00	0.00	0.00	0.56	M10					
ANI004	0.00	0.00	0.00	35.10	M10					
ANI005	0.00	0.00	0.00	77.85	M10					
ANI006	0.00	0.00	0.00	77.11	M10					
ANI007	0.00	0.00	0.00	83.26	M10					
ANI010	0.00	0.00	0.00	48.06	M10					
ATT043	0.00	0.00	0.00	0.70	M10					
ATT349	0.00	0.00	0.00	95.63	M10					
ATT350	0.00	0.00	0.00	94.35	M10					
ATT351	0.00	0.00	0.00	99.97	M10					
ATT352	0.00	0.00	0.00	99.22	M10					
ATT355	0.00	0.00	0.00	0.15	M10					
ATT366	0.00	0.00	0.00	53.33	M10					
ATT374	0.00	0.00	0.00	99.37	M10					
ATT398	0.00	0.00	0.00	19.23	M10					
ATT408	0.00	0.00	0.00	89.46	M10					
ATT465	0.00	0.00	0.00	93.76	M10					
ATT468	0.00	0.00	0.00	8.75	M10					
ATT473	0.00	0.00	0.00	99.10	M10					
ATT482	0.00	0.00	0.00	73.29	M10					
ATT493	0.00	0.00	0.00	40.14	M10					
ATT497	0.00	0.00	0.00	90.69	M10					
ATT498	0.00	0.00	0.00	15.66	M10					
BRE027	0.00	0.00	0.00	0.94	M10					
BRE061	0.00	0.00	0.00	0.59	M10					
BRE062	0.00	0.00	0.00	44.99	M10					
BRE064A	0.00	0.00	0.00	0.32	M10					
BRE166	0.00	0.00	0.00	67.62	M10					
BRE167	0.00	0.00	0.00	44.00	M10					
BRE188	0.00	0.00	0.00	4.18	M10					
BRE189	0.00	0.00	0.00	38.83	M10					
HM028	0.00	0.00	0.00	25.74	M10					
JAM009	0.00	0.00	0.00	9.52	M10					
JAM015	0.00	0.00	0.00	41.25	M10					
JAM016	0.00	0.00	0.00	16.20	M10					
JAM017	0.00	0.00	0.00	2.41	M10					
JAM022	0.00	0.00	0.00	28.45	M10					
JAM035	0.00	0.00	0.00	42.18	M10					
JAM041	0.00	0.00	0.00	99.91	M10					
JAM047	0.00	0.00	0.00	92.97	M10					
JAM052	0.00	0.00	0.00	83.33	M10					
JAM054	0.00	0.00	0.00	48.78	M10					
JAM056	0.00	0.00	0.00	88.73	M10					
JAM060	0.00	0.00	0.00	77.52	M10					
JAM062	0.00	0.00	0.00	6.68	M10					
JAM068	0.00	0.00	0.00	20.87	M10					
JAM078	0.00	0.00	0.00	63.13	M10					
JAM081	0.00	0.00	0.00	25.70	M10					
JAM087	0.00	0.00	0.00	78.17	M10					
JAM089	0.00	0.00	0.00	58.35	M10					
JAM116	0.00	0.00	0.00	25.87	M10					
JAM123	0.00	0.00	0.00	95.34	M10					
JAM125	0.00	0.00	0.00	3.67	M10					
JAM135	0.00	0.00	0.00	99.96	M10					
KCW005	0.00	0.00	0.00	44.60	M10					
KCW007	0.00	0.00	0.00	12.48	M10					

KCW009	0.00	0.00	0.00	99.01	M10
KCW012	0.00	0.00	0.00	82.87	M10
KCW013	0.00	0.00	0.00	88.41	M10
KCW019	0.00	0.00	0.00	42.65	M10
KCW021	0.00	0.00	0.00	72.45	M10
KCW023	0.00	0.00	0.00	4.70	M10
LOA040	0.00	0.00	0.00	43.24	M10
MPC020	0.00	0.00	0.00	47.76	M10
MVP0229	0.00	0.00	0.00	2.04	M10
OT184	0.00	0.00	0.00	44.35	M10
OT206	0.00	0.00	0.00	98.56	M10
OT212	0.00	0.00	0.00	63.20	M10
OT257	0.00	0.00	0.00	86.22	M10
OT259	0.00	0.00	0.00	45.75	M10
OU0028	0.00	0.00	0.00	63.82	M10
OU0032	0.00	0.00	0.00	32.83	M10
OU0042	0.00	0.00	0.00	44.80	M10
OU0045	0.00	0.00	0.00	40.49	M10
OU0046	0.00	0.00	0.00	80.55	M10
OU0047	0.00	0.00	0.00	2.85	M10
OU0050	0.00	0.00	0.00	77.83	M10
PDR033	0.00	0.00	0.00	36.81	M10
PDR037	0.00	0.00	0.00	3.66	M10
RLB052	0.00	0.00	0.00	4.61	M10
RLB178	0.00	0.00	0.00	4.69	M10
UT00451	0.00	0.00	0.00	82.18	M10
UT00455	0.00	0.00	0.00	86.94	M10
UT00464	0.00	0.00	0.00	92.17	M10
UT00468	0.00	0.00	0.00	65.24	M10
UT00480	0.00	0.00	0.00	27.66	M10
UT00481	0.00	0.00	0.00	27.25	M10
UT00485	0.00	0.00	0.00	70.65	M10
UT00486	0.00	0.00	0.00	5.38	M10
UT00489	0.00	0.00	0.00	79.29	M10

Table A2. Macro Group A Mahalanobis distance calculations for specimens projected against two or more groups

Groups Evaluated:

Mimbres-07B (M07B)

Mimbres-13 (M13)

Unassigned A

Variables used:

As, La, Lu, Nd, Sm, U, Yb, Ce, Cr, Cs, Eu, Fe, Hf, Rb, Sb, Sc, Ta, Th, Zn, Zr, Al, Ba, Dy, Mn, Na, Ti, V

The following specimens are assigned to group Mimbres-07B.										
ID. NO.	M01	M03	M07A	M10	Assigned Group					
ATT343	0.00	0.00	0.00	0.00	M07B					
ATT434	0.00	0.00	0.00	0.00	M07B					
ATT461	0.00	0.00	0.01	0.00	M07B					
ATT477	0.00	0.00	0.01	0.00	M07B					
ATT481	0.00	0.00	0.07	0.00	M07B					
ATT487	0.00	0.00	0.37	0.00	M07B					
ATT492	0.00	0.00	0.00	0.00	M07B					
The following specime	_									
ID. NO.	M01	M03	M07A	M10	Assigned Group					
MRM030	0.00	0.00	0.00	0.00	M13					
MRM065	0.00	0.00	0.00	0.00	M13					
MRM171	0.00	0.00	0.00	0.00	M13					
MRM180	0.00	0.00	0.00	0.00	M13					
The following specime	ns are not assig	ned.								
ID. NO.	M01	M03	M07A	M10	Assigned Group					
ATT344	0.00	0.00	0.00	0.02	Unassigned					
ATT346	0.00	0.00	0.00	0.00	Unassigned					
ATT353	0.00	0.00	0.00	0.46	Unassigned					
ATT389	0.00	0.00	0.00	0.00	Unassigned					
ATT438	0.00	0.00	0.00	0.00	Unassigned					
ATT440	0.00	0.00	0.00	0.07	Unassigned					
ATT442	0.00	0.00	0.00	0.00	Unassigned					
BRE041	0.00	0.00	0.00	0.00	Unassigned					
BRE101	0.00	0.00	0.00	0.00	Unassigned					
CAP178	0.00	0.00	0.00	0.00	Unassigned					
CAP201	0.00	0.00	0.00	0.00	Unassigned					
ED-001	0.00	0.00	0.00	0.00	Unassigned					
ED-059	0.00	0.00	0.00	0.01	Unassigned					
JAM057	0.00	0.00	0.00	0.00	Unassigned					
JAM063	0.00	0.00	0.00	0.01	Unassigned					
JAM073	0.00	0.00	0.00	0.00	Unassigned					
JAM074	0.00	0.00	0.00	0.00	Unassigned					
LOA024	0.00	0.00	0.00	0.00	Unassigned					
MPM021	0.00	0.00	0.00	0.00	Unassigned					
MPP014	0.00	0.00	0.00	0.00	Unassigned					
MPT005	0.00	0.00	0.00	0.00	Unassigned					
MRM038	0.00	0.00	0.00	0.00	Unassigned					
MRM042	0.00	0.00	0.00	0.00	Unassigned					
MRM079	0.00	0.00	0.00	0.00	Unassigned					
MRM256	0.00	0.00	0.00	0.00	Unassigned					
MRM262	0.00	0.00	0.00	0.00	Unassigned					
MVP0079	0.00	0.00	0.00	0.00	Unassigned					
OT048	0.00	0.00	0.00	0.00	Unassigned					
OT105	0.00	0.00	0.00	0.01	Unassigned					
	0.00	0.00	0.00	0.02	2					

OT181	0.00	0.00	0.00	0.05	Unassigned
OT269	0.00	0.00	0.00	0.00	Unassigned
RLB101	0.02	0.00	0.00	0.00	Unassigned
RLB190	0.00	0.00	0.00	0.00	Unassigned
RLB227	0.03	0.00	0.00	0.00	Unassigned
SWR012	0.00	0.00	0.00	0.00	Unassigned
SWR031	0.29	0.00	0.00	0.00	Unassigned
SWR057	0.00	0.00	0.00	0.00	Unassigned
SWR112	0.00	0.00	0.00	0.00	Unassigned
SWR128	0.00	0.00	0.00	0.00	Unassigned
SWR199	0.04	0.00	0.00	0.00	Unassigned
TAM218	0.00	0.00	0.00	0.00	Unassigned
TAM251	0.00	0.00	0.00	0.00	Unassigned
UT00465	0.00	0.00	0.00	0.01	Unassigned
UT00493	0.00	0.00	0.00	0.00	Unassigned

Table A3. Principal component analysis for Macro Group A pottery (R-Q factor analysis based on variance-covariance matrix).

Eigenvalues and Percentage of Variance Explained:

Cum. %Var.	61.08	78.09	83.98	87.11	89.34	91.18	92.61	93.66	94.61	95.40	96.17	96.83	97.41	97.85	98.24	98.55	98.84	90.66	99.25	99.41	99.54	99.62	92.66	99.84	99.90	96.66	100.00
	61.08	17.01	5.89	3.13	2.23	1.84	1.42	1.05	96.0	0.79	0.77	99.0	0.57	0.45	0.39	0.31	0.29	0.21	0.19	0.16	0.13	0.11	0.11	0.08	90.0	90.0	0.04
Eigenvalue	0.914	0.255	0.088	0.047	0.033	0.028	0.021	0.016	0.014	0.012	0.012	0.010	0.009	0.007	90000	0.005	0.004	0.003	0.003	0.002	0.002	0.002	0.002	0.001	0.001	0.001	0.001
PCA	\vdash	2	3	4	2	9	7	8	6	10	11	12	13	14	15	16	17	18	19	20	21	22	23	24	25	56	27

tors (larges	arges	: ب	to sm.	allest):			0																	0	9	
3 0.02 0.41 -0.33 0.21	2 0.41 -0.33 0.21 (1 -0.33 0.21	3 0.21 (0.0		0.39		1	0.44 -0	•	•		•			0.04 0.			•			•	•	-0.01	
3 0.20 -0.30 -0.23 -0.03 -0.) -0.30 -0.23 -0.03 -0.) -0.23 -0.03 -0.	3 -0.03 -0.	٠	8		0.03		•	•										•					-0.07	
5 -0.18 -0.02 -0.14 0.15 -0.0	3 -0.02 -0.14 0.15 -0.0	? -0.14 0.15 -0.0	4 0.15 -0.0	- 0.	28		0.00	-									-								0.02	
0 0.02 -0.12 -0.15 0.02 -0.2	2 -0.12 -0.15 0.02 -0.2	? -0.15 0.02 -0.2	5 0.02 -0.2	2 -0.2	(3)		0.07		•																0.02	
2 -0.11 -0.07 -0.17 0.10 -0.0	1 -0.07 -0.17 0.10 -0.0	7 -0.17 0.10 -0.C	7 0.10 -0.0	0.0- 0	∞		0.08		•					•											0.06	
2 0.12 -0.22 -0.26 0.02 0.3	2 -0.22 -0.26 0.02 0.3	? -0.26 0.02 0.3	5 0.02 0.2	2 0.2	53		-0.26																		-0.04	
3 -0.26 0.01 -0.12 0.15 -0.3	5 0.01 -0.12 0.15 -0.0	0.12 0.15 -0.3	2 0.15 -0.2	5.0	$^{\circ}$		0.01	-		-	-				-		-								0.05	
1 0.10 -0.25 -0.17 -0.06 0.0	7 -0.25 -0.17 -0.06 0.0	5 -0.17 -0.06 0.0	7 -0.06 0.0	5 0.0	$\widetilde{\omega}$		0.00		•																0.05	
1 0.11 0.41 0.21 0.00 0.2	1 0.41 0.21 0.00 0.2	0.21 0.00 0.2	1 0.00 0.2	0.2			-0.21																		0.07	
1 0.32 0.15 -0.49 0.18 0.0	2 0.15 -0.49 0.18 0.0	5 -0.49 0.18 0.0	9 0.18 0.0	3 0.0	$\overline{}$		-0.12																		-0.04	
2 0.21 -0.12 -0.12 -0.02 0.0	1 -0.12 -0.12 -0.02 0.0	? -0.12 -0.02 0.C	2 -0.02 0.C	2 0.0	7		0.04			-					-										0.02	
0 0.12 0.22 0.03 0.02 0.1	2 0.22 0.03 0.02 0.1	0.03 0.02 0.1	3 0.02 0.1	2 0.1	$\overline{}$		-0.11		•																0.16	
1 -0.07 -0.14 -0.04 -0.01 0.1	7 -0.14 -0.04 -0.01 0.1	1 -0.04 -0.01 0.1	1 -0.01 0.1	1 0.1	∞		-0.08		•																0.02	
1 -0.09 0.14 -0.09 0.15 -0.1	9 0.14 -0.09 0.15 -0.1	1 -0.09 0.15 -0.1	9 0.15 -0.1	5 -0.1	7		90.0-																		0.05	
3 0.11 0.33 -0.36 0.01 -0.1	1 0.33 -0.36 0.01 -0.1	3 -0.36 0.01 -0.1	5 0.01 -0.1	1 -0.1	()		-0.09								-		-								0.00	
1 0.09 0.11 0.04 0.05 0.12	9 0.11 0.04 0.05 0.13	0.04 0.05 0.13	4 0.05 0.13	5 0.13	\sim	0.00	-0.15	0.03	-0.03	-0.11	0- 90.0-	-0.04 0.	0.16 -0.	-0.07 0	0.17 -0.	-0.18 -0.	-0.15 0.	0.01 -0.11	11 -0.21	21 0.17	17 0.02	02 -0.32	2 -0.53	-0.39	-0.37	
4 -0.02 -0.02 -0.11 0.10 -0.0	2 -0.02 -0.11 0.10 -0.09	9-0.11 0.10 -0.0	1 0.10 -0.0	0.0- (117		-0.01																		-0.07	
3 0.08 -0.09 -0.15 0.02 -0.0	3 -0.09 -0.15 0.02 -0.0	9 -0.15 0.02 -0.0	5 0.02 -0.0	2 -0.0	(Y)		0.01		•																-0.08	
5 -0.13 0.11 -0.06 0.08 -0.0	3 0.11 -0.06 0.08 -0.0	0.0- 80.0 90.0- 1	5 0.08 -0.0	3 -0.0	4		-0.74		•	•		-													0.02	
4 0.06 -0.15 -0.07 -0.06 0.1	5 -0.15 -0.07 -0.06 0.1	5 -0.07 -0.06 0.1	7 -0.06 0.1	5 0.1	O.		-0.09							•											0.04	
2 0.06 -0.03 -0.04 0.01 0.0	5 -0.03 -0.04 0.01 0.0	3 -0.04 0.01 0.0	4 0.01 0.0	1 0.0	\simeq		0.00		•	•															0.89	
5 0.50 0.13 0.17 -0.28 -0.6	0.13 0.17 -0.28 -0.6	3 0.17 -0.28 -0.6	7 -0.28 -0.6	3 -0.6	5		90.0-																		-0.02	
5 -0.28 0.00 -0.07 0.16 -0.1	3 0.00 -0.07 0.16 -0.1	0.07 0.16 -0.1	7 0.16 -0.1	5 -0.1	π)		0.14	-																	-0.06	
5 -0.33 0.20 -0.33 -0.83 0.0	3 0.20 -0.33 -0.83 0.0	0.33 -0.83 0.0	3 -0.83 0.0	3 0.0	$\overline{}$		0.02		•																-0.01	
2 0.30 -0.20 -0.09 -0.14 0.2	7 -0.20 -0.09 -0.14 0.2	.0.09 -0.14 0.2	9 -0.14 0.2	4 0.2	π)		0.07																		-0.02	
9 0.15 -0.01 0.10 -0.05 0.2	5 -0.01 0.10 -0.05 0.2	0.10 -0.05 0.2	0.05 0.2	5 0.2	9		90.0				0.32 0	•	0.29 -0.					08 -0.09							0.01	
V 0.19 0.21 0.24 0.12 0.01 0.2	1 0.24 0.12 0.01 0.2	1 0.12 0.01 0.2	2 0.01 0.2	1 0.2	S		0.27	- 90.0-	_				_				-			-					-0.01	

	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	-0.01	0.00	0.00	0.00	0.00	0.02	0.00	0.00	0.00	0.00	0.00	0.00
	0.00	0.00	-0.01	0.00	0.00	0.00	0.02	0.00	0.00	0.00	0.00	0.01	0.00	0.00	0.00	-0.01	0.00	0.00	0.00	0.00	-0.01	0.00	0.00	0.00	0.00	0.00	0.00
	0.00	0.01	0.01	0.00	0.00	0.00	-0.01	-0.01	0.00	0.00	0.01	0.01	0.01	0.00	0.00	-0.02	0.00	0.01	0.00	0.00	-0.01	0.00	0.00	0.00	0.00	0.00	0.00
							•									•					•					0.00	
		•									•		•			•					•					0.00	
																		•								0.00	
																										0.00	
																										0.00	
																										0.00	
	0.00	0.00	0.02	0.01	-0.03	0.00	0.01	0.01	0.00	0.01	0.01	-0.01	0.00	-0.02	0.00	-0.01	-0.01	-0.02	0.00	0.01	0.00	0.00	-0.01	0.00	-0.01	-0.01	0.01
	0.01	0.01	0.00	0.00	0.00	-0.01	0.00	0.02	0.03	0.00	-0.01	-0.04	0.00	-0.01	0.00	-0.01	0.02	0.02	0.01	-0.01	0.00	0.00	-0.01	0.00	-0.01	0.00	0.01
	-0.01	0.00	0.01	0.02	-0.02	0.01	0.00	0.01	-0.01	-0.02	-0.01	0.02	0.00	0.01	0.01	0.01	0.04	0.02	-0.01	0.00	0.00	0.00	-0.01	0.00	-0.01	-0.01	0.02
	-0.01	0.00	-0.01	0.01	0.02	0.00	0.00	-0.01	-0.01	0.01	-0.02	-0.01	0.02	0.01	0.00	-0.01	-0.01	-0.01	0.01	0.02	0.00	0.01	0.00	0.00	0.01	-0.04	0.04
	0.00	0.02	0.00	-0.06	0.00	-0.01	0.00	0.02	0.00	0.00	0.02	0.01	0.00	0.00	0.00	0.01	-0.01	0.01	-0.01	0.01	0.01	0.00	0.01	0.00	-0.03	-0.02	0.01
	-0.01	0.00	0.00	-0.01	0.00	0.01	0.00	0.00	-0.04	0.00	0.01	-0.01	-0.02	-0.01	0.00	0.00	-0.01	0.00	0.04	-0.03	0.01	0.00	0.02	0.00	0.00	0.03	0.05
	•		•				•												•		•	•			•	0.03	
	-0.05	-0.02	0.03	-0.03	-0.01	0.00	0.03	-0.01	0.02	0.01	0.00	-0.02	0.00	0.00	0.04	-0.01	0.02	-0.01	-0.02	0.00	0.00	0.01	0.03	0.00	0.04	0.01	0.00
	0.00	0.01	-0.02	0.01	0.02	0.02	-0.01	0.01	0.02	-0.05	0.02	-0.01	-0.04	-0.02	0.05	0.00	-0.03	0.00	0.00	-0.03	0.00	-0.02	0.00	-0.01	0.01	-0.03	-0.01
nent):	0.01	0.01	-0.01	-0.01	-0.01	-0.08	0.00	0.01	-0.03	-0.02	0.00	0.00	0.03	-0.01	0.04	0.00	0.00	0.00	0.03	0.02	0.00	-0.02	-0.01	-0.01	0.04	0.01	-0.01
odwo	0.05	0.00	0.00	0.01	0.01	-0.03	0.00	0.00	-0.03	-0.02	0.01	-0.01	-0.01	-0.01	-0.01	-0.02	0.00	0.00	-0.09	-0.01	0.00	-0.01	0.02	0.00	0.01	0.01	0.03
allest c	-0.06	0.02	-0.02	0.04	0.00	-0.06	-0.01	0.00	0.02	90.0	0.02	0.01	-0.04	0.01	-0.02	0.01	-0.01	0.01	-0.01	-0.03	0.00	-0.05	-0.01	0.01	0.00	-0.02	0.00
to sm	0.01	-0.01	-0.01	-0.04	-0.01	0.04	-0.02	0.01	0.04	0.00	0.00	0.02	0.03	-0.02	-0.02	0.02	-0.01	-0.01	-0.01	0.03	0.00	-0.11	-0.03	0.01	0.04	0.04	0.05
argest	0.04	-0.01	0.03	0.00	0.02	0.00	0.03	-0.01	0.00	0.03	0.00	0.00	0.00	0.03	0.00	0.01	0.02	0.00	0.02	-0.01	0.00	-0.05	0.03	-0.15	-0.03	-0.01	0.00
atrix (I	-0.07	-0.05	-0.03	-0.03	-0.04	-0.06	-0.03	-0.04	0.04	-0.11	-0.03	0.01	-0.01	-0.02	-0.08	0.01	-0.02	-0.03	-0.01	-0.02	-0.01	0.04	-0.01	-0.07	-0.02	0.02	0.03
ling M	0.12	-0.09	-0.01	-0.03	-0.02	-0.07	0.00	-0.07	0.12	0.05	-0.04	90.0	-0.04	0.04	0.10	0.03	-0.01	-0.03	0.03	-0.05	-0.01	0.04	0.00	90.0	-0.06	0.00	0.07
ır Loac	0.01	0.10	-0.09	0.01	-0.05	90.0	-0.13	0.05	0.05	0.16	0.10	90.0	-0.03	-0.05	90.0	0.04	-0.01	0.04	-0.06	0.03	0.03	0.25	-0.14	-0.17	0.15	0.07	0.11
d Facto	0.03	0.17	0.14	0.29	0.30	0.12	0.22	0.20	0.30	.0.20	0.31	0.20	0.13	.0.04	0.12	0.20	.0.03	.0.02	0.15	0.13	·0.02	0.15	0.34	0.05	0.02	0.18	0.18
Scale	As	Га	ב	Νq	Sm	⊃	γþ	Ce	ن	ა	Eu	Fe	Ŧ	Rb	Sp.	Sc	Та	드	Zu	Zr	₹	Ва	Δ	Σ	Na	Ti 0.18 0.07 0.00 0.02 -0.01 0.04 -0.02 0.01 0.01 -0.0	>

Appendix B:
Macro Group B Mahalanobis Distance Calculations and PCA Scores

Table B1. Macro Group B-1 Mahalanobis distance calculations for specimens projected against two or more groups.

Mimbres-04A (M04A)

Mimbres-04B (M04B)

Mimbres-04C (M04C)

Mimbres-05A (M05A)

Mimbres-05B (M05B)

Variables used:

ED-006

61.2

0.0

As, La, Lu, Nd, Sm, U, Yb, Ce, Cr, Cs, Eu, Fe, Hf, Rb, Sb, Sc, Ta, Th, Zn, Zr, Al, Ba, Dy, Mn, Na, Ti, V

The following specimens are assigned to group Mimbres-04A.						
ID. NO.	M04A	M04B	M04C	M05A	M05B	Group
ATT402	43.5	0.0	0.0	0.0	0.0	M04A
ATT413	93.4	0.0	9.8	0.0	5.7	M04A
BAS019	28.2	0.0	0.0	0.0	0.1	M04A
BAS036	86.6	0.0	23.7	0.0	1.9	M04A
BAS038	77.3	0.0	5.6	0.0	4.7	M04A
BAS048	14.2	0.0	0.0	0.0	2.2	M04A
BAS049	66.6	0.0	1.5	0.0	0.0	M04A
BAS050	66.1	0.0	1.7	0.0	0.0	M04A
BAS054	78.8	0.0	10.3	0.0	0.0	M04A
BAS055	65.1	0.0	1.4	0.0	2.2	M04A
BAS056	80.5	0.0	49.8	0.0	0.1	M04A
BAS058	83.9	0.0	36.8	0.0	0.6	M04A
BAS064	76.2	12.9	0.2	0.0	1.7	M04A
BAS070	13.9	0.0	0.0	0.0	0.0	M04A
BAS072	43.1	0.0	0.1	0.0	0.0	M04A
BAS075	47.5	0.0	0.2	0.0	0.0	M04A
BAS201	99.6	0.0	21.3	0.0	0.2	M04A
BAS216	79.6	0.0	0.1	0.0	0.1	M04A
BAS218	71.0	0.0	3.3	0.0	0.0	M04A
BAS220	40.4	0.0	0.7	0.0	0.0	M04A
BAS224	96.0	0.0	0.3	0.0	0.8	M04A
BRE002	83.4	0.0	0.1	0.0	0.0	M04A
BRE037	4.4	0.0	0.2	0.0	0.0	M04A
BRE059	66.4	0.0	0.4	0.0	4.4	M04A
BRE063	73.4	0.0	11.4	0.0	0.0	M04A
BRE097	45.7	0.0	0.1	0.0	0.1	M04A
BRE099	43.4	0.0	0.0	0.0	0.1	M04A
BRE102	16.7	0.0	0.0	0.0	0.0	M04A
BRE107	79.5	0.0	3.7	0.0	0.0	M04A
BRE159	49.8	0.0	0.8	0.0	0.0	M04A
BRE186	97.4	0.0	3.1	0.0	0.0	M04A
CAP164	17.8	0.0	0.5	0.0	0.1	M04A
ED-002	6.3	0.0	0.0	0.0	0.0	M04A
ED-003	50.0	0.0	0.9	0.0	0.0	M04A

0.0

0.0

0.0

M04A

ED-008	49.7	0.9	0.1	0.0	0.0	M04A
ED-009	51.9	0.0	0.1	0.0	0.0	M04A
ED-010	0.6	0.0	0.0	0.0	0.0	M04A
ED-011	94.8	0.0	1.1	0.0	0.0	M04A
ED-013	63.0	0.2	0.0	0.0	0.1	M04A
ED-015	62.6	0.0	0.1	0.0	0.0	M04A
ED-016	37.2	23.9	0.5	0.0	0.0	M04A
ED-020	35.2	0.0	0.9	0.0	0.2	M04A
ED-030	70.8	0.0	0.1	0.0	0.0	M04A
ED-031	65.5	0.0	12.7	0.0	0.3	M04A
ED-032	52.5	0.0	0.1	0.0	0.0	M04A
ED-033	64.4	0.1	0.0	0.0	0.0	M04A
ED-034	67.9	0.5	0.0	0.0	0.0	M04A
ED-041	48.2	0.0	4.5	0.0	0.9	M04A
ED-043	94.3	0.0	1.0	0.0	0.6	M04A
ED-053	23.2	2.0	0.0	0.0	0.1	M04A
ED-057	18.6	0.0	0.0	0.0	0.0	M04A
ED-079	95.5	0.0	5.9	0.0	0.0	M04A
HM001	63.3	0.0	0.5	0.0	0.0	M04A
HM002	1.0	0.0	0.0	0.0	0.0	M04A
HM003	8.4	0.0	0.0	0.0	0.0	M04A
HM004	71.4	0.0	0.3	0.0	0.0	M04A
HM006	37.3	0.0	0.5	0.0	0.0	M04A
HM011	92.7	0.0	9.7	0.0	0.4	M04A
HM012	63.3	0.4	0.0	0.0	0.0	M04A
HM017	93.1	0.0	0.1	0.0	0.0	M04A
HM026	99.7	0.0	3.0	0.0	6.0	M04A
HM027	92.4	0.0	7.8	0.0	0.0	M04A
HM032	48.3	0.0	0.7	0.0	0.0	M04A
HM039	34.9	0.0	0.2	0.0	0.0	M04A
HM041	94.7	0.0	3.5	0.0	0.0	M04A
HM044	56.8	0.0	0.0	0.0	0.0	M04A
HM052	81.1	0.0	1.0	0.0	0.0	M04A
HM060	94.8	0.0	11.8	0.0	0.1	M04A
HM069	37.5	0.0	0.0	0.0	0.0	M04A
HM075	99.6	0.0	9.7	0.0	0.1	M04A
JAM013	0.8	0.0	0.0	0.0	0.0	M04A
JAM018	19.0	0.0	0.0	0.0	0.0	M04A
JAM030	62.0	0.0	0.0	0.0	0.0	M04A
JAM040	97.4	0.0	0.8	0.0	0.0	M04A
JAM043	98.3	0.0	10.0	0.0	0.0	M04A
JAM051	47.1	0.0	6.5	0.0	0.1	M04A
JAM058	0.3	0.0	0.0	0.0	0.0	M04A
JAM059	51.3	0.0	0.0	0.0	0.0	M04A
JAM061	98.7	0.0	12.9	0.0	0.1	M04A
JAM064	50.5	0.0	2.4	0.0	0.0	M04A
JAM065	92.8	0.0	0.5	0.0	0.0	M04A
JAM079	92.4	0.0	0.0	0.0	0.0	M04A
JAM082	65.5	0.0	0.0	0.0	0.0	M04A
JAM083	92.4	0.0	17.6	0.5	1.1	M04A
JAM096	1.1	0.0	0.0	0.0	0.0	M04A
JAM097	63.2	0.0	0.0	0.0	0.0	M04A
JAM119	72.0	2.8	0.1	0.0	0.0	M04A

LOA003	59.3	0.0	2.3	0.0	0.0	M04A
LOA043	84.6	0.8	0.1	0.0	0.0	M04A
LOA155	99.6	0.0	22.5	0.0	6.1	M04A
LOA157	96.6	0.0	2.3	0.0	2.7	M04A
LOA162	97.4	0.0	1.8	0.0	0.1	M04A
LOA221	70.0	0.0	6.9	0.0	0.1	M04A
MPC012	5.6	0.0	0.0	0.0	0.0	M04A
MPC013	48.6	0.0	0.8	0.0	0.0	M04A
MPC015	26.2	0.0	0.0	0.0	0.0	M04A
MPC016	49.9	0.0	0.1	0.0	3.9	M04A
MPM001	41.2	0.0	1.4	0.0	0.0	M04A
MPM006	34.2	0.0	0.2	0.0	0.0	M04A
MPM007	0.2	0.0	0.0	0.0	0.0	M04A
MPM009	0.1	0.0	0.0	0.0	0.0	M04A
MPM011	0.1	0.0	0.0	0.0	0.0	M04A
MPM013	13.9	0.0	0.0	0.0	0.9	M04A
MPM017	79.2	0.0	0.4	0.0	3.4	M04A
MPM027	0.0	0.0	0.0	0.0	0.0	M04A
MPN001	0.2	0.0	0.0	0.0	0.0	M04A
MPN006	0.3	0.0	0.0	0.0	0.0	M04A
MPN011	0.0	0.0	0.0	0.0	0.0	M04A
MPN017	18.4	0.0	0.1	0.0	0.0	M04A
MPN024	0.1	0.0	0.0	0.0	0.0	M04A
	2.6					
MRM001		0.0	0.0	0.0	0.0	M04A
MRM027	60.1	0.0	7.8	0.0	0.0	M04A
MRM028	66.1	0.0	0.2	0.0	0.0	M04A
MRM044	2.1	0.0	0.0	0.0	0.0	M04A
MRM057	2.2	0.0	0.0	0.0	0.0	M04A
MRM096	29.9	0.0	0.8	0.0	0.0	M04A
MRM097	23.0	0.0	5.5	0.0	0.3	M04A
MRM101	54.8	0.0	0.1	0.0	1.8	M04A
MRM146	39.1	0.0	0.6	0.0	0.2	M04A
MRM154	21.2	0.0	0.0	0.0	0.3	M04A
MRM157	83.6	0.0	4.8	0.0	1.7	M04A
MRM159	94.7	0.2	2.6	0.0	1.7	M04A
MRM162	98.7	0.0	10.3	0.0	0.1	M04A
MRM210	13.6	0.0	0.4	0.0	0.0	M04A
MVP0006	1.2	0.0	0.0	0.0	0.0	M04A
MVP0009	52.5	0.0	8.9	0.3	0.2	M04A
MVP0021	89.7	0.0	4.3	0.0	0.9	M04A
MVP0022	82.8	0.0	17.9	0.0	0.4	M04A
MVP0027	93.6	0.0	2.2	0.0	0.1	M04A
MVP0028	44.8	0.0	0.3	0.0	0.0	M04A
MVP0029	95.7	0.0	7.5	0.0	0.5	M04A
MVP0032	23.9	0.0	0.2	0.0	0.1	M04A
MVP0041	98.3	0.0	12.0	0.0	0.1	M04A
MVP0044	98.7	0.0	30.5	0.0	0.1	M04A
MVP0054	77.9	0.0	7.8	0.0	0.3	M04A
MVP0057	68.1	22.1	16.3	0.0	4.2	M04A
MVP0066	0.4	0.0	0.0	0.0	0.0	M04A
MVP0080	8.7	1.0	0.0	0.0	0.0	M04A
MVP0084	45.4	0.0	0.2	0.0	0.0	M04A
MVP0097	23.5	0.0	0.0	0.0	0.0	M04A

MVP0109	28.5	0.0	2.3	0.0	0.1	M04A
MVP0110	37.0	0.6	0.1	0.0	0.0	M04A
MVP0115	81.2	0.0	1.3	0.0	0.0	M04A
MVP0130	82.6	0.0	1.3	0.0	10.8	M04A
MVP0137	65.0	0.0	0.0	0.0	0.0	M04A
MVP0140	88.9	0.0	0.0	0.0	0.0	M04A
MVP0145	52.8	0.0	4.1	0.0	0.0	M04A
MVP0146	52.2	0.0	0.0	0.0	3.2	M04A
MVP0150	80.6	0.0	0.0	0.0	0.3	M04A
MVP0159	86.8	0.0	0.1	0.0	0.0	M04A
MVP0163	15.4	0.0	0.0	0.0	2.2	M04A
MVP0164	100.0	0.0	8.8	0.0	0.2	M04A
MVP0169	70.6	0.0	0.0	0.0	0.0	M04A
MVP0171	36.8	0.0	9.5	0.0	0.2	M04A
MVP0174	10.9	0.0	0.0	0.0	0.0	M04A
MVP0181	83.9	0.0	1.8	0.0	0.0	M04A
MVP0188	99.9	0.0	11.7	0.0	2.9	M04A
MVP0195	43.7	0.0	0.4	0.0	0.1	M04A
MVP0206	26.4	0.0	3.8	0.0	0.0	M04A
MVP0213	96.5	0.0	5.2	0.0	0.0	M04A
MVP0224	99.9	15.2	13.8	0.0	1.7	M04A
MVP0225	98.2	0.0	13.2	0.0	1.7	M04A
MVP0232	63.9	0.0	3.2	0.0	1.0	M04A
MVP0235	97.6	0.0	30.3	0.0	0.4	M04A
MVP0237	45.3	0.0	0.1	0.0	0.0	M04A
MVP0238	92.9	0.0	13.5	0.0	0.1	M04A
MVP0243	73.5	0.0	0.0	0.0	0.4	M04A
MVP0245	81.7	0.0	0.0	0.0	0.0	M04A
MVP0246	57.5	0.0	0.9	0.0	0.1	M04A
MVP0247	22.0	0.0	2.0	0.0	0.1	M04A
MVP0261	0.0	0.0	0.0	0.0	0.0	M04A
MVP0264	91.6	0.0	1.4	0.0	0.0	M04A
MVP0266	32.7	0.0	0.2	0.0	0.0	M04A
MVP0273	0.0	0.0	0.0	0.0	0.0	M04A
MVP0274	69.1	0.0	1.1	0.0	0.0	M04A
MVP0278	90.4	0.0	2.2	0.0	7.5	M04A
MVP0282	96.4	0.0	1.6	0.0	0.0	M04A
MVP0284	11.3	0.0	0.4	0.0	0.0	M04A
MVP0287	32.4	0.0	0.1	0.0	0.0	M04A
MVP0293	39.6	0.0	0.1	0.0	0.0	M04A
MVP0294	82.8	0.0	2.9	0.0	0.0	M04A
MVP0300	33.3	0.0	0.0	0.0	8.6	M04A
MVP0301	97.5	0.0	6.0	0.0	0.0	M04A
MVP0308	4.1	0.0	0.0	0.0	0.0	M04A
MVP0314	22.4	0.0	0.1	0.0	0.0	M04A
MVP0315	98.5	0.0	17.4	0.0	0.3	M04A
MVP0318	7.8	0.0	0.0	0.0	0.0	M04A
MVP0320	84.9	0.0	36.2	0.0	0.2	M04A
MVP0321	34.9	0.0	32.2	0.0	0.0	M04A
MVP0322	72.5	0.0	0.1	0.0	0.0	M04A
MVP0332	57.5	0.0	0.0	0.0	0.1	M04A
MVP0338	93.2	0.0	0.2	0.0	0.1	M04A
MVP0354	1.7	0.0	0.1	0.0	0.0	M04A

MVP0358	90.7	0.0	0.0	0.0	0.0	M04A
MVP0375	39.6	0.0	1.0	0.0	0.2	M04A
MVP0378	54.3	0.0	0.1	0.0	0.0	M04A
MVP0379	33.8	0.0	0.0	0.0	0.0	M04A
MVP0391	89.4	0.0	22.0	0.0	0.0	M04A
MVP0393	7.6	0.0	0.0	0.0	0.2	M04A
MVP0395	73.7	0.0	13.3	0.0	0.0	M04A
MVP0396	95.3	0.0	28.4	0.0	0.1	M04A
MVP0397	8.8	0.0	0.0	0.0	0.0	M04A
MVP0405	92.7	0.0	1.8	0.0	0.7	M04A
MVP0413	46.7	1.5	0.4	0.0	10.9	M04A
MVP0414	79.6	0.0	0.3	0.0	0.0	M04A
MVP0423	28.2	0.0	0.1	0.0	0.0	M04A
MVP0428	49.7	0.0	5.9	0.0	0.0	M04A
MVP0430	7.2	0.0	0.0	0.0	0.0	M04A
MVP0442	65.6	0.0	0.2	0.0	3.3	M04A
MVP0449	78.6	0.0	0.7	0.0	0.0	M04A
MVP0452	24.8	0.0	0.5	0.0	0.3	M04A
MVP0454	46.9	0.0	3.0	0.0	0.1	M04A
MVP0467	88.7	0.0	2.5	0.0	7.4	M04A
OK053	45.5	0.0	0.7	0.0	0.1	M04A
OK069	22.9	0.0	0.0	0.0	0.0	M04A
OK077	8.9	0.0	0.0	0.0	0.0	M04A
OK079	94.9	0.0	10.3	0.0	0.1	M04A
OK084	66.0	0.0	0.3	0.0	0.0	M04A
OK102	75.6	0.0	0.1	0.0	7.6	M04A
OK107	34.7	0.0	0.1	0.0	0.0	M04A
OK129	0.0	0.0	0.0	0.0	0.0	M04A
OK131	19.4	0.0	0.0	0.0	0.6	M04A
OK132	44.2	0.0	0.1	0.0	0.8	M04A
OK135	61.6	0.0	0.6	0.0	1.6	M04A
OK137	10.5	0.0	3.1	0.0	0.0	M04A
OK140	50.7	0.0	0.5	0.0	0.0	M04A
OK149	56.6	0.0	1.0	0.0	0.2	M04A
OK151	79.1	0.0	1.1	0.0	1.4	M04A
OT221	85.4	0.0	4.3	0.0	0.0	M04A
OT237	13.9	0.0	1.3	0.0	0.1	M04A
OT253	81.0	0.0	3.4	0.0	0.0	M04A
OT505	86.3	0.0	3.5	0.0	0.0	M04A
OT511	88.5	0.0	5.2	0.0	7.3	M04A
OT512	99.6	0.0	4.1	0.0	0.0	M04A
OT513	90.8	0.0	2.1	0.0	4.0	M04A
RLB001	99.6	0.0	0.8	0.0	0.0	M04A
RLB003	28.9	0.0	0.1	0.0	0.1	M04A
RLB091	82.9	0.0	0.0	0.0	0.0	M04A
RLB093	78.4	0.0	0.0	0.0	0.0	M04A
RLB096	80.1	0.0	0.0	0.0	7.0	M04A
RLB106	43.8	0.0	0.1	0.3	0.0	M04A
RLB153	67.2	0.0	3.9	0.0	0.0	M04A
RLB153	84.2	0.0	0.0	0.0	0.0	M04A
RLB163	52.5	0.0	0.4	0.0	0.0	M04A
RLB105	18.9	0.0	0.7	0.0	0.0	M04A
RLB170	14.1	0.0	0.0	0.0	0.0	M04A
		0.0	0.0	0.0	0.0	.,,,,,,,,,,,,,,,,,,,,,,,,,,,,,,,,,,,,,,

RLB199	60.9	0.0	2.5	0.0	0.0	M04A
RLB200	73.9	0.0	0.1	0.0	0.0	M04A
RLB215	3.3	0.0	0.0	0.0	0.0	M04A
RLB232	0.6	0.0	0.0	0.0	0.0	M04A
RLB268	3.2	0.0	0.0	0.0	0.0	M04A
SWC046	99.7	0.0	5.6	0.0	0.2	M04A
SWR009	88.3	0.0	8.4	0.0	3.9	M04A
SWR010	16.6	0.2	0.0	0.0	0.0	M04A
SWR024	29.2	0.0	7.8	0.0	0.0	M04A
SWR045	9.7	0.0	0.1	0.0	0.1	M04A
SWR049	88.5	0.0	5.8	0.0	1.1	M04A
SWR053	62.6	0.0	7.6	0.0	0.0	M04A
SWR071	80.8	0.0	1.0	0.0	0.3	M04A
SWR075	3.5	0.0	0.0	0.0	0.5	M04A
SWR093	66.3	0.0	1.2	0.0	0.0	M04A
SWR116	70.0	13.8	2.0	0.0	0.0	M04A
SWR130	0.2			0.0	0.2	
		0.0	0.0			M04A
SWR136	13.5	0.0	4.8	0.0	0.0	M04A
SWR148	89.9	0.0	2.6	0.0	0.0	M04A
SWR157	3.8	0.0	0.0	0.0	0.0	M04A
SWR161	26.4	0.0	0.0	0.0	0.0	M04A
SWR162	51.0	0.0	0.1	0.0	0.0	M04A
SWR172	72.4	0.0	0.2	0.0	0.0	M04A
SWR192	54.2	0.0	0.0	0.0	0.0	M04A
SWR194	47.8	0.0	0.3	0.0	0.0	M04A
SWR202	99.7	0.0	6.2	0.0	0.1	M04A
SWR203	72.8	0.0	0.0	0.0	0.0	M04A
SWR223	19.4	0.0	1.5	0.0	3.3	M04A
TAM007	1.1	0.0	0.1	0.0	0.0	M04A
TAM237	33.3	0.0	6.0	0.0	0.0	M04A
TAM238	54.0	0.0	1.2	0.0	0.0	M04A
UT00446	1.9	0.0	0.0	0.0	0.1	M04A
UT00447	81.4	0.0	14.5	0.0	0.0	M04A
UT00460	71.1	0.0	1.2	0.0	0.0	M04A
UT00759	96.0	0.0	6.6	0.0	0.0	M04A
WCRM003	99.9	0.0	20.4	0.0	0.0	M04A
The following	specimens are	assigned to g	roun Mimhres-	04R		
ID. NO.	M04A	M04B	M04C	M05A	M05B	Group
BAS061	4.4	99.7	0.0	0.0	0.0	M04B
BAS170	0.1	0.3	0.0	0.0	0.0	M04B
BAS182	1.0	20.6	0.0	0.0	0.0	M04B
BAS213	0.0	90.1	0.0	0.0	0.0	M04B
BRE005	0.0	0.1	0.0	0.0	0.0	M04B
BRE056A	0.1	42.2	0.0	0.0	0.0	M04B
BRE095	1.4	76.8	0.0	0.0	0.0	M04B
BRE158	0.0	26.7	0.0	0.0	0.0	M04B
CAP188	0.0	85.9	0.0	0.0	0.0	M04B
CAP100	0.2	63.7	0.0	0.0	0.0	M04B
ED-012	0.0	8.8	0.0	0.0	0.0	M04B
ED-012 ED-042	0.0	74.1	0.0	0.0	0.0	M04B
ED-042 ED-060	0.3	74.1 7.4	0.0	0.0	0.0	M04B
HM020	2.0	51.4	0.0	0.0	0.0	M04B

HM025	0.2	87.3	0.0	0.0	0.0	M04B
HM031	0.0	22.9	0.0	0.0	0.0	M04B
HM079	0.0	60.0	0.0	0.0	0.0	M04B
HM082	0.0	23.6	0.0	0.0	0.0	M04B
HM085	0.0	77.4	0.0	0.0	0.5	M04B
JAM024	0.0	43.8	0.0	0.0	0.0	M04B
KCW001	0.3	84.4	0.0	0.0	0.0	M04B
KCW017	3.3	99.9	0.1	0.0	0.0	M04B
KCW018	0.3	97.6	0.0	0.0	0.0	M04B
LOA097	0.1	100.0	0.0	0.0	0.0	M04B
LOA164	4.0	100.0	0.0	0.0	0.0	M04B
LOA176	0.0	74.2	0.0	0.0	0.0	M04B
MPC007	0.1	0.3	0.0	0.0	0.0	M04B
MPC014	0.1	31.6	0.0	0.0	0.0	M04B
MPC018	0.0	1.3	0.0	0.0	0.0	M04B
MPM003	11.7	80.0	0.0	0.0	0.0	M04B
MPM020	0.5	35.5	0.0	0.0	0.0	M04B
MPM025	0.0	39.2	0.0	0.0	0.0	M04B
MPN004	0.0	0.7	0.0	0.0	0.0	M04B
MPT010	0.0	17.8	0.0	0.0	0.0	M04B
MRM061	0.0	0.4	0.0	0.0	0.0	M04B
MRM095	0.0	93.5	0.0	0.0	0.0	M04B
MRM123	0.3	92.0	0.0	0.0	0.0	M04B
MRM155	1.9	92.8	0.0	0.0	0.0	M04B
MVP0017	0.2	72.5	0.0	0.0	0.0	M04B
MVP0030	0.0	68.3	0.0	0.0	0.0	M04B
MVP0046	27.7	99.2	0.3	0.0	5.6	M04B
MVP0056	0.1	71.6	0.0	0.0	0.0	M04B
MVP0075	8.7	97.4	0.0	0.0	0.0	M04B
MVP0095	1.5	99.8	0.0	0.0	0.0	M04B
MVP0106	1.6	50.0	0.0	0.0	0.0	M04B
MVP0133	0.0	41.6	0.0	0.0	0.0	M04B
MVP0144	0.0	76.0	0.0	0.0	0.0	M04B
MVP0160	0.0	87.1	0.0	0.0	0.0	M04B
MVP0177	0.0	36.1	0.0	0.0	0.0	M04B
MVP0189	0.0	72.0	0.0	0.0	0.0	M04B
MVP0198	0.0	94.9	0.0	0.0	0.0	M04B
MVP0203	6.7	99.8	0.0	0.0	0.0	M04B
MVP0211	10.9	78.7	0.1	0.0	0.0	M04B
MVP0216	2.3	87.3	0.0	0.0	0.0	M04B
MVP0218	1.2	99.9	0.0	0.0	0.0	M04B
MVP0220	1.4	99.8	0.0	0.0	0.0	M04B
MVP0221	8.2	99.8	0.0	0.0	0.0	M04B
MVP0222	11.5	87.9	0.0	0.0	0.0	M04B
MVP0254	0.0	52.3	0.0	0.0	0.0	M04B
MVP0259	1.1	34.7	0.0	0.0	0.0	M04B
MVP0260	6.4	16.8	0.0	0.0	0.0	M04B
MVP0271	1.3	99.6	0.0	0.0	0.0	M04B
MVP0279	5.4	69.9	0.0	0.0	0.0	M04B
MVP0290	0.0	0.6	0.0	0.0	0.0	M04B
MVP0291	0.1	61.9	0.0	0.0	0.0	M04B
MVP0295	0.0	0.3	0.0	0.0	0.0	M04B
MVP0296	0.0	0.1	0.0	0.0	0.0	M04B
	2.0		5.0	2.0	2.0	

MVP0330	1.6	99.7	0.0	0.0	0.0	M04B
MVP0348	0.0	0.8	0.0	0.0	0.0	M04B
MVP0372	0.1	99.9	0.0	0.0	0.0	M04B
MVP0385	0.0	0.0	0.0	0.0	0.0	M04B
MVP0398	2.8	95.2	0.0	0.0	0.0	M04B
MVP0426	0.4	93.3	0.0	0.0	0.0	M04B
MVP0436	0.0	92.4	0.0	0.0	0.0	M04B
MVP0437	0.0	92.3	0.0	0.0	0.0	M04B
MVP0453	0.1	67.5	0.0	0.0	0.0	M04B
MVP0459	0.0	12.3	0.0	0.0	0.0	M04B
OK091	1.6	63.8	0.0	0.0	0.0	M04B
OK128	0.1	1.8	0.0	0.0	0.0	M04B
OK134	0.1	49.9	0.0	0.0	0.0	M04B
OK152	1.6	5.7	0.0	0.0	0.1	M04B
OT499	0.0	22.0	0.0	0.0	0.0	M04B
RLB062	0.3	3.7	0.0	0.0	0.0	M04B
RLB095	5.0	17.1	0.0	0.0	0.0	M04B
RLB099	0.0	83.7	0.0	0.0	0.0	M04B
RLB198	0.1	79.5	0.0	0.0	0.0	M04B
RLB202	0.0	1.2	0.0	0.0	0.0	M04B
RLB207	1.3	68.1	0.0	0.0	0.0	M04B
RLB218	0.0	38.0	0.0	0.0	0.0	M04B
RLB223	0.5	79.1	0.0	0.0	0.0	M04B
RLB247	0.3	16.8	0.0	0.0	0.0	M04B
SWR005	0.4	78.7	0.0	0.0	0.0	M04B
SWR007	1.6	20.0	0.0	0.0	0.0	M04B
	1.8			0.0		
SWR018 SWR032	0.0	48.8 80.1	0.0 0.0	0.0	0.0 0.0	M04B M04B
SWR033	0.0	94.4	0.0	0.0	0.0	M04B
SWR039	0.0	74.5	0.0	0.0	0.0	M04B
SWR043	0.0	95.5	0.0	0.0	0.0	M04B
SWR044	0.2	66.0	0.0	0.0	0.0	M04B
SWR046	0.0	76.0	0.0	0.0	0.0	M04B
SWR051	0.0	30.4	0.0	0.0	0.0	M04B
SWR056	0.0	43.8	0.0	0.0	0.0	M04B
SWR059	1.4	57.2	0.0	0.0	0.0	M04B
SWR063	0.1	68.3	0.0	0.0	0.0	M04B
SWR081	0.0	1.9	0.0	0.0	0.0	M04B
SWR085	0.0	1.6	0.0	0.0	0.0	M04B
SWR091	0.2	21.0	0.0	0.0	0.0	M04B
SWR106	0.0	19.4	0.0	0.0	0.0	M04B
SWR145	0.0	22.3	0.0	0.0	0.0	M04B
SWR151	0.0	12.1	0.0	0.0	0.0	M04B
SWR155	0.2	60.8	0.0	0.0	0.0	M04B
SWR160	0.0	7.0	0.0	0.0	0.0	M04B
SWR184	0.0	39.0	0.0	0.0	0.0	M04B
SWR188	0.1	28.6	0.0	0.0	0.0	M04B
SWR191	0.0	45.5	0.0	0.0	0.0	M04B
SWR195	0.1	87.8	0.0	0.0	0.0	M04B
SWR214	0.1	60.0	0.0	0.0	0.0	M04B
TAM002	0.0	1.1	0.0	0.0	0.0	M04B
TAM003	0.0	27.2	0.0	0.0	0.0	M04B
TAM004	0.0	1.6	0.0	0.0	0.0	M04B

TAM211	0.3	61.4	0.0	0.0	0.0	M04B
TAM217	8.6	25.6	0.0	0.0	0.0	M04B
TAM220	0.0	8.8	0.0	0.0	0.0	M04B
TAM224	0.0	29.3	0.0	0.0	0.0	M04B
TAM234	0.0	4.4	0.0	0.0	0.0	M04B
UT00478	0.0	93.8	0.0	0.0	0.0	M04B
UT00483	8.0	94.8	0.1	0.0	0.6	M04B
UT00490	0.7	95.0	0.0	0.0	0.0	M04B
WCRM004	0.1	3.0	0.0	0.0	0.0	M04B
WCMWIOOT	0.1	3.0	0.0	0.0	0.0	WIOTE
The following s	pecimens are as	ssigned to grow	n Mimhres-04C			
ID. NO.	M04A	M04B	M04C	М05А	M05B	Group
ATT375	0.0	0.0	49.0	0.0	1.0	M04C
	0.0	0.0	0.9	0.0	0.0	M04C
ATT404						
ATT404	0.0	0.0	43.0	1.8	0.0	M04C
ATT406	0.8	0.0	66.9	0.3	4.0	M04C
ATT419	6.4	0.0	48.5	0.0	0.0	M04C
ATT420	0.3	0.0	90.4	0.0	0.0	M04C
ATT422	0.5	0.0	16.8	0.0	0.1	M04C
ATT427	1.9	0.0	40.9	0.0	0.1	M04C
ATT445	0.1	0.0	45.9	0.0	0.0	M04C
ATT446	3.7	0.0	77.2	0.0	0.1	M04C
BAS001	0.0	0.0	3.2	0.0	0.0	M04C
BAS002	0.4	0.0	37.1	0.0	0.4	M04C
BAS003	56.7	0.0	84.1	0.9	2.4	M04C
BAS004	10.1	0.0	60.0	2.2	3.1	M04C
BAS010	1.2	0.0	67.5	0.3	26.8	M04C
BAS012	4.9	0.0	43.8	0.1	0.0	M04C
BAS014	48.2	0.0	86.4	1.7	0.4	M04C
BAS016	0.1	0.0	98.0	0.1	13.3	M04C
BAS020	0.2	0.0	94.3	3.0	1.6	M04C
BAS029	0.1	0.0	76.1	8.2	0.7	M04C
BAS030	0.0	0.0	96.2	0.7	18.8	M04C
BAS031	0.6	0.0	96.1	0.1	4.6	M04C
BAS034	6.2	0.0	99.3	0.0	1.3	M04C
BAS035	0.2	0.0	98.7	1.5	9.1	M04C
BAS037	0.6	0.0	93.4	0.5	6.6	M04C
BAS042	0.0	0.0	82.9	1.9	0.0	M04C
BAS043	0.0	0.0	26.5	0.0	0.0	M04C
BAS044	4.9	0.0	99.7	2.4	58.2	M04C
BAS047	2.1	0.0	99.4	0.2	0.1	M04C
				0.2		
BASO53	0.6	0.0	83.4		13.8	M04C
BAS057	0.7	0.0	95.4	0.0	0.0	M04C
BAS117	0.3	0.0	12.4	2.7	5.2	M04C
BAS163	74.0	0.0	92.7	2.8	2.9	M04C
BAS168	0.0	0.0	92.9	0.1	7.6	M04C
BAS173	0.0	0.0	1.6	0.0	0.0	M04C
BAS183	0.0	0.0	95.4	0.4	2.9	M04C
BAS186	0.0	0.0	61.7	0.1	0.0	M04C
BAS188	0.4	0.0	97.0	0.1	6.5	M04C
BAS192	0.1	0.0	78.4	0.0	0.0	M04C
BAS207	3.3	0.0	97.6	0.1	19.1	M04C
BAS223	17.7	0.0	54.8	0.0	4.7	M04C

BRE003	0.0	0.0	7.2	0.7	0.1	M04C
CAP168	27.9	0.0	80.4	2.0	8.6	M04C
HM029	6.8	0.0	96.7	0.2	0.3	M04C
JAM021	0.1	0.0	0.2	0.0	0.0	M04C
JAM029	4.6	0.0	9.8	0.0	0.1	M04C
JAM044	0.5	0.0	4.2	0.0	0.1	M04C
JAM112	3.4	0.0	27.0	0.2	1.5	M04C
JAM114	27.9	0.0	42.6	0.0	1.0	M04C
MPM005	8.7	0.0	11.5	0.0	1.7	M04C
MRM007	0.9	0.0	56.5	0.0	0.1	M04C
MRM068	37.9	0.0	99.2	0.5	0.1	M04C
MRM082	29.3	0.0	89.4	0.4	0.8	M04C
MRM102	0.8	0.0	99.9	4.7	1.4	M04C
MRM104	0.0	0.0	82.7	0.2	0.5	M04C
MRM108	0.0	0.0	82.5	0.1	0.1	M04C
MRM110	0.1	0.0	7.6	1.9	0.2	M04C
MRM112	0.0	0.0	90.6	1.4	0.9	M04C
MRM145	27.8	0.0	89.1	0.3	0.8	M04C
MRM187	13.9	0.0	95.3	0.1	0.3	M04C
MRM190	48.6	0.0	98.3	0.0	4.7	M04C
MRM202	0.0	0.0	85.9	0.0	0.1	M04C
MRM203	0.0	0.0	4.7	0.1	0.3	M04C
MVP0062	24.7	0.0	63.8	3.1	3.1	M04C
MVP0094	0.1	0.0	1.1	0.0	0.0	M04C
MVP0114	12.2	0.0	75.3	0.0	2.4	M04C
MVP0151	0.1	0.0	14.7	0.0	0.3	M04C
MVP0172	0.6	0.0	61.5	0.0	0.9	M04C
MVP0219	0.0	0.0	4.5	0.0	0.0	M04C
MVP0249	0.1	0.0	83.0	0.0	0.4	M04C
MVP0250	0.0	0.0	95.1	0.1	0.3	M04C
MVP0251	0.0	0.0	82.6	0.0	0.0	M04C
MVP0255	0.0	0.0	4.2	0.0	0.4	M04C
MVP0257	0.0	0.0	9.4	0.6	0.1	M04C
MVP0297	0.7	0.0	29.1	0.0	0.9	M04C
MVP0313	14.3	0.0	36.6	0.0	0.7	M04C
MVP0317	22.1	0.0	51.4	0.1	0.4	M04C
MVP0323	0.0	0.0	0.8	0.0	0.0	M04C
MVP0346	0.0	0.0	4.7	0.0	0.0	M04C
MVP0380	2.0	0.0	26.6	0.0	0.3	M04C
MVP0381	0.0	0.0	0.0	0.0	0.2	M04C
MVP0384	0.0	0.0	20.6	0.0	0.4	M04C
MVP0386	1.0	0.0	84.2	0.2	0.8	M04C
MVP0387	8.3	0.0	89.6	0.0	5.9	M04C
MVP0390	0.0	0.0	86.3	0.0	0.0	M04C
MVP0401	35.9	0.0	80.9	0.0	2.5	M04C
MVP0417	50.6	0.0	95.3	0.0	9.9	M04C
MVP0465	6.9	0.0	15.4	0.0	0.3	M04C
OK002	0.0	0.0	40.4	0.3	2.5	M04C
OK008	0.9	0.0	69.9	0.0	2.3	M04C
OK013	0.3	0.0	68.4	0.0	0.0	M04C
OK017	1.9	0.0	13.1	0.0	0.3	M04C
OK026	0.8	0.0	16.8	2.3	0.1	M04C
OK028	15.0	0.0	22.2	0.0	0.3	M04C

OK115	0.0	0.0	0.3	0.0	0.0	M04C
OK125	0.0	0.0	0.0	0.0	0.0	M04C
OK139	0.5	0.0	18.7	0.4	0.0	M04C
OK141	5.2	0.0	0.3	0.0	0.0	M04C
OK147	0.0	0.0	2.9	0.0	0.0	M04C
OT171	0.2	0.0	52.3	0.1	0.1	M04C
OT190	8.2	0.0	73.7	0.6	1.1	M04C
OT209	18.3	0.0	99.9	0.0	0.3	M04C
OT227	0.0	0.0	36.1	0.0	0.3	M04C
OT251	0.5	0.0	37.4	0.0	10.7	M04C
OT255	0.1	0.0	10.1	0.1	0.0	M04C
OT264	6.8	0.0	38.7	0.1	0.2	M04C
OU0044	0.0	0.0	86.2	0.0	48.3	M04C
OU0051	3.2	0.0	90.4	0.2	29.3	M04C
OU0052	3.0	0.0	98.6	0.2	65.6	M04C
SWR004	1.0	0.0	61.2	0.0	1.5	M04C
SWR022	0.0	0.0	16.4	0.0	6.8	M04C
SWR101	6.1	0.0	94.3	0.9	0.4	M04C
SWR119	0.0	0.0	0.9	0.0	0.0	M04C
SWR166	44.7	0.0	94.6	0.0	0.2	M04C
SWR220	2.2	0.0	71.3	0.0	1.3	M04C
SWR221	0.0	0.0	3.5	0.0	0.0	M04C
TAM228	2.5	0.0	46.0	0.1	0.3	M04C
TAM229	1.5	0.0	58.9	0.0	0.4	M04C
UT00785	0.1	0.0	77.9	0.0	0.0	M04C
The following sp		ianad ta araur	NA:makuaa OFA			
The following sp	becimens are ass		iviimbres-usa	•		
ID. NO.	M04A	M04B	M04C	М05А	M05B	Group
				M05A 1.3	M05B 0.0	Group M05A
ID. NO.	M04A	M04B	M04C	M05A 1.3 84.1		-
ID. NO. ANI011	M04A 0.0 0.0 0.0	M04B 0.0	M04C 0.0 0.0 0.0	M05A 1.3 84.1 9.5	0.0	M05A M05A M05A
ID. NO. ANI011 ANI023	M04A 0.0 0.0	M04B 0.0 0.0	M04C 0.0 0.0	M05A 1.3 84.1	0.0 0.1	M05A M05A
ID. NO. ANI011 ANI023 ATT348	M04A 0.0 0.0 0.0	M04B 0.0 0.0 0.0	M04C 0.0 0.0 0.0	M05A 1.3 84.1 9.5	0.0 0.1 2.3	M05A M05A M05A
ID. NO. ANI011 ANI023 ATT348 ATT400	M04A 0.0 0.0 0.0 0.0	M04B 0.0 0.0 0.0 0.0	M04C 0.0 0.0 0.0 0.0	M05A 1.3 84.1 9.5 49.7	0.0 0.1 2.3 0.0	M05A M05A M05A M05A
ID. NO. ANI011 ANI023 ATT348 ATT400 ATT410 BAS021 BAS027	M04A 0.0 0.0 0.0 0.0 0.0 0.0	M04B 0.0 0.0 0.0 0.0 0.0	M04C 0.0 0.0 0.0 0.0 0.0 0.0 0.0 0.0 0.0	M05A 1.3 84.1 9.5 49.7 92.6 53.4 67.5	0.0 0.1 2.3 0.0 0.1	M05A M05A M05A M05A M05A M05A
ID. NO. ANI011 ANI023 ATT348 ATT400 ATT410 BAS021 BAS027 BAS052	M04A 0.0 0.0 0.0 0.0 0.0 0.0 0.0	M04B 0.0 0.0 0.0 0.0 0.0 0.0 0.0 0.0 0.0 0.	M04C 0.0 0.0 0.0 0.0 0.0 0.0 0.0 0.0 0.0 0.	M05A 1.3 84.1 9.5 49.7 92.6 53.4 67.5 99.5	0.0 0.1 2.3 0.0 0.1 0.0 0.3 1.1	M05A M05A M05A M05A M05A M05A M05A
ID. NO. ANI011 ANI023 ATT348 ATT400 ATT410 BAS021 BAS027 BAS052 BAS081	M04A 0.0 0.0 0.0 0.0 0.0 0.0 0.0 0.0 0.0 0.	M04B 0.0 0.0 0.0 0.0 0.0 0.0 0.0 0.0 0.0 0.	M04C 0.0 0.0 0.0 0.0 0.0 0.0 0.0 0.0 0.0 0.	M05A 1.3 84.1 9.5 49.7 92.6 53.4 67.5 99.5 7.1	0.0 0.1 2.3 0.0 0.1 0.0 0.3 1.1 0.0	M05A M05A M05A M05A M05A M05A M05A M05A
ID. NO. ANI011 ANI023 ATT348 ATT400 ATT410 BAS021 BAS027 BAS052 BAS081 BAS102	M04A 0.0 0.0 0.0 0.0 0.0 0.0 0.0 0.0 0.0 0.	M04B 0.0 0.0 0.0 0.0 0.0 0.0 0.0 0.0 0.0 0.	M04C 0.0 0.0 0.0 0.0 0.0 0.0 0.0 0.0 0.0 0.	M05A 1.3 84.1 9.5 49.7 92.6 53.4 67.5 99.5 7.1 98.6	0.0 0.1 2.3 0.0 0.1 0.0 0.3 1.1 0.0 1.0	M05A M05A M05A M05A M05A M05A M05A M05A
ID. NO. ANI011 ANI023 ATT348 ATT400 ATT410 BAS021 BAS027 BAS052 BAS081 BAS102 BAS109	M04A 0.0 0.0 0.0 0.0 0.0 0.0 0.0 0.0 0.0 0.	M04B 0.0 0.0 0.0 0.0 0.0 0.0 0.0 0.0 0.0 0.	M04C 0.0 0.0 0.0 0.0 0.0 0.0 0.0 0.0 0.0 0.	M05A 1.3 84.1 9.5 49.7 92.6 53.4 67.5 99.5 7.1 98.6 41.8	0.0 0.1 2.3 0.0 0.1 0.0 0.3 1.1 0.0 1.0 2.6	M05A M05A M05A M05A M05A M05A M05A M05A
ID. NO. ANI011 ANI023 ATT348 ATT400 ATT410 BAS021 BAS027 BAS052 BAS081 BAS102 BAS109 BAS112	M04A 0.0 0.0 0.0 0.0 0.0 0.0 0.0 0.0 0.0 0.	M04B 0.0 0.0 0.0 0.0 0.0 0.0 0.0 0.0 0.0 0.	M04C 0.0 0.0 0.0 0.0 0.0 0.0 0.0 0.0 0.0 0.	M05A 1.3 84.1 9.5 49.7 92.6 53.4 67.5 99.5 7.1 98.6 41.8 36.8	0.0 0.1 2.3 0.0 0.1 0.0 0.3 1.1 0.0 1.0 2.6 0.0	M05A M05A M05A M05A M05A M05A M05A M05A
ID. NO. ANI011 ANI023 ATT348 ATT400 ATT410 BAS021 BAS027 BAS052 BAS081 BAS102 BAS102 BAS112 BAS114	M04A 0.0 0.0 0.0 0.0 0.0 0.0 0.0 0.0 0.0 0.	M04B 0.0 0.0 0.0 0.0 0.0 0.0 0.0 0.0 0.0 0.	M04C 0.0 0.0 0.0 0.0 0.0 0.0 0.0 0.0 0.0 0.	M05A 1.3 84.1 9.5 49.7 92.6 53.4 67.5 99.5 7.1 98.6 41.8 36.8 75.3	0.0 0.1 2.3 0.0 0.1 0.0 0.3 1.1 0.0 1.0 2.6 0.0 0.0	M05A M05A M05A M05A M05A M05A M05A M05A
ID. NO. ANI011 ANI023 ATT348 ATT400 ATT410 BAS021 BAS027 BAS052 BAS081 BAS102 BAS109 BAS112 BAS114 BAS119	M04A 0.0 0.0 0.0 0.0 0.0 0.0 0.0 0.0 0.0 0.	MO4B 0.0 0.0 0.0 0.0 0.0 0.0 0.0 0.0 0.0 0.	M04C 0.0 0.0 0.0 0.0 0.0 0.0 0.0 0.0 0.0 0.	M05A 1.3 84.1 9.5 49.7 92.6 53.4 67.5 99.5 7.1 98.6 41.8 36.8 75.3 75.4	0.0 0.1 2.3 0.0 0.1 0.0 0.3 1.1 0.0 1.0 2.6 0.0 0.0	M05A M05A M05A M05A M05A M05A M05A M05A
ID. NO. ANI011 ANI023 ATT348 ATT400 ATT410 BAS021 BAS027 BAS052 BAS081 BAS102 BAS102 BAS109 BAS112 BAS114 BAS119 BAS128	M04A 0.0 0.0 0.0 0.0 0.0 0.0 0.0 0.0 0.0 0.	MO4B 0.0 0.0 0.0 0.0 0.0 0.0 0.0 0.0 0.0 0.	M04C 0.0 0.0 0.0 0.0 0.0 0.0 0.0 0.0 0.0 0.	1.3 84.1 9.5 49.7 92.6 53.4 67.5 99.5 7.1 98.6 41.8 36.8 75.3 75.4	0.0 0.1 2.3 0.0 0.1 0.0 0.3 1.1 0.0 1.0 2.6 0.0 0.0 0.0	M05A M05A M05A M05A M05A M05A M05A M05A
ID. NO. ANI011 ANI023 ATT348 ATT400 ATT410 BAS021 BAS027 BAS052 BAS081 BAS102 BAS109 BAS112 BAS114 BAS119 BAS118	M04A 0.0 0.0 0.0 0.0 0.0 0.0 0.0 0.0 0.0 0.	M04B 0.0 0.0 0.0 0.0 0.0 0.0 0.0 0.0 0.0 0.	M04C 0.0 0.0 0.0 0.0 0.0 0.0 0.0 0.0 0.0 0.	M05A 1.3 84.1 9.5 49.7 92.6 53.4 67.5 99.5 7.1 98.6 41.8 36.8 75.3 75.4 97.0 89.4	0.0 0.1 2.3 0.0 0.1 0.0 0.3 1.1 0.0 1.0 2.6 0.0 0.0 0.0 0.0	M05A M05A M05A M05A M05A M05A M05A M05A
ID. NO. ANI011 ANI023 ATT348 ATT400 ATT410 BAS021 BAS027 BAS052 BAS081 BAS102 BAS109 BAS112 BAS112 BAS114 BAS119 BAS128 BAS181 CAP162	M04A 0.0 0.0 0.0 0.0 0.0 0.0 0.0 0.0 0.0 0.	M04B 0.0 0.0 0.0 0.0 0.0 0.0 0.0 0.0 0.0 0.	M04C 0.0 0.0 0.0 0.0 0.0 0.0 0.0 0.0 0.0 0.	1.3 84.1 9.5 49.7 92.6 53.4 67.5 99.5 7.1 98.6 41.8 36.8 75.3 75.4 97.0 89.4 33.6	0.0 0.1 2.3 0.0 0.1 0.0 0.3 1.1 0.0 1.0 2.6 0.0 0.0 0.0 0.0	M05A M05A M05A M05A M05A M05A M05A M05A
ID. NO. ANI011 ANI023 ATT348 ATT400 ATT410 BAS021 BAS027 BAS052 BAS081 BAS102 BAS110 BAS112 BAS114 BAS119 BAS128 BAS119 CAP162 CDA075	M04A 0.0 0.0 0.0 0.0 0.0 0.0 0.0 0.0 0.0 0.	MO4B 0.0 0.0 0.0 0.0 0.0 0.0 0.0 0.0 0.0 0.	M04C 0.0 0.0 0.0 0.0 0.0 0.0 0.0 0.0 0.0 0.	1.3 84.1 9.5 49.7 92.6 53.4 67.5 99.5 7.1 98.6 41.8 36.8 75.3 75.4 97.0 89.4 33.6 98.5	0.0 0.1 2.3 0.0 0.1 0.0 0.3 1.1 0.0 1.0 2.6 0.0 0.0 0.0 0.0 0.0	M05A M05A M05A M05A M05A M05A M05A M05A
ID. NO. ANI011 ANI023 ATT348 ATT400 ATT410 BAS021 BAS027 BAS052 BAS081 BAS102 BAS109 BAS112 BAS114 BAS119 BAS128 BAS114 CAP162 CDA075 CDA186	M04A 0.0 0.0 0.0 0.0 0.0 0.0 0.0 0.0 0.0 0.	MO4B 0.0 0.0 0.0 0.0 0.0 0.0 0.0 0.0 0.0 0.	M04C 0.0 0.0 0.0 0.0 0.0 0.0 0.0 0.0 0.0 0.	1.3 84.1 9.5 49.7 92.6 53.4 67.5 99.5 7.1 98.6 41.8 36.8 75.3 75.4 97.0 89.4 33.6 98.5 96.9	0.0 0.1 2.3 0.0 0.1 0.0 0.3 1.1 0.0 1.0 2.6 0.0 0.0 0.0 0.0 0.0 0.0	M05A M05A M05A M05A M05A M05A M05A M05A
ID. NO. ANI011 ANI023 ATT348 ATT400 ATT410 BAS021 BAS027 BAS052 BAS081 BAS102 BAS109 BAS112 BAS114 BAS119 BAS128 BAS114 CAP162 CDA075 CDA186 CDA189	M04A 0.0 0.0 0.0 0.0 0.0 0.0 0.0 0.0 0.0 0.	MO4B 0.0 0.0 0.0 0.0 0.0 0.0 0.0 0.0 0.0 0.	M04C 0.0 0.0 0.0 0.0 0.0 0.0 0.0 0.0 0.0 0.	1.3 84.1 9.5 49.7 92.6 53.4 67.5 99.5 7.1 98.6 41.8 36.8 75.3 75.4 97.0 89.4 33.6 98.5 96.9 25.9	0.0 0.1 2.3 0.0 0.1 0.0 0.3 1.1 0.0 1.0 2.6 0.0 0.0 0.0 0.0 0.6 1.9 0.0 0.9 0.6 0.0	M05A M05A M05A M05A M05A M05A M05A M05A
ID. NO. ANI011 ANI023 ATT348 ATT400 ATT410 BAS021 BAS027 BAS052 BAS081 BAS102 BAS109 BAS112 BAS114 BAS119 BAS112 BAS114 CAP162 CDA075 CDA186 CDA189 CDA190	MO4A 0.0 0.0 0.0 0.0 0.0 0.0 0.0 0	MO4B 0.0 0.0 0.0 0.0 0.0 0.0 0.0 0.0 0.0 0.	M04C 0.0 0.0 0.0 0.0 0.0 0.0 0.0 0.0 0.0 0.	1.3 84.1 9.5 49.7 92.6 53.4 67.5 99.5 7.1 98.6 41.8 36.8 75.3 75.4 97.0 89.4 33.6 98.5 96.9 25.9 99.8	0.0 0.1 2.3 0.0 0.1 0.0 0.3 1.1 0.0 1.0 2.6 0.0 0.0 0.0 0.6 1.9 0.0 0.9 0.6 0.0 7.4	M05A M05A M05A M05A M05A M05A M05A M05A
ID. NO. ANI011 ANI023 ATT348 ATT400 ATT410 BAS021 BAS027 BAS052 BAS081 BAS102 BAS109 BAS112 BAS112 BAS114 BAS119 BAS128 CDA189 CDA180 CDA191	MO4A 0.0 0.0 0.0 0.0 0.0 0.0 0.0 0	MO4B 0.0 0.0 0.0 0.0 0.0 0.0 0.0 0.0 0.0 0.	M04C 0.0 0.0 0.0 0.0 0.0 0.0 0.0 0.0 0.0 0.	1.3 84.1 9.5 49.7 92.6 53.4 67.5 99.5 7.1 98.6 41.8 36.8 75.3 75.4 97.0 89.4 33.6 98.5 96.9 25.9 99.8	0.0 0.1 2.3 0.0 0.1 0.0 0.3 1.1 0.0 1.0 2.6 0.0 0.0 0.0 0.6 1.9 0.0 0.9 0.6 0.0 7.4 0.2	M05A M05A M05A M05A M05A M05A M05A M05A
ID. NO. ANI011 ANI023 ATT348 ATT400 ATT410 BAS021 BAS027 BAS052 BAS081 BAS102 BAS112 BAS112 BAS114 BAS119 BAS128 BAS181 CAP162 CDA075 CDA186 CDA189 CDA190 CDA191 CDA192	M04A 0.0 0.0 0.0 0.0 0.0 0.0 0.0 0.0 0.0 0.	MO4B 0.0 0.0 0.0 0.0 0.0 0.0 0.0 0.0 0.0 0.	M04C 0.0 0.0 0.0 0.0 0.0 0.0 0.0 0.0 0.0 0.	1.3 84.1 9.5 49.7 92.6 53.4 67.5 99.5 7.1 98.6 41.8 36.8 75.3 75.4 97.0 89.4 33.6 98.5 96.9 25.9 99.8 99.8 42.3	0.0 0.1 2.3 0.0 0.1 0.0 0.3 1.1 0.0 1.0 2.6 0.0 0.0 0.6 1.9 0.0 0.9 0.6 0.0 7.4 0.2 0.0	M05A M05A M05A M05A M05A M05A M05A M05A
ID. NO. ANI011 ANI023 ATT348 ATT400 ATT410 BAS021 BAS027 BAS052 BAS081 BAS102 BAS109 BAS112 BAS114 BAS119 BAS128 BAS181 CAP162 CDA075 CDA186 CDA189 CDA190 CDA191 CDA192 CDA194	MO4A 0.0 0.0 0.0 0.0 0.0 0.0 0.0 0	MO4B 0.0 0.0 0.0 0.0 0.0 0.0 0.0 0.0 0.0 0.	M04C 0.0 0.0 0.0 0.0 0.0 0.0 0.0 0.0 0.0 0.	1.3 84.1 9.5 49.7 92.6 53.4 67.5 99.5 7.1 98.6 41.8 36.8 75.3 75.4 97.0 89.4 33.6 98.5 96.9 25.9 99.8 99.8 99.8 99.8	0.0 0.1 2.3 0.0 0.1 0.0 0.3 1.1 0.0 1.0 2.6 0.0 0.0 0.6 1.9 0.0 0.9 0.6 0.0 7.4 0.2 0.0 0.0 0.0	M05A M05A M05A M05A M05A M05A M05A M05A
ID. NO. ANI011 ANI023 ATT348 ATT400 ATT410 BAS021 BAS027 BAS052 BAS081 BAS102 BAS112 BAS112 BAS114 BAS119 BAS128 BAS181 CAP162 CDA075 CDA186 CDA189 CDA190 CDA191 CDA192	M04A 0.0 0.0 0.0 0.0 0.0 0.0 0.0 0.0 0.0 0.	MO4B 0.0 0.0 0.0 0.0 0.0 0.0 0.0 0.0 0.0 0.	M04C 0.0 0.0 0.0 0.0 0.0 0.0 0.0 0.0 0.0 0.	1.3 84.1 9.5 49.7 92.6 53.4 67.5 99.5 7.1 98.6 41.8 36.8 75.3 75.4 97.0 89.4 33.6 98.5 96.9 25.9 99.8 99.8 42.3	0.0 0.1 2.3 0.0 0.1 0.0 0.3 1.1 0.0 1.0 2.6 0.0 0.0 0.6 1.9 0.0 0.9 0.6 0.0 7.4 0.2 0.0	M05A M05A M05A M05A M05A M05A M05A M05A

CDA297	0.0	0.0	0.0	6.7	0.0	M05A
CDA312	0.0	0.0	0.0	21.8	0.0	M05A
CDA316	0.0	0.0	0.0	76.1	0.0	M05A
CDA359	0.0	0.0	0.0	0.0	0.0	M05A
CDA383	0.0	0.0	0.0	38.6	0.0	M05A
CDA384	0.0	0.0	0.0	97.1	0.4	M05A
CDA403	0.0	0.0	0.0	1.3	0.0	M05A
CDA414	0.0	0.0	0.0	60.6	0.0	M05A
CDA433	0.0	0.0	0.0	87.7	0.1	M05A
CDA434	0.0	0.0	0.0	98.8	0.0	M05A
CDA435	0.0	0.0	0.0	38.3	0.0	M05A
CDA436	0.0	0.0	0.0	46.7	0.2	M05A
CDA437	0.0	0.0	0.0	75.4	0.0	M05A
CDA489	0.0	0.0	0.0	81.5	0.5	M05A
CDA499	0.0	0.0	0.0	79.6	0.0	M05A
CDA500	0.0	0.0	0.0	14.3	0.0	M05A
DJT003	0.0	0.0	0.0	9.5	0.0	M05A
DJT004	0.0	0.0	0.0	82.1	0.3	M05A
DJT013	0.0	0.0	0.0	100.0	0.2	M05A
DJT013	0.0	0.0	0.0	75.9	0.0	M05A
DJT014	0.0	0.0	0.0	18.8	0.0	M05A
JAM080	0.0	0.0	0.0	31.8	0.0	M05A
JAM115	0.0	0.0	0.0	69.1	0.0	M05A
JAM133	0.0	0.0	0.0	31.1	0.1	M05A
	0.0	0.0	0.0	1.1	0.8	M05A
JAM134						
KCW003	0.0	0.0	0.0	34.8	0.4	M05A
KCW011	0.0	0.0	0.0	98.7	0.0	M05A
LOA030	0.0	0.0	0.0	77.4	0.3	M05A
LOA059	0.0	0.0	0.0	12.0	3.1	M05A
LOA077	0.0	0.0	0.0	58.3	1.5	M05A
LOA088	0.0	0.0	0.0	8.2	0.0	M05A
LOA112	0.0	0.0	0.0	80.1	1.4	M05A
LOA114	0.0	0.0	0.0	47.3	5.5	M05A
LOA160	0.0	0.0	0.0	95.9	0.1	M05A
LOA209	0.0	0.0	0.0	90.2	0.0	M05A
LOA217	0.0	0.0	0.0	97.5	0.3	M05A
LOA226	0.0	0.0	0.0	12.8	7.0	M05A
MPP001	0.0	0.0	0.0	34.6	0.0	M05A
MPP004	0.0	0.0	0.0	97.5	0.0	M05A
MPP007	0.0	0.0	0.0	0.2	0.0	M05A
MPP008	0.0	0.0	0.0	52.4	0.0	M05A
MPP010	0.0	0.0	0.0	0.2	0.0	M05A
MRM147	0.0	0.0	0.0	43.0	0.0	M05A
MRM153	0.0	0.0	0.0	52.8	0.1	M05A
MRM156	0.0	0.0	0.0	56.2	0.0	M05A
MRM209	0.0	0.0	0.0	35.3	0.0	M05A
MVP0388	0.0	0.0	0.0	92.5	0.7	M05A
MVP0389	0.0	0.0	0.0	26.6	1.8	M05A
NAM007	0.0	0.0	0.1	13.2	11.9	M05A
OK003	0.0	0.0	0.0	0.3	0.0	M05A
OK031	0.0	0.0	0.0	84.2	0.6	M05A
OK042	0.0	0.0	0.0	9.3	0.0	M05A
OK051	0.0	0.0	0.0	70.9	0.0	M05A

OK056	0.0	0.0	0.0	84.6	0.1	M05A
OT175	0.0	0.0	0.0	9.2	0.3	M05A
OT207	0.0	0.0	0.0	8.0	0.0	M05A
OT224	0.0	0.0	0.0	95.0	0.8	M05A
RLB017	0.0	0.0	0.0	33.5	0.1	M05A
RLB041	0.0	0.0	0.0	3.3	0.0	M05A
RLB046	0.0	0.0	0.0	84.4	0.1	M05A
RLB060	0.0	0.0	0.0	18.0	0.0	M05A
RLB066	0.0	0.0	0.0	19.3	0.1	M05A
RLB067	0.0	0.0	0.0	75.9	0.6	M05A
RLB070	0.0	0.0	0.0	71.2	0.0	M05A
RLB090	0.0	0.0	0.0	75.7	0.1	M05A
RLB155	0.0	0.0	0.0	1.5	0.4	M05A
RLB201	0.0	0.0	0.0	77.4	0.0	M05A
TAM031	0.0	0.0	0.0	1.2	0.2	M05A
TAM047	0.0	0.0	0.0	8.4	0.7	M05A
TAM062	0.0	0.0	0.0	63.9	0.0	M05A
TAM071	0.0	0.0	0.0	27.8	0.0	M05A
TAM073	0.0	0.0	0.0	57.2	0.0	M05A
	g specimens are a	-	-			
ID. NO.	M04A	M04B	M04C	M05A	M05B	Group
ATT390	0.0	0.0	0.0	0.0	27.7	M05B
ATT395	0.0	0.0	0.0	0.0	3.2	M05B
ATT397	0.0	0.0	0.0	0.0	21.0	M05B
ATT403	0.0	0.0	0.0	0.0	1.2	M05B
ATT416	0.0	0.0	0.0	0.0	8.5	M05B
ATT454	0.0	0.0	0.0	0.0	61.6	M05B
ATT500	0.0	0.0	0.0	0.0	3.1	M05B
BAS024	0.0	0.0	0.0	0.3	99.1	M05B
BAS069	0.0	0.0	0.0	0.0	9.5	M05B
BAS166	0.0	0.0	0.0	0.2	84.6	M05B
BAS171	0.0	0.0	0.0	0.0	83.7	M05B
BAS174 BAS189	0.0	0.0	0.0	0.0	66.7	M05B
BRE087	0.0 0.0	0.0 0.0	0.0 0.0	0.0 0.0	44.3 54.9	M05B M05B
BRE090	0.0	0.0	0.0	0.0	22.8	M05B
CAP159	0.0	0.0	0.0	0.0	57.6	M05B
CDA087	0.0	0.0	0.0	0.0	44.4	M05B
CDA087	0.0	0.0	0.0	0.0	0.0	M05B
CDA089	0.0	0.0	0.0	0.0	6.0	M05B
CDA099	0.0	0.0	0.0	0.0	17.8	M05B
CDA091	0.0	0.0	0.0	0.0	96.5	M05B
CDA092	0.0	0.0	0.0	0.0	15.6	M05B
CDA093	0.0	0.0	0.0	0.0	31.1	M05B
CDA094	0.0	0.0	0.0	0.0	95.1	M05B
CDA095	0.0	0.0	0.0	0.0	0.0	M05B
CDA096	0.0	0.0	0.0	16.2	72.7	M05B
KCW016	0.0	0.0	0.0	0.0	7.2	M05B
LOA001	0.0	0.0	0.0	0.1	62.3	M05B
LOA004	0.0	0.0	0.0	0.4	71.9	M05B
LOA005	0.0	0.0	0.0	0.0	98.3	M05B
LOA012	0.0	0.0	0.0	0.0	32.7	M05B

LOA032	0.0	0.0	0.0	3.7	30.3	M05B
LOA053	0.0	0.0	0.0	0.0	93.2	M05B
LOA062	0.0	0.0	0.0	0.2	86.5	M05B
LOA076	0.0	0.0	0.0	1.2	34.5	M05B
LOA104	0.0	0.0	0.0	0.1	9.7	M05B
LOA108	0.0	0.0	0.0	4.2	22.8	M05B
LOA109	0.0	0.0	0.0	0.0	93.6	M05B
LOA121	0.0	0.0	0.0	0.1	99.7	M05B
LOA122	0.0	0.0	0.0	0.1	97.3	M05B
LOA123	0.0	0.0	0.0	0.1	98.1	M05B
LOA126	0.0	0.0	0.0	0.0	97.7	M05B
LOA127	0.0	0.0	0.0	0.0	60.4	M05B
LOA128	0.0	0.0	0.0	0.0	61.3	M05B
LOA132	0.0	0.0	0.0	0.0	97.9	M05B
LOA133	0.0	0.0	0.0	0.0	38.6	M05B
LOA134	0.0	0.0	0.0	0.0	90.8	M05B
LOA135	0.0	0.0	0.0	0.0	86.4	M05B
LOA136	0.0	0.0	0.0	0.1	59.5	M05B
LOA138	0.0	0.0	0.0	0.0	2.4	M05B
LOA141	0.0	0.0	0.0	0.0	86.8	M05B
LOA143	0.0	0.0	0.0	0.0	17.2	M05B
LOA144	0.0	0.0	0.0	0.0	75.7	M05B
LOA146	0.0	0.0	0.0	0.0	49.7	M05B
LOA220	0.0	0.0	0.0	0.0	87.4	M05B
LOA222	0.0	0.0	0.0	0.0	97.8	M05B
MVP0427	0.0	0.0	0.0	0.0	19.2	M05B
MVP0456	0.0	0.0	0.0	0.0	0.4	M05B
OT208	0.0	0.0	0.0	0.0	98.8	M05B
TAM032	0.0	0.0	0.0	0.0	60.2	M05B
TAM033	0.0	0.0	0.0	0.5	58.3	M05B
TAM034	0.0	0.0	0.0	0.0	0.4	M05B
TAM035	0.0	0.0	0.0	0.0	33.7	M05B
TAM037	0.0	0.0	0.0	0.0	0.5	M05B
TAM038	0.0	0.0	0.0	0.0	50.9	M05B
TAM040	0.0	0.0	0.0	0.0	0.9	M05B
TAM042	0.0	0.0	0.0	0.0	71.7	M05B
TAM045	0.0	0.0	0.0	0.0	76.3	M05B
TAM049	0.0	0.0	0.0	9.6	97.4	M05B
TAM051	0.0	0.0	0.0	0.0	57.5	M05B
TAM052	0.0	0.0	0.0	0.0	58.4	M05B
TAM054	0.0	0.0	0.0	1.1	31.2	M05B
TAM055	0.0	0.0	0.0	0.6	96.7	M05B

Table B2. Macro Group B1 Mahalanobis distance calculations for specimens projected against two or more groups

Mimbres-05C (M05C)

Mimbres-09 (M09)

Variables used:

The following specimens are assigned to group Mimbres-5C.						
ID. NO.	M04A	M04B	M04C	M05A	M05B	Group
BRE028	0.0	0.0	0.0	0.0	4.9	M05C
BRE029	0.0	0.0	0.0	0.0	12.1	M05C
BRE030	0.0	0.0	0.0	0.0	1.9	M05C
BRE031	0.0	0.0	0.0	0.0	2.8	M05C
The following	specimens are a	ssigned to group	Mimbres-09.			
ID. NO.	M04A	M04B	M04C	M05A	M05B	Group
BRE086	0.0	0.0	0.0	0.0	0.0	M09
ED-080	0.0	0.0	0.0	0.0	0.0	M09
ED-081	0.0	0.0	0.0	0.0	0.0	M09
HM038	0.0	0.0	0.0	0.0	0.0	M09
HM063	0.0	0.0	0.0	0.0	0.0	M09
HM083	0.0	0.0	0.0	0.0	0.0	M09
JAM126	0.0	0.0	0.0	0.0	0.0	M09
LOA084	0.0	0.0	0.0	0.0	0.0	M09
LOA163	0.0	0.0	0.0	0.0	0.0	M09
LOA208	0.0	0.0	0.0	0.0	0.0	M09
LOA216	0.0	0.0	0.0	0.0	0.0	M09
MVP0170	0.0	0.0	0.0	0.0	0.0	M09
OK018	0.0	0.0	0.0	0.0	0.0	M09
RLB063	0.0	0.0	0.0	0.0	0.0	M09
RLB175	0.0	0.0	0.0	0.0	0.0	M09
RLB216	0.0	0.0	0.0	0.0	0.0	M09
RLB221	0.0	0.0	0.0	0.0	0.0	M09
RLB234	0.0	0.0	0.0	0.0	0.0	M09
SWR120	0.0	0.0	0.0	0.0	0.0	M09
SWR127	0.0	0.0	0.0	0.0	0.0	M09
SWR200	0.0	0.0	0.0	0.0	0.0	M09
TAM058	0.0	0.0	0.0	0.0	0.0	M09
UT00456	0.0	0.0	0.0	0.0	0.0	M09
WCRM009	0.0	0.0	0.0	0.0	0.0	M09

Table B3. Macro Group B-2 Mahalanobis distance calculations for specimens projected against two or more groups.

Mimbres-02A (M02A)

Mimbres-08 (M08)

Mimbres-11 (M11)

Variables used:

The following specimens are assigned to group M02A.					
ID. NO.	M02A	M08	M11	Group	
ATT101	99.3	0.0	0.0	M02A	
BAS063	95.9	0.0	0.0	M02A	
BAS066	99.8	0.0	0.0	M02A	
BAS068	98.7	0.0	0.0	M02A	
BAS200	59.4	0.0	0.0	M02A	
BAS211	94.8	0.0	0.0	M02A	
BAS212	95.8	0.0	0.0	M02A	
BRE010	42.2	0.0	0.0	M02A	
BRE076	65.4	0.0	0.0	M02A	
BRE096A	98.4	0.0	0.0	M02A	
BRE128A	0.0	0.0	0.0	M02A	
BRE185	82.3	0.0	0.0	M02A	
CAP175	98.8	0.0	0.0	M02A	
CAP191	99.0	0.0	0.0	M02A	
CAP198	94.0	0.0	0.0	M02A	
ED-004	88.4	0.0	0.0	M02A	
ED-014	80.9	0.0	0.0	M02A	
ED-018	3.5	0.0	0.0	M02A	
ED-019	90.6	0.0	0.0	M02A	
ED-024	80.8	0.0	0.0	M02A	
ED-025	99.6	0.0	0.0	M02A	
ED-028	28.8	0.0	0.0	M02A	
ED-029	98.3	0.0	0.0	M02A	
ED-039	61.3	0.0	0.0	M02A	
ED-055	8.8	0.0	0.0	M02A	
ED-056	37.3	0.0	0.0	M02A	
ED-058	51.3	0.0	0.0	M02A	
HM014	80.0	0.0	0.0	M02A	
HM018	46.1	0.0	0.0	M02A	
HM035	4.1	0.0	0.0	M02A	
HM048	99.6	0.0	0.0	M02A	
HM050	34.1	0.0	0.0	M02A	
HM056	20.6	0.0	0.0	M02A	
JAM008	0.0	0.0	0.0	M02A	
JAM014	0.0	0.0	0.0	M02A	
JAM069	52.4	0.0	0.0	M02A	
JAM076	99.1	0.0	0.0	M02A	
JAM077	55.9	0.0	0.0	M02A	
JAM095	96.4	0.0	0.0	M02A	

1414000	FO F	0.0	0.0	N402A
JAM098	59.5	0.0	0.0	M02A
JHK001	99.5	0.0	0.0	M02A
JHK002	57.6	0.0	0.0	M02A
JHK003	75.2	0.0	0.0	M02A
JHK007	16.4	0.0	0.0	M02A
JHK008	0.6	0.0	0.0	M02A
LOA171	99.8	0.0	0.0	M02A
MPC001	1.0	0.0	0.0	M02A
MPC004	5.3	0.0	0.0	M02A
MPC009	3.7	0.0	0.0	M02A
MPC019	0.9	0.0	0.0	M02A
MPG036	86.2	0.0	0.0	M02A
MPG042	54.1	0.0	0.0	M02A
MPN009	0.1	0.0	0.0	M02A
MPN023	4.3	0.0	0.0	M02A
MPN025	25.9	0.0	0.0	M02A
MPN026	4.4	0.0	0.0	M02A
MPT001	13.1	0.0	0.0	M02A
MRM022	79.8	0.0	0.0	M02A
MRM024	99.1	0.0	0.0	M02A
MRM026	97.5	0.0	0.0	M02A
MRM031	65.3	0.0	0.0	M02A
MRM032	96.7	0.0	0.0	M02A
MRM033	82.4	0.0	0.0	M02A
MRM035	92.0	0.0	0.0	M02A
MRM036	89.7	0.0	0.0	M02A
MRM039	96.7	0.0	0.0	M02A
MRM043	93.6	0.0	0.0	M02A
MRM046	99.5	0.0	0.0	M02A
MRM047	99.9	0.0	0.0	M02A
MRM049	85.8	0.0	0.0	M02A
MRM050	99.5	0.0	0.0	M02A
MRM052	99.8	0.0	0.0	M02A
MRM053	99.7	0.0	0.0	M02A
MRM054	98.9	0.0	0.0	M02A
MRM060	96.2	0.0	0.0	M02A
MRM087	99.7	0.0	0.0	M02A
MRM098	99.7	0.0	0.0	M02A
MRM099	0.1	0.0	0.0	M02A
MRM117	37.7	0.0	0.0	M02A
MRM118	6.3	0.0	0.0	M02A
MRM119	99.4	0.0	0.0	M02A
MRM122	89.2	0.0	0.0	M02A
MRM132	99.2	0.0	0.0	M02A
MRM137	62.2	0.0	0.0	M02A
MRM141	99.1	0.0	0.0	M02A
MRM142	97.6	0.0	0.0	M02A
MRM184	69.0	0.0	0.0	M02A
MRM196	1.3	0.0	0.0	M02A
MRM222	54.7	0.0	0.0	M02A
MRM223	99.8	0.0	0.0	M02A
MRM247	95.5	0.0	0.0	M02A
MRM251	99.6	0.0	0.0	M02A
	33.0	0.0	5.5	14102/1

MRM252	10.2	0.0	0.0	M02A
MRM253	93.8	0.0	0.0	M02A
MRM254	99.8	0.0	0.0	M02A
MRM257	13.8	0.0	0.0	M02A
MRM265	26.4	0.0	0.0	M02A
MRM266	22.5	0.0	0.0	M02A
MRM269	19.3	0.0	0.0	M02A
MVP0004	4.1	0.0	0.0	M02A
MVP0014	68.3	0.0	0.0	M02A
MVP0019	93.8	0.0	0.0	M02A
MVP0026	97.5	0.0	0.0	M02A
MVP0045	62.3	0.0	0.0	M02A
MVP0078	73.0	0.0	0.0	M02A
MVP0081	78.0	0.0	0.0	M02A
MVP0089	98.5	0.0	0.0	M02A
MVP0099	8.9	0.0	0.0	M02A
MVP0107	84.4	0.0	0.0	M02A
MVP0111	5.2	0.0	0.0	M02A
MVP0116	66.9	0.0	0.0	M02A
MVP0129	95.1	0.0	0.0	M02A
MVP0136	78.4	0.0	0.0	M02A
MVP0139	93.5	0.0	0.0	M02A
MVP0148	98.6	0.0	0.0	M02A
MVP0152	14.3	0.0	0.0	M02A
MVP0167	94.1	0.0	0.0	M02A
MVP0173	6.2	0.0	0.0	M02A
MVP0186	85.5	0.0	0.0	M02A
MVP0187	1.6	0.0	0.0	M02A
MVP0190	95.6	0.0	0.0	M02A
MVP0191	99.9	0.0	0.0	M02A
MVP0196	72.5	0.0	0.0	M02A
MVP0204	92.2	0.0	0.0	M02A
MVP0205	92.7	0.0	0.0	M02A
MVP0212	96.6	0.0	0.0	M02A
MVP0230	90.5	0.0	0.0	M02A
MVP0258	38.8	0.0	0.0	M02A
MVP0285	26.0	0.0	0.0	M02A
MVP0286	60.1	0.0	0.0	M02A
MVP0311	89.0	0.0	0.0	M02A
MVP0351	0.0	0.0	0.0	M02A
MVP0355	0.2	0.0	0.0	M02A
MVP0362	0.0	0.0	0.0	M02A
MVP0377	51.3	0.0	0.0	M02A
MVP0441	2.0	0.0	0.0	M02A
MVP0457	33.6	0.0	0.0	M02A
NAM002	90.6	0.0	0.0	M02A
NAM011	99.9	0.0	0.0	M02A
NAM012	99.9	0.0	0.0	M02A
NAM020	66.4	0.0	0.0	M02A
OK016	5.6	0.0	0.0	M02A
OK022	98.7	0.0	0.0	M02A
OK023	75.2	0.0	0.0	M02A
OK027	96.6	0.0	0.0	M02A

OK083	8.0	0.0	0.0	M02A
OK097	36.0	0.0	0.0	M02A
OK097	0.2	0.0	0.0	M02A
OK101	97.6	0.0	0.0	M02A
OK113	81.3	0.0	0.0	M02A
OK114	84.0	0.0	0.0	M02A
OK117	82.6	0.0	0.0	M02A
OK118	67.4	0.0	0.0	M02A
OT117	81.7	0.0	0.0	M02A
OT120	0.4	0.0	0.0	M02A
OT490	17.7	0.0	0.0	M02A
OU0035	17.2	0.0	0.0	M02A
OU0037	3.9	0.0	0.0	M02A
RLB007	85.2	0.0	0.0	M02A
RLB016	64.5	0.0	0.0	M02A
RLB097	55.9	0.0	0.0	M02A
RLB103	61.6	0.0	0.0	M02A
RLB205	87.0	0.0	0.0	M02A
RLB211	0.0	0.0	0.0	M02A
RLB217	86.0	0.0	0.0	M02A
RLB226	63.6	0.0	0.0	M02A
RLB229	74.9	0.0	0.0	M02A
RLB230	97.2	0.0	0.0	M02A
RLB231	76.1	0.0	0.0	M02A
RLB233	97.7	0.0	0.0	M02A
RLB237	8.3	0.0	0.0	M02A
RLB241	76.0	0.0	0.0	M02A
SWC034	98.0	0.0	0.0	M02A
SWC036	96.0	0.0	0.0	M02A
SWC037	0.5	0.0	0.0	M02A
SWC038	85.3	0.0	0.0	M02A
SWC042	78.9	0.0	0.0	M02A
SWC049	96.9	0.0	0.0	M02A
SWR002	94.0	0.0	0.0	M02A
SWR013	5.2	0.0	0.0	M02A
SWR016	91.7	0.0	0.0	M02A
SWR020	87.0	0.0	0.0	M02A
SWR025	98.9	0.0	0.0	M02A
SWR030	35.1	0.0	0.0	M02A
SWR036	71.3	0.0	0.0	M02A
SWR036X	69.7	0.0	0.0	M02A
SWR047	1.0	0.0	0.0	M02A
SWR055	17.2	0.0	0.0	M02A
SWR066	22.5	0.0	0.0	M02A
SWR067	2.0	0.0	0.0	M02A
SWR076	35.6	0.0	0.0	M02A
SWR078	46.4	0.0	0.0	M02A
SWR080	2.8	0.0	0.0	M02A
SWR086	86.9	0.0	0.0	M02A
SWR089	0.0	0.0	0.0	M02A
SWR094	83.4	0.0	0.0	M02A
SWR095	88.8	0.0	0.0	M02A
SWR096	96.4	0.0	0.0	M02A

SWR103	0.6	0.0	0.0	M02A
SWR107	0.4	0.0	0.0	M02A
SWR110	19.3	0.0	0.0	M02A
SWR111	2.9	0.0	0.0	M02A
SWR118	0.1	0.0	0.0	M02A
SWR122	95.8	0.0	0.0	M02A
SWR129	46.8	0.0	0.0	M02A
SWR132	30.4	0.0	0.0	M02A
SWR135	0.9	0.0	0.0	M02A
SWR138	73.6	0.0	0.0	M02A
SWR140	87.3	0.0	0.0	M02A
SWR154	17.7	0.0	0.0	M02A
SWR179	31.4	0.0	0.0	M02A
SWR181	98.6	0.0	0.0	M02A
SWR182	98.7	0.0	0.0	M02A
SWR183	51.2	0.0	0.0	M02A
SWR190	97.7	0.0	0.0	M02A
SWR193	83.2	0.0	0.0	M02A
SWR197	99.6	0.0	0.0	M02A
SWR204	46.4	0.0	0.0	M02A
TAM001	10.4	0.0	0.0	M02A
TAM005	4.7	0.0	0.0	M02A
TAM006	61.1	0.0	0.0	M02A
TAM009	96.9	0.0	0.0	M02A
TAM010	82.5	0.0	0.0	M02A
TAM070	1.7	0.0	0.0	M02A
TAM201	27.7	0.0	0.0	M02A
TAM205	68.6	0.0	0.0	M02A
TAM209	19.2	0.0	0.0	M02A
TAM213	74.6	0.0	0.0	M02A
				M02A
TAM214	47.7	0.0	0.0	
TAM215	98.1	0.0	0.0	M02A
TAM216	96.6	0.0	0.0	M02A
TAM223	89.5	0.0	0.0	M02A
TAM225	61.3	0.0	0.0	M02A
TAM226	91.0	0.0	0.0	M02A
TAM227	27.1	0.0	0.0	M02A
TAM232	61.0	0.0	0.0	M02A
TAM235	15.4	0.0	0.0	M02A
TAM241	43.7	0.0	0.0	M02A
TAM242	54.0	0.0	0.0	M02A
TAM243	69.2	0.0	0.0	M02A
TAM244	96.7	0.0	0.0	M02A
TAM247	32.4	0.0	0.0	M02A
TAM249	2.3	0.0	0.0	M02A
TAM254	2.1	0.0	0.0	M02A
UT00450	100.0	0.0	0.0	M02A
UT00776	100.0	0.0	0.0	M02A

The following specimens are assigned to group M08.					
ID. NO.	M02A	M08	M11	Group	
BAS148	0.0	99.9	0.0	M08	
BAS217	0.0	94.6	0.0	M08	
BRE008A	0.0	5.3	0.0	M08	
BRE183	0.0	60.1	0.0	M08	
BRE184A	0.0	54.3	0.0	M08	
ED-027	0.0	85.6	0.0	M08	
ED-035	0.0	75.3	0.0	M08	
ED-040	0.0	55.5	0.0	M08	
ED-051	0.0	99.4	0.0	M08	
ED-052	0.0	98.5	0.0	M08	
ED-075	0.0	90.8	0.0	M08	
HM005	0.0	18.5	0.0	M08	
HM010	0.0	29.7	0.0	M08	
HM022	0.0	76.2	0.0	M08	
HM034	0.0	91.8	0.0	M08	
HM058	0.0	25.2	0.0	M08	
LOA153	0.0	94.6	0.0	M08	
MPM008	0.0	0.2	0.0	M08	
MPM012	0.0	42.5	0.0	M08	
MPM014	0.0	10.4	0.0	M08	
MPM022	0.0	0.9	0.0	M08	
MPM2A	0.0	80.4	0.0	M08	
MPM2B	0.0	68.6	0.0	M08	
MPM2C	0.0	13.2	0.0	M08	
MPM2D	0.0	0.1	0.0	M08	
MPN005	0.0	15.7	0.0	M08	
MPT019	0.0	1.4	0.0	M08	
MPT025	0.0	4.9	0.0	M08	
MRM191	0.0	0.1	0.0	M08	
MRM249	0.0	78.4	0.0	M08	
MVP0001	0.0	32.9	0.0	M08	
MVP0043	0.0	79.4	0.0	M08	
MVP0055	0.0	58.3	0.0	M08	
MVP0059	0.0	93.5	0.0	M08	
MVP0147	0.0	93.7	0.0	M08	
MVP0161	0.0	93.8	0.0	M08	
MVP0240	0.0	98.0	0.0	M08	
MVP0256	0.0	18.6	0.0	M08	
MVP0262	0.0	98.0	0.0	M08	
MVP0263	0.0	15.7	0.0	M08	
MVP0267	0.0	99.0	0.0	M08	
MVP0281	0.0	2.6	0.0	M08	
MVP0289	0.0	81.2	0.0	M08	
MVP0310	0.0	79.5	0.0	M08	
MVP0356	0.0	95.4	0.0	M08	
MVP0402	0.0	0.0	0.0	M08	
MVP0404	0.0	86.0	0.0	M08	
MVP0408	0.0	78.9	0.0	M08	
MVP0425	0.0	99.4	0.0	M08	
MVP0429	0.0	10.0	0.0	M08	
MVP0450	0.0	11.1	0.0	M08	

MVP0468	0.0	82.5	0.0	M08
OK024	0.0	43.5	0.0	M08
OK064	0.0	79.6	0.0	M08
OK067	0.0	99.9	0.0	M08
OK080	0.0	75.6	0.0	M08
OK099	0.0	0.4	0.0	M08
OK144	0.0	29.5	0.0	M08
OT102	0.0	60.7	0.0	M08
OT498	0.0	94.6	0.0	M08
OT504	0.0	99.9	0.0	M08
OT506	0.0	29.7	0.0	M08
SWR001	0.0	81.7	0.0	M08
SWR015	0.0	89.8	0.0	M08
SWR021	0.0	49.6	0.0	M08
SWR027	0.0	55.0	0.0	M08
SWR054	0.0	97.8	0.0	M08
SWR073	0.0	71.8	0.0	M08
SWR082	0.0	33.0	0.0	M08
SWR099	0.0	57.7	0.0	M08
SWR117	0.0	2.1	0.0	M08
SWR121	0.0	6.6	0.0	M08
SWR131	0.0	73.0	0.0	M08
SWR142	0.0	4.8	0.0	M08
SWR150	0.0	26.2	0.0	M08
SWR152	0.0	1.7	0.0	M08
SWR167	0.0	36.9	0.0	M08
SWR169	0.0	97.3	0.0	M08
SWR171	0.0	66.9	0.0	M08
SWR176	0.0	80.6	0.0	M08
SWR177	0.0	54.9	0.0	M08
TAM113	0.0	27.6	0.0	M08
TAM114	0.0	14.4	0.0	M08
TAM222	0.0	48.0	0.0	M08
WCRM010	0.0	6.2	0.0	M08
***************************************	0.0	0.2	0.0	11.00
The following spec	cimens are assigned to	group M11.		
ID. NO.	M02A	M08	M11	Group
ATT020	0.0	0.0	25.0	M11
ATT021	0.0	0.0	71.1	M11
ATT100	0.0	0.0	95.7	M11
BAS136	0.0	0.0	99.7	M11
BAS141	0.0	0.0	96.0	M11
ED-074	0.0	0.0	16.6	M11
HM013	0.0	0.0	92.8	M11
HM015	0.0	0.0	95.3	M11
HM053	0.0	0.0	69.5	M11
MPN010	0.0	0.0	1.8	M11
MPT006	0.0	0.0	54.4	M11
MPT015	0.0	0.0	19.9	M11
MPT021	0.0	0.0	3.8	M11
MPT022	0.0	0.0	10.4	M11
MPT023	0.0	0.0	0.4	M11
MRM003	0.0	0.0	92.1	M11
	0.0	3.0	<u></u>	

MRM006	0.0	0.0	97.6	M11
MRM062	0.0	0.0	97.9	M11
MRM081	0.0	0.0	12.5	M11
MRM090	0.0	0.0	2.1	M11
MRM094	0.0	0.0	80.9	M11
MRM116	0.0	0.0	81.1	M11
MRM128	0.0	0.0	34.3	M11
MRM166	0.0	0.0	74.2	M11
MRM246	0.0	0.0	55.9	M11
MVP0034	0.0	0.0	99.2	M11
MVP0040	0.0	0.0	0.7	M11
MVP0058	0.0	0.0	99.8	M11
MVP0096	0.0	0.0	56.6	M11
MVP0134	0.0	0.0	65.7	M11
MVP0138	0.0	0.0	40.3	M11
MVP0155	0.0	0.0	85.6	M11
MVP0156	0.0	0.0	42.2	M11
MVP0183	0.0	0.0	85.1	M11
MVP0185	0.0	0.0	99.6	M11
MVP0197	0.0	0.0	30.8	M11
MVP0202	0.0	0.0	17.4	M11
MVP0208	0.0	0.0	98.2	M11
MVP0208	0.0	0.0	96.7	M11
	0.0	0.0	97.4	M11
MVP0234	0.0			
MVP0268		0.0	36.4	M11
MVP0270	0.0	0.0	7.6	M11
MVP0275	0.0	0.0	67.0	M11
MVP0276	0.0	0.0	16.8	M11
MVP0280	0.0	0.0	99.2	M11
MVP0302	0.0	0.0	76.3	M11
MVP0337	0.0	0.0	0.9	M11
MVP0352	0.0	0.0	0.8	M11
NAM004	0.0	0.0	99.7	M11
NAM017	0.0	0.0	15.7	M11
OK001	0.0	0.0	72.7	M11
OK006	0.0	0.0	60.7	M11
OK025	0.0	0.0	35.0	M11
OK068	0.0	0.0	89.6	M11
OK094	0.0	0.0	35.6	M11
OK116	0.0	0.0	30.4	M11
OK121	0.0	0.0	1.3	M11
OK130	0.0	0.0	70.0	M11
OK136	0.0	0.0	27.3	M11
OT174	0.0	0.0	80.8	M11
OT591	0.0	0.0	0.6	M11
OU0039	0.0	0.0	79.2	M11
OU0040	0.0	0.0	89.0	M11
RLB002	0.0	0.0	10.4	M11
RLB092	0.0	0.0	84.7	M11
RLB105	0.0	0.0	3.8	M11
SWC039	0.0	0.0	73.3	M11
SWC040	0.0	0.0	97.8	M11
SWR011	0.0	0.0	23.9	M11

SWR034	0.0	0.0	97.3	M11
SWR035	0.0	0.0	98.3	M11
SWR040	0.0	0.0	98.5	M11
SWR042	0.0	0.0	7.1	M11
SWR062	0.0	0.0	58.4	M11
SWR065	0.0	0.0	77.6	M11
SWR079	0.0	0.0	4.3	M11
SWR090	0.0	0.0	3.5	M11
SWR097	0.0	0.0	4.3	M11
SWR115	0.0	0.0	13.0	M11
SWR146	0.0	0.0	89.2	M11
SWR185	0.0	0.0	24.2	M11
TAM008	0.0	0.0	0.6	M11
TAM212	0.0	0.0	35.9	M11
WCRM007	0.0	0.0	13.2	M11

Table B4. Macro Group B2 Mahalanobis distance calculations for specimens projected against two or more groups

Mimbres-02B (M02B)

Mimbres-08 (M02C)

Variables used:

The following spe	cimens are assigned to a	group M02B.		
ID. NO.	M02A	M08	M11	Group
BRE160A	0.0	0.0	0.0	M02B
ED-005	0.1	0.0	0.0	M02B
MPN002	0.0	0.0	0.0	M02B
MPT004	0.0	0.0	0.0	M02B
MRM023	0.0	0.0	0.0	M02B
MRM076	10.8	0.0	0.0	M02B
MRM092	1.7	0.0	0.0	M02B
MRM144	0.0	0.0	0.0	M02B
MVP0154	0.7	0.0	0.0	M02B
MVP0207	1.7	0.0	0.0	M02B
MVP0416	0.1	0.0	0.0	M02B
MVP353	0.0	0.0	0.0	M02B
SWR105	0.0	0.0	0.0	M02B
SWR137	0.2	0.0	0.0	M02B
TAM112	0.0	0.0	0.0	M02B
TAM115	0.0	0.0	0.0	M02B
TAM118	0.1	0.0	0.0	M02B
TAM119	1.8	0.0	0.0	M02B
TAM120	0.0	0.0	0.0	M02B
TAM210	0.0	0.0	0.0	M02B
The following spe	cimens are assigned to	group M02C.		
ID. NO.	M02A	M08	M11	Group
MRM014	0.0	0.0	0.0	M02C
MRM089	0.0	0.0	0.0	M02C
MRM181	0.0	0.0	0.0	M02C
MRM238	0.0	0.0	0.0	M02C
MVP0128	0.0	0.0	0.0	M02C
MVP374	0.0	0.0	0.0	M02C
NAM006	0.0	0.0	0.0	M02C
NAM009	0.0	0.0	0.0	M02C
SWR196	0.0	0.0	0.0	M02C
SWR201	0.0	0.0	0.0	M02C

Table B.5. Mahalanobis distance calculations for unassigned specimens projected against Macro Group B compositional groups.

Variables used:

		Мас	ro Group B		Macro Group B-2						
ID. NO.	M04A	M04B	M04C	M05A	M05B	M02A	M08	M11			
ANI001	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0			
ANI008	0.0	0.0	0.0	0.0	0.3	0.0	0.0	0.0			
ANI031	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0			
ANI048	0.0	0.0	0.1	22.6	0.9	0.0	0.0	0.0			
ATT001	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0			
ATT022	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0			
ATT042	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0			
ATT211	0.0	0.0	0.0	0.2	1.0	0.0	0.0	0.0			
ATT239	0.0	0.0	0.0	0.0	6.8	0.0	0.0	0.0			
ATT345	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0			
ATT347	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0			
ATT361	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0			
ATT362	0.0	0.0	0.0	0.0	1.1	0.0	0.0	0.0			
ATT373	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0			
ATT377	0.0	0.0	0.0	0.0	19.7	0.0	0.0	0.0			
ATT382	0.0	0.0	0.0	60.6	0.0	0.0	0.0	0.0			
ATT386	0.0	0.0	0.0	0.0	0.3	0.0	0.0	0.0			
ATT387	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0			
ATT388	0.0	0.0	0.0	0.0	0.1	0.0	0.0	0.0			
ATT391	0.0	0.0	0.0	0.3	0.0	0.0	0.0	0.0			
ATT394	0.0	0.0	0.0	77.6	0.1	0.0	0.0	0.0			
ATT405	0.0	0.0	0.0	51.4	0.2	0.0	0.0	0.0			
ATT430	0.0	0.0	0.0	6.5	0.8	0.0	0.0	0.0			
ATT443	0.0	0.0	0.2	1.1	0.0	0.0	0.0	0.0			
ATT444	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0			
ATT447	0.3	0.0	1.1	0.0	2.8	0.0	0.0	0.0			
ATT450	0.0	0.0	0.0	0.0	8.3	0.0	0.0	0.0			
ATT499	0.0	0.0	0.2	0.1	0.2	0.0	0.0	0.0			
BAS005	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0			
BAS006	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0			
BAS008	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0			
BAS011	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0			
BAS015	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0			
BAS023	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0			
BAS026	0.0	0.0	0.3	2.8	0.6	0.0	0.0	0.0			
BAS041	0.0	0.0	0.0	24.7	0.0	0.0	0.0	0.0			
BAS046	0.0	0.0	0.0	51.0	0.0	0.0	0.0	0.0			
BAS051	0.0	0.0	0.0	0.0	0.1	0.0	0.0	0.0			
BAS059	0.1	0.0	0.0	0.0	25.8	0.0	0.0	14.4			
BAS060	0.0	0.0	1.2	0.3	5.5	0.0	0.0	0.0			
BAS065	0.4	0.0	0.0	0.0	0.0	0.0	0.0	0.0			
BAS073	0.1	6.6	0.0	0.0	0.2	0.0	0.0	0.0			
BAS077	0.0	0.0	0.0	0.1	1.8	0.0	0.0	0.0			
BAS107	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0			

BAS110	0.0	0.0	0.0	13.0	0.0	0.0	0.0	0.0
BAS123	0.0	0.0	0.0	13.6	66.3	0.0	0.0	0.0
BAS129	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
BAS133	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
BAS134	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
BAS137	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
BAS142	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
BAS145	0.0	0.0	0.0	0.0	0.2	0.0	0.0	0.0
BAS157	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
BAS164	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
BAS184	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
BAS191	0.0	0.0	0.6	0.0	0.0	0.0	0.0	0.0
BAS193	0.0	0.0	0.0	73.6	0.2	0.0	0.0	0.0
BAS196	0.0	0.0	0.0	0.0	0.6	0.0	0.0	0.0
BAS199	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
BAS205	0.0	0.0	0.0	0.0	3.0	0.0	0.0	0.0
BAS215	0.0	0.0	0.0	0.0	0.2	0.0	0.0	0.0
BAS219	0.0	0.0	0.0	0.0	0.2	0.0	0.0	0.0
BAS222	0.0	6.8	0.0	0.0	0.0	0.0	0.9	0.0
BRE001	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
BRE007	0.1	0.0	0.0	0.0	0.0	0.0	0.0	0.0
BRE009	0.0	0.0	0.0	0.0	0.0	0.0	0.5	0.0
BRE036	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
BRE038	0.0	0.0	1.1	0.5	0.0	0.0	0.0	0.0
BRE039	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
BRE040A	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
		0.0	0.0					
BRE042	0.0			0.0	0.0	0.0	0.0	0.0
BRE043	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
BRE044	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
BRE046	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
BRE047	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
BRE048A	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
BRE052	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
BRE053	0.0	0.0	0.0	0.0	1.9	0.0	0.0	0.0
BRE060	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
BRE065	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
BRE088A	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
BRE089	0.0	0.0	0.0	0.0	0.1	0.0	0.0	0.0
BRE091	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
BRE092	0.0	0.0	0.0	0.0	3.7	0.0	0.0	0.0
BRE104A	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
BRE105	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
BRE106	0.0	0.0	0.1	0.0	0.0	0.0	0.0	0.0
BRE139	0.0	2.2	0.0	0.0	0.0	0.0	0.0	0.0
BRE161	0.0	0.0	0.0	0.0	0.0	0.0	0.2	0.0
BRE162	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
BRE164	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
BRE187	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
BRE190	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
CAP172	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
CAP174	0.0	0.0	14.7	2.5	0.5	0.0	0.0	0.0
CAP177	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
CAP179	0.0	0.0	0.0	0.0	10.3	0.0	0.0	0.0

CAP189	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
CAP193	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
CAP202	0.1	0.0	0.3	0.0	7.3	0.0	0.0	0.3
CDA073	0.0	0.0	0.3	5.3	1.0	0.0	0.0	0.0
DJT002	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
DJT008	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
DJT011	0.0	0.0	0.0	0.4	0.1	0.0	0.0	0.0
DJT023	0.0	0.0	0.0	8.7	1.3	0.0	0.0	0.0
ED-007	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
ED-017	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
ED-021	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
ED-023	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
ED-038	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
ED-054	0.0	0.0	0.0	0.0	7.5	1.7	0.0	0.0
ED-076	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
ED-098	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
HM007	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
HM008	14.0	0.0	1.0	0.0	0.5	0.0	0.0	0.0
HM016	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
HM019	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
HM030	0.0	0.0	0.0	0.0	0.1	0.0	0.0	0.0
HM033	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
HM049	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
HM061	36.3	0.0	1.2	0.0	19.3	0.0	0.0	0.0
HM072	8.0	11.0	0.0	0.0	0.5	0.0	0.0	0.0
HM074	0.1	0.0	0.0	0.0	3.6	0.0	0.0	0.0
HM076	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
HM077	0.0	0.0	0.0	0.0	5.3	0.0	0.0	2.0
HM094	0.0	0.4	0.0	0.0	0.0	0.0	0.0	0.0
JAM005	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
JAM006	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
JAM010	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
JAM011	0.2	0.0	0.0	0.0	0.0	0.0	0.0	0.0
JAM012	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
JAM028	2.2 0.0	0.0 0.0	0.0 0.0	0.0	0.0	0.0 0.0	0.0 0.0	0.0
JAM032	0.0	0.0	0.0	0.0 0.0	0.0 0.0	0.0		0.0
JAM038 JAM039	0.0	0.0	0.0	0.0	0.0	0.0	0.0 0.0	0.0 0.0
JAM042	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
JAM049	5.5	0.0	0.0	0.0	0.0	0.0	0.0	0.0
JAM050	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
JAM053	0.0	0.0	0.0	0.5	1.5	0.6	0.0	0.0
JAM066	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
JAM067	0.0	0.0	1.6	0.3	6.2	0.0	0.0	0.0
JAM071	0.4	0.0	0.0	0.0	0.0	0.0	0.0	0.0
JAM071 JAM072	0.4	0.0	0.0	0.0	0.0	0.0	0.0	0.0
JAM075	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
JAM085	0.0	0.0	0.0	0.0	1.8	0.0	0.0	2.7
JAM090	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
JAM101	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
JAM101 JAM104	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
JAM104 JAM109	0.0	0.0	0.0	0.0	0.2	0.0	0.0	0.0
JAM118	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
TUINITTO	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0

JAM122	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
JAM126	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
JAM127	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
JAM129	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
JAM131	0.0	0.0	0.0	10.0	0.0	0.0	0.0	0.0
JHK005	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
KCW004	0.0	0.0	0.0	0.0	2.4	0.0	0.1	1.2
KCW014	52.7	70.0	0.1	0.0	0.6	0.0	0.0	0.0
LOA002	0.0	0.0	0.0	9.8	15.4	0.0	0.0	0.0
LOA010	0.0	0.0	0.0	49.9	94.3	0.0	0.0	0.0
LOA011	0.0	0.0	0.0	37.9	79.5	0.0	0.0	0.0
LOA026	0.0	0.0	0.0	0.0	0.1	0.0	0.0	0.0
LOA027	0.0	0.0	0.0	0.4	5.1	0.0	0.0	0.0
LOA028	0.0	0.0	0.0	0.0	0.2	0.0	0.0	0.0
LOA031	0.0	0.0	0.0	0.0	89.7	0.0	0.0	0.0
LOA034	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
LOA042	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
LOA058	0.0	0.0	0.0	0.0	0.1	0.0	0.0	0.0
LOA060	0.0	0.0	0.0	30.6	78.1	0.0	0.0	0.0
LOA061	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
LOA075	0.0	0.0	0.0	1.2	3.3	0.0	0.0	0.0
LOA079	0.0	0.0	0.0	0.0	0.5	0.0	0.0	0.0
LOA080	0.0	0.0	0.0	0.0	0.2	0.0	0.0	0.0
LOA084	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
LOA100	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
LOA102	0.0	0.0	0.0	0.0	25.3	0.0	0.0	0.0
LOA103	0.0	0.0	0.0	1.0	62.1	0.0	0.0	0.0
LOA105	0.0	0.0	0.0	0.0	19.8 7.5	0.0	0.0	0.0
LOA110 LOA113	0.0 0.0	0.0 0.0	0.0 0.0	0.0 10.1	7.5 47.9	0.0 0.0	0.0 0.0	0.0 0.0
LOA115 LOA115	0.0	0.0	0.0	1.2	0.1	0.0	0.0	0.0
LOA113	0.0	0.0	0.0	0.2	23.6	0.0	0.0	0.0
LOA145	0.0	0.0	0.0	4.7	26.3	0.0	0.0	0.0
LOA150	0.0	0.0	0.0	0.3	33.9	0.0	0.0	0.0
LOA223	0.0	0.0	0.0	0.5	3.0	0.0	0.0	0.0
LOA224	0.0	0.0	0.0	0.5	0.0	0.0	0.0	0.0
LOA225	0.0	0.0	0.0	22.5	8.3	0.0	0.0	0.0
LOA227	0.0	0.0	0.0	1.9	18.4	0.0	0.0	0.0
LOA228	0.0	0.0	0.0	14.1	3.3	0.0	0.0	0.0
LOA229	0.0	0.0	0.0	88.7	18.0	0.0	0.0	0.0
MPC003	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
MPC006	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
MPC008	0.1	0.0	0.0	0.0	0.1	0.0	0.0	0.0
MPC010	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
MPC011	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
MPC017	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
MPC022	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
MPC025	8.2	20.8	0.0	0.0	0.0	0.0	0.0	0.0
MPG024	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
MPG026	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
MPG027	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
MPG029	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
MPG046	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0

MPG047	0.0	0.0	0.0	0.0	0.2	0.0	0.0	0.0
MPM002	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
MPM004	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
MPM015	0.0	0.1	0.0	0.0	0.0	0.0	0.0	0.0
MPM018	0.0	0.0	0.0	0.0	0.7	0.0	0.0	0.0
MPM024	1.9	0.0	0.1	0.0	0.0	0.0	0.0	0.0
MPN003	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
MPN007	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
MPN008	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
MPN012	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
MPN014	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
MPN021	1.1	0.0	0.0	0.0	0.0	0.0	0.0	0.0
MPP002	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
MPP006	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
MPP021	0.0	0.0	0.0	0.0	0.2	0.0	0.0	0.0
MPP023	0.0	0.0	0.0	34.2	0.0	0.0	0.0	0.0
MPT009	0.0	0.0	0.0	0.0	0.2	0.0	0.0	0.0
MPT012	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
MPT013	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
MPT017	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
MPT018	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
MPT020	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
MPT024	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
MRM005	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
MRM011	0.0	0.0	0.0	0.0	0.5	0.0	0.0	0.0
MRM018	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
MRM019	0.0	0.0	0.0	0.0	0.2	0.0	0.0	0.0
MRM025	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
MRM029	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
MRM038	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
MRM041	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
MRM059	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
MRM074	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
MRM075	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
MRM078	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
MRM085	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
MRM088	0.0	0.0	0.0	0.0	0.1	0.0	0.0	0.0
MRM105	0.0	0.0	0.0	0.5	0.0	0.0	0.0	0.0
MRM106	0.4	0.0	6.6	0.6	11.9	0.0	0.0	0.0
MRM114	0.0	0.3	0.0	0.0	0.0	0.0	0.0	0.0
MRM120	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
MRM121	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
MRM129	0.0	0.0	0.0	0.0	3.1	0.0	0.0	0.0
MRM133	0.0	2.7	0.0	0.0	0.0	0.0	0.0	0.0
MRM136	0.0 0.0	0.0 0.0	0.0 0.0	0.0 0.0	0.1 0.0	0.0 0.0	0.0 0.0	0.0 0.0
MRM143	0.0	0.0	0.0	0.0	0.0		0.0	0.0
MRM148 MRM149	1.3	0.0	34.1	8.1	11.6	0.0 0.0	0.0	0.0
MRM160	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
MRM161	1.1	0.0	1.8	1.2	11.6	0.0	0.0	0.0
MRM165	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
MRM167	0.0	0.0	0.0	0.0	0.0	0.0	0.2	0.0
MRM182	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
	0.0	0.0	0.0	0.0	0.0	0.0	5.5	5.0

MRM186	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
MRM189	0.0	0.0	0.0	0.0	0.7	0.0	0.0	0.0
MRM194	0.0	0.0	0.0	0.0	0.0	0.0	0.1	0.0
MRM195	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
MRM199	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
MRM204	0.0	0.0	15.8	12.8	6.6	0.0	0.0	0.0
MRM213	0.0	0.0	20.1	13.6	0.6	0.0	0.0	0.0
MRM214	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
MRM225	0.0	0.8	0.0	0.0	0.0	0.0	0.0	0.0
MRM227	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
MRM231	0.0	3.4	0.0	0.0	0.0	0.0	0.0	0.0
MRM234	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
MRM250	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
MRM255	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
MRM260	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
MRM261	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
MRM262	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
MRM263	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
MRM340	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
MVP0002	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
MVP0005	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
MVP0011	0.0	9.9	0.0	0.0	0.0	0.0	33.0	0.0
MVP0012	0.0	0.0	0.0	0.0	2.5	0.0	0.0	0.0
MVP0016	92.8	0.0	16.8	0.0	16.6	0.0	0.0	0.0
MVP0018	59.8	0.0	0.2	0.0	15.5	0.0	0.0	0.0
MVP0020	0.0	3.2	0.0	0.0	0.0	0.0	0.0	0.0
MVP0024	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
MVP0033	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
MVP0038	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
MVP0042	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
MVP0047	0.0	0.0	0.0	0.1	0.0	0.0	0.0	0.0
MVP0049	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
MVP0050	0.0	0.0	0.0	0.0	0.2	0.0	0.0	0.0
MVP0051	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
MVP0053	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
MVP0061	3.5	0.0	81.9	21.3	4.7	0.0	0.0	0.0
MVP0063	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
MVP0064	0.0	0.0	0.0	0.7	0.0	0.0	0.0	0.0
MVP0071	0.0	0.0	0.0	0.3	0.0	0.0	0.0	0.0
MVP0074	0.0	0.0	0.0	0.1	0.0	0.0	0.0	0.0
MVP0076	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
MVP0086	0.0	2.8	0.0	0.0	0.0	0.0	0.0	0.0
MVP0091	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
MVP0093	0.1	0.0	0.0	0.0	0.0	0.0	0.0	0.0
MVP0098	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
MVP0101	0.0	0.0	0.0	0.0	0.3	0.0	0.0	0.0
MVP0102	0.2	1.8	0.0	0.0	0.0	0.0	0.0	0.0
MVP0104	0.0	0.0	0.0	0.0	0.7	0.0	0.0	0.0
MVP0105	0.0	6.9	0.0	0.0	0.0	0.0	0.0	0.0
MVP0112	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
MVP0113	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
MVP0119	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
MVP0120	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0

MVP0121	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
MVP0123	0.0	2.3	0.0	0.0	0.2	0.0	0.0	0.0
MVP0124	0.0	0.0	0.0	0.0	0.9	0.0	0.0	0.0
MVP0125	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
MVP0127	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
MVP0131	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
MVP0141	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
MVP0142	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
MVP0149	0.0	0.0	0.0	0.0	0.3	0.0	0.0	0.0
MVP0157	0.0	0.0	0.0	0.0	0.1	0.0	0.0	0.0
MVP0162	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
MVP0168	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
MVP0175	0.0	0.0	0.0	0.0	0.0	0.1	0.0	0.0
MVP0176	0.2	0.0	0.0	0.0	0.0	0.0	0.0	0.0
MVP0178	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
MVP0182	51.8	86.8	0.0	0.0	0.1	0.0	0.0	0.0
MVP0193	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
MVP0210	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
MVP0214	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
MVP0227	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
MVP0239	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
MVP0241	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
MVP0242	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
MVP0244	0.0	0.0	0.0	0.0	0.1	0.0	0.0	0.0
NAM014	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
NAM016	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
OK011	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
OK014	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
OK015	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
OK030	0.0	0.7	0.0	0.0	0.0	0.0	0.0	0.0
OK047	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
OK063	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
OK085	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
OK100	2.4	8.3	0.0	0.0	0.0	0.0	0.0	0.0
OK108	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
OK110	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
OK119	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
OK120	0.0	0.1	0.0	0.0	0.0	0.0	0.0	0.0
OK126	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
OK127	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
OK138	0.0	0.0	0.0	0.0	0.1	0.0	0.0	0.0
OK142	27.6	0.0	0.1	0.0	0.1	0.0	0.0	0.0
OK145	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
OK146	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
OK150	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
OT033	0.0	0.0	0.0	0.0	0.7	0.0	0.0	0.0
OT075	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
OT088	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
OT101	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
OT119	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
OT132	0.0	0.0	0.0	0.0	1.1	0.0	0.0	0.0
OT134	0.0	0.0	0.2	0.0	0.4	0.0	0.0	0.0
OT157	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0

OT167	0.0	0.0	0.0	18.6	0.0	0.0	0.0	0.0
OT169	0.0	0.0	6.2	0.0	0.0	0.0	0.0	0.0
OT170	4.2	0.0	4.1	0.0	1.4	0.0	0.0	0.0
OT172	1.3	0.0	3.7	0.0	0.1	0.0	0.0	0.0
OT173	0.1	0.0	7.3	0.2	4.4	0.0	0.0	0.0
OT178	0.0	0.0	0.0	0.1	0.0	0.0	0.0	0.0
OT179	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
OT183	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
OT201	0.0	0.0	0.0	0.0	8.9	0.0	0.0	0.0
OT202	0.0	0.0	0.0	0.0	1.4	0.3	0.0	0.0
OT204	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
OT222	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
OT236	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
OT249	0.5	0.0	0.0	0.0	0.1	0.0	0.0	0.0
OT250	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
OT252	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
OT268	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
OT272	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
OT509	0.0	0.2	0.0	0.0	0.0	0.0	0.0	0.0
OT510	0.0	0.0	0.0	0.0	0.1	0.0	0.0	0.0
OT515	0.0	0.0	0.1	0.0	0.0	0.0	0.0	0.0
OT516	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
OT586	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
OT589	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
OU0002	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
OU0018	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
PDR004	0.0	0.0	0.0	0.0	0.1	0.0	0.0	0.0
RLB006	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
RLB008	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
RLB010	0.1	0.0	7.0	3.8	0.0	0.0	0.0	0.0
RLB064	0.0	0.0	0.0	4.0	14.8	0.0	0.0	0.0
RLB104	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
RLB110	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
RLB134	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
RLB175	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
RLB197	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
RLB208	0.0	0.0	0.1	9.9	0.0	0.0	0.0	0.0
RLB209	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
RLB210	0.0	0.2	0.0	0.0	0.0	0.0	0.0	0.0
RLB214	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
RLB219	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
RLB224	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
RLB238	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
RLB242	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
RLB246	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
RLB262	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
SWC032	0.0	0.1	0.0	0.0	0.0	0.0	0.0	0.0
SWC033	0.0	0.6	0.0	0.0	0.0	0.0	0.0	0.0
SWC035	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
SWC044	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
SWR003	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
SWR006	0.6	7.1	0.0	0.0	0.0	0.0	0.0	0.0
SWR019	46.9	0.0	1.4	0.0	23.3	0.0	0.0	0.0

SWR028	75.7	0.0	1.1	0.0	31.8	0.0	0.0	0.0
SWR029	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
SWR037	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
SWR038	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
SWR048	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
SWR052	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
SWR058	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
SWR060	0.0	0.0	0.0	0.0	0.7	0.0	0.0	0.0
SWR064	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
SWR068	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
SWR069	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
SWR070	0.0	0.0	0.0	0.0	0.1	0.0	0.0	0.0
SWR072	0.0	0.0	0.0	0.0	0.1	0.0	0.0	0.0
SWR074	0.6	0.0	0.0	0.0	0.0	0.0	0.0	0.0
SWR077	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
SWR088	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
SWR098	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
SWR100	0.0	0.0	0.0	0.0	0.1	0.0	0.0	0.0
SWR102	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
SWR104	0.0	0.7	0.0	0.0	0.0	0.0	0.0	0.0
SWR108	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
SWR109	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
SWR123	0.0	0.3	0.0	0.0	0.0	0.0	2.6	0.0
SWR124	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
SWR126	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
SWR133	21.5	8.9	0.0	0.0	0.1	0.0	0.0	0.0
SWR141	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
SWR143	0.1	0.0	0.0	0.0	0.0	0.0	0.0	0.0
SWR144	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
SWR153	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
SWR156	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
SWR158	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
SWR159	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
SWR163	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
SWR164	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
SWR165	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
SWR168	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
SWR173	0.0	0.0	0.0	0.0	1.0	0.0	0.0	0.0
SWR174	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
SWR175	0.0	0.0	0.0	0.0	3.5	0.0	0.0	0.1
SWR189	0.1	0.6	0.0	0.0	0.0	0.0	0.0	0.0
SWR198	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
SWR216	0.0	0.0	0.0	0.0	10.8	0.0	0.0	0.0
SWR217	0.0	0.0	0.0	0.0	3.4	0.0	0.0	0.0
TAM026	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
TAM044	0.0	0.0	0.0	7.5	5.9	0.0	0.0	0.0
TAM053	0.0	0.0	0.0	6.7	6.4	0.0	0.0	0.0
TAM061	0.0	0.0	0.0	0.0	0.1	0.0	0.0	0.0
TAM075	0.0	0.0	0.0	18.0	0.0	0.0	0.0	0.0
TAM111	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
TAM202	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
TAM221	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
TAM230	0.1	1.5	0.0	0.0	0.0	0.0	0.0	0.0

TAM231	0.0	0.1	0.0	0.0	0.4	0.0	0.0	0.0
TAM245	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
TAM246	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
TAM248	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
TAM253	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
UT00452	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
UT00457	0.0	0.0	0.1	2.6	2.0	0.0	0.0	0.0
UT00461	0.0	0.0	0.0	0.0	5.1	0.0	0.0	0.0
UT00463	0.0	0.0	0.0	1.0	0.0	0.0	0.0	0.0
UT00479	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
UT00482	0.0	0.0	0.0	0.0	1.3	0.0	0.0	0.0

Table B6. Principal component analysis for Macro Group B pottery (R-Q factor analysis based on variance-covariance matrix).

Eigenvalues and Percentage of Variance Explained:

Cum. %Var. 28.68	7		9	73.04	78.00	81.81	84.76	87.28	89.48	90.92	92.29	93.53	94.65	95.58	96.33	97.04	97.54	98.04	98.42	98.79	99.10	99.41	99.58	99.75	68.66	100.00
%Var. 28.68	7.5	ij	Η.	<u></u>	4.96	3.81	2.95	2.52	2.20	1.45	1.36	1.25	1.11	0.93	0.75	0.71	0.50	0.50	0.39	0.37	0.31	0:30	0.18	0.17	0.14	0.11
Eigenvalue 0.1296	.079	0.0539	.036	0.0304	0.0224	0.0172	0.0133	0.0114	0.0099	0.0065	0.0062	0.0056	0.005	0.0042	0.0034	0.0032	0.0023	0.0022	0.0018	0.0017	0.0014	0.0014	0.0008	0.0008	9000.0	0.0005
PCA 1	2	m ·	4	2	9	7	∞	6	10	11	12	13	14	15	16	17	18	19	20	21	22	23	24	25	56	27

34 0.31 -0.18 0.03 0.00 0.03 0.02 0.07 -0.09 -0.04 -0.06 -0.05 -0.01 -0.03 -0.02 0.01 0.01 0.00 0.00 -0.04 0.04 -0.05 0.00 0.05 -0.03 -0.24 -0.21 -0.27 -0.07 0.18 0.11 -0.05 0.33 -0.35 -0.37 -0.30 -0.30	0.11 0.03 -0.15 -0.03 -0.01 0.15 -0.16 0.00 0.14 0.00 0.29 0.15 0.28 0.27 0.18 -0.32 -0.22 0.03 0.10 0.18 -0.17 -0.20 0.22 -0.70 0.21 0.12 0.24 -0.01 -0.04 -0.04 -0.05 0.07	-0.06 0.02 -0.01 0.02 -0.06 -0.07 -0.03 0.12 -0.03 -0.03 -0.07 -0.05 -0.06 -0.08 -0.04 -0.13 0.09 -0.29 -0.11 -0.06 0.54 -	0.51 -0.34 0.51 0.12 0.18 -0.26 0.00 0.14 0.15 0.13 0.06 0.02 0.06 -0.03 -0.03 0.09 -0.02 -0.04 -0.05 0.02	0.08 0.05 -0.24 -0.09 -0.04 0.14 -0.12 0.16 0.12 0.07 0.09 0.10 0.14 0.11 0.10 -0.24 -0.22 -0.07	-0.04 -0.07 0.00 0.00 0.03 0.03 0.02 0.04 -0.16 -0.34 -0.26 -0.26 0.28 0.29 -0.20 0.32 -0.47 0.33 0.03 -0.04 0.05	0.34 -0.06 -0.08 0.17 -0.23 0.15 0.08 -0.01 0.49 -0.14 -0.23 -0.22 -0.19 0.18 0.07 0.04 0.07 -0.02 0.08 0.00	-0.31 0.04 0.16 -0.21 0.17 0.01 -0.06 -0.05 -0.05 0.01 -0.01 -0.01 -0.03 0.03 0.02 0.07 -0.06 -0.09 0.03 0.01 -0.01	-0.16 - 0.07 0.17 0.02 0.02 - 0.11 - 0.03 0.17 - 0.06 - 0.23 - 0.11 - 0.05 - 0.09 - 0.25 - 0.25 - 0.34 0.02 - 0.12 0.53 0.27 - 0.28 - 0.18 -	0.11 0.05 0.07 0.08 0.01 0.18 0.23 -0.02 -0.17 -0.10 0.12 0.04 0.37 -0.45 0.41 0.27 -0.23 -0.35 0.06 0.00 -0.02	0.12 0.00 -0.22 -0.36 0.23 -0.04 0.15 -0.10 0.10 0.05 0.09 -0.05 0.43 0.12 -0.40 0.25 0.44 -0.20 0.09 0.14 -0.02	0.11 -0.20 -0.05 -0.04 -0.03 0.36 -0.04 -0.18 0.05 -0.58 0.10 0.38 -0.11 -0.30 -0.28 -0.01 0.09 0.10 -0.17 -0.07	$-0.40 \; -0.48 \; -0.18 \; \; 0.13 \; -0.04 \; -0.11 \; -0.03 \; \; 0.13 \; -0.01 \; \; 0.09 \; \; 0.07 \; -0.04 \; \; 0.10 \; -0.01 \; \; 0.07 \; \; 0.02 \; \; 0.01 \; -0.01 \; \; 0.01 \; \; 0.01 \; \; 0.00 \; 0.00 \; \; 0.00 \; \; 0.00 \; \; 0.00 \; \; 0.00 \; \; 0.00 \; \; 0.00 \; \; 0.00 \; \; 0.00 \; \; 0.00 \; \; 0.00 \; \; 0.00 \; \; 0.00 \; \; 0.00 \; \; 0.$	0.02 0.08 0.02 0.07 0.01 -0.02 0.12 0.14 -0.01 0.17 -0.13 -0.05 0.32 -0.31 -0.07 -0.30 0.19 0.52 -0.23 -0.05 0.26	0.22 -0.08 -0.18 -0.14 -0.05 0.34 -0.05 -0.13 -0.17 0.38 0.05 -0.49 -0.19 -0.30 -0.30 -0.08 -0.22 -0.07 0.04 -0.15 -0.05	0.14 -0.06 0.00 0.05 -0.03 0.26 0.08 -0.20 -0.31 -0.07 -0.05 -0.20 0.01 0.12 0.40 -0.05 0.35 0.24 0.26 0.42 0.12	0.06 0.12 -0.21 0.50 0.74 0.08 -0.11 -0.12 -0.08 0.06 -0.09 0.09 -0.16 0.04 -0.05 0.02 0.00 -0.02 0.00 0.00 0.00	0.12 -0.14 -0.18 -0.51 0.31 -0.22 0.46 -0.04 -0.02 -0.09 -0.06 0.08 -0.32 0.00 0.26 -0.18 -0.18 0.13 -0.01 -0.09 0.01	0.00 0.01 0.08 0.02 0.03 0.00 0.02 0.05 -0.16 0.02 -0.04 0.01 0.11 -0.13 0.05 0.00 0.23 0.24 -0.08 -0.33 -0.62	-0.27 -0.19 0.46 -0.21 0.19 0.57 -0.04 -0.05 0.18 0.24 -0.14 0.10 0.00 0.15 0.05 -0.01 0.01 0.01 -0.05 0.00 0.04	0.00 0.07 -0.16 -0.10 -0.17 0.04 -0.12 0.28 -0.05 0.22 -0.05 0.27 -0.32 -0.11 0.07 0.55 0.17 0.17 0.13 -0.02 -0.02	0.05 -0.28 0.11 -0.13 -0.02 -0.08 0.00 -0.04 -0.03 0.05 -0.01 -0.01 -0.01 -0.02 0.02 0.01 0.08	$-0.11 0.00 0.05 \ -0.10 0.23 \ -0.03 \ -0.28 0.16 0.20 \ -0.27 0.56 \ -0.47 \ -0.13 \ -0.12 0.17$	0.21 -0.05 0.04 -0.25 -0.05 -0.24 -0.66 -0.38 -0.24 -0.02 -0.15 0.09 0.05 -0.02 0.10 -0.03 -0.03 0.01 -0.04 0.03 0.03 0.03	013 001 019 009 -013 007 019 011 -049 003 049 017 -016 035 -023
54 0.31 - 06 0.04	0.03 -0.15 -	0.02 -0.01	-0.34 0.51	0.05 -0.24 -	-0.07 0.00	-0.06 -0.08	0.04 0.16	-0.07 0.17	0.05 0.07	0.00 -0.22	-0.20 -0.05	-0.48 -0.18	0.08 0.02	-0.08 -0.18	-0.06 0.00	0.12 -0.21	-0.14 -0.18	0.01 0.08	-0.19 0.46	0.07 -0.16	-0.28 0.11	0.00 0.05	-0.05 0.04	010
smallest compone 0.22 0.54 0.03 0.13 -0.01 -0.08	-0.02	-0.02	0.12	-0.04	0.00	0.01	-0.33	-0.06	-0.01	0.05	0.10	0.64	-0.08	0.09	0.08	0.02	0.10	0.00	90.0	-0.01	-0.32	-0.08	0.13	000
Eigenvectors (largest to smallest component): As 0.10 0.19 -0.23 0.22 0.54 0.03 0.6 La 0.18 -0.03 0.15 0.13 -0.01 -0.08 -0.0	0.09 0.12 -0.01 0.18	0.00 0.18	0.08 0.28	0.08 0.12	-0.03 0.10	0.34 -0.08	0.77 0.22	-0.06 0.11	0.06 -0.07	0.00 0.02	0.12 0.04	0.27 -0.11	0.18 0.07	0.07 0.05	0.03 0.12	0.08 -0.10	-0.03 0.08	0.01 0.03	-0.23 0.02	0.03 0.21	0.13 -0.75	-0.12 0.00	0.03 0.00	0.14 -0.06
Eigenv As (La (3 PN																							>

Appendix C:
Macro Group C Mahalanobis Distance Calculations and PCA Scores

Table C1. Macro Group C-1 Mahalanobis distance calculations for specimens projected against two or more groups.

Mimbres-21 (M21)

Mimbres-23 (M23)

Mimbres-24 (M24)

Variables used:

The	following	specimens a	ra accianad	to group	M21
1116	IUIIUWIIIE	specimens ar	ie assiglieu	to group	IVIZI .

ID. NO.	M21	M23	M24	Group
ANI003	25.7	0.8	0.0	M21
ANIO22	91.9	0.8	0.0	M21
ANIO24	4.1	0.3	0.0	M21
ANIO24	65.6	0.5	0.0	M21
ANIO29	98.3	0.4	0.0	M21
ANI030	93.9	0.2	0.0	M21
BAS120	41.8	0.6	0.0	M21
BAS122	99.1	0.4	0.0	M21
BAS124	89.1	0.7	0.0	M21
BAS125	94.8	0.7	0.0	M21
BAS126	4.2	0.3	0.0	M21
BAS127	10.6	0.3	0.0	M21
BAS130	9.1	0.2	0.0	M21
BAS132	78.0	0.3	0.0	M21
BAS135	40.5	0.4	0.0	M21
BAS139	98.5	1.2	0.0	M21
BAS146	95.7	0.8	0.0	M21
BAS147	75.2	0.5	0.0	M21
BAS149	8.2	0.2	0.0	M21
BAS197	37.4	0.4	0.0	M21
BAS198	97.2	0.5	0.0	M21
BAS203	98.8	0.5	0.0	M21
BAS204	97.5	0.9	0.0	M21
BAS208	99.2	0.3	0.0	M21
BAS209	12.1	0.4	0.0	M21
BRE075	59.9	0.3	0.0	M21
BRE078	73.5	0.5	0.0	M21
BRE082	47.8	1.0	0.0	M21
DJT001	98.3	0.2	0.0	M21
DJT005	99.9	0.9	0.0	M21
DJT007	90.6	0.3	0.0	M21
DJT010	88.4	0.2	0.0	M21
DJT012	98.7	0.6	0.0	M21
DJT015	78.2	0.7	0.0	M21
DJT022	44.6	0.2	0.0	M21
ED-093	16.1	0.6	0.0	M21
ED-100	6.9	0.1	0.0	M21
ED-103	42.0	0.5	0.0	M21
HM040	93.7	0.1	0.0	M21

HM042	88.8	0.3	0.0	M21
HM045	63.3	0.1	0.0	M21
HM059	0.4	0.3	0.0	M21
HM087	19.9	0.2	0.0	M21
HM089	98.0	0.3	0.0	M21
HM091	72.0	0.1	0.0	M21
KCW015	77.2	0.4	0.0	M21
LOA017	98.8	0.6	0.0	M21
LOA018	2.0	0.1	0.0	M21
LOA019	91.8	0.8	0.0	M21
LOA091	75.5	0.3	0.0	M21
LOA092	98.9	0.7	0.0	M21
LOA093	67.0	1.0	1.4	M21
LOA096	98.8	0.5	0.0	M21
LOA119	5.8	0.1	0.0	M21
LOA205	37.7	0.7	0.0	M21
LOA206	78.4	0.6	0.0	M21
LOA207	4.2	0.2	0.0	M21
LOA211	54.0	1.5	0.0	M21
LOA214	86.2	0.3	0.0	M21
LOA215	87.4	0.7	0.0	M21
LOA218	71.2	0.2	0.0	M21
MPC023	3.2	0.1	0.0	M21
MPG048	8.1	0.7	0.0	M21
MPM1A	7.9	0.1	0.0	M21
MPM1B	1.3	0.1	0.0	M21
MPM1D	2.7	0.1	0.0	M21
MPP003	74.5	1.6	0.0	M21
MPP015	43.5	0.8	0.0	M21
MPP019	63.1	0.4	0.0	M21
MPT008	32.5	0.2	0.0	M21
MRM048	89.0	0.8	0.0	M21
MRM100	11.0	0.6	0.0	M21
MRM163	76.8	0.3	0.0	M21
MRM174	92.4	0.4	0.0	M21
MRM200	94.4	0.4	0.0	M21
MRM268	78.6	0.6	0.0	M21
			0.0	M21
MRM272	22.0 6.6	0.2 0.2	0.0	M21
MRM273 MVP0037	39.7	0.5	0.0	M21
	86.5	0.4	0.0	M21
MVP0180 MVP0265	90.5	0.7	0.0	M21
	2.0	0.6	0.5	M21
MVP0312 MVP0326	43.4	0.8	0.0	M21
MVP0335	19.0	0.6	0.0	M21
MVP0336	17.5 28.7	0.3	3.7	M21
MVP0339	28.7 9.8	0.4 0.2	0.0 0.0	M21 M21
MVP0361				M21
MVP0365 MVP0366	1.3 77.8	0.5 0.3	0.0 0.0	
	77.8 61.4			M21
MVP0415 MVP0424		0.7	0.0 0.0	M21
	4.0	0.3		M21
NAM019	27.9	0.1	0.0	M21

OK012	79.5	0.2	0.0	M21
OK019	29.1	0.7	0.0	M21
OK032	5.1	0.2	0.0	M21
OK033	77.6	0.4	0.0	M21
OK038	62.8	0.3	0.0	M21
OK039	30.7	0.2	0.0	M21
OK040	43.6	0.6	0.0	M21
OK041	81.6	0.2	0.0	M21
OK044	66.9	0.3	0.0	M21
OK048	6.3	0.8	0.0	M21
OK049	1.9	0.8	0.0	M21
OK052	26.4	0.7	0.0	M21
OK054	53.3	0.6	0.0	M21
OK055	57.3	0.2	0.0	M21
OK057	81.9	0.5	0.0	M21
OK062	75.9	0.5	0.0	M21
OK088	98.1	0.5	0.0	M21
OK105	69.3	0.2	0.0	M21
OT187	38.2	0.4	0.0	M21
OT189	36.5	0.2	0.0	M21
OT205	93.3	0.5	0.0	M21
OT235	49.2	0.3	0.0	M21
OT262	31.3	0.5	0.0	M21
RLB011	34.2	0.3	0.0	M21
RLB021	0.9	0.1	0.0	M21
RLB027	93.0	0.5	0.0	M21
RLB029	19.2	0.2	0.0	M21
RLB030	84.3	0.7	0.0	M21
RLB031	32.4	0.1	0.0	M21
RLB032	96.3	0.6	0.0	M21
RLB033	86.4	0.5	0.0	M21
RLB034	89.0	0.5	0.0	M21
RLB035	90.9	0.5	0.0	M21
RLB036	94.6	0.3	0.0	M21
RLB038	94.5	1.1	0.0	M21
RLB040	14.2	0.3	0.0	M21
RLB043	42.8	0.8	0.0	M21
RLB044	52.2	0.2	0.0	M21
RLB045	82.5	0.1	0.0	M21
RLB058	88.1	0.2	0.0	M21
RLB061	87.6	0.1	0.0	M21
RLB085	80.4	1.3	0.0	M21
RLB086	91.4	0.3	0.0	M21
RLB087	29.6	0.2	0.0	M21
RLB088	73.8	0.4	0.0	M21
RLB108	7.9	0.8	0.0	M21
RLB111	17.3	0.1	0.0	M21
RLB113	67.4	0.1	0.0	M21
RLB114	4.4	0.8	0.0	M21
RLB115	29.4	0.6	0.0	M21
RLB117	69.1	0.2	0.0	M21
RLB118	11.7	0.1	0.0	M21
RLB119	52.4	0.8	0.0	M21

RLB120	21.8	0.0	0.0	M21
RLB122	34.1	0.1	0.0	M21
RLB123	62.5	0.2	0.0	M21
RLB125	26.8	0.2	0.3	M21
RLB126	95.4	0.2	0.0	M21
RLB127	1.1	0.4	0.0	M21
RLB128	8.7	1.3	0.0	M21
RLB129	8.2	0.5	0.0	M21
RLB130	1.2	0.2	0.0	M21
RLB131	74.2	0.7	0.0	M21
RLB132	1.0	0.6	0.0	M21
RLB133	71.8	0.2	0.0	M21
RLB136	83.4	0.2	0.0	M21
RLB137	3.8	0.2	0.0	M21
RLB138	44.2	0.3	0.0	M21
RLB140	78.2	0.2	0.0	M21
RLB142	1.1	0.3	0.0	M21
RLB144	87.7	0.1	0.0	M21
RLB145	24.1	0.2	0.0	M21
RLB146	98.8	0.4	0.0	M21
RLB195	81.8	0.2	0.0	M21
RLB204	28.4	0.1	0.0	M21
RLB206	6.0	0.1	0.0	M21
RLB212	16.1	0.6	0.0	M21
RLB225	79.4	0.3	0.0	M21
RLB235	24.5	0.1	0.0	M21
RLB236	88.5	0.5	0.0	M21
RLB239	12.7	0.1	0.0	M21
RLB240	8.2	0.1	0.0	M21
TAM057	43.4	0.4	0.0	M21
TAM067	0.2	0.1	0.0	M21
TAM072	98.2	0.2	0.0	M21
TAM233	37.2	0.5	0.0	M21
UT00459	55.5	0.2	0.0	M21
UT00469	92.2	0.6	0.0	M21
UT00477	83.3	0.7	0.0	M21
UT00491	82.6	0.7	0.0	M21
UT00758	84.0	0.5	0.0	M21
	cimens are assigned to		N/24	C
ID. NO.	M21	M23	M24	Group
CAP199	0.0	81.4	0.0	M23
HM093	0.0	59.6	0.0	M23
JHK006	0.0	38.7	0.0	M23
MRM002	0.0	72.7	0.0	M23
MRM009	0.0	4.3	0.0	M23
MRM013	0.0	93.3	0.0	M23
MRM015	0.0	68.3	0.0	M23
MRM016	0.0	47.2	0.0	M23
MRM017	0.0	9.0	0.0	M23
MRM040	0.0	14.7	0.0	M23
MRM045	0.0	36.5	0.0	M23
MRM080	0.0	61.5	0.0	M23

MRM084	0.0	61.4	0.0	M23
MRM091	0.0	61.2	0.0	M23
MRM113	0.0	44.0	0.0	M23
MRM125	0.0	35.3	0.0	M23
MRM135	0.0	9.2	0.0	M23
MRM168	0.0	43.0	0.0	M23
MRM175	0.0	30.4	0.0	M23
MRM179	0.0	63.6	0.0	M23
MRM216	0.0	92.5	0.0	M23
MRM220	0.0	65.8	0.0	M23
MRM228	0.0	63.5	0.0	M23
MRM230	0.0	41.8	0.0	M23
MRM236	0.0	41.8	0.0	M23
MRM237	0.0	18.0	0.0	M23
MRM248	0.0	11.4	0.0	M23
OT503	0.0	95.9	0.0	M23
SWC043	0.0	59.8	0.0	M23
SWC045	0.0	98.6	0.0	M23
3110013	0.0	30.0	0.0	11123
The following speci	imens are assigned to	group M24		
ID. NO.	M21	M22	M24	Group
ANI028	0.0	0.1	11.0	M24
ATT393	0.0	0.3	21.6	M24
ATT409	0.0	0.2	31.1	M24
BAS009	0.0	0.7	89.1	M24
BAS013	0.0	0.2	4.0	M24
BAS018	0.0	1.3	97.5	M24
BAS039	0.0	0.3	20.4	M24
BAS040	0.0	0.5	5.0	M24
BAS045	0.0	2.0	68.9	M24
BAS076	0.0	0.0	99.1	M24
BAS078	0.0	0.1	75.4	M24
BAS079	0.0	0.0	9.9	M24
BAS080	0.0	0.1	39.3	M24
BAS082	0.0	0.0	35.6	M24
BAS083	0.0	0.1	83.9	M24
BAS084	0.0	0.1	34.9	M24
BAS085	0.0	0.3	69.1	M24
BAS086	0.0	0.0	77.4	M24
BAS087	0.0	0.2	84.1	M24
BAS088	0.0	0.0	83.2	M24
BAS089	0.0	0.0	85.4	M24
BAS090	0.0	0.1	45.7	M24
BAS091	0.0	0.1	10.3	M24
BAS091	0.0	0.3	91.5	M24
BAS092 BAS093	0.0	0.3	91.5 97.3	M24
BAS093	0.0	0.3	97.3 24.6	M24
BAS094 BAS095	0.0	0.3	96.1	M24
	0.0	0.2	38.1	M24
BAS096 BAS097	0.0	0.2	50.1	M24
		0.1		
BASO98	0.0 0.0	0.1	37.6	M24 M24
BAS099 BAS100		0.8	82.9 96.9	M24
DHOTOO	0.0	0.4	30.3	IVIZ4

BAS101	0.0	0.9	11.7	M24
BAS103	0.0	0.2	92.5	M24
BAS105	0.0	0.5	2.0	M24
BAS106	0.0	0.8	95.1	M24
BAS108	1.7	0.5	20.6	M24
BAS113	0.0	0.5	64.1	M24
BAS115	0.0	0.3	69.0	M24
BAS151	0.0	0.0	70.1	M24
BAS153	0.0	0.5	97.7	M24
BAS154	0.0	0.0	98.4	M24
BAS155	0.0	0.0	77.8	M24
BAS156	0.0	0.2	84.7	M24
BAS158	0.0	0.0	53.0	M24
BAS159	0.0	0.0	56.0	M24
BAS160	0.0	0.2	6.3	M24
BAS162	0.0	0.0	46.8	M24
BAS165	0.0	3.0	3.9	M24
BAS167	0.0	0.3	44.1	M24
BAS175	0.0	0.3	82.3	M24
BAS176	0.0	0.5	86.2	M24
BAS178	0.0	0.3	47.7	M24
LOA016	0.0	0.4	88.1	M24
LOA044	0.7	1.1	68.7	M24
LOA094	0.1	0.7	7.7	M24
LOA219	0.5	1.3	54.1	M24
MRM151	0.0	2.4	0.3	M24
MRM158	0.0	0.2	97.8	M24
NAM013	1.9	2.5	43.9	M24
OK058	0.0	0.3	5.1	M24
OK061	2.8	0.1	13.5	M24
OU0025	0.0	0.2	87.5	M24
OU0029	0.0	0.1	33.3	M24
OU0033	0.0	0.2	63.5	M24
OU0034	0.0	0.1	36.2	M24
RLB018	0.0	0.1	0.3	M24
RLB037	0.0	0.1	0.3	M24
SWR215	0.1	2.2	68.3	M24
TAM065	0.0	0.0	0.1	M24
TAM069	1.0	0.2	6.5	M24

Table C2. Macro Group C-1 Mahalanobis distance calculations for specimens projected against two or more groups.

Mimbres-22 (M22)

Mimbres-27 (M27)

Mimbres-28 (M28)

Unassigned C1

Variables used:

_, , ,, ,						
The following	specimens	are	assigned	to	group M22	

ID. NO.	M21	M23	M24	Group
BAS118	0.08	0.23	0.00	M22
BRE074	11.42	0.05	0.00	M22
DJT031	0.00	0.08	0.00	M22
ED-096	0.21	0.18	0.00	M22
ED-101	0.00	0.11	0.00	M22
ED-102	0.72	0.26	0.00	M22
LOA070	0.03	0.17	0.00	M22
LOA158	0.00	0.14	0.00	M22
LOA165	0.00	0.13	0.00	M22
LOA169	0.10	0.20	0.00	M22
LOA173	0.00	0.09	0.00	M22
MPP005	0.00	0.10	0.00	M22
MVP0360	0.86	0.21	0.00	M22
MVP0364	0.14	0.14	0.00	M22
MVP0466	0.00	0.15	0.00	M22
OK034	0.31	0.07	0.00	M22
OK071	0.00	0.18	0.00	M22
OK073	0.00	0.11	0.00	M22
OK074	0.00	0.10	0.00	M22
OT225	0.95	0.16	0.00	M22
OT228	0.00	0.08	0.00	M22
OT263	0.02	0.11	0.00	M22
RLB042	0.01	0.07	0.00	M22
RLB059	0.00	0.03	0.00	M22
RLB065	0.46	0.17	0.00	M22
RLB068	0.00	0.07	0.00	M22
RLB071	0.00	0.12	0.00	M22
RLB112	0.13	0.41	0.00	M22
RLB121	0.01	0.05	0.00	M22
RLB124	0.01	0.06	0.00	M22
RLB135	0.00	0.10	0.00	M22
RLB213	0.00	0.08	0.00	M22
RLB243	0.00	0.04	0.00	M22
TAM068	0.09	0.18	0.00	M22
UT00484	0.00	0.10	0.00	M22

The following specir	mens are assigned to	group M27		
ID. NO.	M21	M23	M24	Group
OU0006	0.00	0.04	0.00	M27
OU0011	0.00	0.04	0.00	M27
OU0011	0.00	0.61	0.00	M27
OU0012 OU0014	0.00	0.01	0.00	M27
OU0014 OU0015	0.00	0.01	0.00	M27
OU0013	0.00	0.04	0.00	M27
000023	0.00	0.09	0.00	IVIZ /
The following specir	nens are assigned to	group M28		
ID. NO.	M21	M23	M24	Group
CAP163	0.00	0.85	0.00	M27
CAP165	0.00	0.17	0.00	M27
CAP169	0.00	0.02	0.00	M27
CAP173	0.00	0.08	0.00	M27
The following specir	•			
ID. NO.	M21	M23	M24	Group
BAS007	0.00	0.03	0.00	Unassigned
BAS028	0.48	0.31	0.01	Unassigned
BAS131	0.00	0.05	0.00	Unassigned
BAS143	3.90	4.42	13.12	Unassigned
BAS152	0.00	0.21	0.18	Unassigned
BAS172	0.15	0.57	0.00	Unassigned
BAS180	0.00	0.07	0.10	Unassigned
BAS185	0.00	0.90	0.00	Unassigned
BAS206	0.00	3.65	2.77	Unassigned
BRE057	0.00	1.16	0.00	Unassigned
ED-073	0.00	0.01	0.00	Unassigned
ED-078	0.00	0.28	0.00	Unassigned
JAM020	0.00	1.59	0.00	Unassigned
LOA086	0.00	0.53	0.01	Unassigned
LOA089	0.00	0.06	0.00	Unassigned
MPC024	0.00	2.36	0.00	Unassigned
MPM1C	0.01	0.20	0.00	Unassigned
MPT011	0.00	0.48	0.00	Unassigned
MPT016	0.00	0.32	0.00	Unassigned
MRM012	0.00	1.88	0.00	Unassigned
MRM020	0.00	0.15	0.00	Unassigned
MRM021	0.00	0.12	0.00	Unassigned
MVP0132	0.00	0.12	0.00	Unassigned
MVP0328 MVP0329	0.00 0.00	0.08 0.45	0.00 0.00	Unassigned
MVP0370	0.00	0.45	0.00	Unassigned
	0.00	0.29	0.00	Unassigned
OK035	0.00	0.29	0.00	Unassigned
OK037 OK045	0.00	0.01	0.00	Unassigned Unassigned
OK050	0.00	0.07	0.00	Unassigned
OK060	0.00	0.14	0.00	Unassigned
OK072	0.02	0.13	0.00	Unassigned
OT258	0.00	0.10	0.00	Unassigned
OT584	0.00	0.10	0.00	Unassigned
OT587	0.00	0.04	0.00	Unassigned
01307	0.00	0.04	0.00	Oliassiglieu

OT590	0.00	0.01	0.00	Unassigned
RLB020	0.00	0.29	0.00	Unassigned
RLB022	0.00	0.68	0.00	Unassigned
RLB023	0.00	0.06	0.06	Unassigned
RLB024	0.00	0.12	0.00	Unassigned
RLB025	0.00	0.35	0.00	Unassigned
RLB026	0.00	1.21	0.00	Unassigned
RLB055	0.00	4.95	0.00	Unassigned
RLB056	0.00	0.06	0.00	Unassigned
RLB057	0.07	0.20	0.00	Unassigned
RLB069	0.00	0.75	0.00	Unassigned
RLB143	0.00	0.20	0.00	Unassigned
RLB157	0.08	2.30	0.10	Unassigned
RLB194	0.00	1.00	0.00	Unassigned
SWR014	0.00	5.22	0.00	Unassigned
SWR092	0.00	1.46	0.00	Unassigned
TAM206	0.00	0.05	0.00	Unassigned
TAM207	0.00	2.74	0.00	Unassigned
UT00762	0.00	0.41	0.00	Unassigned

Table C3. Macro Group C-2 Mahalanobis distance calculations for specimens projected against two or more groups.

Mimbres-41 (M41)

Mimbres-49A (M49A)

Variables used:

The following specimens are as	ssigned to group M41.		
ID. NO.	M41	M49A	Group
ATT385	9.93	0.14	M41
ATT399	25.31	2.14	M41
ATT425	2.32	0.00	M41
BAS179	70.19	5.66	M41
BAS210	86.72	0.25	M41
BRE045	0.00	0.00	M41
ED-089	48.36	0.00	M41
ED-090	29.52	0.03	M41
JAM037	5.13	0.37	M41
JAM084	65.82	2.28	M41
JAM102	62.20	0.10	M41
JAM110	2.81	0.00	M41
MRM067	99.60	11.77	M41
MRM069	66.02	2.44	M41
MRM070	99.14	4.00	M41
MRM071	97.98	5.86	M41
MRM073	98.37	6.41	M41
MRM107	68.96	1.69	M41
MRM111	22.94	1.18	M41
MRM201	58.17	0.06	M41
MRM205	99.58	0.22	M41
MRM206	97.47	0.04	M41
MVP0085	89.31	0.33	M41
MVP0087	59.40	0.92	M41
MVP0253	38.44	0.00	M41
OK005	8.95	1.98	M41
OK007	16.72	0.25	M41
OK111	11.41	2.77	M41
OT180	61.72	9.30	M41
OT182	17.40	0.57	M41
OT186	8.34	0.15	M41
OT203	42.54	0.00	M41
OT215	45.59	0.31	M41
OT217	50.14	0.01	M41
OT218	43.13	0.02	M41
OT226	36.97	0.05	M41
OT254	99.55	12.80	M41

OT265	20.60	1.67	M41
OT273	63.62	0.01	M41
RLB014	10.73	1.03	M41
RLB159	0.43	0.02	M41
The following specimens are	assigned to group M49A.		
ID. NO.	M41	M49A	Group
ANI025	0.00	92.36	M49A
ANI027	0.00	90.58	M49A
ATT414	0.01	95.75	M49A
ATT423	0.00	99.54	M49A
ATT457	0.00	84.89	M49A
ATT479	0.00	96.68	M49A
BAS033	0.00	95.06	M49A
BAS062	0.00	99.10	M49A
BAS111	0.00	20.65	M49A
BAS121	0.00	88.53	M49A
BAS138	0.00	99.41	M49A
BAS144	0.00	7.51	M49A
BAS150	0.00	95.91	M49A
BAS169	0.00	1.06	M49A
BAS190	0.01	35.53	M49A
BAS194	0.00	52.59	M49A
BRE117	0.00	67.64	M49A
BRE123	0.00	47.04	M49A
BRE131	0.00	3.94	M49A
CAP157	0.00	99.56	M49A
CAP158	0.00	15.28	M49A
CAP160	0.02	99.03	M49A
CAP161	0.00	95.06	M49A
CAP167	0.00	95.90	M49A
EP112	0.00	93.59	M49A
HM043	0.00	30.49	M49A
HM046	0.00	18.68	M49A
HM057	0.01	0.49	M49A
HM062	0.00	50.85	M49A
HM065	0.01	68.86	M49A
HM066	0.04	76.44	M49A
HM067	0.00	69.28	M49A
HM068	0.00	83.90	M49A
HM081	0.00	63.44	M49A
HM088	0.00	72.07	M49A
JAM023	0.00	38.92	M49A
JAM026	0.00	25.79 72.22	M49A
JAM027	0.00	73.23	M49A
JAM070	0.00	6.23	M49A
JAM086	0.00	3.09	M49A
JAM088	0.00	99.52	M49A
JAM091	0.00	29.27	M49A
JAM105	0.00	58.95	M49A

JAM108	0.00	11.25	M49A
JAM120	0.02	14.39	M49A
JAM130	0.00	0.32	M49A
JAM132	0.00	0.49	M49A
LOA087	0.00	0.52	M49A
MPC002	0.00	23.68	M49A
MRM034	0.00	82.76	M49A
MRM072	0.00	27.35	M49A
MRM109	0.00	91.77	M49A
MRM127	0.00	36.46	M49A
MRM177	0.00	29.28	M49A
MRM183	0.00	37.16	M49A
MRM185	0.00	82.02	M49A
MRM188	0.13	99.16	M49A
MRM192	0.00	93.88	M49A
MRM197	0.00	14.78	M49A
MRM198	0.00	78.12	M49A
MRM219	0.00	51.30	M49A
MST002	0.00	94.96	M49A
MST006	0.13	99.54	M49A
MST009	0.10	86.97	M49A
MST021	0.00	98.48	M49A
MST035	0.00	98.93	M49A
MST036	0.00	15.91	M49A
MST040	0.03	96.43	M49A
MST042	0.00	90.64	M49A
MST052	0.03	89.79	M49A
MST061	0.00	60.59	M49A
MST088	0.00	23.91	M49A
MST100	0.00	97.65	M49A
MVP0025	0.00	90.00	M49A
MVP0048	0.00	81.97	M49A
MVP0065	0.00	4.54	M49A
MVP0069	0.00	95.39	M49A
MVP0083	0.00	83.30	M49A
MVP0090	0.00	91.41	M49A
MVP0092	0.03	66.84	M49A
MVP0158	0.00	38.60	M49A
MVP0184	0.01	86.30	M49A
MVP0201	0.00	4.50	M49A
MVP0223	0.00	24.56	M49A
MVP0236	0.04	96.65	M49A
MVP0298	0.01	95.65	M49A
MVP0305	0.01	89.45	M49A
MVP0306	0.02	93.03	M49A
MVP0307	0.00	1.20	M49A
MVP0359	0.00	14.53	M49A
MVP0373	0.00	51.18	M49A
MVP0376	0.00	35.35	M49A
MVP0382	0.00	0.00	M49A

MVP0394	0.08	2.38	M49A
MVP0403	0.00	22.96	M49A
MVP0410	0.00	3.77	M49A
MVP0418	0.00	10.88	M49A
MVP0419	0.00	30.62	M49A
MVP0420	0.00	85.78	M49A
MVP0431	0.02	45.74	M49A
MVP0432	0.00	96.60	M49A
MVP0438	0.00	83.52	M49A
MVP0446	0.00	91.90	M49A
MVP0463	0.00	14.89	M49A
OK004	0.01	27.81	M49A
OK059	0.00	22.67	M49A
OK087	0.15	99.03	M49A
OK112	0.08	10.29	M49A
OK124	0.00	39.37	M49A
OK148	0.00	32.99	M49A
OT068	0.10	23.60	M49A
OT126	0.01	7.60	M49A
OT193	0.01	16.90	M49A
OT194	0.00	4.79	M49A
OT210	0.00	96.40	M49A
OT211	0.01	87.52	M49A
OT219	0.00	1.64	M49A
OT220	0.04	95.63	M49A
OT223	0.02	73.77	M49A
OT229	0.00	0.00	M49A
OT241	0.00	49.75	M49A
OT244	0.00	2.08	M49A
OT246	0.01	38.27	M49A
OT248	0.00	88.99	M49A
OT256	0.01	31.24	M49A
OT266	0.07	80.17	M49A
OT538	0.00	88.51	M49A
OT543	0.00	81.95	M49A
RLB005	0.00	28.06	M49A
RLB150	0.00	8.17	M49A
RLB152	0.00	76.71	M49A
RLB267	0.00	64.37	M49A
SWR084	0.00	0.61	M49A
SWR149	0.01	80.00	M49A
SWR219	0.00	81.95	M49A
TAM219	0.00	40.06	M49A
UT00458	0.09	96.65	M49A
UT00779	0.00	86.41	M49A
WCRM001	0.00	80.18	M49A
WCRM002	0.00	90.18	M49A
WCRM005	0.00	37.34	M49A
WCRM006	0.00	80.60	M49A
WCRM008	0.00	73.78	M49A
	0.00	, 5., 6	IVITOR

Table C4. Macro Group C-2 Mahalanobis distance calculations for specimens projected against two or more groups.

Mimbres-42 (M42)

Mimbres-43 (M43)

Mimbres-44 (M44)

Mimbres-46 (M46)

Mimbres-47 (M47)

Mimbres-48 (M48)

Mimbres-49B (M49B)

Unassigned C-2

Variables used:

The following specimens are assigned to	group M42.		
ID. NO.	M41	M49A	Group
BRE054	0.00	4.81	M42
HM024	0.00	4.60	M42
HM064	0.00	0.34	M42
JAM093	0.00	0.03	M42
JAM107	0.00	3.66	M42
JAM111	0.00	5.01	M42
MRM232	0.00	0.07	M42
MVP0003	0.00	0.98	M42
MVP0118	0.00	6.67	M42
MVP0228	0.00	0.90	M42
OK092	0.00	0.03	M42
OT494	0.00	2.80	M42
RLB196	0.00	0.02	M42
RLB222	0.00	17.50	M42
SWC047	0.00	1.39	M42
SWR087	0.00	1.90	M42
SWR113	0.00	0.20	M42
SWR170	0.00	35.08	M42
The following specimens are assigned to	o group M43.		
ID. NO.	M41	M49A	Group
RLB100	0.00	0.00	M43
RLB191	0.00	0.00	M43
RLB192	0.01	0.00	M43
RLB193	0.00	0.00	M43
The following specimens are assigned to	•		_
ID. NO.	M41	M49A	Group
ATT428	0.00	0.00	M44
BAS116	0.02	0.00	M44
MRM152	0.00	0.00	M44
RLB098	0.00	0.00	M44
RLB102	0.00	0.00	M44
RLB109	0.00	0.00	M44

RLB166	0.00	0.00	M44
RLB244	0.00	0.00	M44
TAM252	0.00	0.00	M44
The following specimens are assigned to			_
ID. NO.	M41	M49A	Group
BAS025	0.00	0.03	M46
BAS161	0.00	0.14	M46
BAS177	0.00	0.01	M46
OU0026	0.00	0.00	M46
The following specimens are assigned to	group M47.		
ID. NO.	M41	M49A	Group
ATT379	0.00	0.00	M47
ATT392	0.00	0.00	M47
ATT396	0.01	0.00	M47
ATT401	0.00	0.01	M47
ATT412	0.03	0.00	M47
ATT417	0.00	0.00	M47
ATT418	0.01	0.00	M47
ATT441	0.03	0.00	M47
ATT451	0.03	0.00	M47
BAS104	0.00	1.04	M47
BRE032A	0.00	0.00	M47
BRE033	0.00	0.00	M47
			M47
BRE034	0.00	0.00	M47
BRE035	0.00	0.00	
BRE067	0.00	0.00	M47
BRE068	0.00	0.00	M47
BRE163	0.00	0.00	M47
BRE165	0.00	0.00	M47
CAP156	0.61	0.03	M47
JAM025	0.00	0.00	M47
JAM033	0.03	0.02	M47
JAM034	0.00	0.00	M47
JAM036	0.02	0.14	M47
JAM046	0.00	0.00	M47
JAM136	0.00	0.00	M47
MVP0108	0.03	0.00	M47
MVP0166	0.00	0.00	M47
MVP0231	0.04	0.00	M47
MVP0252	0.00	0.00	M47
RLB089	0.09	0.00	M47
The following specimens are assigned to			_
ID. NO.	M41	M49A	Group
ATT354	0.00	0.00	M48
ATT357	0.00	0.00	M48
ATT463	0.00	0.00	M48
ATT467	0.00	0.00	M48
ATT471	0.00	0.00	M48
ATT489	0.00	0.00	M48
ATT495	0.00	0.00	M48

The following specimens are assigned to group M49B.

ID. NO.	M41	M49A	Group
JAM055	0.00	25.90	M49B
LOA037	0.00	33.10	M49B
MRM066	0.00	49.11	M49B
MRM134	0.00	15.66	M49B
SWR114	0.00	0.00	M49B

The following specimens are assigned.	The following energiment are assign	and		
ANIO12			N440A	Group
ATT044 0.00 0.00 Unassigned ATT295 0.00 0.00 Unassigned ATT358 0.00 0.00 Unassigned ATT381 0.00 0.00 Unassigned ATT381 0.00 0.00 Unassigned ATT381 0.00 0.00 Unassigned ATT407 0.00 0.00 Unassigned ATT407 0.00 0.00 Unassigned ATT415 0.00 0.00 Unassigned ATT424 0.00 0.00 Unassigned ATT424 0.00 0.00 Unassigned ATT425 0.07 0.00 Unassigned ATT429 0.02 0.00 Unassigned ATT429 0.00 0.01 Unassigned ATT449 0.00 0.01 Unassigned ATT449 0.00 0.01 Unassigned ATT452 0.00 0.00 Unassigned ATT460 0.00 0.00 Unassigned ATT475 0.00 0.00 Unassigned ATT475 0.00 0.00 Unassigned ATT488 0.00 0.00 Unassigned ATT488 0.00 0.00 Unassigned BAS017 0.00 0.00 Unassigned BAS017 0.00 0.00 Unassigned BAS022 0.00 0.00 Unassigned BAS022 0.00 0.00 Unassigned BAS032 0.14 0.00 0.00 Unassigned BAS032 0.14 0.00 0.00 Unassigned BAS032 0.14 0.00 0.00 Unassigned BAS187 0.13 4.42 Unassigned BAS195 0.07 0.00 Unassigned BAS195 0.07 0.00 Unassigned BAS195 0.07 0.00 Unassigned BAS195 0.07 0.00 Unassigned BAS195 0.00 0.00 Unassigned BAS195 0.00 0.00 Unassigned BAS195 0.00 0.00 Unassigned BRE055 0.00 0.00 Unassigned DIT009 0.03 0.80 Unassigned BRE103 0.00 0.00 Unassigned DIT009 0.03 0.80 Unassigned DIT009 0.03 0.80 Unassigned DIT009 0.03 0.80 Unassigned DIT009 0.03 0.00 Unassigned DIT009 0.03 0.00 Unassigned DIT009 0.03 0.00 Unassigned DIT009 0.03 0.00 Unassigned DIT009 0.00 0.0				-
ATT295 ATT358 O.00 ATT358 O.00 O.00 Unassigned ATT407 O.00 O.00 Unassigned ATT407 O.00 O.00 Unassigned ATT415 O.00 O.00 Unassigned ATT415 O.00 O.00 Unassigned ATT426 ATT426 O.07 O.00 ATT429 O.02 O.00 Unassigned ATT429 O.00 ATT449 O.00 O.01 Unassigned ATT452 O.00 ATT452 O.00 O.00 Unassigned ATT452 O.00 O.00 Unassigned ATT452 O.00 O.00 Unassigned ATT452 O.00 O.00 Unassigned ATT460 O.00 O.00 Unassigned ATT480 O.00 O.00 Unassigned ATT480 O.00 O.00 Unassigned ATT480 O.00 O.00 Unassigned BAS017 O.00 O.00 Unassigned BAS017 O.00 O.00 Unassigned BAS022 O.00 O.00 Unassigned BAS032 O.14 O.00 Unassigned BAS187 O.13 A42 Unassigned BAS187 O.13 A42 Unassigned BAS187 O.00 O.00 Unassigned BAS195 O.07 O.00 Unassigned BAS202 O.00 O.00 Unassigned BAS202 O.00 O.00 Unassigned BAS195 O.07 O.00 Unassigned BAS195 O.07 O.00 Unassigned BAS196 BAS202 O.00 O.00 Unassigned BAS197 O.00 O.00 Unassigned BAS198 BAS199 O.00 O.00 Unassigned BAS199 BAS187 O.00 O.00 Unassigned BAS199 D.00 O.00 Unassigned DIT009 O.00 Unassigned DIT019 O.00 O.00 Unassigned DAM117 O.00 O.0				_
ATT381 0.00 0.00 Unassigned ATT381 0.00 0.00 Unassigned ATT381 0.00 0.00 Unassigned ATT407 0.00 0.00 Unassigned ATT415 0.00 0.00 Unassigned ATT415 0.00 0.00 Unassigned ATT424 0.00 0.00 Unassigned ATT426 0.07 0.00 Unassigned ATT429 0.02 0.00 Unassigned ATT429 0.00 0.01 Unassigned ATT429 0.00 0.01 Unassigned ATT449 0.00 0.00 Unassigned ATT452 0.00 0.00 Unassigned ATT452 0.00 0.00 Unassigned ATT452 0.00 0.00 Unassigned ATT475 0.00 0.00 Unassigned ATT475 0.00 0.00 Unassigned ATT480 0.00 0.00 Unassigned ATT480 0.00 0.00 Unassigned BAS017 0.00 0.00 Unassigned BAS017 0.00 0.00 Unassigned BAS022 0.00 0.00 Unassigned BAS032 0.14 0.00 Unassigned BAS032 0.14 0.00 Unassigned BAS187 0.13 4.42 Unassigned BAS187 0.13 4.42 Unassigned BAS195 0.07 0.00 Unassigned BAS202 0.00 0.00 Unassigned BAS202 0.00 0.00 Unassigned BAS202 0.00 0.00 Unassigned BAS202 0.00 0.00 Unassigned BRE103 0.00 0.00 Unassigned DIT009 0.03 0.80 Unassigned DIT009 0.00 0.00 Unassigned DI				_
ATT381				_
ATT407 ATT415 O.00 ATT415 O.00 ATT424 O.00 ATT424 O.00 ATT426 ATT429 O.02 O.00 Unassigned ATT429 O.02 O.00 ATT429 O.00 ATT449 O.00 ATT455 O.00 ATT455 O.00 ATT460 ATT460 O.00 ATT460 O.00 ATT460 O.00 ATT460 O.00 ATT460 O.00 ATT480 ATT480 O.00 ATT480 ATT4819 ATT480 ATT480 ATT480 ATT480 ATT480 ATT480 ATT480 ATT480 ATT481 ATT480 ATT480 ATT480 ATT480 ATT480 ATT481 ATT480 ATT480 ATT480 ATT480 ATT481 ATT480 ATT480 ATT480 ATT481 ATT480 ATT481 ATT480 ATT481 ATT480 ATT481 ATT480 ATT481 ATT480 ATT481 ATT480 ATT480 ATT48180 ATT48181 ATT481				_
ATT415				_
ATT424 0.00 0.00 Unassigned ATT426 0.07 0.00 Unassigned ATT429 0.02 0.00 Unassigned ATT449 0.00 0.00 0.01 Unassigned ATT449 0.00 0.00 0.00 Unassigned ATT452 0.00 0.00 0.00 Unassigned ATT452 0.00 0.00 0.00 Unassigned ATT460 0.00 0.00 0.00 Unassigned ATT475 0.00 0.00 0.00 Unassigned ATT480 0.00 0.00 0.00 Unassigned ATT480 0.00 0.00 0.00 Unassigned BAS017 0.00 0.00 0.00 Unassigned BAS017 0.00 0.00 Unassigned BAS022 0.00 0.00 0.00 Unassigned BAS032 0.14 0.00 Unassigned BAS187 0.13 4.42 Unassigned BAS187 0.13 4.42 Unassigned BAS195 0.07 0.00 Unassigned BRE055 0.00 0.00 Unassigned BRE055 0.00 0.00 Unassigned BRE055 0.00 0.00 Unassigned BRE056 0.00 0.00 Unassigned BRE071 0.00 0.00 Unassigned DIT009 0.03 0.80 Unassigned DIT009 0.03 0.80 Unassigned DIT009 0.03 0.80 Unassigned HM036 0.05 0.00 Unassigned HM037 0.00 0.00 Unassigned HM037 0.00 0.01 Unassigned JAM031 0.00 0.00 Unassigned JAM031 0.00 0.00 Unassigned JAM031 0.00 0.00 Unassigned LOA036 0.00 0.00 Unassigned LOA036 0.00 0.00 Unassigned JAM117 0.00 0.00 Unassigned JAM117 0.00 0.00 Unassigned JAM117 0.00 0.00 Unassigned JAM117 0.00 0.00 Unassigned JAM128 0.00 0.00 Unassigned LOA036 0.00 0.00 Unassigned LOA036 0.00 0.00 Unassigned LOA031 0.00 0.00 Unassigned LOA032 0.00 0.00 Unassigned LOA033 0.00 0.00 Unassigned LOA034 0.00 0.00 Unassigned LOA035 0.00 0.00 Unassigned LOA036 0.00 0.00 Unassigned LOA031 0.00 0.00 Unassigned LOA032 0.00 0.00 Unassigned LOA033 0.00 0.00 Unassigned LOA034 0.00 0.00 Unassigned LOA035 0.00 0.00 Unassigned LOA036 0.00 0.00 Unassigned LOA036 0.00 0.00 Unassigned LOA036 0.00 0.00 Unassigned LOA039 0.00				_
ATT426 0.07 0.00 Unassigned ATT429 0.02 0.00 Unassigned ATT449 0.00 0.01 Unassigned ATT449 0.00 0.01 Unassigned ATT452 0.00 0.00 0.00 Unassigned ATT460 0.00 0.00 0.00 Unassigned ATT460 0.00 0.00 0.00 Unassigned ATT475 0.00 0.00 0.00 Unassigned ATT480 0.00 0.00 0.00 Unassigned ATT480 0.00 0.00 Unassigned BAS017 0.00 0.00 Unassigned BAS022 0.00 0.00 Unassigned BAS022 0.00 0.00 Unassigned BAS032 0.14 0.00 Unassigned BAS187 0.13 4.42 Unassigned BAS187 0.13 4.42 Unassigned BAS195 0.07 0.00 Unassigned BAS202 0.00 0.00 Unassigned BRE055 0.00 0.00 Unassigned BRE055 0.00 0.00 Unassigned BRE055 0.00 0.00 Unassigned BRE055 0.00 0.00 Unassigned BRE030 0.00 0.00 Unassigned BRE030 0.00 0.00 Unassigned BRE030 0.00 0.00 Unassigned BRE030 0.00 0.00 Unassigned DIT009 0.03 0.80 Unassigned DIT009 0.03 0.80 Unassigned DIT009 0.03 0.80 Unassigned HM036 0.05 0.00 Unassigned HM036 0.05 0.00 Unassigned JAM031 0.00 0.00 Unassigned JAM031				_
ATT429 0.02 0.00 Unassigned ATT4449 0.00 0.01 Unassigned ATT452 0.00 0.00 0.00 Unassigned ATT455 0.00 0.00 0.00 Unassigned ATT475 0.00 0.00 0.00 Unassigned ATT475 0.00 0.00 0.00 Unassigned ATT480 0.00 0.00 0.00 Unassigned ATT480 0.00 0.00 0.00 Unassigned BAS017 0.00 0.00 Unassigned BAS017 0.00 0.00 Unassigned BAS032 0.14 0.00 Unassigned BAS187 0.13 4.42 Unassigned BAS187 0.13 4.42 Unassigned BAS189 0.07 0.00 Unassigned BAS202 0.00 0.00 Unassigned BAS202 0.00 0.00 Unassigned BRE055 0.00 0.00 Unassigned BRE055 0.00 0.00 Unassigned Unassigned BRE103 0.00 0.00 Unassigned CAP170 0.00 0.00 Unassigned Unassigned University 0.00 0.00 Universit				_
ATT449 0.00 0.01 Unassigned ATT452 0.00 0.00 Unassigned ATT460 0.00 0.00 Unassigned ATT475 0.00 0.00 0.00 Unassigned ATT475 0.00 0.00 0.00 Unassigned ATT480 0.00 0.00 0.00 Unassigned BAS017 0.00 0.00 0.00 Unassigned BAS017 0.00 0.00 Unassigned BAS022 0.00 0.00 Unassigned BAS032 0.14 0.00 Unassigned BAS032 0.14 0.00 Unassigned BAS187 0.13 4.42 Unassigned BAS187 0.07 0.00 Unassigned BAS195 0.07 0.00 Unassigned BAS202 0.00 0.00 Unassigned BRE055 0.00 0.00 Unassigned BRE103 0.00 0.00 Unassigned BRE103 0.00 0.00 Unassigned Unassigned BRE103 0.00 0.00 Unassigned Unassigne				_
ATT452 0.00 0.00 Unassigned ATT460 0.00 0.00 Unassigned ATT475 0.00 0.00 Unassigned ATT475 0.00 0.00 Unassigned ATT480 0.00 0.00 Unassigned BAS017 0.00 0.00 Unassigned BAS022 0.00 0.00 Unassigned BAS022 0.00 0.00 Unassigned BAS032 0.14 0.00 Unassigned BAS032 0.14 0.00 Unassigned BAS187 0.13 4.42 Unassigned BAS195 0.07 0.00 Unassigned BAS202 0.00 0.00 Unassigned BAS202 0.00 0.00 Unassigned BRE055 0.00 0.00 Unassigned BRE103 0.00 0.00 Unassigned ED-091 0.00 0.00 Unassigned ED-091 0.00 0.00 Unassigned IM036 0.05 0.00 Unassigned IM036 0.05 0.00 Unassigned IM036 0.05 0.00 Unassigned IM036 0.05 0.00 Unassigned JAM117 0.00 0.01 Unassigned JAM121 0.00 0.00 Unassigned JAM121 0.00 0.00 Unassigned JAM121 0.00 0.00 Unassigned JAM128 0.00 0.00 Unassigned IDAM128 0.00 0.00 Unassigned LOA036 0.00 0.00 Unassigned LOA081 0.00 0.00 Unassigned LOA081 0.00 0.00 Unassigned LOA082 0.00 0.00 Unassigned LOA081 0.00 0.00 Unassigned MPM019 0.00 0.16 Unassigned MRM103 0.00 0.01 Unassigned MRM103 0.00 0.01 Unassigned MRM103 0.00 0.00 Unassigned MRM104 0.00 0.14 Unassigned MRM103 0.00 0.00 Unassigned MRM104 0.00 0.00 Unassigned MRM176 0.00 0.00 Unassigned MRM176 0.00 0.00 Unassigned MRM176 0.00 0.00 Unassigned MVP0082 64.48 2.47 Unassigned MVP0084 0.41 0.88 Unassigned MVP0085 0.00 0.00 Unassigned MVP0084 0.41 0.88 Unassigned MVP0085 0.00 0.00 Unassigned MVP0165				_
ATT460 0.00 0.00 Unassigned ATT475 0.00 0.00 Unassigned ATT480 0.00 0.00 Unassigned ATT480 0.00 0.00 Unassigned BAS017 0.00 0.00 Unassigned BAS022 0.00 0.00 Unassigned BAS032 0.14 0.00 Unassigned BAS187 0.13 4.42 Unassigned BAS187 0.13 4.42 Unassigned BAS195 0.07 0.00 Unassigned BAS202 0.00 0.00 Unassigned BRE055 0.00 0.00 Unassigned BRE103 0.00 0.00 Unassigned BRE103 0.00 0.00 Unassigned CAP170 0.00 Unassigned CAP171 0.00 0.00 Unassigned CAP171 0.00 0.00 Unassigned ED-091 0.00 0.00 Unassigned HM036 0.05 0.00 0.00 Unassigned HM037 0.00 0.01 Unassigned HM037 0.00 0.01 Unassigned JAM031 0.00 0.00 Unassigned JAM031 0.00 0.00 Unassigned JAM117 0.00 0.00 Unassigned JAM121 0.00 0.00 Unassigned JAM121 0.00 0.00 Unassigned JAM121 0.00 0.00 Unassigned JAM128 0.00 0.00 Unassigned LOA036 0.00 0.00 Unassigned LOA031 0.00 0.00 Unassigned LOA032 0.00 0.01 Unassigned LOA033 0.00 0.01 Unassigned LOA034 0.00 0.01 Unassigned MRM103 0.00 0.01 Unassigned MRM172 0.00 0.00 Unassigned MRM174 0.00 0.00 Unassigned MRM175 0.00 0.00 Unassigned MRM176 0.00 0.00 Unassigned MRM176 0.00 0.00 Unassigned MRM176 0.00 0.00 Unassigned MRM212 0.01 0.07 Unassigned MVP0082 64.48 2.47 Unassigned MVP0084 0.41 0.88 Unassigned MVP0085 0.41 0.88 Unassigned MVP0165 0.00 0.00 Unassigned MVP0165	ATT449	0.00		Unassigned
ATT475 0.00 0.00 Unassigned ATT480 0.00 0.00 Unassigned BAS017 0.00 0.00 Unassigned BAS017 0.00 0.00 Unassigned BAS022 0.00 0.00 Unassigned BAS032 0.14 0.00 Unassigned BAS187 0.13 4.42 Unassigned BAS195 0.07 0.00 Unassigned BAS202 0.00 0.00 Unassigned BAS202 0.00 0.00 Unassigned BRE055 0.00 0.00 Unassigned BRE055 0.00 0.00 Unassigned BRE103 0.00 0.00 Unassigned CAP170 0.00 0.00 Unassigned DIT009 0.03 0.80 Unassigned DIT009 0.03 0.80 Unassigned DIT009 0.03 0.80 Unassigned HM036 0.05 0.00 Unassigned HM036 0.05 0.00 Unassigned JAM031 0.00 0.00 Unassigned JAM031 0.00 0.00 Unassigned JAM031 0.00 0.00 Unassigned JAM031 0.00 0.00 Unassigned JAM117 0.00 0.00 Unassigned JAM128 0.00 0.00 Unassigned JAM128 0.00 0.00 Unassigned JAM128 0.00 0.00 Unassigned JAM128 0.00 0.00 Unassigned LOA036 0.00 0.00 Unassigned LOA036 0.00 0.00 Unassigned LOA036 0.00 0.00 Unassigned LOA036 0.00 0.00 Unassigned MPM019 0.00 0.01 Unassigned LOA081 0.00 0.01 Unassigned LOA082 0.00 0.16 Unassigned MPM019 0.00 0.01 Unassigned MRM103 0.00 0.11 Unassigned MRM104 0.00 0.11 Unassigned MRM104 0.00 0.01 Unassigned MRM105 0.00 0.01 Unassigned MRM106 0.00 0.01 Unassigned MRM107 0.00 0.00 Unassigned MRM107 0.00 0.00 Unassigned MRM108 0.00 0.01 Unassigned MRM109 0.00 0.00 Unassigned MRM164 0.00 0.00 Unassigned MRM166 0.00 0.00 Unassigned MRM212 0.01 0.00 0.00 Unassigned MVP0088 0.41 0.88 Unassigned MVP0088 0.41 0.88 Unassigned MVP0165 0.00 0.00 Unassigned MVP0165	ATT452	0.00	0.00	Unassigned
ATT480 0.00 0.00 Unassigned BAS017 0.00 0.00 Unassigned BAS022 0.00 0.00 Unassigned BAS032 0.14 0.00 Unassigned BAS187 0.13 4.42 Unassigned BAS195 0.07 0.00 Unassigned BAS202 0.00 0.00 Unassigned BAS202 0.00 0.00 Unassigned BRE055 0.00 0.00 Unassigned BRE103 0.00 0.00 Unassigned BRE103 0.00 0.00 Unassigned Unassigned CAP170 0.00 0.00 Unassigned Unass	ATT460	0.00	0.00	Unassigned
BAS017 0.00 0.00 Unassigned BAS022 0.00 0.00 Unassigned BAS032 0.14 0.00 Unassigned BAS187 0.13 4.42 Unassigned BAS195 0.07 0.00 Unassigned BRS202 0.00 0.00 Unassigned BRE103 0.00 0.00 Unassigned CAP170 0.00 0.00 Unassigned CAP171 0.00 0.00 Unassigned DIT009 0.03 0.80 Unassigned HM036 0.00 0.00 Unassigned HM037 0.00 0.01 Unassigned JAM031 0.00 0.00 Unassigned JAM177 0.00 0.00 Unassigned JAM121 0.00 0.00 Unassigned LOA036 0.00 0.00 Unassigned LOA036 0.00 0.00 Unassigned LOA081 0.01 16.41 U	ATT475	0.00	0.00	Unassigned
BAS022 0.00 0.00 Unassigned BAS032 0.14 0.00 Unassigned BAS187 0.13 4.42 Unassigned BAS195 0.07 0.00 Unassigned BRE055 0.00 0.00 Unassigned BRE103 0.00 0.00 Unassigned CAP170 0.00 1.52 Unassigned CAP171 0.00 0.00 Unassigned DIT009 0.03 0.80 Unassigned DIT009 0.03 0.80 Unassigned HM036 0.05 0.00 Unassigned HM037 0.00 0.01 Unassigned JAM031 0.00 0.01 Unassigned JAM121 0.00 0.00 Unassigned JAM128 0.00 0.08 Unassigned LOA036 0.00 0.00 Unassigned LOA082 0.00 0.16 Unassigned LOA159 0.01 6.41 Un	ATT480	0.00	0.00	Unassigned
BAS032 0.14 0.00 Unassigned BAS187 0.13 4.42 Unassigned BAS195 0.07 0.00 Unassigned BAS202 0.00 0.00 Unassigned BRE055 0.00 0.00 Unassigned CAP170 0.00 0.00 Unassigned CAP171 0.00 0.00 Unassigned DJT009 0.03 0.80 Unassigned BH036 0.05 0.00 Unassigned HM036 0.05 0.00 Unassigned HM037 0.00 0.01 Unassigned JAM031 0.00 0.00 Unassigned JAM117 0.00 0.00 Unassigned JAM128 0.00 0.00 Unassigned LOA036 0.00 0.00 Unassigned LOA081 0.00 0.00 Unassigned LOA082 0.00 0.01 Unassigned LOA159 0.01 6.41 Una	BAS017	0.00	0.00	Unassigned
BAS187 0.13 4.42 Unassigned BAS195 0.07 0.00 Unassigned BRS202 0.00 0.00 Unassigned BRE055 0.00 0.00 Unassigned BRE103 0.00 0.00 Unassigned CAP170 0.00 0.00 Unassigned CAP171 0.00 0.00 Unassigned DIT009 0.03 0.80 Unassigned BM036 0.05 0.00 Unassigned HM037 0.00 0.01 Unassigned JAM031 0.00 0.00 Unassigned JAM171 0.00 0.00 Unassigned JAM121 0.00 0.00 Unassigned LOA036 0.00 0.00 Unassigned LOA081 0.00 0.00 Unassigned LOA082 0.00 0.16 Unassigned LOA082 0.00 0.01 Unassigned MPM019 0.00 0.01 Un	BAS022	0.00	0.00	Unassigned
BAS195 0.07 0.00 Unassigned BAS202 0.00 0.00 Unassigned BRE055 0.00 0.00 Unassigned BRE103 0.00 0.00 Unassigned CAP170 0.00 0.00 Unassigned CAP171 0.00 0.00 Unassigned DJT009 0.03 0.80 Unassigned ED-091 0.00 0.00 Unassigned HM036 0.05 0.00 Unassigned HM037 0.00 0.01 Unassigned JAM031 0.00 0.00 Unassigned JAM177 0.00 0.00 Unassigned JAM121 0.00 0.00 Unassigned LOA036 0.00 0.00 Unassigned LOA036 0.00 0.00 Unassigned LOA082 0.00 0.16 Unassigned LOA131 0.01 6.41 Unassigned MRM103 0.00 0.01 Un	BAS032	0.14	0.00	Unassigned
BAS202 0.00 0.00 Unassigned BRE103 0.00 0.00 Unassigned CAP170 0.00 1.52 Unassigned CAP171 0.00 0.00 Unassigned DJT009 0.03 0.80 Unassigned ED-091 0.00 0.00 Unassigned HM036 0.05 0.00 Unassigned HM037 0.00 0.01 Unassigned JAM031 0.00 0.00 Unassigned JAM17 0.00 0.00 Unassigned JAM121 0.00 0.00 Unassigned LOA036 0.00 0.00 Unassigned LOA036 0.00 0.00 Unassigned LOA081 0.00 0.16 Unassigned LOA159 0.01 6.41 Unassigned MPM019 0.00 0.01 Unassigned MRM164 0.00 0.00 Unassigned MRM176 0.00 0.00 Una	BAS187	0.13	4.42	Unassigned
BAS202 0.00 0.00 Unassigned BRE055 0.00 0.00 Unassigned BRE103 0.00 0.00 Unassigned CAP170 0.00 1.52 Unassigned CAP171 0.00 0.00 Unassigned DJT009 0.03 0.80 Unassigned ED-091 0.00 0.00 Unassigned HM036 0.05 0.00 Unassigned HM037 0.00 0.01 Unassigned JAM031 0.00 0.00 Unassigned JAM045 0.00 0.00 Unassigned JAM177 0.00 0.08 Unassigned JAM128 0.00 0.00 Unassigned LOA036 0.00 0.00 Unassigned LOA036 0.00 0.00 Unassigned LOA081 0.00 0.00 Unassigned LOA131 0.01 6.41 Unassigned MPM019 0.00 0.01 Un	BAS195	0.07	0.00	Unassigned
BRE055 0.00 0.00 Unassigned BRE103 0.00 0.00 Unassigned CAP170 0.00 1.52 Unassigned CAP171 0.00 0.00 Unassigned DJT009 0.03 0.80 Unassigned DJT009 0.00 0.00 Unassigned HM036 0.00 0.00 Unassigned HM037 0.00 0.01 Unassigned JAM031 0.00 0.00 Unassigned JAM177 0.00 0.00 Unassigned JAM121 0.00 0.00 Unassigned LOA036 0.00 0.00 Unassigned LOA036 0.00 0.00 Unassigned LOA081 0.00 0.16 Unassigned LOA082 0.00 0.16 Unassigned LOA159 0.01 6.41 Unassigned MRM103 0.00 0.01 Unassigned MRM164 0.00 0.01 Un	BAS202	0.00		_
BRE103 0.00 0.00 Unassigned CAP170 0.00 1.52 Unassigned CAP171 0.00 0.00 Unassigned DJT009 0.03 0.80 Unassigned ED-091 0.00 0.00 Unassigned HM036 0.05 0.00 Unassigned HM037 0.00 0.01 Unassigned JAM031 0.00 0.00 Unassigned JAM045 0.00 0.00 Unassigned JAM117 0.00 0.08 Unassigned JAM128 0.00 0.00 Unassigned LOA036 0.00 0.00 Unassigned LOA081 0.00 0.00 Unassigned LOA082 0.00 0.16 Unassigned LOA131 0.01 16.44 Unassigned MPM019 0.00 0.01 Unassigned MRM103 0.00 0.01 Unassigned MRM164 0.00 0.00 U	BRE055	0.00		_
CAP170 0.00 1.52 Unassigned CAP171 0.00 0.00 Unassigned DJT009 0.03 0.80 Unassigned ED-091 0.00 0.00 Unassigned HM036 0.05 0.00 Unassigned HM037 0.00 0.01 Unassigned JAM031 0.00 0.00 Unassigned JAM045 0.00 0.00 Unassigned JAM117 0.00 0.08 Unassigned JAM128 0.00 0.00 Unassigned LOA036 0.00 0.00 Unassigned LOA036 0.00 0.00 Unassigned LOA081 0.00 0.16 Unassigned LOA082 0.00 0.16 Unassigned LOA159 0.01 16.44 Unassigned MPM019 0.00 0.01 Unassigned MRM103 0.00 0.01 Unassigned MRM164 0.00 0.00 U	BRE103			_
CAP171 0.00 0.00 Unassigned DJT009 0.03 0.80 Unassigned ED-091 0.00 0.00 Unassigned HM036 0.05 0.00 Unassigned HM037 0.00 0.01 Unassigned JAM031 0.00 0.00 Unassigned JAM127 0.00 0.00 Unassigned JAM128 0.00 0.00 Unassigned LOA036 0.00 0.00 Unassigned LOA081 0.00 0.00 Unassigned LOA082 0.00 0.16 Unassigned LOA131 0.01 16.44 Unassigned MPM019 0.01 6.41 Unassigned MRM103 0.00 0.01 Unassigned MRM164 0.00 0.01 Unassigned MRM172 0.00 0.00 Unassigned MRM176 0.00 0.00 Unassigned MRV90082 64.48 2.47 <t< td=""><td></td><td></td><td></td><td>_</td></t<>				_
DJT009 0.03 0.80 Unassigned ED-091 0.00 0.00 Unassigned HM036 0.05 0.00 Unassigned HM037 0.00 0.01 Unassigned JAM031 0.00 0.00 Unassigned JAM045 0.00 0.00 Unassigned JAM117 0.00 0.08 Unassigned JAM128 0.00 0.00 Unassigned LOA036 0.00 0.00 Unassigned LOA081 0.00 0.00 Unassigned LOA082 0.00 0.16 Unassigned LOA131 0.01 16.44 Unassigned MPM019 0.01 6.41 Unassigned MRM103 0.00 3.11 Unassigned MRM164 0.00 0.01 Unassigned MRM172 0.00 0.00 Unassigned MRM176 0.00 0.00 Unassigned MVP0082 64.48 2.47 <td< td=""><td></td><td></td><td></td><td>_</td></td<>				_
ED-091 0.00 0.00 Unassigned HM036 0.05 0.00 Unassigned HM037 0.00 0.01 Unassigned JAM031 0.00 0.00 Unassigned JAM045 0.00 0.00 Unassigned JAM117 0.00 0.08 Unassigned JAM121 0.00 0.00 Unassigned JAM128 0.00 0.00 Unassigned LOA036 0.00 0.00 Unassigned LOA081 0.00 0.00 Unassigned LOA082 0.00 0.16 Unassigned LOA131 0.01 16.44 Unassigned LOA159 0.01 6.41 Unassigned MPM019 0.00 0.01 Unassigned MRM103 0.00 3.11 Unassigned MRM164 0.00 14.14 Unassigned MRM172 0.00 0.00 Unassigned MRM212 0.01 0.07				_
HM036 0.05 0.00 Unassigned JAM031 0.00 0.01 Unassigned JAM045 0.00 0.00 Unassigned JAM117 0.00 0.08 Unassigned JAM121 0.00 0.00 Unassigned JAM128 0.00 0.00 Unassigned LOA036 0.00 0.00 Unassigned LOA081 0.00 17.24 Unassigned LOA082 0.00 0.16 Unassigned LOA131 0.01 16.44 Unassigned MPM019 0.01 6.41 Unassigned MRM103 0.00 3.11 Unassigned MRM104 0.00 14.14 Unassigned MRM172 0.00 0.00 Unassigned MRM174 0.00 0.00 Unassigned MRM175 0.00 0.00 Unassigned MVP0082 64.48 2.47 Unassigned MVP0088 0.41 0.88				_
HM037 0.00 0.01 Unassigned JAM031 0.00 0.00 Unassigned JAM045 0.00 0.00 Unassigned JAM117 0.00 0.08 Unassigned JAM128 0.00 0.00 Unassigned LOA036 0.00 0.00 Unassigned LOA081 0.00 17.24 Unassigned LOA082 0.00 0.16 Unassigned LOA131 0.01 16.44 Unassigned MPM019 0.01 6.41 Unassigned MRM103 0.00 3.11 Unassigned MRM104 0.00 14.14 Unassigned MRM172 0.00 0.00 Unassigned MRM176 0.00 0.00 Unassigned MVP0082 64.48 2.47 Unassigned MVP0088 0.41 0.88 Unassigned MVP0143 0.02 0.05 Unassigned MVP0165 0.00 0.00				
JAM031 0.00 0.00 Unassigned JAM045 0.00 0.00 Unassigned JAM117 0.00 0.08 Unassigned JAM121 0.00 0.00 Unassigned JAM128 0.00 0.00 Unassigned LOA036 0.00 0.00 Unassigned LOA081 0.00 17.24 Unassigned LOA082 0.00 0.16 Unassigned LOA131 0.01 16.44 Unassigned MPM019 0.01 6.41 Unassigned MRM103 0.00 3.11 Unassigned MRM104 0.00 14.14 Unassigned MRM172 0.00 0.00 Unassigned MRM176 0.00 0.00 Unassigned MVP0082 64.48 2.47 Unassigned MVP0088 0.41 0.88 Unassigned MVP0143 0.02 0.05 Unassigned MVP0165 0.00 0.00				_
JAM045 0.00 0.00 Unassigned JAM117 0.00 0.08 Unassigned JAM121 0.00 0.00 Unassigned JAM128 0.00 0.00 Unassigned LOA036 0.00 0.00 Unassigned LOA081 0.00 17.24 Unassigned LOA082 0.00 0.16 Unassigned LOA131 0.01 16.44 Unassigned LOA159 0.01 6.41 Unassigned MPM019 0.00 0.01 Unassigned MRM103 0.00 3.11 Unassigned MRM164 0.00 14.14 Unassigned MRM172 0.00 0.00 Unassigned MRM176 0.00 0.00 Unassigned MVP0082 64.48 2.47 Unassigned MVP0088 0.41 0.88 Unassigned MVP0143 0.02 0.05 Unassigned MVP0165 0.00 0.00				_
JAM117 0.00 0.08 Unassigned JAM121 0.00 0.00 Unassigned JAM128 0.00 0.00 Unassigned LOA036 0.00 0.00 Unassigned LOA081 0.00 17.24 Unassigned LOA082 0.00 0.16 Unassigned LOA131 0.01 16.44 Unassigned LOA159 0.01 6.41 Unassigned MPM019 0.00 0.01 Unassigned MRM103 0.00 3.11 Unassigned MRM164 0.00 14.14 Unassigned MRM172 0.00 0.00 Unassigned MRM176 0.00 0.00 Unassigned MVP0082 64.48 2.47 Unassigned MVP0088 0.41 0.88 Unassigned MVP0143 0.02 0.05 Unassigned MVP0165 0.00 0.00 Unassigned				_
JAM121 0.00 0.00 Unassigned JAM128 0.00 0.00 Unassigned LOA036 0.00 0.00 Unassigned LOA081 0.00 17.24 Unassigned LOA082 0.00 0.16 Unassigned LOA131 0.01 16.44 Unassigned MPM019 0.01 6.41 Unassigned MRM103 0.00 0.01 Unassigned MRM164 0.00 14.14 Unassigned MRM172 0.00 0.00 Unassigned MRM212 0.01 0.07 Unassigned MVP0082 64.48 2.47 Unassigned MVP0088 0.41 0.88 Unassigned MVP0143 0.02 0.05 Unassigned MVP0165 0.00 0.00 Unassigned				_
JAM128 0.00 0.00 Unassigned LOA036 0.00 0.00 Unassigned LOA081 0.00 17.24 Unassigned LOA082 0.00 0.16 Unassigned LOA131 0.01 16.44 Unassigned LOA159 0.01 6.41 Unassigned MPM019 0.00 0.01 Unassigned MRM103 0.00 3.11 Unassigned MRM164 0.00 14.14 Unassigned MRM172 0.00 0.00 Unassigned MRM176 0.00 0.00 Unassigned MVP0082 64.48 2.47 Unassigned MVP0088 0.41 0.88 Unassigned MVP0143 0.02 0.05 Unassigned MVP0165 0.00 0.00 Unassigned				_
LOA036 0.00 0.00 Unassigned LOA081 0.00 17.24 Unassigned LOA082 0.00 0.16 Unassigned LOA131 0.01 16.44 Unassigned LOA159 0.01 6.41 Unassigned MPM019 0.00 0.01 Unassigned MRM103 0.00 3.11 Unassigned MRM164 0.00 14.14 Unassigned MRM172 0.00 0.00 Unassigned MRM176 0.00 0.00 Unassigned MVP0082 64.48 2.47 Unassigned MVP0088 0.41 0.88 Unassigned MVP0143 0.02 0.05 Unassigned MVP0165 0.00 0.00 Unassigned				_
LOA081 0.00 17.24 Unassigned LOA082 0.00 0.16 Unassigned LOA131 0.01 16.44 Unassigned LOA159 0.01 6.41 Unassigned MPM019 0.00 0.01 Unassigned MRM103 0.00 3.11 Unassigned MRM164 0.00 14.14 Unassigned MRM172 0.00 0.00 Unassigned MRM176 0.00 0.00 Unassigned MVP0082 64.48 2.47 Unassigned MVP0088 0.41 0.88 Unassigned MVP0143 0.02 0.05 Unassigned MVP0165 0.00 0.00 Unassigned				_
LOA082 0.00 0.16 Unassigned LOA131 0.01 16.44 Unassigned LOA159 0.01 6.41 Unassigned MPM019 0.00 0.01 Unassigned MRM103 0.00 3.11 Unassigned MRM164 0.00 14.14 Unassigned MRM172 0.00 0.00 Unassigned MRM176 0.00 0.00 Unassigned MRM212 0.01 0.07 Unassigned MVP0082 64.48 2.47 Unassigned MVP0088 0.41 0.88 Unassigned MVP0143 0.02 0.05 Unassigned MVP0165 0.00 0.00 Unassigned				
LOA131 0.01 16.44 Unassigned LOA159 0.01 6.41 Unassigned MPM019 0.00 0.01 Unassigned MRM103 0.00 3.11 Unassigned MRM164 0.00 14.14 Unassigned MRM172 0.00 0.00 Unassigned MRM176 0.00 0.00 Unassigned MRM212 0.01 0.07 Unassigned MVP0082 64.48 2.47 Unassigned MVP0088 0.41 0.88 Unassigned MVP0143 0.02 0.05 Unassigned MVP0165 0.00 0.00 Unassigned				_
LOA159 0.01 6.41 Unassigned MPM019 0.00 0.01 Unassigned MRM103 0.00 3.11 Unassigned MRM164 0.00 14.14 Unassigned MRM172 0.00 0.00 Unassigned MRM176 0.00 0.00 Unassigned MRM212 0.01 0.07 Unassigned MVP0082 64.48 2.47 Unassigned MVP0088 0.41 0.88 Unassigned MVP0143 0.02 0.05 Unassigned MVP0165 0.00 0.00 Unassigned				_
MPM019 0.00 0.01 Unassigned MRM103 0.00 3.11 Unassigned MRM164 0.00 14.14 Unassigned MRM172 0.00 0.00 Unassigned MRM176 0.00 0.00 Unassigned MRM212 0.01 0.07 Unassigned MVP0082 64.48 2.47 Unassigned MVP0088 0.41 0.88 Unassigned MVP0143 0.02 0.05 Unassigned MVP0165 0.00 0.00 Unassigned				_
MRM103 0.00 3.11 Unassigned MRM164 0.00 14.14 Unassigned MRM172 0.00 0.00 Unassigned MRM176 0.00 0.00 Unassigned MRM212 0.01 0.07 Unassigned MVP0082 64.48 2.47 Unassigned MVP0088 0.41 0.88 Unassigned MVP0143 0.02 0.05 Unassigned MVP0165 0.00 0.00 Unassigned				_
MRM164 0.00 14.14 Unassigned MRM172 0.00 0.00 Unassigned MRM176 0.00 0.00 Unassigned MRM212 0.01 0.07 Unassigned MVP0082 64.48 2.47 Unassigned MVP0088 0.41 0.88 Unassigned MVP0143 0.02 0.05 Unassigned MVP0165 0.00 0.00 Unassigned				_
MRM172 0.00 0.00 Unassigned MRM176 0.00 0.00 Unassigned MRM212 0.01 0.07 Unassigned MVP0082 64.48 2.47 Unassigned MVP0088 0.41 0.88 Unassigned MVP0143 0.02 0.05 Unassigned MVP0165 0.00 0.00 Unassigned				_
MRM176 0.00 0.00 Unassigned MRM212 0.01 0.07 Unassigned MVP0082 64.48 2.47 Unassigned MVP0088 0.41 0.88 Unassigned MVP0143 0.02 0.05 Unassigned MVP0165 0.00 0.00 Unassigned				_
MRM212 0.01 0.07 Unassigned MVP0082 64.48 2.47 Unassigned MVP0088 0.41 0.88 Unassigned MVP0143 0.02 0.05 Unassigned MVP0165 0.00 0.00 Unassigned				_
MVP0082 64.48 2.47 Unassigned MVP0088 0.41 0.88 Unassigned MVP0143 0.02 0.05 Unassigned MVP0165 0.00 0.00 Unassigned				_
MVP0088 0.41 0.88 Unassigned MVP0143 0.02 0.05 Unassigned MVP0165 0.00 0.00 Unassigned				
MVP0143 0.02 0.05 Unassigned MVP0165 0.00 0.00 Unassigned				_
MVP0165 0.00 0.00 Unassigned				_
· · · · · · · · · · · · · · · · · · ·				_
MVP0179 0.00 0.00 Unassigned				_
	MVP0179	0.00	0.00	Unassigned

MVP0199	0.00	0.07	Unassigned
MVP0215	0.07	0.03	Unassigned
MVP0233	0.00	0.00	Unassigned
MVP0283	0.09	0.39	Unassigned
MVP0288	0.00	0.00	Unassigned
MVP0316	0.00	0.00	Unassigned
MVP0325	0.00	0.00	Unassigned
MVP0411	0.00	0.00	Unassigned
MVP0440	0.00	0.00	Unassigned
MVP0458	0.01	0.69	Unassigned
MVP0462	0.00	0.08	Unassigned
OK089	0.00	0.00	Unassigned
OK104	0.03	7.70	Unassigned
OK106	4.64	2.43	Unassigned
OK109	0.00	0.16	Unassigned
OT140	0.00	0.02	Unassigned
OT238	0.00	0.00	Unassigned
OU0022	0.00	0.00	Unassigned
RLB019	0.00	0.00	Unassigned
RLB161	0.00	0.01	Unassigned
RLB164	0.00	0.00	Unassigned
RLB165	0.00	0.00	Unassigned
RLB168	0.00	0.00	Unassigned
RLB269	0.00	0.00	Unassigned
SWC048	0.00	0.83	Unassigned
SWR050	0.00	0.00	Unassigned
SWR125	0.00	3.14	Unassigned
SWR222	0.00	0.00	Unassigned
TAM250	0.00	0.00	Unassigned
UT00462	0.01	0.00	Unassigned
UT00787	0.00	0.00	Unassigned

Table C5. Principal component analysis for Macro Group C-1 pottery (R-Q factor analysis based on

varianc	rabie c.s. rrificipal componel variance-covariance matrix).	niponent natrix).	iable co. rincipul component analysis jor macro aroup tariance-covariance matrix).	dno
PCA	Eigenvalue	%Var.	Cum. %Var.	
~	0.1487	37.90	37.90	
7	0.0698	17.79	55.68	
က	0.0428	10.89	86.58	
4	0.0332	8.46	75.04	
2	0.0179	4.56	09.62	
9	0.0131	3.33	82.93	
7	0.0093	2.37	85.30	
80	0.0085	2.17	87.47	
တ	0.0073	1.86	89.33	
10	9900'0	1.68	91.02	
7	0.0059	1.50	92.52	
12	0.0055	1.41	93.93	
13	0.0049	1.25	95.18	
1	0.0039	66.0	96.16	
15	0.0033	0.83	97.00	
16	0.0025	0.64	97.64	
17	0.0019	0.48	98.12	
18	0.0018	0.46	98.58	
19	0.0012	0.29	98.88	
20	0.0011	0.28	99.15	
21	0.000	0.22	99.37	
22	0.0007	0.18	99.55	
23	9000.0	0.15	99.70	
24	0.0003	60.0	99.79	
25	0.0003	80.0	29.87	
26	0.0003	0.07	99.94	
27	0.0002	90.0	100.00	

est):
small
largest to
vectors (
Eigen

0.06 0.05 0.02 0.11 0.44 -0.24 0.02 -0.01 -0.50 -0.14 0.42 -0.06 0.02 -0.12 -0.04 0.02 0.00 -0.51 0.06 -0.04 -0.07 -0.10 0.29 -0.01 0.01 0.01 0.36 9.0 0.17 0.01 0.03 0.17 0.03 -0.04 0.00 0.00 0.00 -0.05 -0.78 0.28 0.01 0.11 -0.03 0.01 0.09 -0.16 0.23 -0.02 0.00 0.01 -0.01 0.05 -0.01 0.00 -0.02 0.04 0.08 -0.31 0.00 -0.01 -0.13 0.15 -0.39 0.08 -0.04 -0.04 0.03 0.02 0.17 -0.26 0.01 0.01 0.01 -0.22 0.01 0.00 0.04 -0.05 0.01 0.38 0.76 -0.05 -0.02 -0.05 0.05 0.06 0.08 -0.02 -0.27-0.04 0.28 -0.10 0.19 0.30 -0.28 -0.07 0.28 0.05 0.26 -0.01 -0.08 0.03 -0.01 0.01 -0.02 0.05 -0.01 -0.26 -0.43 0.0 -0.04 0.07 -0.39 -0.02 -0.01 0.70 -0.06 -0.04 0.03 -0.03 0.22 -0.03 0.10 -0.12 -0.28 0.30 -0.11 0.07 0.12 0.11 -0.12 -0.03 0.02 0.01 -0.06 0.04 -0.15 0.20 0.25 -0.23 0.04 0.10 0.01 0.16 -0.04 -0.01 -0.14 -0.03 0.11 0.03 -0.08 0.28 0.13 -0.12 0.05 -0.13 0.52 -0.08 -0.16 0.15 0.00 -0.06 0.00 0.15 -0.52 -0.02 0.22 -0.15-0.07 0.30 -0.10 0.10 -0.08 0.37 0.08 0.47 -0.14 0.13 0.19 -0.05 -0.16 0.15 0.05 -0.03 -0.03 -0.01 -0.07 -0.06 -0.22 -0.09 0.43 -0.04 0.08 0.26 0.15 -0.01 0.10 -0.03 -0.16 0.03 -0.06 -0.17 0.00 0.04 -0.17 0.17 0.01 0.33 -0.06 -0.04 -0.05 -0.10 -0.18 0.25 0.10 0.46 -0.07 0.00 -0.27 -0.08 0.02 0.00 -0.03 -0.15 0.08 90.0 0.27 -0.04 -0.08 -0.12 -0.17-0.05 -0.08 0.03 -0.12 -0.08 0.03 0.36 -0.16 -0.04 0.47 0.30 0.14 90.0 -0.08 0.04 -0.45 -0.05 0.07 -0.05 -0.06 -0.08 -0.02 0.07 -0.17 0.16 0.08 0.18 0.00 0.14 0.17 9.0 0.10 90.0 0.08 -0.65 0.38 0.30 0.00 0.20 -0.13 -0.30 0.09 -0.12 0.01 -0.26 0.06 0.29 0.01 -0.05 -0.23 0.01 -0.28 0.19 -0.03 0.41 0.01 -0.02 0.17 -0.20 -0.03 0.06 0.0 0.49 0.01 -0.01 -0.09 -0.02 0.04 0.12 0.08 0.07 0.08 0.02 90.0 0.07 0.37 0.28 0.15 0.10 -0.47 -0.23 0.10 0.00 -0.03 0.05 0.05 -0.16 0.03 -0.02 -0.06 0.02 -0.22 -0.06 0.61 -0.19 -0.01 0.22 -0.27 -0.12 -0.04 0.21 0.12 0.11 0.26 -0.13 90.0 -0.38 0.02 0.30 -0.19 -0.08 0.15 0.0 0.48 -0.200.12 -0.30 90.0 0.08 0.01 0.02 -0.02 0.05 -0.04 0.08 0.20 -0.09 -0.05 0.07 0.07 0.03 -0.330.01 0.16 -0.52 0.01 -0.11 -0.17 -0.18 0.13 0.19 0.10 0.17 0.05 0.01 -0.15 0.06 -0.28 0.12 0.18 0.14 -0.17 0.02 -0.01 -0.08 0.09 -0.05 0.42 0.0 -0.03 0.05 -0.20 0.00 -0.07 -0.10 -0.52 -0.08 -0.09 0.00 0.08 0.03 0.04 -0.02 0.32 -0.01 -0.02 -0.14 -0.50 0.17 -0.10 0.10 -0.04 0.01 -0.07 0.20 0.09 -0.04 0.01 -0.03 0.04 -0.08 -0.21 0.02 -0.01 -0.74 0.01 0.41 0.09 -0.22 -0.10 0.09 0.15 -0.15 0.07 0.09 -0.10 -0.01 -0.05 -0.04 -0.18 0.02 0.21 0.14 0.07 0.26 -0.44 -0.15 0.13 -0.32 -0.12 -0.22 0.09 -0.03 -0.15-0.18 -0.10 -0.06 0.45 -0.21 0.07 90.0 -0.15-0.17-0.20 0.05 -0.04 -0.04 -0.15 -0.13 -0.45 -0.20 -0.10 -0.23 -0.12 -0.65 -0.02 -0.21 -0.14 -0.06 -0.13 -0.03 -0.05 -0.16 -0.03 0.00 -0.08 -0.18 -0.49 0.05 0.10 0.03 -0.03 -0.04 0.00 0.02 0.74 -0.08 -0.03 0.07 -0.05 0.11 -0.01 0.08 -0.04 0.03 -0.06 0.19 -0.15 0.08 90.0 0.00 -0.53 0.01 0.21 0.01 0.05 0.27 0.21

	8	01	8	8	8	8	8	8	8	8	8	0.0	8.	8.	8	017	8	01	8	8	8	8	8	8	8	0.00	8
																										0.00	
																										00.00	
																										00.00	
																										0.00	
																										0.00	
																										0.00	
																										0.00	
																-	-									0.00	
	0.00	-0.01	0.00	0.00	0.00	0.00	0.00	-0.01	0.00	0.00	0.01	0.01	-0.01	0.02	0.00	0.02	-0.01	0.00	0.00	0.01	0.00	0.00	0.01	0.00	0.00	0.00	-0.02
	0.00	0.01	-0.02	-0.01	0.01	0.00	-0.02	0.05	0.00	0.00	0.01	0.00	0.00	-0.01	0.00	0.00	0.01	0.01	0.00	-0.01	0.00	0.00	0.00	-0.01	0.01	0.00	-0.01
	0.00	0.00	-0.02	0.01	-0.01	0.00	-0.01	0.00	0.00	0.00	-0.01	-0.01	0.00	0.01	0.00	-0.01	0.00	0.00	0.01	0.01	0.00	0.00	0.02	-0.01	0.01	-0.01	0.01
	0.00	0.00	0.01	-0.01	-0.01	-0.01	0.00	0.00	0.00	0.00	-0.01	0.00	0.00	0.02	-0.01	0.00	0.03	0.02	0.01	0.00	0.00	0.00	-0.03	0.00	0.02	0.00	-0.01
	0.00	0.00	0.01	-0.01	0.00	-0.02	0.01	0.00	0.00	0.00	0.00	0.00	-0.01	0.01	0.00	0.01	0.01	0.01	0.01	-0.04	0.00	0.01	0.02	0.00	0.00	-0.01	0.01
																										0.03	
																										-0.02	
																										-0.01	
																										-0.02	
nent):																										0.03 -(
			-			-															-	-				-0.03	
lest co	.02	0.00																								-0.05	
o smal	0	0.00																	-							0.00	
gest t	-0.09																							-0.02 -0		-0.03	
rix (lar	0.02 -0	-0.02 0																								-0.02 -0	
g Mat	09 0.																									-0.01	
oadin	-0.13 -0.09	0.00 -0.															0.01 -0.										
ictor L	33 -0.																									11 0.01	
Scaled Factor Loading Matrix (largest to smallest compo	\$ 0.03																									0.11	
Sc	As	Б	3	ž	Ş	\supset	X	ర	Ċ	ပိ	Д	Ā	Í	쮼	S	Sc	Ţ	⊨	Zr	Zr	₹	B	Δ	Σ	ž	F	>

Table C6. Principal component analysis for Macro Group C-2a pottery (R-Q factor analysis based on correlation matrix).

5	Eigenvalue	%Var.	Cum. %Var.
_	6.7936	25.16	25.16
7	4.3642	16.16	41.33
က	3.2886	12.18	53.51
4	2.0816	7.71	61.21
2	1.2208	4.52	65.74
9	1.0568	3.91	69.65
7	0.9363	3.47	73.12
œ	0.9221	3.42	76.53
တ	0.8154	3.02	79.55
10	0.7918	2.93	82.49
7	0.7238	2.68	85.17
12	0.5793	2.15	87.31
13	0.5334	1.98	89.29
14	0.4681	1.73	91.02
15	0.4313	1.60	92.62
16	0.3356	1.24	93.86
17	0.3223	1.19	92.06
18	0.2733	1.01	96.07
19	0.2031	0.75	96.82
20	0.1874	69.0	97.51
21	0.1683	0.62	98.14
22	0.1386	0.51	98.65
23	0.1188	0.44	60.06
24	0.0848	0.31	99.40
25	0.0755	0.28	89.68
26	0.058	0.22	06.66
27	000	,	

nivectors (largest to smallest): 0.09 -0.06 -0.37 -0.14 -0.07 -0.03 -0.22 0.16 0.09 0.07 -0.20 -0.47 -0.28 0.52 0.07 -0.19 -0.10 0.01 0.01 0.18 -0.17 -0.01 -0.05 -0.11 0.06 0.02
0.30 0.10 0.23 -0.06 -0.06 0.09 -0.09 0.05 -0.03 -0.03 -0.06 -0.29 -0.03 -0.06 -0.10 -0.04 -0.05 0.08 0.33 -0.02 0.12 -0.11 0.40 0.06 -0.27 -0.52 0.3 0.3 0.3 0.3 0.3 0.3 0.3 0.3 0.3 0.3
-0.05 -0.02 -0.02 -0.04 0.05 -0.01 0.12 0.12 0.09 0.30 -0.13 0.20 0.08 0.34 0.07 0.19 0.16 -0.07 0.01 -0.05 0.14 0.07 -0.25 -0.01 -0.21 -0.21 0.05 0.09 0.48 -0.31 0.11 0.09 0.35 -
0.34 0.12 0.13 -0.12 -0.07 -0.01 -0.10 -0.03 -0.05 0.08 0.00 -0.03 0.05 -0.04 -0.01 0.05 0.01 -0.04 0.05 -0.04 -0.09 -0.23 -0.15 0.04 -0.07 -0.12 -
0.16 -0.18 -0.05 -0.05 0.13 -0.15 0.38 0.23 -0.55 -0.20 -0.32 -0.19 0.19 -0.04 0.25 0.25 -0.07 0.04 -0.16 -0.05 -0.15
0.35 -0.03 0.00 -0.08 0.01 -0.10 -0.07 -0.03 0.00 0.05 -0.03 0.26 0.07 0.08 0.15 -0.12 0.10 -0.32 0.08 -0.25 -0.09 0.05 -0.07 -0.55 -0.42 0.17
0.24 0.06 0.09 0.03 -0.09 0.29 0.03 -0.08 0.28 -0.55 0.07 0.19 0.02 0.24 0.23 0.09 -0.35 0.22 -0.28 0.06 0.06 -0.13 -0.10 -0.03 -0.03 -0.03
0.02 0.24 -0.27 0.23 -0.17 0.16 -0.16 -0.18 -0.04 0.06 0.05 -0.42 0.36 -0.14 0.20 0.21 -0.02 -0.34 -0.11 0.03 0.36 -0.07 -0.09 0.00
0.01 0.09 -0.30 -0.29 -0.17 -0.31 0.20 0.12 0.09 0.01 0.50 0.05 0.13 0.25 0.00 0.31 0.25 0.19 0.00 -0.02 0.08 -0.09 0.22 0.07 -0.14 0.10
0.25 0.29 0.18 -0.09 0.06 -0.02 0.04 -0.02 -0.05 0.06 0.02 -0.07 -0.07 -0.07 -0.10 -0.03 -0.13 -0.04 0.13 0.03 -0.23 -0.44 0.17 0.13 0.25 0.59
0.04 0.31 -0.29 0.21 0.09 0.21 0.00 -0.06 -0.01 0.08 0.05 0.04 0.08 -0.13 0.14 -0.20 0.01 0.27 -0.02 0.02 -0.47 0.29 0.11 0.27 -0.39
0.17 -0.09 -0.05 0.52 0.10 -0.09 0.13 0.12 0.03 0.10 0.08 0.13 -0.12 -0.07 0.27 -0.09 0.25 0.08 0.01 0.53 0.11 -0.21 0.18 -0.24 0.08 -0.06
0.17 -0.20 -0.25 -0.06 0.25 0.16 0.26 -0.02 -0.06 0.16 0.28 0.03 0.16 -0.04 -0.45 -0.03 -0.31 -0.14 0.00 0.30 -0.08 -0.14 -0.31 -0.02 -0.10
0.06 -0.12 -0.32 -0.23 -0.19 -0.23 0.12 0.01 0.27 -0.18 0.07 -0.09 -0.25 -0.64 0.22 -0.13 -0.22 -0.06 0.08 -0.04 -0.03 0.06 -0.01 -0.05 0.09 -0.06
0.02 0.40 -0.18 -0.02 -0.12 0.12 0.18 -0.12 -0.10 0.12 -0.02 0.20 0.13 0.11 0.05 0.12 -0.15 0.02 0.27 -0.06 -0.14 0.18 0.08 -0.34 0.52 -0.28
0.18 -0.31 -0.09 0.21 -0.12 0.08 -0.02 -0.14 0.07 -0.08 0.19 -0.16 0.18 0.00 -0.09 -0.19 0.36 0.03 -0.21 -0.41 -0.32 -0.20
0.18 -0.34 -0.04 0.11 -0.08 0.25 0.24 -0.02 0.02 -0.08 0.01 -0.10 0.12 0.10 -0.13 -0.17 -0.10 0.06 0.31 -0.10 0.28 0.34 0.30 0.00 0.06 0.39
0.08 0.13 -0.21 -0.06 0.03 0.28 -0.11 0.74 0.17 0.06 -0.22 0.20 0.17 -0.15 -0.13 -0.06 0.09 0.04 -0.08 -0.17 0.18 -0.12 0.01 0.01 0.08 0.00
0.18 -0.04 0.03 0.45 0.09 -0.15 0.03 0.19 0.17 0.28 0.13 -0.04 -0.34 0.07 0.01 0.42 -0.30 -0.02 0.02 -0.38 -0.02 0.12 -0.10 0.12 0.00 -0.01
-0.08 0.21 0.13 0.09 -0.44 0.25 0.41 0.22 -0.19 -0.16 0.15 -0.09 -0.37 0.04 -0.08 -0.09 0.24 -0.23 0.05 0.02 -0.04 0.04 -0.29 0.03 -0.10 0.02
-0.04 0.18 0.18 0.02 0.08 -0.20 0.52 -0.06 0.58 0.11 -0.34 -0.21 0.26 0.09 -0.04 -0.10 0.07 -0.06 -0.04 0.00 -0.03 -0.01 -0.05 0.01 -0.08
0.33 0.03 0.04 -0.11 -0.13 -0.05 -0.02 -0.03 0.02 0.11 -0.03 0.20 -0.08 0.06 -0.09 -0.02 0.02 -0.46 -0.45 0.20 -0.01 0.33 0.33 0.33 0.14 -0.08
0.10 0.18 -0.11 -0.06 0.61 0.11 -0.03 -0.05 0.12 -0.42 0.04 -0.15 -0.21 -0.05 -0.13 0.24 0.35 -0.18 0.10 0.00 0.00 0.07 0.01 -0.06 0.09
-0.12 0.21 0.19 0.11 0.22 -0.31 -0.07 0.31 -0.10 -0.20 0.43 -0.13 0.23 0.10 0.08 -0.43 -0.25 -0.16 -0.06 0.02 0.15 -0.01 -0.03 0.12 -0.04 -0.04
0.09 0.08 -0.14 0.33 -0.29 -0.42 -0.19 0.02 -0.01 -0.39 -0.24 0.12 0.15 -0.01 -0.47 0.09 -0.02 0.00 0.19 0.14 -0.11 0.04 -0.06 0.04 -0.04 0.05
0.26 -0.29 0.07 0.14 -0.17 0.17 -0.27 -0.24 0.00 -0.14 0.11 -0.28 0.07 -0.16 -0.34 -0.03 0.15 -0.21 -0.29 0.43 -0.19 0.02 0.05

Scal	Scaled Factor Loading Matrix (largest to smallest	or Loa	ding ∿	Natrix ((larges	st to sr	nallest		component)												
As	0.23	-0.12	-0.67	-0.20	-0.08	-0.03	-0.21	0.16	0.08	90.0	-0.17	-0.36	-0.20	0.36	0.04	-0.11	-0.06	0.00	0.00	0.08	Ÿ
La	0.78	0.21	0.42	-0.09	-0.07	0.0	-0.09	0.05	-0.03	-0.03	0.05	-0.22	-0.02	-0.04	-0.07	-0.03	-0.03	0.04	0.15	-0.01	$\overline{}$
3	0.89	-0.08	0.00	-0.14	0.05	-0.12	-0.04	-0.02	-0.02	0.05	-0.01	0.09	0.08	90.0	0.19	-0.07	0.11	0.04	0.15	0.03	$\overline{}$
ΡN	0.71	0.28	0.40	-0.14	-0.08	-0.07	-0.07	0.01	-0.04	0.12	0.06	-0.19	-0.01	-0.14	-0.14	0.03	0.05	0.25	0.14	0.05	$\overline{}$
Sm	0.89	0.25	0.23	-0.17	-0.08	-0.01	-0.09	-0.03	-0.04	0.07	0.00	-0.03	0.03	-0.05	-0.01	0.03	0.00	-0.02	0.02	-0.02	Ÿ
⊃	0.42	-0.37	-0.08	-0.07	0.14	-0.16	0.37	0.22	-0.49	-0.18	-0.27	-0.14	0.14	-0.03	0.17	0.14	-0.04	0.02	-0.07	-0.02	Ÿ
γp	0.90	-0.06	0.01	-0.12	0.01	-0.11	-0.06	-0.03	0.00	0.04	-0.02	0.20	0.05	0.06	0.10	-0.07	0.06	-0.17	0.04	-0.11	Ÿ
Ce	0.63	0.12	0.16	0.04	-0.10	0.30	0.03	-0.08	0.25	-0.49	0.06	0.14	0.01	0.16	0.15	0.05	-0.20	0.12	-0.13	0.03	_
ပ်	0.04	0.51	-0.48	0.34	-0.19	0.16	-0.16	-0.17	-0.04	0.05	0.04	-0.32	0.26	-0.09	0.13	0.12	-0.01	-0.18	-0.05	0.01	_
S	0.02	0.19	-0.54	-0.42	-0.18	-0.32	0.19	0.11	0.09	0.01	0.43	0.04	0.0	0.17	0.00	0.18	0.14	0.10	0.00	-0.01	_
Ш	0.65	0.60	0.33	-0.12	0.07	-0.02	0.03	-0.02	-0.04	0.06	0.02	-0.05	-0.05	-0.07	-0.05	-0.02	-0.08	-0.02	90.0	0.01	Ť
Fe	0.10	99.0	-0.52	0.31	0.10	0.22	0.00	-0.06	-0.01	0.07	0.04	0.03	0.06	-0.09	0.09	-0.11	0.01	0.14	-0.01	0.01	Ť
±	0.44	-0.18	-0.09	0.74	0.11	-0.10	0.12	0.12	0.03	0.09	0.07	0.10	-0.09	-0.05	0.18	-0.05	0.14	0.04	0.00	0.23	_
Rb	0.43	-0.41	-0.45	-0.09	0.28	0.17	0.25	-0.02	-0.06	0.15	0.24	0.05	0.11	-0.03	-0.30	-0.02	-0.18	-0.07	0.00	0.13	Ť
Sb	0.17	-0.25	-0.57	-0.33	-0.21	-0.24	0.11	0.01	0.24	-0.16	0.06	-0.07	-0.18	-0.43	0.14	-0.08	-0.13	-0.03	0.04	-0.02	Ÿ
Sc	0.0	0.83	-0.32	-0.03	-0.13	0.13	0.18	-0.12	-0.09	0.11	-0.02	0.15	0.0	0.08	0.03	0.07	-0.08	0.01	0.12	-0.02	Ÿ
Ta	0.48	-0.64	-0.15	0.31	-0.13	0.08	-0.02	-0.13	0.06	-0.07	0.16	-0.12	0.13	0.00	-0.06	-0.11	0.21	0.02	-0.09	-0.18	Y
T	0.47	-0.71	-0.06	0.16	-0.08	0.26	0.23	-0.02	0.02	-0.07	0.01	-0.08	0.09	0.07	-0.08	-0.10	-0.06	0.03	0.14	-0.04	$\overline{}$
Zn	0.20	0.27	-0.38	-0.09	0.03	0.29	-0.11	0.71	0.15	0.05	-0.19	0.15	0.12	-0.11	-0.09	-0.04	0.05	0.02	-0.04	-0.07	$\overline{}$
Zr	0.46	-0.09	0.06	99.0	0.10	-0.15	0.03	0.18	0.15	0.25	0.11	-0.03	-0.25	0.02	0.01	0.24	-0.17	-0.01	0.01	-0.16	Ÿ
₹	-0.20	0.44	0.24	0.13	-0.48	0.25	0.40	0.21	-0.17	-0.14	0.13	-0.07	-0.27	0.05	-0.05	-0.05	0.14 -	-0.12	0.02	0.01	Ÿ
Ba	-0.10	0.37	0.33	0.03	0.0	-0.20	0.50	-0.05	0.52	0.10	-0.29	-0.16	0.19	90.0	-0.03	-0.06	0.04	-0.03	-0.02	0.00	Ÿ
δ	0.87	0.06	0.06	-0.17	-0.14	-0.05	-0.02	-0.03	0.02	0.0	-0.03	0.15	-0.06	0.04	-0.06	-0.01	0.01	-0.24	-0.21	0.09	Y
Σ	0.26	0.37	-0.21	-0.08	0.67	0.11	-0.03	-0.05	0.11	-0.38	0.03	-0.12	-0.16	-0.03	-0.08	0.14	0.20	-0.09	0.05	0.00	$\overline{}$
Na	-0.31	0.44	0.35	0.16	0.24	-0.32	-0.07	0.30	-0.09	-0.18	0.36	-0.10	0.17	0.07	0.05	-0.25	-0.14	-0.08	-0.03	-0.03	_
F	0.24	0.17	-0.26	0.48	-0.32	-0.43	-0.18	0.02	-0.01	-0.35	-0.20	0.09	0.11	-0.01	-0.31	0.05	-0.01	0.00	0.09	90.0	Ÿ
>	0.24	0.53	-0.52	0.09	0.15	-0.17	0.16	-0.25	-0.21	0.00	-0.12	0.08	-0.20	0.02	-0.10	-0.20	-0.02	0.08	-0.09	0.13	$\overline{}$

0.01 0.03 0.01

-0.01 0.04

0.01

0.02 -0.03 -0.04 -0.03 0.07 0.06 0.04 90.0 -0.11 0.00 0.03 0.00 0.10 0.00 -0.04 -0.10

0.00

-0.09

-0.04 -0.06

0.13

0.00

-0.07

0.00 0.03 -0.01 -0.01 -0.01 0.00 0.02 -0.04 0.00

0.02

-0.11 0.05 -0.03

0.11 -0.08 -0.05

-0.19

0.04 -0.03 -0.01 -0.06

0.07

0.04 0.08 -0.03

-0.01 -0.07 -0.04 0.09 0.00 0.00 0.01 -0.02 -0.02

0.02 0.14 0.09 0.02 0.00 -0.03 -0.02 0.04

0.02 0.07 0.00

-0.07

-0.13

0.00 0.00 0.04 0.01 0.00 0.08 -0.02

0.13 -0.04 0.04 0.01 0.00

0.12 0.07 -0.01

-0.01

-0.07 -0.01 -0.01 -0.10

0.01

0.03 0.02 0.14

-0.01

-0.01 0.00 0.02

-0.05 -0.03 -0.04 -0.16

0.02 0.15 0.03 -0.09

-0.11 -0.01 -0.02

-0.16

0.05

-0.04

0.00 0.00 -0.01

0.00

0.11 0.00

0.12 90.0 0.06

0.00 -0.01

0.01

-0.02

-0.01

-0.02

-0.01

-0.01

0.01

-0.07

0.01

0.00

Table C7. Principal component analysis for Macro Group C-2b pottery (R-Q factor analysis based on variance-covariance matrix).

Cum. %Var. 43.32	56.30	67.16	75.21	81.08	85.26	87.47	89.49	91.32	95.96	94.27	95.26	96.19	96.93	97.60	98.14	98.57	98.92	99.19	99.39	99.53	99.65	99.75	99.84	99.92	76.66	100.00
%Var. 43.32	12.97	10.86	8.05	5.87	4.18	2.21	2.02	1.83	1.64	1.31	0.99	0.93	0.73	0.67	0.54	0.43	0.35	0.27	0.20	0.15	0.12	0.10	0.09	0.08	0.05	0.03
Eigenvalue 0.1255	0.0376	0.0315	0.0233	0.0170	0.0121	0.0064	0.0059	0.0053	0.0047	0.0038	0.0029	0.0027	0.0021	0.0019	0.0016	0.0013	0.0010	0.0008	9000'0	0.0004	0.0003	0.0003	0.0003	0.0002	0.0001	0.0001
PCA	2	က	4	2	9	7	80	6	10	7	12	13	14	15	16	17	18	19	20	21	22	23	24	25	26	27

Eige	Eigenvectors (largest to smallest):	rs (larg	est to	small	est):													
As	-0.24	-0.29	0.43	-0.74	-0.31	-0.07	0.04	-0.03	-0.03	0.02	0.12	0.02	0.10	-0.04	-0.04	0.03	0.05	0.01
La	-0.01	0.16	0.23	0.09	0.01	-0.09	-0.10	0.03	0.08	0.00	-0.03	-0.09	-0.09	-0.17	-0.18	0.01	0.05	0.07
3	0.17	0.22	0.10	-0.01	-0.09	0.02	-0.03	-0.19	-0.03	0.17	0.05	0.47	-0.06	-0.17	0.02	0.21	0.00	-0.40
N	-0.02	0.24	0.32	0.14	-0.07	-0.01	0.05	0.09	-0.15	-0.48	-0.24	0.00	0.44	-0.04	0.38	0.29		0.11
Sm	•	0.19	0.27	0.0	0.00	٠.	-0.06	0.04	0.07	0.03	0.03	-0.13	-0.17	-0.12	-0.12	-0.14		0.20
⊃	-0.04	0.46	0.03	-0.38	0.50		0.42	0.29	0.03	0.21	-0.04	-0.02	0.04	0.02	0.10	-0.11	-0.01	0.03
γp	0.14	0.19	0.13	-0.01	-0.12			-0.15	-0.06	0.12	0.12	0.44	-0.13	0.07	0.13	-0.16		0.67
S	-0.05		0.26	0.05	-0.08	0.02	-0.15	0.0	0.16	0.05	-0.08		0.00	-0.16	-0.41	0.07		-0.13
ပ်	0.02	-0.02	0.02	-0.04				-0.16	-0.03	0.11		-0.05	0.12	-0.17	0.12	-0.19		0.18
S	-0.05			-	0.36			-0.06	-0.07	-0.07	-0.06	90.0	-0.34	-0.26	0.29	0.16		-0.15
Ш	-0.02				-			0.13	0.08	-0.06	-	-0.02	-0.12	-0.04	-0.18	-0.13		0.00
Fe	0.18		0.24	0.05	0.14	-		-0.15	-0.27	-0.03		0.03	0.15		-0.13	-0.05		-0.21
Ξ	0.07		-		•			-0.19	-0.02	-0.03		0.23	-0.02	0.05	-0.33	0.30		0.02
Rb	-0.10	0.09	-	-0.06	0.13			-0.03	-0.15	-0.09	0.16	-0.11	0.0	0.50	-0.33	0.32	0.00	0.17
Sb	-0.31		0.29					-0.24	0.10	0.24	0.01	-0.07	0.01	-0.01	0.09	-0.02		0.02
Sc	0.15					-		-0.17	-0.16	-0.01	0.13	0.13	0.11	0.08	-0.04	-0.06		-0.17
Ta			-0.23		•			-0.28	0.15	0.19	-0.13	-0.15	0.28	-0.26	-0.02	-0.17		-0.03
Т			-0.02	-0.03	0.04		•	-0.23	-0.05	0.10	0.01	0.02	0.26	-0.13	-0.08	0.02		-0.03
Zn	0.11		0.20	-0.02			0.13	-0.32	-0.05	-0.10	-0.55	0.08	-0.12	0.20	-0.26	-0.21		0.04
Zr	-0.02	0.21	-0.11	-0.12	-0.22			-0.10	-0.02	-0.63	0.12	0.02	-0.24	0.02	-0.02	-0.48		-0.19
₹	0.00	-0.01	0.05	-0.03	0.10	-		-0.02	0.01	0.03	0.11	-0.09	-0.08	0.03	0.01	-0.01	-0.15	-0.01
Ba	-0.01	0.14	-0.10	-0.06	-0.32		0.03	0.04	-0.73	0.23	-0.38	-0.22	-0.23	0.00	0.02	0.01	-0.13	-0.02
Dγ	0.0	0.22	0.20	0.03	-0.17	-0.12	-0.14	-0.03	0.16	0.25	0.03	-0.07	-0.16	0.58	0.35	-0.09	0.32	-0:30
Μ		-0.24	0.14	-0.06	-0.17	0.34	0.05	0.33	0.10	0.02	-0.05	-0.08	0.03	0.01	-0.03	0.02	0.00	0.04
Na	-0.06	0.00	0.00	0.02	-0.05	-0.14	0.23	0.17	0.06	-0.05	-0.06	0.18	-0.43	-0.17	-0.04	0.34	_	0.06
F	0.09	0.12	-0.09	-0.20	-0.08	-0.04	0.06	-0.34	0.41	-0.10	-0.39	-0.14	-0.11	0.13	0.13	0.28	-0.55	0.07
>	0.24	0.07	90.0			'	0.21	-0.38	-0.12	-0.08	0.41	-0.51	-0.23	-0.14	0.13	0.18	0.22	0.13

0.22

0.04 0.21 0.52 0.12

0.10

-0.45

0.45

-0.43

0.01 0.37 0.00 0.05 0.05 0.07 0.01 0.11 0.03 0.05 0.03

0.14 0.41 0.04 0.17 -0.01 0.01

0.03

-0.02 -0.13 -0.03

0.01

-0.03 -0.12 -0.26 -0.21 0.07

0.00

-0.01

0.03 -0.20 -0.26 0.44 -0.17

-0.02

0.01 0.12 0.10 0.16 0.28 -0.08 -0.32 -0.32

-0.22 0.03 0.10 -0.04 -0.24 0.12 -0.07 0.32 -0.20 0.06

0.08

0.24 0.11 0.03 0.02 -0.19

-0.08

0.21 -0.03 0.04

0.30

0.08

0.16

0.22 -0.07 -0.02 -0.09

-0.05 0.00 -0.68

-0.01 0.02 0.20

-0.09

0.09

-0.35

0.09 0.02 -0.05 0.12 -0.06 0.03

-0.58

-0.01 0.00 -0.05 0.04

-0.04 0.06 -0.60 -0.02 0.11

-0.11

-0.06 -0.02 -0.53 -0.04 -0.07

0.18 -0.06 -0.19 -0.01

-0.38 -0.01

-0.16

-0.12 -0.36 0.01

-0.05 0.00 0.29 0.00

-0.01

-0.03

-0.04 -0.03 0.02

0.06

-0.03

-0.02

0.01

-0.04

0.10 -0.09 0.32 -0.01

0.48 -0.28 -0.03 -0.14 0.05

0.00

	00.	.01	00.	00.	00.	0.0	0.0	00.	00.	00.	00.	00.	00.	00.	00.	00.	00.	00.	00.	00.	00.	0.0	0.00	00.	00.	00.	00.
																							0.00				
																•							0.00				
											•												0.00				
																							0.00		-		
																					•						
								-															00.00				
																	-				-		0.00				
								•										•			•		1 0.00				
					-											•					-		1 -0.01		-		
			•									-				•				-			0.01				
																							0.01				
																							0.00				
																							0.02				
	0.00	-0.01	-0.01	0.00	-0.01	0.00	0.00	-0.01	-0.01	-0.01	0.00	0.00	0.00	0.02	0.00	0.00	-0.01	-0.01	0.01	0.00	0.00	0.00	0.03	0.00	-0.01	0.01	-0.01
	0.01	0.00	0.00	0.02	-0.01	0.00	-0.01	0.00	0.01	-0.02	-0.01	0.01	0.00	0.00	0.00	0.01	0.01	0.01	-0.01	-0.01	0.00	-0.01	-0.01	0.00	-0.02	-0.01	-0.01
	0.00	-0.01	0.03	0.00	-0.01	0.00	0.02	-0.01	0.00	0.00	0.00	0.00	0.01	-0.01	0.00	0.01	-0.01	0.00	0.00	0.00	0.00	-0.01	0.00	0.00	0.01	-0.01	-0.03
	0.01	0.00	0.00	-0.01	0.00	0.00	0.01	-0.01	-0.01	0.00	-0.01	0.01	0.00	0.01	0.00	0.01	-0.01	0.00	-0.03	0.01	0.01	-0.02	0.00	0.00	0.00	-0.02	0.03
	0.00	0.00	0.01	0.03	0.00	0.01	0.01	0.00	0.01	-0.01	0.00	0.00	0.00	-0.01	0.02	0.00	0.01	0.01	0.01	0.04	0.00	0.02	0.02	0.00	0.00	0.01	0.01
nent):	0	\vdash	0		\vdash	0	0	\vdash	0	$\overline{\Box}$	\vdash	7	0	$\vec{\vdash}$	\vdash	\vdash	\vdash	0	0	Ö	0	2	\vdash	\vdash	0	m	_
odwo	0.00	0.00	0.01	0.01	0.00	0.02	0.01	0.01	0.01	0.01 -	0.01	0.01	0.01	0.00	0.02	0.01 -	0.02	0.02	0.02	0.01	0.00	0.00	0.00	0.03	0.01	0.03	0.03
llest c	0.00	0.01	0.00	0.00	0.00	0.03	0.01	0.01	0.02 -	0.04	0.01	0.01 -	0.02 -	0.03	0.03	. 10.0	0.01	0.00	0.01	0.01	0.00	0.00	0.01	0.00	0.02	0.00	0.02
to sma	0.01	.01	0.00	00.0	0.01	20.0	0.00	0.00	0.01	J.04	00.0	0.01	0.02	0.04	90.0	0.01	.01	00.0	0.01	0.03	00.0	0.01	0.01	20.0	0.02	0.00	0.01
rgest 1	.04	9.00	.01	.01)- 00.	90.0	0.02	.01	.01	.05	0.01	.02 -(0.02	0.02	0.02	.02 -(.02	.01	.04	.03	.01	.04	.02 -(0.02	.01	0.01	. 10.
:rix (la	.11 -0	.01	9.	.02 -0	.01	90.)- 00'	.01	.01	.02 (.02 -(0.01	.01	.01)- 90'(.01	.02	8.	8.	.02 -(00.	.01	.01	.01	.01	.03	8
ig Mai	.08 -C	.04 C	.02 C	.06 C	.05 C	.00 -c	.02 C	.05 ()- 00'	.02 -0	.05 (0.04	.03 -0	0	.05 (.04	.04 -0	00.	.04 C	.02 -0	.01	.02 -0	.04 0	.02 -0	00:	.02 -0	0.01
Loadir	0 90	03 0	0.40	.05 0	040	0 60	040	.05	0 00	.03	040	0 00	.03 -0	.02 0	.040	00	04 -0	03 0	.05	04 -0	0 00	.03 -0	040	.05	0 00	.02 -0	0
actor	08 -0.	00	0 90	01 0.	01 0.	01 0.	05 0.	02 0.	01 0.	02 -0.	01 0.	06 0.	02 0.	04 0	11 -0	05 0.	03 0.	02 0.	04 -0.	01 0.	00	00	02 0.	28 -0.	02 0.	03 0.	0
aled F	s -0.	э 0.	0	d -0.	m -0.	- Ò	ь 0.	e -0.	r 0	s -0.	u Ö	e 0	ıf 0.	اة -	b -0.	٥.	а 0.	Ь 0.	n 0.	r -	<u> </u>	a 0.	Dy 0.02 0.04 0.04 0.01 -0.02 -0.01 -0.01 0.00 0.0	₁n 0.	la -0.	. <u>.</u>	
ĭ	⋖	ت	ī	Z	S	ے	>	O	O	S	ш	ш	I	∝	S	Ñ	Η.	-	Z	7	⋖	В		2	Ž	_	>

Appendix D:

Macro Group D Mahalanobis Distance Calculations

Table D1. Macro Group D Mahalanobis distance calculations for specimens projected against two or more groups.

El Paso Core (ELPC)

El Paso-2 (ELP2)

Loop 375 (Loop)

Variables used:

The following specimens ar	e assigned to group	El Paso Core.		
ID. NO.	ELPC	ELP2	Loop	Group
ANI013	99.29	0.39	0.00	ELPC
ANI014	83.24	0.03	0.00	ELPC
ANI015	38.92	0.07	0.00	ELPC
ANI016	71.59	0.15	0.00	ELPC
ANI017	75.66	0.05	0.00	ELPC
ANI018	63.13	0.01	0.00	ELPC
ANI046	80.25	0.00	0.00	ELPC
ANI050	23.57	1.07	0.00	ELPC
ANI051	76.75	0.08	0.00	ELPC
ATT002	93.20	0.07	0.00	ELPC
ATT005	60.55	0.05	0.00	ELPC
ATT006	95.50	0.07	0.00	ELPC
ATT010	24.39	0.00	0.00	ELPC
ATT012	76.50	0.00	0.00	ELPC
ATT013	8.17	0.01	0.00	ELPC
ATT014	56.82	0.01	0.00	ELPC
ATT015	0.97	0.02	0.00	ELPC
ATT019	99.43	1.23	0.00	ELPC
ATT024	99.76	0.24	0.00	ELPC
ATT028	100.00	1.51	0.00	ELPC
ATT029	52.82	0.23	0.00	ELPC
ATT030	90.28	0.00	0.00	ELPC
ATT034	12.53	0.43	0.00	ELPC
ATT038	99.58	0.80	0.00	ELPC
ATT039	30.18	0.06	0.00	ELPC
ATT041	41.31	0.00	0.00	ELPC
ATT050	12.08	0.05	0.00	ELPC
ATT051	37.91	0.01	0.00	ELPC
ATT052	1.92	0.92	0.00	ELPC
ATT053	5.17	0.04	0.00	ELPC
ATT055	0.92	0.01	0.00	ELPC
ATT056	97.47	0.02	0.00	ELPC
ATT057	38.29	0.02	0.00	ELPC
ATT058	82.03	0.01	0.00	ELPC

ATT059	80.72	0.00	0.00	ELPC
ATT060	87.06	0.03	0.00	ELPC
ATT061	74.60	0.00	0.00	ELPC
ATT062	74.29	1.47	0.00	ELPC
ATT064	6.59	0.00	0.00	ELPC
ATT065	17.56	0.00	0.00	ELPC
ATT066	3.02	0.00	0.00	ELPC
ATT067	10.18	0.00	0.00	ELPC
ATT069	97.86	0.25	0.00	ELPC
ATT070	45.91	0.19	0.00	ELPC
ATT071	11.10	0.00	0.00	ELPC
ATT072	24.62	0.05	0.00	ELPC
ATT074	34.11	0.02	0.00	ELPC
ATT075	88.94	2.62	0.00	ELPC
ATT076	85.80	0.00	0.00	ELPC
ATT077	94.13	0.00	0.00	ELPC
ATT081	54.53	0.00	0.00	ELPC
ATT083	100.00	0.12	0.00	ELPC
ATT084	68.24	0.20	0.00	ELPC
ATT085	99.45	0.11	0.00	ELPC
ATT086	99.73	2.36	0.00	ELPC
ATT087	99.99	0.82	0.00	ELPC
ATT088	98.90	0.95	0.00	ELPC
ATT089	100.00	1.33	0.00	ELPC
ATT090	97.76	0.00	0.00	ELPC
ATT091	99.16	1.32	0.00	ELPC
ATT092	99.96	0.14	0.00	ELPC
ATT093	93.27	0.05	0.00	ELPC
ATT095	13.33	0.00	0.00	ELPC
ATT097	2.92	0.01	0.00	ELPC
ATT098	62.46	0.00	0.00	ELPC
ATT099	99.68	1.03	0.00	ELPC
ATT103	17.31	0.15	0.00	ELPC
ATT105	10.45	0.30	0.00	ELPC
ATT112	18.49	0.00	0.00	ELPC
ATT115	94.38	0.19	0.00	ELPC
ATT116	95.65	0.08	0.00	ELPC
ATT117	61.60	0.02	0.00	ELPC
ATT118	89.11	0.01	0.00	ELPC
ATT119	90.04	0.46	0.00	ELPC
ATT121	0.02	0.00	0.00	ELPC
ATT122	1.23	0.28	0.00	ELPC
ATT123	99.29	0.23	0.00	ELPC
ATT124	56.86	0.01	0.00	ELPC
ATT125	63.91	0.01	0.00	ELPC
ATT126	98.25	0.02	0.00	ELPC
ATT127	27.90	0.00	0.00	ELPC
ATT128	59.97	0.01	0.00	ELPC
ATT130	12.02	0.42	0.00	ELPC
ATT131	72.89	0.00	0.00	ELPC
	. =.55	5.55		0

ATT132	98.86	1.21	0.00	ELPC
ATT133	64.22	0.38	0.00	ELPC
ATT134	58.80	17.01	0.00	ELPC
ATT135	2.40	0.00	0.00	ELPC
ATT136	42.37	0.01	0.00	ELPC
ATT139	85.53	0.14	0.00	ELPC
ATT140	1.07	0.03	0.00	ELPC
ATT144	43.89	0.01	0.00	ELPC
ATT146	60.04	0.06	0.00	ELPC
ATT147	97.92	0.08	0.00	ELPC
ATT149	8.53	0.04	0.00	ELPC
ATT150	32.10	1.08	0.00	ELPC
ATT151	96.36	0.01	0.00	ELPC
ATT152	43.19	0.00	0.00	ELPC
ATT155	93.19	0.13	0.00	ELPC
ATT157	69.28	53.03	0.00	ELPC
ATT158	48.43	0.08	0.00	ELPC
ATT159	3.58	0.02	0.00	ELPC
ATT161	45.50	0.04	0.00	ELPC
ATT162	68.95	0.00	0.00	ELPC
ATT166	98.84	0.19	0.00	ELPC
ATT173	85.41	0.14	0.00	ELPC
ATT174	100.00	1.29	0.00	ELPC
ATT177	100.00	0.98	0.00	ELPC
ATT178	99.41	2.42	0.00	ELPC
ATT179	12.18	0.00	0.00	ELPC
ATT181	96.79	1.38	0.00	ELPC
ATT182	95.11	0.04	0.00	ELPC
ATT183	72.35	0.05	0.00	ELPC
ATT186	97.78	2.51	0.00	ELPC
ATT187	46.90	0.18	0.00	ELPC
ATT188	74.07	0.00	0.00	ELPC
ATT189	66.06	0.01	0.00	ELPC
ATT190	99.98	2.29	0.00	ELPC
ATT191	99.98	0.59	0.00	ELPC
ATT192	29.28	0.14	0.00	ELPC
ATT193	29.60	0.00	0.00	ELPC
ATT194	1.12	0.00	0.00	ELPC
ATT196	93.08	0.00	0.00	ELPC
ATT197	9.43	0.00	0.00	ELPC
ATT202	1.64	0.00	0.00	ELPC
ATT204	84.13	0.00	0.00	ELPC
ATT209	95.96	0.01	0.00	ELPC
ATT213	58.71	0.00	0.00	ELPC
ATT214	99.70	0.00	0.00	ELPC
ATT217	99.03	1.39	0.00	ELPC
ATT219	23.08	0.00	0.00	ELPC
ATT220	19.28	2.38	0.00	ELPC
ATT221	36.04	0.00	0.00	ELPC
ATT223	99.44	0.05	0.00	ELPC

ATT224	99.45	3.74	0.00	ELPC
ATT225	44.34	0.00	0.00	ELPC
ATT226	87.09	0.01	0.00	ELPC
ATT228	99.62	0.01	0.00	ELPC
ATT230	96.38	5.88	0.00	ELPC
ATT231	21.11	0.00	0.00	ELPC
ATT232	99.02	1.84	0.00	ELPC
ATT238	61.19	0.00	0.00	ELPC
ATT241	79.38	8.73	0.00	ELPC
ATT242	92.56	0.00	0.00	ELPC
ATT243	99.89	6.06	0.00	ELPC
ATT244	80.80	0.01	0.00	ELPC
ATT246	95.07	0.22	0.00	ELPC
ATT247	71.62	0.00	0.00	ELPC
ATT249	99.91	0.70	0.00	ELPC
ATT250	100.00	0.37	0.00	ELPC
ATT253	92.14	0.14	0.00	ELPC
ATT257	89.77	0.07	0.00	ELPC
ATT258	99.99	3.97	0.00	ELPC
ATT260	98.15	0.00	0.00	ELPC
ATT261	92.89	0.00	0.00	ELPC
ATT262	45.25	0.07	0.00	ELPC
ATT264	63.13	2.87	0.00	ELPC
ATT265	0.00	0.00	0.00	ELPC
ATT267	56.18	0.00	0.00	ELPC
ATT268	30.37	0.00	0.00	ELPC
ATT269	51.75	0.04	0.00	ELPC
ATT271	98.52	0.37	0.00	ELPC
ATT273	99.99	1.06	0.00	ELPC
ATT275	99.82	6.55	0.00	ELPC
ATT276	99.62	0.48	0.00	ELPC
ATT278	98.60	5.78	0.00	ELPC
ATT280	99.49	0.77	0.00	ELPC
ATT282	97.00	0.03	0.00	ELPC
ATT283	94.23	0.11	0.00	ELPC
ATT284	99.95	1.61	0.00	ELPC
ATT286	95.71	0.02	0.00	ELPC
ATT287	97.12	5.97	0.00	ELPC
ATT288	66.82	0.03	0.00	ELPC
ATT290	41.12	0.07	0.00	ELPC
ATT292	90.86	10.35	0.00	ELPC
ATT294	58.80	9.37	0.00	ELPC
ATT296	96.38	2.40	0.00	ELPC
ATT297	99.99	3.67	0.00	ELPC
ATT298	99.95	0.41	0.00	ELPC
ATT299	99.93	0.31	0.00	ELPC
ATT301	74.18	1.78	0.00	ELPC
ATT302	11.03	0.00	0.00	ELPC
ATT303	16.63	0.85	0.00	ELPC
ATT311	21.33	0.32	0.00	ELPC
		- · - -		

ATT313	6.53	0.04	0.00	ELPC
ATT318	0.00	0.00	0.00	ELPC
ATT319	61.33	0.01	0.00	ELPC
ATT322	12.81	0.00	0.00	ELPC
ATT323	2.91	0.05	0.00	ELPC
ATT324	3.44	0.03	0.00	ELPC
ATT326	99.87	0.01	0.00	ELPC
ATT329	0.00	0.01	0.00	ELPC
ATT330	99.75	0.05	0.00	ELPC
ATT333	43.73	0.02	0.00	ELPC
ATT338	98.30	0.14	0.00	ELPC
ATT339	0.00	0.00	0.00	ELPC
ATT340	24.98	0.30	0.00	ELPC
ATT341	94.81	0.12	0.00	ELPC
BRE014	38.98	0.71	0.00	ELPC
BRE135	0.03	0.01	0.00	ELPC
BRE137	0.83	0.04	0.00	ELPC
BRE169	0.37	0.00	0.00	ELPC
BRE172	50.56	0.03	0.00	ELPC
BRE203	16.98	0.00	0.00	ELPC
BRE204	12.96	0.00	0.00	ELPC
BRE205	1.46	0.00	0.00	ELPC
BRE206	2.62	0.08	0.00	ELPC
EP001	90.70	4.29	0.00	ELPC
EP005	4.15	0.02	0.00	ELPC
EP013	72.41	0.08	0.00	ELPC
EP021	3.15	0.89	0.00	ELPC
EP025	83.53	0.66	0.00	ELPC
EP026	6.12	0.00	0.00	ELPC
EP035	12.10	0.09	0.00	ELPC
EP045	79.44	0.02	0.00	ELPC
EP046	20.73	0.01	0.00	ELPC
EP049	88.05	0.02	0.00	ELPC
EP052	63.14	0.01	0.00	ELPC
EP053	0.14	0.73	0.00	ELPC
EP056	0.87	0.08	0.00	ELPC
EP057	64.22	0.00	0.00	ELPC
EP058	41.93	0.00	0.00	ELPC
EP059	7.85	0.06	0.00	ELPC
EP062	0.54	3.53	0.01	ELPC
EP068	1.46	0.09	0.00	ELPC
EP070A	0.73	0.15	0.00	ELPC
EP073	58.97	0.44	0.00	ELPC
EP075	0.41	0.44	0.00	ELPC
EP077	95.99	0.23	0.00	ELPC
EP077 EP078	57.32	0.23	0.00	ELPC
EP078 EP079	29.27	0.00	0.00	ELPC
EP079 EP084	82.30	0.00	0.00	ELPC
EP085	69.45	3.14	0.00	ELPC
EP087				ELPC
LFU0/	71.30	0.04	0.00	ELPC

EP088	96.53	0.09	0.00	ELPC
EP089	64.90	1.03	0.00	ELPC
EP091A	86.03	0.20	0.00	ELPC
EP114	2.53	17.74	0.00	ELPC
EP115	5.83	0.00	0.00	ELPC
EP116	90.10	0.00	0.00	ELPC
EP119	25.87	4.88	0.00	ELPC
EP134	11.24	5.06	0.00	ELPC
EP146	78.22	0.68	0.00	ELPC
EP153	80.78	0.00	0.00	ELPC
EP155	14.59	0.53	0.00	ELPC
MRM276	6.23	0.00	0.00	ELPC
MRM277	71.37	0.06	0.00	ELPC
MRM280	92.53	0.02	0.00	ELPC
MRM282	46.09	0.75	0.00	ELPC
MRM283	85.37	0.04	0.00	ELPC
MRM284	72.13	0.01	0.00	ELPC
MRM285	5.02	0.80	0.00	ELPC
MRM286	3.07	0.00	0.00	ELPC
MRM287	86.00	1.60	0.00	ELPC
MRM288	24.39	5.52	0.00	ELPC
MRM289	49.07	0.03	0.00	ELPC
MRM290	99.93	0.09	0.00	ELPC
MRM291	86.31	0.62	0.00	ELPC
MRM292	28.37	0.00	0.00	ELPC
MRM293	87.05	0.60	0.00	ELPC
MRM294	21.18	0.19	0.00	ELPC
MRM295	80.40	1.23	0.00	ELPC
MRM296	25.29	0.12	0.00	ELPC
MRM297	47.18	5.08	0.00	ELPC
MRM298	34.23	0.01	0.00	ELPC
MRM299	88.52	14.88	0.00	ELPC
MRM300	98.72	0.12	0.00	ELPC
MRM301	81.96	0.03	0.00	ELPC
MRM302	13.07	0.03	0.00	ELPC
MRM303	94.30	0.31	0.00	ELPC
MRM304	55.42	0.20	0.00	ELPC
MRM305	38.93	0.06	0.00	ELPC
MRM306	71.74	0.04	0.00	ELPC
MRM307	74.42	0.01	0.00	ELPC
MRM308	42.92	0.01	0.00	ELPC
MRM311	92.68	3.84	0.00	ELPC
MRM312	23.80	0.00	0.00	ELPC
MRM313	27.26	0.00	0.00	ELPC
MRM314	10.20	0.69	0.00	ELPC
MRM315	1.62	0.03	0.00	ELPC
MRM318	99.98	2.40	0.00	ELPC
MRM319	99.59	0.06	0.00	ELPC
MRM320	53.17	0.42	0.00	ELPC
MRM321	91.05	2.87	0.00	ELPC
		=	=	0

MRM322	51.02	0.09	0.00	ELPC
MRM323	98.70	1.00	0.00	ELPC
MRM324	91.46	0.03	0.00	ELPC
MRM326	20.86	0.21	0.00	ELPC
MRM328	95.30	5.04	0.00	ELPC
MRM329	41.73	3.31	0.00	ELPC
MRM330	43.13	6.41	0.00	ELPC
MRM332	0.71	0.01	0.00	ELPC
MRM334	61.25	0.01	0.00	ELPC
NAM001	65.86	1.86	0.00	ELPC
OT043	8.62	0.00	0.00	ELPC
OT044	88.92	0.02	0.00	ELPC
OT045	48.27	0.05	0.00	ELPC
OT058	17.48	0.00	0.00	ELPC
OT060	1.43	0.00	0.00	ELPC
OT062	94.62	0.05	0.00	ELPC
OT063	86.31	0.02	0.00	ELPC
ОТ070	99.73	0.00	0.00	ELPC
OT071	34.07	0.01	0.00	ELPC
OT077	66.17	0.00	0.00	ELPC
OT116	94.48	0.01	0.00	ELPC
OT121	79.51	0.05	0.00	ELPC
OT122	14.74	0.00	0.00	ELPC
OT139	44.68	0.01	0.00	ELPC
OT142	99.61	0.00	0.00	ELPC
OT156	92.48	0.16	0.00	ELPC
OT185	87.58	0.00	0.00	ELPC
OT270	97.96	0.42	0.00	ELPC
OT548	1.44	0.01	0.00	ELPC
OT549	60.17	0.01	0.00	ELPC
OT550	1.07	0.00	0.00	ELPC
OT551	96.30	0.50	0.00	ELPC
OT561	26.86	1.31	0.00	ELPC
OT562	64.09	0.58	0.00	ELPC
OTP03X	16.94	0.01	0.00	ELPC
OTP04X	21.50	0.01	0.00	ELPC
PDR001	40.37	0.15	0.00	ELPC
PDR003	98.44	0.00	0.00	ELPC
PDR005	35.05	0.11	0.00	ELPC
PDR007	98.67	0.64	0.00	ELPC
PDR008	6.10	0.01	0.00	ELPC
PDR013	99.53	0.32	0.00	ELPC
PDR014	11.53	1.17	0.00	ELPC
PDR016	71.23	0.05	0.00	ELPC
PDR017	81.11	0.11	0.00	ELPC
PDR018	6.29	0.04	0.00	ELPC
PDR019	82.06	1.18	0.00	ELPC
PDR020	32.15	0.02	0.00	ELPC
PDR021	24.62	2.29	0.00	ELPC
PDR022	14.77	0.05	0.00	ELPC
1 511022	14.//	0.03	0.00	LLFC

PDR024	0.00	0.03	0.00	ELPC
PDR025	0.31	0.00	0.00	ELPC
PDR026	6.56	0.11	0.00	ELPC
PDR027	49.74	0.04	0.00	ELPC
PDR029	57.70	0.72	0.00	ELPC
PDR030	18.23	0.04	0.00	ELPC
PDR031	11.65	0.01	0.00	ELPC
PDR055	55.16	2.34	0.00	ELPC
PDR056	53.99	0.01	0.00	ELPC
PDR057	90.49	0.49	0.00	ELPC
PDR058	37.60	0.01	0.00	ELPC
PDR060	47.32	0.00	0.00	ELPC
PDR061	59.87	0.04	0.00	ELPC
PDR062	29.87	0.05	0.00	ELPC
PDR063	0.07	0.00	0.00	ELPC
PDR064	84.86	0.02	0.00	ELPC
PDR066	95.40	0.16	0.00	ELPC
PDR067	45.80	0.00	0.00	ELPC
PDR069	67.21	0.04	0.00	ELPC
PDR070	88.93	0.15	0.00	ELPC
PDR071	45.28	0.01	0.00	ELPC
PDR073	4.47	0.00	0.00	ELPC
PDR074	99.89	0.09	0.00	ELPC
PDR075	72.01	0.06	0.00	ELPC
PDR076	19.51	0.01	0.00	ELPC
PDR077	40.13	0.02	0.00	ELPC
PDR078	92.43	0.17	0.00	ELPC
PDR079	12.67	1.53	0.00	ELPC
PDR082	99.17	1.55	0.00	ELPC
PDR086	3.33	1.67	0.00	ELPC
PDR087	0.72	0.39	0.00	ELPC
SRS007	68.32	0.27	0.00	ELPC
SRS008	52.52	0.01	0.00	ELPC
SRS009	0.78	0.01	0.00	ELPC
SRS010	58.73	0.01	0.00	ELPC
SWC003	7.27	0.00	0.00	ELPC
SWC004	97.07	2.88	0.00	ELPC
SWC006	66.52	0.93	0.00	ELPC
SWC007	0.42	0.00	0.00	ELPC
SWC008	62.00	1.41	0.00	ELPC
SWC011	67.47	0.00	0.00	ELPC
SWC013	66.94	1.31	0.00	ELPC
SWC017	3.17	36.43	0.00	ELPC
SWC017	39.84	0.00	0.00	ELPC
SWC020	99.62	0.01	0.00	ELPC
SWC051	36.33	0.01	0.00	ELPC
SWC052	30.59	0.04	0.00	ELPC
SWC053	4.81	1.01	0.00	ELPC
SWC055	97.98	0.01	0.00	ELPC
SWC056	2.62	0.01	0.00	ELPC
344 (030	2.02	0.01	0.00	ELPC

SWC058	60.51	0.01	0.00	ELPC
SWC059	73.66	0.64	0.00	ELPC
SWC060	21.36	0.01	0.00	ELPC
SWC062	5.70	0.12	0.00	ELPC
SWC066	2.80	0.11	0.00	ELPC
SWC067	18.02	0.00	0.00	ELPC
SWC068	5.28	0.00	0.00	ELPC
SWC071	46.23	0.24	0.00	ELPC
TAM011	16.53	0.00	0.00	ELPC
TAM012	70.31	0.30	0.00	ELPC
TAM013	1.22	0.00	0.00	ELPC
TAM014	31.68	0.01	0.00	ELPC
TAM015	82.27	0.06	0.00	ELPC
TAM016	25.56	0.00	0.00	ELPC
TAM017	0.02	0.00	0.00	ELPC
TAM018	11.04	0.00	0.00	ELPC
TAM019	0.38	0.00	0.00	ELPC
TAM020	88.52	0.04	0.00	ELPC
TAM092	3.61	0.00	0.00	ELPC
TAM094	3.05	0.00	0.00	ELPC
TAM095	76.34	0.08	0.00	ELPC
TAM097	19.92	0.00	0.00	ELPC
TAM098	63.72	0.16	0.00	ELPC
TAM099	19.66	0.11	0.00	ELPC
TAM102	43.82	0.00	0.00	ELPC
TAM103	36.38	0.00	0.00	ELPC
TAM104	89.57	0.07	0.00	ELPC
TAM105	73.28	0.02	0.00	ELPC
TAM107	55.37	0.04	0.00	ELPC
TAM108	74.66	0.16	0.00	ELPC
TAM109	35.93	0.00	0.00	ELPC
TAM110	42.82	0.47	0.00	ELPC
TAM171	47.30	0.12	0.00	ELPC
TAM172	72.33	0.96	0.00	ELPC
TAM173	3.48	0.00	0.00	ELPC
TAM174	88.21	0.35	0.00	ELPC
TAM175	22.11	0.28	0.00	ELPC
TAM176	12.61	0.01	0.00	ELPC
TAM177	26.85	0.05	0.00	ELPC
TAM178	1.55	0.00	0.00	ELPC
TAM179	95.50	13.79	0.00	ELPC
TAM180	95.97	0.08	0.00	ELPC
TAM181	76.63	25.34	0.00	ELPC
TAM182	59.62	1.03	0.00	ELPC
TAM183	24.45	0.06	0.00	ELPC
TAM184	3.41	0.17	0.00	ELPC
TAM185	23.92	0.98	0.00	ELPC
TAM187	82.25	0.99	0.00	ELPC
TAM188	67.39	0.05	0.00	ELPC
TAM189	80.44	0.29	0.00	ELPC
203	30.11	5.23	5.50	LL. C

TAM190	94.75	1.82	0.00	ELPC
TAM191	2.61	0.17	0.00	ELPC
TAM192	82.95	1.80	0.00	ELPC
TAM193	5.02	1.29	0.00	ELPC
TAM194	37.85	0.09	0.00	ELPC
TAM195	28.90	1.11	0.00	ELPC
TAM196	44.66	0.21	0.00	ELPC
TAM197	68.83	2.73	0.00	ELPC
TAM198	71.74	1.49	0.00	ELPC
TAM199	45.75	0.60	0.00	ELPC
TAM200	11.22	0.35	0.00	ELPC
TRC002	70.47	0.13	0.00	ELPC
TRC003	98.80	0.31	0.00	ELPC
TRC006	91.31	0.82	0.00	ELPC
UT00415	17.63	0.00	0.00	ELPC
UT00416	58.50	0.01	0.00	ELPC
UT00422	8.91	0.01	0.00	ELPC
UT00424	0.49	0.00	0.00	ELPC
UT00426	20.19	2.26	0.00	ELPC
UT00427	87.55	0.01	0.00	ELPC
UT00428	0.14	0.00	0.00	ELPC
UT00434	0.18	0.47	0.00	ELPC
UT00438	1.27	0.00	0.00	ELPC
UT00547	10.86	0.02	0.00	ELPC
UT00548	90.01	0.01	0.00	ELPC
UT00549	97.26	0.31	0.00	ELPC
UT00550	97.73	0.16	0.00	ELPC
UT00551	14.10	0.01	0.00	ELPC
UT00555	98.47	0.00	0.00	ELPC
UT00562	40.67	0.39	0.00	ELPC
UT00567	98.19	0.00	0.00	ELPC
UT00567	86.77	0.03	0.00	ELPC
UT00573	81.62	0.00	0.00	ELPC
UT00577	61.34	0.00	0.00	ELPC
UT00582	89.96	0.00	0.00	ELPC
UT00583	74.83	0.05	0.00	ELPC
UT00584	0.04	0.00	0.00	ELPC
UT00585	54.02	0.02	0.00	ELPC
UT00639	98.47	0.02	0.00	ELPC
UT00640 UT00778	98.78	0.01 0.01	0.00 0.00	ELPC ELPC
0100776	96.82	0.01	0.00	ELPC
The following specimens	are assigned to group	El Daco 2		
ID. NO.	ELPC	ELP2	Loop	Group
ATT049	0.02	69.96	0.00	ELP2
ATT168	0.02	92.21	0.00	ELP2
ATT108 ATT172	0.00	41.57	0.00	ELP2
ATT172 ATT180	0.00	22.71	0.00	ELP2
ATT185	0.01	97.25	0.00	ELP2
ATT203	0.12	77.29	0.00	ELP2
	0.12		0.00	

ATT227	0.02	27.73	0.00	ELP2
ATT245	0.02	20.06	0.00	ELP2
ATT252	0.31	93.38	0.00	ELP2
ATT254	1.55	99.80	0.00	ELP2
ATT259	0.09	82.43	0.00	ELP2
ATT266	3.17	89.36	0.00	ELP2
ATT277	0.00	31.48	0.00	ELP2
ATT285	22.69	94.80	0.00	ELP2
ATT314	0.30	85.21	0.00	ELP2
BRE201	0.00	4.09	0.00	ELP2
EP074	0.21	8.41	0.00	ELP2
EP120	0.89	5.01	0.00	ELP2
MRM278	0.06	55.99	0.00	ELP2
MRM279	0.17	71.78	0.00	ELP2
MRM281	0.16	17.44	0.00	ELP2
OT042	0.65	77.64	0.00	ELP2
OT057	0.26	98.72	0.00	ELP2
OT059	0.00	84.22	0.00	ELP2
OT061	0.00	25.45	0.00	ELP2
OTP01X	0.00	21.31	0.00	ELP2
OTP05X	0.81	7.89	0.00	ELP2
SRS011	0.26	59.50	0.00	ELP2
SWC012	7.03	16.11	0.00	ELP2
SWC014	2.01	26.69	0.00	ELP2
SWC019	0.23	67.01	0.00	ELP2
SWC057	0.11	5.08	0.00	ELP2
SWC061	0.00	23.31	0.00	ELP2
SWC063	0.00	1.02	0.00	ELP2
UT00418	0.81	5.94	0.00	ELP2
UT00419	0.03	17.22	0.00	ELP2
UT00421	0.00	18.10	0.00	ELP2
UT00425	0.16	26.87	0.00	ELP2
UT00430	0.00	72.82	0.00	ELP2
UT00644	2.82	81.42	0.00	ELP2
The following specimens are				
ID. NO.	ELPC	ELP2	Loop	Group
ANI043	0.00	0.01	69.15	Loop
ANI045	0.00	0.05	55.53	Loop
ANI049	0.00	0.00	8.97	Loop
ATT073	0.01	0.04	90.80	Loop
ATT222	0.02	0.02	27.40	Loop
ATT235	0.00	0.00	81.98	Loop
ATT256	0.00	0.01	0.67	Loop
ATT270	0.00	0.00	0.77	Loop
EP002	0.00	0.09	32.72	Loop
EP003	0.00	0.02	42.50	Loop
EP006	0.00	0.01	91.61	Loop
EP007	0.00	0.00	1.09	Loop
EP008	0.00	0.01	90.97	Loop

EP009	0.00	0.14	98.45	Loop
EP011	0.00	0.00	99.75	Loop
EP012	0.00	0.14	23.88	Loop
EP014	0.03	0.25	95.61	Loop
EP015	0.00	0.12	69.00	Loop
EP016	0.00	0.01	99.32	Loop
EP018	0.00	0.01	85.60	Loop
EP022	0.00	0.00	71.77	Loop
EP027	0.00	0.04	91.93	Loop
EP028	0.00	0.00	84.83	Loop
EP029	0.00	0.08	75.73	Loop
EP030	0.00	0.00	19.29	Loop
EP033	0.00	0.03	16.27	Loop
EP034	0.00	0.00	33.96	Loop
EP036	0.00	0.00	1.51	Loop
EP037	0.00	0.00	1.20	Loop
EP038	0.00	0.00	72.75	Loop
EP039	0.00	0.00	47.86	Loop
EP040	0.00	0.00	94.51	Loop
EP041	0.00	0.00	20.01	Loop
EP042	0.00	0.03	73.94	Loop
EP043	0.00	0.01	48.53	Loop
EP044	0.00	0.00	32.01	Loop
EP063	0.00	3.10	0.06	Loop
EP065	0.01	0.04	53.32	Loop
EP066	0.00	0.00	80.29	Loop
EP071	0.00	0.00	10.03	Loop
EP080	0.00	1.81	3.29	Loop
EP086	0.00	0.00	0.57	Loop
EP092	0.00	0.01	95.33	Loop
EP094	0.00	0.00	43.36	Loop
EP095	0.00	0.00	87.09	Loop
EP100	0.00	0.00	9.99	Loop
EP103	0.00	0.00	21.31	Loop
EP110	0.31	0.00	92.28	Loop
EP111	0.00	0.00	26.73	Loop
EP113	0.00	0.02	0.51	Loop
EP118	0.00	0.01	70.37	Loop
EP121	0.00	0.00	91.91	Loop
EP123	0.00	0.00	77.62	Loop
EP124	0.00	0.00	40.81	Loop
EP126	0.00	0.00	88.46	Loop
EP127	0.00	0.00	75.68	Loop
EP128	0.00	0.00	91.27	Loop
EP129	0.00	0.00	72.55	Loop
EP130	0.00	0.00	90.72	Loop
EP131	0.00	0.00	34.22	Loop
EP132	0.00	0.01	0.08	Loop
EP135	0.00	0.00	15.88	Loop
EP137	0.00	0.00	43.20	Loop
· - ·				

EP138	0.00	0.00	14.64	Loop
EP140	0.00	0.00	71.03	Loop
EP143	0.00	0.01	59.06	Loop
EP144	0.00	0.00	24.17	Loop
EP145	0.00	0.00	85.10	Loop
EP147	0.00	0.01	89.11	Loop
EP148	0.00	0.00	64.12	Loop
EP150	0.00	0.00	83.46	Loop
EP151	0.00	0.01	65.92	Loop
EP152	0.00	0.03	99.84	Loop
EP154	0.00	0.09	81.67	Loop
TAM091	0.00	0.02	3.44	Loop
UT00431	0.00	0.01	42.47	Loop
UT00437	0.00	0.00	14.32	Loop

Appendix E:

NAA data and Descriptive Information

ANID	macro arp	Chem2012	CERAMIC TYPE	MATERIAL	SOURCE	ESTATE	SITE NAME	SITE NO	AS	ΓA	Π	ND	SM	П	YB	CE CO	CR
ANI001	Group-B	Unas.	Mimbres Corrugated	Pottery	MURR	ΣN	Beargrass Site	LA 121158	1.76	58.22 0	0.6672	53.60	9.98	8.74 3.9	3.94 130.73	3 11.28	87.99
AN1002	Group-A	Mimbres-10	Alma Rough	Pottery	MURR	MN	Beargrass Site	LA 121158	2.28	58.37 0	0.9583	57.14 12	12.77 5.	5.98 6.3	6.36 141.73	3 5.10	37.05
AN1003	Group-C1	Mimbres-21	Mimbres B/W Style II	Pottery	MURR	NM	Beargrass Site	LA 121158	2.02	39.57 0	0.3944	33.85 6	6.20 2.	2.10 2.	2.76 82.05	5 9.58	54.95
ANI004	Group-A	Mimbres-10	Alma Rough	Pottery	MURR	MN	Power Site	LA 121210	0.00	78.68		86.11 19	19.89 12.	12.46 7.9	7.99 133.18	8 3.63	35.24
AN1005	Group-A	Mimbres-10	Alma Rough	Pottery	MURR	NM	Power Site	LA 121210	3.13					9.40 6.		1 4.92	34.72
ANI006	Group-A	Mimbres-10	Alma Rough	Pottery	MURR	ΣN	Power Site	LA 121210	0.00	81.76	1.1880		19.42 11.90		8.30 122.22		
ANI007	Group-A	Mimbres-10	Alma Rough	Pottery	MURR	ΣN	Power Site	LA 121210	3.32	72.50	1.0618	87.27 18		11.66 6.0	6.69 126.27	7 4.33	39.69
ANI008	Group-B	Unas.	Alma Rough	Pottery	MURR	NM	Power Site	LA 121210	7.05		0.7050	43.73 9	9.97 5.	5.13 5.5	5.59 95.42	2 11.41	67.25
ANI009	Group-A		Clay	Clay	MURR	NM	Clay 1999 #4	Clay 1999 #4	2.70					5.08 6.3	6.28 165.89	9 12.01	41.69
ANI010	Group-A	Mimbres-10	Clay	Clay	MURR	MN	Clay 1999 #19	Clay 1999 #19	. 00'0	107.32 0				5.15 7.	7.10 211.81	1 8.38	37.59
ANI011	Group-B1	Mimbres-05A	Mimbres B/W Style II	Pottery	MURR	MN	LA 121158	LA 121158	2.49	62.27 0	0.5982	60.57 11	11.23 4.	4.99 3.8	3.86 107.97	7 13.40	65.87
ANI012	Group-C2	Unas.	Alma Plain	Pottery	MURR	MN	LA 006829	LA 006829	2.76	52.54 0	0.3698	64.53 9	9.66 2.	2.37 2.9	2.93 117.14	4 12.75	34.97
ANI013	G-dno-D	El Paso Core	El Paso Brown	Pottery	MURR	ΣN	LA 006829	LA 006829	4.50	59.15 0		51.67 9	9.39 4.	4.41 3.0	3.65 117.75	5 6.65	24.77
ANI014	Group-D	El Paso Core	El Paso Polychrome	Pottery	MURR	MN	LA 006829	LA 006829	5.31	69.20 0	0.5726	65.07 11	11.24 4.	4.32 4.02	129.56	6 4.79	24.01
ANI015	Group-D	El Paso Core	El Paso Polychrome	Pottery	MURR	MN	LA 006829	LA 006829	4.26	80.82 0	0.6234	68.67 12	12.31 3.	3.44 4.9	4.54 128.71	1 6.15	25.95
ANI016	Group-D	El Paso Core	El Paso Polychrome	Pottery	MURR	NM	LA 006829	LA 006829	5.46		0.6335		11.03 4.	4.94 4.61	51 138.13	3 5.74	
ANI017	Group-D	El Paso Core	El Paso Bichrome	Pottery	MURR	NM	LA 006829	LA 006829	4.54	75.94 0			11.76 3.		4.36 148.90	0 8.03	29.04
ANI018	Group-D	El Paso Core	El Paso Bichrome	Pottery	MURR	MN	LA 006829	LA 006829	7.26	76.14 0	0.6319	68.30 12	12.55 4.	4.80 4.	4.72 141.19	6.74	26.91
ANI022	Group-C1	Mimbres-21	Mimbres B/W Style III	Pottery	MURR	ΑZ	AZ BB:16:35	AZ BB:16:35	5.18	42.17 0	0.3546	33.09 6	6.36 1.	71 2.8	2.85 84.93	3 10.06	53.96
ANI023	Group-B1	Mimbres-05A	Mimbres B/W Style III	Pottery	MURR	ΑZ	AZ EE:2:44	AZ EE:2:44	3.38	45.00 0	0.5367	39.23 8	8.94 4.	4.27 4.	4.12 100.46	10.44	50.14
ANI024	Group-C1	Mimbres-21	Mimbres B/W Style III	Pottery	MURR	ΑZ	Last Water Ruin	AZ U:15:127	2.43	37.00 0	0.3504	30.91 6	6.37 2.	2.46 2.77	77 74.12	2 8.32	43.82
ANI025	Group-C2a	Mimbres-49A	Mimbres B/W Style III	Pottery	MURR	ΑZ	Last Water Ruin	AZ U:15:127	4.34	43.85 0	0.4775	37.77 8	8.13 2.	2.20 3.77	77 86.92	2 16.23	69.46
ANI026	Group-C1	Mimbres-21	Mimbres B/W Style III	Pottery	MURR	ΑZ	Last Water Ruin	AZ U:15:127	2.37	36.40 0	0.2718	27.94 5		1.67 2.17	17 73.56		56.82
ANI027	Group-C2a		Mimbres B/W Style III	Pottery	MURR	AZ	Last Water Ruin	AZ U:15:127	4.60	46.28 0				2.50 3.8			
ANI028	Group-C1	Mimbres-24	Mimbres B/W Style III	Pottery	MURR	ΑZ	AZ CC:12:48	AZ CC:12:48	5.01				8.42 2.		3.50 83.61	1 13.75	
ANI029	Group-C1	Mimbres-21	Mimbres B/W Style III	Pottery	MURR	ΑZ	AZ BB:16:41	AZ BB:16:41	2.05	_						_	
AN1030	Group-C1	Mimbres-21	Mimbres B/W Style III	Pottery	MURR	ΑZ	AZ BB:16:41	AZ BB:16:41	1.81								
ANI031	Group-B	Unas.	Mimbres B/W Style III	Pottery	MURR	ΑZ	AZ CC:10:99	AZ CC:10:99	3.01							0 10.64	
ANI043	G-dno-D	Loop 375	El Paso Polychrome	Pottery	MURR	ĭ	41EP01673	41EP01673	13.70	_		72.29 14		4.08 10.30	30 141.86		45.69
ANI045	Group-D	Loop 375	El Paso Polychrome	Pottery	MURR	ĭ	41EP01675	41EP01675	12.94	62.37		61.14 12	12.89 4.	4.20 8.8	8.83 118.23	3 7.99	51.68
ANI046	G-dno-D	Loop 375	Mimbres B/W Style Indeter.	. Pottery	MURR	×	41EP01676	41EP01676	12.65			_			1		
ANI048	Group-B	Unas.	Mimbres Corrugated	Pottery	MURR	ĭ	41EP01678	41EP01678	4.96	-						_	
ANI049	G-dno-D	Loop 375	El Paso Polychrome	Pottery	MURR	ĭ	41EP01679	41EP01679	10.98					7.36 13.28			
ANI050	Group-D	El Paso Core	El Paso Bichrome	Pottery	MURR	X	41EP01680	41EP01680	5.87	66.94 0	0.7037	57.07 10	10.57 4.	4.79 5.	5.14 137.08	8 8.94	39.59
ANI051	Group-D	El Paso Core	El Paso Bichrome	Pottery	MURR	X	41EP01681	41EP01681	4.51		0.8071	75.23 13	13.77 3.	3.88 5.8	5.86 168.76		
ATT001	Group-B	Unas.	Alma Plain	Pottery	MURR	×	41HZ00358	41HZ00358	5.66	94.99 0	0.5502	67.48 10	10.60 3.	3.40 4.2	4.29 174.97	7 2.54	11.44
ATT002	G-dno-D	El Paso Core	South Pecos Brown	Pottery	MURR	ĭ	41HZ00358	41HZ00358	3.76	76.39 0	0.5869	63.40 11	11.86 5.	5.01 4.3	4.31 148.68	8 7.26	27.16
ATT005	Group-D	El Paso Core	El Paso Brown	Pottery	MURR	ΧI	41HZ00573	41HZ00573	3.77	72.43 0	0.6336	55.35 10	10.25 5.	5.68 4.3	4.35 128.80	0 8.32	23.26
ATT006	Group-D	El Paso Core	El Paso Brown	Pottery	MURR	×	41HZ00573	41HZ00573	4.43	77.45 0		62.70 11	11.65 2.	2.64 4.9	4.57 133.52	7.67	27.52
ATT010	Group-D	El Paso Core	El Paso Brown	Pottery	MURR	X	41HZ00573	41HZ00573	4.13			60.98 10		3.10 4.3	4.23 137.72		28.98
ATT012	Group-D	El Paso Core	Jornada Brown	Pottery	MURR	X	41HZ00573	41HZ00573	2.73	77.96 0	0.5709	62.00 11	11.55 4.	4.58 4.	4.16 152.19	9 6.04	20.82
ATT013	G-dno-D	El Paso Core	Jornada Brown	Pottery	MURR	ĭ	41HZ00573	41HZ00573	4.57							1	
ATT014	G-dno-D	El Paso Core		Pottery	MURR	ĭ	41HZ00573	41HZ00573	4.40								
ATT015	Group-D	El Paso Core	Jornada Brown	Pottery	MURR	×	41HZ00573	41HZ00573	4.66	68.22 0	0.4510	52.49 10	10.11 2.	2.88 3.4	3.44 134.73	3 10.04	25.76

>	61.08	67.52	52.20	62.02	62.17	53.88	70.18	104.25	70.38	69.57	130.37	72.64	72.88	75.41	87.11	97.92	96.59	90.74	55.20	71.96	41.87	88.07	82.78	94.88	83.38	67.01	57.64	91.76	89.86	96.22	90.07	74.33	80.27	71.39	82.89	20.07	95.10	107.15	76.04	77.55	68.83	72.60	94.42	84.76
I	3132.2	3269.6	2488.8	2589.7	2511.0	3266.8	3016.4	4731.3	4104.0	3390.2	5135.7	4504.7	4308.9	5847.4	6333.7	5751.0	5061.4	6330.6	3013.6	4889.9	2472.6	4638.3	2475.8	4767.8	4094.3	2700.1	2506.5	4682.3	3405.5	3779.5	3770.7	4282.6	3416.2	3667.1	6350.0	1993.2		_	3915.7	5574.4	4147.8	4095.7	4403.7	4411.3
NA	13696.7	15757.1	17192.0			11155.7	10193.2	12792.6	15237.3	11425.4	13208.4	17472.1	18214.4	16359.9	15706.6	13153.1	14238.7	15918.2	17805.7	13471.8	17273.7	16098.0	21425.1	15974.4	19483.5	19485.4	•	~	9821.5	8470.0	11599.5	13895.3	11398.4	13978.6	18238.6	14432.2	22461.4	13737.6	15970.3	13166.8	25756.9	23581.7	23933.1	23890.7
M	563.9	208.9	1099.0	125.1	158.6	148.3	141.8	624.4	875.4	242.7	784.5	581.7	497.1	488.7	446.5	541.8	269.7	542.2	927.5	598.9	885.4	0.608	1180.2	0.667	468.3	1075.8	1224.8	927.6	238.2	345.0	314.1	590.5	274.4	859.1	593.5	170.9	803.3	571.8	460.1	577.7	604.9	637.8	620.0	624.7
\prec	28694.3	31012.3	32831.0	32714.5	30680.7	29369.9	29692.1	28011.2	35923.6	30278.2	22484.2	26261.5	30594.6	31008.7	28068.0	26923.3	30556.1	26745.4	30697.5	32357.9	30159.2	28974.6	23434.0	31665.7	24240.1	28736.4	23741.4	31790.2	26683.5	25001.8	25448.2	30006.9	27790.0	27415.4	27929.8	42551.3	25738.4	29238.6	28101.5	32478.8	28407.9	24779.2	25814.3	24755.2
Dγ	6.797	11.409 3	4.104 3	14.104 3		16.162 2	12.456 2	8.506 2	10.853 3	14.233 3		5.980 2	6.228	7.724 3	9.631		8.851 3	9.153 2	4.464 3	8.019	4.848	6.528 2	3.149 2	6.459 3	6.088 2				15.287 2				_			6.461 4			7.380 2					6.003 2
CA	12686.9	6.7766	12956.4				8970.2	8973.1	31317.7	9771.8		16366.9	16223.8	13671.7	13693.4	13743.2	14103.2	15158.1	9.6986	12322.1	11582.2	30488.0	12229.6	28565.7	15396.3	13560.5	12294.3		•	`	`			12030.0	13558.9	7371.8	15986.4	10610.7	15317.3	15241.6	14636.5	13503.7	12144.7	11993.3
BA	1071.8	835.3	913.0	751.2	671.1	696.4	672.7	834.0	597.3	482.7	525.2	1184.4	959.4	1250.5	1444.9		738.0	1365.2	1042.5	1.779	713.7	732.5	1117.9		793.5			744.2	2.986	1000.2	708.9			920.0	942.6	756.8	1522.7	1018.9	1276.3	1212.1	1236.4	1310.3	1289.8	1303.5
AL	92999.7	90975.1	91118.4	91848.0	90771.4	86178.6	88907.4	87129.0	77371.5	91232.9	92031.2	88698.0	86861.4	85939.8	83325.1		94624.5	92024.1	98523.8 1	85877.3	86123.9	85351.9	93590.2	81471.5	02687.9	98164.5	87830.4	88628.3					80321.2	75314.7	78358.6			92690.8	•					77334.3 1
ZR	193.5	240.7	174.2	259.3	177.0	248.4	224.3	255.9	237.9	177.3	204.2	271.8	282.4	399.0	324.3	444.3	351.9	512.2	158.3	198.0	153.0	195.9	146.5	203.1	_	160.2	148.0	199.5	348.6	395.6			375.0	419.2	362.7	279.1	317.3	332.1	369.1			280.5	315.9	236.0
NZ	88.3	9.6/	120.6	102.9	109.1	95.1	93.5	78.3	120.0	108.8	92.8	133.3	61.3	78.8	71.8	84.1	78.3	79.5	9.68	8.69	74.7	88.8	87.3	94.8	85.7	81.1	80.9	94.3	79.3	85.3	85.2	82.2	75.4	80.9	65.5	78.0	81.7	79.0	68.4	82.7	6.69	65.7	67.8	64.6
H	23.17	29.73	10.51	40.47		33.24	36.00	25.04	36.78	40.64	14.57	10.99	17.73	15.44	20.80	18.96	24.26	26.17	11.08	15.36	66.6	12.94	8.61		11.54				22.13			15.92	25.22					27.99	18.05	15.63		15.85		15.06
TA TB	7 1.26	5 1.94	6 0.73	0 2.67		5 2.67	0 2.38	8 1.55	4 1.96	4 2.64	4 1.50	5 1.15	5 1.21	1 1.40	1.57	9 1.39	4 1.62	1 1.49	5 0.81	5 1.20	8 0.84	4 1.08	0 0.65	6 1.09	7 1.11	.2 0.69	4 0.66									2 1.30	7 1.80	8 1.18	0 1.51	1.48	3 1.44		_	1.35
	3 1.2987	7 2.8145	3 0.8876			1.5905	1.4180	1.6708	3 1.2814	5 2.1244			5 2.8305	1 2.3211	1 2.5699	7 2.4119	3.3.1864	3.2271	0.9235	1.2455	3 0.8218	3 1.2674	0089.0	3 1.3336														3.4588	3 2.1990	1.9002	3.1663			7 2.8981
SR	390.8	153.7	475.3	121.8	141.2	116.5	180.4	154.2	152.3	84.6	359.9	755.8	462.6	378.4	433.4	388.7	502.8	486.7	317.0	303.1	355.8	491.3	444.0			384.8				187.0									384.8					406.7
SC	11.89	12.73	7.63	10.96		11.39	12.00	12.36	11.59	11.54	14.81	7.71	8.16	9.33	10.05	11.79	11.42	11.35	7.62	11.65	6.41	12.27	8.47		11.54				10.90			_					7	9.10	9.35					12.03
SB	0.3924	0.3336	1.4885	0.3017	0.4030	0.3539	0.3422	0.5831	0.3600	0.4242	0.3948	0.3034	0.6069	0.4541	0.3829	0.5534	0.4914	0.4816	2.5418	0.7190	2.3239	0.6328	1.5375	0.7047	0.6775	1.4133	1.1852	1.0865	0.8660	0.9011	0.9590	0.4565	0.9057	0.7810	0.4537	0.2567	0.4806	0.4671	0.5034	0.3493	0.4299	0.6004	0.5504	0.5389
RB	162.12	188.05	142.47	196.31	196.38	184.63	180.61	124.00	228.06	235.47	117.47	92.26	119.22	84.77	100.26	84.78	114.61	105.50	152.84	133.31	132.91	130.68	119.49	133.61	124.57	129.58	116.63	151.28	133.63	142.07	157.12	129.48	154.18	137.98	103.69	131.32	91.33	107.76	111.83	114.24	95.55	85.52	84.75	89.69
Z	9.77	62.1				0.0	0.0	0.0	0.0	0.0	100.0	36.6	0.0	0.0	38.8		48.8	0.0	38.3	34.5	38.2	0.0	30.3	51.0		0.0					_						0.0			50.7	44.5	6.09	54.9	45.9
±	7.02	6.97	7.24	7.22	6.35	7.86	7.39	11.42	13.52	6.44		11.39	11.77	15.05	12.84	16.83	13.55	19.48	7.23	8.78	6.81	8.85	6.63	8.78	7.33	7.09	7.08	9.23	14.62	15.87	17.79	8.63	19.12	15.87	13.76	11.28	12.26	13.41	14.97	12.98	11.04	9.46	11.45	9.19
FE	34785.1	30344.8	27101.4	27517.0	31639.4	28276.9	31226.2	44566.2	36026.5	31666.4	42021.7	36758.1	36484.2	37025.6	40607.0	42411.6	47125.8	50083.0	27827.9	28221.1	24540.0	40410.3	32787.1	40015.3	37678.3	29144.1	26316.3	36569.7	42920.8	45567.0	44215.2	37697.0	38580.9			27590.4		46379.5	35651.6	42018.8	28326.4	32098.6	32303.1	32065.6
EN	1.9026	2.0820	1.2194			2.2338	2.0173	1.4942	1.6501	2.2595	2.0111	2.1119	1.8651	2.4264	2.4031		2.3295	2.4009	1.3884	1.5140	1.2459	1.5087	1.2698	1.5634		1.3453			1.7405				_					1.8090	2.1478		2.9149			2.5321
CS	10.11	6.62	17.69 1		7.17	7.20 2	7.71	5.59	4.68	9.69	5.89 2	2.34 2	3.88	2.71 2	2.82		3.83 2	3.37 2	20.25	7.19	18.70	7.52	19.33												3.05 2	5.60 1		2.94	3.19 2		3.93 2			3.92 2
ANID	ANI001	ANI002	ANI003	ANI004	AN1005	ANI006	AN1007	ANI008	ANI009	ANI010	ANI011	ANI012	ANI013	ANI014	AN1015	ANI016	ANI017	ANI018	ANI022	ANI023	ANI024	ANI025	AN1026	ANI027	AN1028	ANI029	AN1030	ANI031	ANI043	ANI045	ANI046	ANI048	ANI049	AN1050	ANI051	ATT001	ATT002	ATT005	ATT006	ATT010	ATT012	ATT013	ATT014	ATT015

ANID	macro grp	p Chem2012	CERAMIC TYPE	MATERIAL	SOURCE	STATE	SITE NAME	SITE NO	AS	ΓA	ΠΠ	ND	SM	n	YB CE	00	CR
ATT019	G-dno-D	El Paso Core		Pottery	MURR	×	41HZ00573	41HZ00573	7.57	52.21	0.5261	45.26 8	8.33 4.	4.16 3.	3.78 101.80	5.15	26.29
ATT020	Group-B2	Mimbres-11	Mimbres B/W Style Indeter.	Pottery	MURR	X	41HZ00573	41HZ00573	2.37	39.12	0.5479	28.34 5	5.60 5.	5.46 3.7	3.23 76.18	3 8.97	40.75
ATT021	Group-B2	Mimbres-11	Mimbres B/W Style Indeter. Pottery	Pottery	MURR	ΤX	41HZ00573	41HZ00573	2.31	38.61	0.4838	28.92 5	5.44 5.	5.22 3.0	3.09 73.66	5 8.44	40.15
ATT022	Group-B	Unas.	Mimbres B/W Style Indeter. Pottery	Pottery	MURR	Ϋ́	41HZ00573	41HZ00573	2.59	50.55 0	0.5865	31.08 5	5.79 6.	6.59 3.3	3.39 98.00	5.17	24.99
ATT024	G-dno.D	El Paso Core		Pottery	MURR	TX	41HZ00573	41HZ00573	6.95								26.09
ATT028	G-dnoJ9	El Paso Core		Pottery	MURR	X	41HZ00357	41HZ00357	7.41		0.6068				4.22 113.38		33.25
ATT029	G-dnoJ9	El Paso Core		Pottery	MURR	ΤX	41HZ00357	41HZ00357	9.42	54.74 C	0.6092	48.47 9	9.37 4.	4.99 4.3	4.32 107.37	7 7.00	39.58
ATT030	G-dnoJ9	El Paso Core	rome	Pottery	MURR	ΤX	41HZ00357	41HZ00357	7.82			1		4.61 4.21		_	39.40
ATT034	G-dnoJ9	El Paso Core)	Pottery	MURR	TX	41HZ00357	41HZ00357	3.26	70.88					3.29 133.19	7.70	26.17
ATT038	G-dno19	El Paso Core	El Paso Brown	Pottery	MURR	TX	41HZ00357	41HZ00357	10.29	53.49 0				4.56 4.	4.12 106.71	1 6.49	37.29
ATT039	G-dno19	El Paso Core	El Paso Brown	Pottery	MURR	TX	41HZ00357	41HZ00357	9.70	56.01	0.5127	49.65	9.52 5.	5.05 4.3	4.30 110.40	0 6.82	37.00
ATT041	G-dno ₂	El Paso Core	El Paso Brown	Pottery	MURR	ΧŢ	41HZ00357	41HZ00357	6.72	70.59	0.5420	59.73 10	10.73 2.	2.97 4.0	4.05 131.61	96.6	37.02
ATT042	Group-B	Unas.	Alma Plain	Pottery	MURR	TX	41HZ00357	41HZ00357	4.53	92.09	0.3709		7.88 4.	4.72 2.3	2.28 96.65	5 7.41	40.19
ATT043	Group-A	Mimbres-10	Alma Plain	Pottery	MURR	TX	41HZ00357	41HZ00357	3.42	109.25 0	0.7893 1	119.60 21	21.91 3.	3.64 7.0	7.08 175.77	4.66	21.44
ATT044	Group-C2	Unas.	Alma Plain	Pottery	MURR	TX	41HZ00357	41HZ00357	5.46	39.22 C	0.2644		5.88 2.	2.67 2.	2.19 74.76	8.27	31.38
ATT049	G-dno-D	El Paso-2	8/Br)	Pottery	MURR	ΤX	41HZ00357	41HZ00357	7.19				_			1	69.90
ATT050	G-dno-D	El Paso Core		Pottery	MURR	ΤX	41HZ00357	41HZ00357	3.18								26.44
ATT051	Gronp-D	El Paso Core	South Pecos Brown	Pottery	MURR	TX	41HZ00357	41HZ00357	2.80	73.67		53.95 9	9.91 4.	4.34 3.9	3.92 149.30) 6.82	23.06
ATT052	Group-D	El Paso Core	Jornada Brown	Pottery	MURR	TX	41HZ00573	41HZ00573	6.83	49.56 C	0.3106	34.86 6	6.07 2.	2.64 2.3	2.35 75.75	5 5.27	29.13
ATT053	Group-D	El Paso Core		Pottery	MURR	TX	41HZ00573	41HZ00573	2.96	73.50 0			10.72 4.		4.41 136.78		25.58
ATT055	Group-D	El Paso Core	Jornada Brown	Pottery	MURR	TX	41HZ00573	41HZ00573	1.95	29.66	0.4530	44.84 9	9.06	4.32 3.3	3.38 122.86	5 10.49	19.35
ATT056	Group-D	El Paso Core	El Paso Brown	Pottery	MURR	TX	41CU00663	41CU00663	4.17	82.58 C		72.07 13	13.61 4.	4.46 5.3	5.33 167.56	5 8.12	28.33
ATT057	G-dno19	El Paso Core	Jornada Brown	Pottery	MURR	TX	41HZ00360	41HZ00360	3.83	99.99	0.3704	37.44 7	7.55 3.		2.84 122.12	2 8.40	27.28
ATT058	Gronp-D	El Paso Core		Pottery	MURR	TX	41CU00657	41CU00657	5.85						4.03 122.20		27.05
ATT059	G-dnoJ9	El Paso Core		Pottery	MURR	ΤX	41CU00657	41CU00657	5.91	83.45					4.14 150.47		28.32
ATT060	G-dno ₂ D	El Paso Core		Pottery	MURR	TX	41CU00657	41CU00657	3.55								25.91
ATT061	G-dno ₂ D	El Paso Core		Pottery	MURR	X	41CU00666	41CU00666	5.26			_					34.18
ATT062	G-dnoJ9	El Paso Core		Pottery	MURR	X	41CU00666	41CU00666	7.58			43.81 9			3.96 105.85		30.67
ATT064	G-dno-D	El Paso Core	El Paso Polychrome	Pottery	MURR	ΤX	41GA00061	41GA00061	6.91	88.79		61.13 11			4.54 171.78	3 12.95	25.67
ATT065	G-dno-D	El Paso Core		Pottery	MURR	TX	41GA00061	41GA00061	7.31			_				1	25.11
ATT066	G-dnoJ9	El Paso Core	_	Pottery	MURR	×	41CU00660	41CU00660	2.73								26.43
ATT067	G-dnoJ9	El Paso Core		Pottery	MURR	×	41CU00660	41CU00660	3.23	_		,			_		25.88
ATT069	G-dnoJ9	El Paso Core		Pottery	MURR	ĭ	41CU00660	41CU00660	4.86		-						27.14
ATT070	G-dno-D	El Paso Core		Pottery	MURR	ΤX	41CU00660	41CU00660	2.75								25.25
ATT071	G-dno-D	El Paso Core	_	Pottery	MURR	TX	41CU00660	41CU00660	3.16								26.52
ATT072	Gronp-D	El Paso Core		Pottery	MURR	TX	41CU00664	41CU00664	3.86	94.61 C			11.76 3.		4.82 154.18	3 7.90	29.88
ATT073	Gronp-D	Loop 375		Pottery	MURR	TX	41CU00664	41CU00664	9.12		1.0720	55.92 11	11.77 3.		8.89 116.96		40.68
ATT074	Group-D	El Paso Core	El Paso Polychrome	Pottery	MURR	TX	41CU00664	41CU00664	4.32	86.23 C		68.67 12	12.22 3.	3.87 5.17	,	5 7.84	30.43
ATT075	Group-D	El Paso Core		Pottery	MURR	TX	41CU00664	41CU00664	5.62	54.66 C	0.5120			3.20 3.	3.79 93.52	6.17	33.29
ATT076	Group-D	El Paso Core		Pottery	MURR	TX	41HZ00577	41HZ00577	5.02	83.13		69.17 12	12.29 4.	4.87 4.0	4.62 155.58		26.56
ATT077	G-dno.D	El Paso Core		Pottery	MURR	TX	41HZ00577	41HZ00577	4.73					5.07 4.0	4.63 157.51		26.72
ATT081	G-dno-D	El Paso Core		Pottery	MURR	TX	41HZ00577	41HZ00577	4.47								25.43
ATT083	G-dno-D	El Paso Core		Pottery	MURR	ΤX	41HZ00370	41HZ00370	6.64					4.40 4.			32.99
ATT084	G-dno-D	El Paso Core	El Paso Brown	Pottery	MURR	X	41HZ00370	41HZ00370	4.81	68.20 C	0.5242	51.97	9.44 4.	4.69 3.5	3.54 120.97	7 8.01	20.28

>	69.14	65.97	62.01	41.79	68.39	82.00	92.86	118.98	69.66	88.76	85.58	104.86	93.81	54.91	90.77	112.80	98.90	82.67	61.37	104.69	89.09	94.19	79.78	106.46	101.67	74.15	89.39	74.96	108.06	119.78	07.78	54.82	78.05	91.88	82.15	72.88	96.93	60.42	107.88	118.17	104.56	84.80	74.14
I	4727.0	3421.4	4388.1	2047.0	4530.5	4519.3	4813.9	7456.7	5691.2	4640.6	6266.5	6870.5	5273.3	2846.8	4362.3	4526.0	5359.5	4982.0	3543.8	5754.9	5030.4	5358.5	4784.8	5012.1	5885.5	4827.0	6939.0	4282.7	9005.9	8615.3	4047.1	3847 5	4372.5	5029.2	4906.6	3443.8	4527.3	3945.1	0.6979	8104.7	7200.3	5598.8	5316.4
NA	16404.3	13716.3	14216.0	13401.6	17189.3	15422.9	12473.8	16594.4	23181.4	13431.5	12444.0	20837.4	20177.8	10892.8	17961.4	11691.1	26275.9	29836.3	14655.2	13824.6	23538.3	13703.9	20353.7	16809.0	17042.3	16377.2	15516.9	12170.1	20431.2	20269.7	21/4/19	142061	23576.8	20274.7	13660.1	11288.6	13597.3	12005.7	17207.5	16218.1	16801.7	14933.5	14846.1
MN	541.0	1046.3	859.4	505.7	462.3	508.8	506.1	636.0	475.3	492.8	541.7	647.2	406.5	181.7	685.7	459.0	504.5	649.7	231.1	624.5	934.1	531.6	7.709	567.5	531.5	496.9	1039.8	502.4	7.897	9.662	593.2	201.2	450.4	528.7	690.2	305.0	720.1	403.5	682.3	758.1	829.4	539.8	460.3
¥	31546.9	27804.9	31004.2	26570.6	30818.3	29255.0	27042.9	27352.9	27457.5	28523.8	27979.8	28484.2	30545.8	41305.3	21035.6	30674.8	23916.8	31340.3	35072.4	31157.2	29520.8	29191.6	27392.7	28345.3	26998.9	29122.2	29413.1	30860.0	23856.9	27044.0	2/404.8	23432.0	30946.8	24930.0	25839.5	26133.3	29147.4	24521.5	28542.5	28707.1	33032.6	30753.7	28629.4
DΥ	5.435	3.279	3.995	4.075	950.9	6.141	6.454	7.037	5.210	6.719	908.9	7.455	4.324	14.226	3.342	6.647	5.724	950.9	4.040	7.462	5.926	8.822	4.373	6.879	7.289	6.323	8.999	5.554	6.364	7.309	7,007	7.002	6.404	8.583	8.273	11.782	8.327	800.9	7.075	7.153	6.724	6.850	5.635
CA	13802.0	12510.6	14190.7	13711.5	13321.5	15947.7	8824.0	16519.1	23487.4	20407.2	11128.7	16532.3	22370.1	8003.6	21907.8	14000.6	21694.0	9.79161	9680.4	11754.3	16267.7	13487.9	12099.1	15130.6	14903.3	12244.4	22304.3	15897.1	18837.9	18804.6	13311.1	19105 3	12637.4	14169.5	13128.2	10820.6	15005.1	31667.5	22378.1	16474.9	16587.8	12331.4	13803.3
BA	1336.3	710.3	654.2	713.2	1504.4	1046.6	916.6	1203.2	1349.9	1008.0	943.4	912.3	1603.3	945.0	1935.1	931.5	1409.1	1272.4	1267.2	944.0	1385.4	1053.5	1030.0	729.4	756.6	0.906	995.7	1101.0	127.6	592.7	9/3.6	727.3 1095.5	926.8	898.2	1018.0	731.0	1007.8	1291.6	1183.3	1285.7	1393.3	1418.9	1061.1
AL	9.06068	84109.2	83584.0	85501.3		87985.5	101836.7	90428.6	93201.5	91841.5	100072.3	89415.8	94678.1	83782.6	84959.6	89840.9	93587.0	87984.4	89690.1	86631.5	97130.9	90047.4	85307.0	9.96168	92362.0	87164.5	80446.9	97904.5	895//.1	86141.7	1/362.1	877987	89017.9	93412.3	77078.5	83223.9	77447.5	89201.5	89848.9	88002.8	-		98520.9
J ZR	5 303.1	2 190.2	3 165.4		7 257.9		316.1	368.7	3 282.6	3 329.9	311.1	305.8	5 203.9				3 225.7	1 344.7	1 263.8	2 280.7	3 225.5	384.2	5 276.7			_	_				434.7			_	2 517.8		2 527.1	7 233.2					7 269.1
NZ	77.6	66.2	61.8					91.0	8.99	80.3	80.9	94.8	172.6	71.1		82.3	66.3	73.4	80.1	75.2	82.8	81.9	77.6				—				91.5			ĺ	99.2	85.4	92.2						7.77
3 TH		5 19.48				19.70		3 19.85	5 13.79	19.61	3 20.65	4 21.91	0 20.91	5 52.34			13.29		18.59	34.26		2 21.09							_		30.50	_			1 15.85		3 15.10				_		3 27.82
TA TB	3 1.03	1 0.76	6 0.73	0 0.73	3 1.25	8 1.12	8 1.33	4 1.33	0 1.06	7 1.27	9 1.23	0 1.44	06.0 9	2 2.65	2 0.69	9 1.38	3 1.07	3 1.26	9 0.74	0 1.47	3 1.12	3 1.82	3 0.95	3 1.22	3 1.41					` '	1 1.93				9 1.61	1	2 1.58	7 1.30	,	•			9 1.08
	2.6183	1.7041			2.8643	3.0028		2.9504	2.5000	2.6807	2.7169	2.9520	2.8736		1.5832		2.4363	3.1553	1.8039	4.2450	3.2523	2.6003									3.4881				2.0709	3.1200	2.4712	2.1637					3.4299
SR	459.4	264.9	303.2	234.8	396.3	577.7	248.7	471.0	695.5	732.5	423.4	531.1	930.9	234.3	1119.1	452.1	802.9	435.8	310.8	280.4	462.9	295.9	432.6	282.8	303.3	391.3	366.6	386.6	385.4	444.2	3/8.5	351.7	322.1	368.4	307.0	277.1	288.0	369.1	345.3	356.2	439.3	304.6	310.2
SC	8.93	8.08	7.80	7.73	9.21	9.15	10.94	11.09	9.85	9.94	10.12	11.33	10.59	11.58	9.18	13.89	10.61	10.20	8.17	9.84	9.37	11.77	9.01	10.79	11.04	9.37	10.66	9.72	11.38	12.12	12.78	8 96	10.29	13.12	99.6	9.62	9.51	9.78	10.57	11.05	10.70	10.27	8.77
SB	0.5786	0.5740	0.6006	0.4746	0.5929	0.6002	0.8111	0.6628	0.6241	0.7802	0.7477	0.6253	1.5425	0.2716	0.5065	0.7243	0.6134	0.5611	0.6748	0.4559	0.4300	0.4435	0.6485	0.4916	0.4731	0.4734	0.5622	0.6390	0.4040	0.4452	0.5394	0.3440	0.5549	0.5007	0.5450	0.7848	0.5152	0.7340	0.3599	0.3822	0.3498	0.6113	0.5251
RB	109.37	175.36	176.72	178.81	113.68	124.30	146.42	109.59	99.85	125.08	145.87	111.42	91.32	269.84	87.36	135.41	86.99	97.01	136.14	112.45	101.91	112.85	104.41	91.97	93.71	88.80	109.74	126.93	115.20	116.10	111 54	173.42	122.72	103.07	93.54	155.47	90.83	118.08	112.12	102.44	116.24	112.42	113.82
Z	45.9	0.0		0.0	0.0	41.3	0.0	40.9	0.0	0.0	56.1	38.9	41.3	0.0	0.0	0.0	0.0	20.8	-27.9	0.0	0.0	36.2	31.8	0.0	39.7			0.0			0.0	_			42.0	0.0	54.0	47.6	0.0	38.8	_		0.0
生	12.59	7.87	7.26	5.79		13.04		14.33	68.6	13.37	13.17	12.82	8.21	12.36	6.38	10.64	8.84	11.43	9.47	11.73	7.98	14.55	6.67				18.06	11.91			14.5/	11.13	13.54		17.41	13.55	19.21		20.97	13.34	13.73	13.70	10.35
FE	37575.4	20477.2	19970.0	20661.2	37442.0	39183.0	49066.8	52178.8	29255.0	44536.4	45105.5	53266.3	23739.9	33049.1			35783.2	37334.1	33031.0	48173.6	42018.0	41171.2		48871.7			49517.6			58477.8	28460.6			29227.0		38629.2	43088.4	38953.0	53891.7	55071.7	54339.1	44033.6	41039.1
EU	1.5760	1.0733	1.0332	0.9052	1.7003	1.6455	1.7922	2.1687	2.2374	1.6787	1.7272	2.1588	1.9525	1.7620	1.5380	1.5345	2.2584	2.4968	1.2185	1.8995	2.3242	2.7046	1.9610	2.0854	2.3591	1.9797	2.5755	1.6445	2.0973	2.1164	3.1755	1 4510	2.3701	3.2094	2.6298	1.4192	2.6846	1.8141	2.5234	2.5492	2.88 2.5315	2.1161	1.6907
CS	3.46	7.16	96.9		3.89	4.08	9.60	4.22	3.73	4.59	6.15	4.31	4.11	11.02	4.01		3.70	3.64	4.34	3.28	3.77	3.13								_	5.27				3.39	4.77	3.21		2.97	3.10	2.88		3.04
ANID	ATT019	ATT020	ATT021	ATT022	ATT024	ATT028	ATT029	ATT030	ATT034	ATT038	ATT039	ATT041	ATT042	ATT043	ATT044	ATT049	ATT050	ATT051	ATT052	ATT053	ATT055	ATT056	ATT057	ATT058	ATT059	ATT060	ATT061	ATT062	A11064	ATT065	A11066	ATT069	ATT070	ATT071	ATT072	ATT073	ATT074	ATT075	ATT076	ATT077	ATT081	ATT083	ATT084

ANID	macro_grp	p Chem2012	CERAMIC TYPE	MATERIAL	SOURCE	STATE !	SITE_NAME	SITE_NO	AS	LA	Π	QN	SM	Π	YB (CE CO	CR
ATT085	G-dno-D	El Paso Core		Pottery	MURR		41HZ00247	41HZ00247	6.52	67.22	0.6230		10.43	3.57	4.63 133.40	40 7.81	
ATT086	G-dno19	El Paso Core	El Paso Brown	Pottery	MURR		41HZ00247	41HZ00247	98.6	54.28	0.5473	49.55	9.52	3.61	4.27 114.18	18 6.61	32.95
ATT087	G-dnoJ9	El Paso Core	El Paso Brown	Pottery	MURR	, Σ	41HZ00247	41HZ00247	9.38	53.91	0.5381	42.34	8.90	3.94	3.90 106.68	68 6.46	34.19
ATT088	G-dno ₂	El Paso Core		Pottery	MURR		41HZ00247	41HZ00247	11.28	58.86		50.49	9:36	4.52	4.02 116.24	24 8.14	
ATT089	G-dno ₂	El Paso Core		Pottery	MURR	, Σ	41HZ00247	41HZ00247	8.55	55.14	0.5729	48.11	9.27	4.03	4.14 113.94		34.83
ATT090	G-dnoJ9	El Paso Core	El Paso Polychrome	Pottery	MURR		41EP05486	41EP05486	5.56	58.69	0.5269	52.68	9.31	3.89	3.79 117.67	67 5.29	23.54
ATT091	Gronp-D	El Paso Core	El Paso Brown	Pottery	MURR		41EP05486	41EP05486	8.29	53.45		46.21	8.81	3.79	3.96 110.28		
ATT092	G-dno19	El Paso Core		Pottery	MURR		41EP05486	41EP05486	5.33	49.55	0.5141	46.53	8.46	4.05	3.83 101.03	03 4.94	26.72
ATT093	G-dnoJ9	El Paso Core		Pottery	MURR	, X	41EP05486	41EP05486	4.11	54.04	0.6111	49.84	9.70	3.88	4.17 110.26	26 5.10	27.65
ATT095	G-dnoJ9	El Paso Core	El Paso Polychrome	Pottery	MURR		41CU00307	41CU00307	6.49	84.29	0.6672	75.43	13.38	3.46	5.30 159.25	25 8.25	34.50
ATT097	G-dnoJ9	El Paso Core	Jornada Brown	Pottery	MURR	, X	41CU00307	41CU00307	4.56	75.81	0.5303	66.64	10.92	4.62	3.66 153.54	54 15.05	20.78
ATT098	G-dnoJ9	El Paso Core	El Paso Brown	Pottery	MURR	, X	41CU00307	41CU00307	5.31	17.71	0.6104	65.93	11.20	4.41	4.24 147.43	43 4.68	27.44
ATT099	G-dnoJ9	El Paso Core	El Paso Brown	Pottery	MURR	, X	41CU00307	41CU00307	4.06	74.12	0.5125	58.20	11.04	4.78	3.79 140.70	70 10.52	29.42
ATT100	Group-B2	Mimbres-11	Mimbres B/W Style Indeter. Pottery	Pottery	MURR		41CU00658	41CU00658	3.55	40.01	0.5357	30.20	2.88	6.14	3.48 75.98	98 9.31	40.99
ATT101	Group-B2	Mimbres-02A	Mimbres B/W Style Indeter. Pottery	Pottery	MURR	, XI	41CU00658	41CU00658	2.83	40.63	0.4882	32.99	2.87	4.38	3.17 75.76	78.7 97	37.83
ATT103	G-dno19	El Paso Core		Pottery	MURR		41CU00658	41CU00658	4.96	95.04	0.5871		10.17	4.12	4.33 156.06		
ATT105	G-dno19	El Paso Core	El Paso Brown	Pottery	MURR	, XT	41CU00658	41CU00658	6.18	65.73	0.4537	55.91	10.21	3.65	3.41 116.55	55 7.63	36.75
ATT112	G-dno19	El Paso Core	Jornada Brown	Pottery	MURR		41CU00658	41CU00658	1.65	84.04	0.5581	75.45	12.66	3.94	4.21 156.37	37 6.77	18.05
ATT115	G-dno19	El Paso Core	El Paso Brown	Pottery	MURR	, XI	41CU00658	41CU00658	3.80	74.72	0.6392	, 28.39	11.74	3.03	4.66 141.65	65 8.74	30.48
ATT116	G-dnoJ9	El Paso Core	El Paso Brown	Pottery	MURR		41CU00658	41CU00658	6.26	73.47	0.5473	62.21	11.73	7.86	4.56 145.97	97 8.26	29.52
ATT117	G-dnoJ9	El Paso Core	Jornada Brown	Pottery	MURR		41CU00658	41CU00658	2.63	83.96		65.75	12.46		4.96 154.16	16 6.34	23.82
ATT118	G-dnoJ9	El Paso Core	Jornada Brown	Pottery	MURR		41CU00658	41CU00658	5.11	73.71	0.5751	, 09.39	11.80	7.80	4.40 134.84	84 5.62	26.21
ATT119	G-dnoJ9	El Paso Core	El Paso Brown	Pottery	MURR	, X	41CU00658	41CU00658	4.07	68.94	0.5276	58.31	10.82	3.89	4.43 132.34	34 9.25	28.33
ATT121	G-dno ₂	El Paso Core	Jornada Brown	Pottery	MURR		41CU00658	41CU00658	3.00	77.43			10.93		4.29 152.83	83 12.61	18.50
ATT122	Gronp-D	El Paso Core	El Paso Brown	Pottery	MURR	, XT	41CU00658	41CU00658	7.59	65.48	0.5171	55.07	10.28		3.59 114.24		37.27
ATT123	Gronp-D	El Paso Core		Pottery	MURR		41CU00658	41CU00658	3.81	71.86	0.6133		11.78	4.97	4.19 141.37	37 9.61	26.46
ATT124	Gronp-D	El Paso Core	El Paso Brown	Pottery	MURR	, XT	41CU00658	41CU00658	4.39	71.10	0.4859	59.49	10.01	3.05	4.22 122.63	63 5.36	25.55
ATT125	Gronp-D	El Paso Core	El Paso Brown	Pottery	MURR		41CU00658	41CU00658	4.65	71.22			10.80				25.29
ATT126	Gronp-D	El Paso Core	Jornada Red	Pottery	MURR		41CU00658	41CU00658	5.27	58.04		48.61	9.40		4.34 112.08	08 5.91	
ATT127	Gronp-D	El Paso Core		Pottery	MURR		41CU00658	41CU00658	4.63	72.16			11.49				
ATT128	G-dnoJ9	El Paso Core		Pottery	MURR		41HZ00579	41HZ00579	3.10	86.87	0.6447	_	12.81			1	
ATT130	Group-D	El Paso Core	_	Pottery	MURR		41HZ00579	41HZ00579	5.59	98.53		_	14.05		5.94 172.82		
ATT131	Gronp-D	El Paso Core		Pottery	MURR		41HZ00579	41HZ00579	4.04	78.66			11.58				
ATT132	Gronp-D	El Paso Core		Pottery	MURR		41HZ00579	41HZ00579	8.44	75.57			12.06			58 6.51	
ATT133	Gronp-D	El Paso Core	rome	Pottery	MURR		41HZ00579	41HZ00579	7.26	79.34			13.62				
ATT134	Gronp-D	El Paso Core		Pottery	MURR		41HZ00579	41HZ00579	7.34	65.64		53.28	9.46		-	42 6.39	
ATT135	Gronp-D	El Paso Core		Pottery	MURR		41HZ00579	41HZ00579	4.43	40.24		30.11	5.43				
ATT136	G-dnoJ9	El Paso Core		Pottery	MURR		41HZ00579	41HZ00579	5.28	60.29	0.5201	52.62	9.71	3.97	3.58 120.82	82 7.70	25.93
ATT139	Gronp-D	El Paso Core	El Paso Bichrome (B/Br)	Pottery	MURR		41HZ00579	41HZ00579	8.58	55.89		48.06	9.28		3.98 105.65		
ATT140	Gronp-D	El Paso Core		Pottery	MURR		41HZ00579	41HZ00579	4.86	65.16		48.67	98.8	2.57	3.71 115.48		
ATT144	Gronp-D	El Paso Core		Pottery	MURR	, XT	41HZ00579	41HZ00579	4.60	53.03	0.3260	41.23	7.50	4.42	2.66 101.90	_	23.0
ATT146	Gronp-D	El Paso Core		Pottery	MURR		41HZ00579	41HZ00579	4.66	87.58		•	13.07	3.05	5.03 164.98		
ATT147	Gronp-D	El Paso Core	El Paso Brown	Pottery	MURR	, XT	41HZ00579	41HZ00579	7.02	60.95	0.5069	48.75	9.38	4.23	4.07 127.30	30 6.50	27.7
ATT149	Group-D	El Paso Core	El Paso Brown	Pottery	MURR	Ϋ́	41HZ00579	41HZ00579	5.84	72.26	0.5306	52.60	9.53	2.68	3.92 132.41	41 6.57	18.35

>	61.67	86.81	81.06	83.50	80.21	61.42	/3.90	72.97	70.37	95.90	109.02	75.96	90.45	56.35	61.64	65.41	104.38	86.15	99.08	99.55	70.53	65.64	83.88	64.71	98.56	86.87	88.80	74.73	80.29	70.95	92.26	80.78	85.27	83.76	96.79	73.43	81.89	29.06	73.64	80.91	98.88	88.67	81.11	70.58
F	3884.3	4232.4	4764.1	4318.8	4374.3	5331.9	4077.9	4780.9	5801.3	6378.4	5755.8	6012.5	5156.4	2854.5	3018.8	3951.7	5081.9	5568.4	4983.9	6139.5	4445.0	5240.1	5226.5	5651.0	5731.8	5120.3	6144.9	4658.6	2086.6	6075.3	6161.7	5697.5	6739.5	4861.4	5147.0	3852.4	5097.8	9.7509	4196.8	3478.2	4734.5	5078.8	4675.0	3840.3
NA	15652.5	12818.8	12715.4	11844.7	12543.0	19567.4	11090.6	16667.2	16993.4	13523.0	23129.5	19077.9	19588.9	13961.8	12904.2	15769.1	15660.4	27497.5	15297.0	14497.5	23587.1	16066.2	15076.0	20856.3	15290.8	20639.8	16632.1	15697.9	16125.7	16954.8	15008.5	15239.3	18293.4	12796.9	12197.9	11612.3	16422.1	19084.2	14873.0	16498.0	15360.1	12367.9	15286.7	15293.3
MN	512.3	462.0	451.1	469.1	429.0	495.9	386.5	457.7		792.7	1461.5	583.0	648.1	349.1	470.9	463.0	452.6	556.7	632.7	662.0	630.2	505.4	649.3					553.6	461.1	560.0	705.2			498.2	442.8	465.9	463.5	583.1	475.6			634.9		432.1
×	28553.7	28288.6	25829.1	25654.9	25642.3	30769.7	300/8.3	28181.4	26166.8	28574.0	29612.6	31208.7	24732.9	29170.3	27793.2	29438.4	25684.0	32358.3	30345.3	27875.8	30201.5	30255.4	31681.7	33556.4	27257.8	26081.9	28020.7	26747.9	27813.2	30553.2	25834.8	24729.0	32024.2	27233.2	25999.9	27796.4	25453.4	28686.5	26893.6	36194.2	32267.3	25094.8	28530.0	30826.6
DY	6.931	6.673	6.173	5.979	6.536	6.612	6.133	5.698		7.718	080.9	6.253	991.9	4.499	4.618	9.660	5.917	7.211	7.080	6.889	7.519	6.836	6.704	6.192	6.142					6.585	7.985	9.918	6.141	8.165	096.6	5.826	2.963	5.989	6.386	5.417	4.688	7.200		6.246
CA	16959.1	18742.7	19588.4	22955.5	20386.0	16860.4	14/68.9	16909.9	14385.5	14709.4	11254.7	14754.7	15981.8	11702.7	19850.7	17850.9	13841.5	15126.8	18656.5	17536.7	14029.6	18200.5	19183.9	17486.5	15821.5	16322.3	17887.2	16533.7	12405.6	16075.3	12658.4	7896.8	12537.2	15798.5	14354.7	11861.2	14765.2	15444.0	16071.3	11284.1	15646.0	16325.4	14388.5	13212.9
BA	1380.3	1140.1	1212.9	1059.6	1275.1	1269.6	12/8.0	1225.7	1043.7	1131.7	1175.9	1442.0	1066.2	540.5	9.789	1126.3	1395.3	1269.7	1118.0	1016.1	755.7	1566.2	1075.8	1550.5	1419.7	970.9	1543.6	1579.4	871.2	1887.2	853.5	915.0	944.0	1122.8	1120.5	1063.7	752.5	1365.1	1294.3	737.8	951.1	797.2	868.3	868.0
AL	80833.2	90788.2	92217.5	89076.1	88353.7	86700.3	97558.0	85399.9	89156.0	84092.5	86136.0	89791.7	90742.1	83502.8	82307.2	86109.3	96560.2	94689.8	77704.9	84175.9	85598.7	86782.3	75779.4	92848.5	98732.9	91715.4	84438.8	82865.4	88299.5	80053.6	84339.1	77174.9	88689.0	93987.5	91087.9	83223.5	90470.5	82460.8	99417.1	98074.5	89246.9	83085.3	83041.0	87069.1
ZR										857.5	293.1	584.1	284.7	196.9	177.3	327.4		315.2	431.5	343.1	376.5	312.2	295.4	293.6						283.4	457.8				360.4	273.3	261.0	221.5	260.3	188.5				189.7
NZ	67.6										92.1	93.7	72.4	62.4	54.4	74.2	86.6	74.9	85.1	90.3	76.4	81.2	84.8		90.2										87.1	75.1	79.5	90.1		77.3				86.2
B TH						_	-				1 16.28	2 15.93	0 18.11	4 21.96	1 19.86			9 15.30	5 17.23	8 17.58	2 20.51	8 18.19	8 21.27	8 15.73				-							0 23.77	1 25.14	0 26.25	9 20.11	8 20.45					6 28.14
TA TB	3.0500 1.40		2.5823 1.09	_					3.1866 1.32	3.0898 1.69	351 1.21	3.2646 1.32	2.8253 1.30	1.7560 0.74	1.4210 0.71	2.5680 1.29		2.7976 1.39	2.4523 1.25		467 1.52		2.4836 1.38	3.3463 1.28	2.4143 1.26	_	901 1.32		3.0885 1.26	2.7424 1.43		_	_	-+	681 1.90	.5021 1.11	3.0563 0.60	3.0270 1.19	667 1.58	2.8148 1.12	_			3.0972 1.26
SR					_				_		1.6 3.2351				296.6 1.4;					3.0 2.4957	3.8467	.3 2.8007	379.5 2.48									_	_		7	7								
SC										316.1	34 434.6	3 292.7	36 485.7	3 234.8				32 550.0	12 280.8	4 328.0	359.1	391.3		10 396.5		7 405.2			0 309.9							57 232.9	30 286.2	5 457.5		19 307.8				33 316.2
SB S	73 7.82			_						1	71 9.34	93 8.93	64 11.36		16 9.79	98.8		40 10.32	21 10.42	05 11.14	50 9.58	19 8.90	10.21	34 9.40		_				,	J				83 12.09	15 8.57	61 9.30	79 11.15		46 8.49		_		39 8.83
											0.3971	0.5693	0.5864	0.6103				0.4940	0.4621	0.5505	0.4950	0.5919	0.4701	0.5134												0.7215	0.4961	0.3379						0.4439
RB	135.51								,		107.90	86.68	98.41	194.79		120.02		90.76	104.36	106.84	122.66	100.01	97.37	١.												114.34	`	98.73	107.87		`			126.49
Z	31.1									7		0.0	47.4	0.0	0.0	50.1		43.1	0.0	36.3	0.0	0.0	0.0	0.0									ц,		0.0	0.0	0.0	0.0	0.0	0.0				0.0
生						_	_			1 28.02	10.49	3 20.05	10.37	3 7.92		11.53		10.04	14.85	14.89	15.34	13.35	12.17	99.01	8.12	_					_	_		_		12.48	11.54	9.01	-			_	`	8.38
FE	37211.4	42098.0	42612.6	44057.2	43624.4	39695.9	42036.3	39398.4	39634.2	53177.4	44702.0	41936.3	37667.3	22849.8	25459.9	38640.2	35258.4	33123.4	43675.4	46325.4	29604.7	43525.7	41540.3	43436.5	35373.7	34208.5	43182.1	42874.2	42067.6	42603.3	46029.6	39313.0	46795.8	45646.2	46643.5	37132.2	43806.5	46905.6	41438.5	37649.2	42393.5	42694.9	39822.2	39520.1
ED				1.8073	1.7715		_				2.4198	2.7180	2.5218	1.1108	1.0848	_		3.3355	2.1850		2.5805	2.4404	2.1430	2.7476		2.5987				_					2.0880	1.6227	1.0952	1.9976	1.7632	1.6617				1.7048
CS											3.80	3.66	4.53	7.67			6.38	3.96	3.08	3.60	3.81	3.95	3.07	5.02	6.47					3.57							3.35	7.68	3.77		3.06			3.17
ANID	ATT085	ATT086	ATT087	ATT088	ATT089	ATT090	A11091	ATT092	ATT093	ATT095	ATT097	ATT098	ATT099	ATT100	ATT101	ATT103	ATT105	ATT112	ATT115	ATT116	ATT117	ATT118	ATT119	ATT121	ATT122	ATT123	ATT124	ATT125	ATT126	ATT127	A11128	A11130	ATT131	ATT132	ATT133	ATT134	ATT135	ATT136	ATT139	ATT140	ATT144	ATT146	ATT147	ATT149

ANID	macro_gr	macro_grp Chem2012	CERAMIC TYPE	MATERIAL	SOURCE	STATE	SITE_NAME	SITE_NO	AS	ΓA	Π	ND	SM	П	YB	CE CO	CR
ATT150	G-dno _{-D}	El Paso Core	El Paso Brown	Pottery	MURR	×	41HZ00579	41HZ00579	7.68	65.16	0.5376		10.18	4.47 4	4.48 119.26	80.9 95	
ATT151	G-dno ₋ D	El Paso Core	El Paso Brown	Pottery	MURR	×	41HZ00579	41HZ00579	5.92	71.44	0.5481	58.03	10.36	4.90 4	4.50 134.28	28 8.10	32.55
ATT152	G-dno ₋ D	El Paso Core	El Paso Polychrome	Pottery	MURR	×	41HZ00579	41HZ00579	8.80	60.82	0.4985	49.85	9.01	5.42	3.59 120.16	16 9.37	30.22
ATT155	G-dno ₋ D	El Paso Core	El Paso Brown	Pottery	MURR	×	41HZ00579	41HZ00579	7.55	62.77	0.5445	56.76	10.37	3.98 4	4.58 131.38	88 6.34	28.14
ATT157	G-dnoJ5	El Paso Core	El Paso Brown	Pottery	MURR	ĭ	41HZ00579	41HZ00579	8.63		0.6502						
ATT158	G-dno-D	El Paso Core	El Paso Brown	Pottery	MURR	ĭ	41HZ00579	41HZ00579	5.30	90.23	0.5368					8.09	
ATT159	G-dno ₋ D	El Paso Core	El Paso Brown	Pottery	MURR	ĭ	41HZ00579	41HZ00579	5.44	76.44	0.5860	67.33	12.21	4.51 4	4.73 153.55	55 8.65	28.23
ATT161	G-dno ₋ D	El Paso Core	Jornada Brown	Pottery	MURR	ĭ	41HZ00579	41HZ00579	8.11		0.4965			5.08 4			
ATT162	Group-D	El Paso Core	El Paso Brown	Pottery	MURR	X	41HZ00579	41HZ00579	8.52		0.5902			4.46 4	4.88 144.40	_	31.62
ATT166	G-dno-D	El Paso Core	El Paso Polychrome	Pottery	MURR	XX	41EP05488	41EP05488	8.17	90.39	0.5546	53.47	6.87	3.61 4	4.37 125.77	4.95	24.71
ATT168	G-dno-D	El Paso-2	El Paso Polychrome	Pottery	MURR	XX	41EP05488	41EP05488	2.90	23.60	0.5420	48.63	9.28	3.04 4	4.14 102.31	-	78.68
ATT172	G-dno ₋ D	El Paso-2	El Paso Polychrome	Pottery	MURR	×	41EP05488	41EP05488	7.08	46.01	0.3609	39.81	7.87	3.10 3	3.23 83.43	11.89	61.74
ATT173	G-dno-D	El Paso Core	El Paso Polychrome	Pottery	MURR	XX	41EP05488	41EP05488	5.33	61.68	0.5031	48.34	8.80	2.47 3	3.65 108.08	38 4.88	23.48
ATT174	Gronp-D	El Paso Core	El Paso Polychrome	Pottery	MURR	ΤX	41EP05488	41EP05488	6.44	62.64	0.6118	51.51	10.00	3.80 4	4.48 119.41	11 7.03	30.75
ATT177	Group-D	El Paso Core	El Paso Bichrome (R/Br)	Pottery	MURR	X	41EP05488	41EP05488	6.17	54.99	0.5516	43.67	8.73	4.05 4	4.01 106.25	25 5.18	
ATT178	G-dno-D	El Paso Core	El Paso Polychrome	Pottery	MURR	ĭ	41EP05488	41EP05488	2.65		0.5209				3.62 110.05		
ATT179	Group-D	El Paso Core	El Paso Bichrome (B/Br)	Pottery	MURR	X	41EP05488	41EP05488	5.78		0.4681		8.38		3.40 111.01	07.0	
ATT180	G-dno ₂	El Paso-2	El Paso Bichrome (R/Br)	Pottery	MURR	XX	41EP05488	41EP05488	6.59	93.38	0.6420	67.34 1	13.26	2.87 5	5.79 145.27	19.16	82.38
ATT181	Gronp-D	El Paso Core	El Paso Bichrome (R/Br)	Pottery	MURR	ΤX	41EP05488	41EP05488	7.33	70.77	0.6044	56.45 1		3.52 4	4.61 127.68	5.83	28.00
ATT182	G-dno-D	El Paso Core	El Paso Polychrome	Pottery	MURR	XX	41EP05488	41EP05488	8.10	61.91	0.5614	49.75	7 89.6	4.46 3	3.97 119.20	12.11	34.12
ATT183	G-dno-D	El Paso Core	El Paso Bichrome (R/Br)	Pottery	MURR	XX	41EP05488	41EP05488	4.48	50.31	0.4421	41.57	8.19	2.48 3	3.62 110.05)5 8.47	27.93
ATT185	G-dno ₂	El Paso-2	El Paso Bichrome (B/Br)	Pottery	MURR	×	41EP05488	41EP05488	2.68	51.01	0.4525	42.81	8.79	4.07	4.06 102.61	51 12.42	66.42
ATT186	G-dno-D	El Paso Core	El Paso Bichrome (B/Br)	Pottery	MURR	×	41EP05488	41EP05488	6.44	65.63	0.5894	57.06		4.39 4	4.83 123.09	9 7.30	32.54
ATT187	G-dno ₋ D	El Paso Core	El Paso Bichrome (B/Br)	Pottery	MURR	×	41EP05488	41EP05488	4.80		0.6093		9.57		,		
ATT188	Gronp-D	El Paso Core	El Paso Bichrome (B/Br)	Pottery	MURR	ΤX	41EP05488	41EP05488	6.51	52.56	0.5434		7 90.8	4.88 3	3.82 99.45	15 5.70	23.81
ATT189	G-dno ₂ D	El Paso Core	El Paso Brown	Pottery	MURR	X	41EP05488	41EP05488	5.05		0.4715				-		
ATT190	Group-D	El Paso Core	El Paso Polychrome	Pottery	MURR	X	41EP05488	41EP05488	9.85		0.5651	50.85	9.72		4.27 117.88	88 6.73	32.12
ATT191	Gronp-D	El Paso Core	Jornada Brown	Pottery	MURR	ΤX	41EP05488	41EP05488	7.19		0.5683	_	9.74		3.97 114.78	78 5.42	
ATT192	G-dno ₂ D	El Paso Core	El Paso Polychrome	Pottery	MURR	TX	41EP05488	41EP05488	6.15	53.90	0.6828	53.91		4.32 5	5.43 110.23	23 5.15	28.05
ATT193	G-dno-D	El Paso Core	El Paso Polychrome	Pottery	MURR	ĭ	41EP05488	41EP05488	7.68	65.52	0.5294	56.07		4.36 3	3.64 127.34	34 13.10	23.80
ATT194	G-dno-D	El Paso Core	El Paso Brown	Pottery	MURR	ĭ	41EP05488	41EP05488	7.67		0.5293					1	
ATT196	Group-D	El Paso Core	El Paso Polychrome	Pottery	MURR	ĭ	41EP05488	41EP05488	6.22		0.5870						
ATT197	G-dno-D	El Paso Core	El Paso Brown	Pottery	MURR	ĭ	41EP05488	41EP05488	6.57		0.5327			6.01			23.20
ATT202	Group-D	El Paso Core	El Paso Brown	Pottery	MURR	×	41EP05488	41EP05488	6.93	64.51	0.5154	55.84	10.00	4.12 3	Υ.	70 12.61	26.69
ATT203	Group-D	El Paso-2	El Paso Brown	Pottery	MURR	X	41EP05488	41EP05488	5.80		0.4909	44.13	8.63	3.05 4	4.20 94.37	37 10.64	55.77
ATT204	Group-D	El Paso Core	Jornada Brown	Pottery	MURR	X	41EP05488	41EP05488	5.32		0.6630		14.03 4	4.66 4			
ATT209	Gronp-D	El Paso Core	El Paso Polychrome	Pottery	MURR	ΤX	41EP05488	41EP05488	8.12		0.4994	53.86	9.01	3.87 3	3.85 117.96		
ATT211	Group-B	Unas.	Alma Plain	Pottery	MURR	ΤX	41EP05488	41EP05488	8.00	55.03	0.5958	49.63 1	10.14	3.49 4	4.70 100.14	,	39.66
ATT213	Group-D	El Paso Core	El Paso Polychrome	Pottery	MURR	X	41EP05488	41EP05488	6.58	69.03	0.5833		9.19	5.21 3	3.91 127.88	38 11.80	
ATT214	Group-D	El Paso Core	El Paso Polychrome	Pottery	MURR	X	41EP05488	41EP05488	9.48	64.95	0.5270	55.94 1		3.81 3	3.98 118.65		31.34
ATT217	G-dno ₂ D	El Paso Core	El Paso Bichrome (B/Br)	Pottery	MURR	X	41EP05488	41EP05488	7.08		0.5862						
ATT219	G-dno-D	El Paso Core	El Paso Bichrome (R/Br)	Pottery	MURR	ĭ	41EP05488	41EP05488	8.31		0.5984						
ATT220	Group-D	El Paso Core	El Paso Bichrome (R/Br)	Pottery	MURR	ĭ	41EP05488	41EP05488	8.38		0.7800	,		5.16 5	5.72 125.81		
ATT221	G-dno-D	El Paso Core	El Paso Bichrome (R/Br)	Pottery	MURR	ĭ	41EP05488	41EP05488	6.28	64.61	0.4371	51.48	9.73	3.11 3	3.41 120.81	12.46	26.03

EU FE HF NI RB SB SC SR TA TA TB T8880 44783.8 9.09 0.0 105.57 0.6583 10.48 287.9 2.5187 1.44	HF NI RB SB SC SR TA TA TB 44783.8 9.09 0.0 105.57 0.6583 10.48 287.9 2.5187 1.44	HF NI RB SB SC SR TA TA 1000 0.00 105.57 0.6583 10.48 287.9 2.5187 1.44	RB SB SC SR TA TB TD	RB SB SC SR TA TB TD	SB SC SR TA TB 0.6583 10.48 287.9 2.5187 1.44	SC SR TA TB TB 10.48 287.9 2.5187 1.44	TA TB 2.5187 1.44	TB 1.44		TH 33.10	1 1 1				BA 1725.8	CA 14454.9	DY 6.630	X 27826.8	1 1			V 72.20
	5.00 1.9090 4.11 1.9288	49158.7 3 43272.8	11.38	29.3	93.70	0.5878	99.8	509.7	3.1722	1.08	16.06	2 α	322.3 %. 270.4 90	95334.9	983.1	16446.6	5.904	26420.0	650.6	20755.7	5453.1	78.06
				0.0		0.6015			2.6842		20.59	76.8 24		, ,	1027.6	19754.3	6.710	28921.4	١, ١,			63.81
	3.21 2.1651	40809.7	12.37	0.0	115.48	0.4933	9.63	234.5	2.3780	1.40 2	22.47	72.2 29	290.2 87	848/8.9	1.8011	15205.5	6.611	29868.3	578.2	13035.6	41/9.4	70.62
	_			38.8				+	2.8054		25.20			69137.9	796.2	14769.8	7.026	29325.3	_			86.54
	4.12 1.5094			0.0		0.7658			2.8378	1.09 2	23.96				9.668	11246.5	5.555	31347.6	`			87.05
				0.0		0.5466	_		3.1345	1.45 2	23.03			Υ	1118.3	13861.4	6.873	30455.7				116.69
		3 38110.9	· -	0.0		0.4499			2.8594	1.13 2	22.26			90190.4	983.9	15701.8	6.371	25852.9	.			77.90
_				0.0		0.6959					19.40				93.6	17474.8	9.760	24359.7	-			126.33
				0.0		0.6601	7			0.92	19.61			`	1127.6	18152.2	5.976	26935.1				94.06
-+		35881.7		27.1					2.5035		19.98			, ,	1171.5	17254.5	5.261	28071.6	. .			56.47
-+				35.5					2.6513	_	20.04			. '	1165.1	14066.5	0/8/9	30904.0				64.21
	4.08 1.5964 3.61 1.5545	39489.7	13.12	25.9 47.5	121.05	0.4/14	7.09	300.9	2.8353	1.06	78.77	78.0 37	324.9 8	85816.3	1154.0	13222 0	5.823	27492.6	436.8	14215.4	3907.3	73.05
+	_			5.74			8 98		_	-	12.15			,	1096.0	16591 4	5 328	25001.1 25150.5			_	81 92
+				0.0	1.		17.66	_			20.89				1314.5	16744.5	9.593	25814.2				119.44
1	3.98 1.9085	38586.7	13.13	0.0				348.3	2.8524	1.39	21.64	76.6 29			1922.4	20236.6	7.422	30247.8	484.2	13985.7	4765.1	68.58
1	3.81 1.8530	1.8530 49282.1	13.65	17.9	113.93	0.5080	10.91	409.8	3.0914	1.10	21.98	100.0	310.8 92	92956.0	1082.2	19075.4	6.302	30745.5	676.0	16350.6	6523.0 1	127.65
	4.25 1.5780			0.0							18.24			•	1067.1	14208.3		30787.8			_	55.87
	5.90 1.6421			63.5			14.53	244.3	1.8553	1.30	20.76		196.5 90	90939.9	1338.0	15025.0	6.508	29004.2	448.1	11223.8	4895.7	109.11
-				0.0					2.7592	1.27 2	24.05			`	1166.0	15473.0	7.059	30063.2				68.78
				0.0							16.67			—	1084.7	27276.5	6.388	23548.6	_			99.91
-+				0.0							20.67			- '	882.5	13261.9	5.290	35798.8				48.06
	3.96 1.5072	2 30677.2 3 42580 E	13.17	0.0	124.44	0.5234	0.02	334.1	3.1919	1 22 2	18.73	65. L 3	319.2 8.	8/894./	1238.0	1,6887.7	4.804	33114.0	505.4 2	712280.4	4306.6	04.71
+				0.0					2.7210		22.93				1071.1	14998.6	5.797	28171.3			-	69.38
+		3 37901.7		0.0					3.0805		22.23				1202.7	20389.6	8.008	32649.1				73.15
	4.20 2.5948			31.5					3.8486	1.17	14.82				1143.8	21055.5	6.501	24650.2				105.07
-+	_			0.0					4.5165		15.52				1041.8	24032.9	5.748	24922.7	` '			100.27
-		9 53881.5	`	0.0	`		l		3.6668		22.62				1010.4	18795.1	6.538	26217.3				124.94
+				0.0	83.95			7.28.1	3.8852	1.19	14.24			_	1005.3	23331.2	5.983	22407.3				110.61
_	4.88 2.3209		10.04	41.7	97.46	0.5236	10.16	726.7	3.8810	1.1	14.28	7. 0.07	8 6.262	81435.2	16001	19192.8	6.95/	25046.8	810.4	19213.9	/813.8	95.36
+		7 9/87 5/956 6		57.1				_	2 2721	_	18 27	2 4		÷	1.4001	206/19.0	0.239	22045.1			-	70.02
\pm	3.56 1.8160	46258.8		0.0	,				2.7883		21.46				998.5	16943.9	6.084	28918.1			_	99.83
1	4.68 1.8934			51.9				345.4	1.6024		15.76		238.1 92	_	1256.3	17915.9	7.625	31695.8				80.91
	3.32 2.1223	3 46402.8	20.55	0.0	92.91	0.5805	8.31	546.1	4.0996	1.04	16.68	90.5 53	534.6 80	١,	1058.3	14564.2	5.891	30327.3	723.8	20709.8	1.9989	77.67
				0.0			l		3.1289	1.21	21.33			,	1275.8	18233.3	6.644	28725.8			,	115.04
			12.60	0.0					2.5045	1.06 2	24.45			89863.0	980.2	14278.1	5.913	26641.1			4961.8	77.82
-		5 34023.6		27.3					3.6172		16.19			74774.0	834.7		5.190	30836.5				66.11
-		1.7460 40413.3	_	29.5							21.63				786.8		10.547	26368.7				87.94
\dashv	3.59 2.2326	2.2326 45733.1	9.12	0.0	94.61	0.4703	8.50	598.9	3.9158	1.17	14.75	91.1 25	254.3 89	89094.7 1	1178.2	15500.3	6.194	28057.0	945.2 2	23388.6	6617.4	89.24

ANID	macro_gr	macro_grp Chem2012	CERAMIC TYPE	MATERIAL	SOURCE	STATE S	SITE_NAME	SITE_NO	AS	ΓA	П	ND	SM	n	YB C	CE CO	CR
ATT222	Group-D	Loop 375	El Paso Polychrome	Pottery	MURR	TX 4	41EP05488	41EP05488	10.52	72.88	1.0375	68.50 1	14.38 3	3.92 8	8.11 134.74	4 7.86	41.19
ATT223	Gronp-D	El Paso Core		Pottery	MURR		1EP05488	41EP05488	6.26	68.44 (0.6578				5.04 139.11	1 9.05	31.57
ATT224	G-dno-D	El Paso Core		Pottery	MURR	TX 4	41EP05488	41EP05488	7.02	99.21	0.6023	53.99 10	10.52 3	3.89 4	4.20 128.86	6 6.64	34.26
ATT225	Group-D	El Paso Core	_	Pottery	MURR		41EP05488	41EP05488	6.43	57.16 (0.5215		7.64 3			0 6.94	32.11
ATT226	Gronp-D	El Paso Core	(/Br	Pottery	MURR	TX 4	41EP05488	41EP05488	6.94	63.18 (l			5.22 121.49		28.67
ATT227	Gronp-D	El Paso-2	El Paso Polychrome	Pottery	MURR		41EP05488	41EP05488	60'6	46.65	0.5930	40.98		3.53 4	4.41 103.03	3 14.03	
ATT228	Group-D	El Paso Core	El Paso Polychrome	Pottery	MURR		41EP05488	41EP05488	69.9			55.18 10	10.87 4	4.13 4	4.27 132.50		
ATT230	Gronp-D	El Paso Core		Pottery	MURR		41EP05488	41EP05488	7.72	58.07					4.13 112.09	6.56	
ATT231	Gronp-D	El Paso Core		Pottery	MURR	TX 4	41EP05488	41EP05488	5.19		0.5789	55.19 10	10.87	4.09	4.07 142.43	3 11.60	27.88
ATT232	Gronp-D	El Paso Core		Pottery	MURR	TX 4	41EP05488	41EP05488	7.19	53.31	0.5947	46.40	9.46	3.88 4	4.81 106.68	8 6.44	32.26
ATT235	G-dno-D	Loop 375		Pottery	MURR	TX 4	41EP05488	41EP05488	11.07	82.44	1.7375	73.26 16	16.27 5	5.34 13	13.58 160.53	3 7.46	45.70
ATT238	G-dno-D	El Paso Core	El Paso Polychrome	Pottery	MURR		41EP05488	41EP05488	4.63	84.50 (0.6262		14.02	3.55 4	4.44 169.54	4 8.05	25.11
ATT239	Group-B	Unas.	Mimbres Corrugated	Pottery	MURR	TX 4	41EP05488	41EP05488	2.90	64.45 (0.8574	56.45 13	13.10 3	3.77 6	6.82 131.57	7 10.91	35.19
ATT241	Gronp-D	El Paso Core		Pottery	MURR		41EP05488	41EP05488	8.63	61.07	0.6105	55.53 10	10.50 4	4.02 5	5.01 125.83	3 7.39	36.17
ATT242	Gronp-D	El Paso Core	El Paso Polychrome	Pottery	MURR	TX 4	41EP05488	41EP05488	7.10	64.40	0.4824	53.70 10	10.32 4	4.31 3.	3.70 119.42	2 8.50	31.26
ATT243	Gronp-D	El Paso Core		Pottery	MURR		41EP05488	41EP05488	8.27		0.6418					91.9	
ATT244	Group-D	El Paso Core	El Paso Polychrome	Pottery	MURR	TX 4	41EP05488	41EP05488	4.28	87.11 (0.6055	67.66 12	12.13 3	3.38 4	4.32 150.48	8 6.26	23.47
ATT245	G-dno-D	El Paso-2		Pottery	MURR		41EP05488	41EP05488	7.20	98.09	0.6378	55.61 10	10.52 3	3.83 4	4.49 100.90	0 11.12	90.09
ATT246	G-dno-D	El Paso Core	El Paso Polychrome	Pottery	MURR	TX 4	41EP05488	41EP05488	7.84	28.56	0.5608	49.85	9.75 4	4.01	4.73 116.26	6 7.84	32.79
ATT247	G-dno-D	El Paso Core		Pottery	MURR		41EP05488	41EP05488	6.71	66.02	0.5352	51.89		4.67	3.70 127.90	0 11.90	26.49
ATT249	Group-D	El Paso Core	El Paso Polychrome	Pottery	MURR	TX 4	41EP05488	41EP05488	7.07	94.99	0.5671	51.77 10	10.40	3.60 4	4.37 125.22	2 6.18	26.69
ATT250	Group-D	El Paso Core	/Br)	Pottery	MURR		41EP05488	41EP05488	6.71	62.46	0.5876	55.73 10	10.43 3	3.46	3.99 119.28	8 6.01	29.66
ATT252	Group-D	El Paso-2	El Paso Polychrome	Pottery	MURR	TX 4	41EP05488	41EP05488	96.9	43.41 (0.5689	38.33	7.97	3.89	3.80 87.84	4 10.46	58.19
ATT253	G-dno-D	El Paso Core		Pottery			41EP05488	41EP05488	4.82			58.84 10		3.67	4.71 118.34		26.86
ATT254	Gronp-D	El Paso-2	(/Br)	Pottery	MURR	TX 4	41EP05488	41EP05488	7.22	48.56 (0.5950	46.33	9.39 4	4.20 4	4.34 102.00	0 10.36	61.52
ATT256	Group-D	Loop 375		Pottery	MURR		41EP05488	41EP05488	9:26	79.93	1.0350	83.81 17	17.02 4		8.33 147.78		46.68
ATT257	Gronp-D	El Paso Core	El Paso Polychrome	Pottery	MURR	TX 4	41EP05488	41EP05488	4.80	75.28 (0.5993	71.59 12	12.31 3	3.90 4	4.54 156.95	5 7.38	
ATT258	Gronp-D	El Paso Core		Pottery	MURR		41EP05488	41EP05488	5.16		~				L		
ATT259	Group-D	El Paso-2		Pottery	MURR		41EP05488	41EP05488	80.9							_	
ATT260	Group-D	El Paso Core		Pottery	MURR		41EP05488	41EP05488	6.20							3 9.65	
ATT261	Group-D	El Paso Core		Pottery	MURR		41EP05488	41EP05488	7.47						_	_	
A11262	Group-D	El Paso Core	me (B/Br)	Pottery	MURR		41EP05488	41EP05488	61.7						_		
ATT264	Group-D	El Paso Core		Pottery	MURR		41EP05488	41EP05488	4.95								
ATT265	G-dno-D	El Paso Core	me (B/Br)	Pottery	MURR		41EP05488	41EP05488	6.48	_					`	1	
ATT266	Group-D	El Paso-2	El Paso Brown	Pottery	MURR		41EP05488	41EP05488	7.36								
ATT267	Group-D	El Paso Core	El Paso Brown	Pottery	MURR		41EP05488	41EP05488					_		_		
ATT268	Group-D	El Paso Core	El Paso Brown	Pottery	MURR	TX 4	41EP05488	41EP05488			0.7334	83.74 15			5.51 189.72	2 5.19	
ATT269	Group-D	El Paso Core	El Paso Brown	Pottery	MURR	TX 4	41EP05488	41EP05488	8.01		0.4200	27.40	5.64 4		2.75 68.13	3 6.17	28.16
ATT270	Group-D	Loop 375	El Paso Brown	Pottery	MURR		41EP05488	41EP05488	8.83								
ATT271	Group-D	El Paso Core	El Paso Brown	Pottery	MURR		41EP05488	41EP05488	8.27						_	6 6.75	
ATT273	Gronp-D	El Paso Core	El Paso Brown	Pottery	MURR	TX 4	41EP05488	41EP05488	5.55	51.98 (42.84		3.57 3	3.84 99.43		
ATT275	Group-D	El Paso Core		Pottery	MURR		41EP05488	41EP05488	5.51								32.12
ATT276	Group-D	El Paso Core		Pottery	MURR	TX 4	41EP05488	41EP05488	6.35						,		
ATT277	Group-D	El Paso-2	El Paso Brown	Pottery	MURR	TX 4	41EP05488	41EP05488	5.99	42.72 (0.5280	36.52	7.81 4	4.52	3.52 81.10	0 10.42	66.03

>	76.06	84.06	73.72	63.72	96.22	104.25	96.65	78.81	100.29	71.36	72.95	117.19	71.18	86.35	107.52	80.92	79.80	88.05	71.59	74.76	80.69	69.12	69.86	64.48	105.32	77.75	79.01	71.04	79.10	105.53	109.02	71.86	75.96	78.05	84.99	108.44	68.02	84.95	64.12	73.57	69.22	64.04	62.45	103.89
Ξ	3253.6	5801.6	4224.9	4070.2	4939.1	4460.7	6284.8	4802.3	7925.9	3798.6	3412.8	7371.4	4309.9	3635.2	6855.1	3989.5	5659.9	4070.1	3571.1	5801.6	4330.9	4384.0	4556.1	3664.3	4847.3	3717.7	4640.7	4561.9	4374.2	7164.0	6373.5	4610.5	3776.3	6551.0	4056.8	7562.8	5457.6	3747.0	3243.9	4481.1	4012.1	4049.8	4054.7	4650.6
NA	12409.6	16267.2	11998.6	19090.7	18298.7	10740.8	17426.2	12052.0	21206.1	12406.9	11744.2	21808.8	15016.1	13631.6	16018.2	11763.5	17696.8	10460.2	13869.6	20833.2	14498.4	14327.4	11630.2	13642.0	10632.9	11362.7	17299.6	12863.8	11537.9	19722.3	17452.6	14635.9	13113.0	21387.7	11561.6	16401.5	16248.5	11333.8	11278.8	14780.0	14179.1	14039.6	14530.1	11396.8
MN	352.0	619.5	603.8	471.9	549.8	618.3	602.3	496.6	886.1	496.4	352.9	651.6	620.9	648.9	661.6	518.9	575.4	438.3	491.5	783.7	536.1	466.3	452.3	459.6	496.2	323.4	627.9	420.3	385.0	643.0	737.2	398.6	385.7	826.9	306.6	727.8	375.8	336.8	193.7	462.9	380.3	431.8	419.9	434.9
¥	24985.5	28247.3	29115.3	32379.2	31505.8	25445.5	31753.4	27586.8	28900.9	26784.3	25325.9	28844.1	33171.7	34714.6	24686.5	28357.5	31777.5	27978.3	29221.9	28727.1	29124.4	33500.6	29529.7	28285.3	25201.2	25815.1	29212.4	25709.6	27718.1	31876.8	30779.2	27914.6	25738.3	26939.4	27086.7	23061.8	29988.8	30092.6	23900.1	31274.3	28383.7	30373.1	28277.9	23675.9
DΥ	12.124	7.179	6.555	4.717	6.221	5.692	6.399	6.272	6.265	6.759	17.404	8.000	9.985	6.712	5.834	7.002	7.311	7.162	5.900	5.409	7.018	6.291	5.801	6.185	6.310	13.628	6.356	6.432	7.149	6.375	7.348	6.121	6.873	5.760	5.371	6.315	9.776	3.737	17.761	6.416	5.817	6.650	6.249	5.430
CA	13292.0	12850.5	13567.8	10829.6	13381.3	13755.8	15303.0	14219.6	17311.6	15389.0	10100.0	19582.5	11262.7	15971.6	16842.6	14400.2	13470.9	19092.6	16752.7	17657.7	15963.4	14515.4	14698.1	15113.1	15466.8	11731.7	10375.9	15918.9	23854.1	18461.7	17617.3	16485.9	21352.9	15834.7	12541.9	19266.2	13833.2	14438.3	11368.4	16670.9	17392.0	18962.0	14412.3	18921.8
BA	847.5	958.2	1305.5	922.8	989.5	1110.2	1060.1	1262.1	1199.9	1131.3	809.5	1379.1	9.906	2.998	898.5	1073.0	1019.6	923.9	1246.5	821.6	1333.3	1123.8	1335.8	1635.6	1324.8	1095.7	1122.1	1203.1	1286.7	1487.3	1050.5	1103.7	1135.5	1103.9	1051.2	1343.9	1287.9	1242.7	855.5	1120.9	1146.2	1126.5	1516.6	1105.0
AL	82167.0	84434.3	90535.6	77438.8	83113.8	82263.0	88488.6	93665.7	90392.8	90894.9	86038.5	89858.1	86545.8	95188.3	88137.0	93612.1	90162.7	75128.2	86793.0	82670.3	87294.9	88029.3	84006.2	87442.3	84855.2	83662.1	79121.4	82044.3	81054.0	92393.2	89638.3	87697.7	93759.3	91457.0	81690.9	88682.6	90632.2	90897.1	79602.4	92455.3	85444.6	85569.1	87869.8	86213.5
ZR	287.2	410.9	301.1	471.4	415.1	278.6	474.1	374.6	397.9	283.7	419.6	346.5	271.8	323.6	306.8		459.5	251.7	309.0	366.5	349.7	308.2	279.1	292.9		331.0	415.3	336.1								273.2	443.0	261.6	388.3	280.0	333.8			249.1
NZ	78.2	75.7	85.7	85.3	84.9	88.3	88.1	0.88	91.6	87.7	94.6	97.0	7.76	91.0	82.3	79.4	78.3	77.2	80.3	92.3	75.0	6.77	76.6	73.2	9.18	88.4	74.1	73.1	74.7	88.5	90.1	74.6	78.8	9.68	67.9	106.1	73.8	71.4	66.4	92.6	1.99	72.4		71.6
3 TH		17.94				5 15.23	_	1 29.19	9 21.13	3 20.81	27.75) 22.27	17.83	19.94	5 20.25		7 19.52	3 20.03	3 18.85	17.70	5 24.77	7 21.42	1 25.82	1 22.00	2 22.03		15.97		3 19.30						3 21.23		1 22.17	3 29.76	30.70	1 21.20	2 21.73			5 19.36
TA TB	9 2.21	0 1.28	76 1.31	1 0.91		9 1.25	3 1.21	1.31	1.29	1.38	12 2.80	1.60	12 2.11	1.40	1.25		1.57		1.18	1.11	0 1.25	1.37	1.04	1.24		5 2.55	1.47									1.43	1.91	3 0.68	5 2.48	5 1.21	1.12			1.06
	2	2.5660				2.3849	3.6873	2.5346	5.3145	2.4221	3.1282	2.8162	2.3182	2.6865	3.2199		2.3296	1.9129	2.4544	4.2070	2.6460	2.5620	2.0588	2.8041			2.4796										2.2458	3.0063	3.3175		2.5503			2.3528
SR	230.2	227.4	286.7			185.5	676.8	793.6	500.3	280.4	145.4	439.0	244.9	292.2	398.7	7.873	242.8	205.7	458.2	474.6	288.2	281.8	217.1	320.1			258.6	251.6	285.0	411.2	408.9	308.0			212.9	446.3	231.5	305.1	136.7	308.2	280.5			252.0
SC	8.78	9.72	9.73	7.06	9.48	13.30	10.61	10.12	8.36	69.6	9.90	11.99	10.62	10.17	10.59	10.05	10.79	12.87	9.52		9.39	9.32	12.76	9.29	13.51	9.73	9.10	8.92	12.36	9.66	10.22	9.39	10.60	8.28	11.50	11.81	10.97	8.85	8.48	6.66	8.68	9.35	9.19	14.46
SB	0.7204	0.5562	0.5498	0.5973	0.5849	0.6971	0.4949	0.7247	0.4874	0.6031	0.7404	0.3878	0.6396	0.7420	0.5004	0.6476	0.4683	0.6533	0.5164	0.5654	0.5445	0.5529	0.6997	0.4994	0.7610	0.6942	0.4502	0.5681	0.7090	0.4494	0.5615	0.4786	0.7050	0.4671	0.5960	0.5307	0.4732	0.6692	0.6438	0.6781	0.4745	0.6947	0.5668	0.5723
RB	113.41	112.48	124.60	101.33	103.38	124.14	104.40	125.31	93.26	118.05	160.60	92.30	129.83	130.51	119.75	123.18	91.71	121.15	120.82	90.90	118.56	133.57	123.46	120.79	111.79	115.58	98.56	113.48	122.33	105.70	115.70	113.27	100.46	93.53	121.78	100.98	94.30	122.74	151.09	135.26	124.24	122.33	124.75	121.73
Z	33.3	0.0					0.0	0.0	0.0	0.0	0.0	33.5	0.0	29.9	0.0	0.0	33.5	38.2	0.0	0.0	37.1		38.7	0.0	0.0	47.5	45.2	13.2	40.2			0.0	46.2		44.0	28.2	53.4	0.0	36.1	0.0	0.0			19.4
生	12.52	15.21	11.81	17.13	14.56	11.26	16.41	14.23	14.85	11.24	18.64	13.34	11.59	11.95	11.20	12.86	16.06	10.27	11.95	13.64	12.73	12.08	10.74	11.48	10.40	13.60	14.22	13.52	9.55	12.94	12.65	13.17	06.6		11.46	11.04	15.42	10.92	17.91	96.6	13.00		12.04	10.02
FE	34731.2	42827.5	43091.3	36190.2	44812.1	43029.5	48935.9	43768.3	47782.5	41867.8	40829.7	54588.0	40311.0	42936.9	51952.3	44246.0	43056.2	41454.3	41321.6	47762.5	42151.4	41640.5	44162.1	42113.3	46017.1	38646.5	40072.3			45101.1	49647.0	40098.5	43410.4	48414.0	36905.3	55584.9	39418.9	44658.6	35804.9	39942.6	36899.4	36967.4	38884.2	44240.9
ED	1.5560	2.1311	1.8430	1.6253	1.9906	1.6367	2.0149	1.7063	2.3411	1.7034	1.6553	2.9108	1.6753	1.8759	2.0803		2.4259	1.9199	1.8835	2.1446	1.9053	1.9135	1.3822	1.8419				1.7112			2.2904	1.6544	1.9550	2.2485	1.4097		3.1779	1.0469	1.1249	1.8907	1.5891	1.7711	1.8375	1.4177
CS		3.56	4.43	3.45	3.79	4.87	3.57	4.62	3.25	4.39	5.20	3.41	4.40	5.32	4.77		2.98	5.36	3.86	3.33	4.24	4.31	5.42				2.91	4.05							5.30		2.70	4.43	4.54	4.24	4.16	4.17		5.70
ANID	ATT222	ATT223	ATT224	ATT225	ATT226	ATT227	ATT228	ATT230	ATT231	ATT232	ATT235	ATT238	ATT239	ATT241	ATT242	ATT243	ATT244	ATT245	ATT246	ATT247	ATT249	ATT250	ATT252	ATT253	ATT254	ATT256	ATT257	ATT258	ATT259	ATT260	ATT261	ATT262	ATT264	ATT265	ATT266	ATT267	ATT268	ATT269	ATT270	ATT271	ATT273	ATT275	ATT276	ATT277

ANID	macro_gr	macro_grp Chem2012	CERAMIC TYPE	MATERIAL	SOURCE	STATE	SITE_NAME	SITE_NO	AS	ΓA	ΓΩ	ND	SM	n	YB CE	E C0	CR
ATT278	Group-D	El Paso Core	El Paso Brown	Pottery	MURR	Ϋ́	41EP05488	41EP05488	9.22		0.5756	40.93	8.90	3.97 4.	4.10 101.16		
ATT280	Group-D	El Paso Core	El Paso Brown	Pottery	MURR	X	41EP05488	41EP05488	4.38	62.62 0		52.34 10	10.15 3	3.11 4.	4.32 111.46		29.61
ATT282	Gronp-D	El Paso Core	El Paso Brown	Pottery	MURR	TX	41EP05488	41EP05488	6.67	28.96 0	0.5171	45.23 8	8.62 2	2.62 3.	3.74 108.12	2 4.58	24.44
ATT283	G-dno-D	El Paso Core	El Paso Brown	Pottery	MURR	X	41EP05488	41EP05488	5.62	50.51 0	0.5315	42.73	8.53 3	3.61 3.	3.91 100.61	1 5.91	28.69
ATT284	Group-D	El Paso Core	Jornada Brown	Pottery	MURR	X	41EP05488	41EP05488	6.12						_		
ATT285	Group-D	El Paso-2	Jornada Brown	Pottery	MURR	ĭ	41EP05488	41EP05488	7.40		0.5404	40.19	8.42 3	3.59 3.	3.97 96.68	9.74	51.88
ATT286	Gronp-D	El Paso Core	Jornada Brown	Pottery	MURR	ĭ	41EP05488	41EP05488	3.79	70.85 0		60.80		4.02 4.	4.36 140.41	1 5.74	24.22
ATT287	Gronp-D	El Paso Core	Jornada Brown	Pottery	MURR	ĭ	41EP05488	41EP05488	9.17						_	3 6.31	34.71
ATT288	Group-D	El Paso Core	Jornada Brown	Pottery	MURR	X	41EP05488	41EP05488	3.97						-		24.35
ATT290	Group-D	El Paso Core	El Paso Brown	Pottery	MURR	ΙX	41EP05488	41EP05488	3.06		0.5870	45.18		4.39 3.	3.97 109.07	7 8.79	
ATT292	Group-D	El Paso Core	El Paso Brown	Pottery	MURR	ΙX	41EP05488	41EP05488	98.8	29.99	0.6105	47.70	9.92 4	4.16 4.	4.52 113.70	0 7.72	34.81
ATT294	G-dno-D	El Paso Core	El Paso Brown	Pottery	MURR	ĭ	41EP05488	41EP05488	8.25	57.52 0	0.6254	48.25	9.83 5	5.25 4.	4.46 107.79	9 6.05	35.39
ATT295	Group-C2	Unas.	Alma Scored	Pottery	MURR	ĭ	41EP05488	41EP05488	4.73	33.33 0		27.60		3.15 2.	2.90 66.86	19.6	39.19
ATT296	Group-D	El Paso Core	El Paso Polychrome	Pottery	MURR	ĭ	41EP05488	41EP05488	7.26	55.87 0	0.5798		9.58 5	5.04 4.	4.26 112.16	9.97	29.15
ATT297	Group-D	El Paso Core	El Paso Bichrome (B/Br)	Pottery	MURR	X	41EP05488	41EP05488	5.88	61.11 0	0.5871	48.84		4.96 4.	4.14 111.51	1 5.35	27.16
ATT298	Group-D	El Paso Core	El Paso Polychrome	Pottery	MURR	X	41EP05488	41EP05488	7.15	69.11 0	0.5631	51.99 10	_	5.02 4.		8 5.12	
ATT299	Group-D	El Paso Core	El Paso Polychrome	Pottery	MURR	X	41EP05488	41EP05488	4.82			_				6 6.25	
ATT301	G-dno-D	El Paso Core	El Paso Polychrome	Pottery	MURR	X	41EP05488	41EP05488	4.88	75.00 0	0.5246	50.49	9.22 3	3.55 3.	3.97 124.13	3 6.68	28.35
ATT302	G-dno-D	El Paso Core	Jornada Brown	Pottery	MURR	MN	LA 008055	LA 008055	2.81	86.38	0.5503	61.08 12	12.03 4	4.16 4.	4.39 181.99	9 5.47	24.90
ATT303	Gronp-D	El Paso Core		Pottery	MURR	NN	LA 008055	LA 008055	4.19	42.63 0				3.19 2.	2.87 85.76	6 4.29	27.41
ATT311	Group-D	El Paso Core		Pottery	MURR	MN	LA 008055	LA 008055	2.45	61.91	0.5164	47.36	8.69	3.18 3.	3.75 129.51	1 6.42	28.37
ATT313	Gronp-D	El Paso Core	Jornada Brown	Pottery	MURR	MN	LA 130727	LA 130727	5.52	89.64	0.6496	57.50 11	11.19 4	4.23 4.	4.98 155.12	7.16	28.27
ATT314	G-dno-D	El Paso-2	El Paso Polychrome	Pottery	MURR	ΣN	LA 130727	LA 130727	6.94	50.32	0.5572	39.91	8.51 3	3.19 4.	4.31 91.52	2 8.53	63.11
ATT318	Group-D	El Paso Core	Jornada Brown	Pottery	MURR	MN	LA 130727	LA 130727	5.13	87.78			10.21 6		6.48 175.95		
ATT319	Gronp-D	El Paso Core	El Paso Brown	Pottery	MURR	ΣN	LA 130727	LA 130727	3.76	79.37 0		65.93 17			4.03 134.75		
ATT322	Gronp-D	El Paso Core	Jornada Brown	Pottery	MURR	ΣN	LA 130727	LA 130727	3.19								
ATT323	Group-D	El Paso Core	El Paso Polychrome	Pottery	MURR	MN	LA 130727	LA 130727	6.21			_		3.71 3.		8 8.09	
ATT324	Gronp-D	El Paso Core		Pottery	MURR	NM	LA 130727	LA 130727	5.77					3.73 3.			
ATT326	Gronp-D	El Paso Core	El Paso Bichrome (R/Br)	Pottery	MURR	NM	LA 130727	LA 130727	7.07		0.5949	67.14 17	11.22 3	3.86 5.	5.01 148.75	5 8.40	29.86
ATT329	Gronp-D	El Paso Core	Jornada Brown	Pottery	MURR	MN	LA 130727	LA 130727	2.89	0.20	0.4596	50.75		5.56 3.	3.08 119.52	2 11.54	15.65
ATT330	Group-D	El Paso Core	El Paso Brown	Pottery	MURR	Σ	LA 130727	LA 130727	5.89			_			_		
ATT333	Gronp-D	El Paso Core	_	Pottery	MURR	M	LA 130727	LA 130727	4.85			`					
ATT338	Gronp-D	El Paso Core		Pottery	MURR	M	LA 132521	LA 132521	4.85							9 10.85	
ATT339	Group-D	El Paso Core	El Paso Brown	Pottery	MURR	ΣN	LA 132521	LA 132521	1.41	62.50 0		46.79		3.99 3.	3.33 119.63		20.85
ATT340	Group-D	El Paso Core	El Paso Brown	Pottery	MURR	MN	LA 132521	LA 132521	4.06	63.67 0	0.4512	44.80	8.22 3	3.75 2.	2.99 116.60	0 7.05	22.27
ATT341	Group-D	El Paso Core	wn	Pottery	MURR	MN	LA 132521	LA 132521				60.52		5.01 4.			23.58
ATT343	Group-A	Mimbres-07B	Alma Rough	Pottery	MURR	NM	LA 129562	LA 129562	3.39	144.97	`	133.61 25		4.42 8.	8.58 269.94	4 14.57	108.09
ATT344	Group-A	Unas.	Alma Plain	Pottery	MURR	MM	LA 129562	LA 129562		199.10	1.5177 1	186.73 35		6.15 12.	12.55 377.28		23.55
ATT345	Group-B	Unas.	Alma Rough	Pottery	MURR	MM	LA 129562	LA 129562	2.84	91.35	1.0721		17.44 4	4.15 8.		3 11.54	
ATT346	Group-A	Unas.	Alma Rough	Pottery	MURR	MM	LA 129562	LA 129562	1.59	97.33 0	0.7185	83.07 16	16.73 4		5.25 139.79		12.72
ATT347	Group-B	Unas.	Alma Rough	Pottery	MURR	MN	LA 129562	LA 129562	3.26		_	7			7.97 212.49	,	
ATT348	Group-B1	Mimbres-05A	Alma Rough	Pottery	MURR	M	LA 129562	LA 129562	4.41							_	
ATT349	Group-A	Mimbres-10	Alma Rough	Pottery	MURR	¥	LA 129562	LA 129562	4.45					6.92 7.	_		28.37
ATT350	Group-A	Mimbres-10	Alma Rough	Pottery	MURR	MN	LA 129562	LA 129562	4.34	66.02 0	0.9093	55.71 17	11.74 8	8.11 6.	6.31 121.75	5 5.71	28.01

>	77.70	59.19	62.02	49.92	72.69	93.32	71.44	71.58	46.12	79.41	86.73	83.14	63.72	60.35	78.00	65.67	62.28	61.08	93.33	57.82	68.26	102.48	97.48	87.36	90.05	82.21	115.45	122.56	103.25	106.79	109.92	76.76	00.67	85.24	81 13	109.45	35.53	78.30	35.56	88.75	100.15	53.42	48.69
I	3989.1	4458.0	3593.4	4268.5	3925.9	4011.0	5364.2	4407.1	3,0998	5049.1	4684.0	4685.8	3430.5	4185.7	4540.1	4291.6	4364.1	4090.5	4662.2	3941.1	4625.6	5030.1	4820.1	3857.1	5611.2	4662.4	4210.5	4419.1	5374.5	5127.0	6371.8	70501	1.0C04 59.45.0	4430.6	5437.3	5675.3	2744.3	6590.2	1988.2	7142.6	2904.0	3237.0	2926.5
NA	12201.6	15200.3	15766.8	14565.2	14192.0	10954.7	16874.5	12729.1	15245.9	13714.8	11244.3	11926.8	9329.7	13445.1	13642.5	14400.8	15523.1	13181.4	26029.7	14825.3	16003.2	21836.2	11325.4	24400.4	21377.4	22023.1	16681.8	17709.9	15908.0	21534.3	15594.0	20019.3	22003.0	24535.7	241361	18648.2	11166.6	17294.4	8819.4	17137.6	10871.8	16099.7	15987.9
MN	397.4	454.1	346.7	476.6	401.4	356.9	479.7	452.8	523.9	538.6	537.6	445.9	576.1	497.9	454.4	396.8	388.3	395.7	583.0	332.2	1.099	466.7	363.5	813.8	453.0	402.2	442.8	501.8	527.4	1012.2	583.0	0.213	170 E	587.5	0809	498.9	273.2	386.9	319.5	511.7	718.3	387.2	348.8
¥	26566.5	27553.4	28714.3	29600.3	29935.1	22617.5	35002.1	28909.6	29575.6	24436.8	28416.1	26961.3	21331.6	27915.2	29394.4	31528.5	28349.1	30807.7	29654.0	29811.3	27166.3	28414.2	30826.2	26696.2	31376.8	30353.1	29321.7	32752.4	30298.1	30860.6	30885.3	30097.4	21056 E	2,9620.2	29968 4	38532.4	42520.6	36671.0	47777.9	37785.9	35265.5	35647.6	35211.8
DY	5.982	6.725	5.816	5.394	6.243	6.152	7.079	6.410	2.699	5.496	6.705	6.663	4.256	5.220	6.289	6.484	7.395	5.772	7.879	5.087	5.689	7.748	6.831	7.888	7.615	9.085	6.430	5.773	7.718	5.684	8.248	7.2457	1.301	5 366	7.137	18.856	28.778	14.487	9.810	14.721	5.626	10.886	9.214
CA	14126.8	22792.4	15072.6	16251.8	14229.9	27031.4	14087.2	15341.0	13852.0	22655.4	16126.8	14671.3	30186.6	20686.0	14308.4	15749.2	23414.3	16799.6	13919.5	8467.7	9992.2	11663.8	12815.9	8565.7	12094.4	14576.4	19249.8	14793.2	14530.9	17922.1	15278.3	1/2/6/1	18706 1	12141 6	14675.0	12658.4	6635.5	9390.0	4133.1	9242.6	10891.3	9527.2	10788.7
BA	1064.9	1189.4	1150.0	1045.9	1035.1	1325.9	1190.4	8.096	927.8	811.9	1122.0	1.096	722.2	1205.5	1255.0	1175.7	1463.9	1406.8	1535.9	624.7	1248.7	941.8	1282.4	716.3	1218.8	1413.8	1534.4	1134.8	1135.0	1206.0	952.0	13/1.2	0.1001	1169 9	1227.3	1197.1	992.8	1028.4	812.4	1012.4	881.3	791.3	802.2
AL	92416.1	82747.3	88490.2	81671.9	88793.2	79624.2	79738.3	95545.4	84819.1	80072.9	98687.3	103351.5	68362.7	87703.6	93380.7	89733.1	84366.8	88369.4	95825.4	81305.9	77301.8	90886.4	89323.7	89645.9	97227.7	100882.6	99833.7	104427.4	91616.1	103013.7	91645.1	8.181.6	0.71040	827771	899477	90421.9	81964.0	81902.7	89934.5	86494.9	81665.7	83087.2	82320.9
ZR	345.7	319.0			313.8	286.3		295.9	337.4	361.5	397.1	340.8	218.1	334.8	299.2	292.1	341.1	328.8	328.4	319.8	280.8	362.9	260.6			295.6			392.7	248.9		_	7000		_		337.4	380.0	253.0	425.5			319.7
NZ	78.6	59.4		8.69	1.69	71.8	77.8	91.2	71.6	85.9	76.8	84.4	8.89	76.5	75.1	79.2	6.69	68.1	93.8	9.99	77.5	73.1	72.6	93.0					85.7	7.77			74.3			_		89.9	66.4	103.1			8.69
H		19.49		21.20	, 22.02	18.74	16.54	22.31	21.35	15.80	24.63	31.00	9.62	20.27	22.10		20.32	20.47	18.69	23.21	14.25	18.43	23.75	25.91	15.46							15.60				_	39.70	22.59	61.00	24.70			40.58
۲ TB	3 1.11	3 1.28	1.05	5 1.13	3 1.27	1.07	1.41	1.24	0.99	5 1.17	3 1.29	3 1.30	0.80	3 1.21	1.17	1.28	1.34	1.16	3 1.76	2 0.82	1.10	7 1.55	1.07	1.50			1.24	1.17					001.00				4.94	5 2.51	3 1.91	4 2.72	1.00		3 1.66
TA	2.4303	2.6118		2	2.8973	2.1191		2.5566	2.7080	2.6426	2.6038	2.6123	1.0322	2.7018	2.8194	2.6601	2.7861	2.6332	2.9268		2.5347	3.2427	2.0839	5.3270								2417.7					1.3200	1.5916	0.9013	1.5914			2.4778
SR	297.5	293.9	328.9	285.3	330.6	295.3	327.0	240.0	305.3	264.3	302.8	280.2	316.8	322.3	288.5	330.8	316.8	299.0	279.7	142.1	203.8	390.9	627.3	325.9	396.9	574.5	722.9	564.2	809.1	626.8	569.7	493.3	321.3	313.9	259.6	336.6	90.2	167.1	114.7	208.9	273.8	192.9	202.0
SC	10.10	8.58	8.66	8.77	9.12	10.93	8.72	10.39	8.20	9.21	9.95	9.88	8.59	8.97	90.6	8.93	8.46	8.37	12.75	7.43	9.40	11.89	12.31	11.86	12.03	12.97	13.53	13.43	10.81	7.77	10.84	10.71	10.42 0 0	8.57	9.33	21.49	10.97	16.07	10.20	16.77	10.25	8.63	8.67
SB	0.7529	0.5567	0.5053	0.5665	0.5015	0.6888	0.4749	0.7689	0.4356	0.5191	0.6880	0.6829	0.6632	0.6688	0.4853	0.4887	0.5438	9009.0	0.4818	0.5074	0.5767	0.5689	0.7146	0.6705	0.5242	0.4394	0.5123	0.5436	0.5013	0.3510	0.5231	0.54/3	0.3330	0.3030	0.5561	0.2227	0.1446	0.2200	0.3765	0.3115	0.6230	0.4884	0.4480
RB	130.00	111.89	129.08	129.71	120.14	123.04	97.13	122.41	124.73	87.20	120.73	127.27	103.85	125.09	120.38	127.16	116.60	124.39	91.11	130.23	85.85	99.96	131.29	138.29	99.64	92.19	95.72	101.98	109.31	95.85	108.76	75.30	116 74	119 34	115.23	156.65	172.60	152.14	265.18	138.56	139.33	206.97	204.61
Z	33.8	0.0			0.0	39.1	46.7	0.0	31.1	0.0	0.0	0.0	0.0	0.0	0.0		31.5	0.0	24.0	15.0	25.3	46.1	0.0	0.0	0.0	38.1	40.2			_			0.0				52.5	0.0	0.0	0.0			0.0
生	13.34	12.58	13.34		13.05	11.27	13.12	11.21	12.50	13.60	13.57	13.32	7.98	12.54	12.30	11.38	12.80	11.43	11.10	13.41	10.13	14.12	12.03	20.52	9.78	9.33	8.02	7.52	14.33	9.13	11.81	7.52	14.20 Q E 2		_	14.87	12.64	15.22	06.6	17.35	6.33		13.58
FE	43161.9	36185.3	36535.4	37641.8	39372.4	36210.8	37667.8	43354.2	34946.8	36507.4	41884.0	42282.6	26457.9	37309.1	39002.9		36309.2	35804.7	35049.9	31313.4	30076.5	29957.9	40533.1	32999.1			42518.2	44688.3			48569.6	31438.0		27568 4	32167.6		36546.0	41985.2	27808.5	46390.6			27000.8
EN	1.6951	1.8992	1.6109	1.6120	1.7414	1.4701	2.4864	1.7707	1.5066	1.8473	1.8371	1.7270	1.1846	1.7277	1.7786	1.8562	1.9992	1.7082	3.5833	1.0616	3.76 2.0349	3.99 2.7756	1.5474	1.9728	2.9454	3.3504	2.5024	2.4020	2.2431	1.9200	2.2142	2.8994	2.2703	1 9148	3 97 7 7 7 7 60	3.3378	4.1452	2.5626	2.2091	2.8006	1.3350	1.2799	1.3420
CS	4.95	3.80	3.91	4.05	3.83	29.62		4.30	3.58	3.96	4.57	4.92	7.19	3.97	3.83		3.74	4.33	4.60	4.02	3.76	3.99	5.28	4.13	4.40				3.90			4.00	3.90	4.30	3 92	3.01	2.46	2.65	7.33	2.89	5.44		7.84
ANID	ATT278	ATT280	ATT282	ATT283	ATT284	ATT285	ATT286	ATT287	ATT288	ATT290	ATT292	ATT294	ATT295	ATT296	ATT297	ATT298	ATT299	ATT301	ATT302	ATT303	ATT311	ATT313	ATT314	ATT318	ATT319	ATT322	ATT323	ATT324	ATT326	ATT329	ATT330	A11333	A11330	ATT340	ATT341	ATT343	ATT344	ATT345	ATT346	ATT347	ATT348	ATT349	ATT350

ANID	macro_grp	Chem2012	CERAMIC TYPE	MATERIAL	SOURCE	STATE !	SITE_NAME	SITE_NO	AS	ΓA	Π	S	SM	U YB	3 CE	00	CR
ATT351	Group-A	Mimbres-10		Pottery	MURR		LA 129562	LA 129562	3.65	67.91 0.8	0.8508 5	59.49 11.88	88 7.30	30 5.70	0 135.08	5.98	28.69
ATT352	Group-A	Mimbres-10	Alma Rough	Pottery	MURR	NN I	LA 129562	LA 129562	3.89	66.91 0.5	0.9666 5	55.65 11.85	85 7.09	09.9 60	0 124.24	5.94	28.54
ATT353	Group-A	Mimbres-07A		Pottery	MURR	NM	LA 129562	LA 129562	1.64	156.11 1.5	1.5152 14	146.05 28.20	20 5.19	9 11.76	5 331.66	7.93	38.54
ATT354	Group-C2c	Mimbres-48	Alma Rough	Pottery	MURR		LA 129562	LA 129562	3.31	28.94 0.3	0.3846 2	27.27 5.	5.72 1.71	71 2.84		11.95	16.34
ATT355	Group-A	Mimbres-10	Alma Rough	Pottery	MURR	NN I	LA 129562	LA 129562	3.11	93.77 1.3	1.3132 8	82.25 16.52	52 10.43		8 179.89	7.40	31.47
ATT356	Group-A	Mimbres-07A	Alma Rough	Pottery	MURR	I WN	LA 129562	LA 129562	3.90	144.65 1.3	1.3430 13	137.30 26.43	43 6.99	10.04	4 307.02	8.34	35.11
ATT357	Group-C2c	Mimbres-48		Pottery	MURR		LA 129562	LA 129562	3.25	24.67 0.3	0.3920 2	25.09 5.	5.68 1.95	3.06	6 61.42	15.55	15.12
ATT358	Group-C2	Unas.	Alma Plain	Pottery	MURR	MN	LA 129562	LA 129562	1.86	31.72 0.3		23.78 5.	5.28 1.96	96 2.46	6 63.24	10.37	25.33
ATT360	Group-A	Mimbres-07A	Alma Rough	Pottery	MURR	NN N	LA 129562	LA 129562	0.00	431.43 1.9	1.9809 47	479.44 69.32	32 8.24	17.92	2 665.69	69.9	44.28
ATT361	Group-B	Unas.	Alma Rough	Pottery	MURR	MN	LA 054814	LA 054814	1.26	41.85 0.4	0.4051 3	33.29 6.	6.37 2.88	38 2.99	9 72.69	10.16	29.44
ATT362	Group-B	Unas.	Alma Plain	Pottery	MURR	NN N	LA 054814	LA 054814	2.30	61.63 0.7	0.7719 5	53.25 11.43	43 5.92	2 5.33	3 119.97	10.79	46.23
ATT363	Group-A	Mimbres-07A	Alma Rough	Pottery	MURR		LA 054814	LA 054814	2.31	170.32 1.7	1.7133 16	166.94 32.41	41 8.98	13.17	7 369.89	9.04	35.28
ATT364	Group-A	Mimbres-07A	Alma Rough	Pottery	MURR	I WN	LA 054814	LA 054814	2.17 1	172.37 1.5	1.5950 16	163.30 32.25	25 8.99	12.54	4 364.06	8.89	34.17
ATT365	Group-A	Mimbres-07A	Alma Plain	Pottery	MURR	- N	LA 054814	LA 054814	0.00	159.92 1.4	1.4005 15	154.95 29.56	56 7.89	10.81	1 316.77	10.64	55.74
ATT366	Group-A	Mimbres-10	Alma Plain	Pottery	MURR	I WN	LA 054814	LA 054814	2.94	86.38 1.6	1.6343 8	85.70 18.60	8.15	12.37	7 201.06	5.39	27.62
ATT367	Group-B1	Unas.		Pottery	MURR		LA 054814	LA 054814			0.4853 2	24.79 4.91	91 3.95	3.18			16.69
ATT368	Group-A	Mimbres-07A	Alma Rough	Pottery	MURR	I WN	LA 054814	LA 054814	2.08	160.84 1.3	1.3747 15	158.92 29.41	41 7.64	10.66	6 319.34	10.46	58.80
ATT369	Group-A	Mimbres-07A	Alma Rough	Pottery	MURR	I WN	LA 054814	LA 054814	2.01	169.30 1.6	1.6687 16	169.46 32.37	37 8.41	11 12.76	6 375.39	10.22	34.74
ATT370	Group-A	Mimbres-07A	Alma Plain	Pottery	MURR	NN N	LA 054814	LA 054814	2.14 1	166.19 1.6	1.6829 16	162.55 31.90	90 8.56	56 12.93	3 369.78	9.02	32.74
ATT371	Group-A	Mimbres-07A	Alma Plain	Pottery	MURR	NN N	LA 054814	LA 054814	4.25 1	154.38 1.2	1.2752 14	145.76 27.74	74 7.06	17.6 9.71	1 314.55	8.52	36.55
ATT372	Group-A	Mimbres-07A	Alma Plain	Pottery	MURR	l MN	LA 054814	LA 054814	1.92	162.63 1.3	1.3961 15	155.41 29.85	85 7.06	10.67	7 321.14	9.85	61.52
ATT373	Group-B	Unas.	h	Pottery	MURR	NN N	LA 054814	LA 054814	2.40		1.1163 10	105.53 20.12	12 4.33	3 8.75	5 230.43	14.22	40.30
ATT374	Group-A	Mimbres-10		Pottery	MURR	NN N	LA 054814	LA 054814	4.06	64.55 0.8	0.8014 5	57.40 11.41	41 6.66	5.54	4 131.37	2.81	24.65
ATT375	Group-B1	Mimbres-04C		Pottery	MURR	NN I	LA 054814	LA 054814	2.36	37.11 0.3			5.19 3.82	32 2.50		8.95	31.80
ATT376	Group-A	Mimbres-07A	Alma Plain	Pottery	MURR	I WN	LA 054814	LA 054814	3.97	144.87 1.1		140.37 26.23	23 5.22	9.24	4 307.46	7.84	34.08
ATT377	Group-B	Unas.	Mimbres B/W Style Indeter. Pottery	Pottery	MURR		LA 059652	LA 059652	2.24	41.34 0.5	0.5445 2		5.79 4.48	18 3.58	8 84.28	5.88	31.67
ATT378	Group-A	Mimbres-07A	Alma Rough	Pottery	MURR	I WN	LA 059652	LA 059652	0.00	195.07 1.7	1.7764 19	192.32 37.86	86 11.38	13.71	1 378.15	6.27	32.72
ATT379	Group-C2b	Mimbres-47	Alma Rough	Pottery	MURR		LA 059652	LA 059652			0.2663 4		8.10 2.83		_	6.34	24.02
ATT380	Group-C2	Unas.	Alma Punched	Pottery	MURR	l MN	LA 059652	LA 059652	2.72	34.15 0.3	0.3469 2	27.00 5.	5.63 2.17	7 2.54	4 65.54	10.14	38.41
ATT381	Group-C2	Unas.	Mimbres B/W Style Indeter. Pottery	Pottery	MURR		LA 059652	LA 059652		27.19 0.3			5.63 2.62	52 2.85		11.82	24.26
ATT382	Group-B	Unas.	Three Circle R/W	Pottery	MURR		LA 059652	LA 059652									55.55
ATT383	Group-B1	Mimbres-04C	V Style Indeter.	Pottery	MURR		LA 059652	LA 059652									31.78
ATT385	Group-C2b	Mimbres-41		Pottery	MURR		LA 059652	LA 059652						2.30		11.84	24.68
ATT386	Group-B	Unas.	Alma Rough	Pottery	MURR		LA 059652	LA 059652								4.23	27.26
ATT387	Group-B	Unas.	Mimbres B/W Style Indeter. Pottery	Pottery	MURR		LA 059652	LA 059652	1.34					3.76	_	1	67.31
ATT388	Group-B	Unas.		Pottery	MURR		LA 059652	LA 059652	1.42		0.7293 5	51.41 9.	9.87 2.72	72 5.61			28.37
ATT389	Group-A	Mimbres-07A*		Pottery	MURR		LA 059652	LA 059652		224.43 1.4	1.4129 16	3		l	8 324.41	7.70	31.83
ATT390	Group-B1	Mimbres-05B	Alma Scored	Pottery	MURR	NN I	LA 059652	LA 059652	1.81	46.67 0.6	0.6301 4	43.18 8.	8.02 6.58	4.37	7 86.44	4.07	40.68
ATT391	Group-B	Unas.	Alma Plain	Pottery	MURR		LA 059652	LA 059652	3.11	58.79 0.5	0.5744 4	49.63 8.	8.50 4.78	78 4.23	3 107.03	6.63	57.96
ATT392	Group-C2b	Mimbres-47	Alma Rough	Pottery	MURR		LA 059652	LA 059652	3.38	43.49 0.2	0.2626 4	41.27 7.	7.60 2.7	71 2.25	5 93.08		31.18
ATT393	Group-C1	Mimbres-24	Alma Plain	Pottery	MURR		LA 059652	LA 059652	5.72	40.86 0.4	0.4358 3		7.53 2.21	3.53	3 85.74	13.90	33.91
ATT394	Group-B	Unas.	Style Indeter.	Pottery	MURR		LA 059652	LA 059652	2.49		0.5866 3	37.67					51.10
ATT395	Group-B1	Mimbres-05B	d	Pottery	MURR		LA 059652	LA 059652		_			8.90 4.75				34.75
ATT396	Group-C2b	Mimbres-47	Alma Rough	Pottery	MURR	NN N	LA 059652	LA 059652	2.20	39.57 0.2	0.2521 3	37.73 6.	6.60 2.17	7 1.97	7 81.30	5.57	24.18

>	48.61	61.14	65.51	102.47	62.54	66.55	92.66	76.80	57.54	105.46	80.09	57.68	65.87	62.34	41.41	46.78	98.89	67.13	68.05	67.14	78.61	112.05	50.04	58.45	50.46	56.75	63.99	56.48	64.62	91.64	78.00	65./1	67.50	40.11	108.96	41.39	63.49	27.66	76.74	61.35	65.98	73.16	34.59	56.02
I	3292.3	3410.0	5042.8	3026.7	4176.3	4887.9	2709.1	2713.7	5799.4	9.7665	4307.7	5290.6	4880.5	5716.3	2743.6	3727.3	5555.7	5579.4	5533.9	5778.1	5793.0	7393.0	2490.1	4154.4	5196.5	2554.3	5871.0	2939.2	3482.1	4254.4	4704.9	2918.4	3232.1	2772.5	0.9289	2600.7	4948.0	4113.9	4539.6	2953.1	3617.3	3966.6	2441.0	2917.3
NA	15676.1	16074.6	15303.3	15929.9	16627.7	14067.8	14496.3	18810.4	17756.6	16644.5	15285.7	16226.2	16675.6	16655.2	14064.7	15716.3	17691.3	16261.2	16146.2	14347.2	17223.0	15390.2	15454.4	15817.0	14642.5	13048.0	15698.6	19747.1	14374.4	15298.5	16611.7	18244.0	1/263.6	130/6.2	156/4.6	13917.7	15978.6	13658.9	14896.1	12910.7	19254.3	16606.8	10953.4	18990.2
M	368.8	357.0	470.1	1011.6	583.4	321.9	1204.7	794.7	191.4	410.6	662.9	278.0	376.0	353.9	293.5	319.5	353.7	524.7	338.4	458.3	345.0	584.6	140.4	611.4	249.4	285.9	163.6	145.1	651.1	1003.4	466.9	5//.0	5/1.4	258.5	1005.9	289.8	514.4	346.4	268.8	301.6	724.9	496.3	382.0	125.8
¥	35387.1	33759.6	33553.1	26226.0	30866.0	33340.1	28678.5	29337.3	37708.0	27058.4	30844.9	34714.9	31729.3	31546.6	32103.4	33393.1	34366.4	30368.7	31464.4	30216.1	31538.3	32799.4	36288.7	30397.5	31577.3	27405.3	30469.2	23628.8	31920.3	26642.3	24933.5	28000.3	31047.2	34394.4	20640.9	35835.9	35327.8	32242.0	28755.9	28976.7	20497.5	29809.6	36622.3	25543.2
DY	9.451	10.375	22.653	4.417	12.997	20.660	4.554	3.825	43.929	4.288	9.338	26.434	24.272	20.467	17.351	3.791	21.587	23.742	25.603	19.824	21.350	16.526	8.842	3.933	18.716	4.200	27.931	4.324	3.650	3.822	6.507	4.255	3.500	1.551	4.641	8.048	29.923	6.064	5.109	4.101	5.596	7.009	6.164	4.076
CA	9207.8	11554.5	9543.7	22586.0	9467.0	7866.0	19818.9	16889.9	8981.0	14519.5	9315.4	9513.5	10830.4	9442.5	7414.2	12651.9	10783.6	9073.7	8778.5	9295.1	10543.2	11966.7	6261.6	13487.8	8581.8	15273.9	10659.2	10054.6	25131.9	13955.5	10253.9	14860.5	5789.6	8192.4	0.6///1	7015.8	10336.9	9133.6	11437.6	9234.7	12355.1	10989.9	8916.5	11349.6
BA	744.8	779.0	919.0	823.9	731.6	1060.6	1221.3	1190.7	864.3	1011.6	698.2	925.9	845.3	918.4	729.0	1069.4	841.3	919.7	821.4	1158.7	878.2	871.0	826.4	775.0	6.806	557.5	823.3	9.611	933.8	708.8	525.2	845.9	1313.9	907.3	61/.2	808.8	1146.5	932.8	1159.7	996.5	839.0	621.9	1061.7	794.5
AL	84249.8	82150.9	85854.0	94203.5	88261.1	80334.3	91024.0	86634.4	94774.3	9.06988	81542.5	84768.4	80280.1	73528.1	85767.5	91396.7	84113.4	79507.1	81919.3	79545.8	83265.7	8.00698	85049.0	73973.7	81527.4	84715.4	86658.7	6.80086	71724.2	95712.1	82218.7	8/48/.1	82257.1	/1954.3	80972.0	77381.0	87764.5	77447.2	78867.1	93593.3	96026.0	81642.3	89797.1	95745.1
ZR	267.8	300.0	475.4	9.801	489.2	475.2	139.8	167.5	443.4	288.3	281.0	581.8	599.4	485.1	200.0	188.9	461.9	621.4	599.0	478.2	538.9	455.3	251.4	179.9	459.9	159.2	594.2	139.7	169.7	193.1	184.9	127.1	126.6	138.6	234.0	168.5	379.3	188.9	175.1	0.0	179.0	238.8	154.8	7.76
NZ	72.3	70.2	105.1	124.1	85.5	101.8	88.3	72.1	147.7	104.4	8.06	108.2	114.2	114.3	76.9	51.1	113.6	112.1	114.6	92.4	113.3	114.6	58.2	67.9	84.2	72.6	107.3	59.1	76.2	100.7	79.5	6/.5	54.1	53.8	129.3	77.6	109.3	84.3	75.0	62.3	104.6	70.3	70.6	61.6
H	37.92	40.79	(~)			31.62		9.19	68.31	15.64	28.73	38.60	39.04	33.28	41.37		32.54	36.88	36.87	36.50	33.58	24.38	41.29		29.88	21.27	7	8.83										23.49	_				. 7	8.58
A TB	3 1.62	5 1.71	3.86	0.00	1 2.18	5 3.84	5 0.75	1 0.68	3 8.67	1 0.71	5 1.62	5 4.43	7 4.45	3 4.07	3.00	9.0	3.96	3 4.36	5 4.51	1 3.60		1 2.85	1.44	0.67	3.42	0.74	5.12		0.70	_					_			5 1.07		_	3 1.15	_		0.87
TA	2.1228				2.8254	1.6496	0.5975	0.6544	1.7493	1.4814	1.6725	2.0545	1.9477	1.8098	2.7635		1.7435	1.9360	2.0496	1.6784	1.7727	1.4801	2.0622		`					_								1.7436			1.0283			0.6180
SR	161.7	217.0	189.5	660.9	198.6	164.1	672.7	602.6	141.9	360.5	146.7	115.1	128.2	192.3	116.9	275.4	180.5	155.5	121.9	164.2	205.7	179.9	136.2	338.0	167.7	246.3	150.3	422.5	383.7	454.4	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
SC	8.81	8.88	14.74	12.83	10.13	13.46	12.09	9.35	20.89	9.47	11.65	15.29	15.05	16.19	8.78	6.92	16.47	14.89	14.60	13.76	16.55	18.66	7.16	7.19	12.57	8.26	15.51	7.16	7.96	11.55	11.31	8.21	7.33	7.41	10.39	7.47	14.73	9.36	10.18	8.58	10.55	9.56	8.74	7.30
SB	0.4697	0.4363	0.3698	0.5081	0.5648	0.3537	0.4967	0.2259	0.1746	0.3991	0.4715	0.2305	0.2351	0.2910	0.4951	0.3380	0.2248	0.2798	0.2467	0.3194	0.2231	0.2369	0.6298	0.3898	0.2848	0.4344	0.2062	0.3730	0.3876	0.5130	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000
RB	205.84	205.05	128.95	96.34	205.58	135.84	90.98	83.28	142.85	98.55	185.38	140.10	145.64	141.49	223.76	127.83	155.38	136.79	146.97	146.94	148.23	149.05	235.99	132.86	141.92	165.10	143.58	101.89	115.25	133.52	133.30	140.06	75.75	199.42	92.53	198.55	116.00	162.04	100.82	120.14	104.08	150.00	153.38	85.07
Z	0.0	0.0		0.0	0.0	0.0	0.0	0.0	83.7	0.0	50.7	77.4	44.5	68.1	0.0	0.0	41.8	48.5	46.8	0.0	63.3	51.5	0.0	25.7	46.5			0.0			0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
土	11.16	12.08	19.06	5.69	25.14	17.99	5.65	6.28	13.39	11.40	9.82	21.90	22.66	18.24	8.95	7.71	18.17	23.14	24.32	18.57	19.66	18.72	9.31		_		22.80			7.01	9.89	8.92	5.80	1.31	12.40	6.44	20.77	9.97				9.94	7.71	4.18
FE	27598.5	27487.5	41932.0	51298.4	30764.3	42331.3	53959.1	34296.0	35009.7	54365.2	35360.5	41355.5	40775.1	38831.4	30776.1	24914.0	36624.0	41073.5	40250.6	46821.8	36857.2	48354.1	23314.5	26366.7	44156.6	23314.6	30618.3			44405.3	39136.3	30101.5	30044.0	20684.6	59001.9	21079.0	43766.7	18156.3	33875.6	33967.4	39077.6	32564.7	19910.4	27491.4
EU	1.2847	1.3130	3.4375	1.4927	1.5889	3.2901	1.5511	1.3239	8.4875	1.3058	1.8006	3.8127	3.7946	3.6919	1.7204	1.0184	3.7738	3.7598	3.6878	3.4273	3.7294	2.9422	1.3221	1.0543			4.1635	1.9767	1.1806	1.5098	1.3238	1.4033	1.4618	1.3659	1.4696	1.2464	4.2972	1.2058	`	1.9890	1.6209	1.2876		1.5877
CS	8.16	7.86	3.35	5.16	8.72	2.99	3.83	1.68	3.48	3.77	8.15	3.31	3.30	3.07	5.75		3.73	3.35	3.25		3.81	3.45	8.51					4.21	3.35	9.33	10.68	5.67	3.12	7.30	3.35	_		5.18	3.59	4.88	15.58	10.43	5.73	3.13
ANID	ATT351	ATT352	ATT353	ATT354	ATT355	ATT356	ATT357	ATT358	ATT360	ATT361	ATT362	ATT363	ATT364	ATT365	ATT366	ATT367	ATT368	ATT369	ATT370	ATT371	ATT372	ATT373	ATT374	ATT375	ATT376	ATT377	ATT378	ATT379	ATT380	ATT381	ATT382	A11383	A11385	A11386	A1138/	ATT388	ATT389	ATT390	ATT391	ATT392	ATT393	ATT394	ATT395	ATT396

ANID	macro_grp	Chem2012	CERAMIC TYPE	MATERIAL	SOURCE	STATE	SITE_NAME	SITE_NO	AS	ΓA	Π	S QN	NS N	YB	CE	00	CR
ATT397	Group-B1	Mimbres-05B	Alma Scored	Pottery	MURR	ΜN	LA 059652	LA 059652	1.92	45.37 0.	0.6405 4	42.66 8.7	8.16 6.48	4.82	84.54	3.83	40.54
ATT398	Group-A	Mimbres-10	Alma Rough	Pottery	MURR	M	LA 059652	LA 059652		112.41 1.		93.71 18.7	71 6.95	19.6	194.95	8.63	26.81
ATT399	Group-C2b		Alma Rough	Pottery	MURR	ΝN	LA 059652	LA 059652	1.97	36.24 0.	0.3742 2	29.69 5.35	35 2.59	2.61	66.99	99.6	21.14
ATT400	Group-B1	Mimbres-05A	Mimbres B/W Style Indeter.	Pottery	MURR	M	LA 059652	LA 059652	4.42	41.95 0.	0.6159 4	40.85 9.09	33.11	4.86	90.04	10.67	56.38
ATT401	Group-C2b			Pottery	MURR	NM	LA 059652	LA 059652	2.24	30.12 0.		28.07 4.87			59.21	5.14	25.74
ATT402	Group-B1	Mimbres-04A	h	Pottery	MURR	¥	LA 059652	LA 059652	3.18		0.5295 3		7.45 4.28	3.72	81.95		18.52
ATT403	Group-B1	Mimbres-05B	Alma Plain	Pottery	MURR	NN	LA 059652	LA 059652	1.66	45.89 0.	0.6779 3	38.85 8.67	57 5.59	4.83	85.17		31.29
ATT404	Group-B1	Mimbres-04C		Pottery	MURR	¥	LA 059652	LA 059652	2.05	38.79 0.					70.28		40.30
ATT405	Group-B	Unas.	Mimbres B/W Style Indeter.	Pottery	MURR	NM	LA 059652	LA 059652	3.59	44.66 0.			47 2.77	_	82.05		45.51
ATT406	Group-B1	Mimbres-04C		Pottery	MURR	MN	LA 059652	LA 059652	2.58	45.28 0.	0.5923 3	33.92 6.58	28 6.67	3.64	91.76		39.50
ATT407	Group-C2	Unas.	Alma Rough	Pottery	MURR	MN	LA 059652	LA 059652	2.41	27.26 0.	0.3883 2	29.83 7.20	3.14	2.68	60.43	31.86	29.50
ATT408	Group-A	Mimbres-10	Mimbres Red	Pottery	MURR	M	LA 059652	LA 059652	3.59	136.93 1.	1.3038 10	107.36 24.32	32 7.04	10.45	209.03	6.63	26.50
ATT409	Group-C1	Mimbres-24	Mimbres B/W Style Indeter.	Pottery	MURR	MN	LA 059652	LA 059652	4.30	42.31 0.	0.4199 3	36.10 7.67	57 2.09	3.68	84.57		37.36
ATT410	Group-B1	Mimbres-05A	Mimbres B/W Style Indeter. Pottery	Pottery	MURR	MN	LA 059652	LA 059652	3.87	41.30 0.	0.5630 3	36.03 8.03	33 3.01	4.54	85.53	9.92	56.57
ATT411	Group-B1	Unas.	Mimbres Red	Pottery	MURR	MN	LA 059652	LA 059652	2.21	53.34 0.	0.8775 4	47.96 10.46	46 8.02	6.02	114.28	5.10	37.59
ATT412	Group-C2b		Alma Rough	Pottery	MURR	MN	LA 059652	LA 059652	2.45	29.82 0.	0.2290 2	26.36 5.05	2.94	1.85	62.90	5.42	25.34
ATT413	Group-B1	Mimbres-04A	Mimbres B/W Style Indeter. Pottery	Pottery	MURR	MN	LA 059652	LA 059652	2.06	44.48 0.	0.4277 3	31.77 5.83	33 3.52	3.15	75.21	8.49	21.88
ATT414	Group-C2a	Mimbres-49A	Alma Smudged	Pottery	MURR	M	LA 059652	LA 059652	4.23	43.59 0.	0.4179 3	35.68 7.8	7.83 2.57	3.47	83.77	10.34	54.96
ATT415	Group-C2	Unas.	Alma Plain	Pottery	MURR	MN	LA 059652	LA 059652	2.31	29.97 0.	0.2054 2	22.46 4.31	31 1.45	1.57	57.10	7.20	25.91
ATT416	Group-B1		Alma Plain	Pottery	MURR	MN	LA 059652	LA 059652	3.22	62.21 0.	0.7969 5	50.43 10.82	32 4.65	6.04	105.40	9.49	35.19
ATT417	Group-C2b	Mimbres-47	Alma Plain	Pottery	MURR	M	LA 059652	LA 059652	2.23	46.30 0.	0.2619 4	40.91 7.91	3.15	1.90	108.60	6.47	23.72
ATT418	Group-C2b	Mimbres-47	Alma Rough	Pottery	MURR	MN	LA 059652	LA 059652	2.82	34.76 0.	0.2787 2	29.58 5.42	42 2.70	1.89	70.35	69.9	24.56
ATT419	Group-B1	Mimbres-04C	ityle Indeter.	Pottery	MURR	NM	LA 059652	LA 059652	2.21			35.66 6.84			94.87		28.31
ATT420	Group-B1	Mimbres-04C		Pottery	MURR	NM	LA 059652	LA 059652	1.47	44.88 0.			59 2.90	3.56	88.47		30.76
ATT421	Group-A	Mimbres-03	Painted black-on-white	Pottery	MURR	M	LA 059652	LA 059652	2.28	44.14 1.		_			88.69		11.65
ATT422	Group-B1			Pottery	MURR	¥	LA 059652	LA 059652	2.48								26.18
ATT423	Group-C2a		Mimbres Red	Pottery	MURR	¥	LA 059652	LA 059652	4.15	-							59.05
ATT424	Group-C2		Mimbres B/W Style Indeter. Pottery	Pottery	MURR	MN	LA 059652	LA 059652	1.51	_							27.20
ATT425	Group-C2b	Mimbres-41	Mimbres B/W Style Indeter. Pottery	Pottery	MURR	M	LA 059652	LA 059652	1.70		0.2858 3	30.04 5.49	49 2.19	2.42	74.63	13.18	26.55
ATT426	Group-C2	Unas.		Pottery	MURR	M	LA 059652	LA 059652	3.10			21.84 4.31		2.38	48.18		22.86
ATT427	Group-B1			Pottery	MURR	¥	LA 059652	LA 059652	2.00	_					_		31.46
ATT428	Group-C2b		Mimbres B/W Style Indeter.	Pottery	MURR	N N	LA 059652	LA 059652	1.51						_		19.31
ATT429	Group-C2	Unas.	Style Indeter.	Pottery	MURR	M	LA 059652	LA 059652	1.94	35.85 0.	0.3345 3		99 1.88	2.88		12.52	22.64
ATT430	Group-B	Unas.		Pottery	MURR	¥	LA 059652	LA 059652	3.84		0.4451 4	41.93 8.4	8.45 3.00	3.62	104.31	7.62	39.13
ATT431	Group-A	Mimbres-07B	El Paso Brown	Pottery	MURR	M	LA 059652	LA 059652			1.7355 26	266.06 47.87	37 5.58	14.49			32.27
ATT432	Group-A	Mimbres-07A	Alma Rough	Pottery	MURR	¥	LA 059652	LA 059652	0.00	186.12 1.	1.5686 17	175.11 34.53	53 5.61	12.76	354.19	10.15	44.25
ATT433	Group-A	Mimbres-07A	Alma Plain	Pottery	MURR	NM	LA 059652	LA 059652	0.00	367.47 1.		412.23 60.00		19.88	640.89		40.34
ATT434	Group-A	Mimbres-07B	Alma Plain	Pottery	MURR	NM	LA 059652	LA 059652	0.00	172.07 1.	1.0213 16	164.17 30.25	25 3.89	8.75	297.39	15.34	123.21
ATT435	Group-A	Mimbres-07A	Alma Plain	Pottery	MURR	¥	LA 059652	LA 059652	2.70	297.91	1.7726 34	341.35 49.86	36 5.27	17.86	518.53	7.17	33.32
ATT436	Group-A	Mimbres-07A	Alma Plain	Pottery	MURR	MN	LA 059652	LA 059652	2.03	188.14 1.	1.4796 18	187.37 35.96	96 5.15	12.86	351.40	69.7	34.61
ATT437	Group-A	Mimbres-07A	Alma Plain	Pottery	MURR	NM	LA 059652	LA 059652	4.11	168.44 1.	1.3221 16	162.91 30.64	54 7.51	10.94	349.22	8.74	38.22
ATT438	Group-A	Mimbres-07A*	Jh J	Pottery	MURR	M	LA 059652	LA 059652		•	_			16.41	634.54		40.64
ATT439	Group-A	Mimbres-03		Pottery	MURR	M	LA 059652	LA 059652						8.49			16.84
ATT440	Group-A	Mimbres-07A*	Alma Plain	Pottery	MURR	M	LA 059652	LA 059652	2.21	148.46 1.	1.6759 14	144.69 27.78	78 6.26	13.72	290.47	10.18	50.29

>	54.77	56.35	92.89	84.69	29.68	46.68	55.04	63.49	88.78	57.97	211.25	40.68	89.91	74.97	61.24	58.34	55.90	85.67	44.21	55.33	55.91	56.30	54.60	77.47	24.23	46.54	96.92	52.27	60.56	73.79	55.04	91.22	119.01	61.73	54.49	76.69	63.57	129.67	61.68	73.10	78.46	79.16	37.95	80.32
F	3926.0	2130.7	3037.9	4251.5	3317.2	2722.9	3428.6	4044.5	4844.9	3493.4	5413.4 2	7309.6	4691.7	5348.3		2918.9	3181.1	4318.6	2464.0	4338.5	3298.4	3192.0	2873.9	3994.5			4054.0						~					_						5897 6
NA			0				14224.8 3.		16344.6 4	16537.6 3	17846.8 5	14957.2			13981.6 4	15929.9 2				18070.3 4			17373.6 2		5650.1 1.				٥.														_	
MN	1.6 13621.1	14362.0	.6 17121.	_	.0 22378.1	5 15929.9		17889.7			1		1 18868.7	1.8 15995.1			.8 14645.7	.3 15997.5	.8 24155.4		1.4 20521.4	.6 16160.0	,	_			15526.5			•	•	- 1						٠,٠	'			`	,	1 1 1 1 1 1 1 1 1 1
×	.6 356.6	.9 493.3	.9 483.6	.3 581.7	.1 179.0	.5 172.5	.2 198.9	.2 404.7	9.684 9.6	.4 354.8	.2 1679.4	.3 303.1	.1 736.1	.8 488.8	.2 198.6	.7 184.5	.9 409.8	.0 487.3	.8 422.8	.3 875.8	.9 193.4	.1 184.6	.6 954.5	.8 497.5		.6 492.3	.2 468.9						_			_			.2 259.8					1 370 3
	33154.6	37946.9	28722.9	28307.3	31692.1	30690.5	32859.2	30937.2	26622.6	27491.4	28656.2	38893.3	22578.1	25887.8	30887.2	27772.	33616.9	30299.0	22680.8	31511.3	30998.9	31492.1	25703.6	25076.8			30457.2				- 1	- 1		_				30573.8		34464.4				38863 1
Dλ	6.693	18.283	3.736	7.637		5.968	7.560	5.179	7.220	5.545	4.272	23.320	5.896	7.255	8.603	2.712	4.101	6.671	2.598	8.795	3.975	3.349	4.879	4.846	1		5.921			3.295				_				19.768		27.395				23 712
CA	6732.2	7683.0	19183.8	11078.4	16374.4	10552.2	9451.5	13814.0	10555.3	13268.3	23147.7	5802.3	11242.9	9692.0	10172.1	10163.3	9780.4	15853.2	11903.7	12959.9	11220.2	11017.2	13500.0	16185.7	8358.3	14041.3	17081.3	13299.0	20864.4	14243.9	13341.2	21207.3	19177.3	10018.3	11728.4	10804.6	10820.1	13978.1	11755.9	11062.6	10697.5	10886.9	10139.4	10074 5
BA	1038.4	796.8	1046.7	567.4	1023.5	791.9	838.9	884.6	490.1	704.6	836.5	738.6	743.9	571.1	852.5	898.4	646.2	8.9/8	944.1	858.3	848.7	0.798	940.3	801.0	145.6	991.0	806.8	1.696	1259.1	989.2	942.3	994.4	807.3	1061.4	1039.4	943.4	898.2	1139.1	1083.6	874.2	768.0	894.5	292.7	9776
AL	77291.8	98261.0	84297.8	91283.7	90524.8	93673.8	80948.2	83552.7	81732.2	88361.7	100631.3	91306.0	98808.2	89152.2	87356.8	94607.5	89481.9	87439.8	89917.9	89680.5	92514.0	90035.9	80164.3	83036.6	89105.4	76426.0	89321.1	90198.9	86274.2	6.66996	81225.1	102074.9	101250.8	84154.3	87600.3	85217.7	92496.2	88389.2	89160.2	82958.1	79476.3	91060.7	94097.0	882923
ZR	211.0	157.1	166.4	209.0	141.1	9.661	241.6	266.2	248.2	220.1	119.3	240.1	260.3	257.6	247.2	1.691	238.3	197.5	130.8	263.1	136.1	144.8	243.4	175.6	177.6	227.0	211.9	143.9	150.8	164.5	180.3	137.5	125.6	191.0	511.7	554.7	590.5	361.4	511.5	629.1	463.3	450.7	197.0	6 8 9
NZ	1.99	64.0	51.1	94.0	54.3	59.9	59.4	56.1	81.2	72.5	91.8	70.2	94.2	87.1	7.67	61.1	6.89	6.96	207.6	114.9	61.7	63.4	58.4	65.3			87.5				59.4	70.8		_	138.7	126.6	144.4	153.5	134.5	90.3	102.8	154.1	94.4	120 9
H	24.72	46.70	10.70	14.82		18.83	22.99	15.00	14.66	19.68	9.17	41.32	10.83	15.01	26.38	6.22	21.75	12.91	7.70	24.05		86.6	15.29	15.76			12.85	8.25		11.30	_		99.6							35.31	33.56			36.87
TB	1.33	3.29	0.84	1.44	0.42	0.95	1.22	0.78	1.43	0.85	0.69	4.12	0.94	1.18	1.53	0.49	69.0	1.02	0.48	1.53	0.76	0.51	0.87	0.89		0.82	1.12	0.54	0.63	0.51			_			4.74	7.55	3.64		4.87	4.02			4.11
TA	2.1701	2.5237	0.9417	1.7355	0.7825	1.3900	2.9420	1.2921	1.5111	1.3867	0.4667	2.0866	0.9896	1.3781	2.9356	0.7286	1.5317	1.0360	0.5994	1.5624	0.7666	0.6890	1.2052	1.2522	2.2805		1.0555	0.6757	0.9770	0.8710	1.2536	0.5779	0.6226	1.1213	1.9422			1.2100	1.8133	2.0369		1.9108	2.1847	2.4365
SR	0.0	0.0	1012.3	0.0	919.0	257.7	149.8	327.0	228.6	238.3	569.7	166.3	375.5	207.0	177.6	491.2	211.8	285.6	539.5	388.0	421.0	371.5	368.8	329.9	79.9	395.6	279.5	514.1	548.7	434.2	341.2	541.1	367.1	232.2	133.6	169.5	154.5	425.8	187.2	170.9	186.6	162.7	99.8	192.2
SC	8.99	9.95	7.48	11.21	6.38	7.02	9.92	8.00	9.52	8.82	7	8.39	10.66	11.14	12.08	7.35	7.15	11.96	6.21	9.34	7.08	7.23	6.57	7.79			12.06	6.50					1		-			23.57				(7		16.03
SB	0.5389	0.0000	0.0000	0.0000	0.0000	0.2359	0.3053	0.3517	0.5178	0.4803	0.3036	0.6001	0.6325	0.5942	0.3556	0.3462	0.3824	0.6915	0.3129	0.3474	0.3391	0.3935	0.3555	0.3225	0.4067	0.2596	0.6758	0.3081	0.2477	0.4025	0.4420	0.2966	0.4752	0.5960	0.1555	0.2043	0.1829	0.1947	0.2182	0.2017	0.2634	0.1949	0.4783	0.2526
RB	165.52	241.02	90.13	131.23	84.23	142.06	192.32	116.50	160.46	151.52	131.96	260.55	122.30	142.07	186.19	106.76	183.56	131.62	89.49	172.34	103.50	125.68	124.72	105.44	305.16	104.89	134.46	89.77	77.43	134.91	118.80	77.57	92.05	144.75	152.95	161.51	156.95	158.15	147.56	152.47	134.85	137.98	255.47	187.09
Z	0.0	0.0	0.0	0.0	0.0	0.0	54.3	0.0	36.5	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	22.1	34.1	0.0	0.0	0.0	0.0		45.4	0.0			0.0	0.0	0.0	0.0									0.0	73.5
生	10.25	7.08	6.94	10.25	2.69	7.91	86.6	9.58	9.61	8.18	4.52	8.02	9.55	10.12	8.43	5.89	9.13	7.74	4.99	10.56	4.70	4.59	10.38	7.44	9.90	68.6	7.68	5.89	6.27	6.21	7.69	2.17	5.56			22.25	20.66	12.73		24.11	17.20	14.45		27.76
FE	17663.6	31696.8	30562.3	39459.9	25590.3	24882.6		28096.8	33174.2	28506.0	73129.9	28100.5	42585.3	38788.7	29973.7	28298.9	28789.2	40364.6	26195.4	33904.3	1.8904 28787.1	29230.3	25412.5	30055.5	14929.7	27802.6	39597.1	26516.0	30711.9	33319.8	24669.7	48663.4	1.4420 52626.1				7.3069 42328.2	3.8146 53252.6		41649.2				3.4825 49663.1
EN	1.2458	2.6406	1.2695	1.4115	1.0618	1.3378	1.3395	1.3245	1.3295	1.2902	1.8584	2.7907	1.7182	1.3566	1.5894		1.1325	1.7280	1.0782	1.4947	1.8904	1.3179	1.4198		0.5811		1.7346		1.3754	1.0416		1.5914		1.4326	5.8543	1.2373	.3069	3.8146		4.2808	3.7968		_	3.4875
CS	4.73	10.97	3.22		3.25	4.50 1	6.21	3.59 1	9.74	5.71	7.66	9.05 2	18.17	11.04	6.80		5.53	6.21	5.21	4.13	3.42	3.66	4.31	3.64	2.65	3.43	6.19								2.94 5	3.48 4		2.80				3.03 7		3.64
ANID	ATT397	ATT398	ATT399	ATT400	ATT401	ATT402	ATT403	ATT404	ATT405	ATT406	ATT407	ATT408	ATT409	ATT410	ATT411	ATT412	ATT413	ATT414	ATT415	ATT416	ATT417	ATT418	ATT419	ATT420	ATT421	ATT422	ATT423	ATT424	ATT425	ATT426	ATT427	ATT428	ATT429	ATT430	ATT431	ATT432	ATT433	ATT434	ATT435	ATT436	ATT437	ATT438	ATT439	ATT440

ANID	macro arp	macro arp Chem2012	CERAMIC TYPE	MATERIAL	SOURCE	STATE	SITE NAME	SITE NO	AS	F	n	S QN	NS IN) YB	CE	00	CR
ATT441	Group-C2b	Mimbres-47		Pottery	MURR	MN	LA 059652	LA 059652		_	0.2881	33.03 6.32	32 2.70	2.14	82.75	5.83	24.93
ATT442	Group-A	Mimbres-07A*	Alma Rough	Pottery	MURR	MN	LA 059652	LA 059652	2.30	139.76 1.	1.1742 13	132.83 24.69	5.56	9.71	270.82	5.13	50.78
ATT443	Group-B	Unas.	Mimbres B/W Style Indeter. Pott	Pottery	MURR	MN	LA 059652	LA 059652	1.84	41.22 0.	0.3841	31.16 6.10	10 3.54	1 2.74	81.74	11.21	42.35
ATT444	Group-B	Unas.	Alma Smudged	Pottery	MURR	MN	LA 059652	LA 059652	3.10	56.54 0.	0.9285	59.37 13.39	39 5.61	7.40	126.45	6.63	33.75
ATT445	Group-B1	Mimbres-04C	Mimbres B/W Style Indeter. Pottery	Pottery	MURR	NM	LA 059652	LA 059652	2.07					3.31	80.98	7.64	27.61
ATT446	Group-B1	Mimbres-04C	Mimbres B/W Style Indeter. Pottery	Pottery	MURR	M	LA 059652	LA 059652				37.10 7.21	21 3.53	3.48	98.83	11.76	30.49
ATT447	Group-B	Unas.		Pottery	MURR	Σ	LA 059652	LA 059652	2.51	41.84 0.	0.5263 2	29.13 5.67	57 3.32	3.73	76.52	6.34	30.51
ATT449	Group-C2	Unas.	Alma Smudged	Pottery	MURR	Σ	LA 059652	LA 059652							82.10	12.68	27.67
ATT450	Group-B		Mimbres B/W Style Indeter. Pottery	Pottery	MURR	NM	LA 059652	LA 059652			0.6122			4.53	94.35	5.90	33.26
ATT451	Group-C2b	Mimbres-47		Pottery	MURR	MN	LA 059652	LA 059652		40.61 0.	0.2989			3 2.17	93.72	68.6	27.15
ATT452	Group-C2		Alma Rough	Pottery	MURR	NM	LA 059652	LA 059652	3.53	29.87 0.	0.1558 2	23.59 3.55	55 2.39	1.22	54.79	5.25	18.83
ATT453	Group-A	Mimbres-07A	Alma Smudged	Pottery	MURR	MN	LA 059652	LA 059652	1.99 1	164.82 1.	1.3763 14	142.62 26.46	46 5.78	12.73	368.66	8.01	29.31
ATT454	Group-B1	Mimbres-05B		Pottery	MURR	NM	LA 059652	LA 059652	2.64		0.7628 4		52 4.26	5.76	116.39	10.31	35.17
ATT455	Group-A	Mimbres-07A	Alma Plain	Pottery	MURR	NM	LA 059652	LA 059652	1.67	162.30 1.	1.4371 13	136.25 25.70	70 6.78	12.13	363.78	8.10	31.68
ATT456	Group-A	Mimbres-07A	Alma Plain	Pottery	MURR	NM	LA 059652	LA 059652	2.07	142.24 1.	1.2594 11	118.66 22.40	40 6.18	10.52		11.08	40.00
ATT457	Group-C2a			Pottery	MURR	NM	LA 059652	LA 059652		39.47 0.	0.3744 2	28.73 6.05	05 2.00	3.02		12.62	41.67
ATT458	Group-A	Mimbres-07A		Pottery	MURR	NM	LA 059652	LA 059652				133.28 22.98	98 4.81	11.03	329.87	8.44	39.75
ATT459	Group-A	Mimbres-07A	Alma Rough	Pottery	MURR	MN	LA 059652	LA 059652	0.00	220.85 1.	1.4846 16	165.43 30.13	13 6.11	14.29	486.57	13.59	43.93
ATT460	Group-C2	Unas.	Alma Plain	Pottery	MURR	NN	LA 059652	LA 059652	2.07	52.89 0.	0.3183	32.65 5.17	17 2.02		84.14	8.12	22.94
ATT461	Group-A	Mimbres-07B	Mimbres Red	Pottery	MURR	MN	LA 059652	LA 059652	2.47 2	207.90 1.	1.3585 15	153.58 29.43	43 4.08	13.01	414.51	15.05 1	109.74
ATT462	Group-A	Mimbres-07A	Alma Plain	Pottery	MURR	MN	LA 059652	LA 059652	0.00	309.37 1.	1.3034 21	214.85 37.82	32 3.92	14.26	592.55	9.20	41.10
ATT463	Group-C2c	Mimbres-48	Alma Plain	Pottery	MURR	MN	LA 059652	LA 059652	3.40	25.86 0.	0.3684 2	22.47 5.14	14 1.46	5 2.73	57.01	14.30	14.75
ATT464	Group-A	Mimbres-07A		Pottery	MURR	NN	LA 059652	LA 059652	0.00	٥.			3.73	14.67	457.41	6.02	33.88
ATT465	Group-A	Mimbres-10	pə	Pottery	MURR	NM	LA 059652	LA 059652			0.9175		31 4.43	7.02	155.05	3.44	24.69
ATT466	Group-A	Mimbres-07A		Pottery	MURR	M	LA 059652	LA 059652		318.22 1.	1.3683 20	204.99 39.64	54 3.83	14.79	556.12	5.82	49.44
ATT467	Group-C2c	Mimbres-48	h	Pottery	MURR	M	LA 059652	LA 059652						2.58	47.53	12.01	15.52
ATT468	Group-A	Mimbres-10		Pottery	MURR	M	LA 059652	LA 059652				_		7.30	156.27	3.29	26.64
ATT469	Group-A	Mimbres-07A	h	Pottery	MURR	M	LA 059652	LA 059652			1	7		12.49	350.05	10.43	42.61
ATT470	Group-A	Mimbres-07A		Pottery	MURR	M	LA 059652	LA 059652	0.00		1.3756 13	133.77 24.61	51 6.91	11.06	343.77	7.42	34.36
ATT471	Group-C2c	Mimbres-48		Pottery	MURR	M	LA 059652	LA 059652		_				2.84	60.09	12.89	14.82
ATT472	Group-A	Mimbres-07A		Pottery	MURR	¥	LA 059652	LA 059652		`		(*)		15.87	483.26	7.67	33.02
ATT473	Group-A	Mimbres-10		Pottery	MURR	ΣN	LA 059652	LA 059652		_				5.55	101.86	3.50	26.38
ATT474	Group-A	Mimbres-07A		Pottery	MURR	M	LA 059652	LA 059652	7			221.89 37.95		16.26	515.00	6.40	35.48
ATT475	Group-C2	Unas.	ч	Pottery	MURR	M	LA 059652	LA 059652						2.94	57.23	8.44	20.61
ATT476	Group-A	Mimbres-07A		Pottery	MURR	ΣN	LA 059652	LA 059652	2.17 1		1.3471 16	162.81 28.73		12.45	377.43	9.33	42.26
ATT477	Group-A	Mimbres-07B		Pottery	MURR	NM	LA 059652	LA 059652	1.71	174.86 1.	1.2490 15		57 3.56	11.82	351.93	,	107.04
ATT478	Group-A	Mimbres-07A	Alma Rough	Pottery	MURR	NM	LA 059652	LA 059652		276.33 1.		209.80 38.04	04 5.30	15.97	511.64	6.53	32.75
ATT479	Group-C2a	Mimbres-49A	Alma Rough	Pottery	MURR	Σ	LA 059652	LA 059652	3.57	36.73 0.	0.3850	31.75 5.92	92 2.46	5 2.82	67.50	10.03	41.39
ATT480	Group-C2	Unas.	Alma Plain	Pottery	MURR	NM	LA 059652	LA 059652		29.51 0.	0.4298 2	29.18 5.87	37 2.13	2.97	62.04	8.69	20.69
ATT481	Group-A	Mimbres-07B		Pottery	MURR	NM	LA 059652	LA 059652	0.00	`	1.3764 16	160.01 28.58	58 4.31	12.51	368.29	12.67	88.99
ATT482	Group-A	Mimbres-10	h	Pottery	MURR	NN	LA 059652	LA 059652	3.63	69.85 0.	0.8206 6	63.25 12.69	99.9	6.42	132.57	13.93	56.54
ATT483	Group-A	Mimbres-07A		Pottery	MURR	M	LA 059652	LA 059652		-	_			14.57	542.68	8.87	36.11
ATT484	Group-A	Mimbres-07A		Pottery	MURR	NM	LA 059652	LA 059652						16.81	617.45	11.52	40.84
ATT485	Group-A	Mimbres-07A	Alma Rough	Pottery	MURR	MN	LA 059652	LA 059652	0.00	346.31 1.	1.3835 2E	258.03 44.39	39 3.64	15.10	516.00	6.22	42.21

>	63.53	63.94	83.57	70.13	61.51	54.69	56.31	95.69	60.54	80.02	45.20	54.13	59.15	51.94	72.97	86.36	65.17	63.80	82.98	126.13	56.42	76.14	51.83	45.90	64.49	129.83	55.97	67.42	54.96	96.46	55.80	49.23	75.05	84.34	117.40	48.34	68.12	77.99	96.53	72.76	29.77	76.67	54.29
I	2860.4	4155.8	3618.8	4221.7	3478.9	2370.1	2777.2	2450.0	2373.9	3716.3	2926.3	4795.4	3326.4	4523.5	5049.1	3605.0	5833.4	5870.4	2500.2	6569.5	4907.8	2931.0	5078.8	2976.4	5507.0	3456.2	2760.8	5241.9	5035.0	3031.0	5429.0	5936.4	3293.6	5725.9	5537.7	5376.5	3099.2	4127.1	5310.5	3838.9	5060.2	5516.1	4639.4
NA	19823.6	17909.2	16643.9	14100.9	18256.9	17515.5	13858.6	11485.0	12469.3	16714.8	22730.6	16518.6	17033.6	16501.4	14814.2	13289.3	16729.4	17780.9	18926.4	19269.4	16081.7	13995.8	19105.6	15401.4	17289.3	17707.0	15158.1	16931.2	16254.4	15807.9	18596.5	186894	15492.1	14809.0	20088.9	18542.0	13572.4	1,09091	19291.6	13777.2	16441.8	15024.0	16447.7
MN	147.5	171.4	653.2	762.2	478.1	8.506	355.8	2076.4	291.4	166.5	85.3	242.7	878.1	255.2	411.6	787.1	283.3	243.0	442.0	367.4	391.9	1345.0	179.6	142.4	200.8	883.5	164.0	273.0	223.9	1019.1	256.5	194 5	622.2	254.2	286.5	198.6	552.7	636.4	287.0	1162.3	332.2	516.9	222.9
¥	26486.4	40318.6	24891.2	25456.6	24910.0	26662.5	33076.4	22542.4	28839.9	25759.4	24797.5	33734.4	29492.5	35683.9	30560.0	28287.6	31652.8	34122.6	23811.0	29774.0	31579.6	21585.1	39326.9	37361.2	33702.7	28813.0	34775.3	35197.1	33652.5	24274.7	3/928.1	37964.8	28901.7	31676.2	31851.7	36980.6	25590.4	27295.4	34372.8	32190.4	34047.2	32015.8	36512.6
DY	4.076	18.251	4.011	11.811	4.312	4.638	4.623	2.999	5.994	3.757	1.933	26.793	7.581	25.082	21.795	4.459	21.587	29.936	3.008	28.743	37.019	3.516	34.087	9.663	40.014	4.445	14.947	24.491	21.831	3.969	34.203	38 132	4.017	25.345	24.193	37.757	4.563	4.297	25.712	9.726	35.872	40.030	40.664
CA	10772.1	8392.0	18838.8	11123.3	14741.7	14249.0	16751.4	16396.2	16048.5	11106.7	12566.9	11554.2	14372.8	10954.1	11695.1	30481.5	11516.9	11931.8	11788.0	13857.9	10754.3	23531.8	9983.5	9.909/	11041.8	22824.4	7513.1	11282.6	0.0550.0	23973.5	7400.0	9683 9	20222.3	11269.1	14102.3	10626.4	38317.5	21477.8	11369.4	10337.6	10375.7	11450.0	10670.8
BA	705.5	904.3	818.3	9.089	776.3	9.769	901.6	1014.0	476.1	848.9	839.0	891.9	707.3	832.3	1056.1	0.798	843.8	919.5	997.3	1058.6	927.1	847.2	974.4	762.5	902.3	677.4	787.9	892.8	834.8	775.4	928.1	936.1	8.796	772.4	1051.9	1010.8	702.5	829.9	1053.2	798.9	992.9	951.5	0.626
AL	100618.3	81591.3	91620.6	82940.9	95031.1	80834.5	80511.1	78489.5	87534.3	95843.8	98462.5	80634.4	82378.3	82473.4	80153.4	76725.9	7.70667	90108.4	87435.4	92452.4	89389.4	96811.6	88617.5	82248.2	94307.8	8.8286	84491.4	77326.5	1/0/9.3	93250.2	86952.1	01742 1	88305.0	81316.1	90495.0	92388.3	74294.1	7.79016	88645.2	87203.9	85810.1	91105.2	90941.0
ZR	132.9	526.2	186.0			224.1	130.2	171.9	166.0	133.7	106.3	493.5	217.5	1.955	490.9		545.8	428.6	229.3	402.8	373.7	8.66	454.9								2.706				375.2	546.0	506.6	188.2	456.8	211.7			437.0
NZ	57.8	88.8	64.8	91.5	73.2	61.7	72.5	282.3	78.9	8.99	38.8	120.6	118.2	135.3	1		117.3	182.1	54.6	218.8	174.4	136.4	141.2		_			151.9	115.3	Ψ,	159.7	,		_	170.7	168.2	86.3	90.3	152.6	103.0			146.0
3 TH	9.46	5 32.09	14.21	17.77		3 15.80	18.74	01.10	5 22.22	10.15	7 11.24	5 36.62	7 22.40	7 40.93		13.24	31.75	49.69	7 12.52	5 38.90	6 26.95	5 8.72	1 46.81		2	_			٠,٠		7, 7, 7,			(,,	2 35.99	1 51.75	12.75	8.77					56.75
TA TE	5 0.59	3.15	6 0.74	78.1		0.93	14 0.81	0.70	2 0.96	5 0.74	4 0.37	2 4.76	8 1.47	8 4.57	3.72	0.76	3.89	3 5.54	0.57	4 5.35	1.09	0.75	5 6.21		1.51						1 1 22				4.32	16 6.81	7 0.74	5 0.82	6 4.53	1.81			3 7.75
	0.7575		1.0816	1.5976	1.2500	1.2670	1.3954	0.9106	1.4832	0.7755	0.6754	1.9322	1.5918	1.9578			1.8408	2.0763	0.6820	1.6114	1.7557	0.5456		- 1				_			2.2/36				1.7188	2.2136	1.0027	0.7065	٠.	1.8305			1.6963
SR	388.0	191.8	440.4	139.6	300.7	314.6	325.0	412.1	205.6	412.4	464.6	181.7	396.6	153.7	158.6		159.8	182.0	513.0		150.1	8.899	150.7			646.1	222.1	176.1		•	131.1		552.3		444.1	186.5	437.4	615.0	254.3	139.5	179.5		130.9
SC	7.47	13.46	10.17	1		6.84	7.43	8.79	8.87	8.34	5.68	13.72	9.44	13.33	_	9.61	13.73	18.36	8.98	23.95	18.53	13.65	16.94		,	_		· 1			77.75	_			22.37	18.14	8.96	11.00	20.92	13.78			19.58
SB	0.3852	0.1791	0.3082	0.5328	0.3452	0.4150	0.4182	0.6697	0.4373	0.3864	0.3641	0.2208	0.3944	0.1706	0.3309	0.4137	0.3099	0.2806	0.2706	0.2953	0.1877	0.4715	0.1196	0.6554	0.1876	0.3615	0.6330	0.2368	0.2531	0.4213	0.134/	0.0510	0.4046	0.3445	0.1766	0.1431	0.4631	0.3873	0.2370	0.5391	0.2073	0.2334	0.2027
RB	114.73	218.24	128.45	158.75	135.71	125.84	131.10	105.76	178.78	104.02	90.75	150.18	180.77	158.36	146.75	126.34	143.74	155.08	84.99	152.26	137.50	96.65	171.68	253.89	148.54	102.99	249.13	157.52	151.92	97.71	1//.26	174.89	113.64	136.52	159.68	169.82	126.17	114.98	161.80	188.94	139.37	142.52	147.40
Z	0.0	56.1	0.0	0.0	0.0	0.0	0.0	0.0	0.0	46.9	0.0	8.09	0.0	45.8	0.0	0.0	51.2	88.5	18.0	57.1	105.6	0.0	45.0	0.0	71.5	0.0	20.4	77.6	0.0	0.0	81.0	72.7	0.0	9.99	1.79	73.0	0.0	0.0	103.8	59.6			82.5
生	4.61	19.51	5.72	11.53	12.77	8.07	6.01		6:36	5.08	4.55	19.98	_		2	7.50	23.15	15.83	69.6	16.53	`	4.57	17.48		`				٠,	_	20.94			, ,	13.92	21.61	7.86	8.24	17.88	7.72			14.36
HE	58658.9	27117.0	34130.6	43266.9		7.9862	23521.4	39824.8	25431.7	35982.1	25728.6	41502.0	34912.4	35208.2			37254.1	34210.2	34769.6			49342.5									44654.1				50167.4	37240.4	32491.0	35167.7		44155.2			28418.9
EU	1.4439	3.0103	1.4272	2.3043		1.4570	`	1.3791	1.2813	1.6890	0.8328	3.9522	1.4761	3.7939			3.6493	4.9408	1.2783	3.34 4.9336	6.8833	1.4272									5.3307		1.4870		3.50 4.1740	6.1535	1.2406	1.5956		2.0699			7.5012
CS	4.58	3.90	6.48	8.87	5.18	4.35	5.56	3.48	10.13	3.95	3.16	2.94	4.70	3.23	3.74	3.91	3.58	3.79	2.12	3.34	3.21	5.43	2.68	8.82	3.33	4.22	8.70	3.51	3.34	4.92	2.92	3.25	4.45	3.85	3.50	2.94	4.12	4.52	3.34	8.81	3.00	3.82	2.93
ANID	ATT441	ATT442	ATT443	ATT444	ATT445	ATT446	ATT447	ATT449	ATT450	ATT451	ATT452	ATT453	ATT454	ATT455	ATT456	ATT457	ATT458	ATT459	ATT460	ATT461	ATT462	ATT463	ATT464	ATT465	ATT466	ATT467	ATT468	ATT469	A114/0	ATT471	A114/2	ATT474	ATT475	ATT476	ATT477	ATT478	ATT479	ATT480	ATT481	ATT482	ATT483	ATT484	ATT485

ANID	macro_grp	Chem2012	CERAMIC TYPE	MATERIAL	SOURCE	STATE	SITE_NAME	SITE_NO	AS	ΓA	n	ND	SM	Λ	B CE	00	CR
ATT486	Group-A	Mimbres-07A		Pottery	MURR		LA 059652	LA 059652	0.00	278.44	1.4721 2	71.77 37.77	_	3.92 15.11		7.27	32.17
ATT487	Group-A	Mimbres-07B	Alma Rough	Pottery	MURR		LA 059652	LA 059652	1.97		1.3016 1		27.04 4.	4.30 11.74		13.69	86.56
ATT488	Group-A	Mimbres-07A	Alma Plain	Pottery	MURR	NM	LA 059652	LA 059652	00.0	220.89	1.7859 1	194.66 34	34.39 5.	5.58 16.23	3 448.51	5.71	27.85
ATT489	Group-C2c	Mimbres-48		Pottery	MURR		LA 059652	LA 059652	3.31	25.98 (2.05 2.59		1	17.54
ATT490	Group-A	Mimbres-07A	Alma Plain	Pottery	MURR	1 MN	LA 059652	LA 059652	0.00	323.71	1.4825 2	257.27 42	42.33 4.	4.26 15.99	9 601.51		38.70
ATT491	Group-A	Mimbres-07A	Alma Rough	Pottery	MURR		LA 059652	LA 059652	0.00	284.57	1.8776 2	229.28 41	41.01 5.	5.53 17.64	4 538.53	9.84	38.86
ATT492	Group-A	Mimbres-07B	Alma Plain	Pottery	MURR		LA 059652	LA 059652		181.39	1.4611 1	161.26 29		3.23 11.67	371.11	12.31	89.61
ATT493	Group-A	Mimbres-10	Alma Plain	Pottery	MURR		LA 059652	LA 059652	3.76		0.7577	61.27 12.	12.55 5.	5.18 6.38		13.05	54.82
ATT494	Group-A	Mimbres-07A	Alma Rough	Pottery	MURR	NM L	LA 059652	LA 059652	00.0	356.80	1.6089 2	257.04 46	46.28 5.	5.31 17.15	5 657.68	95.9	39.42
ATT495	Group-C2c	Mimbres-48	Mimbres Red	Pottery	MURR	NM L	LA 059652	LA 059652	2.95	25.57 (0.3718	25.81 5.	5.37 0.	0.77 2.69	9 52.91	12.37	17.01
ATT496	Group-A	Mimbres-07A	Alma Plain	Pottery	MURR	1 MN	LA 059652	LA 059652	2.83	172.05	1.4519 1	160.60 29	29.14 6.	6.70 11.90	0 385.12	10.89	39.68
ATT497	Group-A	Mimbres-10	Alma Rough	Pottery	MURR	NM L	LA 059652	LA 059652	5.70	71.73 (0.8616		12.30 5.	5.38 5.97	7 142.79	3.17	30.02
ATT498	Group-A	Mimbres-10	Alma Rough	Pottery	MURR	1 WN	LA 059652	LA 059652	1.92	117.13	1.4617 1	101.10	19.39 6.	6.07 12.31	1 244.19	8.47	36.90
ATT499	Group-B	Unas.	Alma Rough	Pottery	MURR	1 WN	LA 059652	LA 059652	4.67	40.14 (0.4026	30.20	5.73 2.	2.43 2.57		9:26	40.74
ATT500	Group-B1	Mimbres-05B	Alma Rough	Pottery	MURR	1 WN	LA 059652	LA 059652	2.98	61.98	0.8002	53.03 10	10.07	3.82 5.86	121.82	19.6	31.36
ATT501	Group-A	Mimbres-07A	Mimbres Red	Pottery	MURR		LA 059652	LA 059652	00'0		1.2153 1	137.30 23	23.39 5.	5.64 10.00	3	l	33.98
BAS001	Group-B1	Mimbres-04C	Mogollon R/B	Pottery	MURR) MN	Galaz	LA 000635	1.33	35.97	0.3636	31.47 5	5.69 2.	2.57 2.78	74.26	9.76	28.10
BAS002	Group-B1	Mimbres-04C	Mogollon R/B	Pottery	MURR) MN	Galaz	LA 000635	2.38	40.10	0.4527	35.79 6		4.47 3.00	00 78.59	3.63	31.16
BAS003	Group-B1	Mimbres-04C	Mogollon R/B	Pottery	MURR) WN	Galaz	LA 000635	2.78	45.48	0.5040	40.31	7.50 4.	4.33 3.80	105.32	9.33	28.96
BAS004	Group-B1	Mimbres-04C	Mogollon R/B	Pottery	MURR) MN	Galaz	LA 000635	4.73	43.58	0.5219	36.39	7.16 4.	4.46 3.57	17 98.90	8.10	29.34
BAS005	Group-B	Unas.	Mogollon R/B	Pottery	MURR) WN	Galaz	LA 000635	4.68	37.83	0.3960	32.23 6	6.02 3.	3.37 2.97	76.41	12.77	58.36
BAS006	Group-B	Unas.		Pottery	MURR) MN	Galaz	LA 000635	3.33	68.38	0.4409	49.13	7.72 5.	5.95 2.48	109.40	99.9	32.82
BAS007	Group-C1	Unas.	Mogollon R/B	Pottery	MURR) MN	Galaz	LA 000635	1.12	40.47	0.4179	38.43	7.46 1.	1.71 3.19		11.26	15.50
BAS008	Group-B	Unas.		Pottery	MURR		Galaz	LA 000635	1.93	43.78 (0.4307		6.48 3.			6.39	41.76
BAS009	Group-C1	Mimbres-24		Pottery	MURR		Galaz	LA 000635	4.35		0.4466					1	31.03
BAS010	Group-B1	Mimbres-04C	Mogollon R/B	Pottery	MURR		Galaz	LA 000635	3.28		0.4150	34.88 5	5.74 2.	2.95 2.90			31.98
BAS011	Group-B	Unas.		Pottery	MURR		Galaz	LA 000635	3.26	45.09	0.3543					_	43.93
BAS012	Group-B1	Mimbres-04C		Pottery	MURR		Galaz	LA 000635	1.70		0.4298						33.77
BAS013	Group-C1	Mimbres-24		Pottery	MURR		Galaz	LA 000635	1.54		0.4321					1	28.03
BAS014	Group-B1	Mimbres-04C		Pottery	MURR		Galaz	LA 000635	3.14		0.4883				•		28.03
BAS015	Group-B	Unas.		Pottery	MURR		Galaz	LA 000635	2.44	_	0.4998						37.67
BAS016	Group-B1	Mimbres-04C		Pottery	MURK		Galaz	LA 000635	2.21	_	0.4552						36.19
BAS017	Group-C2	Unas.		Pottery	MURR		Galaz	LA 000635	1.57		0.4282					_	93.10
BAS018	Group-C1	Mimbres-24		Pottery	MURR		Galaz	LA 000635	5.24		0.5222					1	46.31
BAS019	Group-B1	Mimbres-04A		Pottery	MURR		Galaz	LA 000635	2.44		0.7345				_		23.98
BAS020	Group-B1	Mimbres-04C		Pottery	MURR		Galaz	LA 000635	2.03		0.5932						42.30
BAS021	Group-B1	Mimbres-05A		Pottery	MURR		Galaz	LA 000635	3.40		0.6709		10.40 2.		1	_	87.74
BAS022	Group-C2	Unas.	Three Circle R/W	Pottery	MURR		Galaz	LA 000635	3.02		0.3589		4.64 2.			9.31	23.21
BAS023	Group-B	Unas.		Pottery	MURR		Galaz	LA 000635	5.53		0.4150						97.80
BAS024	Group-B1	Mimbres-05B	,	Pottery	MURR		Galaz	LA 000635	3.06		0.5482			4.35 3.88			41.46
BAS025	Group-C2a	Mimbres-46		Pottery	MURR		Galaz	LA 000635	3.10	39.93	0.4136	37.66	7.38 2.	2.47 2.64	4 85.28	24.06	86.92
BAS026	Group-B	Unas.		Pottery	MURR		Galaz	LA 000635	3.20		0.4165						45.58
BAS027	Group-B1	Mimbres-05A		Pottery	MURR		Galaz	LA 000635	3.78	49.78 (0.7536						72.47
BAS028	Group-C1	Unas.	Three Circle R/W	Pottery	MURR	NM	Galaz	LA 000635	3.43	50.45 (0.5670	42.29 8	8.35 2.	2.74 4.06	95.19	11.70	49.51

>	40.54	95.40	47.05	94.72	72.80	73.81	94.11	77.33	62.58	80.18	80.97	66.29	61.90	79.98	43.23	58.28	68.51	50.91	48.16	51.37	74.30	80.64	103.62	59.15	89.09	48.56	59.40	68.19	90.45	63.91	79.85	48.03	236.10	77.91	71.19	73.93	109.75	62.65	116.31	50.59	116.13	64.78	83.64	78.61
=	4418.8	5477.3	5403.9	3119.2	4931.6	6550.2	5323.9	3597.6	5334.9	3078.4	5437.8	2661.9	3857.8	3114.2			3136.6	2984.1	3108.9	3112.6	3609.3	9.7693	4120.0 1	3438.1		2410.9	4247.4											2333.6	4693.1 1		,			3677.3
NA	17939.3	18921.3	17193.8	14260.4	16019.3		18307.3	3180.0	16957.9	13345.6	15229.4	13995.1	16656.4	12588.4	16829.7	14963.7	14738.0	14924.7	13866.7	3690.1	9186.0	17409.2	22877.4		18167.5	12458.9	14421.8											9603.5	2490.2		16399.7			16722.2
MN		305.5 18	209.5 17		384.3 16	296.2	241.5 18:	998.3 13	230.8 16	1219.8 13.	278.2 15.	124.4 13	284.8 16	488.4 12	994.9 16		497.3 14	173.5 14	687.3 13	619.6 13	519.9	649.3 17	361.2 22	558.2		465.0 12	616.1 14				`	•		`	`	416.9 17.		589.3	485.0 12		1084.9 16			663.8 16
¥	35014.1 2	30256.1 3	42366.2 2	1		30158.4 2	30039.9 2	27216.8 9	30629.9	19103.8 12		32885.7	31252.1 2	26568.8 4	28007.7	33876.0 3	25264.4 4	32319.8	26378.1 6	26077.5 6	9	23192.7 6	20885.0 3	33104.8 5			31621.1 6						_					26363.3 5						27795.6 6
DY	34.499 350	22.776 302	32.548 423	3.917 253	35.760 309	37.874 30	24.413 300	8.883 27.	39.242 300	3.478 19	22.328 302	9.738 328	18.270 31;	3.871 26	6.522 280		3.369 25;	4.083 323	5.520 263	5.531 260	3.985 32.	3.865 23	4.867 208	4.605 33			3.850 316					- 1			- 1	6.135 266	7.764 243	3.127 263	4.714 243	-	4.458 29			6.456 27
CA			8479.2 32.				11069.5 24.	8856.7 8.	9887.6 39.		9644.5 22.	6.0096	9476.9 18.			,		9784.4 4.		13434.8 5.	9476.0 3.															13001.3 6.		9725.4 3.						
٨	1 10480.2	6 13078.9		8 21989.0	4 10316.3	0 11645.4	`			2 21807.4				0 48127.4	4 21765.8		6 20154.4		4 13932.6			2 10867.9	9 20339.0				6 12602.9			`	`						l		7 15832.1		2 17613.9			7 12266.3
BA	947.1	985.6	955.0		924.4	1	1030.5		1 902.7	751.2	725.7	783.4	0.069	926.0	684.4		821.6	729.6	794.4	901.3	411.8	1066.2	6.669				797.6				_							858.9						710.7
AL	88510.0	90012.4	89982.8	105368.5	87583.4	91349.6	88311.5	85169.8	94260.8	97077.4	87866.3	91464.6	82580.2	69314.8	70187.8	77390.5	85164.4	77689.6	82692.8	76112.3	78518.6	89087.9	93565.9	74777.0	92425.2	77011.8	88070.7	85057.7	96591.6	79607.4	89655.1	85908.1	90842.5	95794.1	88998.9	89436.2	90669.2	90075.8	87705.4	81072.2	77377.3	82649.0	81035.9	78822.4
ZR	437.8	424.6	9.575	113.0	437.1	551.3	437.6	195.6	442.8	8.96	548.7	201.5	311.4	167.0	214.3	467.8	156.9	183.4	219.1	223.6	139.9	275.5	191.0	186.2	218.0	206.8	172.8	181.3	183.6	211.8	315.8	163.9	130.3	194.9	229.4	220.6	216.1	124.2	178.9	174.2	191.9	173.7	189.7	204.0
NZ	159.9	140.8	138.7	126.4	161.1	202.2	149.8	114.0	154.7	128.8	110.6	74.4	115.0	81.0	107.2	112.2	82.4	76.9	71.6	80.4	243.8	147.6	154.4	226.2	95.1	76.7	138.2	79.5	134.4	72.3	78.2	71.8	105.5	77.1	69.3	76.7	104.1	82.8	74.6	74.0	93.6	118.1	91.3	87.3
H	50.82	31.82	49.65	8.60	91.09	54.37	37.87	32.35	63.71	8.73	36.45	41.70	49.73	16.22	20.02	89.68	15.54	18.99	17.96	17.73	14.07	19.56	9.19	15.58		18.54	14.24	Z				_		12.11	22.99	17.45	15.63	11.23	14.46	21.28	10.76			13.75
TB	6.27	4.10	5.87	0.77	66.9	6.93	4.56	1.76	7.97	0.73	4.37	1.74	3.12	0.69	1.48	3.50	0.73	0.78	1.03	1.01	0.77	0.86	1.01	96.0	1.05	0.78	0.74	0.95			_	_	0.86	1.13	1.71	1.14	1.40	0.56	0.72	1.05	0.89			1.12
TA	1.7548	1.5291	2.2112	0.5367	1.7850	2.2878	1.8753	1.9034	1.9421	0.5895	1.9459	2.2543	2.8158	0.9596	1.3065	1.6298	1.0903	1.3671	1.3806	1.3004	1.1025	3.2306	0.7514	1.2017	0.9370	1.2533	1.1133	1.3437	0.8434	1.3165	3.0540	1.2840	0.5670	1.0156	1.4422	1.3457	1.5258	0.7251	1.1485	1.7593	0.8200	1.1311	1.6409	1.5023
SR	194.8	370.4	126.7	567.4	153.1	122.3	260.0	158.6	102.4	617.0	131.0	202.4	121.0	487.0	349.5	236.6	547.7	376.8	350.2	340.6	205.4	539.3	701.0	352.4	392.4	331.2	426.4	261.1	632.4	329.7	413.1	350.4	8.689	348.0	248.6	306.3	416.3	407.4	204.2	668.7	532.8	395.5	397.3	332.7
SC	16.18	20.08	16.96	13.32		20.93	• •	13.23	19.80	13.31	15.12	8.95	12.17	8.45	8.72	12.38	99.8	8.43	7.87	7.89		10.23	10.37		10.31		68.6		10.20	7.92	10.70			10.87		9.37	1		_	9.30	16.03			10.28
SB	0.1444	0.2885	0.2425	0.5092	0.2615	0.1810	0.2669	0.6145	0.1892	0.4768	0.3702	0.6094	0.4714	0.4692	0.3178	0.3006	0.2505	0.3703	0.3400	0.3384	1.0125	1.6356	0.2526	0.9614	0.5311	0.3941	0.4516	0.3619	0.3929	0.3450	0.7177	0.3531	0.2865	0.5737	0.4092	0.3950	0.4453	0.4094	0.7639	0.4402	0.3627	0.5471	0.6035	0.8427
RB	147.73	162.56	209.49	93.22	145.05	158.02	154.20	184.72	136.69	90.23	144.65	232.78	223.28	115.94	188.57	140.89	114.14	126.17	126.23	125.89	168.89	98.06	85.83	133.03	124.80	128.44	120.45	130.29	106.80	128.38	100.57	128.46	150.54	124.24	154.44	134.42	129.40	118.68	155.76	173.49	143.85	135.20	145.28	153.84
Z	0.0	59.8	58.1	0.0	0.0	106.7	50.6	51.1	115.9	0.0	52.5	0.0	37.8	0.0	0.0		30.4	0.0	0.0	0.0		0.0	0.0	50.8		0.0	0.0				0.0			0.0		0.0		0.0	0.0	0.0		_		0.0
生	16.37	17.27	23.24	4.30	14.59	20.93	16.61	7.62	15.57	4.49	22.34	8.33	13.34	7.06	8.98	18.09	6.48	7.10	7.32	8.50	6.01	9.55	7.18	96.9	8.21	7.76	7.01	6.47	7.05	7.49	11.27	7.29	2.69	7.77	80.6	8.15	9.43	5.43	7.63	8.26	7.47	7.42	8.86	8.35
Ή	33822.4	46476.1	38068.3	49926.4	51164.5	55004.4	_	42898.7	31463.0	49921.3	53519.1	28201.7	37228.0	1.1948 30911.3	30846.5	40679.2	32617.5	26178.4	26514.1	1.4286 26835.6	1.2420 33834.2	28207.1	40751.7	28146.1	37590.6	29968.9	34927.4	27249.5	37312.7	27005.9	23954.8	30022.5	75221.9	36828.8	32626.8	31375.7	48515.7	37442.5	46061.6	29580.6	54985.8	36437.3	41384.5	1.5989 37908.8
ED	6.0357	3.9159	4.9536	1.4280	6.8189	6.2712		1.9859		1.4242	4.0038	1.4500	2.3633	.1948	1.4831		1.3470	1.2233	1.4454	.4286	.2420	1.8691	1.8984	1.3334	1.6361		1.3934					_	_		2.1108		1.7313	1.1673			1.9109		1.5382	.5989
SS	2.80 6	3.42	3.36 4	5.16	3.24 6	3.50 6		8.74	2.93 7	5.43	4.29 4	8.93	6.65	3.20	4.39		4.40	3.53 1	3.73	3.72	10.54	5.00	19.60	5.78			4.24			3.90					5.71 2				19.25 1	7.06	4.65	5.22		12.11
ANID	ATT486	ATT487	ATT488	ATT489	ATT490	ATT491	ATT492	ATT493	ATT494	ATT495	ATT496	ATT497	ATT498	ATT499	ATT500	ATT501	BAS001	BAS002	BAS003	BAS004	BAS005	BAS006	BAS007	BAS008	BAS009	BAS010	BAS011	BAS012	BAS013	BAS014	BAS015	BAS016	BAS017	BAS018	BAS019	BAS020	BAS021	BAS022	BAS023	BAS024	BAS025	BAS026	BAS027	BAS028

ANID	macro grp	macro grp Chem2012	CERAMIC TYPE	MATERIAL	SOURCE	STATE	SITE NAME	SITE NO	AS	ΓA	Π	ND	SM	n	YB	CE CO	CR
BAS029	Group-B1	Mimbres-04C	Three Circle R/W	Pottery	MURR	ΣN	Galaz	LA 000635	1.89	51.43 (0.6077	45.48	8.93 6	6.39 4.	4.14 96.24		44.3
BAS030	Group-B1	Mimbres-04C	Three Circle R/W	Pottery	MURR	MN	Galaz	LA 000635	2.45	44.76 (37.69	6.76 3	3.10 3.	3.36 91.09	10.78	42.29
BAS031	Group-B1	Mimbres-04C	Mimbres B/W Style I	Pottery	MURR	NM	Galaz	LA 000635	2.16	47.49 (0.4927	36.70	7.04 2	2.66 3.	3.37 93.17	7 9.15	36.57
BAS032	Group-C2	Unas.	Mimbres B/W Style I	Pottery	MURR	NM	Galaz	LA 000635	4.82	40.21		36.87	7.17 3	3.31 3.	3.00 78.42		
BAS033	Group-C2a		Mimbres B/W Style I	Pottery	MURR	NN	Galaz	LA 000635	2.48						3.10 93.67	_	
BAS034	Group-B1	Mimbres-04C	Mimbres B/W Style I	Pottery	MURR	M	Galaz	LA 000635	2.19								
BAS035	Group-B1	Mimbres-04C	Mimbres B/W Style I	Pottery	MURR	MN	Galaz	LA 000635	2.53					3.75 3.	3.37 90.74	4 9.49	36.43
BAS036	Group-B1	Mimbres-04A	Mimbres B/W Style I	Pottery	MURR	MN	Galaz	LA 000635	3.21								
BAS037	Group-B1	Mimbres-04C	Mimbres B/W Style I	Pottery	MURR	M	Galaz	LA 000635	2.21	_							
BAS038	Group-B1	Mimbres-04A	Mimbres B/W Style I	Pottery	MURR	NM	Galaz	LA 000635	2.21			37.10		4.09 3.	3.48 86.49		
BAS039	Group-C1	Mimbres-24	Mimbres B/W Style I	Pottery	MURR	M	Galaz	LA 000635	6.46	39.59 (36.49	7.83 2		3.51 86.36	13.99	33.96
BAS040	Group-C1	Mimbres-24	Mimbres B/W Style I	Pottery	MURR	NM	Galaz	LA 000635	4.29	43.37	0.5220		8.45 2	2.86 3.	3.76 88.96	13.26	41.09
BAS041	Group-B	Unas.	Mimbres B/W Style I	Pottery	MURR	NM	Galaz	LA 000635	3.75	39.53 (4.20 79.90		
BAS042	Group-B1	Mimbres-04C	Mimbres B/W Style I	Pottery	MURR	NM	Galaz	LA 000635	0.00	44.48 (0.5300	34.22	7.28 4	4.02 3.	3.46 94.54	9.38	47.77
BAS043	Group-B1	Mimbres-04C	Mimbres B/W Style I	Pottery	MURR	NM	Galaz	LA 000635	0.95	44.94 (_	34.22		3.82 3.	3.99 92.82	7.80	40.50
BAS044	Group-B1	Mimbres-04C	Mimbres B/W Style I	Pottery	MURR	NM	Galaz	LA 000635	3.28	49.35 (3.85 93.78	8.16	
BAS045	Group-C1	Mimbres-24	Mimbres B/W Style I	Pottery	MURR	NM	Galaz	LA 000635	2.92				8.26 3		3.92 81.72	2 10.45	
BAS046	Group-B	Unas.	Mimbres B/W Style II	Pottery	MURR	MN	Galaz	LA 000635	1.84	43.55 (0.4320		6.78 3	3.57 2.	2.98 73.45	5 11.16	43.59
BAS047	Group-B1	Mimbres-04C	Mimbres B/W Style II	Pottery	MURR	MN	Galaz	LA 000635	1.28	42.22	0.5050	33.52	6.72 3	3.68 3.	3.39 86.44	7.63	36.39
BAS048	Group-B1	Mimbres-04A	Mimbres B/W Style II	Pottery	MURR	NM	Galaz	LA 000635	2.21					3.25 3.		7 6.25	21.54
BAS049	Group-B1	Mimbres-04A	Mimbres B/W Style II	Pottery	MURR	MN	Galaz	LA 000635	2.15	33.50	0.3856	25.64	4.90 4	4.08 2.	2.59 62.32	12 4.66	20.44
BAS050	Group-B1	Mimbres-04A	Mimbres B/W Style II	Pottery	MURR	MN	Galaz	LA 000635	2.28	32.81	0.3802	24.72	4.68 4	4.25 2.	2.49 60.54	4.16	20.47
BAS051	Group-B	Unas.	Mimbres B/W Style II	Pottery	MURR	MN	Galaz	LA 000635	2.04	71.29 (0.5017	37.74	6.73 3	3.11 3.	3.26 112.28	8.94	
BAS052	Group-B1	Mimbres-05A	Mimbres B/W Style II	Pottery	MURR	MN	Galaz	LA 000635	3.95	46.11 (0.7114			4.12 4.	4.85 92.23		
BAS053	Group-B1	Mimbres-04C	Mimbres B/W Style II	Pottery	MURR	M	Galaz	LA 000635	2.62			_		3.71 3.			35.34
BAS054	Group-B1	Mimbres-04A	Mimbres B/W Style II	Pottery	MURR	MN	Galaz	LA 000635	1.81								
BAS055	Group-B1	Mimbres-04A	Mimbres B/W Style II	Pottery	MURR	M	Galaz	LA 000635	2.54						2.75 76.42		
BAS056	Group-B1	Mimbres-04A	Mimbres B/W Style II	Pottery	MURR	M	Galaz	LA 000635	1.53								
BAS057	Group-B1	Mimbres-04C	Mimbres B/W Style II	Pottery	MURR	M	Galaz	LA 000635	1.08					3.41 2.		1 5.92	30.85
BAS058	Group-B1	Mimbres-04A	Mimbres B/W Style II	Pottery	MURR	MN	Galaz	LA 000635	1.82								
BAS059	Group-B	Unas.	Mimbres B/W Style II	Pottery	MURR	N.	Galaz	LA 000635	3.07							1	
BAS060	Group-B	Unas.	Mimbres B/W Style II	Pottery	MURK	N N	Galaz	LA 000635	1.35								
BAS061	Group-B1		Mimbres B/W Style III	Pottery	MURR	Σ	Galaz	LA 000635	2.03	_							
BAS062	Group-C2a		Mimbres B/W Style III	Pottery	MURR	M	Galaz	LA 000635	3.52							1	
BAS063	Group-B2	Mimbres-02A	Mimbres B/W Style III	Pottery	MURR	M	Galaz	LA 000635	2.04	_							
BAS064	Group-B1	Mimbres-04A	Mimbres B/W Style III	Pottery	MURR	M	Galaz	LA 000635	2.91					4.93 2.		1 5.46	
BAS065	Group-B	Unas.	Mimbres B/W Style III	Pottery	MURR	NM	Galaz	LA 000635	5.16					4.91 4.	4.08 109.81		
BAS066	Group-B2	Mimbres-02A	Mimbres B/W Style III	Pottery	MURR	Σ	Galaz	LA 000635	2.20	46.56	0.5694		7.33 4	4.82 3.	3.73 76.01	11 5.90	40.33
BAS067	Group-A	Mimbres-01	Mimbres B/W Style III	Pottery	MURR	NM	Galaz	LA 000635	2.76	52.06 ()	20.21	3.78 10	10.56 3.	3.00 76.65		
BAS068	Group-B2	Mimbres-02A	Mimbres B/W Style III	Pottery	MURR	NM	Galaz	LA 000635	1.52	41.93 (33.85		4.40 3.			36.82
BAS069	Group-B1	Mimbres-05B	Mimbres B/W Style III	Pottery	MURR	NM	Galaz	LA 000635	5.36	46.60 (0.7613	48.20 10	10.55 4	4.87 5.	5.37 101.38	1.59	36.64
BAS070	Group-B1	Mimbres-04A	Mimbres B/W Style III	Pottery	MURR	M	Galaz	LA 000635	3.30						1		7
BAS071	Group-A	Mimbres-01	Mimbres B/W Style III	Pottery	MURR	NM	Galaz	LA 000635	2.76				1			1.71	
BAS072	Group-B1	Mimbres-04A	Mimbres B/W Style III	Pottery	MURR	NM	Galaz	LA 000635	4.02	48.67 (0.5841	37.81	7.70 4	4.25 3.	3.90 91.77	7 7.43	20.42

>	99.99	67.08	58.15	91.42	62.61	57.36	68.70	48.07	58.41	38.24	74.58	80.95	79.90	83.95	75.11	09.79	92.54	87.92	66.35	62.75	55.18	55.96	84.99	75.65	58.52	48.18	47.28	48.65	71.24	48.25	59.89	10.70	00.00	45.24	48.38	38.99	09.69	18.57	64.18	56.35	67.31	20.13	31.96
I	4326.9	3108.7	2676.9	3590.8	3992.4	2622.4	3355.2	2706.0	3090.0	2585.2	3741.4	3773.1	4553.7	4126.9	3059.9	3354.2	4073.4	4031.2	3325.0	2878.3	2842.2	3440.4	3512.9	4594.2	3071.9	3351.3	3301.5	3267.8	3379.1	3565.9	3064.3	0.600	4150 6	3042 3	3066.1	1068.2	2855.5	741.5	3170.1	4791.7	2782.9	1370.5	2289.8
NA	16409.7	17021.7	16437.4	11591.0	16316.2	16591.7	16741.2	14437.3	14953.9	14422.3	18310.9	17451.9	15037.9	16224.0	14713.0	15665.9	18914.5	16534.6	14756.5	15133.3	15970.5	16646.0	16036.2	15038.7	17638.0	17801.7	14278.6	18079.2	17106.8	15563.4	13734.6	112000	13050.7	10466 9	13069.8	13985.4	12290.9	19042.7	13457.2	13117.3	14523.8	19364.1	14484.4
M	368.9	714.4	613.1	457.5	428.9	474.7	537.1	266.4	309.5	539.5	577.2	494.8	379.5	512.3	355.2	481.6	411.4	505.2	322.4	460.2	449.8	199.0	561.8	484.1	541.8	639.0	370.2	318.8	257.8	315.1	507.1	401.1	28/10	189.1	309.1	1277.1	277.4	191.9	218.8	323.4	359.2	226.2	1279.7
\prec	24578.0	25729.0	27428.3	22758.9	21790.2	27843.0	28846.4	31563.2	25636.3	28734.3	22298.1	22846.5	25404.1	21992.8	22451.1	26197.3	27907.6	23626.0	21977.9	27555.4	26446.9	26471.0	29863.8	23260.6	28803.1	28100.6	31547.2	28310.2	24529.7	25829.3	27647.8	24201.0	7 11700	29600 8	36851.5	24062.2	24656.1	24480.2	25233.2	33358.4	26735.4	32967.6	23783.2
DΑ	6.609	4.148	4.200	4.525	4.926	3.583	4.384	3.919	4.481	4.434	5.809	5.900	7.588	5.226	4.392	2.667	6.337	4.682	5.003	6.125	3.216	3.157	4.438	7.609	4.681	5.160	3.348	4.198	4.432	5.773	4.949	64.243	3 307	3,662	3.864	5.526	4.983	2.249	5.075	8.467	7.428	2.942	5.231
CA	14130.8	16833.8	16795.2	12839.8	15957.8	13782.0	15726.3	13636.5	11455.6	11366.5	13814.6	11397.8	9974.8	17319.3	13266.2	13611.3	15250.8	20890.2	14872.4	13225.7	10898.9	10090.9	12922.9	10439.8	15031.1	14776.2	9054.4	10556.9	11862.6	14302.0	10502.7	1,20,021	13020	6536.6	13442.1	13698.1	12910.9	11556.7	13408.8	6343.9	16145.1	22328.7	11568.6
BA	749.8	8.989	701.1	703.9	918.3	2.769	938.8	730.5	716.0	694.0	528.4	589.2	351.2	719.7	8.699	729.6	831.1	913.6	848.1	1105.8	843.9	954.7	741.4	536.8	8.607	921.1	683.6	943.1	6.799	1202.9	507.0	004.3	0.140	478 3	637.1	920.6	527.0	158.3	508.8	571.8	705.9	106.0	833.9
AL	85613.8	82215.2	88462.5	90206.9	88556.5	81977.0	77023.8	82856.6	81577.7	83804.1	90455.3	89678.3	76939.6	84850.7	83115.9	92371.8	94372.2	86495.6	85056.0	89370.6	6.66106	91456.0	87022.7	82970.8	91374.7	81720.9	7.60806	89649.2	84196.4	86848.5	84866.0	1.709.1	92420.2	88561 9	81209.9	84447.3	90192.0	96246.8	85691.9	91491.9	84306.3	104965.4	82711.4
ZR	232.6		195.5	138.3	207.4	187.2	219.0	164.3	168.3	210.4	187.8	185.2	201.0	177.9	176.9		221.1	197.7	163.8	158.4	148.3	164.5	190.3	1.891		231.4				176.8	152.9	2.012					190.1	132.3	152.9	235.2	169.8		154.3
NZ	77.1	9.68	88.2	68.0	83.3	71.2	79.9	76.3	83.3	75.8	101.3	99.2	98.2	91.3	1.96	93.5	91.8	73.4	89.1	74.6	9.89	8.09	88.4	95.3	78.8	52.7	80.8	59.5	75.6	71.1	74.3	74.4	00.0	63.5	63.5	68.8	64.8	45.9	61.9	63.5	61.7	44.8	67.8
TH	17.24							21.81	17.23	21.04	10.89	13.89	15.67	15.69	17.10	19.61	12.91	14.67	17.91	19.42	19.24	18.63		16.95			22.73						12.15			_	21.35	47.42	17.69	20.88		52.88	19.50
\ TB	1.14							89.0	1.00	0.85	3 1.13	1.18	1.18	1.04	1.11	1.04	3 1.22	0.81	1 0.91	1.04	_	0.58	3 0.80	1.28					_			0.0		_	_		0.00	0.37	0.81	1.47		1 0.37	96.0
TA	1.3476		~			`	1.3494	1.5554	1.2669	1.4431	0.9063	1.1114	1.5024	1.2700	1.1983		1.1508	1.0836	1.2531	1.3779	1.4537	1.4305	1.3168	١.	`		`	`		_		1.0003		١,		1	1.5100	2.1952	1.2755	1.6299	1.2357		1.3426
SR	330.9	363.1	368.2	418.6	380.0	303.9	396.2	2.962	274.2	219.3	368.4	335.5	230.1	340.8	1.792	307.2	397.4	536.2	344.8	313.2	279.5	273.7	315.3	248.4	1.192	282.2	221.9	254.4	295.7	330.7	224.1	121.0		173.1	188.7	' '	261.2	105.7	264.7	137.4		105.7	301.7
SC	9.75	8.89	9.50	8.69	11.67	8.08	8.35	7.44	8.94	7.25	11.66	11.42	10.84	10.30	9.93	10.08	10.44	11.50	9.49	7.31	7.63	7.66	8.93	12.10	8.67	6.42	7.29	7.59	8.29	7.94	8.02	10.7	12 60	10.47	6.49	8.26	12.25	4.34	10.87	9.50	8.65	3.97	7.59
SB	0.3875	0.4143	0.4310	0.7398	0.3518	0.4279	0.4258	0.3662	0.4296	0.4583	0.6790	0.5990	0.5468	0.3573	0.3941	0.4303	0.5127	0.3140	0.3831	0.3557	0.3349	0.3062	0.4667	0.5601	0.4720	0.2469	0.3679	0.3276	0.3589	0.3221	0.5845	0.2004	0.4190	0.4976	0.4729	0.2951	0.4068	1.2676	0.3425	0.9338	0.2881	0.7165	0.2643
RB	140.83	146.00	149.47	112.58	109.56	137.27	136.71	174.09	144.82	181.00	126.82	128.58	167.06	105.67	109.72	135.62	119.86	120.33	117.29	154.46	125.10	125.83	143.44	147.99	145.63	139.12	175.06	132.71	110.00	132.90	175.60	00.011	113.01	181 35	152.61	124.61	145.01	246.66	140.33	191.34	132.32	206.04	129.67
Z	0.0	17.7	0.0	0.0	0.0	23.4	23.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	42.5	28.9	0.0	0.0	30.5	0.0	0.0	0.0	44.7	29.6			0.0				04.4				17.3		0.0	0.0	21.3	0.0		32.4
士	9.20	8.35			7.89	7.95	9.54	7.51	7.91	8.90	8.80	8.34	8.76	7.12	99.9	8.75	8.44	7.33	6.73	7.49	97.9	7.42		8.79	8.12					7.74	7.32	0.21		-	_		8.00	5.63	6.57	10.85			6.54
FE	32241.9						34076.3	26516.7	32571.9	28481.6	38172.9	40064.3	38060.6	37550.0	34364.3	33411.9	36695.1	37409.0	29196.2	27570.6	27597.0	27516.7	34136.3									240700					28251.4	14776.5	26153.6	25041.5			24738.6
EU	1.7473	1.3793						1.0438	1.4035	1.3064	1.7124	1.7142	1.2841	1.4519	1.3773		1.4996	1.5915	1.3606	1.4224	0.9819	0.9584		1.3738		1.3596						1.2100			5.82 0.9185	1.5718	1.3928	0.4710		1.3761	1.9819		1.4230
CS	5.21	5.69	6.15	5.25	4.38	4.84	4.65	5.59	5.26	5.77	23.22	16.97	10.57	4.53	4.88	5.75	9.57	7.17	5.17	5.23	4.94	5.13	5.92	96.9	5.50	4.13	5.55	4.58	4.35	4.89	7.09	4.09	5.00	20.00	5.82	4.84	20.01	19.58	13.34	8.53	4.43	14.55	4.65
ANID	BAS029	BAS030	BAS031	BAS032	BAS033	BAS034	BAS035	BAS036	BAS037	BAS038	BAS039	BAS040	BAS041	BAS042	BAS043	BAS044	BAS045	BAS046	BAS047	BAS048	BAS049	BAS050	BAS051	BAS052	BAS053	BAS054	BAS055	BAS056	BAS057	BAS058	BAS059	DAS000	BAS061	RAS063	BAS064	BAS065	BAS066	BAS067	BAS068	BAS069	BAS070	BAS071	BAS072

ANID	macro_grp	Chem2012	CERAMIC TYPE	MATERIAL	SOURCE	STATE	SITE_NAME	SITE_NO	AS	ΓA	Π	ND	SM	n	YB C	CE CO	CR
BAS073	Group-B	Unas.	Mimbres B/W Style III	Pottery	MURR	MN	Galaz	LA 000635	3.49	40.51 0	0.4068 2	25.83 4	4.98 4	4.62 2.	2.53 71.00	0 5.07	32.74
BAS074	Group-A	Mimbres-01	Mimbres B/W Style III	Pottery	MURR	MN	Galaz	LA 000635	2.05	52.03 0		23.32 4		11.59 3.	3.35 88.19	9 2.79	5.73
BAS075	Group-B1	Mimbres-04A	Mimbres B/W Style III	Pottery	MURR	M	Galaz	LA 000635	2.29	43.34 0	0.4929 3	31.30 5	5.97	4.07 3.	3.11 79.69	9 7.21	18.05
BAS076	Group-C1	Mimbres-24	Mogollon R/B	Pottery	MURR	M	Wind Mountain	LA 127260	4.85	39.06	0.4834 3	35.47 7	7.14	1.49 3.	3.23 76.13	3 13.02	24.34
BAS077	Group-B	Unas.	Mogollon R/B	Pottery	MURR	MN	Wind Mountain	LA 127260	6.02	60.94 0	0.7630 5	55.11 12	12.34 3	3.16 5.	5.45 130.70	0 11.30	48.56
BAS078	Group-C1	Mimbres-24	Mogollon R/B	Pottery	MURR	NM	Wind Mountain	LA 127260	2.52	37.95 0	0.4780 3	35.51 7	7.10 1	1.51 3.	3.15 76.53	3 12.41	24.14
BAS079	Group-C1	Mimbres-24	Mogollon R/B	Pottery	MURR	MN	Wind Mountain	LA 127260	3.51	46.11 0		43.31 8	8.86	1.69 3.	3.26 96.18	8 15.41	32.95
BAS080	Group-C1	Mimbres-24	Mogollon R/B	Pottery	MURR	M	Wind Mountain	LA 127260	6.02	43.34 0	0.5113 4	40.14 8		1.70 3.	3.43 86.43		
BAS081	Group-B1	Mimbres-05A	Mogollon R/B	Pottery	MURR	MN	Wind Mountain	LA 127260	3.60	41.03 0	0.6419 4	40.63 9	90.6	3.52 4.	4.31 89.84	4 12.38	58.91
BAS082	Group-C1	Mimbres-24	Mogollon R/B	Pottery	MURR	M	Wind Mountain	LA 127260	3.35	39.57 0	0.4857 3	36.70	7.42		3.35 78.38	8 13.52	40.99
BAS083	Group-C1	Mimbres-24	Mogollon R/B	Pottery	MURR	MN	Wind Mountain	LA 127260	3.26	40.60	0.4712 3	36.24 7	7.20 2	2.25 3.	3.17 76.83	3 12.44	28.09
BAS084	Group-C1	Mimbres-24	Mogollon R/B	Pottery	MURR	M	Wind Mountain	LA 127260	4.41	38.87 0	0.4922 3	34.32 6	6.81	1.68 3.	3.41 79.70	0 14.62	29.30
BAS085	Group-C1	Mimbres-24	Mogollon R/B	Pottery	MURR	M	Wind Mountain	LA 127260	2.50	37.43 0	0.4644 3	35.56 6	6.91	2.31 3.	3.11 73.21	1 11.87	30.78
BAS086	Group-C1	Mimbres-24	Mogollon R/B	Pottery	MURR	M	Wind Mountain	LA 127260	3.00	40.52 0	0.4747 3	39.44	7.83 1	1.42 3.	3.37 82.36	6 13.76	27.63
BAS087	Group-C1	Mimbres-24	Mogollon R/B	Pottery	MURR	M	Wind Mountain	LA 127260	3.28	39.95 0	0.4680 3	37.09	7.39 1	1.91 3.	3.18 76.53		31.84
BAS088	Group-C1	Mimbres-24	Mogollon R/B	Pottery	MURR	MN	Wind Mountain	LA 127260	5.26					1.46 3.	3.14 81.06		
BAS089	Group-C1	Mimbres-24	Mogollon R/B	Pottery	MURR	M	Wind Mountain	LA 127260	5.25	38.20 0	0.4507 3	35.81 6	6.90	1.68 2.	2.92 72.66	6 12.08	23.82
BAS090	Group-C1	Mimbres-24	Mogollon R/B	Pottery	MURR	M	Wind Mountain	LA 127260	2.79	38.92 0	0.4838 3			1.52 3.	3.27 78.06	6 14.02	38.03
BAS091	Group-C1	Mimbres-24	Three Circle R/W	Pottery	MURR	ΣN	Wind Mountain	LA 127260	5.64	40.36 0	0.5467 3	36.86	7.57	2.24 3.	3.71 82.04	4 8.97	47.78
BAS092	Group-C1	Mimbres-24	Three Circle R/W	Pottery	MURR	M	Wind Mountain	LA 127260	2.08			34.61 7	7.81	2.36 3.			
BAS093	Group-C1	Mimbres-24	Three Circle R/W	Pottery	MURR	MN	Wind Mountain	LA 127260	4.07	38.62 0		35.44 7	7.58 1	1.65 3.			37.33
BAS094	Group-C1	Mimbres-24	Three Circle R/W	Pottery	MURR	MN	Wind Mountain	LA 127260	4.54	42.69 0	0.5494 3	37.14 7	7.71 2	2.17 3.	3.76 85.96	6 10.73	52.66
BAS095	Group-C1	Mimbres-24	Three Circle R/W	Pottery	MURR	MN	Wind Mountain	LA 127260	2.65	37.82 0		32.62	7.12	1.96 3.	3.54 75.93	3 7.90	37.46
BAS096	Group-C1	Mimbres-24	Three Circle R/W	Pottery	MURR	NM	Wind Mountain	LA 127260	5.45					2.21 3.			
BAS097	Group-C1	Mimbres-24	Three Circle R/W	Pottery	MURR	M	Wind Mountain	LA 127260	3.87	39.13 0							
BAS098	Group-C1	Mimbres-24	Three Circle R/W	Pottery	MURR	M	Wind Mountain	LA 127260	3.98	37.35 0							
BAS099	Group-C1	Mimbres-24	Three Circle R/W	Pottery	MURR	NM	Wind Mountain	LA 127260	4.20	41.07 0	0.5170 3	35.05 7	7.95 3	3.20 4.	4.03 87.30	0 12.41	51.56
BAS100	Group-C1	Mimbres-24	Three Circle R/W	Pottery	MURR	M	Wind Mountain	LA 127260	3.89							_	
BAS101	Group-C1	Mimbres-24	Three Circle R/W	Pottery	MURR	M	Wind Mountain	LA 127260	4.44								
BAS102	Group-B1	Mimbres-05A	Three Circle R/W	Pottery	MURR	N	Wind Mountain	LA 127260	3.03	_		_					
BAS103	Group-C1	Mimbres-24	Three Circle R/W	Pottery	MURR	N	Wind Mountain	LA 127260	5.03	_						_	
BAS104	Group-C2b	Mimbres-47	Three Circle R/W	Pottery	MURR	M	Wind Mountain	LA 127260	2.57								
BAS105	Group-C1	Mimbres-24	Three Circle R/W	Pottery	MURR	N	Wind Mountain	LA 127260	4.77							_	
BAS106	Group-C1	Mimbres-24	Mimbres B/W Style I	Pottery	MURR	N	Wind Mountain	LA 127260	5.23							_	
BAS107	Group-B	Unas.	Mimbres B/W Style I	Pottery	MURR	N	Wind Mountain	LA 127260	3.16						1		
BAS108	Group-C1	Mimbres-24	Mimbres B/W Style I	Pottery	MURR	M	Wind Mountain	LA 127260	3.54							_	
BAS109	Group-B1	Mimbres-05A	Mimbres B/W Style I	Pottery	MURR	NM	Wind Mountain	LA 127260	4.77						1		45.95
BAS110	Group-B	Unas.	Mimbres B/W Style I	Pottery	MURR	MN	Wind Mountain	LA 127260	3.39	45.70 0	0.5073 3	38.74 8		3.21 4.	4.24 87.83	3 11.57	74.14
BAS111	Group-C2a	Mimbres-49A	Mimbres B/W Style I	Pottery	MURR	MN	Wind Mountain	LA 127260	3.09	35.35 0	0.3171 2	24.87 5	5.13 3		2.04 67.06	9.41	35.91
BAS112	Group-B1	Mimbres-05A	Mimbres B/W Style I	Pottery	MURR	MN	Wind Mountain	LA 127260	2.61	50.34 0		45.74 8	8.96 2	2.98 5.	5.43 126.91	1 6.13	
BAS113	Group-C1	Mimbres-24	Mimbres B/W Style I	Pottery	MURR	NM	Wind Mountain	LA 127260	5.98	41.33 0	0.4314 3		7.70 2	2.37 3.	3.45 87.08	8 13.97	48.72
BAS114	Group-B1	Mimbres-05A	Mimbres B/W Style I	Pottery	MURR	MN	Wind Mountain	LA 127260	3.34								
BAS115	Group-C1	Mimbres-24	Mimbres B/W Style I	Pottery	MURR	N	Wind Mountain	LA 127260	5.76	_							
BAS116	Group-C2b	Mimbres-44	Mimbres B/W Style I	Pottery	MURR	N	Wind Mountain	LA 127260	2.07	42.01 0	0.3447 3	38.96 6	6.71	1.24 2.	2.61 76.99	9 11.77	23.65

>	55.14	16.25	32.96	78.52	82.84	66.05	111.26	88.08	85.74	84.62	69.05	98.51	85.27	81.70	80.30	74.33	78.49	98.48	84.25	85.98	80.56	80.26	74.50	62.56	86.38	98.95	72.50	88.81	63.87	69.73	83.70	49.52	14.76	78.11	16.77	81.49	60.03	101.53	63.51	66.82	96.34	71.66	80.30	100.26
I	3208.2	1341.1	2288.0	4297.7	4159.3	3808.5	4492.4	3150.5	2865.2	3519.5	4022.4	3753.5	3404.7	3043.2	4051.4	3775.0	3561.2	4443.0	3768.9	4793.7	3877.4	4140.7	3266.8	2846.5	4037.0	3951.5	3955.0	3844.1	3353.1	3840.4	4186.5	27475	3617.8	4849.9	1634.8	3331.9	3221.2	4853.1	2962.5	4098.9	4920.2	4480.1	4147.2	3834.7
NA	12580.0	11988.3	14700.8	20695.6	12971.8	18882.1	19773.5	17902.5	14024.3	18933.4	18881.1	21190.0	16300.2	20160.3	19081.1	20838.1	21346.4	19942.0	11206.8	13321.1	17395.8	14408.1	12305.5	14625.9	17070.1	19929.8	15136.7	17601.4	14030.9	14964.7	19824.0	17215.9	13242.9	19003.9	13543.4	1 / 263.4	15803.7	16095.7	16406.7	14994.9	19013.2	13588.3	20610.5	14930.6
W		196.4	437.6	510.5	478.6	449.0	. 1.7.79	382.9	646.6	482.1	2003	6.699	499.3	515.6	464.8	380.1	353.9	513.1	397.4	-	524.3	466.4	322.4	251.1	464.9										- 1					288.8	547.0			718.1
¥	24945.0	35722.6	31892.3	23273.6	29332.3	21440.9	17606.7	20106.3	26792.4	27541.3	21539.3	18668.3	22504.6	16924.3	27656.7	20237.2	22116.1	23283.1	29120.3	26524.4	23391.0	27822.2	26440.5	27159.3	20774.9	21366.5	26172.0	22867.5	27062.2	29873.8	18161.1	7,0027	26827.1	0.12642	29440.0	2/042.5	26369.4	24983.5	22399.0	27186.6	23075.9	25606.1	20179.2	17694.4
DY	3.052	3.419	4.255	5.297	10.187	4.977	6.707	5.176	898.9	4.941	5.395	4.260	4.813	4.711	5.720	5.243	4.743	7.029	6.443	6.052	5.563	6.197	5.905	5.876	5.420	5.560	7.103	5.820	5.727	8.060	5.367			_	_	4.784	8.227	6.446	_	7.143	6.447	8.736	5.424	4.303
CA	10848.7	7642.3	12936.9	16369.7	10478.1	18695.1	23827.3	15332.2	13091.5	25596.9	12912.0	12584.0	19097.7	22261.7	18449.5	17432.1	15009.0	23548.5	12538.0	14657.9	20148.9	18968.3	13998.5	13584.4	19816.2	19621.2	18968.2	23431.8	13016.2	10962.7	17192.0	9114.8	138/6.4	13330.4	13223.0	12300.7	12784.9	19389.3	9511.4	12844.4	14269.6	12305.8	11038.5	20886.5
BA	9.707	390.4	782.2	646.7	559.7	1067.3	673.9	712.0	570.3	735.4	871.3	707.1	2.998	832.1	694.7	713.2	9.707	1032.1	1257.4	1354.8	713.8	1257.7	1204.7	1733.0	616.0	971.3	1164.0	726.0	1735.4	529.3	872.7	7.699	13/2.4	0000.8	9/5.4	926.4	677.3	554.1	674.2	735.3	657.8	326.8	618.0	702.2
AL	90220.6	100013.6	89059.9	96228.9	7.00977	90353.0	91289.3	96054.5	75363.3	89387.3	91922.7	90278.3	90291.0	8.09856	89575.9	106246.1	97451.5	92554.4	97448.2	89447.9	94649.9	95884.3	92589.3	89905.1	8.66766	96012.1	87696.0	96284.4	86823.4	85848.8	98622.8	93/65.3	93147.2	70404	18494.3	910//.9	87852.5	74982.2	103064.4	83504.5	97887.8	84475.0	99617.8	98590.1
ZR	176.9	175.4			214.1	149.6	180.4	179.6	187.4	182.4	160.8	192.4	188.7	160.5	152.0	. 157.5	167.6	187.2	203.1	191.6	158.3	170.2	212.1	193.0													227.5			287.2				156.1
NZ	61.6	52.9			90.9	78.2	87.3	9.88	85.1	86.5	90.6	86.8	78.0	78.1	62.5		6'66		87.3	79.8	84.4	78.7	67.9	62.7												<u>-</u>					95.7	_		83.5
3 TH			7	9.65	17.41		9.48	10.89	15.17	9.44		9.79	07.6	6.57	10.28		3 9.62	9.60	3 13.08	12.41	11.11	3 12.79	5 11.29	5 11.39	l				_		-+										10.97		_	9.92
TA TE	6 0.54		4 0.75	0 0.92	7 1.7	7 1.12	5 1.06	3 1.04	7 1.29	7 0.98	4 1.12	1 0.92	2 0.84	2 0.99	8 1.16	96.0 6	6 0.83	86.0 9	1 0.98	1 1.23	5 1.22	1 1.03	4 0.95	8 0.95			8 1.30	7 1.05					_					3 1.25	7 0.62	`	1			9 0.85
	1.4736	2.4359		0.7910	1.3157	0.7857	0.8585	1.0783	1.3287	0.9097	0.8364	0.8841	0.8242	0.8802	8988'0		0.8016	0.8816	1.4291	1.2921	0.9535	1.2131	1.0644	1.0828				_	_										_		_			0.6629
SR	185.8	113.9	334.6	440.8	195.3	484.8	416.1	392.2	346.1	561.0	498.4	466.8	431.3	425.9	365.6	466.2	422.9	496.9	410.1	443.4	330.8	461.9	467.6	468.1	355.2	515.6	496.3	437.0	476.1	267.0	466.3	349.2	468.4	400.0	8.75/	487.2	220.0	367.5	400.2	265.2	393.6	176.3	351.0	421.0
SC	8.48	4.29	6.88	10.20	10.40	09.6	10.98	11.43	6.97	10.51	10.21	89.6	9.45	10.33	10.33	11.31	11.02	10.32	10.45	9.46	10.93	9.73	8.89	7.89	10.37	10.80	9.27	11.00	9.01	10.97	11.66	7.59	8.8/	1.40	5.81	8.86	12.03	9.77	9.56	11.56	11.94	12.93	11.22	11.88
SB	0.5128	0.5457	0.4085	0.5717	1.0625	0.3674	0.3884	0.9059	0.6910	0.4161	0.4022	0.5346	0.4000	0.3900	0.5759	0.4773	0.5569	0.4105	1.3998	1.3573	0.5660	1.1176	1.3424	1.3469	0.5328	0.5652	1.4689	0.5984	1.1198	0.7915	0.6685	0.3885	1.3508	0.0038	1.4308	0.9941	0.6084	0.6156	0.4027	0.5012	0.7168	0.5572	0.6486	0.3461
RB	160.60	235.78	164.54	118.29	151.94	94.53	122.68	118.41	128.76	89.22	110.59	113.86	110.78	114.08	109.35	115.17	107.66	104.37	135.22	131.47	118.55	131.03	128.29	128.20	136.46	123.46	142.50	128.89	130.63	152.26	119.92	116.53	131.87	130.07	144.96	136.54	152.52	155.70	108.35	155.23	121.31	163.29	125.73	89.14
Z	0.0	0.0		0.0	15.8	0.0	0.0	0.0	33.0	0.0	0.0	0.0	19.6	0.0	0.0	0.0	0.0	0.0	37.0	33.0	0.0	0.0	0.0	0.0	0.0			0.0			0.0	0.0	0.0			0.0	0.0	0.0	0.0	0.0	0.0			15.8
生	7.45	7.44	98.9	7.80	9.47	7.00	7.70	7.43	89.8	8.80	7.08	99.8	7.45	7.08	7.31	7.28	7.34	7.82	8.52	8.22	7.41	8.18	8.53	7.46		7.24	8.32	7.02	89.8	8.82	7.40	5.33	7.38	6.29	5.71			11.07	6.05	10.62	9.11	10.03	7.79	5.36
FE	29981.5	12200.2		40122.5	37654.5	36442.5	44853.6	40456.2	34280.7	41424.7	37663.4	43442.9	37673.6	41257.0	39016.4	41398.6	39887.8	40216.1	41608.2	36447.3	37239.3	37955.4	35212.6		37867.5	40082.8	34346.5	37372.2			41633.9	24013.4	34912.4	7.02014				35357.7	29902.8	32256.1				53516.4
EU	0.9052	0.5921	1.1415	1.6475	1.8617	1.5323	1.9979	1.7005	1.3479	1.6369	1.6304	1.5303	1.5263	1.7321	1.6539	1.8318	1.6553	1.6075	1.4297	1.4812	1.5601	1.4389	1.4301	1.4878	1.5672	1.6027	1.5423	1.5602	1.3372	1.4569	1.7029	1.14/3	1.5213	1.748/	1.2051	1.5/29	1.5395	1.4188	1.1361	1.3571	1.7551	1.2989		1.6438
CS	6.59	17.75	4.22	23.91	8.20	11.89	25.06	22.42	5.34	14.37	14.37	17.92	10.71	22.54	13.45	30.49	24.51	12.99	15.74	15.96	14.18	13.86	15.34	17.85	16.98	19.59	19.48	16.50	9.59	8.20	22.53			_				6.73	2.90	7.72	21.44	7.99		3.52
ANID	BAS073	BAS074	BAS075	BAS076	BAS077	BAS078	BAS079	BAS080	BAS081	BAS082	BAS083	BAS084	BAS085	BAS086	BAS087	BAS088	BAS089	BAS090	BAS091	BAS092	BAS093	BAS094	BAS095	BAS096	BAS097	BAS098	BAS099	BAS100	BAS101	BAS102	BAS103	BAS104	BAS105	DAC100	BAS10/	BAST08	BAS109	BAS110	BAS111	BAS112	BAS113	BAS114	BAS115	BAS116

ANID	macro grb	macro arp Chem2012	CERAMIC TYPE	MATERIAL	SOURCE	STATE	SITE NAME	SITE NO	AS	Р	n	QN	SM	U YB	3 CE	00	CR
BAS117	Group-B1	Mimbres-04C	Mimbres B/W Style I	Pottery	MURR	MN		LA 127260	2.03	43.44 0	0.4858 3		7.11 4.87	~	88	-	34.05
BAS118	Group-C1	Mimbres-22	Mimbres B/W Style I	Pottery	MURR	MN	Wind Mountain	LA 127260	5.93		0.3283 3	38.87 6.	6.57 1.37	37 2.90	0 85.29	6.51	14.92
BAS119	Group-B1	Mimbres-05A	Mimbres B/W Style I	Pottery	MURR	MN	Wind Mountain	LA 127260	3.47	40.94 0	0.6826 4	43.09 9.	9.68 3.93	93 5.58	3 82.58	7.63	59.35
BAS120	Group-C1	Mimbres-21	Mimbres B/W Style I	Pottery	MURR	MΝ	Wind Mountain	LA 127260	2.18	39.14 0	0.3240 3	30.19 5.	5.64 1.3	1.38 2.51	1 80.02	98.8	51.10
BAS121	Group-C2a	Mimbres-49A	Mimbres B/W Style II	Pottery	MURR	NM	Wind Mountain	LA 127260	2.97	_						,	59.42
BAS122	Group-C1	Mimbres-21	Mimbres B/W Style II	Pottery	MURR	M	Wind Mountain	LA 127260	2.71			28.70 5.	5.39 1.7		3 75.42	11.34	80.80
BAS123	Group-B	Unas.	Mimbres B/W Style II	Pottery	MURR	M	Wind Mountain	LA 127260	2.68		0.6568 4		10.18 4.2	4.25 4.56	5 88.78		42.49
BAS124	Group-C1	Mimbres-21	Mimbres B/W Style II	Pottery	MURR	M	Wind Mountain	LA 127260	2.90								66.22
BAS125	Group-C1	Mimbres-21	Mimbres B/W Style II	Pottery	MURR	NM	Wind Mountain	LA 127260	1.99	42.48 0				1.86 2.60		10.54	75.26
BAS126	Group-C1	Mimbres-21	Mimbres B/W Style II	Pottery	MURR	MN	Wind Mountain	LA 127260	2.92		0.3324 3	30.03 5.	`	1.33 2.42		80.8	39.40
BAS127	Group-C1	Mimbres-21	Mimbres B/W Style II	Pottery	MURR	MN	Wind Mountain	LA 127260	2.46	38.24 0	0.3223 2	26.01 4.		1.13 1.92	2 75.38	7.31	29.81
BAS128	Group-B1	Mimbres-05A	Mimbres B/W Style II	Pottery	MURR	MN	Wind Mountain	LA 127260	4.59	51.41 0	0.7497 4	42.61 9.	9.73 3.93	93 5.54	4 92.32	9.41	80.99
BAS129	Group-B	Unas.	Mimbres B/W Style II	Pottery	MURR	MN	Wind Mountain	LA 127260	2.38		0.4452 3	36.75 7.		1.99 3.28		7.09	48.44
BAS130	Group-C1	Mimbres-21	Mimbres B/W Style II	Pottery	MURR	MN	Wind Mountain	LA 127260	4.15	39.88 0	0.3560 3	30.58 5.	5.89 1.3	1.38 2.43	3 79.04	7.17	26.69
BAS131	Group-C1	Unas.	Mimbres B/W Style II	Pottery	MURR	NM	Wind Mountain	LA 127260	3.42	34.85 0	0.5107 3		6.72 1.6	1.62 3.26		11.47	19.73
BAS132	Group-C1	Mimbres-21	Mimbres B/W Style II	Pottery	MURR	NM	Wind Mountain	LA 127260	2.60				5.83 1.47			11.51	49.10
BAS133	Group-B	Unas.	Mimbres B/W Style II	Pottery	MURR	NM	Wind Mountain	LA 127260	8.19		ц,	1		31 6.54	1	4.33	30.49
BAS134	Group-B	Unas.	Mimbres B/W Style II	Pottery	MURR	NM	Wind Mountain	LA 127260	2.90	24.51 0	0.3349 1	15.36 2.		1.58 2.14	4 38.47	2.15	14.27
BAS135	Group-C1	Mimbres-21	Mimbres B/W Style II	Pottery	MURR	NM	Wind Mountain	LA 127260	1.74	39.85 0	0.3658 3	31.19 5.	5.54 1.42			89.8	49.40
BAS136	Group-B2	Mimbres-11	Mimbres B/W Style III	Pottery	MURR	MN	Wind Mountain	LA 127260	2.93	33.18 0	0.4645 2		4.59 3.78	78 2.99		19.35	43.55
BAS137	Group-B	Unas.	Mimbres B/W Style III	Pottery	MURR	MN	Wind Mountain	LA 127260	2.98	54.56 0	0.4334 3	37.36 6.	6.54 3.08	3.00	08.99	5.05	17.34
BAS138	Group-C2a	Mimbres-49A	Mimbres B/W Style III	Pottery	MURR	MN	Wind Mountain	LA 127260	2.54	40.64 0	0.3396 3	34.15 6.	6.39 2.30	30 2.59	9 78.59	13.60	51.02
BAS139	Group-C1	Mimbres-21	Mimbres B/W Style III	Pottery	MURR	MN	Wind Mountain	LA 127260	3.46	41.30 0	0.4268 3	_		1.52 3.03		12.15	81.95
BAS141	Group-B2	Mimbres-11	Mimbres B/W Style III	Pottery	MURR	NM	Wind Mountain	LA 127260	2.73						4 72.81	7	44.57
BAS142	Group-B	Unas.	Mimbres B/W Style III	Pottery	MURR	M	Wind Mountain	LA 127260	2.98				5.39 3.14	14 2.81			17.40
BAS143	Group-C1		Mimbres B/W Style III	Pottery	MURR	MN	Wind Mountain	LA 127260	4.74								66.11
BAS144	Group-C2a		Mimbres B/W Style III	Pottery	MURR	M	Wind Mountain	LA 127260	4.41							1	42.19
BAS145	Group-B	Unas.	Mimbres B/W Style III	Pottery	MURR	M	Wind Mountain	LA 127260	1.84								26.94
BAS146	Group-C1	Mimbres-21	Mimbres B/W Style III	Pottery	MURR	ΣN	Wind Mountain	LA 127260	4.62							11.37	62.00
BAS147	Group-C1	Mimbres-21	Mimbres B/W Style III	Pottery	MURR	ΣN	Wind Mountain	LA 127260	3.76							_	83.63
BAS148	Group-B2	Mimbres-08	Mimbres B/W Style III	Pottery	MURR	ΣN.	Wind Mountain	LA 127260	3.12		_						25.04
BAS149	Group-C1		Mimbres B/W Style III	Pottery	MURR	MZ :	Wind Mountain	LA 127260	2.17								29.28
BAS150	Group-C2a		Mimbres B/W Style III	Pottery	MURR	Σ	Wind Mountain	LA 127260	2.94								49.58
BAS151	Group-C1	Mimbres-24	Mogollon R/B	Pottery	MURR	ΣN	Old Town	LA 001113	4.45	_						_	21.02
BAS152	Group-C1	Unas.	Mogollon R/B	Pottery	MURR	M	Old Town	LA 001113	4.54					2.16 2.67			34.24
BAS153	Group-C1	Mimbres-24	Mogollon R/B	Pottery	MURR	NM	Old Town	LA 001113	4.95		0.4604 3	35.66 7.	7.29 2.37	37 3.44		12.56	41.18
BAS154	Group-C1	Mimbres-24	Mogollon R/B	Pottery	MURR	NM	Old Town	LA 001113	5.17			36.27 7.	7.55 1.4	1.46 3.24		13.45	24.61
BAS155	Group-C1	Mimbres-24	Mogollon R/B	Pottery	MURR	NM	Old Town	LA 001113	3.59	38.95 0	0.4539 3	37.13 7.	7.02 1.54	54 3.16		12.77	15.05
BAS156	Group-C1	Mimbres-24	Mogollon R/B	Pottery	MURR	Σ	Old Town	LA 001113	3.15	37.43 0	0.4833 3	34.55 7.	7.15 2.21	21 3.72	2 72.75	12.22	44.16
BAS157	Group-B	Unas.	Mogollon R/B	Pottery	MURR	MN	Old Town	LA 001113	5.71	63.75 0	0.3442 4	44.06 8.	8.26 5.14	14 2.41	1 101.53	7.86	43.11
BAS158	Group-C1	Mimbres-24	Mogollon R/B	Pottery	MURR	M	Old Town	LA 001113	2.49								16.05
BAS159	Group-C1	Mimbres-24	Mogollon R/B	Pottery	MURR	M	Old Town	LA 001113	4.56								21.40
BAS160	Group-C1		Mogollon R/B	Pottery	MURR	M	Old Town	LA 001113	4.12								29.14
BAS161	Group-C2a	Mimbres-46	Mogollon R/B	Pottery	MURR	MM	Old Town	LA 001113	6.53	40.64 0	0.5071 3	35.19 7.	7.52 2.3	2.34 2.87	7 79.49	18.48	89.28

>	78.18	38.22	65.10	42.88	94.00	54.05	56.30	48.45	53.53	44.55	28.96	00.96	47.06	36.51	85.45	49.19	54.76	29.58	54.55	56.73	50.29	63.59	72.63	64.89	36.63	86.38	82.11	33.93	60.36	57.22	48.92	50.17	57.75	78.75	58.80	78.10	60.96	94.19	84.15	127.08	84.47	85.25	89.26	135.98
I	4123.8	2168.0	4639.0	2259.5	4006.9	2218.9	3712.9	2360.0	2178.1	1474.3	1071.3	4649.8	2479.1	1766.2	2948.3	2083.9	3110.1	1430.9	1094.1	3683.6	3122.2	3837.1	3182.5	2931.7	2158.9	3547.4	3655.7	2251.1	2289.4	2790.5	2925.8	2556.1	3474.2	4627.4	2622.0	3678.3	3546.1	4298.4	4200.1	5606.3	3461.2	4672.5	3420.6	5615.9
NA	17546.2	11397.0	14909.2	17501.5	16938.3	17901.7	11879.7	16762.4	17439.1	19027.8	15022.1	15394.8	16797.7	13543.5	16938.4	16812.0	10774.7	8321.2	17587.1	10211.0	14394.5	16626.0	17569.3	9656.7	14490.3	16311.2	14488.1	15422.6	16937.5	17947.2	9267.0	92626	16477.3	18075.8	10454.9	16450.0	19919.0	22095.8	20369.9	19211.1	23645.4	24171.2	16618.0	17025.9
MN				1123.7	738.2	1179.6	524.8	1064.9	1117.7	9.806	1096.4	516.8	749.8	772.1	1192.9	990.3	143.4	400.2	1170.8	637.5	395.6	572.2	934.6	639.3	415.2			189.0	941.7	1034.7	204.3			554.9	263.7	497.0	610.1	470.5	505.0	633.3	510.1			1029.3
×	28816.9	28852.5	26423.5	24239.4	21163.1	27123.2	22954.6	22658.7	25765.0	20729.1	26016.5	26280.8	28313.9	31276.5	28369.5	22348.9	34551.1	14251.0	25196.7	30026.5	30382.0	23003.2	26621.3	30682.3	26759.9	26369.0	24499.4	25931.8	28481.7	22093.4	30828.3	20320.6	23121.7	21757.7	30204.5	24586.3	21874.1	20638.1	26278.9	22788.3	23672.6	20116.2	22187.3	26232.6
DΑ	5.652	3.810	8.395	3.516			7.338	3.874	3.231	3.350	2.510	8.168	4.233	3.086	3.678	3.244	11.143	2.470	3.853	3.274	3.851	4.740	3.954	3.082	2.882		6.435	3.714	3.557	4.849	2.525	2.979	3.435		3.837	4.842	5.579	5.720	5.160	5.033	5.168	4.860	6.833	5.033
CA	11639.1	21545.4	92636	13091.5	17633.0	17219.3	8794.3	12849.5	13382.1	20500.2	16495.6	14199.5	15878.0	22177.5	18741.5	17637.2	5349.2	9236.3	10402.8	9349.6	12729.5	16336.6	5499.6	10023.3	14343.7	11001.6	18568.7	10757.0	10549.3	6322.6	6392.0	25416.6	18119.4	12711.8	12352.1	17372.9	17389.7	22127.3	21179.1	13443.9	18738.0	20524.0	14286.1	20288.3
BA	1067.4	6.097	510.5	1475.2	944.8	783.1	623.2	738.9	713.4	555.3	845.6	466.5	749.9	735.5	413.3	749.0	357.8	304.4	730.7	429.0	908.3	725.5	781.1	419.3	817.7	654.0	1029.6	572.0	797.5	0.959	388.0	855.1	764.1	753.4	1488.4	738.1	659.3	802.8	869.5	1104.7	757.1	955.7	9.269	1052.5
AL	85881.4	97590.7	74548.0	82775.9	97582.2	86448.7	86118.3	76923.9	84905.2	8.69686	89171.8	80403.4	84939.3	90682.4	92240.0	87299.3	94163.5	90296.9	85738.6	78533.2	82509.1	92274.0	83858.0	79032.0	81204.1	85195.3	88958.0	86850.8	90839.8	79816.4	80947.7	90655.9	93542.1	100171.7	90615.7	92175.9	94647.8	101034.8	89786.4	02063.3	99808.2	98546.1	96385.8	89923.3
ZR	249.1	151.4	269.9	167.5	187.7	147.4	181.3	177.1	196.8	153.1	136.4	247.8	150.0	136.7	162.2	183.2	272.5	112.5	179.9	159.8	235.9	177.3	188.5	153.0	276.4	200.6	166.2		184.5	187.1	162.8				133.0	179.3	190.2	198.3	175.5	203.7			196.0	222.1
NZ	80.0	9.6/	116.4	78.4	82.4	93.1	6.69	83.8	83.6	1.68	9.77	109.2	2.07	1.06	148.0	102.7		54.6	85.5	67.2	54.8	66.5	88.1	1.79	0.99	86.7	110.0	50.2	93.5	99.1	49.8	91.4	103.0	95.2	0.69	89.0	0.68	9'88	85.9	190.2			85.5	96.4
TH S		10.53	_		2 11.34		17.87		10.54		3 8.85		12.60	07.6	10.20			5 21.30	1 9.51	18.77	15.21	5 11.07	2 10.79	18.56	14.82				_				_			10.63	9.33	68.8	10.97	2		_		11.03
TA TB	58 0.88	95 0.89	30 1.67	74 0.75	9 1.22	_	1.35		24 0.83	23 0.81	21 0.58	28 1.55	06'0 60	0.77	10.0	54 0.75	13 1.89	59 0.36	94 0.71	24 0.57	9 0.80	12 0.76	92 0.92	19.0 66	35 0.70			69.0 9	0.77				33 0.73		0.73	1.00	1.16	1 0.89	38 0.96	58 0.94	1.01	_	39 1.30	20 1.00
			2.1530	•		_	1.6302		0.8424	0.7323	0.5221	1.8628	0.9209	0.7898	0.7397			1.5259	0.6294	1.5524	0.9469	0.8712	0.9092)					•					0.9701	0.8877	0.8414	1 0.6971	0.9288	_				0.8520
SR	373.5	326.3	210.1	393.1	480.0	376.8	192.2	404.4	344.1	410.5	36698	288.8	342.2	339.1	631.4	468.4	88.9	106.8	351.2	194.2	228.6	493.4	360.2	224.7	242.7	308.2	438.1	272.9	353.2	338.6	140.1	469.1	499.2	440.5	299.0	435.0	498.6	519.4	485.1	563.1	533.4	636.3		421.5
SC	9.26	5.17	9.67		_		11.25		8.15	6.46	5.37	11.19	7.42	5.37	12.15	8.28	_	96.9	6.59	7.75	6.25	10.31	9.30	8.02		10.06	_		8.33			6.95	10.34	10.63	7.16	10.90	10.82	10.00	10.22	_				15.26
SB	0.4162	2.3870	0.5602	1.8568	0.4253	1.6888	0.5061	1.5862	1.5913	1.1485	3.4451	0.5724	0.7602	3.9475	0.4074	1.6521	1.0675	0.2297	2.1485	0.7990	1.1254	0.3282	1.9841	0.7498	1.1237	1.3166	0.7697	0.3608	2.3132	2.0696	0.6226	1.1227	0.3141	0.4527	1.3921	0.6429	0.4898	0.3599	0.4799	3.0934	0.4173	0.4162	0.6564	0.8890
RB	135.30	158.16	167.74	126.46	104.81	117.32	138.52	122.36	128.29	118.11	122.82	141.05	137.52	140.44	137.75	116.19	211.08	66.07	125.36	200.61	114.84	95.32	132.38	198.15	111.15	136.37	107.38	166.91	141.56	129.39	185.26	105.15	99.75	104.27	132.21	123.77	104.54	112.28	116.77	79.36	107.01	105.07	131.82	122.54
Z						_	35.1			25.4	0.0	34.5	20.0	0.0	0.0	0.0	20.9	0.0	0.0	0.0	0.0	0.0		18.9					0.0		0.0	28.9	28.3		42.5	0.0	0.0	0.0	30.1	26.9	27.4		0.0	43.3
生	8.62	60.9	10.25	6.51	7.60	6.56	7.53	7.43	7.40	6.85	6.04	89.6	6.92	6.52	5.97	6.56	11.63	7.74	9.80	96.9	9:26	69.9	7.82	7.09	11.53	9.14	7.28	6.63	7.35	8.13	7.52	6.50	6.98	7.64	6.33	7.23	7.97	7.08	7.30	7.11	7.18	7.45	7.22	8.42
H	28011.6	20741.8	36435.7	26227.9	36189.3	28685.0	29515.4	26659.3	28050.1	23572.2	21852.2	39516.1	25910.8	22554.4	42730.9	32958.5	23837.0	13657.8	24832.7	23430.2	22133.2	35863.7	33735.9	24213.6	21869.5	35357.4	37139.6	21997.4	30062.0	32912.3	20814.5	26445.5	36561.8	38797.3	29783.9	38938.2	41085.5	38620.6	36453.5	29409.4	35000.5	38945.8	38261.4	53769.1
ED				_					1.2840	1.3073	1.1496	1.3303	1.1938	1.2132	1.7306			0.4332	1.1872	7.39 0.8943	1.3301	1.4812	1.4298	0.9585		_									1.0660	1.6411	1.7385	1.6864	1.5324	2.0135				1.7658
CS	4.71						7.22	16.04	16.18		20.54	6.93	14.73	23.97	25.00	23.04	10.05	6.58	17.31	7.39	5.97	3.34	15.43	7.58 (5.94										11.98	15.95	18.03	21.44	17.10	4.08				8.04
ANID	BAS117	BAS118	BAS119	BAS120	BAS121	BAS122	BAS123	BAS124	BAS125	BAS126	BAS127	BAS128	BAS129	BAS130	BAS131	BAS132	BAS133	BAS134	BAS135	BAS136	BAS137	BAS138	BAS139	BAS141	BAS142	BAS143	BAS144	BAS145	BAS146	BAS147	BAS148	BAS149	BAS150	BAS151	BAS152	BAS153	BAS154	BAS155	BAS156	BAS157	BAS158	BAS159	BAS160	BAS161

ANID	macro grp	macro grp Chem2012	CERAMIC TYPE	MATERIAL	SOURCE	STATE	SITE NAME	SITE NO	AS	ΓA	Π	ND	SM) N	YB CE	E CO	CR
BAS162	Group-C1	Mimbres-24	Mogollon R/B	Pottery	MURR			LA 001113	4.62	38.76 0.	0.4749 3		6.91	1.06 2.99	99.46	12	16.98
BAS163	Group-B1	Mimbres-04C	Mogollon R/B	Pottery	MURR	M	Old Town	LA 001113	3.51	44.80 0.	0.5287 3	37.58 7.	7.50 3.	71 3.56		6 8.15	28.64
BAS164	Group-B	Unas.	Mogollon R/B	Pottery	MURR	M	Old Town	LA 001113	3.17	57.66 0.	0.3362 3	37.46 7.	7.38 4.	4.73 2.29	66'18 67	9 6.03	41.49
BAS165	Group-C1	Mimbres-24	Mogollon R/B	Pottery	MURR	MN	Old Town	LA 001113	3.98	36.66 0.	0.4037 3	30.31 6.	6.16 2.0	2.04 2.82	32 70.10	0 8.27	38.05
BAS166	Group-B1	Mimbres-05B	Three Circle R/W	Pottery	MURR	NM	Old Town	LA 001113	3.03							,	
BAS167	Group-C1	Mimbres-24	Three Circle R/W	Pottery	MURR	M	Old Town	LA 001113	5.24				8.37 2.	2.59 3.85		1	
BAS168	Group-B1	Mimbres-04C	Three Circle R/W	Pottery	MURR	M	Old Town	LA 001113	2.01	44.70 0.	0.4876 3			3.11 3.25	25 83.03	3 8.91	36.26
BAS169	Group-C2a	Mimbres-49A	Three Circle R/W	Pottery	MURR	M	Old Town	LA 001113	2.38							1	
BAS170	Group-B1	Mimbres-04B	Three Circle R/W	Pottery	MURR	NM	Old Town	LA 001113	2.80	42.40 0.				5.06 2.88			
BAS171	Group-B1	Mimbres-05B	Three Circle R/W	Pottery	MURR	MN	Old Town	LA 001113	3.26	_	0.5598 3	34.43 7.	7.30 4.	4.35 4.01)1 83.84	4 10.15	41.46
BAS172	Group-C1	Unas.	Three Circle R/W	Pottery	MURR	NN	Old Town	LA 001113	2.90	42.51 0.		37.89 7.	7.65 2.	2.63 3.47	17 91.00	0 13.56	86.96
BAS173	Group-B1	Mimbres-04C	Three Circle R/W	Pottery	MURR	MN	Old Town	LA 001113	2.10	41.12 0.	0.4587 3	33.02 6.	6.42 3.0	3.00 3.00	104.84	4 8.02	28.98
BAS174	Group-B1	Mimbres-05B	Three Circle R/W	Pottery	MURR	MN	Old Town	LA 001113	2.84	_				4.11 4.23			
BAS175	Group-C1	Mimbres-24	Three Circle R/W	Pottery	MURR	NM	Old Town	LA 001113	5.31				7.50 2.	2.14 3.49		4 13.57	39.72
BAS176	Group-C1	Mimbres-24	Three Circle R/W	Pottery	MURR	NM	Old Town	LA 001113	5.09				7.07	2.35 3.47		4 7.96	
BAS177	Group-C2a	Mimbres-46	Three Circle R/W	Pottery	MURR	NM	Old Town	LA 001113	2.66					2.38 2.41		7	93.47
BAS178	Group-C1	Mimbres-24	Three Circle R/W	Pottery	MURR	NM	Old Town	LA 001113	4.86				7.94 2.			4 8.26	
BAS179	Group-C2b	Mimbres-41	Three Circle R/W	Pottery	MURR	MN	Old Town	LA 001113	1.54	37.24 0.:	0.3386 2	27.58 5.	5.41 1.3	1.80 2.33	33 73.59		24.68
BAS180	Group-C1	Unas.	Three Circle R/W	Pottery	MURR	M	Old Town	LA 001113	6.54	39.56 0.	0.5586 3	34.95 7.	7.48 2.	2.54 3.89	39 81.87	7 11.56	55.42
BAS181	Group-B1	Mimbres-05A	Mimbres B/W Style I	Pottery	MURR	MN	Old Town	LA 001113	3.38	43.27 0.	0.6546 3		7.89 3.		53 71.42	2 8.55	59.50
BAS182	Group-B1	Mimbres-04B	Mimbres B/W Style I	Pottery	MURR	Z	Old Town	LA 001113	2.43		0.3792 2	24.59 4.	4.60 5	5.26 2.52	52 61.56	3.18	22.35
BAS183	Group-B1	Mimbres-04C	Mimbres B/W Style I	Pottery	MURR	MN	Old Town	LA 001113	2.93	43.59 0.	0.5197 3	32.42 6.	6.41 2.	2.96 3.39	39 81.81	1 9.38	37.70
BAS184	Group-B	Unas.	Mimbres B/W Style I	Pottery	MURR	MN	Old Town	LA 001113	2.00	47.91 0.	0.4238 3	34.26 6.	6.33 2.	2.03 2.73		8 8.51	22.20
BAS185	Group-C1	Unas.	Mimbres B/W Style I	Pottery	MURR	M	Old Town	LA 001113	3.41	26.48 0.			5.49 2.	2.25 2.61		_	
BAS186	Group-B1	Mimbres-04C		Pottery	MURR	NN	Old Town	LA 001113	2.16	43.11 0.	0.5442 3	35.17 6.	6.61 2.	2.46 3.59	59 90.56	6 9.30	34.21
BAS187	Group-C2	Unas.		Pottery	MURR	NN	Old Town	LA 001113	3.01	36.63 0.			7.21 4			1	
BAS188	Group-B1	Mimbres-04C		Pottery	MURR	M	Old Town	LA 001113	2.06	_							
BAS189	Group-B1	Mimbres-05B		Pottery	MURR	MN	Old Town	LA 001113	3.13								
BAS190	Group-C2a	Mimbres-49A		Pottery	MURR	N	Old Town	LA 001113	2.08				6.54 2.	2.65 3.38		0 10.73	
BAS191	Group-B	Unas.	Mimbres B/W Style I	Pottery	MURR	MN	Old Town	LA 001113	1.97							_	
BAS192	Group-B1	Mimbres-04C	Mimbres B/W Style I	Pottery	MURR	M	Old Town	LA 001113	1.97		٥.						
BAS193	Group-B	Unas.	Mimbres B/W Style I	Pottery	MURR	M	Old Town	LA 001113	4.56	_							52.72
BAS194	Group-C2a	Mimbres-49A	Mimbres B/W Style I	Pottery	MURR	M	Old Town	LA 001113	1.79				9.17 2.			5 9.77	63.34
BAS195	Group-C2	Unas.	Mimbres B/W Style I	Pottery	MURR	NM	Old Town	LA 001113	2.29	48.55 0.	0.3358 3	37.99 6.	6.45 1.	1.55 2.37		3 9.12	19.08
BAS196	Group-B	Unas.	Mimbres B/W Style II	Pottery	MURR	NM	Old Town	LA 001113	5.16	40.95 0.	0.7100 3	38.21 8.	8.54 5	5.21 4.96	96 80.64	4 4.93	36.05
BAS197	Group-C1	Mimbres-21	Mimbres B/W Style II	Pottery	MURR	Z	Old Town	LA 001113	2.52	34.75 0.	0.3438 2	27.94 5.	5.22 1.	1.39 2.38	38 70.62	2 11.06	53.20
BAS198	Group-C1	Mimbres-21	Mimbres B/W Style II	Pottery	MURR	MN	Old Town	LA 001113	2.25	37.88 0.				1.21 2.37		4 10.85	46.03
BAS199	Group-B	Unas.	Mimbres B/W Style II	Pottery	MURR	NM	Old Town	LA 001113	4.57	36.14 0.					76 67.83		58.81
BAS200	Group-B2	Mimbres-02A	Mimbres B/W Style II	Pottery	MURR	Z	Old Town	LA 001113	1.59	41.17 0.	0.4341 3		5.89 4.	4.89 2.89		99.6	36.17
BAS201	Group-B1	Mimbres-04A	Mimbres B/W Style II	Pottery	MURR	NN	Old Town	LA 001113	1.67		0.5387 3		7.78 4.	4.94 3.71	11 94.47		
BAS202	Group-C2	Unas.	Mimbres B/W Style II	Pottery	MURR	M	Old Town	LA 001113	1.26				4.78 1.	1.69 1.89			
BAS203	Group-C1	Mimbres-21	Mimbres B/W Style II	Pottery	MURR	M	Old Town	LA 001113	2.36	~	_					_	
BAS204	Group-C1	Mimbres-21	Mimbres B/W Style II	Pottery	MURR	N	Old Town	LA 001113	2.08	_							
BAS205	Group-B	Unas.	Mimbres B/W Style II	Pottery	MURR	MN	Old Town	LA 001113	1.39	37.41 0.	0.4237 2	26.23 5.	5.24 3.	3.46 2.83	33 72.66	6 5.89	28.45

>	82.28	54.49	106.13	61.13	60.81	71.45	60.58	69.86	37.79	54.83	81.37	57.54	62.33	70.44	73.44	127.53	83.13	68.53	66.49	67.92	43.61	70.36	62.45	103.14	61.71	111.53	60.15	62.48	65.70	78.25	77.08	68.54	67.07	C+.C0	47.53	57.21	58 74	51.14	49.54	47.21	63.05	51.35	51 95
I	3744.1	2988.9	5974.1 10		3728.9	3488.3	3436.9	2769.4	2491.2	2448.5		4523.1	3365.6	3778.1	. 0.9968		4297.4	3156.4	3273.0	4237.1	7258.5	. 9.1772	2706.9			_						4291.6								2906.8	3619.7		2500 1
NA					8768.3 3		17906.9 3.		15481.7 2.	8664.4	18039.9	18413.5 4	8503.6	19643.8 3		17285.3 3	14464.3 4.			16429.6 4.	14337.8 2.		12582.4 2	12683.3 3																			
MN	1.0 22799.4	.7 15132.9	1.2 18637.1	_		.9 15695.9		.6 16382.7	١,		١.	1			_	,		.9 17689.1	1.19761.1	`		.7 17543.7	,		14008.4					<u> </u>	,					1.	Ι'		1	1.1 21747.1			0 14071 0
×	.2 564.0	7.179 7.	.9 298.2		.9 647.0	9.668 9.	.5 598.4	.4 1099.6	.4 157.8	.5 618.4	.3 1083.5	.6 560.4	.5 588.7	.6 475.5	.2 361.3	.6 1094.8	.3 371.1	.0 617.9	.2 419.1	.5 471.7	.2 159.0	.8 544.7	.5 430.5	.9 926.2		.6 496.6							.5 411.9	2 6						.9 370.1	.9 1041.1		0 00V C
	22452.2	30371.7	25481.9		27135.9	28902.6	27374.5	22111.4	32935.4	27893.5	1 23713.3	28070.6	27077.5	26729.6	28543.2	34361.6	29419.3	, 25851.0	23516.2	27550.5	28060.2	25810.8	29841.5				_						210015	-						22078.9			32100 2
Dλ	5.034	5.430	4.639			6.685	4.923	4.675	3.441	2.697		4.078	5.686	4.938	5.030		5.291	3.515	5.270	6.943	3.175	4.683	4.469	3.191			-						4.900							3.076			1001
CA	16302.7	11036.5	13736.8	10474.6	18337.6	16985.0	14801.0	15319.8	9486.9	18362.7	22047.6	14602.1	17477.9	14390.4	12486.1	22304.6	12517.1	20730.9	23197.4	12719.1	9105.6	15334.0	11589.1	12736.7	15376.5	12585.0	16471.9	18852.2	16364.3	15693.6	13132.5	10/68.3	135/9.7	8083.0	30363.7	17145.3	12291.3	12710.0	21103.5	14577.9	23075.0	30648.8	12500 3
BA	836.4	871.0	1345.1	1035.2	770.8	995.0	674.6	708.4	645.9	720.2	704.1	762.8	438.1	641.6	1404.3	884.5	1690.3	813.9	9.706	463.7	540.8	9.899	748.7	433.4	771.6	820.0	621.0	711.9	631.8	631.1	599.7	491.2	6.601	564.7	7.45	739.2	635.2	473.7	834.5	981.2	944.1	6.789	718 1
AL	94668.2	79576.1	99910.1	89135.0	84161.3	84605.2	82664.9	88541.3	79075.2	83816.1	71494.1	95262.2	83625.5	90814.3	93508.8	91285.4	94805.1	89985.3	74752.4	73147.7	88764.8	88845.5	84081.9	97957.8	84935.9	86874.5	83784.3	96802.9	78799.5	82015.5	85392.9	79104.2	C. / 2026	04004.7	83355 /	86451.8	774363	82919.8	91218.3	91327.0	91766.7	83023.0	73080 2
ZR	162.8	178.4	193.1	157.4	185.5	182.0	182.7	197.4	190.0	186.6	170.8	269.2	188.4	160.5	187.9		206.3	155.6	195.9	193.0	141.4	224.9	179.2	146.7	203.2								122.2	7307						99.2	175.6	164.5	1417
NZ	82.2	61.0	151.3	8.69	78.1	9.79	80.0	76.3	43.6	79.1	7.16	70.8	79.1	80.9	77.4	0.79	70.0	66.3	69.5	91.6	54.3	83.9	55.5	123.5	86.0	72.1	79.4	82.8	87.1	93.5	85.7	90.5	0.00	1.60	7.00	87.9	68.2	72.9	79.4	234.6	84.3	74.9	1 44
H	8.69	17.23	21.37		21.35	12.17			26.90	21.29		15.02	22.08	11.68	11.19		12.26		12.95	16.25	25.37		14.07	10.49				_				10.04					15.43			8.32			18 57
۱ TB	7 0.93	1.00	1 0.80	0.94	3 1.11	5 1.21		1.37	9.0 9	1.01	1.24	9 0.75	1.07	1.11	1 0.92	1 0.87	1.21	7 0.62	3 1.07	1.16	0.55	7 0.83	5 0.80	3 0.73							_			1 21			7 0 71	_		1 0.57			84 U G
TA	0.7747	1.2970	2.9704	0.9252	1.8223	1.2726	1.2927	0.9512	1.4296	1.8222	1.0374	1.2459	1.9067	1.0467	1.1691		1.4544	0.9117	1.3893	1.6212	1.4920	1.2767	0.8335	0.7538		0.8894				,		1.4987	0.9233							0.6701	0.7351		6946 L
SR	553.6	292.7	564.9	308.8	660.1	421.1	359.1	470.1	287.7	1266.5	408.4	334.4	638.8	431.4	455.8	554.8	559.8	700.9	8.699	353.4	232.1	397.4	297.7	470.2	315.6	397.4	373.7	595.6	386.3	416.4	295.9	7.44.7	418.7	174.0	517 g	394.4	456.5	339.3	305.9	583.4	422.5	482.7	274 6
SC	66.6	8.05	11.84			8.70		11.99	5.89	9.18		8.34	9.33	1	8.46	l	8.92	8.13		10.57		8.93	6.48	13.20		1							00.0	1						6.97		68.9	6 10
SB	0.5372	0.3540	1.5918	1.3350	0.4586	1.3480	0.4629	0.3561	0.2997	0.4469	1.4405	0.3423	0.4480	0.6244	1.0815	0.3165	1.2129	0.2492	1.9264	0.5551	0.2794	0.5135	0.1884	0.4811	0.3927	0.7511	0.3431	0.4119	0.3722	0.3568	0.3705	0.61/9	0.3343	0.2007	2,6685	1.4004	12208	0.6858	0.2852	0.3044	1.2728	2.0972	0 4497
RB	89.60	116.79	83.07	131.90	172.16	133.33	144.15	96.43	146.03	169.99	136.67	125.17	175.44	126.27	122.32	140.22	132.95	96.40	139.30	142.84	150.73	145.80	104.73	141.03	101.76	129.56	131.23	171.21	109.56	102.55	109.60	156.42	92.70	180.80	107.00	127.07	133.24	178.45	128.00	87.18	124.89	128.25	156.57
Z	0.0	28.4	24.5	21.5	0.0	0.0	32.4	34.6	0.0	0.0	33.8	48.5	32.0	0.0	0.0	41.9	0.0	0.0	0.0	0.0	0.0	0.0	25.1	0.0		0.0		54.2	0.0		0.0	0.0	38.0			_		_	0.0	0.0			0 0
生	6.88	7.76	7.63	6.59	8.53	7.43	8.98	7.72	8.04	8.89	8.02	10.81	6.07	7.38	8.09	7.92	8.15	6.36	8.13	8.10	6.59	10.00	7.76	6.75	8.63	7.58	7.37	8.00	8.81	7.69	9.82	9.02	0.40	10.07	6.71	6.25	7.56	8.69	6.23	5.05	7.34	7.40	7.45
FE	1.7056 38836.4	25807.3	22604.3		31248.0	31682.3		36904.6	20830.2	30659.4	33478.5	32479.4	31053.2	1.5655 37917.9	36527.6	53492.3	36439.3	33117.9	31946.8	35928.6	23814.6	33489.4	22038.5	50029.9							34656.5	36456.1	39889.0				30359 7			25702.5	1.2369 29309.4		18932 6
EU	1.7056	1.4363	1.8348	1.2833	1.1566	1.5021	1.3309	3.85 2.1966	0.9481	1.1853	1.3803	1.3928	1.2911	1.5655	1.3526	1.7694	1.4076	1.4127	1.3575	1.2481	5.71 0.8374	1.3201	1.2890		1.2872	1.6491	1.3820	1.7046	1.3412	1.2793	1.2702	1.2391	2.0021	1 1677	1 2070	1.3186	1 2974	1.0604	1.4161	1.1378	1.2369	1.1901	1 0243
CS	18.84	4.17	4.19			. 70.96	5.54	3.85	3.91	7.14	12.37	5.04	7.16	15.37	6.93		13.99	3.19	33.23	6.04	5.71	2.67	2.74	14.63	4.48			_					4.08			17.66	887			5.73			. V6 6
ANID	BAS162	BAS163	BAS164	BAS165	BAS166	BAS167	BAS168	BAS169	BAS170	BAS171	BAS172	BAS173	BAS174	BAS175	BAS176	BAS177	BAS178	BAS179	BAS180	BAS181	BAS182	BAS183	BAS184	BAS185	BAS186	BAS187	BAS188	BAS189	BAS190	BAS191	BAS192	BAS193	BAS194	BAS195	BAS107	BAS198	BAS199	BAS200	BAS201	BAS202	BAS203	BAS204	RAS205

ANID	macro grp	macro arp Chem2012	CERAMIC TYPE	MATERIAL	SOURCE	STATE	SITE NAME	SITE NO	AS	ΓA	N7	ND	SM	n	YB CE	00	CR
BAS206	Group-C1	Unas.	Mimbres B/W Style II	Pottery			Old Town	LA 001113	2.58	35.62	0.4857	33.05	7.39 2	2.38 3.	3.36 79.85	9.80	49.07
BAS207	Group-B1	Mimbres-04C	Mimbres B/W Style II	Pottery	MURR	MN	Old Town	LA 001113	2.22	45.00 (0.5720	35.82	6.77 3	3.61 3.	3.45 85.18	3 8.23	33.34
BAS208	Group-C1	Mimbres-21	Mimbres B/W Style II	Pottery	MURR	ΝN	Old Town	LA 001113	2.39	37.55 (0.3483	30.46	5.50 1	1.12 2.	2.36 75.80	11.51	78.32
BAS209	Group-C1	Mimbres-21	Mimbres B/W Style II	Pottery	MURR	MN	Old Town	LA 001113	2.67	38.57 (0.3590	31.78	5.46 1	1.26 2.	2.39 76.72	8.44	51.63
BAS210	Group-C2b		Mimbres B/W Style II	Pottery	MURR	NM	Old Town	LA 001113	1.58	38.42				1.98 2.		1	27.03
BAS211	Group-B2	Mimbres-02A	Mimbres B/W Style III	Pottery	MURR	M	Old Town	LA 001113	1.31				7.20 4	4.46 3.		6.91	38.98
BAS212	Group-B2	Mimbres-02A	Mimbres B/W Style III	Pottery	MURR	ΣN	Old Town	LA 001113	1.88	43.00 (0.4809	29.31	6.43 3	3.78 3.	3.42 82.11		40.67
BAS213	Group-B1	Mimbres-04B	Mimbres B/W Style III	Pottery	MURR	ΣN	Old Town	LA 001113	2.77							3 4.57	22.68
BAS214	Group-A	Mimbres-01	Mimbres B/W Style III	Pottery	MURR	NM	Old Town	LA 001113	3.63		0.6164			12.73 2.	2.59 93.63	3 1.41	6.99
BAS215	Group-B	Unas.	Mimbres B/W Style III	Pottery	MURR	Σ	Old Town	LA 001113	1.81		0.6237	38.60		7.94 3.	3.55 102.21	1 5.17	31.05
BAS216	Group-B1	Mimbres-04A	Mimbres B/W Style III	Pottery	MURR	NM	Old Town	LA 001113	2.85	45.98 (0.4779	33.29	6.80 5	5.02 3.	3.17 87.73		19.24
BAS217	Group-B2	Mimbres-08	Mimbres B/W Style III	Pottery	MURR	NM	Old Town	LA 001113	3.19	35.86 (0.4873	20.10	4.00 5	5.87 2.	2.51 68.44	3.58	25.16
BAS218	Group-B1	Mimbres-04A	Mimbres B/W Style III	Pottery	MURR	NM	Old Town	LA 001113	2.50						1		20.23
BAS219	Group-B	Unas.	Mimbres B/W Style III	Pottery	MURR	ΣN	Old Town	LA 001113	2.90		0.4724			3.00 3.		7 10.17	30.68
BAS220	Group-B1	Mimbres-04A	Mimbres B/W Style III	Pottery	MURR	ΣN	Old Town	LA 001113	3.89								21.06
BAS221	Group-A	Mimbres-01	Mimbres B/W Style III	Pottery	MURR	NM	Old Town	LA 001113	1.71				4.36 12			7 1.30	6.35
BAS222	Group-B	Unas.	Mimbres B/W Style III	Pottery	MURR	NM	Old Town	LA 001113	2.34								20.40
BAS223	Group-B1	Mimbres-04C	Mimbres B/W Style III	Pottery	MURR	MN	Old Town	LA 001113	1.44	39.25 (0.3984	26.31			2.47 77.94		29.13
BAS224	Group-B1	Mimbres-04A	Mimbres B/W Style III	Pottery	MURR	MN	Old Town	LA 001113	2.82	50.26	0.5255	40.69	7.55 4	4.96 3.	3.68 105.96	5 4.20	21.85
BAS225	Group-A	Mimbres-01	Mimbres B/W Style III	Pottery	MURR	MN	Old Town	LA 001113	2.98	64.75 (0.7407		4.94 14	14.19 3.	3.42 105.22	2 2.51	7.23
BAS226	Clay		Clay	Clay sample	le (MURR	Σ	Wind Mountain	LA 127260	2.76	55.01	0.4710	42.89	8.16 3	3.65 3.	3.58 105.92	10.18	32.95
BAS227	Clay		Clay	Clay sample	le (MURR	MN	Wind Mountain	LA 127260	3.29	23.66	0.5139	43.21	8.56 4	4.32 3.	3.86 108.14	15.33	34.48
BAS228	Clay		Clay	Clay sampl	sample (MURR	MN	Wind Mountain	LA 127260	1.97	48.25 (42.41	8.40 4	4.23 3.	3.91 109.24	-	27.41
BAS229	Clay		Clay	Clay sample	le (MURR	NM	Wind Mountain	LA 127260	2.33								25.81
BAS230	Clay		Clay	Clay sample	le (MURR	NM	Wind Mountain	LA 127260	2.63		0.7136	38.77			4.91 112.26	5 10.12	29.39
BAS231	Clay		Clay	Clay	MURR	ΣN			2.86	39.11 (34.15
BAS232	Clay		Clay	Clay	MURR	NM			4.24	30.40						4 8.99	31.20
BAS233	Clay		Clay	Clay	MURR	NM			2.79								19.66
BAS234	Clay		Clay	Clay	MURR	NM			3.45			32.79	5.26 2	2.83 2.	2.57 69.34		48.19
BAS235	Clay		Clay	Clay	MURR	M			1.67			24.77		1.55 1.	1.35 65.13	3 7.58	18.38
BAS236	Clay		Clay	Clay	MURR	ΣN			3.70				_				8.17
BAS237	Clay		Clay	Clay	MURR	M			2.86								39.50
BAS238	Clay		Clay	Clay	MURR	ΣZ			8.55							_	46.89
BAS239	Clay		Clay	Clay	MURR	ΣN			2.88					2.73 2.			16.53
BAS240	Clay		Clay	Clay	MURR	ΣN			1.61				6.24 4	4.07 3.	3.97 69.71		4.60
BAS241	Clay		Clay	Clay	MURR	NM			10.50	49.13 (5.19 3.	3.56 105.49	11.28	38.66
BAS242	Clay		Clay	Clay	MURR	NM			4.83						2.46 63.61	10.43	41.54
BAS243	Clay		Clay	Clay	MURR	NM			19.07	39.76	0.5295			_	3.42 84.51	14.19	43.59
BAS244	Clay		Clay	Clay	MURR	NM			12.44	36.61					3.10 77.37		49.25
BAS245	Clay		Clay	Clay	MURR	NM			5.09		0.1865		2.70 1		1.12 28.96		24.07
BAS246	Clay		Clay	Clay	MURR	NM			3.98	38.09 (0.4326	29.56	5.69 3	3.37 3.	3.06 75.75	5 9.28	34.12
BAS247	Clay		Clay	Clay	MURR	ΣN			2.15					_			19.99
BAS248	Clay		Clay	Clay	MURR	ΣN			2.41							7.32	20.46
BAS249	Clay		Clay	Clay	MURR	MN			1.97	42.75 (0.5336	36.88	7.03 4	4.86 3.	3.73 87.17		20.29

>	78.71	56.36	63.37	43.39	97.42	77.89	63.52	58.08	23.88	68.83	42.41	46.65	49.09	58.12	52.79	17.76	36.85	56.26	44.63	17.12	71.61	70.20	52.96	42.56	54.93	48.74	50.74	32.88	65.21	36.27	86.09	59.41	94.39	36.21	18.82	119.76	71.24	119.41	106.29	41.66	44.54	35.76	68.21	37.29
F	3501.1	3136.8	2795.1		~	3007.7	3407.7		1730.7	3261.7	2454.9	2831.8	2588.1	2208.9	3405.0	1965.2	2798.5	3961.0	2719.4	1387.8	4181.7	4023.4	3125.7	3764.1			1875.9	1459.7	2176.1							3672.7 1	3489.9	4616.9 1	3675.2		2306.6	1224.5	2068.9	2463.7
NA				21973.2	16292.1	14516.2		12050.7	11368.4	11870.6	16221.0	9839.8	15313.6	13153.4	18883.3	8144.2	10134.3	16820.3	. 1.97991	15347.4	18264.2	15971.3	18698.7	21462.6	17882.2		14613.9									717.6		2652.3	914.8	. 29167	10383.7	~~		12400.9
MN	706.4 16		1135.4 20	1170.3 21		240.6 14	210.2 13	341.0 12	118.7 11	231.8 11	191.4 16	164.5 9	765.3 15	1125.9 13	292.9 18	1	231.8 10	315.1 16	185.4 16	246.1 15	388.9 18	818.9 15	766.3 18	524.4 21	701.0		552.6 14		- 1		=			598.8	11	178.3		655.9 2	180.8	260.5 2	582.2 10			360.4 12
¥		2		•		27194.9 2	26356.3 2	29126.3	35379.3	30927.5 2	30665.7	30833.1	25725.6	24982.7 11	34187.1	33821.0 1	31458.3 2	24450.8	30835.1	30574.3 2	30897.3	37109.0	32556.3 7				23964.9 E								19506.4 7	29268.7		21558.8 6	28186.8	7167.2 2	26338.7			27234.0
DY		- 1	,	3.279 25		5.492 27		5.737 29	2.858 35	5.520 30	4.717 30	3.033 30	6.186 25	3.633 24	5.081 34		3.520 31	3.747 24	4.875 30	3.336 30	5.759 30	5.855 37	5.543 32	7.012 30	7.416 32		2.361 23			` '	`			3.769 27	6.198 19	6.843 29.	3.959 22	7.222 21	3.915 28	1.716 7	3.977 26	`		5.251 27.
CA	13027.5 6					12608.9 5	14799.2 5	8131.3 5	6081.4 2	10168.8 5	10880.7	6287.5	13024.6 6	15029.4 3	11323.0 5	6414.7 2.	6976.2	12913.7 3	12129.5 4	9262.2	12966.8 5	15289.2 5	14069.3 5	12952.5 7	27896.0		65477.1									13195.2 6	41030.2 3.	8445.0 7	4023.8	282378.2	53854.2	~	_	15285.1 5
BA	•	1								`					711.3 11																_													
									3 280.7	5 574.0	5 716.7	396.1	3 730.2	4 543.9		320.2	3 563.6	5 699.5	9 766.5	9 219.8	7 933.7	1 1038.0	7 700.1				5 721.9	_		_				5 428.4		3 2998.8		5 764.9	7 1675.3		1 537.0			5 484.1
A	90619.1	87708.4	91576.2	88985.9	91239.2	93709.8	90222.7	88514.6	96076.0	95167.5	85707.5	83067.0	87859.3	80532.4	84398.7	93767.0	77696.3	84710.6	81276.9	111592.9	95709.7	97916.1	86897.7	85168.8	86455.1	74696.7	73125.6	65573.3	71196.2	83603.9	67403.0	62163.3	86049.4	79906.6	83292.8	84448.0	71165.1	93022.6	90019.7	24601.1	74693.1	33247.9	81335.4	77993.6
ZR	162.5	178.4	172.9	147.6	141.3	137.3	149.0	180.6	134.2	164.6	162.5	159.2	135.8	117.4	165.0	151.2	130.1	166.4	184.1	149.7	127.1	130.5	136.6	196.8	279.2	170.9	146.1	103.3	186.5	95.8	117.6	280.6	155.8	103.5	84.3	146.8	145.9	156.9	113.3	78.4	144.7	61.1	104.5	155.1
NZ	101.8	92.9	86.2	82.6	76.7	8.09	66.4	48.3	50.8	62.4	59.0	47.4	9.99	81.9	53.7	38.0	46.7	71.9	62.0	52.0	125.7	156.0	125.4	138.6	125.0	61.4	73.5	55.4	70.5	64.4	50.4	55.1	94.6	70.7	63.9	91.2	67.5	134.9	71.5	8.69	6.69	42.8	79.0	69.2
TH	11.42	17.27	9.13	9.37	10.54	19.00	19.56	29.42	50.57	25.97	23.17	30.24	19.08	21.92	22.36	53.21	24.41	17.11	22.68	60.77	19.24	20.08	17.74	17.19	18.61	13.48	11.87	13.58	13.21	11.91	15.15	99.6	13.64	11.84	15.44	15.80	10.52	16.58	13.70	4.76	16.73	8.45	22.31	20.50
TB	1.00	0.86		0.65	0.73	1.08	0.84	1.01	0.42	96.0	0.87	0.50	1.15	0.79	0.84	0.43	0.59	0.65	0.99	0.52	1.06	1.18	1.10	1.23	1.31		0.59		0.70	0.46		0.00	0.82	0.76	1.22	1.20	0.75	1.06	0.93	0.35	0.71	0.49		0.98
TA	1.1609	1.2983	0.6682	0.6146	0.9564	1.3590	1.3417	1.6594	2.5731	1.5695	1.4542	1.5930	1.4022	1.2814	1.4808	3.1765	1.5061	1.2575	1.4335	2.5345	1.1492	1.1978	1.1641	1.1871	1.9109	1.2556	1.0104	0.9671	1.2238	1.0977	1.2675	0.8695	1.1189	1.1997	2.0655	1.0599	0.9281	1.0678	1.0569	0.4789	1.1749	0.5558	1.3993	1.4496
SR	315.5		382.6			305.5	275.4	175.1	70.1	204.5	295.6	126.9	224.8	374.2	255.5	153.3	191.6	265.3	297.2	111.4	438.3	433.3	359.8	481.2			521.3		515.6	994.6				304.4	164.9	127.2	221.3	127.8	159.7		349.7		_	325.1
SC	9.59	8.58	8.36	6.37	8.55	11.93	12.50	7.11	4.26	8.85	7.91	6.52	8.19	9.21	7.15	4.16	5.90	7.72	7.63	5.04	11.08	11.72	9.28	8.69	9.30	5.47	6.25	4.34	7.11	5.29	2.72	9.34	13.51	8.62	6.35	13.37	6.90	13.77	14.32	3.96	7.98	4.11	9.20	6.85
SB	0.6990	0.4080	1.2259	1.1166	0.2943	0.3507	0.3803	0.4247	0.6693	0.6708	0.3961	0.5223	0.2574	0.5266	0.4052	0.5882	0.4738	0.3566	0.4085	0.7960	0.4734	0.5839	0.4302	0.4240	0.5358	0.4487	0.5184	0.3341	0.5233	0.2888	0.2986	1.1977	1.4757	0.3180	0.2423	1.2980	1.3715	2.4351	2.0661	0.5345	0.5226	0.3430	0.4857	0.3716
RB	142.82	145.36	122.79	123.12	98.72	145.59	151.28	167.94	238.41	216.79	157.11	200.16	133.75	176.48	161.17	249.06	176.71	138.15	158.66	262.03	151.50	152.12	149.39	146.30	137.53	114.42	99.25	97.34	119.58	89.18	60.71	110.46	203.35	154.80	165.43	179.31	122.76	162.00	174.83	40.22	155.96	69.75	181.15	197.75
Z	33.7	_				0.0		0.0	0.0	24.3		0.0	0.0	0.0	20.7	0.0	0.0	34.1	0.0	0.0	29.9		24.5	0.0			0.0			0.0				0.0	0.0	0.0	0.0	0.0	0.0	0.0	23.2		21.5	0.0
生	6.81	8.06	6.48	6.91	6.34	7.06	7.18	7.43	6.17	7.18	7.75	8.02	6.81	6.58	7.86	09.9	6.28	7.54	8.24	6.88	6.24	6.19	90.9	9.91	13.37	8.80	98.9	2.00	99.6	4.99	2.11	12.29	6.25	5.45	5.20	5.57	7.02	7.17	5.77	3.83	7.34	2.86	5.46	7.90
FE	33849.5	32188.5	29703.4	25585.4	33630.9	28027.6	28903.6	23619.1	13057.7	20543.2	19930.8	21172.7	26764.2	27892.8	21794.5	10245.1	19590.1	25514.1	20439.4	13743.6	37226.7	39625.9	32235.3	30351.9	35532.4	25290.7	25545.5	16148.3	27307.3	18726.4	12148.1	19114.4	29832.1	25256.5	11251.9	25486.5	30290.2	47614.8	22506.0	19546.3	26927.4	16272.3	8.29 0.8378 27023.8	1.1903 22288.7
EU	1.5771	1.3309	1.2279	1.1316	1.3671	1.4194	1.2872	1.3732	0.5337	1.4575	1.3441	0.6844	1.5505	1.2129	1.3108		0.8359	1.1172	1.5023	1.6245	1.5743	1.5934	1.5447	1.6311	1.5801	1.1779	1.9637			1.0586	0.8648	1.3414		.9649	.8184	1.7301	1.1746	1.6664	1.1319	1.5093	1.0899	0.8117	.8378	.1903
CS	12.19					16.69 1	15.10 1	5.46	21.01 0	12.47	4.95	7.44 0	4.86	18.94	4.54	11.17 0	7.18 0	4.62	4.77	18.23 0.6245	6.17	6.15	5.14		5.24	3.78	4.99 0.9637						29.92	8.79 0.9649	7.67 0.8184	22.55	13.15 1	21.19 1	15.74 1	2.10 0.5093	5.85	3.01 0	8.29 C	8.74
ANID	BAS206	BAS207	BAS208	BAS209	BAS210	BAS211	BAS212	BAS213	BAS214	BAS215	BAS216	BAS217	BAS218	BAS219	BAS220	BAS221	BAS222	BAS223	BAS224	BAS225	BAS226	BAS227	BAS228	BAS229	BAS230	BAS231	BAS232	BAS233	BAS234	BAS235	BAS236	BAS237	BAS238	BAS239	BAS240	BAS241	BAS242	BAS243	BAS244	BAS245	BAS246	BAS247	BAS248	BAS249

ANID	macro arp Chem2012	Chem2012	CERAMIC TYPE	MATERIAL	SOURCE	STATE SITE NAME	SITE NO	AS	ГА	n	QN	SM	Λ	YB CE	00	CR
BAS250	Clay		Clay		MURR			17.14	44.46 0.	0.4432 3		8.17 2.	2.71 3.57	7 95.35	7	34.62
BAS251	Clay		Clay	Clay	MURR	NN		6.50	36.04 0.	0.2801 2	26.07 4.	4.93 2.	2.09 2.10	0 61.55	5 6.48	33.71
BAS252	Clay		Clay	Clay	MURR	NN		2.59	43.32 0.	0.2501 3	31.94 5.	5.20 2.	2.91 1.95	95.88	09.9	24.84
BAS253	Clay		Clay	Clay	MURR	NM		5.21	24.62 0.	0.2302 2	21.28 3.	3.76 2.	2.33 1.71	1 49.28	3 5.58	29.35
BAS254	Clay		Clay	Clay	MURR	NM		1.67	-	0.2022 3	33.26 4.	4.98 2.	2.96 1.65	5 81.35	5 4.47	11.89
BAS255	Clay		Clay	Clay	MURR	NN		2.14	52.81 0.	0.2035 3	34.02 5.	5.15 3.	3.56 1.43	101.83	3 4.02	6.26
BAS256	Clay		Clay	Clay	MURR	NM		3.72	28.49 0.	0.1619 2	20.44 3.	3.01 2.	2.00 0.87	17 56.41	1 2.83	4.71
BAS257	Clay		Clay	Clay	MURR	NN		30.09	10.80 0.	0.1163	8.99	1.69 2.	2.10 0.68	19.58	82.9	17.45
BAS258	Clay		Clay	Clay	MURR	NN		86.6	20.89 0.	0.2486 2	23.07 5.	5.10 1.	1.22 2.04	14 43.96	5 28.26	43.52
BAS259	Clay		Clay	Clay	MURR	NN		20.41		0.4390 3	33.25 7.	7.08 2.			18.77	80.94
BAS260	Clay		Clay	Clay	MURR	NN		6.33	29.90 0.	0.3974 2	28.48 5.	5.47 4.	4.96 2.53	3 59.70	11.67	45.95
BAS261	Clay		Clay	Clay	MURR	NN		9.57	35.64 0.	0.3950 3	32.92 6.	6.25 4.	4.25 2.98	99.69 8	5 12.65	43.16
BAS262	Clay		Clay	Clay	MURR	MN		9.62	36.91	0.4116 3	33.72 6.	6.72 3.	3.37 3.30	13.20	15.65	43.19
BAS263	Clay		Clay	Clay	MURR	MN		4.81	52.46 0.	0.4932 4	42.47	7.55 4.	4.73 3.66	6 103.26	5 8.07	38.53
BAS264	Clay		Clay	Clay	MURR	MN		7.11	28.62 0.	0.3464 2	28.57 6.	6.15 3.	3.18 2.55	5 68.25	5 25.91	62.02
BAS265	Clay		Clay	Clay	MURR	NN		4.15	62.39 0.	0.7336 7	70.75 14.	14.77 5.	5.92 5.90	146.65	9.84	40.77
BAS266	Clay		Clay	Clay	MURR	NM		5.21	34.23 0.	0.4208 2	29.41 6.	6.23 3.	3.58 3.26	13.54	14.11	32.43
BAS267	Clay		Clay	Clay	MURR	NM		10.16	35.65	0.4086 3	31.63 6.	6.33 4.	4.81 2.93	3 70.10	10.69	42.93
BAS268	Clay		Clay	Clay	MURR	MN		7.81	27.41 0.	0.3733 2	25.68 5.	5.19 2.	2.57 2.63	3 54.45	5 8.32	29.34
BAS269	Clay		Clay	Clay	MURR	NM		10.43	28.09	0.3618 2	21.72 4.	4.07 3.	3.48 2.61	1 56.79	9 5.39	17.86
BAS270	Clay		Clay	Clay	MURR	MN		2.78	24.37 0.	0.1863 1	16.59 2.	2.85 1.	1.21 1.42	12 31.36	5 2.51	14.29
BAS271	Clay		Clay	Clay	MURR	NM		3.66	61.16 0.	0.4728 4	45.00 7.	7.36 3.	3.86 3.45	5 92.42	2 4.98	13.43
BAS272	Clay		Clay	Clay	MURR	NM		1.89	15.11 0.	0.2346 1			2.43 1.74		1.27	2.11
BAS273	Clay		Clay	Clay		NN		1.89	46.13 0.	0.4782 3	35.88 6.			110.33		9.19
BAS274	Clay		Clay	Clay	MURR	NM		4.66	41.63 0.	0.2976 3		6.26 2.	2.76 2.38	8 82.26	9.81	23.62
BAS275	Clay		Clay	Clay		NM		10.39					4.98 6.09	100.33	14.29	27.44
BAS276	Clay		Clay	Clay		NM		17.68					4.00 3.34		16.15	37.18
BAS277	Clay		Clay	Clay		NN		25.61	44.81 0.	0.4206 4		8.21 2.			17.11	38.82
BAS278	Clay		Clay	Clay		NM		5.01				5.43 1.	1.36 2.96		0 48.52	196.86
BAS279	Clay		Clay	Clay		NM		0.00	53.59 0.			9.65 1.	1.11 2.62	1	5 10.68	19.50
BAS280	Clay		Clay	Clay		NM		2.53							. 4	91.17
BAS281	Clay		Clay	Clay	R			2.66								33.02
BRE001	Group-B	Unas.	Mimbres B/W Style III	Pottery	TAM	NAN NAN	LA 002465	1.55	48.47 0.			6.78 2.	2.84 3.17			19.33
BRE002	Group-B1	Mimbres-04A		Pottery		NAN NAN	LA 002465	2.08	42.83 0.				3.65 3.01		1 5.95	16.68
BRE003	Group-B1	Mimbres-04C	Mimbres B/W Style I	Pottery			LA 002465	2.25			38.68 6.		2.71 3.32	12 83.62	1	47.58
BRE005	Group-B1	Mimbres-04B	Mimbres Polychrome	Pottery	TAM	NM NAN	LA 002465	3.65					3.61 2.83		4.99	26.09
BRE007	Group-B	Unas.	Mimbres B/W Style III	Pottery	TAM	NAN NAN	LA 002465	2.54					3.81 3.48	1		19.58
BRE008A	Group-B2	Mimbres-08	Mimbres B/W Style III	Pottery	TAM	NM NAN	LA 002465	1.46	32.38 0.	0.4293 2	23.17 3.					20.73
BRE009	Group-B	Unas.	Mimbres B/W Style II	Pottery		NM NAN	LA 002465	3.35	30.68 0.			3.24 3.	3.26 2.03			23.06
BRE010	Group-B2	Mimbres-02A	Mimbres B/W Style II	Pottery	TAM	NM NAN	LA 002465	2.14	44.03 0.				3.19 3.51			36.09
BRE011	Group-A	Mimbres-03	Whiteware	Pottery			LA 008675	1.57					4.38 8.58			11.62
BRE012	Group-A	Mimbres-03	Whiteware	Pottery			LA 008675	3.33					_	1		17.21
BRE013	Group-A	Mimbres-03	Whiteware	Pottery		_	LA 008675	2.81	47.04 1.			10.84 3.				10.33
BRE014	Group-D	El Paso Core	El Paso Polychrome	Pottery	TAM	TX Gobernadora	41EP00321	6.85	49.49 0.	0.4573 4	41.13 7.	7.75 2.	2.43 3.24	4 97.73	3 6.91	31.83

>	107.89	57.04	45.56	58.62	34.97	30.60	24.02	41.33	161.63	124.40	101.34	87.79	101.90	99.86	95.35	112.22	92.98	91.89	75.56	44.46	20.12	48.82	23.14	63.69	59.17	97.90	96.28	79.24	271.92	89.79	122.78	62.00	77.75	41.86	80.39	47.16	49.71	36.47	49.80	65.29	14.80	28.33	23.63	85.10
I					1593.2 3	1122.3 3		912.9 4	_	4677.7 12	_	4572.2 8	3400.2 10	3493.3 9	5411.3 9		3333.6	3949.3 9	3616.5 7	1803.7 4	938.0 2	2279.4 4	463.6 2			2704.0 9	3061.8 9				`					2175.9 4		2577.5 3						3642.5 8
4																				ľ											_													
NA	7595.5	8687.0	14745.0	8572.9	18094.1	12571.2	10631.9	889.3	5505.6	4312.3	779.6	438.0	408.8	418.9	5245.4	558.3	6050.4	1716.4	2853.0	5573.9	2042.6	14569.4	2822.9	11021.8	13107.8	7718.7	6375.4	5448.5	15892.2	24595.4	14019.7	14642.7	17080.0	15844.2	14661.9	9621.0	15996.0	10589.6	12413.1	13540.3	7661.8	8164.0	5872.2	13489.5
MN	757.2	423.9	546.5	271.0	768.9	674.1	383.1	812.2	541.4	1021.6	616.0	556.1	613.0	107.0	707.5	58.8	0.0	589.4	449.6	594.8	140.6	298.2	141.7	876.2	616.9	839.7	964.1	829.4	1327.1	466.2	969.3	570.7	266.8	514.7	443.7	234.1	260.2	172.8	164.6	231.8	553.2	673.9	519.5	437.9
~	38527.0	27603.8	32454.3	16461.3	23141.2	24642.0	19942.9	7520.2	19899.9	18963.1	23945.6	31129.0	36049.3	27704.8	24426.9	36632.6	25779.6	26034.6	18260.3	21795.0	7899.8	26266.7	7662.5	30333.3	30884.3	37101.3	49117.0	48373.6	9.0264	12860.5	19259.8	29830.5	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
Dγ		- 1			2.241	1.920	1.430	1.188	3.668	5.488	4.816	4.665	5.196	5.549	4.403		5.307	5.268	4.283	2.572	2.436	4.997	1.506				5.220		3.996	•		-	4.645	5.438	3.957	4.014	4.540	2.724	1.739	5.008	10.131	14.909	11.631	4.807
CA	34259.2	15834.5	23450.0	129580.6	27454.6	45789.3	151700.9	154283.3	59482.5	38024.6	12941.1	27788.5	22399.1	7141.3	52288.8	5338.0	8158.3	8.0599	16499.9	136343.2	298970.4	13180.2	280138.1	13577.6			22274.7	18707.9	43956.2	28274.6	22267.0	45227.1	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0				0.0
BA	378.4	877.1	970.3	628.4	715.5	567.3	651.8	88.4	502.5	252.9	373.0	255.6	257.1	289.5	506.5	246.4	6.695	405.4	762.1	298.9	190.4	1061.4	174.2	717.9	651.2	447.9	418.8	476.2	455.3	1128.5	595.4	948.8	809.1	896.5	623.9	269.0	930.3	522.8	748.2	785.6	174.5	203.4	112.9	1103.1
AL	_				90831.4	86706.5	63043.0	20510.2	77928.1	78399.0	69149.6	80222.5	85209.3	89356.3	84966.2		79608.2	80488.3	69857.3		26790.1	77627.5 1	27544.0				93154.0			`							80073.3	74688.2		82517.0	75529.9			87625.4 1
ZR							86.5 63	42.6 20	91.8 77												53.4 26																							
Z	223.1 125.5		54.0 137.8	65.7 119.2	58.1 145.0	55.3 119.6		514.5 42	284.3 91	222.7 191.2	72.0 204.1	89.4 147.4	102.3 166.7	68.7 146.2	94.2 150.8	99.6 181.2	74.7 170.9	80.5 181.4	51.4 188.2	66.5 111.2	49.5 53	51.6 166.6	19.7 60.1	67.0 171.6	99.6 152.9	180.5 261.4	206.8 146.2									65.3 179.2		40.9 352.1	50.5 255.6	58.5 202.0	96.2 249.6			78.9 330.3
	7												ĺ																															
TB	1.12 13.71		1	0.51 9.89	0.52 15.37	0.49 15.00	0.29 10.20	0.22 1.82	0.66 2.45	1.05 10.48	0.68 10.25	0.87 12.15	0.88 12.59	0.88 16.41	0.82 6.27	1.68 15.18	0.92 12.60	0.82 13.21	0.74 8.79	0.57 12.11	0.39 4.28	0.90 26.67	0.35 8.75	0.87 19.36	0.75 10.98	1.75 18.85	1.09 13.94	1.04 13.84	0.78 4.22					_		0.67 27.31	0.91 20.85	0.42 25.06	0.33 27.30	0.97 19.10	1.72 35.63			0.84 18.88
	1.2227 1.	.1509 0.			1.3238 0.	1.3312 0.	0.9110 0.	0.1780 0.	0.3262 0.	0.8750 1.	0.8888 0.	1.0123 0.	1.0226 0.	1.2631 0.	0.5585 0.		1.1843 0.	1.0847 0.	0.7694 0.	0.8789 0.	0.3280 0.	1.4646 0.	0.6131 0.	1.3001 0.	1.0250 0.	2.7890 1.	0.9979 1.						-	-+		1.5900 0.	1.4000 0.	1.6800 0.	1.8600 0.		2.2200 1.			2.4100 0.
SR	184.5 1.2	_			470.2 1.3	421.0 1.3	808.4 0.9	73.3 0.1	96.0 0.3	0.0	76.4 0.8	251.2 1.0	259.2 1.0	100.1	258.3 0.5	71.8 1.1	213.8 1.1	127.4 1.0	108.2 0.7	201.5 0.8	153.1 0.3	307.0 1.4	182.4 0.6	265.1 1.3	375.1 1.0		79.0 0.9									0.0 1.5	0.0	0.0 1.6	0.0 1.8		0.0			0.0 2.4
SC	12.65 18		4.80 5		3.42 4	2.70 42		4.51	18.48	18.14	10.49	12.49 25	13.68 25	12.25	14.04 2	. 01.31	10.47 2	11.21	8.73 10	4.34 20	3.12		1.59 18	6.09	7.47	10.14 24	13.64						6.18	6.31	9.50	8.17	7.00	5.48	9.60	11.70	5.51	66.9	4.93	9.58
SB					0.2319	0.2336		3.5759	1.3012 18	1.5593 18	1.7160 10	1.5743 12	1.4459 13	1.5135 12		1.7438 15	1.2972 10	2.7477 11	2.9235	1.4539 4	0.3418	0.4500	0.1092	0.3455 (0.8251 13		3		_							0.5461		`				0.5205
RB					72.94 0	75.90 0		43.51 3	114.36 1	112.98	138.78	173.99	202.03	171.13 1			134.58 1	156.97 2	121.69 2	104.92	36.71 0	133.27 0	29.74 0				222.14 0											194.80 0	196.10					122.60 0
Z			0.0	11.8 8	0.0	15.7	13.4 6	0.0	59.2 11	58.8 11	27.3 13	0.0	0.0	0.0	48.9 12	0.0 25	31.8 13	0.0	35.5 12	10.1	0.0	23.9 13	0.0	0.0		0.0	0.0	39.8 22	0.0							0.0		0.0	0.0	0.0		0.0		0.0
生					2.69	4.92	3.49	0.94	3.54	6.53	7.22	5.86	5.49	5.38	5.10		6.56	6.58	7.39	4.70	1.65	5.75	2.46	6.26	5.19	11.94	4.73					_	6.11	7.66	7.63	00.9	5.73	11.91	7.27	6.47	9.45	10.58	10.09	6.67
Æ	38510.8				15552.9	12545.6			43785.3	58855.9	40073.6	36205.5	34628.5	29325.4	51775.0		33822.8	36945.1	28248.2	16664.2	. 0.8956	20444.9	5961.0	30119.3	27038.0		40095.4			_							20107.8	17716.1 1	21893.6					
EU		_																-		_										_														1.4008 40391.0
	80 1.5893			4.97 0.7557	2.41 1.0531	2.21 1.0694	1.39 0.6797	3.86 0.3662	27 1.4423	9.09 1.5876	41 1.1350		00 1.3164	60 1.3540	9.86 1.5625	26 3.0013	64 1.2713	71 1.1887	35 1.1142	7.59 0.7291	2.84 0.6289	5.81 1.2914	0.97 0.3543	5.77 1.1424			03 1.5940			_					4.76 1.3810	7.15 1.0531	4.73 1.58	6.96 0.7054		82 1.4306	5.46 0.5564	6.27 0.7650		4.35 1.40
	10.80	7.	3	4.	2.	2	1	3.6	15.27	9.6	13.41	23.75	31.00	25.60	9.6	41.26	13.64	19.71	11.35	7.1	2.6	5.5	0.6	.5	5.	ω.	12.03	12.38	2.1	0.	4.0	2.	د	4.	4.	7.			9.	14.82	5.	9	4	4
ANID	BAS250	BAS251	BAS252	BAS253	BAS254	BAS255	BAS256	BAS257	BAS258	BAS259	BAS260	BAS261	BAS262	BAS263	BAS264	BAS265	BAS266	BAS267	BAS268	BAS269	BAS270	BAS271	BAS272	BAS273	BAS274	BAS275	BAS276	BAS277	BAS278	BAS279	BAS280	BAS281	BRE001	BRE002	BRE003	BRE005	BRE007	BRE008A	BRE009	BRE010	BRE011	BRE012	BRE013	BRE014

ANID	macro grp	macro grp Chem2012	CERAMIC TYPE	MATERIAL	SOURCE	STATE	SITE NAME	SITE NO	AS	ΓA	ΓΩ	ND S	SM	U YB	3 CE	00	CR
BRE027	Group-A	Mimbres-10	Mimbres corrugated	Pottery	TAM	ĭ	Gobernadora	41EP00321	5.94	58.80	0.6627	61.37 10.	10.76 3.82	32 4.72	2 111.18	7	33.08
BRE028	Group-B1	Mimbres-05C	Mimbres corrugated	Pottery	TAM	X	Gobernadora	41EP00321	4.34	59.37 0.	0.7560	66.35 11.	11.87 2.07	7 5.93	3 122.89	9.88	28.50
BRE029	Group-B1	Mimbres-05C	Mimbres corrugated	Pottery	TAM	X	Gobernadora	41EP00321	4.83	0 61.79	0.8213	72.26 13.	13.04 2.64	6.41	132.12	10.64	30.44
BRE030	Group-B1	Mimbres-05C	Mimbres corrugated	Pottery	TAM	XX	Gobernadora	41EP00321	5.45	63.74 0.	0.7560	57.90 11.	11.87 3.18	18 5.52	110.33	10.58	31.30
BRE031	Group-B1	Mimbres-05C	Mimbres corrugated	Pottery	TAM	TX	Gobernadora	41EP00321	4.77			1	13.06 2.11	11 6.50	1	11.39	31.18
BRE032A	Group-C2b	Mimbres-47	Mimbres corrugated	Pottery	TAM	TX	Ojasen	41EP00289	2.50	28.88 0.	0.1960		4.05 1.45	1.42	2 53.57	3.82	22.55
BRE033	Group-C2b	Mimbres-47	Mimbres corrugated	Pottery	TAM	XX	Ojasen	41EP00289	4.48	38.88 0.	0.2427	39.01 6.	6.22 1.18	18 2.24	1 77.28	6.81	25.52
BRE034	Group-C2b	Mimbres-47	Mimbres corrugated	Pottery	TAM	TX	Ojasen	41EP00289	4.45	37.31 0.	0.2427	38.23 5.	5.93 1.17	17 1.91	17.68	7.20	25.70
BRE035	Group-C2b	Mimbres-47	Mimbres corrugated	Pottery	TAM	TX	Ojasen	41EP00289	4.61		0.2800		6.34 1.15	15 2.06	5 78.01	6.33	23.12
BRE036	Group-B	Unas.	Mimbres corrugated	Pottery	TAM	XX	Ojasen	41EP00289	09'9	28.58 0.	0.3640	34.07 3.	3.88 3.19	19 2.42	2 60.44	7.32	17.27
BRE037	Group-B1	Mimbres-04A	Mimbres corrugated	Pottery	TAM	MN	NAN	LA 002465	1.64	31.72 0.	0.3360	29.68 4.	4.45 2.66	56 2.26	69.29	5.16	18.16
BRE038	Group-B	Unas.	Mimbres corrugated	Pottery	TAM	MN	NAN	LA 002465	3.51	44.65 0.	0.4107	57.07 6.	6.65 2.10	10 2.95	5 84.84	10.74	35.78
BRE039	Group-B	Unas.	Mimbres corrugated	Pottery	TAM	MN	NAN	LA 002465	3.07	50.81 0.	0.5133	55.28 8.	8.30 3.71	71 3.63	_	2.67	18.41
BRE040A	Group-B	Unas.	Mimbres corrugated	Pottery	TAM	MN	NAN	LA 002465	2.74	50.15 0.	0.4387	43.08 7.	7.13 2.70	3.16	5 97.47	8.11	16.55
BRE041	Group-A	Unas.	Mimbres corrugated	Pottery	TAM	MN	NAN	LA 002465	2.05	43.28 0.	0.2333 10	101.22 7.	7.74 2.06	1.97	7 186.70	99.9	34.63
BRE042	Group-B	Unas.	Mimbres corrugated	Pottery	TAM	MN	NAN	LA 002465	3.97	.0 90.98	0.7280	41.51 15.	15.60 4.55	55 5.11	1 82.58	7.01	26.25
BRE043	Group-B	Unas.	Alma Neckbanded	Pottery	TAM	MN	NAN	LA 002465	94.9	45.43 0.	0.4387	38.64 6.	6.13 3.95	95 2.81	1 81.57	5.61	30.15
BRE044	Group-B	Unas.	Alma Neckbanded	Pottery	TAM	MN	NAN	LA 002465	2.40	48.47 0.	0.5133	38.82 5.	5.64 5.45	15 3.04	1 86.19	6.27	15.74
BRE045	Group-C2b	Mimbres-41	Alma Neckbanded	Pottery	TAM	MN	NAN	LA 002465	3.06	44.43 0.	0.4387 (60.81 6.	6.20 2.46	16 2.98	3 124.65	7.20	24.61
BRE046	Group-B	Unas.	Mimbres corrugated	Pottery	TAM	MN	NAN	LA 002465	2.74	58.36 0.		39.13 8.	8.74 3.04	3.11	1 89.87	2.60	21.17
BRE047	Group-B	Unas.	Mimbres corrugated	Pottery	TAM	MN	NAN	LA 002465	1.99	43.29 0.	0.5413 4	40.30 6.	6.75 4.56	3.62	2 77.39	7.22	25.71
BRE048A	Group-B	Unas.	Mimbres corrugated	Pottery	TAM	MN	NAN	LA 002465	5.54	49.50 0.	0.4760	44.15 6.	6.61 3.68	3.16	9.67 5	7.53	28.79
BRE049	Group-C2b	Mimbres-41	Whiteware	Pottery	TAM	MN	NAN	LA 002465	2.17	42.16 1.	1.1200	44.42 10.	10.06 4.96	90.8 96	5 100.86	4.51	25.45
BRE051	Group-A	Mimbres-03	Whiteware	Pottery	TAM	MN	NAN	LA 002465	2.42	39.16	1.1107		10.50 5.80	30 8.37		1.32	5.98
BRE052	Group-B	Unas.	Mimbres B/W Style II	Pottery	TAM	NM	McSherry	LA 015050	4.99	58.87 0.	0.4760	56.24 8.	8.73 2.99	3.49	1		14.22
BRE053	Group-B	Unas.	Mimbres B/W Style III	Pottery	TAM	MN	McSherry	LA 015050	3.33								36.02
BRE054	Group-C2a	Mimbres-42	Mimbres B/W Style III	Pottery	TAM	MN	McSherry	LA 015050	2.09				5.93 1.52				61.26
BRE 055	Group-C2	Unas.	Mimbres B/W Style III	Pottery	TAM	M	McSherry	LA 015050	0.00	_						1	22.90
BRE056A	Group-B1	Mimbres-04B	Mimbres B/W Style III	Pottery	TAM	ΣN	McSherry	LA 015050	1.38					15 2.95			27.40
BRE057	Group-C1	Unas.	Mimbres B/W Style III	Pottery	TAM	MN	McSherry	LA 015050	3.23	_	0.2987	52.32 8.	8.78 2.89	39 2.37	7 92.91	20.21	33.93
BRE058	Group-A	Mimbres-01	Mimbres B/W Style III	Pottery	TAM	ΣN	McSherry	LA 015050	2.17	_			1				6.23
BRE059	Group-B1	Mimbres-04A	Mimbres B/W Style III	Pottery	TAM	MN	McSherry	LA 015050	2.62								25.96
BRE060	Group-B	Unas.	Mimbres corrugated	Pottery	TAM	ΣN	McSherry	LA 015050	2.53							-	44.09
BRE061	Group-A	Mimbres-10	Mimbres corrugated	Pottery	TAM	ΣN	McSherry	LA 015050	3.05		0.7840 10	100.11 16.	16.63 5.03	3 5.95	5 167.05	7.56	31.04
BRE062	Group-A	Mimbres-10	Mimbres corrugated	Pottery	TAM	NM	McSherry	LA 015050	3.12	82.52 1.	1.1667 10	101.41 17.	17.34 5.41	11 8.58	-	7.04	31.97
BRE063	Group-B1	Mimbres-04A	Alma Neckbanded	Pottery	TAM	₽	McSherry	LA 015050	1.76	43.67 0.	0.4760	47.22 7.	7.15 3.81	3.40) 91.03	8.79	19.39
BRE064A	Group-A	Mimbres-10	Mimbres corrugated	Pottery	TAM	NM	McSherry	LA 015050	2.03			76.20 13.	13.23 16.37	37 4.78	142.61		31.88
BRE065	Group-B	Unas.	Mimbres corrugated	Pottery	TAM	₽	McSherry	LA 015050	4.59	41.82 0.	0.5040	31.65 5.	5.80 7.82	32 3.16	5 85.33	10.51	39.41
BRE067	Group-C2b	Mimbres-47	Mimbres corrugated	Pottery	TAM	NM	NAN	LA 002465	1.60	45.90 0.	0.2613		7.07 2.28	28 2.04		4.30	19.34
BRE068	Group-C2b	Mimbres-47	Mimbres corrugated	Pottery	TAM	NM	NAN	LA 002465	2.02	45.67 0.	0.2800		7.26 2.30	30 1.94			20.56
BRE074	Group-C1	Mimbres-22	Mimbres B/W Style III	Pottery	TAM	NM	West Fork	LA 008675	4.59	43.21 0.	0.3173		5.73 1.18	18 2.17	79.41	5.86	12.49
BRE075	Group-C1	Mimbres-21	Mimbres B/W Style III	Pottery	TAM	MM	West Fork	LA 008675	6.45							_	30.13
BRE076	Group-B2	Mimbres-02A	Mimbres B/W Style III	Pottery	TAM	M	West Fork	LA 008675	0.00	_						5.65	33.35
BRE077	Group-A	Mimbres-03	Whiteware	Pottery	TAM	NM	West Fork	LA 008675	2.43	37.37 1.	1.1480	49.52 8.	8.87 6.21	7.83	3 86.71	2.09	10.99

>	79.71	52.65	53.63	55.10	50.98	47.35	48.04	55.88	50.59	40.78	47.16	72.45	55.69	35.49	53.33	63.53	58.43	36.37	37.35	60.49	55.10	48.33	23.73	18.04	36.37	65.39	93.73	86.37	39.71	69.61	15.98	48.14	60.49	58.63	47.16	58.33	26.67	86.39	55.00	53.92	33.04	67.94	52.16	18.92
F	3778.5	4296.9	4516.3		4930.8	2777.2	2390.8	2666.8	2742.8	2900.7	2791.1	3785.1	2958.6	2501.0	2898.8	2720.1	3031.9		3573.6	2910.4	3276.5	3224.9	1314.9	0.076	2559.8			3098.7	2524.6	3310.1								3725.3	2677.9		1684.4			1623.4
NA	16360.2	~	1.12771		17851.3	21550.3	9.69161		18825.9	15022.4	17026.7	15496.8	11583.2	15580.9	18072.6			11694.5	15801.0	18322.2	16385.2	11547.5	6142.0							` '								13523.1	20993.7		. 12788.8			5417.7
MN		705.2 18	708.6 17		752.1 17	115.3 21	141.5 19	145.8 18	136.8 18	268.2 15	207.9	569.1 15	313.3 11	388.5 15	116.0 18			365.1 11	549.1 15	130.1	430.7 16	549.8 11	610.2 6			668.8 15	` "				1	`		-			168.8 14:	556.2 13	83.5 20	•	743.2 12		-	484.0 5
¥		0.0	0.0		0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0			0.0	0.0		0.0	0.0	9 0.0	0.0		0.0												0.0	0.0	0.0				0.0
DY	8.047	8.143	10.236	7.885	10.217	2.227	3.574	3.326	4.243	2.686	2.494	4.769	6.279	4.205	4.215	9.299	3.823	3.708	5.085	6.375	5.199	3.890	11.115	12.262	5.448	3.928	3.613	3.278	4.310	3.402	2.150	3.919	3.221	9.271	12.683	5.008	8.468	3.813	3.660	3.995	2.934	3.049	5.132	9.720
CA	0.0	0.0	0.0 10.	0.0	0.0 10.	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0		0.0	0.0	0.0	0.0	0.0	0.0	0.0 12.		0.0									1			0.0	0.0	0.0				0.0
BA	955.1	824.2	055.8	916.9	1177.1	872.9	510.5	1512.2	1341.8	285.7	833.4	885.0	692.1	861.5	674.8	477.5	730.0	963.9	1011.3	965.7	658.3	698.7	835.2	178.9	1071.3	681.4	992.8	878.2	705.4	720.9	281.1	840.1	735.3	9.798	725.3	880.0	877.1	690.2	923.4	6.076	8.065	839.3	520.3	141.0
AL	7		_		`		1			_															`						_											_		Ì
	84492.		77373.6		78462.4	86453.3	86448.2	85323.2	88693.0	97877.8		85279.8	84024.0	79217.9	87328.5			80148.6	78680.7		78408.3	76901.4	71099.7															84435.6	84597.8					73978.6
I ZR	262.9	325.5	326.7	338.8	349.8	142.4	142.7	195.6	131.4	211.6	163.1	239.9	189.8	219.2	242.7			124.8	201.9	220.5	212.7	192.6	199.0	198.3	217.4								178.0					213.5	223.8		123.8			162.9
ZN	101.6	97.3	102.7	107.8	102.8	55.4	56.7	59.4	56.4	43.1	55.0	80.3	62.0	53.8	107.3	92.3	52.7	48.1	57.8	70.4	123.5	127.4	9.99	145.7	71.8	70.4	92.9	208.2	50.5	73.4	45.6	51.6	88.3	107.4	76.1	57.8	0.69	81.3	42.2	45.4	87.4	93.4	58.6	198.7
TH	32.62	17.32	17.60	17.65	l	8.53	8.33	8.95	8.54	24.78		15.19	20.88	20.66	52.67			18.65	10.16	18.22	22.93	23.07		33.90	18.17	16.72											43.79	31.47	8.13		9.50			34.56
۲ TB	1.61	1.80	0 2.04	1.58	1.96	0.44	0.74	0.78	0.76	0.47		0.93	1.13	0.89	0 2.03			0.95	1.21	0.99	0.88	06.0	0.89	2.16	1.16	0.86		0.86			_					0.98	1.88	89.0 0	08.0	0.84	0.71	_		1.91
TA	1.9700	2.2100	2.3700	2.1900	2.3500	0.6600	0.6800	0.7500		1.9700		1.4400	1.3500	1.3100	1.9500			1.4200	0.8300	1.3200	1.5000	1.6400	0.8300	2.7900	1.2700											1.3900	1.2200	1.1500	0.6700	0.7200	0.6700	_		2.3500
SR	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
SC	10.55	8.38	9.18	8.89	9.23	2.96	6.52	6.85	6.44	5.95	7.41	8.66	8.73	98.9	13.16	8.41	7.37	6.23	7.36	6.84	7.33	7.69	7.14	4.37	60.6	10.05	14.70	12.36	6.92	8.44	3.87	7.92	8.70	10.64	9.31	7.50	8.62	8.34	6.18	6.35	4.69	7.54	9.83	5.33
SB	1.1520	0.6059	0.6315	0.5973	0.5888	0.6827	0.6315	0.5717	0.4096	0.8619	0.5205	0.4437	2.2613	4.5568	0.5376	1.1093	0.9557	0.2475	0.5973	0.3413	2.2272	1.8773	0.6059	0.7339	0.5291	0.7253	0.0000	1.2800	0.8704	0.5120	0.6059	0.5120	0.6144	1.8005	1.6896	0.4437	0.4608	0.5973	0.4523	0.5717	1.7237	1.8432	0.5717	0.6485
RB	141.20	152.90	127.40	144.40	127.40	80.90	88.00	93.50	90.30	141.60	129.20	126.50	138.00	138.00	245.50	151.20	190.10	118.10	122.00	136.40	160.90	166.80	110.50	296.70	154.30	151.80	88.60	95.60	197.50	156.60	192.10	148.40	230.50	194.70	236.90	125.20	166.00	176.80	106.90	111.70	140.50	134.40	154.90	294.60
Z	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0			0.0	0.0	0.0	0.0	0.0	0.0	0.0		0.0	0.0									0.0		0.0	0.0	0.0				0.0
±	9.19	11.46	11.12	11.58	12.52	5.50	4.53	4.47	3.98	7.37	5.62	8.33	2.87	60.9	9.71	5.88	7.48	5.39	6.55	7.38	7.96	6.17	2.60	9.83	6.63	99.9	6.58	5.89	7.41	5.80	6.13	9.11	5.51	2.77	8.33	69.9	7.70	2.86	5.43	5.39	5.86	99.9	6.94	9.26
FE	39697.8	34302.4	35947.9	36437.4	36804.7	22557.3	28388.7	30215.7	28433.6	27164.0	24354.8	34200.1	30196.1	21781.3	38366.3	22125.1	23796.2	23650.3	30039.3	24360.1	23599.6	24062.2	27560.6	11381.0	22966.8	33546.4	44247.3			29307.3	11780.5	24323.9	30971.0	35525.7		26910.3		29570.6	21652.3	22375.9	20208.0	33136.6	22219.1	12793.1
EU	1.6790	1.6989	1.6989	1.6393	1.7386	0.9836	1.5896		1.5300	0.8047	0.9637	1.4008	1.4803	1.4505	1.6294	1.3015	1.2220	1.3015	2.5732	1.2518	1.3710	1.4505	1.9572	0.5464	1.9274	1.4306	1.6194	1.5697	1.0233	2.0268	0.5564	1.2121	1.1624	1.7188	2.0069	1.3214		1.1624	1.9274	2.0268	1.3313	1.3810	1.0432	0.4769
CS	2.44	5.33	3.84		3.97	3.22	3.37	3.53	3.36	9.48	4.50	4.16	4.87	4.04	14.66			3.41	4.30	3.95		5.54	3.62		4.28													8.45	3.14				22.57	5.44 (
ANID	BRE027	BRE028	BRE029	BRE030	BRE031	BRE032A	BRE033	BRE034	BRE035	BRE036	BRE037	BRE038	BRE039	BRE040A	BRE041	BRE042	BRE043	BRE044	BRE045	BRE046	BRE047	BRE048A	BRE049	BRE051	BRE052	BRE053	BRE054	BRE055	BRE056A	BRE057	BRE058	BRE059	BRE060	BRE061	BRE062	BRE063	BRE064A	BRE065	BRE067	BRE068	BRE074	BRE075	BRE076	BRE077

ANID	macro_grp	macro_grp Chem2012	CERAMIC TYPE	MATERIAL	SOURCE	STATE	SITE_NAME	SITE_NO	AS	Ŋ	21	ND	SM	n	YB	CE CO	CR
BRE078	Group-C1	Mimbres-21	Mimbres B/W Style III	Pottery	TAM	NM	West Fork	LA 008675	4.96	38.35	0.3173	38.04	5.63	1.33 2	2.45 76.45	45 10.08	3 31.30
BRE079	Group-A	Mimbres-03	Mimbres B/W Style III	Pottery	TAM		West Fork	LA 008675	2.83		1.2973	56.46 10	10.50	4.61	8.97 100.68		
BRE080A	Group-A	Mimbres-03	Whiteware	Pottery	TAM	MN	West Fork	LA 008675	1.98	47.22 1	1.1107	54.69 10	10.69	5.30 7	7.44 77.45	45 2.05	5 9.31
BRE081	Group-A	Mimbres-03	Whiteware	Pottery	TAM	MN	West Fork	LA 008675	2.77		1.2787	-	11.10	5.81 9	9.53 110.89	89 2.37	
BRE082	Group-C1	Mimbres-21	Mimbres B/W Style III	Pottery	TAM		West Fork	LA 008675	1.68		0.3640						
BRE083	Group-A	Mimbres-03	Mimbres B/W Style I	Pottery	TAM		West Fork	LA 008675	1.86	42.01		48.70 10	10.21	7.22	8.28 87.32	32 2.19	10.67
BRE084	Group-A	Mimbres-03	Mimbres B/W Style III	Pottery	TAM	MN	West Fork	LA 008675	1.23						_		
BRE085	Group-A	Mimbres-03	Mimbres B/W Style II	Pottery	TAM	MN	West Fork	LA 008675	5.09	49.70 1	1.1387	54.15 1;		5.94	8.74 90.74	74 2.85	5 14.93
BRE086	Group-B1	Mimbres-09	Mimbres B/W Style III	Pottery	TAM	NM	West Fork	LA 008675	0.00	55.50 C	0.5227		10.40	3.67	3.91 118.85	85 2.03	3 15.34
BRE087	Group-B1	Mimbres-05B	Mimbres B/W Style Indeter. Pottery	Pottery	TAM	MN	West Fork	LA 008675	2.91	63.62	0.8587	65.26 1:	12.91	3.68 6	6.53 86.68	69.9 89	9 45.10
BRE088A	Group-B	Unas.	Mimbres B/W Style Indeter. Pottery	Pottery	TAM	MN	West Fork	LA 008675	2.65	48.01	0.2520	29.94	3.97	2.88	1.67 71.90	90 4.28	
BRE089	Group-B	Unas.	Smudged Corrugated	Pottery	TAM	MN	West Fork	LA 008675	4.36	41.57 0	0.6720	37.63	8.87	7.50 4	4.61 92.15	15 7.98	3 47.64
BRE090	Group-B1	Mimbres-05B	Textured (Punctated)	Pottery	TAM	MN	West Fork	LA 008675	5.77	77.10	1.1293	74.84 1	17.30	4.24	8.09 114.61	11.7	1 38.22
BRE091	Group-B	Unas.	Mimbres B/W Style Indeter. Pottery	Pottery	TAM	MN	West Fork	LA 008675	5.10	56.31	0.8587	58.72 13	12.87	4.76 6	6.21 101.89	96.9 68	5 40.73
BRE092	Group-B	Unas.	Mimbres B/W Style Indeter. Pottery	Pottery	TAM	MN	West Fork	LA 008675	3.27	43.90 C	0.5227	44.92	6.03	4.69 3	3.63 80.03	03 7.58	3 31.84
BRE093	Group-A	Mimbres-01	Mimbres B/W Style III	Pottery	TAM	MN	Pueblo Vinegaroon	LA 073824	0.00			39.15	ļ	12.51 3	3.24 89.90		7 7.15
BRE094	Group-A	Mimbres-01	Mimbres B/W Style III	Pottery	TAM	MN	Pueblo Vinegaroon	LA 073824	0.00	37.45	0.3920	22.02	2.88	6.65 2	2.10 51.35	35 3.34	4 9.82
BRE095	Group-B1	Mimbres-04B	Mimbres B/W Style III	Pottery	TAM	MN	Pueblo Vinegaroon	LA 073824	0.00	55.47 0	0.5600	41.75	8.53	7.00	3.67 89.29	29 5.78	3 25.00
BRE096A	Group-B2	Mimbres-02A	Mimbres B/W Style III	Pottery	TAM	MN	Pueblo Vinegaroon	LA 073824	0.00	39.72	0.4573	37.39	6.05	5.69 2	2.93 71.58	58 4.42	2 34.74
BRE097	Group-B1	Mimbres-04A	Mimbres B/W Style III	Pottery	TAM	MN	Pueblo Vinegaroon	LA 073824	2.35	51.02	0.4667	35.02	7.16	4.19 3	3.38 78.73		7
BRE098	Group-A	Mimbres-01	Mimbres B/W Style III	Pottery	TAM	MN	Pueblo Vinegaroon	LA 073824	1.81	82.78	0.7933	33.14	5.04	9.97	4.78 103.54	54 2.32	
BRE099	Group-B1	Mimbres-04A	Mimbres B/W Style III	Pottery	TAM	MN	Pueblo Vinegaroon	LA 073824	2.42	42.24 C	0.4573	39.40	7.35	4.24 3	3.23 109.93	93 7.19	9 24.54
BRE101	Group-A	Unas.	Mimbres corrugated	Pottery	TAM	MN	Pueblo Vinegaroon	LA 073824	2.20		0.4573	32.40		8.48	3.16 77.37	1	41.02
BRE102	Group-B1	Mimbres-04A	Mimbres corrugated	Pottery	TAM	NM	Pueblo Vinegaroon	LA 073824	3.71				7.82				
BRE103	Group-C2	Unas.	Mimbres corrugated	Pottery	TAM	MN	Pueblo Vinegaroon	LA 073824	3.06		0.2800	_			2.32 93.14		
BRE104A	Group-B	Unas.	Mimbres corrugated	Pottery	TAM	MM	Pueblo Vinegaroon	LA 073824	2.13							1	
BRE105	Group-B	Unas.	Alma Neckbanded	Pottery	TAM	M	Pueblo Vinegaroon	LA 073824	3.87								
BRE106	Group-B	Unas.	Mimbres corrugated	Pottery	TAM	MN	Pueblo Vinegaroon	LA 073824	2.57		_						
BRE107	Group-B1	Mimbres-04A	Mimbres corrugated	Pottery	TAM	M	Pueblo Vinegaroon	LA 073824	3.55							56 7.52	
BRE128A	Group-B2	Mimbres-02A*	Mimbres corrugated	Pottery	TAM		Agape Acres	LA 019165	4.32				_				
BRE135	G-dno-D	El Paso Core	El Paso Polychrome	Pottery	TAM		Agape Acres	LA 019165	4.95						_		
BRE13/	Group-D	El Paso Core	El Paso Polychrome	Pottery	I AM		NAN	LA 002465	7.88	_							
BRE139	Group-B	Unas.	Mimbres B/W Style III	Pottery	TAM		NAN	LA 002465	3.40								
BRE141	Clay		Clay	Clay	TAM		NAN	LA 002465	0.00								
BRE142	Clay		Clay	Clay	TAM		NAN	LA 002465	0.00			_					
BRE144A	Clay		Clay	Clay	TAM	MM	NAN	LA 002465	2.29					2.86 2		12 10.89	
BRE145	Clay		Clay	Clay	TAM	NM	West Fork	LA 008675	4.87			_		4.66 3		27 7.16	
BRE146	Clay		Clay	Clay	TAM		West Fork	LA 008675	5.27	43.53 C	0.6347	52.11	9.02	3.44 4	4.59 101.93	93 10.12	2 42.29
BRE148	Clay		Clay	Clay	TAM	M	West Fork	LA 008675	3.87								
BRE149	Clay		Clay	Clay	TAM		West Fork	LA 008675	3.69			46.59		3.19 4			c
BRE150	Clay		Clay	Clay	TAM	NM	NAN	LA 002465	2.62	11.37 0	0.1120	6.79	1.53	1.12 C	0.66 19.47	47 4.34	4 8.76
BRE151	Clay		Clay	Clay	TAM	MN	NAN	LA 002465	1.69						2.18 47.95		
BRE155	Clay		Clay	Clay	TAM		SE side of Taylor Mtn.	Raw Clay Loc	10.10		0.5133	44.52	8.98	2.80 4	4.13 85.99	99 13.35	5 34.23
BRE156	Clay		Clay	Clay	TAM		SE side of Taylor Mtn.	Raw Clay Loc	26.52	40.98	0.4107	40.96	7.83	2.49 3	3.39 88.35	35 15.66	34.46

>	61.96	25.59	21.37	21.18	55.10	20.39	22.25	25.20	30.69	56.47	54.61	61.37	96.19	51.96	48.43	22.25	30.78	50.98	56.47	88.09	11.47	46.47	81.67	55.88	59.90	85.69	60.10	58.53	58.24	70.00	85.20	94.41	46.08	91.37	77.77	70.57	10.4.0	20.70	47.35	30.39	8.43	62.65	10 70
I		1517.0	1443.3	1444.2	2641.1	2044.7	1746.4	1535.6	2829.1		3317.5	3295.0	3427.6	3572.7	2567.6	1688.0	1130.4	2730.6	3097.9	2966.3	1139.7	4112.0	3617.8		3190.3	3548.6				3430.9	7116.9	4834.4	77,77	4/01.1	1402.7	4559.9	0.7070	20020			1492.1	3137.8	
NA		5543.6 1			8043.0 2	7324.5 2	·	7753.6 1	19980.7	13470.2	10961.6	11910.9	11279.8 3	12233.5 3	12109.6 2	13902.7	8676.1 1	10695.2 2	10491.1 3	13223.8 2	17430.7	13128.0 4	15972.2 3											19/85.2 4		186/2.1					751.3	6138.2	
MN	_	626.4 55	550.8 44		1069.2 180	538.2 73	287.6 60	444.7 7.7	218.5 199	492.0 134	320.2 109	614.5 119	541.9 112	578.7 122	524.2 121		240.7 86	391.7 106	195.0 104	550.4 132	495.4 174	369.0 131	593.9 159	534.7 136		`	497.3 12E	`			_			707.3 197		530.2			١,	-		1033.5 61	ı
¥		0.0			0.0		0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0		0.0								0.0		0.0				1		0.0 103	
DY	3.441	367	688	128	4.129	125	9.022	806	7.818	372	2.026	6.509)34	996	4.960	4.100	1.959	5.964	4.320	4.893	3.766	4.521	4.616	5.371	3.746	4.320	4.559	3.804	4.989	3.966	7.426	5.352	2.456	4.502	020	4.212 5.300	0.370	4.471	9 691	0.000	1.787	069.9	000
CA	0.0	0.0 12.367		0.0 13.428	0.0	0.0 11.125	0.0	0.0 11.908	0.0	0.0 10.972	0.0	0.0	0.0 15.034	0.0 11.966	0.0	0.0	0.0	0.0	0.0 4.3	0.0	0.0	0.0 4.5	0.0	0.0		0.0 4.3								0.0		0.0						0.0	200
-	7	7			7	6	2		5	7		_			2																						2 1	0.0			_		
BA	_	134.7			860.2	230.9	121.2	189.5	1138.2	481.7	765.4	534.1	403.9	359.7	522.6		581.0	632.5	622.9	573.5	318.0	788.8	671.6		888.4									6.018	ľ	0.027					414.1	490.9	101
AL	90211.7	77542.5	76440.2	82353.0	83689.6	77676.5	75364.7	81965.9	87382.4	75579.2	89145.1	78763.0	83410.3	79168.8	76645.4	91929.3	98681.2	90849.7	83756.3	86165.9	99306.9	78146.0	88228.1	84141.4	85829.5	87886.8	72319.1	86454.6	85392.7	77594.9	86977.1	707016	/8339.6	7.00028	10070.3	1.929.1	0.14007	4.9714.9 4.3245.4	695597	15055.1	65059.2	79673.6	0.4510.4
ZR			158.8	172.5	173.3	203.2	153.8	171.9	193.9	179.5	149.3	268.8	245.4	264.4	171.7	216.4	146.7	241.6	239.7	184.0	149.8	238.6	227.7	200.5		209.8								220.0		1.657						93.3	000
NZ	91.2	64.2	8.16	54.5	4.36	199.0	0.99	74.4	9.77	75.8	52.8	0.98	89.1	81.9	72.7	43.3	50.3	58.3	49.3	84.6	40.3	51.3	73.4	29.9		76.2	52.4	28.0	64.2	87.0	78.0					71.3		07.0		1		195.7	7 1 7 7
3 TH					1 11.02	2 37.31	3 39.84	3 41.16	15.44	5 20.28		18.57	1 21.92	1 21.44	22.14		3 40.08	1 26.21	9 20.36	7 18.14		20.51	5 58.72	_					_	_				7.1.75		0/10/0					7	9 12.18	400
TA TB	00 0.74	00 2.25	00 1.90	00 2.15	00 0.81	00 2.12	00 1.73	00 2.18	1.37	00 1.95	00 0.43	1.29	00 2.61	1.91	00 0.82	00 0.47	00 0.23	1.01	00 0.79	00 0.87	00 0.55	00 0.90	00 0.65	00 0.80	00 0.80	00 0.62	00 0.83)		_	_	00 0.67		00 0.82			`	00 0.18	00 0.32	00 1.19	700
SR	0.0 0.6400	0.0 2.3000	0.0 2.3300		0.0 0.8700	0.0 2.5100	0.0 2.4000	0.0 1.9600	0.0 1.0600	0.0 1.6900	0.0 1.1400	0.0 1.5000	0.0 1.7000	0.0 1.6700	0.0 1.8900	0.0 2.3300	0.0 2.0500	0.0 1.5100	0.0 1.4700	0.0 1.2700	0.0 2.3200	0.0 1.5400	0.0 0.9800	0.0 1.1200	0.0 0.9100	0.0 1.0800	0.0 1.5000							0.0 0.9900		0.0 1.6900					0.0 0.9900	0.0 0.8400	0 0 1 0000
SC			5.12 () 61.7	5.37 (5.12 (6.91	9.33 (9.31 (92.6	8.05	3.91 (2.67	89.8	10.00	7.54 (7.30 (6.39	8.40 (7 20						12.42 (
SB		0.6229 5.			1.4421 7.	0.7765 5.	0.4864 5.	0.5461 6.		0.5205 9.		_	0.5461 10.84	4.5739 9.	0.4779 8.	0.5205 3.	0.6400 5.	0.5717 8.	0.4437 10.	.7 7669.0	0.6827 3.	0.5632 7.	0.7851 9.	0.5376 8.							_			1 5260 7		0.4096 7.				Ť		1.4165 12.	1 0752 12 02
RB																																											
Z		0.0 266.50		0.0 306.80	0.0 161.90	0.0 331.70	0.0 289.20	0.0 273.50	0.0 139.90	0.0 146.30	0.0 172.60	0.0 122.60	0.0 116.00	0.0 117.40	0.0 137.90	0.0 212.20	0.0 275.30	0.0 148.60	0.0 144.10	0.0 142.00	0.0 203.50	0.0 140.20	0.0 172.40	0.0 105.10		0.0 162.50								0.0 107.90		0.0 134.60					0.0 370.50	0.0 213.60	0.0 215 40
生				10.97	7.62 (12.00 (9.73 (9.20	98.8	8.47 (6.64	7.48	7.41	8.56 (7.15 (5.44 (96.98	7.24 (7.07	6.10	9.88	5.59 (6.51										11.70		10.21						4.11 (1 64 1
丑	31200.3				. 7926.5	13501.9 12		15452.8	16058.2	27317.5		30685.8	29245.0	27492.9	25204.4	11881.4	16683.3	25627.5	. 52027		10761.4	22568.3	34548.3										,	34/82.3 10	_	33364.7 II	,					37473.1	
EN			0.5067 13		1.4306 29				2.2950 16	1.8281 27.	0.7749 27	1.0531 30	1.9969 29	1.3710 27	0.9836 25		0.4173 16	1.3313 25	1.1227 22	1.2816 26396.1	0.6756 10	1.3810 22	1.2916 34	1.3015 30	1.6393 27							_		1.37.10 34		0.0637 23			_			1.5300 37	1 5005 40002 5
CS			4.84 0.5		17.74 1.4	4.93 0.6160	4.70 0.5961	6.05 0.6955	4.06 2.2	6.26 1.8	6.31 0.7	10.10	7.73 1.9	6.20 1.3	4.43 0.9	17.47 0.5	16.55 0.4	6.20 1.3	20.74 1.1	5.41 1.2	17.67 0.6	4.71 1.3	7.87											2.07	3.73	3.30 1.3	7.0 0.7	7.7U 1.4	653 11		30.49 0.3	11.30 1.5	11 00 1 1
ANID)A		BRE082 1	BRE083	BRE084		BRE086	BRE087	BRE088A	BRE089 1	BRE090	BRE091	BRE092		BRE094 1	BRE095	BRE096A 2	BRE097	BRE098 1	BRE099	BRE101			A	_			A				BKE141		BKE144A BDF145					(*)	BRE155 1	111111

ANID	macro_grp	macro_grp Chem2012	CERAMIC TYPE	MATERIAL	SOURCE	STATE	SITE_NAME	SITE_NO	AS	ГА	ΓΩ	ND	SM	Π	YB	CE CO	C CR
BRE157	Clay		Clay	Clay	TAM		SE side of Taylor Mtn.	Raw Clay Loc	9.32	48.32	0.5040	40.56	7.42	1.50	3.87 98.90	90 11.19	9 22.59
BRE158	Group-B1	Mimbres-04B	Mimbres B/W Style III	Pottery	TAM	MN	Old Town	LA 001113	0.00	47.40	0.4480	54.36		5.00	3.29 82.19		
BRE159	Group-B1	Mimbres-04A	Mimbres B/W Style III	Pottery	TAM	MN	Old Town	LA 001113	1.89	45.19	0.4480	34.42	90.9	4.46	3.02 87.65	65 5.73	
BRE160A	Group-B2	Mimbres-02B	Mimbres B/W Style III	Pottery	TAM	NM	Old Town	LA 001113	2.53		0.4947	37.73		4.39	3.33 83.90		
BRE161	Group-B	Unas.	Mimbres B/W Style III	Pottery	TAM	MN	Old Town	LA 001113	4.03		0.3827	33.39					
BRE162	Group-B	Unas.	Mimbres B/W Style III	Pottery	TAM	M	Old Town	LA 001113	3.37		0.3733	27.48	4.26	3.40	2.52 75.80	7	
BRE163	Group-C2b	Mimbres-47	Mimbres corrugated	Pottery	TAM	MN	Old Town	LA 001113	1.61	31.31	0.2240	33.01			1.31 73.24		6 24.45
BRE164	Group-B	Unas.	Mimbres corrugated	Pottery	TAM	MN	Old Town	LA 001113	3.64	30.75	0.9333	34.30	5.58	4.37	6.27 77.65		
BRE165	Group-C2b	Mimbres-47	Mimbres corrugated	Pottery	TAM	MN	Old Town	LA 001113	2.37		0.2520	36.02	2.68	2.43	1.73 80.12		
BRE166	Group-A	Mimbres-10	Mimbres corrugated	Pottery	TAM	NM	Old Town	LA 001113	3.43		0.9147	27.04			6.45 64.71		
BRE167	Group-A	Mimbres-10	Mimbres corrugated	Pottery	TAM	NM	Old Town	LA 001113	4.34	56.22	0.9240	62.77	10.26	3.90	6.76 88.43		6 28.50
BRE169	Group-D	El Paso Core	El Paso Polychrome	Pottery	TAM	ΣN	Old Town	LA 001113	6.12	52.33	0.3547	46.34			2.64 100.06	06 8.89	9 24.54
BRE172	Group-D	El Paso Core	El Paso Polychrome	Pottery	TAM	MN	Old Town	LA 001113	6.24	74.30	0.4947	82.10	11.99	3.54	4.09 122.20	20 6.63	3 23.99
BRE183	Group-B2	Mimbres-08	Mimbres B/W Style III	Pottery	TAM	MN	Rock House	LA 001118	2.53	38.41	0.3920	26.27	3.83	5.04	2.13 64.31	31 4.31	1 19.25
BRE184A	Group-B2	Mimbres-08	Mimbres B/W Style III	Pottery	TAM	ΣN	Rock House	LA 001118	3.16	37.94	0.4200	35.82	4.47			82 3.45	5 23.10
BRE185	Group-B2	Mimbres-02A	Mimbres B/W Style III	Pottery	TAM	MN	Rock House	LA 001118	0.00	37.48	0.4947	29.14	4.68	5.50	2.95 62.63	63 5.23	3 41.87
BRE186	Group-B1	Mimbres-04A	Mimbres B/W Style III	Pottery	TAM	MN	Rock House	LA 001118	0.00	51.72	0.5693	48.54	9.10	5.05	3.90 118.97	97 5.87	7 19.68
BRE187	Group-B	Unas.	Mimbres Corrugated	Pottery	TAM	MN	Rock House	LA 001118	3.40	42.14	0.7933	32.98	6.58	4.18	5.21 103.66		
BRE188	Group-A	Mimbres-10	Mimbres Corrugated	Pottery	TAM	MN	Rock House	LA 001118	3.49	81.80	0.7560	. 18.19	12.88	3.79	5.18 148.84	84 5.38	8 19.04
BRE189	Group-A	Mimbres-10	Mimbres Corrugated	Pottery	TAM	MN	Rock House	LA 001118	3.50	53.60	0.9427	53.82	10.90	7.48	6.37 135.53	53 8.28	8 31.63
BRE190	Group-B	Unas.	Mimbres Corrugated	Pottery	TAM	MN	Rock House	LA 001118	4.10	38.74	0.5880	34.14	7.16	2.17	4.23 80.58	58 7.29	9 21.10
BRE201	Group-D	El Paso-2	El Paso Polychrome	Pottery	TAM	MN	Acequia Seca	LA 015054	7.86		0.4853	42.80		1.92	4.33 102.18	18 14.60	
BRE203	Group-D	El Paso Core	El Paso Polychrome	Pottery	TAM	MN	Acequia Seca	LA 015054	10.80		0.3173	36.20				27 8.15	
BRE204	Group-D	El Paso Core	El Paso Polychrome	Pottery	TAM	MN	Acequia Seca	LA 015054	8.34	38.23	0.3360	35.06	5.29	2.56	2.22 70.98	98 6.45	20.96
BRE205	Group-D	El Paso Core	El Paso Polychrome	Pottery	TAM	MN	Acequia Seca	LA 015054	12.18		0.3920	51.59			1	49 8.53	
BRE206	Group-D	El Paso Core	El Paso Polychrome	Pottery	TAM	MN	Acequia Seca	LA 015054	8.48		0.3547	96.99					
BRE214	Clay		Clay	Clay	TAM	MN	West Fork	LA 008675	3.34	43.21	0.5787	50.26			5.02 90.64		
BRE215	Clay		Clay	Clay	TAM		SE side of Taylor Mtn.	Raw Clay Loc	9.61	47.08	0.4480	58.20			3.38 81.55	55 13.02	2 34.44
BRE216A	Clay		Clay	Clay	TAM		SE side of Taylor Mtn.	Raw Clay Loc	25.72		0.3827	52.00			3.20 83.43		9 36.83
BRE217	Clay		Clay	Clay	TAM		SE side of Taylor Mtn.	Raw Clay Loc	9.02		0.3640	33.83	6.18	1.31	3.44 65.99	1	9 26.64
BRE218	Clay		Clay	Clay	TAM	M	NAN	LA 002465	1.26		0.3547	28.57		4.15			8 1.62
BRE219	Clay		Clay	Clay	TAM	MN	West Fork	LA 008675	4.49	36.07	0.5320	40.98	5.81	4.45	4.93 79.78	78 7.55	
BRE220	Clay		Clay	Clay	TAM	MN	West Fork	LA 008675	5.26		0.6907	59.81					
BRE221	Clay		Clay	Clay	TAM	MN	West Fork	LA 008675	5.46		0.5413	38.19			4.00 74.16	16 6.99	
BRE223	Clay		Clay	Clay	TAM	M	TJ Ranch House		4.46		0.6720	57.28	8.75		5.13 94.82		
BRE224A	Clay		Clay	Clay	TAM	ΣN	NAN	LA 002465	2.77		0.4293	31.42	5.78				
CAP156	Group-C2b		Mimbres B/W Style I	Pottery	MURR	NM	Victorio	LA 088889	2.09		0.3636	27.18	5.32			64 9.55	
CAP157	Group-C2a	Mimbres-49A	Mimbres B/W Style I	Pottery	MURR	ΣN	Victorio	LA 088889	2.28		0.5073	45.78	8.75	2.27	_	69 10.14	4 43.43
CAP158	Group-C2a		Mimbres B/W Style I	Pottery	MURR	MN	Victorio	LA 088889	2.86		0.4704					26 12.16	
CAP159	Group-B1	Mimbres-05B	Mimbres B/W Style I	Pottery	MURR	NM	Victorio	LA 088889	4.51	58.40	0.8795		11.30	3.14	6.32 112.60		2 34.98
CAP160	Group-C2a	Mimbres-49A	Mimbres B/W Style I	Pottery	MURR	M	Victorio	LA 088889	2.61		0.4206	39.24	7.29	2.17		_	
CAP161	Group-C2a	Mimbres-49A	Mimbres B/W Style I	Pottery	MURR	M	Victorio	LA 088889	2.93		0.4567	45.84	7.82	2.73	_		
CAP162	Group-B1	Mimbres-05A	Mimbres B/W Style I	Pottery	MURR	MN	Victorio	LA 088889	3.42		0.5840	47.28	6.39	3.11	3.91 104.21	21 13.19	9 46.97
CAP163	Group-C1	Mimbres-28	Mimbres B/W Style I	Pottery	MURR	MN	Victorio	LA 088889	3.00	28.68	0.2114	25.46	4.65	1.19	1.65 52.97	97 11.74	4 41.2

>	55.20	47.75	54.12	63.82	37.25	64.02	48.53	37.06	51.86	55.39	19.61	106.96	91.96	38.92	42.55	49.61	47.45	47.65	43.33	46.96	58.73	111.08	103.53	95.00	94.41	94.80	64.31	62.35	103.92	81.76	18.53	51.76	26.08	41.67	57.16	73.33	57.22	78.37	63.52	61.54	78.57	90.69	119.38	70.16
F		3166.7	2729.1			3204.3	2573.7	1630.8	3061.7	1996.9	2548.7	5927.5	6506.7	2651.2	2663.5	3536.7	2856.8	2096.6	1680.2	2957.8	2760.7	5366.3 1	6025.8 1		6013.6	5218.8	4295.2			2273.4								3220.4	3758.5	2813.8	4799.3			2661.7
NA		9776.4			8551.1		19315.8	12041.7	19428.6	11046.7	10165.2	16757.3	16545.6		9708.3		15521.7	13283.5	, 2.7859	9485.5	15588.6	11405.3	14540.3	15504.0			13923.1			٠.								15678.0	16145.6		15865.1			15981.7
MN		180.6	1		220.2	833.1 9	116.9 19	178.4 12	90.4 19	229.0 11	175.5 10	١.	618.8 16		178.1		288.7 15	228.2 13	488.3 6	626.2	543.0 15	471.1 11	428.0 14	492.5 15	`	`	643.6 13					`	_		٠ ١			797.2 15	681.7 16	489.6 13	545.3 15	`		580.2 15
¥	l	0.0			0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0		0.0	0.0	l										20926.0	23913.7 (20138.2			22895.8
DY	6.375	4.893	3.890	2.687	2.514	2.686	3.211	6.040	3.240	6.040	10.016	3.775	7.445	2.581	3.154	3.919	6.155	6.250	9.796	9.548	6.203	7.273	3.957	3.517	4.224	4.090	8.697	6.451	5.400	4.043	1.873	5.610	7.178	5.199	7.302			5.784 20	4.557 23	9.194 25	4.107 20			2.019 22
CA	0.0	0.0			0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0		0.0	0.0											15926.0	17221.3		15590.7			17926.3
BA	350.7	621.7	932.0	621.7	769.4	496.8	1262.8	9.807	1191.2	774.9	1149.2	729.1	7.676	537.3	602.9	405.7	831.3	1201.7	930.7	902.4	642.5	670.7	2665	844.6	836.8	1106.1	581.0	441.0	698.2	354.7	391.4	597.4	543.3	298.0	608.7	628.5		875.9	933.3	516.2	804.5	998.5	731.6	983.3
AL	62440.4	85053.2	86373.4	87322.5	68283.7	82102.7	88955.9	80701.7	88672.3	88411.8	7.19616	87052.9	85264.2	71379.1	80208.0	86296.8	84874.0	81881.2	85011.2	75809.6	88343.5	82448.7	93178.2	89301.1	81805.6	81498.4	73014.3	83404.5	88295.8	79142.7	63274.6	64514.8	73213.1	69428.1	63174.8	79742.3	89536.2	93009.4	82793.2	81760.0	95033.1	84041.2	89607.5	95614.8
ZR	115.1	149.4	157.2		191.0	183.3	189.7	135.2	160.9	181.4	128.8	219.2	303.0	167.1	9.761		9.961	152.4	212.2	270.6	211.7	162.0	241.9	228.0	240.1		255.7									288.9		189.1	171.5		193.5		143.0	95.3
Z		52.1	53.7	70.4	47.8		51.1	87.3	43.7	87.5			80.2	33.3	40.9	60.2	61.3	84.1	73.6	0.69	71.2	78.7	64.5	66.4	67.7		77.6				28.6					71.1	65.1	76.4	70.9					57.6
H		23.61		21.81	25.58	19.15	8.33	30.65	11.31	37.71	47.54	25.53	23.65		27.52		19.18	28.67	36.62	33.76		16.97	25.41				19.27									_		12.67					_	5.62
A TB	0.97	0 0.79	0 0.86	0 0.93	0 0.57	0 0.65	0 0.59	0 1.05	0.70	0 1.02	0 1.82	0 0.92	0 1.28	0 0.47	0 0.55	0 0.65	0 1.16	0 1.10	0 1.82	0 1.78	0 1.13	0 1.21	0 0.75	0 0.59	0 0.88	0 0.85	0 1.40									0 0.78	1 0.63	1 1.09	3 0.86	4 1.67	5 0.81	3 0.92		7 0.47
TA	_	1.3800		1.6300	1.6300	1.4900	0.7500	2.0400	0.7200	2.3500	2.5700	3.1000	2.8900	1.6200	1.6500		1.3900	1.8500	1.5200	1.9000	1.8500	1.8300	2.6200	3.0600		2.4000	1.8700									1.4200		1.0131	0.9533	1.9814	1.1135			0.4567
SR	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	427.4	340.5	471.0	496.7	408.2	360.6	334.4	512.0
SC	7.90	6.57	6.78	9.57	4.60	9.19	6.64	8.88	6.44	10.14		68.6	9.73	4.69	6.17	10.73	8.49	8.25	7.41	8.67	6.79	14.06	9.57	9.44			8.17		13.34	9.27								10.95		66.6	11.15		14.56	7.74
SB	0.4523	0.4693	0.4523	1.3056	0.4352	2.9611	0.8107	0.7424	0.5717	0.7168	0.8875	0.9131	0.4352	0.8448	0.9045	0.7083	0.3840	0.6485	0.7424	0.5632	0.9557	0.7680	0.6059	0.6912	0.8021	0.6912	0.7168	2.5173	0.9557	1.8944	1.5957	0.7083	0.8619	0.7253	0.6656	0.4864	0.3656	0.3880	0.4213	0.6305	0.4426	0.3262	0.5002	0.4254
RB	121.00	153.80	150.60	189.50	195.30	205.00	138.70	253.90	133.60	227.90	245.00	101.90	100.30	188.10	178.90	186.20	126.00	246.60	268.40	239.50	139.10	119.70	103.20	98.30	105.10	91.20	188.10	199.90	211.10	138.70	386.10	198.00	192.70	183.40	179.00	135.00	103.90	113.79	113.09	174.07	111.83	109.24	146.40	93.12
Z		0.0		0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0		0.0	0.0									0.0		29.3	0.0	0.0	27.9			37.7
生	3.75	5.13	6.36	2.98	8.06	7.02	6.62	6.53	7.75	7.61	99.9	8.95	10.22	2.96	6.85	99.8	6.64	2.69	99.9	7.53	89.9	8.70	10.30	8.75	99.6	10.54	9.58	4.43	4.96	5.01	3.67	7.78	10.15	7.18	10.03	9.90	5.35	7.09	6.94	8.08	8.37	7.40	19.9	4.07
FE	23693.0	19950.4	24135.5	25741.4	15528.0	28078.1	23743.6	25332.9	24249.5	28483.9	30813.9	49090.6	44228.6	16932.3	20607.3	22185.7	26927.9	24173.3	24793.9	31587.3	37994.2	43800.3	45481.3	41168.8			27756.8	37012.1	39006.1	26683.8	6204.1	21040.6	1.1425 23754.6		25402.0		30943.9	33519.9	34304.9	29536.7	38570.5	30247.1	42746.0	26675.9
EU	1.5002	1.1525	1.3611	1.3114	0.7551	1.0034	1.3611	0.8246	1.5101	0.7054	1.2021	1.4803	2.2354	0.6955	8.19 0.7749		1.6194	0.9438	1.5399	1.3810	1.3710	1.7287	1.2916	1.1127	1.3512		1.2419	1.4207			0.3974	0.8743	1.1425	0.9041	1.1922	1.1922	1.4523	1.9902	1.5554	1.3770	1.6817			1.2122
CS		5.74		47.71	5.93	8.14	3.58	9.75 (3.30	8.96	10.01	3.32	3.34	6.49	8.19		4.79		11.97	, 60.9	4.79	5.29	3.75	3.36	3.45		6.24	10.99	11.16					_				4.33	7.83		4.55	3.08		7.59
ANID	BRE157	BRE158	BRE159	BRE160A	BRE161	BRE162	BRE163	BRE164	BRE165	BRE166	BRE167	BRE169	BRE172	BRE183	BRE184A	BRE185	BRE186	BRE187	BRE188	BRE189	BRE190	BRE201	BRE203	BRE204	BRE205	BRE206	BRE214	BRE215	BRE216A	BRE217	BRE218	BRE219	BRE220	BRE221	BRE223	BRE224A	CAP156	CAP157	CAP158	CAP159	CAP160	CAP161	CAP162	CAP163

ANID	macro_grp	Chem2012	CERAMIC TYPE	MATERIAL	SOURCE	STATE §	SITE_NAME	SITE_NO	AS	ΓA	Π	ND	SM	n	YB CE	E CO	CR
CAP164	Group-B1	Mimbres-04A	Mimbres B/W Style I	Pottery	MURR		Victorio	LA 088889	2.23	33.33 0	0.3790				2.60 61.92	2 5.00	25.41
CAP165	Group-C1	Mimbres-28	Mimbres B/W Style I	Pottery	MURR	M	Victorio	LA 088889	4.36	31.66 0	0.2367	7 68.92	4.90	1.26 1.	1.53 57.63	3 11.62	40.51
CAP166	Group-A	Mimbres-03	Mimbres B/W Style I	Pottery	MURR	NM	Victorio	LA 088889	3.08	39.68	1.3119	37.02	9.14 7	7.28 9.	9.14 92.79	9 1.68	9.47
CAP167	Group-C2a	Mimbres-49A	Mimbres B/W Style I	Pottery	MURR		Victorio	LA 088889	3.87	49.38 0	0.5027	45.88	8.62 2	2.80 3.	3.58 95.79	9.04	40.45
CAP168	Group-B1	Mimbres-04C	Mimbres B/W Style I	Pottery	MURR	MN	Victorio	LA 088889	4.23	43.94 0	0.5185	35.14	6.80 4	4.17 3.	3.52 87.55	5 6.27	30.70
CAP169	Group-C1	Mimbres-28	Mimbres B/W Style I	Pottery	MURR		Victorio	LA 088889	2.91	34.93 0	0.2469	32.14	5.22 C	0.92	1.59 56.70	0 11.74	37.59
CAP170	Group-C2	Unas.	Mimbres B/W Style I	Pottery	MURR		Victorio	LA 088889	4.79	35.33 0	0.5453	32.47	7.06 2	2.98 3.	3.38 69.90	0 13.00	45.88
CAP171	Group-C2	Unas.	Mimbres B/W Style I	Pottery	MURR		Victorio	LA 088889	2.07	37.45 0	0.3797	34.09	6.45	1.57 2.	2.59 77.41	1 15.56	22.24
CAP172	Group-B	Unas.	Mimbres B/W Style I	Pottery	MURR	MN	Victorio	LA 088889	2.09	49.22 0	0.9422	51.07 12	12.00 4	4.33 6.	6.76 108.43	3 9.35	33.23
CAP173	Group-C1	Mimbres-28	Mimbres B/W Style I	Pottery	MURR	MN	Victorio	LA 088889	2.71	31.85 0	0.2328	32.23 E	5.05	1.67	1.65 55.97	7 12.26	44.45
CAP174	Group-B	Unas.	Mimbres B/W Style I	Pottery	MURR	MN	Victorio	LA 088889	4.72	43.71 0	0.4738	34.28	6.65	2.11 3.	3.45 85.88	8 11.84	46.41
CAP175	Group-B2	Mimbres-02A	Mimbres B/W Style III	Pottery	MURR	MN	Kelly Canyon	LA 001125	2.50	51.57 0	0.6916	45.77 8	8.34 4		4.18 92.76	1.61	41.20
CAP176	Group-A	Mimbres-01	Mimbres B/W Style III	Pottery	MURR	MN	Kelly Canyon	LA 001125	1.69	49.64 0	0.4202	19.55	3.97 15	15.63 2.	2.57 75.50	0 2.13	7.39
CAP177	Group-B	Unas.	Mimbres B/W Style III	Pottery	MURR	MN	Kelly Canyon	LA 001125	1.45	47.10 0	0.4274		6.53 3	3.02	2.96 91.59	9 12.40	38.40
CAP178	Group-A	Mimbres-01*	Mimbres B/W Style III	Pottery	MURR	MN	Kelly Canyon	LA 001125	4.06	54.87 0	0.4266	24.28 4	4.41 14	14.44 2.	2.76 92.63	3 3.46	5.91
CAP179	Group-B	Unas.	Mimbres B/W Style III	Pottery	MURR		Kelly Canyon	LA 001125	3.04			28.01	_				32.86
CAP180	Group-A	Mimbres-01	Mimbres B/W Style III	Pottery	MURR	١	Victorio	LA 088889	1.86	63.35 0	0.5442	31.72	5.71 9	9.88	3.56 107.32	2 2.55	6.74
CAP181	Group-A	Mimbres-01	Mimbres B/W Style III	Pottery	MURR	MN	Victorio	LA 088889	2.06	60.39	0.4684	31.64	5.37 11	11.73 3.	3.15 101.52	2 2.40	6.26
CAP182	Group-A	Mimbres-01	Mimbres B/W Style III	Pottery	MURR	MN	Victorio	LA 088889	96.0	60.39 0	0.4781	24.72 4	4.44 11	11.79 2.	2.94 91.34	1.61	3.72
CAP183	Group-A	Mimbres-01	Mimbres B/W Style III	Pottery	MURR	MN	Victorio	LA 088889	3.00	54.43 0	0.4795	24.20 4	4.57	9.70 2.	2.97 85.26	1.77	11.08
CAP184	Group-A	Mimbres-01	Mimbres B/W Style III	Pottery	MURR	NM	Victorio	LA 088889	2.73	53.19 0	0.4404	24.78	4.45 10		2.87 86.75	5 2.39	12.96
CAP185	Group-A	Mimbres-01	Mimbres B/W Style III	Pottery	MURR	MN	Victorio	LA 088889	1.79	0 26.69	0.5944	37.47 6	6.32 10	10.70	4.02 111.91	1 3.19	6.55
CAP186	Group-A	Mimbres-01	Mimbres B/W Style III	Pottery	MURR		Victorio	LA 088889	2.43	61.26 0	0.5162	29.71 E	5.54 10	10.70	1	4 3.08	6.51
CAP187	Group-A	Mimbres-01	Mimbres B/W Style III	Pottery	MURR		Victorio	LA 088889	2.59								96.9
CAP188	Group-B1	Mimbres-04B	Mimbres B/W Style III	Pottery	MURR		Victorio	LA 088889	3.78	43.93 0			6.08		3.29 79.31		19.40
CAP189	Group-B	Unas.	Mimbres B/W Style III	Pottery	MURR		Victorio	LA 088889	2.75					6.84 6.		5 5.30	18.93
CAP190	Group-A	Mimbres-01	Mimbres B/W Style III	Pottery	MURR		Victorio	LA 088889	2.38			24.71 4					14.69
CAP191	Group-B2	Mimbres-02A	Mimbres B/W Style III	Pottery	MURR		Victorio	LA 088889	1.60	47.02 0				_	-		42.51
CAP192	Group-A	Mimbres-01	Mimbres B/W Style III	Pottery	MURR		Victorio	LA 088889	1.59				1		1		6.81
CAP193	Group-B	Unas.	Mimbres B/W Style III	Pottery	MURR		Victorio	LA 088889	1.79								30.28
CAP194	Group-A	Mimbres-01	Mimbres B/W Style III	Pottery	MURR		Victorio	LA 088889	2.24				_		_		6.56
CAPI95	Group-A	Mimbres-01	Mimbres B/W Style III	Pottery	MUKK		Victorio	LA 088889	3.17	_			_				9.12
CAP196	Group-A	Mimbres-01	Mimbres B/W Style III	Pottery	MURR		Victorio	LA 088889	4.74								3.12
CAP197	Group-A	Mimbres-01	Mimbres B/W Style III	Pottery	MURK		Montoya	LA 088891	2.04	_			_				6.83
CAP198	Group-B2	Mimbres-02A	Mimbres B/W Style III	Pottery	MURR		Montoya	LA 088891	1.24								37.14
CAP199	Group-C1	Mimbres-23	Mimbres B/W Style III	Pottery	MURR		Montoya	LA 088891	3.35							_	45.22
CAP200	Group-B1	Mimbres-04B	Mimbres B/W Style III	Pottery	MURR		Montoya	LA 088891	2.46						_		31.70
CAP201	Group-A	Mimbres-01*	Mimbres B/W Style III	Pottery	MURR		Montoya	LA 088891	2.01	54.04 0	0.6526	21.91		10.65 2.	2.84 89.14		7.58
CAP202	Group-B	Unas.	Mimbres B/W Style III	Pottery	MURR		Montoya	LA 088891	2.39	35.67 0	0.4929	24.24	4.88 3		3.02 68.20		37.09
CAP203	Group-A	Mimbres-01	Mimbres B/W Style III	Pottery	MURR		Montoya	LA 088891	2.43		0.7033						6.36
CAP204	Group-A	Mimbres-01	Mimbres B/W Style III	Pottery	MURR	NM	Montoya	LA 088891	2.43	52.05 0	0.6407	19.38	4.22 11	11.55 2.	2.92 81.84	4 2.90	7.69
CDA073	Group-B	Unas.		pottery	MURR	. ,	3-Up	LA150373				41.01					49.12
CDA075	Group-B1	Mimbres-05A		pottery	MURR		3-Up	LA150373							_		75.95
CDA087	Group-B1	Mimbres-05B	Undiff. Brown Ware	pottery	MURR		TJ Ruin	LA54955		44.72 0	0.5256	33.51	7.74 3	3.78 3.	3.94 89.42	2 12.35	41.76

>	63.19	75.55	7.07	82.92	69.10	52.30	119.07	106.03	67.80	70.60	75.93	73.57	27.47	10.09	47.86	54.31	30.25	35.40	15.15	31.97	28.21	28.67	29.77	24.35	48.31	44.27	26.98	74.90	25.92	29.66	28.29	26.75	22.04	24.66	75.02	82.56	48.62	75.35	92.99	20.13	22.17	109.57	101.99	69.05
I	3146.3		1272.4		_	2326.1			4635.6	3420.4	3555.7	3262.3	1606.6	. 9.6901			1983.0	1939.4	1075.3	1704.6	1945.8	1803.1	1905.1		2527.2													3781.4	29967	1242.8	1683.6			4363.0
NA								,			33												·																					
	3 13180.3	5 16321.3		,	_	5 13364.3	8 11861.9	1 13654.7	2 14047.6	8 18987.4	0 15972.	8 12881.9	4 13951.4	2 14214.8	`		4 18148.4	9 12094.8	0 23187.7	2 6618.3	5 10655.1	5 15409.0	6 12964.7	3 16371.2	1 11272.9		2 12115.9			·	_	_		`		0 12783.7	8 13234.1	9 15292.6	8 12420.9		8 15812.4	`		6 13058.6
MM	5 251.3				1 579.7	809.5	1187.8	1321.1	719.2	593.8	793.0	342.8	120.4	1031.2				153.9	190.0	145.2	175.5	272.5	225.6	183.3	310.1				_									1132.9	479.8	184.2	335.8			681.6
×	21993.6	25360.2	48657.4	20910.9	32685.4	26607.0	21803.9	17832.0	21838.0	24312.0	25901.6	27657.8	25804.5	32549.7	29856.5	25712.3	31022.8	35416.1	25695.5	33452.2	32222.4	39256.2	37678.1	33195.1	31983.6	29202.5	38112.7	26319.5	39657.7	27487.4	33062.0	35941.1	34498.4	33875.1	28428.6	30775.6	30357.4	35804.6	27470.7	36792.6	27017.1	31990.2	30373.4	32728.6
DΥ	3.293	2.298	11.405	5.829	4.718	2.645	5.293	3.580	11.150	2.986	4.498	6.155	2.130	2.630	3.966	4.567	3.961	3.500	2.798	3.174	2.611	4.761	3.494	2.304	4.168	8.480	3.340	5.818	4.312	3.568	4.767	2.894	3.231	2.475	6.250	4.016	5.488	6.937	4.559	3.118	3.509	4.899	8.131	5.453
CA	10276.5	22101.5	13535.9	12635.4	14416.4	17439.1	14986.0	21438.3	12131.3	21043.0	12282.0	13998.5	5846.5	6814.9	13289.0	7741.8	6949.2	7517.1	5070.0	6227.6	5934.0	9821.0	8133.7	6119.2	6.9006	13294.6	9253.6	12186.4	8027.9	8199.4	5430.8	6372.2	7250.5	5632.5	12018.1	37782.8	10948.3	10411.5	16031.7	7193.5	7563.0	24543.3	15975.7	23369.2
BA	704.6	9.686	344.4	988.3	1047.5	1079.0	620.9	648.4	721.4	1230.4	176.9	590.7	290.2	349.1	958.4	453.0	437.3	8.959	190.0	253.7	571.8	570.5	584.0	337.3	540.7	692.5	615.3	525.2	558.8	604.8	470.0	544.2	394.1	401.9	523.9	779.0	9.199	803.2	551.6	469.0	359.1	694.7	487.3	495.3
AL	97395.8	85266.1	80412.6	93483.6		92332.5	85555.1	96513.0	86175.2	92355.9	79028.7	87280.9	96502.4	98082.9	90489.6	88561.1	102178.1	103349.6	108141.9	97771.3	101849.4	109835.2	107977.1	91483.6	77328.1	104890.6	95940.5	92498.7	111092.2	92236.8	99995.0	101052.7	101512.6	108713.0	87809.9	77099.5	88334.7	89275.1	89081.7	104441.2	87198.7	83209.0	82605.5	75493.9
ZR	152.8	101.7	170.0	162.9	219.9	125.7	148.3	99.3	240.9	140.6	202.4	188.2	183.8	164.3	196.5		. 9:5/1	181.7	153.2	120.4	. 9.5/1	173.9	171.7	175.5	166.4		155.7	176.6	183.9	184.2					195.9	130.1	161.4	167.5	150.8	149.4	177.5	213.1	208.5	148.0
NZ	74.8	57.2	237.7	_		l I	93.0	85.2	111.4	61.3	99.1	63.5	47.3	62.9		60.7	44.1	56.2	42.6	299	20.7	50.8	45.9	39.1					∞	_	45.7					78.2	9.07	41.6	8.89		38.9			102.2
H	20.84	5.88	35.26	12.38	18.03	5.48	10.78	9.42	16.77	6.07	14.42	19.29	51.08	14.67	50.49	21.52	47.56	46.68	53.03	46.55	45.85	49.08	48.77	42.24	24.95	29.27	42.46	19.91	51.83	30.38	49.14	49.51	54.29	57.95	18.24	13.37	30.25	44.33	19.36	53.24	42.40	19.52	16.60	17.49
TB	0.63	0.58	1.69		0.83	0.55	0.91	0.71	1.98	0.53	0.82	1.05	0.31	0.71	0.44	0.74	69.0	0.64	0.42	0.44	0.40	0.75	0.53	0.33	0.73	1.25	0.49								0.95	0.76	0.88	0.47	89.0	0.49	0.47	0.88	1.31	0.91
TA	1.4961	0.4822	2.4131	0.9453	1.3882	0.4343	0.8797	0.5656	1.5804	0.5359	1.1790	1.4149	2.6418	1.1019	2.6224	1.2785	2.2244	2.1293	2.5360	2.1965	2.4590	2.2540	2.2325	2.4409	1.5216	4.3761	2.3680	1.3874	2.2413	1.6374	2.3028	2.4289	2.3441	2.5642	1.3767	1.0189	1.6912	2.2365	1.4117	2.3269	2.1496	1.2800	1.6007	1.4897
SR	213.7	541.0	63.7	301.8	306.6	454.4	333.6	406.4	128.0	584.3	336.7	289.5	82.6	277.2	117.6	130.6	142.9	125.8	79.8	80.0	7.96	147.1	140.9	107.8	156.7	259.8	158.3	293.5	144.9	191.3	96.3	82.5	155.1	152.8	332.6	645.0	234.7	130.8	388.9	106.0	120.6	447.9	358.7	391.5
SC	9.41	7.62	5.20	11.06	8.60	7.34	13.10	14.12	18.06	7.93	9.22	12.72	4.14	8.59	4.16	9.07	4.44	4.70	3.90	5.12	4.97	4.32	4.24	3.50	6.26	9.92	5.58	12.51	4.68	8.39	4.70	4.93	3.79	5.28	11.09	10.55	8.23	3.87	8.76	4.55	3.67	11.77	13.15	9.93
SB	0.4023	0.4850	0.8067	0.3751	0.3963	0.4805	0.8479	0.3400	0.5436	0.6543	0.5592	0.4484	0.7141	0.2392	0.8067	0.4199	0.5945	0.5637	0.3927	0.8605	0.5719	0.6054	0.8690	0.5796	0.4313	0.4895	0.4129	0.4066	0.5637	0.6038	0.7429	0.7544	0.6545	0.6377	0.3856	0.7460	0.6971	0.7040	0.5515	0.8117	0.7259	0.5417	0.7373	0.5357
RB	136.25	113.28	274.63	112.23	129.66	129.00	124.55	100.90	159.27	119.79	123.45	141.51	223.63	120.37	218.74	175.62	193.30	192.75	229.11	243.76	234.08	193.20	202.18	207.43	171.41	224.48	220.45	146.56	218.50	176.22	194.63	232.62	181.70	219.24	137.78	162.69	181.18	177.28	169.01	236.77	171.72	132.83	131.78	154.47
Z	0.0	40.6	0.0			45.5	0.0	38.6	0.0	0.0	299	51.0	0.0	54.5			0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0														0.0	0.0	0.0	0.0		-	
士	69.9	4.26	10.00	6.77	9.15	4.45	6.36	5.04	9.64	4.51	8.12	7.13	6.41	9:22	19.9	6.24	7.45	99.9	6.02	5.85	7.26	7.37	6.51	6.57	7.11	69.6	7.47	7.16	7.09	7.29	8.12			8.31	7.20	5.41	6.72	6.62	17.9	2.99	6.83	8.56	8.84	7.10
FE	31059.0	27344.4			27436.2	26320.8	42069.9		49358.0	28827.7	32833.2	27999.2	12150.5	29103.8	12217.1		11575.0	10165.9	8981.5	13775.3	14811.7	10923.2	92626	10498.4		22381.8			11161.9			14527.2						11740.3	27844.1	10508.1	11293.0	39500.0		30129.7
EU	0.8880	1.3442	0.4774	1.9945	1.3362	1.3785	1.6203	1.5861	2.0410	1.3103	1.4670	1.6157	0.4011	1.4087	0.5397	1.1571	0.8518	0.7673	0.5595	0.5444	0.5186	0.9795	15.21 0.7108	0.3859	1.0251	1.0061	0.6368	1.4763	0.8463	0.8721	0.8494	0.5249	0.4858	0.5340	1.4574	1.3043	1.2453	0.5997	1.0062	0.5509	0.5706	1.4747	1.6239	1.3599
CS	6.62		5.35		4.90	21.66		3.34	67.6	20.42		17.03	22.95	5.34	13.30	8.15	14.33	_	16.71	21.78 0.5444	15.62 0.5186	10.85 0.9795	15.21	13.39	2.77	9.21					16.67	24.39 0.5249	11.75 0.4858			10.64	8.30	12.31	77.7	16.96	11.66	5.75	6.51	7.48
ANID	CAP164	CAP165	CAP166	CAP167	CAP168	CAP169	CAP170	CAP171	CAP172	CAP173	CAP174	CAP175	CAP176	CAP177	CAP178	CAP179	CAP180	CAP181	CAP182	CAP183	CAP184	CAP185	CAP186	CAP187	CAP188	CAP189	CAP190	CAP191	CAP192	CAP193	CAP194	CAP195	CAP196	CAP197	CAP198	CAP199	CAP200	CAP201	CAP202	CAP203	CAP204	CDA073	CDA075	CDA087

ANID	macro_grp	macro_grp Chem2012	CERAMIC TYPE	MATERIAL	SOURCE STATE	TE SITE_NAME	SITE_NO	AS	LA	J.	ND SM	۱ (۱	J YB	CE	00	CR
CDA088	Group-B1	Mimbres-05B		pottery	MURR	TJ Ruin	LA54955	3	35.56 0.8450	50 38.38	38 10.08	8 4.85	6.33		12.25	49.23
CDA089	Group-B1	Mimbres-05B	Undiff. Brown Ware	pottery	MURR	TJ Ruin	LA54955	(C)	36.19 0.7759	59 32.78	78 8.48	8 8.24	5.48	82.41	9.30	41.30
CDA090	Group-B1	Mimbres-05B	Undiff. Brown Ware	pottery	MURR	TJ Ruin	LA54955	ω	88.80 1.4507	07 83.85	85 19.75	5 8.59	10.25	136.06	8.08	49.42
CDA091	Group-B1	Mimbres-05B	Undiff. Brown Ware	pottery	MURR	TJ Ruin	LA54955	7	75.03 0.9076	76 67.83	83 14.66	6 4.87	0.70	118.05	7.67	47.93
CDA092	Group-B1	Mimbres-05B		pottery	MURR	TJ Ruin	LA54955	5					6.34		8.52	40.50
CDA093	Group-B1	Mimbres-05B	Undiff. Brown Ware	pottery	MURR	TJ Ruin	LA54955	6	60.28 0.8636	36 59.02	02 12.40	0 3.84		118.67	9.01	41.51
CDA094	Group-B1	Mimbres-05B	Undiff. Brown Ware	pottery	MURR	TJ Ruin	LA54955	9	66.87 1.1112	12 66.83	83 16.08	8 5.40	8.26	108.42	8.29	42.20
CDA095	Group-B1	Mimbres-05B	Undiff. Brown Ware	pottery	MURR	TJ Ruin	LA54955	4	43.03 0.4210				3.02		9.46	31.81
CDA096	Group-B1	Mimbres-05B	Undiff. Brown Ware	pottery	MURR	TJ Ruin	LA54955				27 8.73	3 4.34			_	45.39
CDA186	Group-B1	Mimbres-05A	Undiff. Red Ware	pottery	MURR	Dutch Ruin	NM Y:5:1 (ASM); LA	w	45.13 0.5187	87 37.31		3 3.17	3.95	84.93		57.51
CDA189	Group-B1	Mimbres-05A	Undiff. Brown Ware	pottery	MURR	Dutch Ruin	NM Y:5:1 (ASM); LA	w	43.84 0.4237	37 37.20	20 7.02	2 2.68	3.81	84.96	13.59	75.85
CDA190	Group-B1	Mimbres-05A	Undiff. Brown Ware	pottery	MURR	Dutch Ruin	NM Y:5:1 (ASM); LA8		47.02 0.5777	77 39.08	08 8.27	7 3.44	4.81	92.04	10.87	59.31
CDA191	Group-B1	Mimbres-05A	Undiff. Brown Ware	pottery	MURR	Dutch Ruin	NM Y:5:1 (ASM);			43 39.12		1 3.05	4.99		11.83	62.66
CDA192	Group-B1	Mimbres-05A	Undiff. Brown Ware	pottery	MURR	Dutch Ruin	NM Y:5:1 (ASM); LA8		46.34 0.7129	29 41.23			1 5.67	98.11	11.06	72.94
CDA194	Group-B1	Mimbres-05A	Undiff. Red Ware	pottery	MURR	Dutch Ruin	NM Y:5:1 (ASM); LA8		43.59 0.5583	83 38.65	65 7.89		5 4.67	84.51	13.32	73.82
CDA195	Group A	Mimbres-10	Undiff. Brown Ware	pottery	MURR	Dutch Ruin	NM Y:5:1 (ASM); LA			37 58.60	60 14.60		11.30	134.20	4.15	31.94
CDA292	Group-B1	Mimbres-05A	Undiff. Red Ware	pottery	MURR	Black Mountain	LA49	4							15.54	66.53
CDA297	Group-B1	Mimbres-05A	Undiff. Brown Ware	pottery	MURR	Spear Ranch	AZ CC:1:11 (/	2	52.17 0.6840		69.8 89	9 2.53	3 5.22	101.80	9.18	46.37
CDA312	Group-B1	Mimbres-05A	Undiff. Brown Ware	pottery	MURR	Spear Ranch	AZ CC:1:11 (/	Z.	57.13 0.7485	85 45.21	21 9.13	3 2.92	5.66	104.65	10.91	53.22
CDA316	Group-B1	Mimbres-05A	Undiff. Brown Ware	pottery	MURR	Spear Ranch	AZ CC:1:11 (4	J.			30 8.76		5.74	98.08	10.65	51.46
CDA346			Clay	clay	MURR	n/a	n/a	ω	31.82 0.4631	31 27.59	59 5.71	1 2.97	3.47	65.03	14.03	32.41
CDA347			Clay	clay	MURR	n/a	n/a	3	39.79 0.4706	06 32.39	39 6.82	2 3.29	3.28	81.73	15.64	34.07
CDA359	Group-B1	Mimbres-05A	Undiff. Red Ware	pottery	MURR	Kuykendall	AZ FF:2:2 (ASM)		61.83 0.6627	27 52.46	46 10.30		9 5.61	121.13	9.40	79.83
CDA383	Group-B1	Mimbres-05A	Undiff. Brown Ware	pottery	MURR	Ormand Village	LA5793	מ					4.07		13.58	77.87
CDA384	Group-B1	Mimbres-05A	Undiff. Brown Ware	pottery	MURR	Ormand Village	LA5793	4					3 4.73		14.03	75.99
CDA403	Group-B1	Mimbres-05A	Undiff. Brown Ware	pottery	MURR	Ormand Village	LA5793		-							84.43
CDA414	Group-B1	Mimbres-05A	Undiff. Red Ware	pottery	MURR	Dutch Ruin	NM Y:5:1 (ASM); LA	w								65.72
CDA433	Group-B1	Mimbres-05A	Undiff. Red Ware	pottery	MURR	Dinwiddie	LA 106003; NM S:14									55.06
CDA434	Group-B1	Mimbres-05A	Undiff. Red Ware	pottery	MURR	Dinwiddie	LA 106003; NM S:14		46.18 0.4701			2 2.59	3.63			65.63
CDA435	Group-B1	Mimbres-05A	Undiff. Red Ware	pottery	MURR	Dinwiddie	LA 106003; NM S:14		49.18 0.5540	40 45.89	89 10.75	5 3.16	5 4.67	95.82	12.23	86.45
CDA436	Group-B1	Mimbres-05A	Undiff. Brown Ware	pottery	MURR	Dinwiddie	LA 106003; NM S:14								12.37	55.43
CDA437	Group-B1	Mimbres-05A	Undiff. Brown Ware	pottery	MURR	Dinwiddie	⋝	S:14 4			_			_	12.98	86.76
CDA489	Group-B1	Mimbres-05A	Belford Plain	pottery	MURR	Spear Ranch	AZ CC:1:11 (/	ч)							10.73	53.76
CDA499	Group-B1	Mimbres-05A	Belford Plain	pottery	MURR	Krider Kiva	AZ CC:1:43(A	4							9.83	52.33
CDA500	Group-B1	Mimbres-05A	Belford Plain	pottery	MURR	Krider Kiva			52.01 0.5780		83 9.24		4.31	101.32	10.83	48.58
DJT001	Group-C1	Mimbres-21	Mimbres B/W Style III	Pottery		Powers Ranch	_	1.85 3							9.28	48.26
DJT002	Group-B	Unas.	Mimbres B/W Style III	Pottery	MURR AZ	Powers Ranch		5.75 5	57.53 0.7597		62 10.86	6 4.25	4.96		11.90	27.15
DJT003	Group-B1	Mimbres-05A	Mimbres B/W Style III	Pottery		Powers Ranch	,	3.46 5	54.85 0.6379	79 43.79		2 3.14	4.21	100.54	13.50	51.91
DJT004	Group-B1	Mimbres-05A	Mimbres B/W Style III	Pottery		Powers Ranch		3.49 4	44.28 0.6341		98 8.50	0 3.19	4.19	77.77	10.04	54.19
DJT005	Group-C1	Mimbres-21	Mimbres B/W Style III	Pottery	MURR AZ	Powers Ranch	3	2.74 3	39.21 0.3556	56 31.55		2 1.46	5 2.28		9.96	59.51
DJT007	Group-C1	Mimbres-21	Mimbres B/W Style III	Pottery	MURR AZ	Powers Ranch		2.29 3	37.14 0.3361		74 5.51	1.15	5 2.12		12.19	68.16
DJT008	Group-B	Unas.	Mimbres B/W Style III	Pottery		Powers Ranch					_			145.67		23.91
DJT009	Group-C2	Unas.	Mimbres B/W Style III	Pottery	MURR AZ	Powers Ranch										37.00
DJT010	Group-C1	Mimbres-21	Mimbres B/W Style III	Pottery	MURR AZ	Powers Ranch	AZ CC:3:46 (/ 3	3.26 4	40.36 0.3729	29 30.72	72 5.87	7 1.02	2.69	81.33	10.98	49.76

>	54.46	49.02	66.54	64.20	50.83	44.80	56.80	64.53	53.24	88.72	101.12	91.26	95.68	116.80	94.03	60.77	80.76	78.54	80.30	89.19	40.02	76.04	83.42	91.52	96.36	127.80	93.28	79.55	106.68	135.98	87.67	98.81	80.10	93.69	84.82	53.35	91.11	75.26	90.82	61.92	54.49	66.84	89.10	67.64
F	3809.6	4500.5	4066.6	4017.5	4376.7	4717.3	3859.0	4127.4	4729.8	4134.7	4859.9	5057.2	5224.4		5297.6	3651.8	5927.3	4839.5	4773.2	3872.9	2304.1	3529.1	3976.7	5137.9			5599.6				4568.9	5436.8	4274.3	4401.1	5200.0	2454.1	4624.2	5593.8	4572.0	2198.7	3838.2	3735.6	5087.8	3306.1
NA		13069.0	11272.4	13902.0			12994.5	17244.9		11728.5	15624.9	14166.8	17305.0	15994.7				12360.6	12788.6	12089.0	14025.8	10425.7	11073.6	13727.5		4									13253.8	19739.7	14262.8	13975.0		17244.4				18501.5
MN	692.0 12:	677.4 13	529.7 11.	494.3 13	1	828.7 12	626.5 12	444.8 17.		514.6 11	700.3 15	669.7 14	734.7 17.	784.1 15	,	`	.	530.5 12	652.7 12	544.0 12	1330.1 14	1032.0 10	371.3 11	645.7 13	_	552.8	•	'	`	_	_			•	682.7 13.	1024.4 19	836.0 14.	947.5 13	`		2			970.9 18
¥	29766.4 6	33106.8 6	25932.0 5	31506.7 4			26760.0 6	31190.9 4		34804.5 5	39366.4 7	32987.3 6	33557.6 7	33578.2 7	_			32339.3 5	28291.0 6	34484.3 5	25295.4 13	25290.5 10	29040.9 3	36203.0 6					33637.0 7	_					28424.2 6	28753.5 10	29466.6 8	30314.8 9	29934.0 4		1			26578.4 9
DY	8.870 297	7.104 331	5.365 259	10.170 315			13.314 267	4.876 311	7.070 299	6.729 348	5.876 393	7.017 329	7.253 335	7.723 335	- 1			5.526 323	7.729 282	7.398 344	3.566 252	4.735 252	7.408 290												6.802 284	3.909 287	8.677 294	7.482 303	7.190 299	4.041 307			- 1	4.262 265
CA		13110.0 7.	12251.1 15.	1			12167.9 13.			11039.0 6.	12773.2 5.	10458.3 7.	13591.7 7.	10277.9 7.		1		12459.8 5.		12804.5 7.	22196.4 3.	71172.3 4.	11680.6 7.	16661.3 7.					15269.5 5.			_			_	10503.1 3.	8266.6	12282.2 7.		15690.5 4.		1		
Ą				.6 15319.7	`	`	`	.9 18953.1	`			Ì	`		1				.7 13440.7	_						1					•				•	Ì					l			.3 11432.1
L BA	_	8 407.4	3 441.0	2 420.6			405.0	0 721.9		3 624.5	6 763.9	1 643.4	0 684.9	5 617.4				1 644.4	4 490.7	4 669.2	5 423.8	3 429.7	8 582.4						6 751.5		_				3 800.9	1 955.7	9 690.1	0 661.5					_	9 832.3
Al	85218.7	74871.8	91565.3	83520.2	63115.2	79882.8	88457.6	89821.0	77122.5	91276.3	80469.6	76471.1	80735.0	80800.5	84772.8	92107.8	78057.4	82806.1	82995.4	88375.4	67535.5	76382.3	89974.8	87659.6	87443.3	100097.0	89110.7	82859.0	89233.6	83132.6	82920.7	75658.1	89007.5	84521.0	75868.3	89290.1	102746.9	84529.0	95546.7	91116.9	92737.3	105869.8	97504.7	99167.9
ZR	182.8	203.8	221.4	194.6			190.1	208.4	176.2	162.4	256.0	259.3	253.0	319.3				161.8	181.6	210.6	160.8	165.3	208.7	209.2											194.1	1.6/1	272.0	246.1		176.3	171.8			176.6
NZ	101.1	119.2			93.5		103.8	97.1	112.8	104.3	92.8	103.2	9.86	101.8	1	80.3	—	79.3	6.06	91.4	168.3	90.2	75.8	114.1	113.1				134.8			_			78.7	74.8	82.8	74.5	113.3	81.2	99.1	94.6	67.1	84.6
3 TH		20.20	7 26.56	22.16			1 23.05	17.91	18.84	16.32	16.27	17.24	15.96	16.60			15.00	14.97	16.46	5 16.22	7 15.62	13.90	17.71	5 14.33					_	_			16.97		15.85	9.72	18.30	14.30	_		8.89		12	9.87
TA TB	33 1.59	1.12	07 2.57	1.82	.8849 1.62	`	1.94	.3765 0.70	1.08	1.22	1.23	93 1.59	1.39	25 1.40		54 2.83	1.1	11.2	71 1.31	1.26	25 0.87	41 0.94	76 1.38	33 1.16	,	`	•	_	114 1.27	05 1.57	`	1.59	1.2	•	1.12	126 0.80	1.55	1.36	1.2716 1.29	000 0.88	10 0.68			93 0.83
SR	108.8 2.0433	135.0 1.9300	158.4 1.9507	220.6 1.8497			188.0 1.7624	400.3 1.37	453.9 1.5442	243.7 1.2927	284.9 1.1851	187.6 1.6493	330.3 1.5729	248.4 1.6725	299.7 1.2852			196.2 1.0017	242.5 1.2771	215.0 1.1803	358.6 1.7625	444.7 1.5841	102.9 1.0476	335.9 1.2433	_	_		`			_		_	_	1.1 1.1012	362.3 0.7826	218.5 1.0760	369.2 1.1285	231.8 1.27	314.1 0.7000	360.0 0.6710	-	_	310.6 0.7093
SC		9.46 13	12.61 15	10.75 22			10.29 18	8.92 40	10.83 45:	12.99 24	12.62 28	11.11	10.67 33	10.47 24				14.54 19	15.34 24.	13.86 21	7.71 35	10.82 44	16.03 10	13.18 33					13.07 35						13.88 261.1		13.22 21	11.42 36	12.43 23	7.36 31.	8.64 36			8.62 31
SB	1	0.5797 9	0.6846 12				0.5259 10	0.4619 8		0.6289 12	0.7173 12	0.6537 11	0.6037 10		1			0.3159 14	0.4675 15	0.5996 13	1.0418 7	1.0912 10	0.5576 16	0.7279 13									_		0.2811 13	1.2107 7	0.9581 13	0.5901 11	,					1.4094 8
RB			138.05 0.6							138.19 0.6		142.45 0.6				_																												
Z	136	137.59	138	131.01	158	151	136.81	112.26	144.50	138	142.00	142	142.97	154.61	148.25	259.77	118	113.03	112.37	135.24	131.12	144.62	121.22	127.04	150.01	127.44	145.43	141.27	131	143.12	131	129.67	149.29	113.78	106.65	28.0 128.11	46.6 156.31	34.4 128.46	20.1 140.19	36.8 128.20			27.1 130.45	43.8 126.48
生	8.59	7.75	8.91	90.8	9.20	9.85	8.22	8.46	7.09	7.51	9.51	10.15	10.99	13.41	10.62	7.95	7.67	6.31	7.97	8.54	6.14	6.94	00.6	8.19	8.60	7.76	10.88	00.6	8.36	9.55	7.97	9.32	9.41	9.48	7.63		9.51 4	8.53 3.	8.38 2	6.61 3				6.51 4.
Æ		26437.3	31855.4				28692.4	33150.7	32140.4	42666.8	44514.6	37863.6 10	39390.7 10	42633.0 13	1				49366.4	41926.0	31449.6	31486.4	46059.5		_	_	_								43769.4	27642.4	38843.1	30584.1	31265.8	26188.7		-		31338.5
EU		0.8704 26	2.5267 318				1.9945 286	1.4080 33			1.3933 44	1.3670 378	1.4101 393	1.3902 420				1.6097 422	1.7262 493	1.6109 419	0.9292 31	1.1775 314	1.2828 460	1.7439 460								-+			1.6690 43	1.1976 27	1.8709 388	1.5880 30						1.2977 313
CS	4.80 1.0	6.50 0.8	11.53 2.5				8.16 1.9	8.06 1.4	7.69 1.3	9.44 1.3	11.25 1.3	7.04 1.3		9.99 1.3				4.15 1.6	5.00 1.7	6.17 1.6	5.45 0.9	10.38 1.1	6.45 1.2	7.42 1.7					8.62 1.5						3.68 1.6	16.42 1.1	10.41 1.8	5.84 1.5						18.31 1.2
																						_						_		_					_									
ANID	CDA088	CDA089	CDA090	CDA091	CDA092	CDA093	CDA094	CDA095	CDA096	CDA186	CDA189	CDA190	CDA191	CDA192	CDA194	CDA195	CDA292	CDA297	CDA312	CDA316	CDA346	CDA347	CDA359	CDA383	CDA384	CDA403	CDA414	CDA433	CDA434	CDA435	CDA436	CDA437	CDA489	CDA499	CDA500	DJT001	DJT002	DJT003	DJT004	DJT005	DJT007	DJT008	DJT009	DJT010

ANID	macro_grp	Chem2012	CERAMIC TYPE	MATERIAL	SOURCE	STATE	SITE_NAME	SITE_NO	AS	LA	21	QN	SM	n	YB	E C0	CR
DJT011	Group-B	Unas.	Mimbres B/W Style III	Pottery	MURR	AZ	Powers Ranch	AZ CC:3:46 (4	3.15		0.5706	45.52	19.6	4.30 3	3.92 104.20	97.8	39.02
DJT012	Group-C1	Mimbres-21	Mimbres B/W Style III	Pottery	MURR		Powers Ranch	AZ CC:3:46 ()	1.82	38.42	0.3686	28.66	5.63	1.55 2	2.41 75.76	9.19	50.68
DJT013	Group-B1	Mimbres-05A	Mimbres B/W Style III	Pottery	MURR	ΑZ	Powers Ranch	AZ CC:3:46 (/	2.85	44.85	0.6145	41.52	9.13	3.38 4	4.31 98.15	5 7.85	47.54
DJT014	Group-B1	Mimbres-05A	Mimbres B/W Style III	Pottery	MURR	ΑZ	Powers Ranch	AZ CC:3:46 (4	2.25	28.68	0.6761	-	10.06	4.04	4.31 92.15	5 6.73	53.76
DJT015	Group-C1	Mimbres-21	Mimbres B/W Style III	Pottery	MURR		Powers Ranch	AZ CC:3:46 ()	5.51	41.16	0.3840	30.70	6.03	1.41 2	2.67 82.29	65 677	51.20
DJT016	Group-B1	Mimbres-05A	Mimbres B/W Style III	Pottery	MURR		Powers Ranch	AZ CC:3:46 (4	2.90	48.48	0.7233	44.15	86.6	3.75 4	4.57 110.20	7.87	53.78
DJT022	Group-C1	Mimbres-21	Mimbres B/W Style II	Pottery	MURR	ΑZ	Powers Ranch	AZ CC:3:46 ()	2.07		0.3479	27.16	5.30	1.20 2		30 13.56	92.57
DJT023	Group-B	Unas.	Mimbres B/W Style II	Pottery	MURR	ΑZ	Powers Ranch	AZ CC:3:46 (4	4.00		0.5920	44.14	80.6	4.00	3.89 87.93	3 6.46	35.80
DJT031	Group-C1	Mimbres-22	Cibola whiteware	Pottery	MURR		Powers Ranch	AZ CC:3:46 (4	12.23	37.87	0.2826	29.04	4.87	1.09	1.94 73.39	19 6.41	8.77
ED-001	Group-A	Unas.	Mimbres B/W Style III	Pottery	TAM	MN	NAN	LA 002465	2.27	40.78	0.3827	66.49	5.32	4.42	2.75 145.75	75 12.06	53.38
ED-002	Group-B1	Mimbres-04A	Mimbres B/W Style III	Pottery	TAM	MN	NAN	LA 002465	2.21	43.04	0.4200	34.59	5.27		2.75 79.30	89.9 08	16.76
ED-003	Group-B1	Mimbres-04A	Mimbres B/W Style III	Pottery	TAM		NAN	LA 002465	2.19	43.60	0.4387	39.61	6.43	5.92	3.11 76.54	6.09	19.79
ED-004	Group-B2	Mimbres-02A	Mimbres B/W Style III	Pottery	TAM	MN	NAN	LA 002465	1.66	41.59	0.4667	38.31	6.32	4.63 3	3.20 81.03	3 5.98	35.76
ED-005	Group-B2	Mimbres-02B	Mimbres B/W Style III	Pottery	TAM	MN	NAN	LA 002465	3.57	42.70	0.4853	33.90		4.66	3.39 72.42	12 6.65	34.30
ED-006	Group-B1	Mimbres-04A	Mimbres B/W Style III	Pottery	TAM	MN	NAN	LA 002465	1.85	41.41	0.4480	32.83	5.53	5.23 3	3.15 74.61	1 4.87	17.42
ED-007	Group-B	Unas.	Mimbres B/W Style III	Pottery	TAM		NAN	LA 002465	2.80		0.4293	30.03		2.10 2			25.39
ED-008	Group-B1	Mimbres-04A	Mimbres B/W Style III	Pottery	TAM	MN	NAN	LA 002465	5.69	48.76	0.4760	43.25	5.71	4.30 2	2.90 92.84	34 7.96	23.19
ED-009	Group-B1	Mimbres-04A	Mimbres B/W Style III	Pottery	TAM		NAN	LA 002465	2.43	47.23	0.4480	35.33	6.71	4.78	2.96 80.32	32 4.52	18.19
ED-010	Group-B1	Mimbres-04A	Mimbres B/W Style III	Pottery	TAM	MN	NAN	LA 002465	3.18	55.82	0.5507	60.20	9.31	5.57 4	4.20 109.68	12.51	18.42
ED-011	Group-B1	Mimbres-04A	Mimbres B/W Style III	Pottery	TAM	MN	NAN	LA 002465	3.15	42.44	0.4107	38.88	5.93	4.73 3	3.04 75.13	13 3.91	19.47
ED-012	Group-B1	Mimbres-04B	Mimbres B/W Style III	Pottery	TAM	MN	NAN	LA 002465	1.62	58.09	0.5320	47.16	7.45		3.18 97.81		22.61
ED-013	Group-B1	Mimbres-04A	Mimbres B/W Style III	Pottery	TAM	MN	NAN	LA 002465	5.66	40.02	0.4293	41.78	6.19	4.96	2.59 79.20		23.40
ED-014	Group-B2	Mimbres-02A	Mimbres B/W Style III	Pottery	TAM	MN	NAN	LA 002465	2.06	39.39	0.4760	38.91	5.82	4.25	3.24 65.46	16 5.70	30.40
ED-015	Group-B1	Mimbres-04A	Mimbres B/W Style III	Pottery	TAM		NAN	LA 002465	1.52	42.45	0.4387	32.19			2.85 64.96	4.70	18.78
ED-016	Group-B1	Mimbres-04A	Mimbres B/W Style III	Pottery	TAM		NAN	LA 002465	3.40	47.18	0.5320	40.65		5.35 3	3.13 79.70	7.08	26.69
ED-017	Group-B	Unas.	Mimbres B/W Style III	Pottery	TAM		NAN	LA 002465	5.03	55.11	0.5320	45.27		6.21 3	3.29 84.92	7.76	
ED-018	Group-B2	Mimbres-02A	Mimbres B/W Style III	Pottery	TAM	NM	NAN	LA 002465	2.84	45.61	0.4387	36.67	5.81	1.97	2.81 63.86		25.93
ED-019	Group-B2	Mimbres-02A	Mimbres B/W Style III	Pottery	TAM		NAN	LA 002465	1.80		0.4573	38.54		4.68 2			
ED-020	Group-B1	Mimbres-04A	Mimbres B/W Style III	Pottery	TAM		NAN	LA 002465	2.99		0.4293	37.87	9.00	4.16 2	2.60 70.14		25.38
ED-021	Group-B	Unas.	Mimbres B/W Style III	Pottery	TAM		NAN	LA 002465	1.07	_	0.6813	44.05	_				12.21
ED-022	Group-A	Mimbres-01	Mimbres B/W Style III	Pottery	TAM		NAN	LA 002465	2.57	_	0.6347	48.60	1		1		9.07
ED-023	Group-B	Unas.	Mimbres B/W Style III	Pottery	TAM		NAN	LA 002465	1.75		0.3360	34.73				1	
ED-024	Group-B2	Mimbres-02A	Mimbres B/W Style III	Pottery	TAM		NAN	LA 002465	1.91		0.5040	51.09					
ED-025	Group-B2	Mimbres-02A	Mimbres B/W Style III	Pottery	TAM		NAN	LA 002465	1.46		0.4853	43.58			3.26 63.79		37.34
ED-026	Group-A	Mimbres-03	Mimbres B/W Style III	Pottery	TAM		NAN	LA 002465	1.72		1.0173	50.73	8.57	5.60 7			10.32
ED-027	Group-B2	Mimbres-08	Mimbres B/W Style III	Pottery	TAM		NAN	LA 002465	2.99	32.39	0.3547	16.21	3.43	5.68 2	2.02 50.97	3.01	19.85
ED-028	Group-B2	Mimbres-02A	Mimbres B/W Style III	Pottery	TAM		NAN	LA 002465	2.41		0.5600	57.98		2.40 4	4.19 91.76	76 8.55	34.64
ED-029	Group-B2	Mimbres-02A	Mimbres B/W Style III	Pottery	TAM	MN	NAN	LA 002465	1.92	38.91	0.4480	33.76	4.58	5.02	2.96 65.00	00 4.69	37.31
ED-030	Group-B1	Mimbres-04A	Mimbres B/W Style III	Pottery	TAM	MN	NAN	LA 002465	1.04	42.38	0.4107	40.25	5.59	4.18 2	2.70 80.04	4.50	19.28
ED-031	Group-B1	Mimbres-04A	Mimbres B/W Style III	Pottery	TAM		NAN	LA 002465	2.36	51.07	0.4947	52.48	7.37	3.65	3.29 99.52		21.82
ED-032	Group-B1	Mimbres-04A	Mimbres B/W Style III	Pottery	TAM	MN	NAN	LA 002465	2.15	35.01	0.3733	22.94	4.25	3.81 2	2.24 55.11	1 4.84	17.79
ED-033	Group-B1	Mimbres-04A	Mimbres B/W Style III	Pottery	TAM		NAN	LA 002465	1.95		0.4387	35.20	5.35	2.93 2	2.69 78.20	09.9 0	17.52
ED-034	Group-B1	Mimbres-04A	Mimbres B/W Style III	Pottery	TAM		NAN	LA 002465	3.05	39.99	0.4200	32.66		3.28 2	2.45 74.10	0 4.73	21.30
ED-035	Group-B2	Mimbres-08	Mimbres B/W Style III	Pottery	TAM	N N	NAN	LA 002465	3.03	34.36	0.3547	17.73	3.58	5.03 2	2.14 56.86	36 2.79	19.12

>	75.29	58.99	77.76	92.42	59.17	84.36	70.77	60.91	44.22	36.06	33.31	43.90	59.27	50.56	33.80	40.03	50.34	38.05	45.60	46.61	32.10	52.94	48.32	47.42	49.28	66.79	43.85	52.15	49.56	36.42	28.45	65.11	54.22	59.16	0.00	34.74	57.95	44.36	41.21	55.79	40.95	0.00	44.60	44.93
I	3721.3	2304.3	4380.9	4671.2	2832.9	4444.7	2656.7	3488.9	1559.2	3241.7	2619.4	3510.5	2908.1	2471.2	2512.8	1933.8	2165.6	2181.2	3354.3	3031.4	2605.7	3404.2	2655.4	3712.1	3130.0	3322.7	2012.7	3241.2	2716.5	2664.8	1160.6	3930.9	2/34.9	3263.7	1023.1	2636.2	2575.8	2855.7	3025.3	3207.0	2636.5	2979.3	3309.3	2415.4
NA	13423.0	17947.3	14403.5	14890.5	17454.3	14673.6	19569.1	13010.0	10715.9	16687.4	14542.4	13116.3	13158.6	9579.1	17668.9	10584.4	12989.8	16522.3	15357.3	17068.4	13878.4	12641.0	14767.8	14466.2	12820.7	10229.5	13677.6	14482.4	15825.9	13569.1	11499.3	1/191.0	12859.6	13364.3	5991.1	9291.6	12073.6	10891.7	17557.1	15999.8	13498.3	17031.0	14811.4	9822.8
W	429.8	1101.4	378.8	322.4	1138.2	305.4	1322.0	453.0	774.7	294.6	397.0	379.4	217.5	482.6	220.2	419.6	541.1	173.2	330.8	197.4	202.7	365.1	357.5	291.1	559.4	478.8	444.6	279.7	202.2	894.3	197.6	0.000	424.9	240.3	593.8	152.4	436.6	166.1	225.7	466.3	219.8	438.2	238.7	153.3
\prec	27192.4	28573.4	29363.4	27517.7	31606.7	27723.3	24384.1	29746.3	39558.3	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
DΥ	8.383	3.709	8.031	8.372	4.186	9.018	3.757	6.850	3.217	3.594	4.826	4.683	5.037	3.603	3.670	3.842	4.234	4.712	6.929	3.947	4.884	4.884	4.253	4.435	5.094	4.874	4.463	4.100	4.444	7.130	4.865	7.886	5.46/	4.932	9.940	2.361	6.241	3.498	4.005	6.193	2.781	4.750	4.148	0.000
CA	15202.8	18069.3	13229.5	18486.0	9.8776	11423.0	19344.5	10310.2	26803.9	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
BA	463.6	891.6	576.3	648.0	810.2	267.8	792.5	532.5	922.7	1352.6	786.8	897.4	676.3	520.9	891.9	408.0	0.789	6.697	732.5	767.2	869.5	685.0	551.6	804.1	673.0	462.5	511.2	520.6	693.3	632.1	603.0	7.30.6	540.T	627.3	306.8	514.9	546.5	419.9	7.706	812.4	662.2	858.3	712.0	531.4
AL	9.60006	90153.1	87360.3	96227.1	96918.2	94793.1	93385.7	88652.2	99512.9	77818.7	84226.8	78201.9	77935.6	81719.3	71221.2	71476.6	82221.0	78551.7	78884.6	80549.7	72322.9	79606.2	74547.8	81018.7	81135.4	83807.9	79806.7	83865.1	84672.7	82474.0	100488.9	89262.3	83837.6	82/48.8	/2430./	76198.0	76244.6	79410.0	76851.1	88242.6	83452.8	82133.5	84181.8	75251.8
ZR	169.9	171.2	241.1	207.2	186.0	255.3	149.8	193.5	148.8	292.6	176.7	185.0	194.5	152.1	198.0	127.5	177.6	212.7	172.3		174.4	211.4	165.5	207.1	171.3	152.8	149.4	177.1	186.3	177.3	163.4	158.2	1/5.0	114.1	1/1.5	182.2	157.1	221.5	180.4	256.2	200.0	180.0	203.0	168.7
NZ	90.6	81.9	74.4	63.1	78.7	133.7	76.9	61.1	79.5	101.7	69.2	49.2	55.3	9.89	46.1	64.5	78.7	53.0	56.9	50.7	47.2	48.2	53.6	53.1	86.3	149.0	57.3	48.3	53.8	50.2	51.2	69.6	59.7	65.6	87.7	36.3	60.9	56.8	51.4	52.1	65.5	60.5	53.0	34.0
TH	1					17.18		l	90.6	35.94	23.45	21.08	18.15	21.65	18.42	23.60	22.71		20.50	21.15	27.40	22.21	21.72	19.07																	19.93			25.32
TB 1	1.32	\sim	'	1.33	0.70	1.60	0.70	1.14	0.54	1.70	0.83	0.85	0.84	99.0	0.70	0.71	0.75	98.0	1.24	99.0		0.75	0.72	0.78				0.72													0.47			0.39
TA	1.2481							1.5796	0.5434	2.9000	1.5500	1.5600	1.3700	1.5100			1.4700	1.3100	1.7600	1.4300	1.7800	1.5800	1.5500	1.4400				,		_	-	_						`		`	`			1.4800
SR	237.1	344.7	293.8	282.0	300.0	280.9	387.1	302.8	296.1	635.3	216.5	176.7	305.2	9.161	252.5	267.8	214.2	238.4	211.5	240.6	125.3	190.4	303.5	214.8	184.5	121.9	317.7	298.2	279.7	149.6	98.7	414.1	359.2	287.4			305.1	179.5	277.9	260.5				148.3
SC	10.41	6.79	11.27	12.75	7.26	13.14	9.44	9.73	4.46	15.09	6.78	6.78	10.99	8.77	5.64	6.74	7.15	6.45	9.92	69.9	6.34	6.85	9.19	6.15	7.03	8.30	8.21	9.82	7.51	4.29	5.71	10.03	9.76	10.58	5.53	5.48	10.85	9.62	60.9	7.00	6.33	5.76	6.56	5.12
SB	0.8754	2.1954	0.7610	0.6022	2.5489	0.7960	1.3473	0.4378	3.7700	0.9387	0.7680	0.4608	0.5291	1.0667	0.5120	0.8533	0.8021	0.4523	0.4864	0.4864	0.7424	0.5205	0.4949	0.4523	0.6997	1.3739	0.5291	0.5120	0.5035	0.4096	1.2117	0.4864	0.5205	0.4608	0.3584	0.6485	0.5547	0.6571	0.5291	0.3840	0.5291	0.4608	0.6400	0.5632
RB	131.03	126.18	138.57	127.49	145.67	142.24	122.15	133.70	156.88	272.30	164.69	171.66	140.78	207.30	145.60	127.72	170.39	138.10	145.84	142.33	178.96	147.24	160.30	163.08	164.00	140.41	140.49	151.34	141.18	188.16	248.96	136.66	151.29	144.79	740.17	167.19	146.54	177.79	152.25	136.79	158.10	167.17	156.97	173.22
Z	27.6	13.8	28.7	18.1	20.3	17.7	49.1	27.2	21.8	0.0	0.0	0.0	0.0	0.0		0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0			0.0			0.0	0.0	0.0	0.0			0.0			0.0	0.0	0.0	0.0	0.0	0.0
生	5.58	6.32				8.82			5.55	12.20	7.37	9.90	7.23	6.01		6.05	9.85	8.35	6.27	6.40		7.84	6.64	7.86														9.17						6.01
FE	27058.3					26389.5	31200.2		18802.6	41950.6	24598.3	21355.6	26474.8	24815.6	19262.5	21328.0	26296.6	19266.1	25107.6	23136.5	18102.4	24791.4	23419.4	20160.7							12920.5							20820.8						17152.5
EU	1.5145					1.6385	1.2306	1.4376	1.1642	2.5036	1.1525	1.3611	1.3412	1.1227		0.7749	1.1823	1.2518	1.5598		1.2518	1.1425	1.1127	1.2220							_			1.3313	5.34 0.506/	6.96 0.6160	25.06 1.5995	0.7551	1.2319	1.4803			1.0730	5.93 0.6557
CS	13.79	16.48	7.39	6.94	18.33	8.29	18.58	6.30	31.69	24.59	4.19	4.43	13.38	39.49	4.09	11.02	29.6	4.42	4.11	4.01	7.56	5.38	15.55	3.93	5.71	6.33	19.49	13.67	4.61			6.48	20.43	15.91	5.34	96.9	25.06	19.25	4.31	3.67		4.04	5.63	5.93
ANID	DJT011	DJT012	DJT013	DJT014	DJT015	DJT016	DJT022	DJT023	DJT031	ED-001	ED-002	ED-003	ED-004	ED-005	ED-006	ED-007	ED-008	ED-006	ED-010	ED-011	ED-012	ED-013	ED-014	ED-015	ED-016	ED-017	ED-018	ED-019	ED-020	ED-021	ED-022	ED-023	ED-024	ED-025	ED-026	ED-027	ED-028	ED-029	ED-030	ED-031	ED-032	ED-033	ED-034	ED-035

ANID	macro grp	macro grp Chem2012	CERAMIC TYPE	MATERIAL	SOURCE	STATE	SITE NAME	SITE NO	AS	ΓA	Π	ND	SM	Λ	YB CE	00	CR
ED-036	Group-A	Mimbres-01	Mimbres B/W Style III	Pottery	TAM		NAN	LA 002465	1.39	53.42 0.	0.4947	28.69	3.67 12.18	18 2.17	7 81.91	3.22	90.9
ED-038	Group-B	Unas.	Mimbres B/W Style III	Pottery	TAM	MN	NAN	LA 002465	3.18	32.18 0.	0.4480 2	25.84 4	4.08	1.70 2.7	3 62.70	11.62	22.74
ED-039	Group-B2	Mimbres-02A	Mimbres B/W Style III	Pottery	TAM	MN	NAN	LA 002465	1.43	38.37 0.	0.4293 3	30.38 4	4.56 4.	4.82 2.64	4 65.59	19:91	33.63
ED-040	Group-B2	Mimbres-08	Mimbres B/W Style III	Pottery	TAM	MΝ	NAN	LA 002465	3.29	37.94 0.	0.4200	29.55 4	4.11 5.	5.56 2.33	3 62.51	4.09	20.61
ED-041	Group-B1	Mimbres-04A	Mimbres B/W Style III	Pottery	TAM	NM	NAN	LA 002465	2.36								22.04
ED-042	Group-B1	Mimbres-04B	Mimbres B/W Style III	Pottery	TAM	NM	NAN	LA 002465	2.72	42.14 0.	0.4200 3		5.57 5.	5.42 2.55	5 76.37	4.55	22.03
ED-043	Group-B1	Mimbres-04A	Mimbres B/W Style III	Pottery	TAM	NM	Avilas Canyon Village	LA 045000	2.20	40.62 0.	0.4200 3	35.95 6	6.37 4.0	4.05 2.85	5 77.00	92.20	22.89
ED-044	Group-A	Mimbres-01	Mimbres B/W Style III	Pottery	TAM	NM	Las Animas Village	LA 003949	2.03	65.62 0.	0.5787 3	30.43 4	4.49 10.33	33 2.85		3.34	7.95
ED-045	Group-A	Mimbres-01	Mimbres B/W Style III	Pottery	TAM	MN	Las Animas Village	LA 003949	00.00	82.06 0.	0.7653 4	46.10 8	8.01 13.91	91 4.21	123.57	7.76	7.26
ED-046	Group-A	Mimbres-01	Mimbres B/W Style III	Pottery	TAM	MN	LA 044997	LA 044997	1.65	47.18 0.	0.4947 2	29.55 3.	3.82 11.05	05 2.36			5.89
ED-047	Group-A	Mimbres-01	Mimbres B/W Style III	Pottery	TAM	MN	Ronnie Pueblo	LA 045103	1.92	55.30 0.	0.4853 2	29.21	4.09 9.	9.79 2.44	4 81.24	2.31	8.70
ED-048	Group-A	Mimbres-01	Mimbres B/W Style III	Pottery	TAM	MN	Las Animas Village	LA 003949	1.68	53.28 0.	0.5507 3	31.57	3.65 11.68	68 2.57	7 82.47	7 2.21	5.78
ED-049	Group-A	Mimbres-01	Mimbres B/W Style III	Pottery	TAM	MN	Buckaroo Site	LA 070259	2.67	75.24 0.	0.7467 4	41.45 5.	5.36 9.	9.63 4.06	106.49	2.44	6.02
ED-050	Group-A	Mimbres-01	Mimbres B/W Style III	Pottery	TAM	MN	Las Animas Village	LA 003949	1.16	61.93 0.	0.5133 3	34.96	4.24 10.09	09 2.60		2.71	7.90
ED-051	Group-B2	Mimbres-08	Mimbres B/W Style III	Pottery	TAM	NM	NAN	LA 002465	2.40		0.3547 2	22.69 3	3.34 4.	4.74 2.03	3 57.88	5.53	22.87
ED-052	Group-B2	Mimbres-08	Mimbres B/W Style III	Pottery	TAM	NM	NAN	LA 002465	2.34	34.85 0.				3.85 2.14		5.42	23.18
ED-053	Group-B1	Mimbres-04A	Mimbres B/W Style III	Pottery	TAM	NM	NAN	LA 002465	1.93	48.68 0.	,	_		2.94 2.56			23.45
ED-054	Group-B	Unas.	Mimbres B/W Style III	Pottery	TAM	MN	NAN	LA 002465	00.00	43.36 0.	0.4947 4	44.37	7.00 3.	3.49 3.26	9 70.95	6.14	33.71
ED-055	Group-B2	Mimbres-02A	Mimbres B/W Style III	Pottery	TAM	MN	NAN	LA 002465	2.22	36.96 0.	0.4387 3	33.39 4	4.85 2.:	2.36 2.74	4 58.48	5.75	26.63
ED-056	Group-B2	Mimbres-02A	Mimbres B/W Style III	Pottery	TAM	MN	NAN	LA 002465	1.92	40.31 0.		31.82 4	4.29 2.	2.99 2.73	3 68.75	4.34	31.21
ED-057	Group-B1	Mimbres-04A	Mimbres B/W Style III	Pottery	TAM	MN	NAN	LA 002465	2.45	43.96 0.	0.4107 3	39.77 5	5.92 2.	2.58 2.61	1 76.42	3.64	16.00
ED-058	Group-B2	Mimbres-02A	Mimbres B/W Style III	Pottery	TAM	MN	NAN	LA 002465	2.32	57.23 0.	0.5320 5	51.16 7	7.90 2.	2.38 3.46	6 74.47	6.42	37.96
ED-059	Group-A	Mimbres-01	Mimbres B/W Style III	Pottery	TAM	MN	NAN	LA 002465	2.29	46.80 0.	0.4667 3	32.69 4	4.55 7.	7.74 2.60		3.34	16.60
ED-090	Group-B1	Mimbres-04B	Mimbres B/W Style III	Pottery	TAM	MN	NAN	LA 002465			0.5787 5			3.18 3.61			24.64
ED-071	Clay		Clay	Clay, Adobe	TAM	NM	NAN	LA 002465	1.59	41.03 0.	0.3920 2	23.25 5	5.35 3.	3.38 2.87			44.15
ED-072	Group-A	Mimbres-01	Mimbres B/W Style III	Pottery	•	M	Elk Ridge	LA 078963	1.50				1		_		6.54
ED-073	Group-C1	Unas.	Mimbres B/W Style III	Pottery	TAM	M	Elk Ridge	LA 078963	1.94							1	54.06
ED-074	Group-B2	Mimbres-11	Mimbres B/W Style III	Pottery	TAM	M	Elk Ridge	LA 078963	2.74								35.96
ED-075	Group-B2	Mimbres-08	Mimbres B/W Style III	Pottery	TAM	M	Elk Ridge	LA 078963	1.80				3.64 5.	5.50 2.14			23.15
ED-076	Group-B	Unas.	Mimbres B/W Style III	Pottery	TAM	M	Elk Ridge	LA 078963					_				15.99
ED-077	Group-A	Mimbres-01	Mimbres B/W Style III	Pottery	TAM	ΣN	Elk Ridge	LA 078963					1		_		7.47
ED-078	Group-C1	Unas.	Mimbres B/W Style III	Pottery	TAM	Σ	Elk Ridge	LA 078963								_	36.63
ED-079	Group-B1	Mimbres-04A	Mimbres B/W Style III	Pottery	TAM	Σ	Elk Ridge	LA 078963							_		18.89
ED-080	Group-B1	Mimbres-09	Mimbres B/W Style III	Pottery	TAM	ΣN	Elk Ridge	LA 078963									12.57
ED-081	Group-B1		Mimbres B/W Style III	Pottery	TAM	MM	Elk Ridge	LA 078963				_			1		17.15
ED-083	Group-C2b	Mimbres-41	Clay	Clay	TAM	NM	NAN	LA 002465	1.31	29.27 0.							22.80
ED-084	Group-C2b		Clay	Clay	TAM	NM	NAN	LA 002465	1.43		0.2520 2		3.85 1	1.29 1.80		8.05	17.11
ED-085	Group-C2b	Mimbres-41	Clay	Clay	TAM	NM	NAN	LA 002465	1.69	28.38 0.	0.2613 1		4.06 1	1.39 1.91	1 53.02	7.40	19.11
ED-086	Group-C2b	Mimbres-41	Clay	Clay	TAM	Σ	NAN	LA 002465	1.36	29.76 0.	0.2893 2	25.75 4	4.30 2	2.20 1.82	2 52.12	92.9	20.46
ED-087	Group-C2b	Mimbres-41	Clay	Clay	TAM	MN	NAN	LA 002465	00.00	27.75 0.	0.2707	23.42	4.07	1.91 2.08	8 55.56		20.59
ED-088	Group-C2b		Clay	Clay	TAM	NM	NAN	LA 002465	0.00	29.47 0.	0.3080 2		4.54 2	2.39 1.94	4 53.16	6.95	20.91
ED-089	Group-C2b		Mimbres B/W Style III	Pottery	TAM	M	NAN	LA 002465	0.00								23.36
ED-090	Group-C2b	Mimbres-41	Mimbres B/W Style III	Pottery	TAM	M	NAN	LA 002465								1	24.42
ED-091	Group-C2	Unas.	Mimbres B/W Style III	Pottery	TAM	MM	NAN	LA 002465	2.96	29.75 0.	0.2333 2	25.90 4	4.58 2.	2.00 1.80	0 61.88	8.24	25.28

>	0.00	46.69	39.00	40.15	45.01	46.82	62.71	24.53	34.25	20.02	27.01	18.85	21.76	20.36	42.25	40.76	58.71	60.75	42.14	43.83	44.66	66.25	30.85	54.22	78.43	32.16	70.25	54.74	43.67	40.36	25.44	76.14	44.14	37.67	49.75	68.43	73.06	71.26	73.06	68.43	79.56	81.21	76.26	00.09
I	0.0	0.0	3110.7	2528.1	3822.4	2936.8	3763.7	1411.3	2015.0	1828.9	1443.8	1617.1	1630.1	1296.7	2964.0	2210.5	3579.2	3525.7	2476.7	3557.4	3173.7	3200.8	1703.5	2710.9	4596.5	1885.0	3539.0	3757.2	2624.8	3106.2	1621.3	3993.5	3590.1	3147.4	3072.9	3605.3	3462.4	3606.7	4002.0	3247.6	3372.3	4263.6	4136.4	3304.4
NA	24125.8	14019.1	11539.8	8942.1	14338.3	10753.6	12837.3	11657.4	19324.3	13935.3	11571.7	16453.5	13737.3	12142.2	9814.9	9723.0	13545.4	15692.7	13303.8	12319.8	19157.9	14755.8	14269.4	11142.0	19422.0	15309.5	19579.7	12720.0	8416.0	16367.1	12892.2	15514.6	16453.6	17373.6	16451.6	15181.2	16137.8	16352.4	15867.0	16415.7	15859.9	16165.0	16736.6	24180.9
M	160.1	993.2	179.5	240.9	454.8	205.1	442.8	587.0	280.1	226.5	152.5	328.8	350.9	492.2	224.8	243.9	565.7	256.1	354.7	241.1	227.4	325.4	256.5	369.9	612.7	252.9	1170.0	501.1	176.1	299.3	182.5	626.8	454.8	279.2	218.9	433.3	348.2	341.0	354.0	373.9	317.0	900.4	755.3	1073.5
¥	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
DΥ	0.000	3.364	4.301	2.972	4.635	4.377	5.237	3.842	6.661	2.982	2.590	2.829	4.157	2.915	3.058	2.705	5.046	5.132	3.785	3.555	4.138	5.658	2.886	6.681	4.578	4.406	3.861	4.721	2.877	6.270	3.508	3.565	4.826	7.483	9.376	3.221	3.011	2.399	3.221	3.555	3.374	4.110	3.938	3.192
CA	0:0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0:0	0.0	0.0	0.0	0.0	0:0	0:0	0.0	0.0	0.0	0.0	0.0	0.0	0:0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0:0	0.0	0.0	0.0	0.0	0.0	0:0	0:0
BA	313.9	449.5	411.9	449.7	831.7	280.0	807.1	6.229	753.9	762.1	1100.5	492.5	419.0	619.8	454.3	428.2	679.1	9.069	530.9	454.1	800.9	595.2	425.7	726.1	722.4	642.9	894.8	492.1	416.2	7.686	408.8	808.5	815.7	1036.7	921.0	674.4	710.1	764.2	561.0	993.3	748.8	825.2	828.0	1040.9
AL	99180.3	66326.7	78723.6	78447.3	78028.6	88297.4	88291.8	106897.4	113324.3	107637.5	103407.6	9.805901	99745.8	93763.4	82735.1	80717.7	83983.5	90453.6	77498.0	82841.0	89712.0	92439.4	85283.9	80199.2	78142.3	110527.5	98811.0	78763.6	79617.7	85371.0	103976.1	84959.0	82795.6	90459.6	91755.6	89174.7	90800.4	89114.5	90642.5	89556.7	93552.0	89048.8	80828.8	922626
ZR	177.1	130.9			235.0	173.7	260.1	169.2	192.8	184.5	157.8	188.6	151.1	170.7	179.7	176.6	212.6	249.9	147.0	237.8	197.1	191.6	150.9	205.5	264.4	163.9				213.4						154.8	152.2	160.5	161.5	180.6	156.5			138.6
NZ	43.9	55.0			54.0		56.9	46.5	41.1	41.5	45.9		41.9	42.6	39.1	37.5	44.0	49.7	43.5	48.9	41.8		43.6	45.6													_,	73.9	73.1	76.1	73.1	61.2		102.6
3 TH	9 51.72	3 19.12		30.45	17.17		19.25	48.46	5 51.00	47.46	9 50.94	50.44	5 49.52	46.89	5 25.48	7 25.65) 22.31	5 21.80	19.88	23.62	5 22.83		37.64		14.46	3 48.35										_			66.6	9.70				3 7.24
A TE	0 0.29	0 0.58	0 0.58	0 0.46		0 0.65	0 0.89	0 0.46	96.0 0	0 0.37	0 0.39	0.30	99.0 0	0 0.41	0 0.35	0 0.37	0.69	0 0.76	0 0.55	0 0.52	0 0.75		0 0.45	_	0 0.65	0 0.73	0.69									0 0.58	0 0.39	0 0.48	0 0.46	0 0.56	0 0.56			0 0.53
TA	2.4600	1.2800		1.6000		1.5500	1.5100	2.3000	2.2400	2.6800	2.1500	2.5500	2.5700	2.0400	1.4900	1.4800	1.4700	1.4500	1.3700	1.7400	1.5000		2.0000	1.5200	1.3400	2.3000	`			1	- 1					0.8900	0.7600	0.8700	0.8900	0.8600	0.9000			0.6500
SR	117.2	320.7	162.1	132.9	319.4	152.4	242.8	141.3	166.7	137.2	132.2	108.7	103.2	140.2	97.4	115.2	212.0	280.9	310.0	186.1	279.2	302.3	158.3	149.2	320.4	177.2	368.1	208.8	112.9	226.1	151.6	444.0			203.5	557.1	593.4	579.0	498.6	620.9	528.7	467.7		683.3
SC	3.86	6.24	9.21	5.51	6.23	7.48	7.14	4.40	4.20	4.00	4.84	3.86	4.06	4.18	5.61	5.43	6.71	96.6	7.87	7.76	5.86	11.33	5.73	6.64	6.09	4.62	8.31	7.05	6.03	7.77	5.37	9.11	6.38	8.76	9.36	8.46	7.30	7.93	8.49	8.22	8.50	7.69	8.06	6.56
SB	0.6144	0.4011	0.6229	0.6997	0.4352	0.4608	0.4779	0.7168	0.5717	0.5803	0.7168	0.5632	0.6400	0.7680	0.5632	0.5205	0.4181	0.3755	0.3157	0.5632	0.3669	0.4949	0.6997	0.5120	0.3499	0.5632	1.5531	0.6827	0.6315	0.5632	0.8960	0.5803	0.4096	0.6229	0.6400	0.3328	0.2816	0.3328	0.3243	0.2731	0.2731	0.2645	0.3328	0.4523
RB	218.63	138.87	170.98	183.10	137.23	157.65	135.91	212.62	149.76	183.96	226.00	232.25	216.59	216.22	189.30	190.66	150.99	147.47	126.03	180.93	153.89	148.15	199.12	152.93	128.73	173.31	127.24	173.59	180.02	110.47	200.44	122.22	150.81	121.63	99.36	94.35	82.84	87.86	92.52	92.59	92.95	70.81	76.53	79.03
Z	0.0	0.0		0.0		0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0		0.0	0.0	0.0	0.0			0.0			0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
Ή	5.49	5.30	8.07	6.11	8.27	4.95	8.67	5.70	5.15	5.63	5.35	5.33	5.24	5.41	6.74	6.41	7.38	8.48	5.78	9.29	6.51		5.62	6.43	66.6	6.62	7.02	7.64	7.94					8.10	8.05	5.59	5.41	5.71	5.85	6.11	5.30	5.46	5.81	5.28
FE	12166.8	23949.1	19714.6	19217.7		23342.4	24838.9	12603.9	11902.6	10883.0	13072.9	12337.3	11010.0	12130.9	19265.9	18678.3	24359.1	24907.5	19674.0	17702.8	17050.4		15374.0	22121.2	29646.0	12146.8										32886.2	28831.2	31254.2	30680.9	32591.7	32579.6			31309.3
EU	0.4371	0.8147		0.6656	1.2220	5.83 0.9538	1.2121	11.08 0.6160	1.2518	10.68 0.4868	14.39 0.5762	23.00 0.4769	18.28 0.7650	11.24 0.5862	0.6259	0909.0	1.1227	1.3710	0.8842	16.16 0.7551	1.2021	1.5499	0.7451	1.5201	1.1227	0.9538	1.4108	0.9637	0.6756					2.0665			1.1326	1.1326	1.1624	1.2121	1.2021			1.2319
CS	23.67	12.42	17.33	6.55	3.85	5.83	4.61	11.08	10.11	10.68	14.39	23.00	18.28	11.24	6.97	6.83	5.13	13.89	14.28	16.16	3.86	17.70	14.26	5.26	2.92	10.30	21.08		7.17	4.07	44.21	11.52	4.15	4.15	4.77	3.96	3.18	3.47	3.95	3.79	3.89	2.46	2.64	5.01
ANID	ED-036	ED-038	ED-039	ED-040	ED-041	ED-042	ED-043	ED-044	ED-045	ED-046	ED-047	ED-048	ED-049	ED-050	ED-051	ED-052	ED-053	ED-054	ED-055	ED-056	ED-057	ED-058	ED-029	ED-090	ED-071	ED-072	ED-073	ED-074	ED-075	ED-076	ED-077	ED-0/8	ED-079	ED-080	ED-081	ED-083	ED-084	ED-085	ED-086	ED-087	ED-088	ED-086	ED-090	ED-091

ANID	macro grp	macro grp Chem2012	CERAMIC TYPE	MATERIAL	SOURCE	STATE	SITE NAME	SITE NO	AS	ΓA	Π	ND	SM	U YB	3 CE	00	CR
ED-093	Group-C1	Mimbres-21	Mimbres B/W Style III	Pottery	TAM	MN	West Fork	LA 008675	3.50	41.93 0	0.3267	32.52 5.	5.72 1.83	33 2.12	2 78.65	7.51	29.50
ED-094	Group-A	Mimbres-03	Mimbres B/W Style II/III	Pottery	TAM	MN	West Fork	LA 008675	5.09	39.59	1.1387	50.00 9.	9.65 3.66	56 7.39	9 102.62	2.45	8.98
ED-095	Group-A	Mimbres-03	Mimbres B/W Style III	Pottery	TAM	NM	West Fork	LA 008675	2.36	39.96	1.0640	42.87 8.	8.76 4.00	00 6.87	77.17	1.94	8.35
ED-096	Group-C1	Mimbres-22	Mimbres B/W Style III	Pottery	TAM	NM	West Fork	LA 008675	9.40	41.53 0	0.2893		Ì	1.55 1.97	73.17	5.97	11.49
ED-097	Group-A	Mimbres-03	Whiteware (not Mimbres)	Pottery	TAM	MN	West Fork	LA 008675	2.77		1.0827		8.89 4.05	7.14		2.12	9.12
ED-098	Group-B	Unas.	Mimbres B/W Style III	Pottery	TAM	MN	West Fork	LA 008675	2.24	30.63 0							13.30
ED-036	Group-A	Mimbres-03	Cibola whiteware	Pottery	TAM	MN	West Fork	LA 008675	2.67	34.49	1.3813	36.70 9.	9.97 4.03	33 9.78		1.92	7.27
ED-100	Group-C1	Mimbres-21	Mimbres B/W Style III	Pottery	TAM	MN	West Fork	LA 008675	4.25				5.61 1.18				25.96
ED-101	Group-C1	Mimbres-22	Mimbres B/W Style III	Pottery	TAM	M	West Fork	LA 008675	10.43							6.58	11.18
ED-102	Group-C1	Mimbres-22	Mimbres B/W Style III	Pottery	TAM	Σ	West Fork	LA 008675	4.21	38.15 0	0.2613	40.55 5.	5.10 0.00	00 2.08		7.41	20.91
ED-103	Group-C1	Mimbres-21	Mimbres B/W Style III	Pottery	TAM	MN	West Fork	LA 008675	3.14	42.18 0	0.3080	36.76 5.	5.86 0.00	00 2.40	087.30	8.92	30.10
ED-104	Group-A	Mimbres-03	Mimbres B/W Style III	Pottery	TAM	MN	West Fork	LA 008675	2.97	38.44 0	0.8587	46.72 8.	8.61 5.28	92.9 87.9	5 77.13	2.55	14.66
ED-105	Group-A	Mimbres-03	Mimbres B/W Style III	Pottery	TAM	NM	West Fork	LA 008675	4.02	46.03			10.73 3.60	50 8.27	_		14.91
ED-107	Group-A	Mimbres-03	Mimbres B/W Style II/III	Pottery	TAM	NM	West Fork	LA 008675	1.28		1.0453	54.87 11.	11.08 7.85	35 8.40	0 85.57	1.86	9.18
EP001	G-dno-D	El Paso Core	El Paso Polychrome	Pottery	TAM	X	FB 9859	41EP02770 (F	9.28	60.75 0	0.5787	52.11 9.	9.89 2.41	11 4.46	_	7.01	30.28
EP002	Group-D	Loop 375	El Paso Polychrome	Pottery	TAM	ĭ	FB 9859	41EP02788 (F	11.29					30 6.22		v	45.14
EP003	Group-D	Loop 375	El Paso Polychrome	Pottery	TAM	ĭ	FB 9859	41EP02788 (F	11.26								46.94
EP005	Gronp-D	El Paso Core	El Paso Polychrome	Pottery	TAM	X	FB 9859	41EP02788 (F	3.61	78.83 0		74.70 12.	12.43 2.60	50 6.03	3 151.46	5.81	27.06
EP006	Group-D	Loop 375	El Paso Brownware undif.	Pottery	TAM	ΤX	FB 9859	41EP02788 (F	6.77	59.74	1.0453	56.64 11.06	06 3.79	79 8.02	2 106.09	6.26	39.60
EP007	G-dno-D	Loop 375	El Paso Brownware undif.	Pottery	TAM	ΤX	FB 9859	41EP02788 (F	10.88	57.00 1	1.1293		12.73 2.28	28 8.97			40.50
EP008	G-dno-D	Loop 375	El Paso Brownware undif.	Pottery	TAM	ΤX	FB 9859	41EP02788 (F	11.33	55.43 0	0.9613 (60.09 11.	11.50 2.26	26 7.67			43.01
EP009	G-dno-D	Loop 375	El Paso Polychrome	Pottery	TAM	TX	FB 7899	41EP01621 (F	12.58	83.36	1.2413 8	83.21 16.11	11 4.05	08'6 9'80	147.96	7.58	47.46
EP011	G-dno-D	Loop 375	El Paso Polychrome	Pottery	TAM	X	FB 7899	41EP01621 (F	12.06			_	13.32 3.72	12 9.72	1		40.59
EP012	Gronp-D	Loop 375	El Paso Polychrome	Pottery	TAM	TX	FB 7899	41EP01621 (F	10.48					7.33		5.82	38.50
EP013	Group-D	El Paso Core	El Paso Brownware undif.	Pottery	TAM	ĭ	FB 7899	41EP01621 (F	7.72	49.24 0				2.96 2.63	3 84.66		27.95
EP014	Group-D	Loop 375	El Paso Brownware undif.	Pottery	TAM	ĭ	FB 7899	41EP01621 (F	11.48				13.88 4.06				46.71
EP015	Group-D	Loop 375	El Paso Bichrome	Pottery	TAM	ĭ	FB 7899	41EP01621 (F			_						48.61
EP016	Group-D	Loop 375	El Paso Polychrome	Pottery	TAM	ĭ	FB 7899	41EP01621 (F	13.07				12 3.57				45.14
EP018	G-dno-D	Loop 375	El Paso Polychrome	Pottery	TAM	ĭ	FB 7899	41EP01621 (F	12.20				15.44 2.7	71 10.32			42.38
EP021	G-dno-D	El Paso Core	El Paso Polychrome	Pottery	TAM	ĭ	FB 7899	41EP01621 (F	3.66							1(34.08
EP022	G-dno-D	Loop 375	El Paso Polychrome	Pottery	TAM	× i	FB 7899	41EP01621 (F	12.79	_		1				7.78	44.42
EP025	Group-D	El Paso Core	El Paso Brownware undif.	Pottery	IAM	× i	FB /634	41EP01143 (F	8.01	_							31.46
EP026	G-dno-D	El Paso Core	El Paso Brownware undif.	Pottery	TAM	× i	FB 7634	41EP01143 (F	5.97								22.61
EP027	Group-D	Loop 375	El Paso Polychrome	Pottery	TAM	×	FB 9802	41EP02738 (F	12.68								52.16
EP028	G-dno-D	Loop 375	El Paso Polychrome	Pottery	TAM	×	FB 9802	41EP02738 (F	13.32								42.55
EP029	G-dno-D	Loop 375	El Paso Polychrome	Pottery	TAM	×	FB 9802	41EP02738 (F	13.06							8.23	54.77
EP030	G-dno-D	Loop 375	El Paso Polychrome	Pottery	TAM	X	FB 9802	41EP02738 (F	13.05	89.26			17.59 3.05	12.93	3 163.74	6.67	54.29
EP033	G-dno-D	Loop 375	El Paso Brownware undif.	Pottery	TAM	X	FB 6895	41EP01664 (F	9.62	46.46 0	0.9520	53.90 9.	9.81 3.41		124.94	9.23	38.20
EP034	G-dno-D	Loop 375	El Paso Polychrome	Pottery	TAM	X	FB 6895	41EP01664 (F	9.70	49.78	1.1760	58.98 10.71	71 3.00	9.11		8.78	40.29
EP035	G-dno-D	El Paso Core	El Paso Brownware undif.	Pottery	TAM	X	FB 6895	41EP01664 (F	4.78	86.18 0	0.8400	75.96 15.	15.45 2.82	32 6.27	7 183.14		28.34
EP036	Group-D	Loop 375	El Paso Polychrome	Pottery	TAM	ĭ	FB 6895	41EP01664 (F	10.85	_			13.96 2.7	77 11.16			37.07
EP037	G-dno-D	Loop 375	El Paso Polychrome	Pottery	TAM	ĭ	FB 6895	41EP01664 (F	`		`			7	_		31.33
EP038	Group-D	Loop 375	El Paso Polychrome	Pottery	TAM	ĭ	FB 6895	41EP01664 (F									36.46
EP039	Group-D	Loop 375	El Paso Brownware undif.	Pottery	TAM	ĭ	FB 6895	41EP01664 (F	8.84	88.51	1.9880	81.59 14.	14.35 5.6	5.68 15.63	3 141.67	5.42	31.32

>	52.98	18.35	24.67	34.54	16.45	24.95	26.00	51.22	42.98	47.00	57.10	31.20	32.36	14.25	71.76	79.22	79.41	81.67	68.33	64.31	80.49	83.53	82.16	68.92	105.78	83.63	91.57	81.47	91.08	98.14	92.06	73.63	96.76	85.59	84.80	89.31	91.57	79.31	67.55	78.53	72.75	58.63	75.69	57.16
I		1603.8	1245.9	2312.2	1627.1	1947.5	1759.5		1939.4	2805.6		1429.3	2175.0	1873.9	4249.0		3541.9	5654.8	3459.2	3266.7	3493.5	3499.5	3519.6	3122.1		3972.6	4017.4			_						_		3143.3	3570.6		2483.4			2255.6
NA							Ì																																					
	_	3 4887.5	1 5214.7	1 15427.4	7 6141.5	3 5859.3	1 6833.7	7 18608.5	3 13510.9	3 15206.5	7 17091.4	0 6152.3	5 8022.3	9 5302.6	5 10686.8		1.777.1	15620.9	0 8895.7	2 12022.2	0 9458.6	7 9335.1	4 9405.9	5 10731.2	3 12054.6	3 8375.0	3 8860.8			$\overline{}$		`	1					10760.6	1 10202.8	3 15999.2	14736.3	_		3 13885.6
MN	l	694.8	723.1	804.1	744.	523.0	741.1		918.3	1039.8	916.7	601.0	730.6	611.9	423.6		262.7	404.4	246.0	247.2	255.0	244.7	294.4	211.6	415.8	234.3	250.3									297.2	318.8	346.2	344.1	578.8	173.4			168.3
×	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
DΥ	3.976	12.195	10.972	3.794	11.029	8.344	13.810	3.594	3.641	4.177	4.664	9.863	12.721	13.275	6.528	8.946	13.485	8.678	10.733	10.742	10.800	13.887	12.472	9.070	4.282	12.291	13.657	13.715	13.705	690.9	14.518	5.964	3.957	12.912	13.676	13.858	16.725	9.404	11.650	10.188	13.829	24.830	13.552	17.308
CA	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	17120.7	11582.9	5832.2	13768.1	13696.3	10809.8	11627.4	15119.9	14188.2	12479.0	15822.0	12765.2	14972.2					14137.3					15925.4	8962.1	8326.8			_		10981.0
BA	740.9	131.4	172.3	834.8	170.6	190.2	121.3	720.4	964.3	700.8	763.1	176.3	227.5	218.1	1306.3	1111.9	476.7	1181.8	9.7801	893.8	882.2	773.0	1058.0	586.4	1372.3	942.5	775.4	760.0	795.3	864.3	829.0	1592.0	1419.7	1502.8	1306.0	1011.0	1488.1	1445.5	1073.4	1514.6	824.8	1587.0	1349.8	1164.6
AL	107087.6	83015.9	83294.1	105542.0	81374.5	73133.1	82508.4	97148.4	104618.2	108252.8	101095.3	84514.5	85312.0	80858.1	84952.3	80110.1	88119.8	73587.4	77316.0	80615.3	86743.0	83301.2	85903.3	76325.6	93786.4	84300.8	83177.1	84877.5	85431.3	84198.4	87795.8			83834.2	85057.3	88321.4	98335.2	73246.8	74258.8	74461.8	85520.1	72731.3		75951.3
ZR	,	168.9	161.9	140.4	166.0	164.0	177.9	178.5	1.991	138.9	168.5	142.5	180.0	165.1	260.0	331.1	315.2	499.5	352.6	368.4	285.6	407.7	388.8	399.1	308.5	438.2	408.5	388.7	334.3	275.4	360.2	347.9	185.5	291.4	318.0	298.1	417.4	347.3	446.0	387.8	284.0	401.2	350.9	304.1
NZ	1	59.4	64.5	79.3	89.1	52.3	67.3	93.1		94.8	101.3	53.7	9:59	78.6	73.7		81.0	60.7	58.4	73.0	71.3	80.7	72.0	62.8	69.3	78.5	68.2	7									7.76	67.4	67.3	63.4	77.8			67.9
H	10.97	41.06	34.01	9.02	32.37	28.71	33.63	9.73	10.16	10.25	10.52	32.78	36.38	33.53	19.25	18.76	24.11	19.66	18.26	23.64	20.07	21.25	22.49	20.50	19.74	23.66	20.38	20.22	20.35	22.98	22.10	21.97	26.25	21.49	22.38	19.93	29.94	19.66	18.19	19.12	25.32	30.50	23.17	32.35
TB	0.59	1.46	1.27	0.46	1.31	1.11	1.62	0.55	0.57	0.64	0.79	1.36	1.71	1.88	1.17	1.64	2.75	1.67	1.90	2.11	1.88	2.60	2.18	1.81	0.86	2.45	2.70	2.55	2.32	1.13				2.29		2.19	2.74	1.57	1.70	1.99	2.31			2.66
TA	0.8000	2.3600	2.3000	0.5700	2.1200	2.2600	2.4000	0.8200	0.5900	0.6800	0.7500	2.1400	2.3400	2.4100	2.5200	2.8100	2.6300	2.6100	2.5500	3.0000	2.9600	2.9900	2.5500	2.6500	2.5700	2.4800	2.5300	2.1800	2.7400	2.2100	2.2100	2.5700	2.6700	2.5700	2.6800	3.3900	2.6300	2.5900	2.6800	3.4600	3.0200	3.0700		5.2200
SR	270.5	50.5	42.5	279.4	57.8	38.1	48.7	274.9	295.8	291.8	332.6	62.5	70.2	76.3	296.0	224.8	92.0	215.0	193.9	146.2	189.2	307.2	248.7	281.5	372.2	401.5	282.8	320.8	275.4	331.3	295.5	398.0	263.6	324.4	275.1	224.1	355.9	305.2	200.3	432.9	126.1	257.7	256.6	215.5
SC	5.98	4.51	4.60	4.16	4.72	4.83	4.38	5.74	4.74	2.68	6.55	5.19	6.13	4.81	8.93	10.28	11.04	66.6	8.78	9.94	10.67	10.57	10.34	9.34	10.12	10.77	10.73	10.79	10.25	10.75	10.99	9.71	7.25	11.44	10.68	10.98	12.48	8.40	8.65	9.16	10.15	7.12	9.14	7.94
SB	1.8005	0.3499	0.2475	2.7221	0.2987	0.4693	0.3243	1.5872	2.9013	1.5701	1.6811	0.3499	0.4352	0.2389	0.6741	1.0240	0.9216	0.5547	0.7083	0.7168	0.8448	0.8960	0.6997	0.7509	0.6229	0.8704	0.8704	0.9387	0.7680	0.5376	0.9728	0.7424	0.5120	0.8789	0.7851	1.0155	1.1947	0.6827	0.8192	0.5376	0.7765	0.5376	0.8363	0.5973
RB	138.50	259.81	262.78	138.53	274.88	241.73	263.32	126.42	149.03	137.71	138.44	226.67	247.45	275.04	114.30	131.90	164.10	84.80	138.50	160.30	165.40	126.60	134.60	137.50	116.90	130.30	124.50	122.60	118.00	138.00	117.00	120.50	112.70	119.70	106.80	117.90	134.00	128.10	139.90	95.80	185.20	168.50	137.40	180.30
Z		0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0											0.0	0.0		0.0			0.0
生		9.52	9.50	5.82	8.84	7.87	6.36	6.93	7.04	5.83	7.77	8.49	8.99	9.47	11.04		14.14	18.30	14.72	16.80	12.59	14.91	17.35	14.03	10.13	15.69	13.62			10.85	14.60	13.58					18.20	12.84	18.91	14.21	10.64	18.41	13.28	14.15
FE	23663.5	11990.9	12305.6	18766.9	13096.2	13510.4	11488.3	23711.6	21430.7	22342.7	28395.4	14337.9	16461.0	12263.6	39698.0	38764.9	45172.3	37086.0	35890.0	44486.3	42756.9	42496.9	42366.6	36980.9	46536.9		41977.4	42300.6	39033.0	44573.5	42108.7	41591.2		45627.8	42288.3	43161.3		34115.5	33764.8	33511.2	40273.6	1.5300 28412.2	37046.1	31273.7
EU		0.6358	0.4073	1.2220	0.4272	0.4371	0.4371	1.2816	1.3810	1.4406	1.4903	0.5464	0.6358	0.5166	1.7386		1.6393	1.9473	1.2816	1.3412	1.4605	1.8777	1.5598	1.3412	1.4406	1.8082	1.9870	1.8479	_		1.8579	1.7684	1.0233	1.9274	1.8579	1.8877		1.3214	1.3909	2.4540	1.3710	1.5300		1.1227
CS	16.70	4.00 (4.22	21.16	4.56	4.60 0.4371	4.24 (14.00	23.04	20.79	18.53	4.54 (4.96	4.48 (4.22		7.38	2.91	4.27	5.51	5.24	2.88	5.12	4.63	4.31	6.40	6.12								5.40	5.55	5.78	4.68	4.91		6.20			4.00
ANID	ED-093	ED-094	ED-095	ED-096	ED-097	ED-098	ED-036	ED-100	ED-101	ED-102	ED-103	ED-104	ED-105	ED-107	EP001	EP002	EP003	EP005	EP006	EP007	EP008	EP009	EP011	EP012	EP013	EP014	EP015	EP016	EP018	EP021	EP022	EP025	EP026	EP027	EP028	EP029	EP030	EP033	EP034	EP035	EP036	EP037	EP038	EP039

ANID	macro_grp	macro_grp Chem2012	CERAMIC TYPE	MATERIAL	SOURCE	STATE	SITE_NAME	SITE_NO	AS	ГА	21	QN	SM	П	YB (CE CO	O CR
EP040	Group-D	Loop 375		Pottery	TAM	X	FB 6895	41EP01664 (F	8.97	68.41	1.1853	75.33	13.20	3.27	9.73 120.70	.70 6.62	2 36.50
EP041	Group-D	Loop 375		Pottery	TAM	ĭ	FB 6895	41EP01664 (F	10.64	91.76							5 35.83
EP042	Gronp-D	Loop 375		Pottery	TAM	TX	FB 6895	41EP01664 (F	11.45		0.9333	69.29		2.83			
EP043	Gronp-D	Loop 375	undif.	Pottery	TAM	TX	FB 6895	41EP01664 (F	98.6	49.64	0.9520		10.35	3.17	6.83 134.76	.76 8.87	_
EP044	Group-D	Loop 375		Pottery	TAM	ĭ	FB 6895	41EP01664 (F	13.74	65.26	1.1013	_					
EP045	Group-D	El Paso Core		Pottery	TAM	ĭ	FB 9895	41EP02805	6.15		0.4853	54.27			4.37 124.31		
EP046	Group-D	El Paso Core		Pottery	TAM	ĭ	FB 9895	41EP02805	5.34		0.5227	81.42					
EP049	Group-D	El Paso Core		Pottery	TAM	TX	FB 9895	41EP02805	6.12	59.55	0.5133	72.23		3.04	3.66 120.45	.45 7.10	0 24.28
EP052	Gronp-D	El Paso Core		Pottery	TAM	TX	FB 9895	41EP02805	2.90	26.68	0.4947	26.57		2.19	4.51 128.44	.44 7.01	1 31.1
EP053	Group-D	El Paso Core		Pottery	TAM	TX	FB 9895	41EP02805	6.82	40.83	0.3173	29.97	5.29	3.87	2.57 56.04	.04 4.66	6 21.66
EP056	Group-D	El Paso Core		Pottery	TAM	ĭ	FB 9895	41EP02805	5.92	58.03	0.4107	48.94	8.09	2.11	4.14 87.20	.20 5.16	6 24.02
EP057	Group-D	El Paso Core	El Paso Brownware undif.	Pottery	TAM	ĭ	FB 9895	41EP02805	5.75	60.12	0.5227	61.19	10.12	2.74	4.42 130.57	.57 7.18	8 29.02
EP058	Group-D	El Paso Core	El Paso Brownware undif.	Pottery	TAM	ĭ	FB 9895	41EP02805	5.10	57.87	0.5040	59.01	9.27	2.69	4.18 128.89	.89 7.11	1 28.39
EP059	Group-D	El Paso Core		Pottery	TAM	ĭ	FB 9895	41EP02805	5.50	55.74	0.5413	51.24	8.15	1.78	4.15 93.10	.10 5.41	1 24.1
EP062	Group-D	El Paso Core		Pottery	TAM	ĭ	FB 6772	41EP01143 (F	6.77	68.02	0.7747	69.28	11.25	1.88	6.74 121.40	.40 9.40	0 41.55
EP063	Group-D	Loop 375		Pottery	TAM	TX	FB 6772	41EP01143 (F	7.88		0.9147	63.66	11.13		8.14 108.41	.41 7.87	7 61.3
EP065	G-dno _{-D}	Loop 375		Pottery	TAM	ĭ	FB 6772	41EP01143 (F	10.02	62.51	0.9240	99.99	11.81	2.09	7.78 108.37	.37 7.37	7 44.37
EP066	Group-D	Loop 375		Pottery	TAM	ĭ	FB 6772	41EP01143 (F	8.45	69.65	1.2413	65.21	11.61	2.89 1	11.10 142.19	.19 61.	1 36.93
EP068	Group-D	El Paso Core		Pottery	TAM	ĭ	FB 6772	41EP01143 (F	5.87	80.65	0.6627	68.84	10.58	3.22	6.20 152.78	.78 8.93	3 40.22
EP070A	Group-D	El Paso Core		Pottery	TAM	ĭ	FB 6772	41EP01143 (F	6.84	72.79	0.6813	66.83	10.88	5.60	5.06 142.82	.82 9.18	8 38.07
EP071	Group-D	Loop 375		Pottery	TAM	ΤX	FB 6772	41EP01143 (F	7.46	29.80	1.4373	1 98.79	11.02	5.31 12	12.32 128.94	.94 6.92	2 37.50
EP073	Group-D	El Paso Core		Pottery	TAM	ĭ	FB 6772	41EP01143 (F	5.55	66.02	0.4293	66.24	8.95	4.70	3.72 115.60	.60 7.82	2 24.90
EP074	Group-D	El Paso-2	El Paso Brownware undif.	Pottery	TAM	ĭ	FB 6772	41EP01143 (F	6.29	87.16	0.5880	91.11	13.07	2.36	5.27 156.63	.63 12.44	4 63.35
EP075	Group-D	El Paso Core		Pottery	TAM	ĭ	FB 6772	41EP01143 (F	5.77	78.02	0.6813	82.20		3.19	5.56 178.20	.20 11.39	9 43.90
EP077	Gronp-D	El Paso Core		Pottery	TAM	TX	FB 9895	41EP02805	2.87	59.78	0.5040	61.37		2.10	4.07 112.83	.83 6.48	8 34.35
EP078	Gronp-D	El Paso Core		Pottery	TAM	XX	FB 9895	41EP02805	7.48		0.4947	73.40			4.60 136.29		1 29.1
EP079	Group-D	El Paso Core	El Paso Brownware	Pottery	TAM	TX	FB 9895	41EP02805	5.40	49.90	0.4387	64.70	8.19	1.95	3.79 105.21	.21 7.00	0 26.44
EP080	Gronp-D	Loop 375		Pottery	TAM	XX	FB 9788	41EP02724 (F	14.09		1.1013	84.22				.58 7.86	
EP084	Group-D	El Paso Core		Pottery	TAM	TX	FB 9895	41EP02805	8.39	50.84	0.4947	61.01				.83 6.68	8 29.69
EP085	Group-D	El Paso Core		Pottery	TAM	×	FB 9895	41EP02805	6.46		0.6253						
EP086	G-dno-D	Loop 375		Pottery	TAM	×	FB 9895	41EP02805	13.14	-+	1.2600				_		
EP08/	Group-D	El Paso Core		Pottery	I AM	×	FB 9835	41EP02//0 (F	16.1		0.5133	/0.18					
EP088	Group-D	El Paso Core		Pottery	TAM		FB 9835	41EP02770 (F	8.74		0.5413	66.57					
EP089	Group-D	El Paso Core		Pottery	TAM		FB 9835	41EP02770 (F	8.10		0.4947	63.92			_		
EP091A	Gronp-D	El Paso Core	undil.	Pottery	TAM	ĭ	FB 9835	41EP02770 (F	9.53		0.4480					_	
EP092	Group-D	Loop 375		Pottery	TAM	ĭ	FB 6884	41EP01664 (F	9.16	72.23	1.0547						
EP094	Group-D	Loop 375	undif.	Pottery	TAM	ĭ	FB 6884	41EP01664 (F	11.90		1.1107						
EP095	Group-D	Loop 375		Pottery	TAM	TX	FB 6884	41EP01664 (F	10.19	59.30	0.9893	58.35		3.65	8.38 104.90	.90 6.73	3 41.62
EP100	Group-D	Loop 375		Pottery	TAM	ĭ	FB 6884	41EP01664 (F	9.75	75.53	1.2693				10.99 128.91		
EP103	Group-D	Loop 375		Pottery	TAM		FB 6884	41EP01664 (F	10.80		1.3347			-			
EP110	Group-D	Loop 375		Pottery	TAM	ĭ	FB 6884	41EP01664 (F	11.72		0.9613	82.95		2.19	7.82 120.10		9 43.14
EP111	Group-D		El Paso Polychrome	Pottery	TAM	X	FB 6884	41EP01664 (F	8.04		1.1200				`		
EP112	Group-C2a		Mimbres B/W Style Indeter. Pott	Pottery	TAM	X	FB 6884	41EP01664	4.31							1	
EP113	Group-D	Loop 375	El Paso Polychrome	Pottery	TAM	X	FB 6884	41EP01664 (F	9.17	87.58	1.2507	112.58 1	17.35	2.96	9.45 186.70	.70 6.52	2 43.23

>	68.63	66.27	84.22	73.14	68.43	79.12	54.51	78.04	78.82	71.86	26.86	82.84	67.45	56.37	69.69	78.63	67.45	70.98	80.29	90.39	65.10	84.41	102.45	98.98	88.24	72.06	80.29	84.31	82.16	82.94	79.61	81.86	76.47	80.59	81.47	77.06	79.02	78.14	68.14	73.24	88.04	72.35	106.76	89 02
⊏	3175.3	2706.1	3512.7		2798.6	4837.5		4924.6	5286.1		2692.5	5374.4	5279.3	3459.4	3970.5			3209.7	4885.4	4161.5	3336.5	4856.4	4647.3 10			5207.1	5602.5				_							3502.1						07100
NA				~	_ /	1										_																												
	1 9110.1	3 10570.6	9318.9		10093.7	14448.7	14660.1	16002.4	5 17063.7	11192.2	16402.5	17370.9	17149.2	7 15789.1	11680.6	_		10749.6	13028.2	7 12612.5	11529.4	13325.9	10550.3	13267.8	`		_			_		-	.	,	_		_	8509.2	`	_		.		100100
MM	223.1	193.3	363.7		225.6	504.1	385.5	489.9	548.6	235.5	300.9	520.4	590.1	350.7	346.0	269.9		250.9	926.3	7.779	293.9	475.6	531.6	1051.0					537.7									252.5	253.9					217
~	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	
Dγ	13.285	17.987	961.6	9.873	11.947	796.9	6.231	6.164	9.700	3.431	5.381	6.289	5.629	5.916	9.404	9.481	10.637	12.033	7.541	7.187	11.698	5.534	8.783	7.751	966.9	6.757	5.228	11.211	6.002	7.034	13.686	5.820	6.040	6.872	6.805	12.530	13.791	10.828	14.489	15.531	12.128	12.233	5.476	15 204
CA	14726.8	14575.8	9537.5	8493.7	8638.9	17092.8	18156.6	15761.2	13708.5	11681.8	13457.0	14198.2	12456.2	17171.2	10933.6	7313.6	8732.2	11466.9	10299.8	6544.5	9283.9	12535.6	18671.7	10524.2	16010.4	16174.6	14479.4	11658.3	12325.6	14258.6	11150.7	16500.0	15403.7	19503.7					10713.9					15507 2
BA	1015.7	1839.0	1099.2	1374.2	1809.1	1896.0	1623.2	1305.2	1471.9	1057.8	1481.0	1356.6	1273.4	1532.4	1113.9	716.3	938.9	1252.5	9.798	8.956	1128.9	1160.6	1294.0	1211.8	950.4	1464.4	1370.1	951.5	1207.1	1096.2	3332.0	947.1	1290.4	1538.8	1337.0	1358.3	1165.5	1378.0	981.9	1113.3	1244.1	919.0	840.8	1010 E
AL	80806.1	81610.4	74911.5	74434.8	75638.2	87526.7	93079.7	85748.0	85093.1	84279.7	6.76777	86261.8	86290.6	83333.1	76993.8	76974.2	73734.0	77255.1	72609.8	73598.8	80163.9	87366.7	87213.0	72932.6	89637.7	84746.6	89736.0	84077.6			_	95701.4	92775.4	84841.5	90853.5	82684.6	86606.0	81587.4	88586.6	85832.1	87371.8	83578.2		7 0 6 6 7 6
ZR	393.6	303.8	392.9	374.1	424.0	279.1	333.9	419.5	427.1	316.8	280.1	540.9	428.7	298.3	321.8	425.7	481.3	429.4	551.5	539.3	400.3	301.2	292.0	501.3	299.2	324.2	325.4	362.0	365.8	369.6	378.9	383.4	390.4	267.0	276.0	327.5	391.4	363.2	372.5	389.4	354.7	256.9	261.3	7 7 7
NZ	9:59	72.1	70.2	78.6	72.2	72.2		72.7	71.9	22.0	66.5	71.8	73.2	73.8	71.2	6.67	72.1	74.0	92.4	0.06		75.5	89.7				76.3											77.5						7.0
王	20.55	26.22	18.37	18.95	20.92	19.31	19.80	19.00	18.16	24.13	16.23	19.47	18.83	25.94	16.80	22.44	16.36	29.15	23.75	27.27	24.16	23.54	26.32	24.87	20.72	23.19	18.66	21.60	20.71	20.89	29.33	23.11	20.78	19.97	21.38	20.46	24.74	20.18	31.05	22.28	20.27	20.65	11.69	10 00
TB	2.11	2.91	1.71	1.84	2.16	1.10	1.35	1.12	1.29	0.56	0.94	1.26	1.44	1.18	1.89	1.72	1.85	1.93	1.42	1.43	2.00	1.11	1.64	1.61	_	1.29	1.06				•		`			2.30	2.17	1.73	2.32	2.47	2.07			272
TA	2.3800	4.5700	2.1800	2.6800	2.5000	2.5900	2.7200	2.6400	2.5800	2.0500	2.1700	3.0500	2.7100	2.3100	2.5000	2.0100	2.1900	2.8800	3.6000	3.2900	3.5900	2.6500	2.9400	4.1800	2.7500	3.1700	2.2300	2.5500	2.9600	3.1800	3.1600	2.9400	2.5700	2.5500	2.7100	2.4800	3.1700	2.2000	2.8700	5.2900	2.2100	2.5800	1.1800	2 0800
SR	232.1	309.7	257.5	251.3	278.7	351.1	370.9	350.8	309.9	198.5	305.5	374.5	387.5	404.0	276.0	148.2	195.2	298.7	167.5	167.3		363.5	234.4	223.2	304.6	317.3	329.4	306.0	350.2	418.3	527.3	329.7	397.0	462.4	348.9			352.7	250.4	276.7	388.8	200.6		312 6
SC	9.04	8.74	89.8	8.41	8.93	9.93	8.56	9.32	9.95	7.51	7.41	9.74	10.19	7.84	60.6	9.48	9.20	9.14	8.28	7.61	9.37	10.38	13.91	8.35	10.07	10.31	9.74	11.12	8.90	8.72	10.64	10.97	99.6	9.43	9.07	10.10	9.90	10.17	9.03	9.27	10.49	8.94	12.23	0 03
SB	0.7765	0.6571	0.7680	0.7168	0.6571	0.5376	0.6912	0.4437	0.6229	0.6485	0.7595	0.4352	0.4181	0.6656	1.1861	0.8021	0.8192	0.7253	0.7851	0.8363	0.6059	0.7339	0.9472	0.6997	0.5632	0.4864	0.4096	0.7595	0.5632	0.6229	0.7595	0.6912	0.6315	0.6741	0.6485	0.6059	0.5205	0.6741	0.5632	0.6741	0.8192	0.6485	0.6144	0.8031
RB	124.20	144.90	127.80	125.50	160.80	114.00	151.60	125.20	123.40	102.60	124.20	134.50	139.80	146.50	137.90	143.10	137.90	141.80	144.50	129.00	154.60	102.20	136.40	142.10	122.90	115.30	128.80	143.50	127.50	120.20	155.20	133.00	123.50	106.90	121.10	146.10	153.70	132.80	180.70	136.90	119.10	169.70	112.10	132 20
Z	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0		0.0	0.0											0.0	0.0					
生	14.81	10.74	14.71	13.56	15.17	9.14	10.54	12.47	13.26	6.56	9.72	15.26	13.10	10.45	12.13	14.61	14.84	16.83	17.53	19.09	20.49	10.22	9.72	18.06	10.72		11.51	15.82			15.48	13.33	13.77	10.76	8.88	12.01	16.16	16.20	16.52	14.44	13.86	10.81	9.26	17 01
H	35029.3	33502.7	34947.9	36019.6	36103.7	41141.4	36295.3	38536.3	42738.4	31711.0	32024.8	41216.6	43156.7	34443.0	35888.1	37141.7	37205.4	37042.3	38537.6	1.4605 35981.7	1.2419 36746.4	40885.3	45567.8	38711.4	41267.4	42251.6	41741.2	43734.2			44802.2	43413.4			40992.3	40483.0	43076.1	40348.8		37028.6	41461.3	35228.1	1.4903 39916.5	2 0864 25300 4
EN	1.4306	1.6194	1.3214		1.3412	1.8380			1.9771	0.9538	1.6492		2.1758	1.7684	1.8976		1.5995	1.2021	1.5300	.4605	.2419	1.8976	2.1460				1.8479		1.5896	1.7486								1.3015				1.2518	.4903	1700
SS	5.24	4.16	4.35	4.38	4.12	3.71			3.55 1	3.28 0	3.67	4.04	4.66	4.15 1	5.10 1	6.34	5.47	4.18	5.65	4.92		3.82	7.97			3.76 2	4.14											5.26						7 70
ANID	EP040	EP041	EP042	EP043	EP044	EP045	EP046	EP049	EP052	EP053	EP056	EP057	EP058	EP059	EP062	EP063	EP065	EP066	EP068	EP070A	EP071	EP073	EP074	EP075	EP077	EP078	EP079	EP080	EP084	EP085	EP086	EP087	EP088	EP089	EP091A	EP092	EP094	EP095	EP100	EP103	EP110	EP111	EP112	FD113

ANID	macro_grp	macro_grp Chem2012	CERAMIC TYPE	MATERIAL	SOURCE	E STATE	SITE_NAME	SITE_NO	AS	ΓA	n	ND	SM	U YB	B CE	00	CR
EP114	G-dno-D	El Paso Core	El Paso Brownware undif.	Pottery	TAM	X	FB 9788	41EP02724 (F	8.05	70.53 0.	0.6627	80.39 10	10.79 3.0	3.65 4.77	7 126.65	69.9	37.21
EP115	Group-D	El Paso Core	El Paso Brownware undif.	Pottery	TAM	X	FB 9788	41EP02724 (F	6.37	50.71 0.	0.4573	38.25 6	6.71 2.	71 3.15		6.44	25.10
EP116	Gronp-D	El Paso Core	El Paso Brownware undif.	Pottery	TAM	XX	FB 9788	41EP02724 (F	91.9		0.4760	29.08	7.64 3.0	3.06 3.24	4 96.30	7.35	28.32
EP118	Group-D	Loop 375	El Paso Polychrome	Pottery	TAM	X	FB 9788	41EP02724 (F	10.57	58.51 0.	0.9613	75.27 10	10.83 3.01	99'8 10	68.76 9	60'9	38.86
EP119	Group-D	El Paso Core		Pottery	TAM	X	FB 9788	41EP02724 (F	5.36			1	1.35 3.7	70 5.94			33.25
EP120	Group-D	El Paso-2	El Paso Brownware undif.	Pottery	TAM	X	FB 9788	41EP02724 (F	00.9	55.71 0.	0.4573		8.09 3.8	3.82 3.18	8 114.16	9.24	45.32
EP121	Group-D	Loop 375	El Paso Polychrome	Pottery	TAM	×	FB 9788	41EP02724 (F	11.69	65.68 1.	1.1200 8	84.62 13	13.29 3.2	3.26 9.92	2 140.05	7.12	44.02
EP122	Group-D	Loop 375		Pottery	TAM	×	FB 9788	41EP02724 (F	8.21					_			35.09
EP123	Group-D	Loop 375		Pottery	TAM	X	FB 9788	41EP02724 (F	90.6	68.03 1.	1.2880		14.94 2.21	21 11.22			35.69
EP124	Group-D	Loop 375	El Paso Polychrome	Pottery	TAM	X	FB 9788	41EP02724 (F	10.33	67.78 1.	1.3160	94.09 15	15.30 3.8	3.83 12.11			34.58
EP126	Group-D	Loop 375	El Paso Polychrome	Pottery	TAM	X	FB 9788	41EP02724 (F	6.59	76.16 1.	1.1573 9	98.00 14.31		3.32 9.47	7 135.48	06.9	36.44
EP127	G-dno-D	Loop 375	El Paso Brownware undif.	Pottery	TAM	ĭ	FB 9788	41EP02724 (F	60.6	82.07 1.	1.3813	99.29 16	16.53 2.	2.19 11.33	3 120.32	7.70	40.64
EP128	Group-D	Loop 375	El Paso Polychrome	Pottery	TAM	X	FB 9788	41EP02724 (F	8.59	59.42 1.	1.0640 7	79.04 12	12.70 3.27	27 9.60	0 114.03	59.45	35.52
EP129	G-dno-D	Loop 375	El Paso Brownware undif.	Pottery	TAM	ĭ	FB 9788	41EP02724 (F	6.50	79.40 1.	1.3160 10	106.15 15	15.60 3.8	3.84 10.75	5 122.49	7.39	40.28
EP130	Group-D	Loop 375	El Paso Polychrome	Pottery	TAM	X	FB 9788	41EP02724 (F	6.26	89.94 1.	1.4560 11	111.13 17.	17.31 2.8	2.85 12.04	4 131.87	8.06	38.63
EP131	Group-D	Loop 375	El Paso Polychrome	Pottery	TAM	X	FB 9788	41EP02724 (F	8.73	81.17 1.	1.3347		16.00 2.5	2.54 11.92	2 124.49	7.62	37.95
EP132	Group-D	Loop 375	El Paso Brownware undif.	Pottery	TAM	X	FB 9788	41EP02724 (F	1 07.9	150.80 1.	1.3533 13	133.69 19	19.20 2.6	2.62 11.26	6 237.64	7.36	48.22
EP134	Group-D	El Paso Core	El Paso Brownware undif.	Pottery	TAM	ĭ	FB 9788	41EP02724 (F	5.26	76.39 0.	0.7373	55.81	11.58 3.9	3.90 5.60	0 135.31	19.9	35.83
EP135	Group-D	Loop 375	El Paso Brownware undif.	Pottery	TAM	ĭ	FB 9788	41EP02724 (F	7.16	95.35 1.	1.4653	99.51 18	18.86 4.7	4.18 12.01	1 117.93	7.51	36.95
EP137	G-dnoJ9	Loop 375	El Paso Polychrome	Pottery	TAM	ĭ	FB 9788	41EP02724 (F	6.51	84.93 1.	1.5213	76.43 16	16.83 3.9	3.92 12.41	1 123.85	8.16	40.34
EP138	Group-D	Loop 375	El Paso Polychrome	Pottery	TAM	ĭ	FB 9788	41EP02724 (F	11.82	73.12 1.	1.3533	90.93 15.7		3.38 11.43	3 119.12	19.9	36.89
EP140	G-dnoJ9	Loop 375	El Paso Polychrome	Pottery	TAM	ĭ	FB 9788	41EP02724 (F	8.30	82.06 1.	1.1947	71.95 15	15.38 3.2	3.23 11.63	3 137.09	6.94	36.71
EP143	Group-D	Loop 375	El Paso Polychrome	Pottery	TAM	ĭ	FB 9788	41EP02724 (F	11.91	73.80 0.	0.9800	77.22 14	14.70 2.8	2.88 9.43	3 108.79		45.98
EP144	G-dno-D	Loop 375		Pottery	TAM	ĭ	FB 9788	41EP02724 (F	6.19		1.1480		13.13 3.5	3.53 9.58	8 107.40	5.70	37.80
EP145	Gronp-D	Loop 375	El Paso Brownware undif.	Pottery	TAM	ΤX	FB 9788	41EP02724 (F	8.79	89.57 1.	1.2787 8		17.99 3.3	3.35 12.00	0 124.51	8.18	38.33
EP146	Gronp-D	El Paso Core		Pottery	TAM	XX	FB 9788	41EP02724 (F	8.07	72.08 0.			11.00 3.0	3.03 5.02	2 130.55		29.41
EP147	Gronp-D	Loop 375		Pottery	TAM	ΤX	FB 9788	41EP02724 (F	10.92	-			10.95 3.3	3.35 9.23		6.58	41.65
EP148	Gronp-D	Loop 375		Pottery	TAM	TX	FB 9788	41EP02724 (F	10.85				13.37 3.2	3.20 9.14	1	6.73	39.49
EP150	Gronp-D	Loop 375	El Paso Brownware undif.	Pottery	TAM	TX	FB 9788	41EP02724 (F	10.04		0.9427	53.94 11	11.40 3.0	3.08 8.33	3 97.38	6.19	41.61
EP151	Group-D	Loop 375	El Paso Brownware undif.	Pottery	TAM	ĭ	FB 9788	41EP02724 (F	10.86	58.98 0.	0.9613 (60.70	11.55 3.0	3.05 8.74	4 103.05	7.47	46.94
EP152	Group-D	Loop 375		Pottery	TAM	ĭ	FB 9788	41EP02724 (F	11.84				10.45 3.41		_		45.73
EP153	Group-D	El Paso Core	undif.	Pottery	TAM	×	FB 9788	41EP02724 (F	4.12				9.74 2.	71 4.12			25.32
EP154	Group-D	Loop 375		Pottery	TAM	ĭ	FB 9788	41EP02724 (F	11.49					4.19 8.91			42.79
EP155	Group-D	El Paso Core	El Paso Polychrome	Pottery	TAM	X	FB 9788	41EP02724 (F	3.88	73.81 0.	0.7187 (62.54 10	10.43 3.0	3.66 5.46	6 128.71	6.38	38.85
HM001	Group-B1	Mimbres-04A		Pottery	TAM	NM	NAN	LA 002465	1.55	49.64 0.	0.4550		6.82 5.3	5.36 3.50	0 100.61	4.58	22.17
HM002	Group-B1	Mimbres-04A		Pottery	TAM	NM	NAN	LA 002465	2.16	42.23 0.	0.3727	35.60 5		9.75 2.41			19.48
HM003	Group-B1	Mimbres-04A		Pottery	TAM	NM	NAN	LA 002465	2.58		0.4277		6.51 6.0	6.63 3.38		3.95	19.73
HM004	Group-B1	Mimbres-04A	Mimbres B/W Style III	Pottery	TAM	N	NAN	LA 002465	2.23	49.76 0.	0.4566	42.01 6	6.84 6.9	6.94 3.61	1 99.36	4.49	23.37
HM005	Group-B2	Mimbres-08	Mimbres Polychrome	Pottery	TAM	N	NAN	LA 002465	2.65	35.73 0.	0.3800	24.03 3	3.75 5.5	5.59 2.14	4 63.35	4.36	26.27
900MH	Group-B1	Mimbres-04A		Pottery	TAM	NM	NAN	LA 002465	2.09	48.21 0.	0.4744		6.69 5.14			4.49	22.52
HM007	Group-B	Unas.		Pottery	TAM	NM	NAN	LA 002465	2.62	47.42 0.	0.4617	38.00 6	6.33 9.63	63 3.29	9 95.84	4.65	38.10
HM008	Group-B	Unas.		Pottery	TAM	M	NAN	LA 002465	2.51				4.62 4.30				26.87
HW009	Group-A	Mimbres-03		Pottery	TAM	NM	NAN	LA 002465	3.24				10.11 5.8			1.83	10.22
HM010	Group-B2	Mimbres-08	Mimbres B/W Style III	Pottery	TAM	MN	NAN	LA 002465	1.45	33.65 0.	0.3814	24.50 3	3.37 4.9	4.99 2.09	9 54.80	2.66	20.57

>	83.53	60.59	88.24	84.80	75.78	79.61	93.33	91.96	74.41	83.24	71.86	75.00	75.10	75.78	68.63	81.76	67.65	80.29	78.24	73.43	78.14	71.27	88.24	72.84		88.73		84.31			94.22	86.27			41.84	40.30	42.45	34.46		47.60		21.12
I	3750.6	4666.0	6322.4		4562.2	4320.4	3913.7	4674.5	3312.7	3572.9	3889.9	3894.3	3639.2	3388.4	3191.8		3187.4	4578.4	3167.4	3094.1		2783.0	3365.3	2841.1				3447.4					4681.5			2788.8	2819.5	2382.1		2492.9		7 000
NA	10625.7	22815.8	15916.5	9984.1	13803.0	12875.3	8616.8	13475.1	11350.8	11375.1	10347.4	10346.3	10692.1	11426.1	10817.3	11480.9	12488.1	16525.6	9874.0	11017.1	11977.6	10749.2	10190.0	11558.0	10247.4	13339.4	9274.2	9285.0	9043.2	8284.1	19857.9	9311.1	11880.1	13640.0	14957.5	14765.7	14435.8	9209.9	13862.9	14115.5	11357.3	0,00
MN	305.8	541.1	520.6		269.7	328.7	293.8	411.2	276.0	268.8	262.0	310.5	291.2	253.7	244.5			286.0	269.7	274.3	279.5	247.6	276.3	230.7				244.4				270.1		182.0		194.1	176.2	247.4	185.2	189.6	344.1	
~	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	26027.0	30159.6	26711.8	24897.7	33409.2	32487.1	23546.5	24589.6	0100
DY	8.898	4.970	4.769	11.220	8.774	5.706	13.504	12.558	15.588	15.062	13.801	17.394	13.428	16.343	16.601	15.034	15.005	8.468	16.840	14.795	13.973	15.053	13.380	12.702	_	6.872	10.781	12.014	11 631	10.188	6.002	10.379	7.837	4.653	3.840	4.137	5.082	2.558	5.126	4.083	3.587	
CA	14717.7	4195.1	17415.0	12427.5	13349.6	13372.8	14584.6	11954.1	14514.1	12651.8	13851.1	15311.9	13344.8	14068.8	13202.5	11176.9	13174.1	12694.1	15118.9	11369.7	8781.9	14287.1	12795.6	12193.8	12930.5	16484.7	10712.9	12103.8	10061 B	11511.6	17021.8	10907.2	11801.6	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	
BA	1723.4	902.4	1187.6	863.3	1103.4	1134.9	1442.1	870.1	895.5	1085.2	1144.7	1085.2	1013.6	1117.4	1107.9	895.5	1024.6	963.1	992.5	93.6	985.5	1289.3	1402.3	1165.4	985.4	1315.7	1207.8	1140.9	870.8	1044.0	1040.1	934.2	1041.3	823.1	868.1	861.0	826.3	535.3	781.7	823.8	824.4	
AL	89598.6	86143.8	86247.0	87734.0	79640.7	84223.0	89244.5	82859.5	85855.0	89249.7	81530.7	85693.8	91409.8	85938.7	79179.7	83237.8	79398.1	73842.8	79011.4	76936.4	82489.3	79490.6	86361.9	83062.9	81965.8	92029.8	81252.9	85143.7	863123	86025.1	89794.3	87624.1	71655.6	79616.1	78809.3	81165.7	79449.5	70141.0	82459.1	78019.1	81215.8	
ZR	285.5	455.7	327.6	250.0	376.2	258.3	364.3	713.2	326.4	308.5	286.3	337.8	290.4	453.9	316.0	508.4	424.8	502.8	383.7	578.0	2.695	381.4	400.4	515.2				314.2				431.4	520.4	133.1		103.9	158.6	128.1	187.8	151.1		
NZ	84.3	77.5	6.89		79.0	58.3			79.3	80.4	78.4	77.7	9.6/	82.8	9.08	80.4		82.1	73.7	85.1	78.1	69.7	78.2					77.0		62	64.7		88.6	62.3				38.5	58.2	59.1		
TH.	9 26.97	3 15.17	1 22.34	3 21.86		5 24.99	9 26.03	3 23.95	5 21.45	3 22.71	2 18.80		7 21.37	7 22.80	1 21.73			1 22.62		1 22.52		9 20.90	19.10	5 22.03				18.81	_	_	7 19.18	3 26.69					19.28	3 28.04		3 20.92		-
TA TB	00 1.39	0.83	0.94	1.68	00 1.49	0.95	00 2.19	1.99	30 2.45	00 2.63	2.52	2.81	2.07	77.7	3.04	00 2.53	2.71	1.41	77.7	00 2.61	00 2.21	00 2.39	2.31	30 2.06	• •			1.81	٠.		_	00 1.88	00 1.43	95 0.93	77 0.77	0.89	28 1.00	52 0.48	55 1.02	51 0.93		
	2 3.3800	4 3.5700	2 2.9800	2 3.0400	1 3.3900	3 2.2400	6 2.4800	4 3.3000	0 2.8100	0 3.5300	6 2.3700	2 2.5400	9 2.5300	5 2.4900	8 2.7000	6 4.1800	0 2.1600	3.4400	6 2.1500	2 4.1300	1 2.6800	9 2.3600	4 2.4300	1 2.6200				2 2.0600	_		3.1000	5 2.8800	7 3.2200	8 1.3295		3 1.3807	8 1.2628	7 1.4662	5 1.1855	1.3861	'	
SR	403.2	286.4	413.2		352.1	230.3	321.6	213.4	295.0	334.0	296.6	261.2	511.9	390.5	276.8		370.0	421.9	390.6	200.2	386.1	331.9	273.4	336.1				205.2			378.4	167.5	236.7	285.8		325.3	233.8	143.7	313.5	318.6	232.5	
SC	9.27	6.15	9.76	10.03	7.92	6.65	11.02		9.58	9.85		9.92	9.83	9.46	9.52	_	9.31	8.12	9.34	16.6		8.85	10.64	6.63			_	9.97			9.47	10.91	8.00	7.48	7.05		7.51	5.59	7.21	8.02		
SB	0.8960	0.6741	0.5632	0.7765	0.6741	0.6827	0.8619	0.7936	0.6229	0.6997	0.7595	0.9728	0.6741	0.8363	0.8107	0.8448	1.0069	0.7168	0.8533	0.8448	0.8363	0.7083	0.7168	0.8619	0.7339	0.8107	0.7509	0.8192	0.7043	0.7851	0.4608	0.8533	0.5717	0.5071	0.2952	0.4463	0.4255	0.5527	0.4215	0.3299	0.5531	
RB	162.40	102.60	102.10	135.90	113.20	110.00	124.00	126.50	142.30	141.30	131.70	134.70	144.20	145.10	148.60	128.20	143.50	132.80	116.60	139.50	123.70	136.00	147.20	149.40	131.50	116.70	132.80	123.90	164 30	129.30	125.50	148.90	125.60	140.83	141.76	141.39	137.83	201.28	135.04	142.52	146.72	
Z	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0				0.0				0.0	0.0	0.0		0.0	0.0	0.0	0.0	0.0	0.0	
生	12.03	16.20	12.94	13.42	15.44	10.44		38.81	15.59	14.07	12.01	15.06	13.15	17.37	13.44			15.23	11.72	18.86	18.14	14.95	15.42					14.98			10.56	16.59	16.81	6.41	61.7	5.32	7.04	6.44	8.47	8.52	8.15	1
FE	38399.1	30493.3	45572.4	39329.8		33565.3			40165.7	41806.0	35063.5	38007.7	41563.7	37006.8	36811.7	43428.6	36672.4	32289.5	36099.7	38219.6	40347.0	35216.3	41516.5	39186.3			41426.0	39939.8			45203.0	1.4605 43421.3		22375.7		19520.5	21913.6	18953.7	21215.5	22516.1		
EU	1.7188	1.5101	1.5697	1.2916	1.6592	1.2319	1.6592	1.8082	1.5995	1.6592	1.6492	1.8678	1.5697	1.8579	1.9373	1.6890	1.8479	1.5896	2.0168	1.8777	1.6393	1.5598	1.8777	1.4903	1.9373	1.9671	1.3313	1.6790	1 5002	1.3710	2.0665	1.4605		1.4348	1.2124	1.3939	1.4829	0.7058	1.4561	1.4631	1.0386	
CS	09.9	4.03	3.42	4.95	4.48	4.92		5.31	4.87	5.25		4.75	4.74	4.94	4.93	5.39	4.41	4.23	5.03	5.03	4.79	4.13	4.78	4.96		_		4.65			_	6.77					4.97	9.90	4.20	4.64		
ANID	EP114	EP115	EP116	EP118	EP119	EP120	EP121	EP122	EP123	EP124	EP126	EP127	EP128	EP129	EP130	EP131	EP132	EP134	EP135	EP137	EP138	EP140	EP143	EP144	EP145	EP146	EP147	EP148	FP151	EP152	EP153	EP154	EP155	HM001	HM002	HM003	HM004	HM005	900MH	HM007	HM008	0000

ANID	macro_grp	Chem2012	CERAMIC TYPE	MATERIAL	SOURCE	STATE SITE_NAME	SITE_NO	AS	LA	Π	ND	SM	Π	YB C	CE CO	CR
HM011	Group-B1	Mimbres-04A	Mimbres B/W Style III	Pottery	TAM	M NAN	LA 002465	2.88	40.21	0.4073	37.03	5.90	5.40 2.	2.65 70.98	98 6.21	1 26.49
HM012	Group-B1	Mimbres-04A	Mimbres B/W Style III	Pottery	TAM	NAN NAN	LA 002465	2.31	47.84 (0.5083	41.59	6.28	7.62 3.	3.01 78.72	72 6.04	4 27.67
HM013	Group-B2	Mimbres-11	Mimbres Polychrome	Pottery	TAM	NAN NAN	LA 002465	2.88	35.61 (0.4133	29.81	4.69	4.96 3.	3.22 72.15	17.61	1 43.06
HM014	Group-B2	Mimbres-02A	Mimbres Polychrome	Pottery	TAM	NAN NAN	LA 002465	0.00	42.90	0.4635		6.41	4.06 3.	3.23 76.73	73 5.68	8 35.4
HM015	Group-B2	Mimbres-11	Mimbres Polychrome	Pottery	TAM	NAN NAN	LA 002465	3.37	34.34 (0.4461	28.56	4.63	4.21 2.	2.84 71.54	54 16.35	5 43.92
HM016	Group-B	Unas.	Mimbres B/W Style III	Pottery	TAM NM	M NAN	LA 002465	2.26	44.24 (0.4429	41.37	6.18	6.22 2.	2.79 82.12	12 4.30	18.96
HM017	Group-B1	Mimbres-04A	Mimbres B/W Style III	Pottery		NAN NAN	LA 002465	2.35	50.73 (0.4858	37.47	7.01	5.23 3.	3.45 91.48	Ξ,	
HM018	Group-B2	Mimbres-02A	Mimbres B/W Style III	Pottery		NAN NAN	LA 002465	1.49	46.31	0.5089	28.98	7 90.9		3.12 70.31		3 32.30
HM019	Group-B	Unas.	Mimbres B/W Style III	Pottery	TAM NM	M NAN	LA 002465	1.23	20.97	0.4898	39.76	7.08	5.34 3.	3.36 92.20	20 4.20	0 45.94
HM020	Group-B1	Mimbres-04B	Mimbres B/W Style III	Pottery	TAM	NM Elk Ridge	LA 078963	2.05	44.46 (0.4456	30.39	5.43	5.61 2.	2.64 74.45	15 3.15	5 24.2
HM021	Group-A	Mimbres-01	Mimbres B/W Style III	Pottery	TAM NM	M Elk Ridge	LA 078963	1.34	45.89 (0.4783	34.72	3.66 10	10.81 2.	2.24 68.35	35 1.37	7 8.75
HM022	Group-B2	Mimbres-08	Mimbres B/W Style III	Pottery	TAM	NM Elk Ridge	LA 078963	2.18	34.67 (0.3696	26.49	3.72	4.88 2.	2.07 55.25	25 3.09	9 23.1
HM024	Group-C2a	Mimbres-42	Mimbres B/W Style III	Pottery	TAM N	NM Elk Ridge	LA 078963	2.28	40.04	0.3188	27.95	5.92	2.53 2.	2.23 72.00	16.41	1 56.08
HM025	Group-B1	Mimbres-04B	Mimbres B/W Style III	Pottery	TAM NM	M Elk Ridge	LA 078963	1.95	50.40	0.5052	43.04	99.9	6.37 3.		99.5 97	9 25.96
HM026	Group-B1	Mimbres-04A	Mimbres B/W Style III	Pottery	TAM N	NM Elk Ridge	LA 078963	2.25		0.4275	36.72	5.89	3.83 2.	2.88 77.39	96.56	6 27.32
HM027	Group-B1	Mimbres-04A	Mimbres B/W Style III	Pottery	TAM N	NM Elk Ridge	LA 078963	1.94					4.14 4.	4.02 92.12	12 7.05	5 27.74
HM028	Group-A	Mimbres-10	Mimbres B/W Style III	Pottery	TAM	NM Elk Ridge	LA 078963	3.94	96.92	1.0536	83.39	14.76	4.62 8.	8.69 161.61	51 5.65	5 30.2
HM029	Group-B1	Mimbres-04C	Mimbres B/W Style III	Pottery	TAM	NM Elk Ridge	LA 078963	2.19	32.96 (0.3825	33.00	5.48	2.95 2.	2.71 67.60	50 4.38	8 31.18
HM030	Group-B	Unas.	Mimbres B/W Style III	Pottery	TAM	NM Elk Ridge	LA 078963	2.07	39.32	0.3643	33.70	4.68	2.85 2.	2.62 78.19	19 7.13	3 41.93
HM031	Group-B1	Mimbres-04B	Mimbres B/W Style III	Pottery	TAM N	NM Elk Ridge	LA 078963	2.12	50.16	0.4579		7.31	5.49 3.	3.01 96.57		3 29.3
HM032	Group-B1	Mimbres-04A	Mimbres B/W Style III	Pottery	TAM N	NM Elk Ridge	LA 078963	1.99	20.50	0.4712		7.26	3.93 3.	3.26 95.10	10 4.55	
HM033	Group-B	Unas.	Mimbres B/W Style III	Pottery	TAM N	NM Elk Ridge	LA 078963	1.52	42.43 (0.4992	37.46	6.74	3.74 3.	3.40 75.63	53 5.45	5 39.94
HM034	Group-B2	Mimbres-08	Mimbres B/W Style III	Pottery	TAM N	NM Elk Ridge	LA 078963	2.79	34.43 (0.3874		3.43	4.65 2.	2.28 64.57	57 4.19	9 23.88
HM035	Group-B2	Mimbres-02A	Mimbres B/W Style III	Pottery	TAM	NM Elk Ridge	LA 078963	2.27		0.4315	28.14	4.43	4.22 2.	2.73 62.22	22 3.94	
HM036	Group-C2	Unas.	Mimbres B/W Style III	Pottery	TAM NM		LA 078963	0.85	37.55 (0.3368		6.22	1.12 2.	2.57 86.67	57 14.96	
HM037	Group-C2	Unas.	Mimbres B/W Style III	Pottery	TAM	NM Elk Ridge	LA 078963	2.07			38.37	7.11	2.36 2.	2.57 91.07	70.8 70	7 59.41
HM038	Group-B1	Mimbres-09	Mimbres B/W Style III	Pottery	TAM	NM Elk Ridge	LA 078963	1.51	62.88	0.5461	68.58 1		4.01 3.	3.97 135.60	50 2.62	2 23.7
HM039	Group-B1	Mimbres-04A	Mimbres B/W Style III	Pottery			LA 078963	4.71				~		1		
HM040	Group-C1	Mimbres-21	Mimbres B/W Style III	Pottery	TAM	NM Elk Ridge	LA 078963	2.84				5.71 (0.80 2.	2.37 77.85	_	
HM041	Group-B1	Mimbres-04A	Mimbres B/W Style III	Pottery			LA 078963	1.44			_					
HM042	Group-C1	Mimbres-21	Mimbres B/W Style III	Pottery			LA 078963	2.00							`	_
HM043	Group-C2a	Mimbres-49A	Mimbres B/W Style III	Pottery			LA 078963	2.80							_	
HM044	Group-B1	Mimbres-04A	Mimbres B/W Style III	Pottery			LA 078963	4.08								
HM045	Group-C1	Mimbres-21	Mimbres B/W Style III	Pottery			LA 078963	1.61								
HM046	Group-C2a	Mimbres-49A	Mimbres B/W Style III	Pottery			LA 078963	2.28							1	ц)
HM047	Group-A	Mimbres-01	Mimbres B/W Style III	Pottery			LA 078963	1.44				`	12.93 4.	_		
HM048	Group-B2	Mimbres-02A	Mimbres B/W Style III	Pottery			LA 078963	1.49								
HM049	Group-B	Unas.	Mimbres B/W Style III	Pottery	TAM	NM Elk Ridge	LA 078963	1.77	49.64 (0.5561			10.12 3.	3.04 96.02		5 27.66
HM050	Group-B2	Mimbres-02A	Mimbres B/W Style III	Pottery		NM Elk Ridge	LA 078963	1.83		0.4538	33.79	5.23	5.87 3.	3.00 70.54	54 4.98	8 40.28
HM051	Group-A	Mimbres-03	Mimbres B/W Style III	Pottery			LA 078963	2.06	47.20	1.2369	56.92	2.28	6.66 9.	9.55 102.42	12 2.19	9 15.1
HM052	Group-B1	Mimbres-04A	Mimbres B/W Style III	Pottery	TAM		LA 078963	1.56	47.37 (0.4660	39.42	7.32	5.24 3.	3.45 87.24		
HM053	Group-B2	Mimbres-11	Mimbres B/W Style III	Pottery			LA 078963	2.43								
HM054	Group-A	Mimbres-01	Mimbres B/W Style III	Pottery			LA 078963	2.43	_			1				
HM055	Group-A	Mimbres-03	Mimbres B/W Style III	Pottery	TAM	NM Elk Ridge	LA 078963	1.84	48.96	1.3458	51.86	13.01	8.52 10.	10.71 114.40	10 2.10	0 12.28

^		5 49.59		_	69.99	40.79	37.90	62.00	9 49.39	37.13	9 26.28	36.49	9 7.83	41.99	3 45.60			58.54	49.08	5 60.84	3 40.92	2 69.82	38.54			_					102.28					2 64.59	7 42.86	3 56.12	3 15.72			22 51
7 T	3 3254.6	3 3239.5		9 2892.7	3159.0) 2275.1	3 2787.5	2 3027.1				1 2620.5	4616.9	2 2455.6	5 3583.8			3306.2	1901.0	3 2721.2	5 2829.3	3294.2	3 2781.1								3 2/15.9					9 2992.2	7 1731.7	7 3088.8	2 1198.8	3 2698.6		14847
NA	8 12735.3	0 12959.8	`		2 10440.0	9 15822.0	6 15342.8	13384.2	4 15214.2	1 15706.9	5 12876.2	11031.1	5 20375.4	0 10331.2	414089.6		9 13333.7	5 15656.2	7 6674.9	7 9781.3	8 15028.6	5 11664.0	3 8846.8	6 12212.2	٠,			. 1.		,	7 110002	١,				2 14456.9	1 12705.7	9 10301.7	6 6574.2	3 15817.3		1 15050 0
M	.2 368.8	.5 338.0		0.0	.1 1183.2	.7 189.9	.1 220.6	.5 439.6	.7 198.4	.7 194.1	.9 159.5	7 180.6	.8 719.5	.6 591.0	.4 358.6		.3 507.9	.5 190.5	.0 724.7	.5 269.7	.7 214.8	.5 254.5	.6 196.3	.5 239.6						,	1 440.7	-				.8 309.2	.0 761.1	.0 188.9	.3 501.6	.9 530.3		7 336 /
	1 23416.2	9 21811.5	3 26634.0		3 25259.1	1 22638.7) 25453.1	3 26359.5	5 25892.7	38322.7	5 40117.9	3 31840.7	3 26538.8	26259.6	1 26118.4		1 29558.3	30371.5	0.0	9 25726.5	3 25491.7	1 23934.5	33199.6						- 1		30010.5	-		1		30054.8	1 28990.0	7 35025.0	4 60183.3	31610.9		10401
CA DY	0.0 3.884	0 4.319			0.0 3.398	0.0 3.714	0.0 5.120	0.0 5.063	0.0 5.186	0.0 3.740	0.0 2.346	0.0 3.068	0.0 3.733	0.0 5.202	0.0 4.194	0.0 5.186	l	0.0 3.878	0.0 3.230	0.0 4.709	0.0 3.933	0.0 5.611	0.0 2.951	0.0							0.0 3.558					0.0 4.006	0.0 3.501	0.0 4.457	0.0 12.454	0.0 5.175		0000
		0										0				0												0														
BA	770.6	662.7			597.4	874.2	793.8	524.2	743.6	639.4	419.0	504.1	1031.5	585.6	762.5	745.7		829.2	500.2	605.0	735.0	597.0	532.2	453.2			_				819.4					655.5	558.5	517.4	199.8	867.4		E117
AL	84733.3	81848.6			82374.0	75233.1	84471.1	80313.7	90128.6	86380.5	106462.0	75162.4	106281.5	830068	83701.2			85775.0	9′16262	95791.5	8.86608	90827.8	76360.6		L		_				105407				112161.3	9.59698	71413.0	81625.2	72786.8		79718.2	2 0000
V ZR	2 204.1	.6 260.0		7 212.3	3 181.6	3 250.6	9 144.2	4 188.6	6 158.7		5 182.7	6 194.9	3 146.7	3 209.5	5 282.0	2 228.4	1 221.5	0 213.2	2 134.2	9 210.2	4 176.6	6 179.7	8 236.9						6	2	3 1/8./					2 189.2	7 216.0	9 299.3	8 235.6	2 279.9		1 207 1
NZ H	9 62.2	82	0 53.7		,6 58.3	14 54.3	9 51.9	5 48.4	9 21.6	3 47.0	7 41.5	34.6	3 90.3	.6 58.3	2 48.5	6 57.2	4 62.1	0.09 80	7.7 67.2	8 57.9	0 58.4	9765 00	38.8	9 38.3					C)		122.0					3 55.2	1 58.7	5 52.9	9.58 6	1 50.2		M AE 7
TB T	0.65 19.89	0.83 21.25	0.60 18.10	0.79 20.52	0.62 17.76	0.83 28.84	0.89 17.89	.79 19.45	0.89 17.99	0.67 24.33	0.37 48.37	0.43 24.04	0.74 8.73	0.83 25.26	0.71 20.22	0.99 18.46	2.22 28.84	0.68 16.08	0.60 24.72	0.86 26.48	0.96 18.80	0.83 17.00	0.41 28.53	0.56 20.39	0.68 8.72			_	_	1	0.63 9.61			1	0.85 51.53	0.77 19.43	0.81 29.61	0.80 22.85	2.52 38.49	1.09 16.91		0 54 50 04
TA	1.2066 0	1.3332 0			1.3497 0	1.1612 0	1.2537 0	1.3801 0	1.2837 0	1.5034 0	2.4094 0	1.4957 0	0.6872 0	1.5833 0	1.5045 0	1.3450 0	2.0578 2.	1.2602 0	1.6182 0	1.8077 0	1.3757 0	1.3275 0	1.7471 0	1.7324 0							0.7504 0					1.3923 0	1.6960 0	1.5863 0	2.4930 2	1.3706 1	1.5298 0	C773
SR	231.8 1	175.1		234.3 1	217.5	285.8 1	265.7 1	329.2	275.3 1		135.7 2	161.1	600.5 0	147.8 1	209.4			289.2	305.2	152.6	224.1	291.8	122.9	183.0					_		3/3.5 0					316.1		254.8 1	0.0	284.3 1		107 6
SC	7.61		7.50	9.47	8.00	6.43	7.04	8.30	7.10	6.22	3.95	5.14	13.86	7.58	7.01	90.8	8.12	8.70	8.74	8.40	7.47	11.74	5.75				_	8.04		-	12 50			_		10.43	8.26	11.09	5.72	7.44		7 17
SB	0.5219	0.5677	0.7188	0.6708	0.8761	0.4017	0.3916	0.4023	0.3817	0.5404	0.6262	0.5208	0.3867	0.5209	0.4872	0.4700	0.5633	0.4727	0.6685	0.4587	0.4570	0.4469	0.5652	0.5804	0.2783	0.3726	0.8055	0.3500	1.6207	0.3599	1.32/4	0.0337	1.2628	0.4186	0.6893	0.3518	0.5739	0.4529	0.4508	0.3366	0.7255	07770
RB	137.81			147.06	195.26	145.44	129.68		121.75	167.36	232.77	181.56	78.16	172.23	143.48			125.62	169.19	154.38	128.61	125.60	189.92								123.17	,			Ι'		164.41	151.73	306.62	128.40	183.99	25/1 20
F	5 0.0	7 0.0		3 0.0	0.0	9 0.0	7 0.0	4 0.0	1 0.0	4 0.0	9 0.0	0.0	4 0.0	1 0.0	2 0.0	2 0.0	1 0.0	8 0.0	8 0.0	0.0 9	2 0.0	8 0.0	1 0.0	1 0.0							4 0.0			<u>.</u>		5 0.0	0.0 6	0.0	0.0 0	2 0.0		1
FE HF	6.0 7.35	9.5 7.47	2.9 6.79	7.6 7.73	1.2 6.70	6.5 7.19		1.1 6.94		9.8 5.44		3.5 5.96	1.3 6.24	9.6 5.41	3.4 9.22		3.3 7.21	8.8 7.38	3.4 6.38	8.2 6.56	6.4 6.02	7.4 6.38	4.1 7.81	7.6 8.51							0.0 6.44						2.1 6.19	4.2 9.10	9.8 10.20	9.9 8.12		1 6 71
EU	14 25406.0	46 25519.5			82 24701.2	17 21146.5		32 22561.1	96 20770.3	99 18929.8	41 12300.4	84 16843.5	78 39971.3	17 22479.6	32 22693.4	25 28442.9	95 25873.3	04 27258.8	84 28253.4	88 25438.2	19646.4	98 25517.4	08 19534.1	16 17367.6							53 29136.6					20 26073.7	34 22812.1	25 24434.2	82 14149.8			1 1 1 7 7 7 1
CS	5.05 1.1314	5.52 1.1946	6.99 1.0037	19.63 1.1635	7.26 0.9782	4.54 1.3017	4.61 1.4231	15.26 1.1432	4.74 1.3996	6.41 0.9899	.17 0.5141	6.53 0.6884	6.19 1.5578	6.18 1.2317	4.95 1.2132	5.34 1.5125	7.11 1.7495	4.34 1.2604	.01 0.9084	6.08 1.3288	4.67 1.4860	15.20 1.3998	6.85 0.7008	13.98 0.8116	5.86 1.5926				_		18.59 1.4153				21.35 1.1230	15.30 1.2920	9.52 0.9934	22.40 1.0925	5.83 0.7282	4.10 1.5177	8.00 0.9490	19 AE 0 5757
	5.			`						9.9	20.17	9	9						13.01	9	4.	15.	9					7	19.8/		<u>×</u>	i 4						22.	5.	4.		
ANID	HM011	HM012	HM013	HM014	HM015	HM016	HM017	HM018	HM019	HM020	HM021	HM022	HM024	HM025	HM026	HM027	HM028	HM029	HM030	HM031	HM032	HM033	HM034	HM035	HM036	HM037	HM038	HM039	HM040	HM041	HIM042	HM044	HM045	HM046	HM047	HM048	HM049	HM050	HM051	HM052	HM053	HMOSA

ANID	macro grp	macro grp Chem2012	CERAMIC TYPE	MATERIAL	SOURCE	STATE	SITE NAME	SITE NO	AS	LA	N U	ND SM	Π	YB	CE	00	CR
HM056	Group-B2	Mimbres-02A	Mimbres B/W Style III	Pottery	TAM	MN		LA 078963	1.54	41.31 0.4247	47 40.27	75.97	4.45	3.06	74.44 5	5.90	39.77
HM057	Group-C2a	Mimbres-49A	Mimbres B/W Style III	Pottery	TAM	MN	Elk Ridge	LA 078963	2.48	35.70 0.3302	02 33.47	17 5.67	1.16		68.17 14		46.13
HM058	Group-B2	Mimbres-08	Mimbres B/W Style III	Pottery	TAM	MN	Elk Ridge	LA 078963	2.54	33.24 0.3694	18.61	3.32	4.43	2.29 E	54.01 4	4.50 2	24.38
HM059	Group-C1	Mimbres-21	Mimbres B/W Style III	Pottery	TAM	M	Elk Ridge	LA 078963	1.67	37.25 0.3218	18 25.78	8 5.16	1.77	2.45	68.74 9	9.37 6	62.47
090MH	Group-B1	Mimbres-04A	Mimbres B/W Style III	Pottery	TAM	M	Elk Ridge	LA 078963	2.15	37.82 0.3703	03 31.42		5.13	2.33 (23.97
HM061	Group-B	Unas.	Mimbres B/W Style III	Pottery	TAM	NM	Elk Ridge	LA 078963	1.71	37.14 0.3626		0 5.55	3.66	2.34 (68.84 4	4.33 3	30.10
HM062	Group-C2a	Mimbres-49A	Mimbres B/W Style III	Pottery	TAM	NM	Elk Ridge	LA 078963	1.22	52.87 0.3927	27 48.64	7.90	2.98	3.05	98.97 10	10.40 4	40.77
HM063	Group-B1	Mimbres-09	Mimbres B/W Style III	Pottery	TAM	NM	Elk Ridge	LA 078963	0.00	53.15 0.5302		88.88	2.17	3.76 10	101.54 2	2.36 1	13.28
HM064	Group-C2a		Mimbres B/W Style II/III	Pottery	TAM	NM	Elk Ridge	LA 078963					2.57				57.03
HM065	Group-C2a	Mimbres-49A	Mimbres B/W Style III	Pottery	TAM	MN	Elk Ridge	LA 078963	3.68	42.56 0.3546	46 38.85	82 6.78	1.76		73.19 12	12.13 5	59.75
990MH	Group-C2a	Mimbres-49A	Mimbres B/W Style III	Pottery	TAM	MN	Elk Ridge	LA 078963		37.01 0.2600	32.74	74 5.34	1.43	1.92	73.91 11	11.93 5	58.06
HM067	Group-C2a	Mimbres-49A	Mimbres B/W Style III	Pottery	TAM	MN	Elk Ridge	LA 078963	2.80	41.25 0.3064	64 37.32	82 6.24	1.34	2.05	68.43 11	11.26 6	60.87
890MH	Group-C2a	Mimbres-49A	Mimbres B/W Style III	Pottery	TAM	MN	Elk Ridge	LA 078963	2.43	34.92 0.3118	18 27.01	11 5.52	1.48	2.27	71.45 11	11.42 6	62.41
690MH	Group-B1	Mimbres-04A	Mimbres B/W Style III	Pottery	TAM	MN	Elk Ridge	LA 078963	1.31	40.25 0.3584		73 5.36	3.52	2.18		3.74 2	20.18
HM070	Group-A	Mimbres-01	Mimbres B/W Style III	Pottery	TAM	NM	Elk Ridge	LA 078963			84 28.59	9 4.02	11.42	2.46	85.39 1		9.71
HM071	Group-A	Mimbres-01	Mimbres B/W Style II	Pottery	TAM	MN	Elk Ridge	LA 078963	2.26 E	54.93 0.3175	75 18.73	3 3.62	12.26	2.38	83.61 2	2.77	5.58
HM072	Group-B	Unas.	Mimbres B/W Style III	Pottery	TAM	MN	Elk Ridge	LA 078963	1.92	52.41 0.5017	17 40.15	16.97	5.43	3.15	80.48	5.36 2	28.19
HM073	Group-A	Mimbres-01	Mimbres B/W Style III	Pottery	TAM	MN	Elk Ridge	LA 078963	1.81	55.29 0.5246	46 19.92	3.97	10.85	2.74	81.48	2.27	8.20
HM074	Group-B	Unas.	Mimbres B/W Style III	Pottery	TAM	MN	Elk Ridge	LA 078963	2.19	48.83 0.5623	23 31.43	13 5.68	5.19	3.79	85.05	7.19 3	35.55
HM075	Group-B1	Mimbres-04A	Mimbres B/W Style III	Pottery	TAM	MN	Elk Ridge	LA 078963		48.65 0.4733	33 33.08	8 6.57	4.21	3.31	84.73 4	4.80 2	23.68
HM076	Group-B	Unas.	Mimbres B/W Style III	Pottery	TAM	MN	Elk Ridge	LA 078963	2.86 €	51.52 0.5812	12 28.60	5.32	2.95	3.86	74.05 6	6.31 2	27.62
HM077	Group-B	Unas.	Mimbres B/W Style II	Pottery	TAM	MN	Elk Ridge	LA 078963	3.42	44.19 0.5147	47 27.22	2 5.91	4.87	3.46 7	74.67 12	12.98 4	40.35
HM078	Group-A	Mimbres-03	Mimbres B/W Style II	Pottery	TAM	M	Elk Ridge	LA 078963	2.18 4	43.73 1.2160	60 35.98	10.14	6.83	8.94	94.79	2.09	15.15
HW079	Group-B1	Mimbres-04B	Mimbres B/W Style III	Pottery	TAM	MN	Elk Ridge	LA 078963			23 48.60	9.36	19.9		96.91		31.53
HM080	Group-A	Mimbres-01	Mimbres B/W Style II/III	Pottery	TAM	NM	Elk Ridge	LA 078963		56.94 0.5818	18 20.65	5 4.14	11.00	3.01	88.26 2	2.39 1	13.36
HM081	Group-C2a	Mimbres-49A	Mimbres B/W Style III	Pottery	TAM	NM	Elk Ridge	LA 078963	2.34		04 28.86		2.45		68.11 11		57.17
HM082	Group-B1	Mimbres-04B	Mimbres B/W Style III	Pottery	TAM	NM	Elk Ridge	LA 078963			85 46.76	6 8.79	4.96	4.21 9			30.40
HM083	Group-B1	Mimbres-09	Mimbres B/W Style III	Pottery	TAM	NM	Elk Ridge	LA 078963				10.63	3.72				15.92
HM084	Group-A	Mimbres-01	Mimbres B/W Style III	Pottery	TAM	M	Elk Ridge	LA 078963				09.9 6	11.76				13.64
HM085	Group-B1	Mimbres-04B	Mimbres B/W Style III	Pottery	TAM	M	Elk Ridge	LA 078963		62.05 0.5574	74 48.94	8.53	5.43	3.99 10	102.92	5.45 2	27.88
980MH	Group-A	Mimbres-01	Mimbres B/W Style III	Pottery	TAM	M	Elk Ridge	LA 078963					_				13.33
HM087	Group-C1	Mimbres-21	Mimbres B/W Style III	Pottery	TAM	M	Elk Ridge	LA 078963				39 5.51	1.21				28.76
HM088	Group-C2a	Mimbres-49A	Mimbres B/W Style III	Pottery	TAM	M	Elk Ridge	LA 078963				30 7.16					92.09
HM089	Group-C1	Mimbres-21	Mimbres B/W Style III	Pottery	TAM	M	Elk Ridge	LA 078963		_					_		52.43
HM090	Group-A	Mimbres-01	Mimbres B/W Style II	Pottery	TAM	M	Elk Ridge	LA 078963	2.24			32 4.01	11.74		93.81 2		7.69
HM091	Group-C1	Mimbres-21	Mimbres B/W Style III	Pottery	TAM	Σ	Elk Ridge	LA 078963		41.59 0.2995	95 42.52	5.92	0.80	2.39	86.71 10	10.88 4	43.17
HM092	Group-A	Mimbres-01	Mimbres B/W Style III	Pottery	TAM	MN	LA 086736	LA 086736	2.56	60.94 0.6144	44 24.28	4.74	10.84	3.18	93.51 3		13.21
HM093	Group-C1	Mimbres-23	Mimbres B/W Style III	Pottery	TAM	MN	LA 086736	LA 086736	4.02	35.51 0.3472	72 33.05	99'5 2'66	2.87	2.27	73.84 12	12.54 4	44.92
HM094	Group-B	Unas.	Mimbres B/W Style III	Pottery	TAM	¥	LA 086736	LA 086736	2.69	37.38 0.4058		9 4.25	5.09	2.47	67.85 4	4.93 3	33.08
HM095	Group-A	Mimbres-01	Mimbres B/W Style III	Pottery	TAM	NM	LA 086736	LA 086736		57.76 0.3613			13.69	1		3.66 1	10.57
960MH	Group-C2a	Mimbres-49A	Clay	Clay	TAM	NM	Elk Ridge	LA 078963	2.82	39.79 0.3704	04 43.63	6.22	2.40	2.51 7	75.89 13	13.87 4	44.85
HM097	Group-C2a		Clay	Clay	TAM	M	Elk Ridge	LA 078963							_	_	40.31
HM098	Group-C2a		Clay	Clay	TAM	NM	Elk Ridge	LA 078963					` '				46.04
HM099	Group-C2a	Mimbres-49A	Clay	Clay	TAM	NN	Elk Ridge	LA 078963	2.03	37.93 0.3417	17 31.43	13 5.98	1.99	2.53 (69.58 12	12.04 3	39.89

>	63.55	76.88	33.17	52.39	47.63	52.93	74.44	32.50	95.34	91.83	82.01	72.34	79.49	45.53	26.59	22.84	49.85	20.24	50.52	40.18	47.99	56.83	24.66	59.53	24.18	72.01	69.42	40.20	33.35	58.81	24.92	56.34	95.27	61.71	20.05	58.69	34.10	76.22	55.57	23.39	71.81	67.28	78.82	77.80
F	2827.0	4022.5	2286.4	2534.9	3361.0	3522.4	3544.2	2451.5	3852.7	4530.7	4166.1	3876.9	3785.3	2810.9	1523.5	1234.0	2730.0	1281.4	2551.3	3287.4	1889.9	3267.0	1472.2	2786.4	1164.4	3778.0	2771.7	3311.7	2019.5	2721.3	1513.4	2040.9	5004.6	2199.6	1395.4	2650.0	1738.8	2575.8	3598.2	1477.0	3478.5	3727.3	3385.4	3907.3
NA	12918.0	18946.4	9456.8	19350.6	13973.3	11773.9	16282.1	18700.4	21314.7	12185.4	16937.9	16892.9	15428.1	17003.2	10036.9	17034.4	10712.4	12581.9	12606.5	17131.6	13726.8	14075.7	4975.0	11154.0	15331.3	18594.1	9146.1	15632.0	15849.2	10373.9	13698.1	9486.5	17928.5	18453.7	13804.3	16033.3	18702.2	12683.8	12359.8	17737.8	19769.0	17597.9	17958.6	16552.2
M	206.7	. 873.8	160.0	1051.2	3	248.5	. 697.3	330.1	603.1	654.8	467.0	459.7	460.9	253.5	131.1	282.5			. 9.795	259.0		578.4	663.4	573.4							371.3				278.2			649.2				735.9		9:059
\checkmark	29525.8	33723.7	35113.4	30123.1	29526.1	28131.7	20868.0	23986.8	29753.7	27966.9	28728.7	27202.3	14027.5	27559.0	36364.1	31762.6	28305.4	27840.5	29028.1	29623.4	23250.6	34072.5	49724.6	28381.0	25228.8	19833.0	26360.4	31097.8	34736.6	29557.0	40062.5	23643.1		_	31873.2	27393.2	28224.7	30704.5	25722.4	22096.0	27980.4	27606.0	21127.9	22076.4
DΑ	4.228 2					3.673 2	4.922 2	5.952 2	3.674 2	4.209 2	3.675 2	3.970 2	3.869 1	4.023 2	2.370 3		5.451 2	2.878 2	4.618 2		3.717 2	4.213 3	11.194 4										_					3.470 3	2.705 2	2.136 2	3.167 2			4.227 2
CA	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
BA	658.4	1013.3	443.1	011.0	705.0	765.2	1159.1	1106.0	974.6	782.6	846.6	832.5	922.7	854.0	526.0	604.3	589.0	349.0	8.899	736.5	401.1	543.3	180.9	614.7	324.4	881.7	9.609	1121.0	621.8	643.4	661.4	7,61.1	1021.4	949.2	366.0	897.1	373.6	1073.3	855.7	475.4	830.1	848.1	783.4	725.9
AL	84903.7			_	79495.8	76161.7	94580.2 1	87251.3 1	97458.6	92188.6	97727.4	99205.7	92477.5	86462.3	96612.4	06204.4	90450.0	101744.1	84450.8	86142.7	7.171.7	78992.6	83781.7	00326.0	95613.2	93156.3		•	107639.0	101026.7	14498.5	_		91790.2	97820.1	88642.5	97633.3	78820.3 1	92288.6	97222.4	76766.1	78023.6	84006.4	80735.4
ZR	252.5	231.9	252.9	239.7	166.9	l I	191.2	185.2	239.7	142.7	174.3	154.7	227.0	220.2	163.3	168.0	159.4	157.7	244.7	197.0	147.2	160.4	186.7	184.9	186.4	157.8	151.7	241.7	177.3	205.9	200.5	151.7	210.9	178.4	169.6	153.4	171.1	142.7	162.8	178.9	172.4	167.6	194.5	157.5
NZ	53.7	61.0				54.4		73.2	79.4	118.5		66.4	67.7	51.5	43.3			43.9	74.1	55.5	60.7	0.79	71.4			63.1																		71.6
B TH	0 20.62	5 10.87	2			5 18.91	1 13.25	3 13.70	3 9.05	1 11.72	3 12.13	5 12.07	9 11.03	7 18.33	7 47.21	_			7 21.84			1 22.52	6 39.10			2 12.02		_					_	-	_			0 12.66	6 27.76	1 51.14				4 10.55
TA	1.3463 0.80	1.1793 0.75	1.5274 0.42	$0.5680 \mid 0.55$	1.3215 0.65	1.4766 0.75	0.9453 1.01	0.9945 1.2	0.7239 0.63	1.1223 0.81	1.0970 0.73	1.1171 0.85	0.9530 0.69	1.3209 0.67	2.4692 0.37	2.4596 0.27	1.3843 1.00	2.1287 0.33	1.4251 0.77	1.3280 0.65	2.1460 0.55	2.0139 0.61	2.5272 1.46	1.5593 1.04	2.3413 0.42	1.0575 0.52		_	2.1907 0.87		2.6283 0.42			0.6017 0.64	2.2575 0.41	0.6883 0.7	2.0976 0.44	1.0523 0.70	1.5892 0.46		1.0799 0.67			0.9307 0.64
SR	425.4						350.8 0	232.6 0	702.1 0	369.2	316.0	335.2	423.4 0	268.2	84.1 2		153.4 1	71.7 2	176.0 1		279.9 2	256.0 2	77.1		78.9 2												132.1 2	611.3	201.8 1		648.2			629.8 0
SC	12.31	9.33	5.47	6.71	19.9	7.92	11.50	8.22	13.80	11.86	10.81	10.28	12.13	6.83	4.01	3.92	7.26	4.14	6.44	6.72	7.34	8.39	4.88	8.24	4.03	10.60	9.05	99.6	5.13	8.53	4.65	18.9	11.51	7.30	4.35	8.95	4.54	10.39	8.13	3.85	89.8	7.57	8.09	8.28
SB	0.3302	0.4716	0.4248	1.0910	0.3317	0.3312	0.2990	0.5636	0.2486	0.5368	0.5182	0.4268	0.4688	0.5217	0.7766	0.6164	0.4919	0.6708	0.4754	0.3503	0.3919	0.6799	0.3689	0.4386	0.7800	0.4274	0.4475	0.5964	0.6527	0.4303	0.7598	1.0930	0.6553	1.2659	0.7667	1.4111	0.6979	0.8096	0.5939	0.8992	0.4456	0.3796	0.4831	0.4391
RB	154.36	128.02	214.30	127.33	135.15	137.40	95.72	113.95	89.71	00.66	113.02	115.91	90.24	133.78	217.52	169.85	156.90	199.39	174.81	137.50	189.60	184.97	246.01	155.40	211.77	106.67	136.30	120.84	208.08	163.51	244.46	117.88	99.01	119.82	218.89	129.50	193.31	177.16	172.73	198.87	108.58	97.39	96.12	95.22
Z	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0			0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
生	7.19	6.23	7.66	6.07	6.48	6.93	7.47	7.98	6.28	7.00	7.80	6.55	6.63	6.93	9.00	90.9	5.99	5.42	9.05	98.9	5.88	7.22	9.91	5.90	9.90	6.45	5.12	7.89	6.87	8.18	7.84	99.9	8.38	6.80	6.70	6.59	6.07	4.92	6.04	6.17	6.94	6.32	7.42	6.47
FE	28910.5	33342.6	17858.7	25027.3	20797.1	25654.1	37391.0	17095.6	39677.2	42684.0	38594.9	34551.6	37274.7	25081.6	12587.1	11286.1	22760.1	11348.7	23587.8	21732.7	20566.5	25536.1	12438.3		10632.9	33810.7	31065.7	18310.4	13847.7	25189.2	13727.6	26688.7	38380.9	26797.7	11969.1			32801.1	26890.8	11276.0	32618.4	28870.7		30113.2
EU	1.4612					1.1668	2.1691					1.3801	1.4013	1.1589	0.5157			0.5245	1.1450	1.3273	20.98 0.9050	1.1089	0.4693											1.2003		1.5267		1.3271	10.55 0.7642		1.3744			1.3118
CS	16.85	7.81	6.84	17.65	4.47	5.19	3.55	3.74	90.9	4.37	4.52	4.33	3.81	4.88	16.88	7.48	5.88	13.11	5.30	4.42	20.98	7.25	4.01	5.90	13.79	4.23	6.15	4.33	14.29	6.29	14.79	16.31	8.67	18.84	15.91	21.71	15.93	11.18	10.55	15.00	3.54	3.02	3.07	3.90
ANID	HM056	HM057	HM058	HM059	HM060	HM061	HM062	HM063	HM064	HM065	990MH	HM067	890MH	690MH	HM070	HM071	HM072	HM073	HM074	HM075	9/0WH	HM077	HM078	HM079	HM080	HM081	HM082	HM083	HM084	HM085	980WH	HM087	HM088	HM089	HM090	HM091	HM092	HM093	HM094	HM095	960MH	HM097	HM098	660MH

ANID	macro grp	Chem2012	CERAMIC TYPE	MATERIAL	SOURCE	CE STATE	E SITE NAME	SITE NO	AS	ΓA	Π	ND S	SM	Λ	YB CE	00	CR
JAM003	Clay		Clay	Clay, Hearth			Lake Roberts Vista	LA 071877	4.56	33.73 0.3	0.3057 0		5.93 1.5	1.59 2.10	0 63.95	5 18.70	39.69
JAM005	Group-B	Unas.	Mimbres Corrugated	Pottery	TAM	MN	Pueblo Vinegaroon	LA 073824	2.61	48.47 0.4	0.4182 C	0.00	7.44 5.01	3.09	9 83.43	3 4.79	17.06
JAM006	Group-B	Unas.	Mimbres Corrugated	Pottery	TAM	NN	Pueblo Vinegaroon	LA 073824	2.81	25.03 0.2	0.2712 0	0.00	2.83 2.9	2.90 1.65	5 38.01	1 2.17	14.74
JAM008	Group-B2	Mimbres-02A*	Mimbres Corrugated	Pottery	TAM	MN	NAN	LA 002465	2.82	48.22 0.4	0.4604 0	0.00	6.91 2.87	37 3.1	1 59.54	1 6.63	30.73
JAM009	Group-A	Mimbres-10	Mimbres Corrugated	Pottery	TAM	MN	NAN	LA 002465	4.46								31.96
JAM010	Group-B	Unas.	Mimbres Corrugated	Pottery	TAM	M	NAN	LA 002465	4.42	55.42 0.7				2.46 6.12	1	5 4.49	27.79
JAM011	Group-B	Unas.	Mimbres Corrugated	Pottery	TAM	M	NAN	LA 002465	2.55	47.38 0.4	0.4596 C	0.00	7.39 3.91			5.63	18.21
JAM012	Group-B	Unas.	Mimbres Corrugated	Pottery	TAM	M	NAN	LA 002465	1.79								21.21
JAM013	Group-B1	Mimbres-04A		Pottery	TAM	NM	NAN	LA 002465	2.87		0.4273 C						19.09
JAM014	Group-B2	Mimbres-02A*	Mimbres Corrugated	Pottery	TAM	MN	NAN	LA 002465	2.77	32.87 0.4	0.4157 0	0.00 5.	5.07 2.9	2.98 2.85	5 58.41		35.38
JAM015	Group-A	Mimbres-10	Mimbres Corrugated	Pottery	TAM	NM	NAN	LA 002465	3.45	67.11 1.1	1.1466 C	0.00 13.	13.96 3.8	3.82 8.30	0 151.44	1 7.20	33.22
JAM016	Group-A	Mimbres-10	Mimbres Corrugated	Pottery	TAM	MN	NAN	LA 002465	69.9	80.82	1.0619 0	0.00	14.16 6.57	57 7.36	6 159.13	3 4.87	32.90
JAM017	Group-A	Mimbres-10	Mimbres Corrugated	Pottery	TAM	MN	NAN	LA 002465	2.30					1.99 5.04	l		22.92
JAM018	Group-B1	Mimbres-04A	Mimbres Corrugated	Pottery	TAM	MN	NAN	LA 002465	2.81	42.50 0.3	0.3867 0	0.00	5.54 2.8	2.84 3.01	13.91	3.56	18.47
JAM020	Group-C1	Unas.	Mimbres Corrugated	Pottery	TAM	MN	NAN	LA 002465	9.03	29.09 0.3	0.3596 0	0.00	4.96 2.4	2.40 2.19	9 57.25	5 10.22	24.07
JAM021	Group-B1	Mimbres-04C	Mimbres Corrugated	Pottery	TAM	MN	NAN	LA 002465	2.64	34.47 0.3	0.3863 C	0.00	5.08 2.51		2 70.36	5 4.96	26.55
JAM022	Group-A	Mimbres-10	Mimbres Corrugated	Pottery	TAM	MN	Pueblo Vinegaroon	LA 073824	2.23	58.19 0.7	0.7366 C	0.00	11.05 7.7	7.13 5.37	7 125.29	96 ['] S	30.86
JAM023	Group-C2a	Mimbres-49A	Mimbres Corrugated	Pottery	TAM	MN	NAN	LA 002465	3.66	31.12 0.3	0.3110 0	0.00	4.39 2.7	2.13 2.08	18 66.51	11.00	48.05
JAM024	Group-B1	Mimbres-04B	Mimbres Corrugated	Pottery	TAM	MN	NAN	LA 002465	1.40	45.76 0.4	0.4400 C	0.00	5.54 3.71	71 2.89	9 87.38	3 3.76	23.50
JAM025	Group-C2b	Mimbres-47	Mimbres Corrugated	Pottery	TAM	MN	NAN	LA 002465	3.62	28.89 0.2	0.2292	0.00	4.75 2.4	2.43 1.72	2 63.32	2 4.07	21.16
JAM026	Group-C2a	Mimbres-49A	Mimbres Corrugated	Pottery	TAM	MN	NAN	LA 002465	3.57	44.05 0.3	0.3561 0	0.00	6.70 1.91	91 2.96	6 93.48	3 16.89	85.44
JAM027	Group-C2a	Mimbres-49A	Mimbres Corrugated	Pottery	TAM	MN	NAN	LA 002465	2.54	32.25 0.2	0.2698 C	0.00	5.49 1.9	1.95 2.33	3 76.46	5 12.53	56.08
JAM028	Group-B	Unas.	Mimbres Corrugated	Pottery	TAM	MN	NAN	LA 002465	3.59	43.61 0.4	0.4642 C	0.00	7.17	3.96 4.03	13 97.51	1 6.19	15.34
JAM029	Group-B1	Mimbres-04C	Mimbres Corrugated	Pottery	TAM	MN	NAN	LA 002465	2.61	39.90 0.4	0.4126 C	0.00	5.89 3.27	27 3.22	2 94.11	1 5.46	24.25
JAM030	Group-B1	Mimbres-04A	Mimbres Corrugated	Pottery	TAM	MN	NAN	LA 002465	0.00	44.68 0.4	0.4382 0	0.00	6.05 3.7	3.13 2.96	6 81.27	2.90	16.68
JAM031	Group-C2	Unas.	Mimbres Corrugated	Pottery	TAM	NN	NAN	LA 002465	3.54	21.95 0.2			3.45 1.5			7 3.93	13.82
JAM032	Group-B	Unas.	Mimbres Corrugated	Pottery	TAM	NM	NAN	LA 002465	2.58	0.00 0.3	0.3827 0			7.94 2.05		4 4.01	20.50
JAM033	Group-C2b	Mimbres-47	Mimbres Corrugated	Pottery	TAM	NM	NAN	LA 002465	2.83				6.07 2.01		1 71.90	8.63	24.87
JAM034	Group-C2b	Mimbres-47	Mimbres Corrugated	Pottery	TAM	NN	NAN	LA 002465	0.00		0.3114 C	0.00	6.75 2.5	2.54 2.14	4 119.40	69.6	25.24
JAM035	Group-A	Mimbres-10	Mimbres Corrugated	Pottery	TAM	M	NAN	LA 002465	3.45	108.55 1.3	1.3509 C	0.00 19.	19.02 3.8	3.88 10.00	0 155.57	7 5.08	30.98
JAM036	Group-C2b	Mimbres-47	Mimbres Corrugated	Pottery	TAM	M	NAN	LA 002465	1.41								25.71
JAM037	Group-C2b	Mimbres-41	Mimbres Corrugated	Pottery	TAM	M	NAN	LA 002465	0.00	_			4.64 1.8				27.70
JAM038	Group-B	Unas.	Mimbres Corrugated	Pottery	TAM	M	NAN	LA 002465	0.00			0.00		6.66 3.83	3 108.55	5 10.79	69.94
JAM039	Group-B	Unas.	Mimbres Corrugated	Pottery	TAM	M	NAN	LA 002465	0.00	50.93 0.7	0.7590		8.99 8.		9 101.03	3 9.92	67.57
JAM040	Group-B1	Mimbres-04A	Mimbres Corrugated	Pottery	TAM	NM	NAN	LA 002465	2.87	42.25 0.4	0.4427 C	0.00	6.27 3.5	3.52 2.84	77.19	9 6.61	16.71
JAM041	Group-A	Mimbres-10	Mimbres Corrugated	Pottery	TAM	N	NAN	LA 002465	2.72	96.47 0.8	0.8633 0	0.00	17.26 6.(6.05 6.22	2 190.94	1 8.03	35.93
JAM042	Group-B	Unas.	Mimbres Corrugated	Pottery	TAM	MN	NAN	LA 002465	0.00	43.26 0.4		0.00	6.96 2.0	2.09 3.23	3 86.11	1 7.31	57.98
JAM043	Group-B1	Mimbres-04A	Mimbres Corrugated	Pottery	TAM	MN	NAN	LA 002465	2.25	43.34 0.3	0.3993 0	0.00	6.28 3.0	3.60 2.73	3 84.11	1 5.93	19.62
JAM044	Group-B1	Mimbres-04C	Composite	Pottery	TAM	N	NAN	LA 002465	3.86	34.40 0.3	0.3143 0	0.00	4.76 2.8	2.84 2.56	6 66.93		28.28
JAM045	Group-C2	Unas.	Mimbres Corrugated	Pottery	TAM	NM	NAN	LA 002465	5.82	55.15 0.4	0.4539 C	0.00	8.42 3.0	3.09 3.52			22.58
JAM046	Group-C2b	Mimbres-47	Mimbres Corrugated	Pottery	TAM	NM	NAN	LA 002465	2.64	49.71 0.2	0.2692 C	0.00	8.45 1.5	1.52 2.19	9 101.58	3 5.92	25.57
JAM047	Group-A	Mimbres-10	Mimbres Corrugated	Pottery	TAM	MN	NAN	LA 002465	3.69			1			-		29.84
JAM048	Group-C2b	Mimbres-47	Chihuahua Indented	Pottery	TAM	M	NAN	LA 002465	1.17						1		22.80
JAM049	Group-B	Unas.	Mimbres Corrugated	Pottery	TAM	MN	NAN	LA 002465	2.53	47.69 0.4	0.4948 C	0.00	7.26 4.0	4.02 3.15	5 77.07	7 5.88	14.65

>	123.09	47.02	26.08	67.83	52.11	55.93	43.33	48.65	33.98	64.85	50.53	58.77	26.67	38.89	72.66	53.06	42.86	73.80	36.28	50.71	104.50	75.92	40.40	50.21	40.16	47.99	40.73	59.72	26.06	48.44	5/.6/	11.19	50.02	38.47	59.85	69.63	38.64	48.55	37.49	58.57	60.79	50.30	7 7 7
I	4202.8	2746.7	2228.7		2321.7	2841.9	2620.3	2988.9	2795.6	2938.1		2484.5	2227.5	3067.1			2239.4	4718.2	2556.4		4428.7	4411.9		3097.5							0.7062	3307 7	3387.3	3257.6	2868.5		3188.4	3013.2		3510.6			
NA	7308.6 4	11906.7 2	12714.1 2		12006.7 2	13454.6 2	14540.0 2	15716.2 2	16532.4 2	15869.2 2	13251.9 1	12167.6 2	10236.8 2	16771.3 3	8614.0 2		13187.0 2	14007.5 4	12527.5 2	19136.5 3	14193.4 4	14215.7 4	5098.8 2	5424.6 3								15051 2					15174.4	13513.8 3	18711.9 4	20134.2 3			
MN	692.7 73	337.5 119	160.5 127	`	242.1 120	٠.	384.2 145	433.2 157	222.7 165	175.4 158	١.	275.2 121	262.6 102	201.1 167		_	489.9 131	455.2 140	240.9 125	139.6 191	644.9 141	479.4 142	371.8 150	315.7 154	l							400.9 129 467.9 150					465.1 151	552.5 135	١,	139.5 201		,	
~		0.0	0.0		0.0	0.0	0.0	0.0 43	0.0	0.0	0.0	0.0	0.0	0.0				0.0	0.0		0.0	0.0	0.0	0.0								0.0					0.0	0.0	0.0	0.0			
>																																											
Y DY	0 4.086	5.404	0 2.650	0 5.525	0 6.433	7.728	0 4.875	0 5.856	0 4.457		12.115	10.988	908.6	3.697				0 2.786	4.024	3.019		3.863	04.790	0 4.119						1		5.408					4.094	3.649					
S	0.0	0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	
BA	504.3	697.4	531.0	632.5	634.4	615.7	850.0	854.1	902.1	543.5	713.2	634.6	0.686	892.5	987.4	908.2	851.1	849.3	676.5	849.5	974.7	1001.0	887.7	1004.1	933.6	1162.2	632.9	908.1	8.666	755.9	101/.3	1300 5	1163.4	905.6	808.2	1015.8	862.4	913.9	299.2	763.5	848.3	1079.0	1
AL	71598.6	78870.2	70849.6	79643.5	88542.9	82742.3	79712.5	84796.1	77027.5	84877.5	79937.3	87823.2	81874.5	75264.6	78041.8	82060.8	76250.2	82993.6	75878.4	81104.8	87731.9	93644.3	75275.3	78368.9	77621.7	83959.4	77457.5	85121.4	88409.7	83502.1	89102.1	94142.1	86151 3	78562.0	94144.8	94651.9	77524.2	80050.7	88443.5	96937.5	92736.5	85831.4	1
ZR	146.3	164.6	121.8	137.3	181.0	276.4	203.9	235.8	201.7	266.6	237.6	295.4	268.5	249.5	157.6	205.8	256.7	261.5	158.8	185.8	191.3	172.4	184.5	178.2	200.8	147.0	152.4	144.5	186.3	215.9	124.8	170.0		218.7	222.9	220.3	148.9	146.2	263.5	139.3	190.8	150.3	7
NZ	63.5	52.1	34.5	52.9	87.5	6.92	48.3	63.0	52.4	43.5	90.4	104.7	147.1	45.2	86.5	52.3	59.3	73.0	58.8		82.1	87.2	62.8	67.3	47.3	265.6	44.4	62.3	20.2	76.5	85.2	02.0	2, 2, 2, 2, 2, 2, 2, 2, 2, 2, 2, 2, 2, 2	49.3	113.2	70.5	48.0	9.99	113.6	70.5	8.8	46.2	1
H		20.72	20.64		34.36	29.33	21.26	18.15	20.92	19.55	42.34	50.09	46.88	19.33		15.73		13.42	30.14	8.01		11.72	17.61	17.61	l		(~)		_	7	70.07		_		_		19.18	18.90	11.19	6.77	7		,
4 TB	5 0.78	5 0.85	0.39	3 0.86	9 1.05	5 1.37	0.94	1.03	1 0.79	0.84	9 2.11	5 2.20	3 1.91	5 0.75	9 0.63	9 0.70	3 1.67	3 0.56	1 0.79	5 0.52	1 0.97	3 0.82	1.00	96.0 9	5 0.84					3 3.29		10.0 4		1 -			5 0.82	69.0	5 1.11	3 0.89			2
TA	0.7886	1.3615	1.4180		2.8939	1.5706	1.5390	1.3744	1.4211	1.4360	2.1529	3.7596	1.0073	1.2505)	1.2229	1.4163	1.1178	1.8701	0.7695	0.9911	0.9923	1.3290	1.3366		0.6243						1.0329			١,		1.3595	1.3550	3.8596	0.8993			1 4007
SR	275.4	235.9	164.6	319.8	144.0	117.7	271.6	266.4	308.2	267.0	162.0	117.2	101.5	373.4	175.0	297.2	171.1	328.4	249.6	409.7	504.6	361.0	289.8	338.2	296.6	475.1	189.2	469.9	408.5	94.0	565.6	311.6	310.2	292.1	154.2	414.2	276.0	323.4	9.08	641.6	178.6	397.0	7
SC	12.27	6.91	4.72			8.71	7.06	8.47	6.58	11.12		12.13	1	5.95	1			10.22	97.9		12.87			7.92							7.63	-			,	,	6.45	7.31	11.97	98.9	_		0 7
SB	3.4126	3.9341	1.5743	1.4041	2.2596	1.9940	1.5701	3.0039	1.1035	1.1567	1.4183	1.5535	1.1799	0.6597	1.4580	0.9694	0.8570	1.0377	0.6994	0.9214	0.8353	0.6902	0.7803	0.4994	0.5040	0.7229	0.6652	0.5357	0.7366	1.1385	0.4955	0.5/30	0.3110	0.4230	0.6672	0.3935	0.3126	0.4685	0.9663	1.2249	0.7089	0.5289	1001
RB	125.26	144.81	140.67	110.49	219.47	248.28	138.69	135.05	140.80	117.09	246.18	273.66	232.15	128.93	198.01	136.25	221.69	105.44	195.27	119.76	101.91	108.13	123.86	143.98	119.61	140.55	216.22	100.76	125.65	276.02	80.10	175 58	174 35	131.85	219.30	101.75	131.36	139.44	102.91	73.65	239.85	136.16	110 12
Z	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0
Ή	2.65	2.06	5.78		5.76		5.55	6.35	6.85	80.6	7.17		9.61	7.55				8.93	6.10	6.82	7.21	6.72	6.75	91.9							4.76	0.00				_	6.51	6.04	11.90	5.05			7 2 7
FE	36757.9	24567.4	16048.6	22743.8	27757.1	29068.8	25527.2	26904.0	21061.1	26810.9	30035.2	43887.2	31840.7	17133.2	46023.0	25258.1	24059.2	36570.1	19161.1	22506.0	43699.4	40525.4	25037.7	27735.0	23126.8	34224.1	19059.4	29628.9	29296.8	31240.4	28684.7	330 IO. /	30476.4	20279.9			22542.6	25847.0	39099.0	24713.5			10425
ED	1.2167	1.2101	0.5316	1.2445	0.8369	1.1908	1.3056	1.6064	1.3899	1.0021	1.6234	1.5573	1.5540	1.1918	1.2842	1.2426	1.4142		1.0135	1.1629	1.7533	1.3739	1.3897	1.3427	1.2420	0.9712	0.5634	1.4562	1.7366	1.9871	1.3494	1,007	1 6922	1.2960	1.8155	1.6767	1.2927	1.1912		1.9586	1.3421	2.0644	1 201/
CS	4.73	4.55	2.06			11.76	4.13	4.16	3.69	11.10	6.52	11.92	2.67	3.26	11.21		5.17	3.51	6.51		3.31	3.63	3.36								3.50						3.76	4.57	4.48	3.47			7
ANID	JAM003	JAM005	JAM006	JAM008	JAM009	JAM010	JAM011	JAM012	JAM013	JAM014	JAM015	JAM016	JAM017	JAM018	JAM020	JAM021	JAM022	JAM023	JAM024	JAM025	JAM026	JAM027	JAM028	JAM029	JAM030	JAM031	JAM032	JAM033	JAM034	JAM035	JAM036	JAM037	I A MO30	JAM040	JAM041	JAM042	JAM043	JAM044	JAM045	JAM046	JAM047	JAM048	OVOVV

ANID	macro_grp	Chem2012	CERAMIC TYPE	MATERIAL	SOURCE	STATE	SITE_NAME	SITE_NO	AS	ГА	Π	ND	SM	n	'B CE	00	CR
JAM050	Group-B	Unas.	Mimbres Corrugated	Pottery	TAM		NAN	LA 002465	3.19	39.61 0	0.3887	0.00	3.97	3.64 2.17	17 72.60		30.18
JAM051	Group-B1	Mimbres-04A	Mimbres Corrugated	Pottery	TAM	MN	NAN	LA 002465	3.21		0.5048 (0.00	8.51 4	4.52 3	3.28 98.07	62.9	24.98
JAM052	Group-A	Mimbres-10	Mimbres Corrugated	Pottery	TAM	MN	NAN	LA 002465	4.89	32.93	1.0197	0.00	5.96 3	3.87 6.	6.52 62.63	3 3.86	26.37
JAM053	Group-B	Unas.	Mimbres Corrugated	Pottery	TAM	MN	NAN	LA 002465	1.97	49.11 0	0.4539 (0.00	7.20	3.68 3.	3.02 77.10	00.5	36.24
JAM054	Group-A	Mimbres-10	Mimbres Corrugated	Pottery	TAM	MN	NAN	LA 002465	4.22	31.77 1		9 00.0	6.50 4	4.04 8.	8.82 64.93	3.20	23.17
JAM055	Group-C2a	Mimbres-49B	Mimbres Corrugated	Pottery	TAM	MN	NAN	LA 002465	3.09	62.31 0	0.5246 (0.00	11.87	2.32 4.	4.36 97.45	5 14.75	61.16
JAM056	Group-A	Mimbres-10	Mimbres Corrugated	Pottery	TAM	MN	Old Town	LA 001113	3.23	42.05 0	0.8483 (0.00	8.58	3.16 5.	5.94 77.77	3.69	29.38
JAM057	Group-A	Unas.	Mimbres Corrugated	Pottery	TAM	MN	NAN	LA 002465	2.45	68.81 0	0.7315 (0.00	7.29 6.		4.70 111.38	3 6.05	17.97
JAM058	Group-B1	Mimbres-04A	Mimbres Corrugated	Pottery	TAM	MN	NAN	LA 002465	2.94	47.79 0	0.5029 (9 00.0	6.69	4.99 3.	3.30 80.42	5.71	17.21
JAM059	Group-B1	Mimbres-04A	Mimbres Corrugated	Pottery	TAM	MN	NAN	LA 002465	2.49	58.08 0	0.5705 (0.00	9 61.6	6.29	4.06 100.05	5 5.25	18.60
JAM060	Group-A	Mimbres-10	Mimbres Corrugated	Pottery	TAM	MN	NAN	LA 002465	4.18	33.95	1.0216 (9 00.0	6.27 4	4.13 7.	7.23 61.77	3.68	23.74
JAM061	Group-B1	Mimbres-04A	Mimbres Corrugated	Pottery	TAM	MN	NAN	LA 002465	3.06	39.82 0	0.4176 (9 00.0	6.57	3.88 2.	2.94 77.06	5 4.94	22.00
JAM062	Group-A	Mimbres-10	Mimbres Corrugated	Pottery	TAM	MN	NAN	LA 002465	5.06	58.23 0	0.8347 (0.00	9.76	3.69 5.	5.30 131.46	5 5.09	19.04
JAM063	Group-A	Unas.	Mimbres Corrugated	Pottery	TAM	MN	NAN	LA 002465	6.77	44.46 0	0.8869	0.00	8.25 7	7.13 5.	5.42 87.31	3.47	26.72
JAM064	Group-B1	Mimbres-04A	Mimbres Corrugated	Pottery	TAM	MN	NAN	LA 002465	2.27	33.99 0	0.3296 (0.00	5.03	3.15 2.	2.46 71.49	9 4.61	19.54
JAM065	Group-B1	Mimbres-04A	Mimbres Corrugated	Pottery	TAM	MN	NAN	LA 002465	2.03	44.69 0	0.4769 (0.00	6.56	4.67 2.	2.90 89.32	2 7.29	19.34
JAM066	Group-B	Unas.	Mimbres Corrugated	Pottery	TAM	MN	NAN	LA 002465	2.72	58.46 0	0.5457 (0.00	8.44	4.45 3.	3.35 106.59	9 6.12	16.22
JAM067	Group-B	Unas.	Mimbres Corrugated	Pottery	TAM	MN	NAN	LA 002465	3.40	46.34 0	0.5600	0.00	6.73 5	5.02	3.45 94.13	3 6.53	40.25
JAM068	Group-A	Mimbres-10	Mimbres Corrugated	Pottery	TAM	MN	NAN	LA 002465	2.61	126.02 0	0.9324 (0.00 20	20.63 3	3.67 6.	6.32 198.95	5 5.04	29.72
JAM069	Group-B2	Mimbres-02A	Mimbres Corrugated	Pottery	TAM	MN	NAN	LA 002465	2.08	34.36 0	0.4483 (0.00	5.50 4	4.24 2.	2.82 62.27	7 5.01	36.56
JAM070	Group-C2a	Mimbres-49A	Mimbres Corrugated	Pottery	TAM	MN	NAN	LA 002465	0.00	41.81 0	0.4166 (0.00	7.36	1.99 3.	3.37 129.54	11.39	51.39
JAM071	Group-B	Unas.		Pottery	TAM	MN	NAN	LA 002465	2.42	53.30 0	0.4880	0.00	8.57 4	4.44 3.	3.49 90.82	94.9	14.85
JAM072	Group-B	Unas.	Mimbres Corrugated	Pottery	TAM	MN	McSherry	LA 015050	3.24	38.45 0	0.7856 (9 00.0	6.06	3.51 4.	4.86 63.31	1 4.73	32.06
JAM073	Group-A	Unas.		Pottery	TAM	MN	McSherry	LA 015050	3.00		0.6102		9.71		4.20 118.25	5 2.27	19.56
JAM074	Group-A	Unas.		Pottery	TAM	NM	Old Town	LA 001113	3.46	32.93 0	0.7139 (0.00	6.14 4	4.36 4.	4.95 60.52		19.07
JAM075	Group-B	Unas.	Mimbres Corrugated	Pottery	TAM	NM	Old Town	LA 001113	3.48								29.12
JAM076	Group-B2	Mimbres-02A	Mimbres B/W Style Indeter. Pottery	Pottery	TAM	NM	NAN	LA 002465	0.00	39.18 0	0.4157 (0.00	5.84 4	4.39 2.91	91 68.92	6.48	35.63
JAM077	Group-B2	Mimbres-02A	ndeter.	Pottery	TAM	NM	NAN	LA 002465	0.00								32.97
JAM078	Group-A	Mimbres-10		Pottery	TAM	ΣN	NAN	LA 002465	2.42	51.07					_		21.97
JAM079	Group-B1	Mimbres-04A	Mimbres Corrugated	Pottery	TAM	NM	Pueblo Vinegaroon	LA 073824	3.90						3.50 97.56		18.00
JAM080	Group-B1	Mimbres-05A	ndeter.		TAM	N N	NAN	LA 002465	1.76								53.42
JAM081	Group-A	Mimbres-10		Pottery	TAM	M	McSherry	LA 015050	2.01			_			1		26.02
JAM082	Group-B1	Mimbres-04A		Pottery	TAM	NM	McSherry	LA 015050	3.11								18.58
JAM083	Group-B1	Mimbres-04A	Mimbres Corrugated	Pottery	TAM	M	NAN	LA 002465	2.59			0.00			2.85 86.77	7 5.80	26.31
JAM084	Group-C2b	Mimbres-41	Mimbres B/W Style II	Pottery	TAM	M	NAN	LA 002465	0.00							_	26.39
JAM085	Group-B	Unas.		Pottery	TAM	NM	NAN	LA 002465	3.64							1	44.16
JAM086	Group-C2a	Mimbres-49A	Mimbres Corrugated	Pottery	TAM	NM	LA 005841	LA 005841	1.58					2.73 3			57.27
JAM087	Group-A	Mimbres-10		Pottery	TAM	M	Pueblo Vinegaroon	LA 073824	3.17	53.54	1.2267 (0.00	11.07	5.11 8.	1		26.36
JAM088	Group-C2a	Mimbres-49A		Pottery	TAM	M	Pueblo Vinegaroon	LA 073824	0.00	_						1	49.55
JAM089	Group-A	Mimbres-10	Mimbres Corrugated	Pottery	TAM	M	Pueblo Vinegaroon	LA 073824	3.15								35.84
JAM090	Group-B	Unas.	Mimbres Corrugated	Pottery	TAM	M	Pueblo Vinegaroon	LA 073824	1.49	36.65 0		0.00		2.92 3.	3.03 57.63		21.48
JAM091	Group-C2a	Mimbres-49A	Mimbres Corrugated	Pottery	TAM	NM	LA 005841	LA 005841	0.00					2.14 2.			53.07
JAM092	Clay		Clay	Clay, Hearth	TAM	NM	Lake Roberts Vista	LA 071877	3.56								47.43
JAM093	Group-C2a	Group-C2a Mimbres-42	Mimbres B/W Style Indeter. Pottery	Pottery	TAM	N	NAN	LA 002465	1.79	39.17 0	0.2790	0.00	5.69 0	0.83 2.	2.17 76.92	16.24	52.80

\ IT	2832.3 43.27	3.7 61.72				5346.3 97.00	2666.9 47.99	11.1 37.52	2387.3 44.07	2728.5 54.10	0.7 49.29	3563.9 51.33	1722.9 39.23	2306.1 51.90	2324.6 49.09	2935.3 48.75	2840.8 47.18	13.1 72.56	2910.2 50.72	3190.4 62.58	3940.8 83.81	3104.4 46.17	9.1 60.06	1709.6 41.99							2861.8 50.47		7.1 58.95	78.77	3942.4 64.05		2353.6 49.54	4298.3 79.46	2812.3 55.82	2252.6 50.15	4311.6 83.90	l
NA								3.9 2221.1			2.0 2000.7							9.7 3833.1					4.4 2089.1	ľ									9.6 3517.1	1.4 4222.7								
MN	11628.4	14989.7		179.8 13303.0		18410.7	13031.4	14723.9	0.5 12950.0	392.6 14465.3	7332.0	1.5 13701.2	.5 7567.3	1.1 4105.6	0.7877.0	7.0 16094.0		.2 14389.7	5.5 11811.3	192.2 16721.3	1.7 17875.5	_	.7 10944.4	96.8 3240.7				, 1,		Ι,	432.1 13144.8	١,	14759.6	702.8 14161.4	.1 10770.3	14973.9	11001.5	763.2 14691.3	.6 9580.3	2.2 8517.1	.5 12625.4	l
×	0.0 306.1	0.0 464.9			0.0	0.0 790.4	0.0 319.7	0.0 354.4	0.0 1389.5	0.0	0.0 220.9	0.0 284.5	0.0 399.5	0.0 560.1	0.0 237.0	0.0 527.0	0.0 376.9	0.0 411.2	0.0 335.5	0.0	0.0 334.7	0.0 478.1	0.0 271.7	0.0		0.0 367					0.0 432.1		0.0 340.2	0.0	0.0 661.1	0.0 380.9	0.0 554.2	0.0	0.0 281.6	0.0 162.2	0.0 261.5	
DΥ	184	980.9	7.156	5.562	101	986.9	8.568	111	22	7.165	8.135	4.244	7.998	7.297			5.549	4.718		11:	5.385		7.077							17.			137	3.899	4.936	5.409	78	22	7.895	42	.41	
CA	0.0 3.084	0.0			0.0 9.301	0.0	0.0	0.0 5.011	0.0 5.157	0.0	0.0	0.0	0.0	0.0	0.0 3.597	0.0 5.582	0.0 5.5	0.0	0.0 12.933	0.0 4.211	0.0	0.0	0.0	0.0		0.0 5.984					0.0 12.832		0.0 4.937	0.0	0.0	0.0	0.0 12.178	0.0 4.657	0.0	0.0 5.442	0.0 4.741	
BA	647.1	841.9	545.9	735.4	512.2	912.2	721.9	615.5	847.1	771.6	491.2	776.4	719.8	598.9	843.2	931.2	9.806	7.098	342.7	572.1	910.8	914.4	773.5	9.189	1071.4	648.6	599.3	662.2	819.9	824.6	705.9	952.3	781.9	898.5	538.6	1384.4	771.4	844.4	754.7	937.5	1369.8	
AL	80605.7 6	80260.9 8				81723.6 9	80952.4 7	83416.4 6	81529.8		91863.9 4		78457.4 7	92197.4 5	82394.6 8	80218.6 9	82427.1 9	83983.0 8	87338.7 13	83221.9 5	91693.9	84516.0	90935.0 7	81950.6 6							81871.7	_		77733.3 8	79015.5 5	89470.0 13	83038.2 7	90375.8 8	94190.7 7		94113.6 13	
ZN ZR	48.4 145.2	187.0		184.5	134.1	79.0 229.3	61.8 162.8	46.5 152.0	52.7 142.9	65.7 198.9	93.9 149.8	56.2 248.7	64.0 188.2	132.3 185.8	49.0 159.3	51.2 232.3	54.9 176.7	74.7 230.7	106.7 238.3	57.0 199.8	71.7 259.4		110.6 163.4	197.7	157.1	197.9	205.8	176.7	250.4		56.7 314.5	189.6	58.7 270.1	62.2 151.9	157.0	67.6 393.6	63.8 158.0	68.5 217.6	85.2 131.6	75.3 171.9	62.0 240.0	
王	26.86 4	18.87 6				6.69	35.48 6	45.96 4	19.86 5		32.12	18.22 5	31.32 6	36.57 13	18.26 4	19.59 5	27.89 5	20.15 7	47.21 10	20.63 5	12.91	18.24 11	28.55 11								30.34 5		17.99 5				32.56 6	12.35 6	34.46 8	31.83 7		
TB	0.59	1.13	1.16	1.03	1.52	1.43	1.45	0.93	0.74	1.16	1.19	0.87	1.44	1.32	09.0	0.87	1.13	0.87	2.80	0.79	0.98	1.02	96.0	1.32	0.88	1.02	0.76	0.80	1.33	1.09	1.91	0.88	0.80	99.0	89.0	06.0	1.88	0.74	1.04	98.0	97.0	
TA	1.8300				2.4177	0.9309	2.3150	1.5267	1.2181	1.1884	1.6604	1.3892	1.8644	2.3739	1.2305	1.4194	1.3663	1.7194	3.4775	1.5425	1.0619	1.2128	2.5495	2.4807							3,8654		1.3826	0.9993	1.4329		2.1081	1.1267	2.2221	1.2701	0.9842	
SR	185.1			3	83.1	423.1		172.8	201.1	230.4	9.96	248.1	102.2	0.0	265.6	263.1	264.4	281.1	111.7		372.3		96.4	`							110.7	280.9	280.1	499.4	248.6	452.3	246.1	394.1	159.0	164.0	381.2	
3 SC	6.74	7.40	_	1		12.04	1 8.84	7.46	5 6.55		7 8.52	2 7.25	3 7.00	3 9.98	1 6.67		1 7.58	7 9.45	7 12.06	5 11.42	5 10.36		9.60			3 9.76	_			,	7.76		90.8	97.7	9 8.29	3 10.39	5 8.26	0 10.28	5 10.20	5 8.20	10.59	
SI	0.6016	0.4862	0.701	0.4941	0.7220	0.5140	0.6641	0.3612	0.3575	0.3671	0.5687	0.3732	1.0513	0.7273	0.3831	0.4405	0.3551	0.5087	0.5617	0.5576	0.4826	0.1830	0.5136	0.4869	0.3887	0.5548	0.3935	0.4517	0.4409	0.3126	0.4012	0.3295	0.3510	0.4099	0.7409	0.2743	0.5065	0.4570	0.4455	0.2686	0.2874	
RB	194.32	122.11	277.08	122.83	270.69	91.34	231.55	171.73	129.89	105.30	247.82	117.89	284.33	303.55	128.85	130.73	115.42	119.05	240.99	129.70	92.81	119.71	239.24	301.03	334.88	259.32	143.31	134.30	235.08	131.70	226.82	121.08	140.35	86.24	155.31	98.41	223.87	112.60	200.56	169.44	88.21	
Z	0.0	0.0			0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0		0.0	0.0	0.0	0.0	0.0	0.0	0.0		0.0					0.0		0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	
生	6.17	7.42	6.13	6.35	2.67	8.23	6.78	4.94	4.93	6.07	2.68	8.91	629	5.59	5.92	7.08	5.89	7.92	7.02	6.95	8.80	6.32	5.29	5.79		5.85	6.62	6.06	7.15	5.75	8.16	4.94	7.65	6.10	6.92	15.62	6.57	7.09	6.20	6.93	9.54	
FE	22364.4				32795.6	41063.9	24275.5	20443.7	19267.5	29265.2	31258.7	24894.0	23374.7	63709.0	23692.9	24715.8	28022.6	30355.5	34877.4	26770.7	37210.2	27697.0	28045.2		40187.0	30333.6					22477.2	23889.8	25941.8	31189.7	25391.6	38689.8	28445.9	36324.0	29271.6	25425.4	32257.5	
EU	0.7347	1.5455		1.5378		2.6405	1.1464	1.0391	1.1386	1.5954	0.8225	1.2329	1.2061	0.9834	1.0759	1.2759	1.4692	1.2463	1.8930	1.0699	1.6028	1.5260	0.9258	1.0459							1.6512	1.4252	1.3325	1.2934	1.0931		1.2334	1.5053	0.8385	0.7297	1.4037	
CS	6.05	3.55	9.46	9.03	7.74	2.98	5.83	8.21	3.72	4.09	8.43	3.91	15.06	10.23	4.80	4.31	3.71	5.16	12.04	12.05	2.93	3.46	12.10	8.65	6.01	10.02	17.26	15.20	5.25	4.01	6.50	3.66	4.75	3.48	7.18	3.13	6.75	3.29	9.88	4.73	3.21	
ANID	JAM050	JAM051	JAM052	JAM053	JAM054	JAM055	JAM056	JAM057	JAM058	JAM059	JAM060	JAM061	JAM062	JAM063	JAM064	JAM065	JAM066	JAM067	JAM068	JAM069	JAM070	JAM071	JAM072	JAM073	JAM074	JAM075	JAM076	JAM077	JAM0/8	JAM0/9	JAM081	JAM082	JAM083	JAM084	JAM085	JAM086	JAM087	JAM088	JAM089	JAM090	JAM091	

ANID	macro arp	Chem2012	CERAMIC TYPE	MATERIAL	SOURCE	E STATE	SITE NAME	SITE NO	AS	ΓP	In	ND SM	n	YB	CE	00	CR
JAM095	Group-B2	Mimbres-02A	Mimbres B/W Style Indeter. Pottery	Pottery	TAM		NAN	LA 002465		40.95 0.4618		0.00 6.02	2 4.49	3.26	72.69	7.35	37.81
JAM096	Group-B1	Mimbres-04A	Mimbres B/W Style Indeter. Pottery	Pottery	TAM	MN	NAN	LA 002465	5.72	59.58 0.5872	72 0.00	00 10.50	3.70	3.97	118.99	91.9	20.27
JAM097	Group-B1	Mimbres-04A	Mimbres Corrugated	Pottery	TAM	MN	Pueblo Vinegaroon	LA 073824	3.75	50.79 0.5151		0.00 8.22	2 2.71	3.94	69.16	6.42	16.99
JAM098	Group-B2	Mimbres-02A	Mimbres Corrugated	Pottery	TAM	MN	McSherry	LA 015050	1.76	36.41 0.4410		0.00 5.50	0 4.83	2.80	59.45	4.15	27.20
JAM101	Group-B	Unas.	1	Pottery	TAM	NN	Old Town	LA 001113				0.00 10.35	5 3.60	5.33	122.53	6.30	26.79
JAM102	Group-C2b	Mimbres-41	Mimbres B/W Style II	Pottery	TAM	M	NAN	LA 002465		33.07 0.3037		0.00 4.66	5 1.19	2.17	64.44	9.76	23.88
JAM103	Group-C2b	Mimbres-41	Punctated	Pottery	TAM	M	NAN	LA 002465	1.37	35.62 0.2865		0.00 4.93	3 1.24	2.24	71.11	10.96	26.07
JAM104	Group-B	Unas.	Mimbres Corrugated	Pottery	TAM	NN	McSherry	LA 015050	7.09	42.06 0.5174		0.00 6.51	1 2.13	4.20	95.38	5.25	22.19
JAM105	Group-C2a	Mimbres-49A	Mimbres Corrugated	Pottery	TAM	NM	LA 005841	LA 005841		44.83 0.3815		0.00 7.75	5 1.55	3.08	87.15	7.86	58.49
JAM107	Group-C2a	Mimbres-42	Mimbres B/W Style Indeter. Pottery	Pottery	TAM	MN	NAN	LA 002465	2.14	40.77 0.3269	00.0 69	90 6.18	3 1.19	2.16	81.67	16.49	54.52
JAM108	Group-C2a	Mimbres-49A	Mimbres Corrugated	Pottery	TAM	MN	LA 005841	LA 005841	00.0	42.25 0.4368	00.0 89	7.74	1.88	2.91	94.37	7.75	25.66
JAM109	Group-B	Unas.	Mimbres Corrugated	Pottery	TAM	MN	Pueblo Vinegaroon	LA 073824	3.07	51.39 0.5112		0.00	5.36	3.22	87.14	5.18	17.41
JAM110	Group-C2b	Mimbres-41	Mimbres Corrugated	Pottery	TAM	MN	McSherry	LA 015050		35.51 0.3419	119 0.00	5.11	1.62	1.66	73.08	11.29	27.80
JAM111	Group-C2a	Mimbres-42	Mimbres B/W Style Indeter. Pottery	Pottery	TAM	MN	NAN	LA 002465	1.52	37.90 0.3366		0.00 5.93	3 1.47	1.95	78.26	16.98	58.02
JAM112	Group-B1	Mimbres-04C	Mimbres Corrugated	Pottery	TAM	MN	McSherry	LA 015050	2.34	38.28 0.3806		0.00 5.33	3 3.04	2.76	63.79	8.20	32.72
JAM113	Clay		Clay	Clay, Wall Pla	PIETAM	MN	Lake Roberts Vista	LA 071877	2.09	35.85 0.3390		0.00 6.28	3 1.81	2.29	88.99	16.62	68.81
JAM114	Group-B1	Mimbres-04C	Mimbres B/W Style II	Pottery	TAM	MN	NAN	LA 002465		32.63 0.3726	726 0.00	00 4.47	7 4.18	2.39	55.85	5.05	31.86
JAM115	Group-B1	Mimbres-05A	Mimbres B/W Style Indeter. Pottery	Pottery	TAM	MN	NAN	LA 002465		54.64 0.5594		0.00 8.81	1 2.93	4.38	96.62	6.79	54.66
JAM116	Group-A	Mimbres-10	Mimbres Corrugated	Pottery	TAM	M	NAN	LA 002465	3.38	60.55 0.7628		0.00 8.43	3 3.59	5.01	115.09	4.45	43.23
JAM117	Group-C2	Unas.		Pottery	TAM	MN	Old Town	LA 001113	4.08	32.77 0.3502		0.00 5.60	1.54	2.47	62.77	15.88	48.33
JAM118	Group-B	Unas.	Mimbres Corrugated	Pottery	TAM	M	Lake Roberts Vista	LA 071877	1.47	39.52 0.3256		0.00 6.01	1.38	2.41	83.02	11.22	34.78
JAM119	Group-B1	Mimbres-04A		Pottery	TAM	MN	Lake Roberts Vista	LA 071877	7.39	43.71 0.3843		0.00 5.73	3 3.64	2.53	76.73	4.04	19.32
JAM120	Group-C2a	Mimbres-49A		Pottery	TAM	M	Lake Roberts Vista	LA 071877	1.26	39.65 0.4277		0.00 6.36	5 2.07	2.26	72.63	7.29	41.04
JAM121	Group-C2	Unas.		Pottery	TAM	MN	Old Town	LA 001113	2.67	36.80 0.2360	00.0 099	50 6.13	3 2.40	2.08	82.89	8.50	23.80
JAM122	Group-B	Unas.	Mimbres Corrugated	Pottery	TAM	MN	Old Town	LA 001113	1.06	8088 0.8308		0.00 13.54	3.70	5.19	134.36	5.30	21.55
JAM123	Group-A	Mimbres-10	Mimbres Corrugated	Pottery	TAM	M	McSherry	LA 015050						6.29	100.63		27.88
JAM124	Group-A	Mimbres-01	ndeter.	Pottery	TAM	MM	NAN	LA 002465						2.52	84.60	1.91	10.41
JAM125	Group-A	Mimbres-10		Pottery	TAM	NM	NAN	LA 002465				0.00 7.75		3.96	68.54	2.94	20.06
JAM126	Group-B	Unas.	Mimbres Corrugated	Pottery	TAM	NM	McSherry	LA 015050	1.84	60.04 0.5812		0.00 11.33	3 3.59	3.92	111.96	2.81	16.79
JAM127	Group-B	Unas.		Pottery	TAM	MN	Old Town	LA 001113						3.73			32.35
JAM128	Group-C2	Unas.		Pottery	TAM	M	Lake Roberts Vista	LA 071877						2.68			143.50
JAM129	Group-B	Unas.		Pottery	TAM	M	Lake Roberts Vista	LA 071877						2.27			67.52
JAM130	Group-C2a	Mimbres-49A		Pottery	TAM	Z	Lake Roberts Vista	LA 071877		_				3.00			71.93
JAM131	Group-B	Unas.		Pottery	TAM	Z	Lake Roberts Vista	LA 071877						2.85			99.79
JAM132	Group-C2a	Mimbres-49A		Pottery	TAM	M	Lake Roberts Vista	LA 071877						2.59			67.31
JAM133	Group-B1	Mimbres-05A		Pottery	TAM	M	Lake Roberts Vista	LA 071877						3.75		7.82	44.71
JAM134	Group-B1	Mimbres-05A	Mimbres Corrugated	Pottery	TAM	MM	Lake Roberts Vista	LA 071877	7.69					3.20	87.41	14.99	61.18
JAM135	Group-A	Mimbres-10		Pottery	TAM	MM	Old Town	LA 001113	4.11	37.53 0.9411	111 0.00	00 6.52		6.79	85.21	6.14	33.47
JAM136	Group-C2b	Mimbres-47		Pottery	TAM	MM	Old Town	LA 001113		40.25 0.2356				1.74	84.14	4.69	26.01
JHK001	Group-B2	Mimbres-02A		Pottery	MURR	Mexico	Calderon	Ch-254		41.30 0.5262		78 5.50		3.37	66.54		37.42
JHK002	Group-B2	Mimbres-02A		Pottery	MURR	Mexico	Calderon	Ch-254	3.30			31 7.04	4 3.91	4.10	85.07	8.82	37.71
JHK003	Group-B2	Mimbres-02A	Mimbres B/W Style III	Pottery	MURR	Mexico		Ch-254							86.00	8.98	38.24
JHK004	Group-A	Mimbres-01		Pottery	MURR	Mexico		Ch-254					_		97.31	2.55	4.57
JHK005	Group-B	Unas.		Pottery	MURR	Mexico	Calderon	Ch-254	2.07	45.22 0.4762	'62 35.61	51 6.86	5.68	3.15	91.04	8.86	52.62

ANID	macro_grp	Chem2012	CERAMIC TYPE	MATERIAL	SOURCE	STATE	SITE_NAME	SITE_NO	AS	ΓA	Π	ND SM	n W	J YB	CE	00	CR
3HK006	Group-C1	Mimbres-23		Pottery	MURR	Mexico	Calderon	Ch-254	5.13	36.26 0.3	0.3672 29	29.28 5.99	3.22	2 2.55		11.63	39.70
JHK007	Group-B2	Mimbres-02A		Pottery	MURR	Mexico	Calderon	Ch-254	3.19		0.5587 37	37.59 7.14	4 3.94	4 3.93	81.57	8.43	41.56
JHK008	Group-B2	Mimbres-02A*		Pottery	MURR	Mexico	Calderon	Ch-254	4.38	36.90 0.4	0.4766 27	27.05 5.80	30 6.46	3.16	63.18	4.81	34.40
KCW001	Group-B1	Mimbres-04B	Mimbres B/W Style III	Pottery	MURR	MN	LA 015187	LA 015187	3.05	54.37 0.5	0.5402 42	42.62 7.67	6.14	3.55	102.82	5.41	21.78
KCW002	Group-A	Mimbres-03	Mimbres B/W Style I	Pottery	MURR	M	LA 015187	LA 015187	3.27	40.25 1.2	1.2552 36	36.32 9.66	99. 7.85	5 9.41	91.70	2.71	11.04
KCW003	Group-B1	Mimbres-05A	Mimbres B/W Style II	Pottery	MURR	NM	LA 015187	LA 015187	2.95	48.51 0.6	0.6726 40	40.08 9.12	3.80	0 4.63	122.21	68'5	52.59
KCW004	Group-B	Unas.	Mimbres B/W Style II	Pottery	MURR	NM	LA 161345	LA 161345	1.85	35.33 0.4	0.4898 23	23.06 4.53	5.15	5 3.00	66.42	7.08	28.72
KCW005	Group-A	Mimbres-10	Corrugated	Pottery	MURR	NM	LA 161345	LA 161345	1.79	67.41 0.9	0.9107 53	53.04 10.12	3.15	5 6.85	104.92	4.27	20.64
KCW006	Group-A	Mimbres-07A	Plain	Pottery	MURR	MM	LA 161347	LA 161347	`			143.90 28.86	5.83	3 12.06			46.46
KCW007	Group-A	Mimbres-10	Plain	Pottery	MURR	MN	LA 161347	LA 161347	3.56		0.8186 117	111.68 21.65		0.44		10.34	39.49
KCW008	Group-A	Mimbres-07A	Reserve, no corrugations	Pottery	MURR	MN	LA 161357	LA 161357	3.86	154.88 1.3	1.3365 134	134.18 26.16	6 4.53	3 11.62	375.09	19.10	45.20
KCW009	Group-A	Mimbres-10	Obliterated corrugated	Pottery	MURR	MN	LA 161357	LA 161357	2.78	80.36 1.0	1.0154 70	70.43 14.82	32 4.25	5 7.91	145.42	96'9	37.51
KCW010	Group-A	Mimbres-07A	Plain	Pottery	MURR	MN	LA 161359	LA 161359	0.00	158.59 1.1	1.1951 135	135.19 26.34	4 6.06	5 10.08	326.44	7.24	33.02
KCW011	Group-B1	Mimbres-05A	Mimbres B/W Style III	Pottery	MURR	MN	LA 161361	LA 161361	3.81	49.24 0.6	0.6238 50	50.37 10.19	9 4.60	0 4.72	113.38	9.31	54.40
KCW012	Group-A	Mimbres-10	Corrugated	Pottery	MURR	M	LA 161361	LA 161361	3.82	60.24 1.4	1.4944 54	54.57 11.87	37 7.48	3 11.18	157.34	6.59	29.67
KCW013	Group-A	Mimbres-10	Obliterated corrugated	Pottery	MURR	MM	LA 161362	LA 161362	2.59	94.49 0.8		89.77 16.87	37 5.46	6.34	165.09	5.03	28.30
KCW014	Group-B	Unas.	Mimbres B/W Style III	Pottery	MURR	MM	LA 161362	LA 161362	1.89	51.05 0.6							27.74
KCW015	Group-C1	Mimbres-21	Mimbres B/W Style III	Pottery	MURR	MN	LA 161368	LA 161368	2.70	37.23 0.3	0.3507 30	30.63 5.60	1.55	5 2.91	79.09	11.72	77.31
KCW016	Group-B1	Mimbres-05B	Oblit corrugated	Pottery	MURR	MN	LA 161368	LA 161368	3.13	55.05 0.7	0.7428 50	50.55 9.61	3.86	5.98	149.77	91.9	24.24
KCW017	Group-B1	Mimbres-04B	Mimbres B/W Style III	Pottery	MURR	MN	LA 125819	LA 125819	2.27	53.16 0.5	0.5774 38	38.74 7.81	31 7.65	5 3.79	98.10	90.9	24.89
KCW018	Group-B1	Mimbres-04B	Mimbres B/W Style III	Pottery	MURR	¥	LA 161374	LA 161374	1.92	50.84 0.5	0.5456 38	38.84 7.42	12 6.51	1 3.61	96.70	4.39	24.67
KCW019	Group-A	Mimbres-10	Obliterated corrugated	Pottery	MURR	MN	LA 161374	LA 161374	3.81	58.96 0.8	0.8157 47	47.29 9.69	9 4.17	6.36	67.63	4.24	24.15
KCW021	Group-A	Mimbres-10	Corrugated	Pottery	MURR	M	LA 161375	LA 161375	2.29	116.48 1.1	1.1618 97	91.41 19.14	4 5.37	89.8	173.35	5.21	32.90
KCW023	Group-A	Mimbres-10	Obliterated corrugated	Pottery	MURR	M	LA 161376	LA 161376	3.71		1.0111 37			3 6.85	74.85		26.44
LOA001	Group-B1	Mimbres-05B	Alma Plain	Pottery	MURR	M	East Fork	LA 011074	4.44	50.14 0.7	0.7801 45	45.86 9.78	78 4.03	3 6.05	101.18	8.71	42.67
LOA002	Group-B	Unas.	Alma Plain	Pottery	MURR	M	East Fork	LA 011074	3.27				3.82		-	_	47.29
LOA003	Group-B1	Mimbres-04A	Alma Plain	Pottery	MURR	M	East Fork	LA 011074	1.93								19.27
LOA004	Group-B1	Mimbres-05B	Alma Plain	Pottery	MURR	M	East Fork	LA 011074	3.12	45.05 0.7						,	42.68
LOA005	Group-B1	Mimbres-05B	Corrugated	Pottery	MURR	M	East Fork	LA 011074	5.16	67.63 1.0			1 4.59	7.56	•		43.98
LOA008	Group-A	Mimbres-03	Indeter. Whiteware	Pottery	MURR	M	East Fork	LA 011074	2.24	47.64 1.1	1.1692 46	46.84 11.85	35 6.11			2.56	14.79
LOA009	Group-A	Mimbres-03	Indeter. Whiteware	Pottery	MURR	M	East Fork	LA 011074	1.35		4				_		89.6
LOA010	Group-B	Unas.	Corrugated	Pottery	MURR	M	East Fork	LA 011074	3.87	_							41.82
LOA011	Group-B	Unas.	Corrugated	Pottery	MURR	M	East Fork	LA 011074	4.50	55.27 0.6		52.65 10.21	_			10.63	39.73
LOA012	Group-B1	Mimbres-05B	Corrugated	Pottery	MURR	MM	East Fork	LA 011074	7.60	65.00 1.1	1.1322 65	65.26 16.05	15 6.97	8.97	135.84	8.80	44.94
LOA015	Group-A	Mimbres-03	Mimbres B/W Style I	Pottery	MURR	MM	East Fork	LA 011074	2.45	42.67 1.3	1.3844 43	43.09 11.52	52 7.08	3 10.11	98.94	2.80	7.78
LOA016	Group-C1	Mimbres-24	Mimbres B/W Style I	Pottery	MURR	MN	East Fork	LA 011074	4.94	42.16 0.5	0.5203 38	38.16 7.89	39 2.48	3 3.98	85.10	14.06	45.04
LOA017	Group-C1	Mimbres-21	Mimbres B/W Style III	Pottery	MURR	MN	East Fork	LA 011074	3.26	41.72 0.4	0.4285 36	36.20 6.42	1.80	3.22	87.68	10.06	63.24
LOA018	Group-C1	Mimbres-21	Mimbres B/W Style III	Pottery	MURR	MN	East Fork	LA 011074	2.36	38.97 0.3	0.3382 34	34.86 6.06	1.20	0 2.40	83.27	12.56	51.19
LOA019	Group-C1	Mimbres-21	Mimbres B/W Style III	Pottery	MURR	Z	East Fork	LA 011074	4.30	43.16 0.3	0.3811 33	33.85 6.55	1.89	3 2.82	86.77	12.72	60.36
LOA021	Group-A	Mimbres-03	Indeter. Whiteware	Pottery	MURR	MN	East Fork	LA 011074	3.37	53.31 1.4	1.4243 52	52.62 13.02	0.75	5 11.18	106.11	3.07	10.54
LOA024	Group-A	Mimbres-03*	Indeter. Whiteware	Pottery	MURR	MN	East Fork	LA 011074	12.37	42.83 1.3	1.3880 37	37.95 10.77	71 8.04	10.90		2.46	7.39
LOA025	Group-A	Mimbres-03	Indeter. Whiteware	Pottery	MURR	M	East Fork	LA 011074	3.09			_			1		9.07
LOA026	Group-B	Unas.	Reserve Indented Smudged Pottery	Pottery	MURR	M	East Fork	LA 011074	2.40								47.05
LOA027	Group-B	Unas.	Reserve Indented Smudged Pottery	a Pottery	MURR	MN	East Fork	LA 011074	4.60	67.94 0.6	0.6428 66	66.08 12.37	37 2.94	4 5.28	117.15	11.20	40.32

>	84.44	64.26	57.44	47.97	13.19	68.21	36.52	44.09	70.73	75.38	83.35	66.15	60.07	91.72	57.57	42.20	49.71	57.87	39.92	47.05	42.38	57.49	51.38	46.84	45.82	57.95	53.24	51.23	26.58	24.87	11.19	66.62	69.27	72.46	7.06	86.48	50.51	47.69	81.92	25.53	15.05	19.65	80.01	73.90
F	4038.0	4961.8	3929.6	2574.6	1659.3	4844.2	2899.2	2477.9	5691.3	3129.1	6400.0	2993.0	5414.2	4221.4	3054.4	2832.4	3078.5	2589.8	3221.5	2564.0	2786.5	3010.2	2471.5	2117.9			3166.9	3165.7	3169.5	1584.0	1510.8	3857.5	4318.9	3068.4	1437.0	4245.7	2747.8	2065.6	2442.5	1272.2	1390.8		3364.4	4506.5
NA	12076.6	7	11346.9	11488.7	5771.8	2608.9	5158.2	11444.2	19163.6	16099.5	15806.6	13325.6	19295.2	12888.6	14242.4	3300.8	12587.3	19919.0	3959.3	11084.0	11220.1	10290.7	14866.9			14522.8									5129.9		20024.6	13465.3	18735.4		7282.3			5181.5
MN	588.6 12	447.9 13	377.9 11	329.9 11	654.5	_	284.3 15	178.9 11	277.2	964.7 16		568.5 13	226.5 19	422.0 12	387.5 14	271.0 13	300.6 12	1058.9 19	743.5 13	529.9 11	198.9	232.1 10	313.5 14		724.7	837.1 14	_		`					_	650.5	525.3 18		776.6 13	942.0 18	685.1			_	693.5 15
¥	27511.7	26706.9	28647.9	28863.7	46372.0	28048.6	34427.8	36468.1	35719.5	35180.1	31947.8 1	30122.1	33844.6	23214.4	33184.8	34578.8	29426.7	28163.0 1	35996.3	30497.3	30461.1	36310.4	35461.4	37412.0	32313.7				28482.2	44303.4		_	29612.7	3	42262.7	24672.9	30982.3 1	19685.9	24746.0		60116.1	47063.1	26555.7	28238.8
Dγ	4.088 2	5.590 2	4.682 2	5.484 2	11.412 4	8.139 2	3.432 3	11.143 3	23.999 3	16.316 3	23.230 3	13.319 3	22.185 3	8.426 2	12.689 3	12.830 3	5.353 2	3.493 2	7.863 3	5.656 3	5.087 3	8.872 3	17.045 3	8.501 3				_				- 1	- 1	_	12.811 4	5.840 2		2.994 1	3.851 2	14.961 5	12.586 6		- 1	8.010 2
CA	53105.0	14681.2	9084.1	7976.5	34964.7	13569.6	8317.3	8365.9 1	10415.0 2	11260.8	12820.1	11291.5	11247.9 2	14605.0	8841.5		8892.2	15182.6	9876.4	8088.1	7982.6	15112.0	7067.8	15058.9	15520.3	12272.4	13520.0				`	12312.4				11737.2	8730.7	14169.3	11663.2		8407.5	_		10858.8
BA	8.029	670.2	206.0	9.897	807.1	651.6	593.0	1152.7	1353.1	1489.0	1194.0	927.0	1469.0	595.0	7.997	1095.3	682.1	1072.6	726.4	637.8	637.5	813.0	802.8	858.7	720.9	9.989	928.6	563.2	542.3	218.4	106.3	704.7	614.0	433.3	147.4	594.0	8.908	673.4	7.697	227.4	155.4	52.8	669.3	743.2
AL	76213.3	90416.9	83140.6	83586.3	78125.8	83928.9	81773.4	87989.9	85797.4	88792.0	85393.6	89351.7	90912.9	91893.4	92179.3	87406.8	83517.4	91691.2	87253.4	0.77806	93620.6	89691.8	01187.0	8.68956	80707.1	78448.1	86377.7	74545.9	84684.2	90089.3	77512.2	80283.4	79598.5	88860.5	79892.1	00513.5	86852.1	70975.9	96415.7	81610.7	81739.6	81111.1	84644.6	84485.7
ZR	123.5	202.4	161.7	222.7	203.2	255.6	205.8	260.3	539.0	279.6	508.1	182.2	525.9	244.0	248.2	285.7	220.8	199.5	253.0	189.4	172.7	276.6	230.6	141.8				243.6	235.1	200.7	206.7	210.2	202.6	261.8	210.3	223.3	215.9	200.6	186.5	205.8	205.8	201.4		263.8
NZ	79.8	77.3	62.1	52.1	189.8	84.4	55.4	80.7	118.4	97.5	120.7	75.2	105.6	83.5	8.79	75.6	84.2	94.5	78.5	62.2	8.09	114.5	95.3	95.1	107.2	110.4	73.5	85.4	94.2	99.3	81.2	92.1	93.1	83.9	99.4	92.0	1.68	91.2	105.3	143.9	118.3	6.99	76.8	102.3
TH 8	7 12.32	9 22.00	3 21.94	9 27.92	34.39	17.10	1 23.17	5 45.21	39.05	99.09		38.12	35.01	5 16.72	34.62	34.79	1 23.98	1 9.05	3 20.18	7 26.10	1 26.49	2 46.95	146.61			7 20.52								1 23.71		11.66	10.97	96.6	5 10.35	37.22				16.27
TA TB	1 0.77	3 0.99	2 0.68	66'0 9	3 1.95	3 1.39	19.0 8	5 1.65	0 4.50	3.13	5 4.28	7 2.30	3.99	5 1.55	1 2.16	7 2.51	8 0.91	0 0.64	7 1.38	3 0.97	9 0.94	5 1.42	8 3.10	1.21	7 1.79	2 1.47	1.09	_			•		8 1.53	_	7 2.23	1.14	4 0.82	1 0.75	8 0.75	9 2.41	3 2.04		0.98	3 1.61
	0.9811	1.376	1.6472		3 2.2723	5 1.4803	9 1.8348	1 2.8645	5 2.0620	3 1.1064	1.9805	1 2.1707	1.6228	1.1985	3.0921	1.3817	5 1.4528	1 0.6510	1.8137	1.5213	1.5899	5 3.3035	9 2.5448	1 2.4186	1.8217	3 1.6262	3 1.3199								5 2.3271	1.0769	0.8524	0.7801	9 0.7238	1 2.4349	3 2.5383			1.5583
SR	590.1	435.7	204.2	167.7	128.3	228.5	207.9	219.1	197.6	160.3	154.0	132.1	231.1	295.4	98.2	149.4	174.5	394.4	209.0	151.0	169.7	199.5	139.9	121.1		242.3			7			274.7		_			303.1	332.0	358.9	70.4	64.3			272.9
SC	10.63	12.47	8.56	6.41	4.91	11.09	6.35	10.36	16.52	12.95	15.51	11.36	13.45	12.85	8.65		7.51	8.05	7.65	7.81	7.50	11.23	89.6	9.17		10.38			_					10.99		1	7.74	90.6	9.81	5.19	4.89			10.68
SB	0.8735	0.4383	0.8908	0.3682	0.9034	0.4755	0.4265	0.3799	0.2305	0.4608	0.3721	0.5082	0.2776	0.8217	0.5530	0.3200	0.4728	1.6883	0.7106	0.4519	0.4283	0.4552	0.5803	0.5003		0.5560	0.3043	0.4566	0.6318	0.4950	0.2606	0.5585	0.5652	0.5733	0.3833	0.6748		1.5412	1.7141	0.3948	2.7115	0.3898	0.4005	0.4909
RB	162.60	166.01	193.38	172.52	267.91	158.29	221.06	224.95	141.65	168.32	148.77	199.67	141.52	134.26	267.37	206.41	179.00	121.15	201.13	182.77	181.46	249.04	273.20	300.70	153.83	144.74	133.48	184.30	151.98	283.91	286.71	139.58	139.94	148.13	244.90	132.85	144.85	135.68	136.64	303.44	353.15	293.98	121.67	130.22
Ξ	33.4	0.0	0.0	0.0	0.0	27.6	16.3	0.0	69.4	50.4	65.7	0.0	55.8	0.0	0.0	32.8	17.1	37.1	0.0	15.5	0.0	0.0	0.0	0.0		22.8	0.0				_		_		0.0	0.0	19.8	32.4	0.0	0.0	0.0			50.2
生	4.68	7.54	96.9	8.20	10.34	9.95	8.42	10.75	18.84	10.11	18.16	7.18	20.03	8.93	9.50	9.43	7.32	7.58	10.20	6.53	6.16	11.15	7.88	6.14	9.45	9.20	6.56	9.71	9.62	98.6	10.05	8.82	89.8	9.41	10.15	8.57	8.21	7.28	7.18	10.90	11.36	66.6	10.19	10.01
FE	32160.0	31537.8	23811.5	21985.5	13324.7	29397.5	18009.7	29426.0	27847.5	42339.6	54408.6	31304.2	26197.3	29500.3	26540.4	28153.0	24206.1	32209.0	26639.2	1.3056 22893.1	1.2556 22812.4	29906.2	28699.4	33459.7	26722.3	33986.8	24341.1	26794.1	29913.7	16450.9	12512.3	30523.1	30753.1	30288.8	12826.4	41047.8	29218.6	34585.9	38386.8	14256.8	12933.9			1.9569 36688.4
EU	1.2174	1.3334	1.0367	1.3211	0.5224	1.4032	0.8533	1.0039	4.0888	2.8296	3.5834	1.9125	3.6117	1.6170	1.4162	2.0227	1.2443	1.2470	1.3650	1.3056	1.2556	6.71 0.9634	2.32 2.2269			1.3749	1.4828	1.2626	1.9526	0.6223	0.5457	1.7648	1.6984	2.0153	0.5855		1.3818	1.4181	1.4973	0.7515	4.06 0.5202	0.5384	0.9297	1.9569
CS	11.30	79.08	34.15	5.22	4.42	11.40		5.77	3.16	5.57	4.08	7.76	3.21	8.20	7.60		2.99	16.39	10.61	6.33	, 68.9	6.71	12.32													17.81		21.91	20.16	4.81	4.06	4.57 (4.40
ANID	JHK006	JHK007	JHK008	KCW001	KCW002	KCW003	KCW004	KCW005	KCW006	KCW007	KCW008	KCW009	KCW010	KCW011	KCW012	KCW013	KCW014	KCW015	KCW016	KCW017	KCW018	KCW019	KCW021	KCW023	LOA001	LOA002	LOA003	LOA004	LOA005	LOA008	LOA009	LOA010	LOA011	LOA012	LOA015	LOA016	LOA017	LOA018	LOA019	LOA021	LOA024	LOA025	LOA026	LOA027

ANID	macro grp	Chem2012	CERAMIC TYPE	MATERIAL	SOURCE	STATE	E SITE NAME	SITE NO	AS	ΓA	Π	ND	SM	n	YB	CE CO	CR
LOA028	Group-B	Unas.	Reserve Plain Smudged	Pottery	MURR			LA 011074	2.08	48.70	0.7515 3		7.73 4	4.59 4.	4.98 97.61	1 8.16	34.25
LOA030	Group-B1	Mimbres-05A	Reserve Plain Smudged	Pottery	MURR	MN	East Fork	LA 011074	2.29	48.49 0	0.6990 4	41.02	9.35	3.57 5.	5.53 107.56	6 14.74	57.90
LOA031	Group-B	Unas.	Reserve Plain Smudged	Pottery	MURR	MN	East Fork	LA 011074	0.00	63.01 0	0.9736 6	63.65 12	12.63 4	4.05 7.	7.70 135.67	7 4.83	30.23
LOA032	Group-B1	Mimbres-05B	Reserve Smudged	Pottery	MURR	MN	East Fork	LA 011074	4.26	63.88 0	0.6864 5	55.65 10	10.38 4	4.40 5.	5.03 109.09	9 12.22	27.60
LOA034	Group-B	Unas.	Alma Plain	Pottery	MURR	NM	Gatton Park	LA 011075	2.44								
LOA036	Group-C2	Unas.	Alma Plain	Pottery	MURR	MM	Gatton Park	LA 011075	1.92	31.88 0	0.2952 2	25.72 4	4.82 2		2.30 63.94	11.01	22.20
LOA037	Group-C2a	Mimbres-49B	Alma Plain	Pottery	MURR	Σ	Gatton Park	LA 011075	2.62	58.53 0	0.4567 5	57.53 10	10.52 2	2.36 3.	3.72 76.37	7 9.87	47.38
LOA038	Group-A	Mimbres-01	Indeter. Whiteware	Pottery	MURR	Σ	Gatton Park	LA 011075	3.75	_					-		
LOA040	Group-A	Mimbres-10	Corrugated	Pottery	MURR	NM	Gatton Park	LA 011075	2.35	71.51 0		`	11.91	11.23 4.	4.98 120.22	2 4.40	30.29
LOA042	Group-B	Unas.	Mimbres Corrugated	Pottery	MURR	MN	Gatton Park	LA 011075	1.85		0.5307 3	38.78 7	7.16 2		3.72 97.91	1 6.13	16.00
LOA043	Group-B1	Mimbres-04A	Mimbres B/W Style III	Pottery	MURR	MN	Gatton Park	LA 011075	3.73	44.58 0	0.4617 3	30.44 6	6.33 5	5.26 2.	2.88 83.35	5 4.11	22.19
LOA044	Group-C1	Mimbres-24	Mimbres B/W Style III	Pottery	MURR	MN	Gatton Park	LA 011075	2.29	38.95 0	0.4460 3	34.10 6	6.88 2	2.39 3.	3.44 80.21	14.33	33.77
LOA053	Group-B1	Mimbres-05B	Reserve Smudged	Pottery	MURR	MN	Gatton Park	LA 011075	2.63	58.58	0.9561 5	54.40 11	11.38 4	4.31 7.	7.41 119.49		30.10
LOA058	Group-B	Unas.	San Francisco Red - matte		MURR	MN	Gatton Park	LA 011075	3.73	66.45 0	0.8765 6	62.35 13	13.22 4	4.57 7.	7.55 145.09	9 10.50	41.99
LOA059	Group-B1	Mimbres-05A	Alma Plain	Pottery	MURR	MN	Diamond Creek	LA 129463	0.00	55.54 0	0.6314 4	49.29 9	9.60	3.22 5.	5.24 109.15	5 13.70	47.86
LOA060	Group-B	Unas.	Alma Plain	Pottery	MURR	MN	Diamond Creek	LA 129463	3.93	47.76 0	0.7126 4	48.51 9	9.53 4	4.11 6.	6.03 110.27	7 7.93	42.26
LOA061	Group-B	Unas.	Alma Plain	Pottery	MURR	MN	Diamond Creek	LA 129463	2.79	25.88	0.6512 4		9.16		4.68 117.37	80.9	
LOA062	Group-B1	Mimbres-05B	Alma Scored	Pottery	MURR	MN	Diamond Creek	LA 129463	0.00	55.07 0	0.9701 4	48.58 11	11.28 3	3.98 7.	7.62 132.07	7 4.98	29.29
LOA063	Group-A	Mimbres-03	Indeter. Whiteware	Pottery	MURR	MN	Diamond Creek	LA 129463	3.70	38.51	1.3999 3	39.80 10	10.52 6	6.05 10.15	15 97.59	9 1.95	8.34
LOA064	Group-A	Mimbres-03	Indeter. Whiteware	Pottery	MURR	MN	Diamond Creek	LA 129463	2.38	42.57	1.0886 4	41.75 10	10.93 7	7.26 8.	8.10 82.88	1.97	11.16
LOA065	Group-A	Mimbres-03	Indeter. Whiteware	Pottery	MURR	M	Diamond Creek	LA 129463	2.30	38.81	1.2094 3	35.57 9	9.61 6	6.63 8.	8.99 87.26	6 2.18	10.77
LOA066	Group-A	Mimbres-03	Indeter. Whiteware	Pottery	MURR	M	Diamond Creek	LA 129463	2.31	43.11	1.1358 3	39.05 10	10.35 5	5.74 8.	8.57 87.79	1.67	8.39
LOA067	Group-A	Mimbres-03	Indeter. Whiteware	Pottery	MURR	M	Diamond Creek	LA 129463	2.28	47.82	1.4203 5	53.95 15	15.61 6	6.96 11.70	70 118.35	5 2.89	9.84
LOA068	Group-A	Mimbres-03	Indeter. Whiteware	Pottery	MURR	M	Diamond Creek	LA 129463	1.78		1.2850 3	38.98 10	10.12	7.37 9.	9.25 104.03		
LOA069	Group-A	Mimbres-03	Indeter. Whiteware	Pottery	MURR	M	Diamond Creek	LA 129463	3.02	39.89	1.1473 3	39.26 10		6.11 8.	1	0 2.32	
LOA070	Group-C1	Mimbres-22	Indeter. Whiteware	Pottery	MURR	M	Diamond Creek	LA 129463	5.37						_		1
LOA073	Group-A	Mimbres-03	Indeter. Whiteware	Pottery	MURR	MN	Diamond Creek	LA 129463	1.30				12.36 7	1	1		
LOA074	Group-A	Mimbres-03	Indeter. Whiteware	Pottery	MURR	NM	Diamond Creek	LA 129463	1.84			`	11.69 6				
LOA075	Group-B	Unas.	Corrugated	Pottery	MURR	NM	Diamond Creek	LA 129463	5.07	51.64 0		39.29 7	7.44 3		3.93 97.29	9 13.43	
LOA076	Group-B1	Mimbres-05B	Corrugated	Pottery	MURR	M	Diamond Creek	LA 129463	2.49	59.42 0	0.9475 5	57.26 12	12.72 3		7.25 134.10	0 4.64	32.52
LOA077	Group-B1	Mimbres-05A	Corrugated	Pottery	MURR	ΣN	Diamond Creek	LA 129463	4.02								
LOA079	Group-B	Unas.	Corrugated	Pottery	MURR	M	Diamond Creek	LA 129463	5.45								
LOA080	Group-B	Unas.	Mimbres Corrugated	Pottery	MURR	M	Diamond Creek	LA 129463	5.21	48.53 0	0.7043 3					9 7.03	48.17
LOA081	Group-C2	Unas.	Mimbres Corrugated	Pottery	MURR	NM	Diamond Creek	LA 129463	2.97		0.5029 4	48.09 9	9.57 2	2.81 3.	3.91 98.92	2 22.51	87.33
LOA082	Group-C2	Unas.	Mimbres B/W Style II/III	Pottery	MURR	NM	Diamond Creek	LA 129463	2.38	59.19 0	0.6583 5	59.19 12	12.56 3	3.82 5.	5.03 109.63	3 10.43	46.63
LOA084	Group-B	Unas.	Mimbres B/W Style II	Pottery	MURR	Ž	Diamond Creek	LA 129463	3.26	57.88 0	0.5452 5	51.55 10	10.25 2	2.42 4.	4.00 105.16	6 3.43	19.25
LOA086	Group-C1	Unas.	Mimbres B/W Style I	Pottery	MURR	MN	Diamond Creek	LA 129463	5.88	36.75 0	0.4083 3	34.11 7	7.48 2		3.35 74.37	7 12.20	43.59
LOA087	Group-C2a	Mimbres-49A	Mimbres B/W Style I	Pottery	MURR	MN	Diamond Creek	LA 129463	2.36	52.76 0	0.4536 4	44.72 8	8.73 2	2.35 3.	3.48 95.88	8 7.19	39.63
LOA088	Group-B1	Mimbres-05A	Mimbres B/W Style II	Pottery	MURR	Ž	Diamond Creek	LA 129463	29.6	51.75 0	0.5864 4	42.32 8	8.70 3	3.96 4.	4.18 93.44	4 7.15	
LOA089	Group-C1	Unas.	Mimbres B/W Style II	Pottery	MURR	MN	Diamond Creek	LA 129463	2.41	44.65 0	0.4868 4			3.24 3.	3.86 90.27		1
LOA091	Group-C1	Mimbres-21	Mimbres B/W Style III	Pottery	MURR	M	Diamond Creek	LA 129463	2.91				5.53				
LOA092	Group-C1	Mimbres-21	Mimbres B/W Style III	Pottery	MURR	M	Diamond Creek	LA 129463	3.08				Ì				
LOA093	Group-C1	Mimbres-21	Mimbres B/W Style III	Pottery	MURR	M	Diamond Creek	LA 129463	2.73								
LOA094	Group-C1	Mimbres-24	Mimbres B/W Style III	Pottery	MURR	MN	Diamond Creek	LA 129463	2.26	37.01 0	0.4052 3	33.47 6	6.63 2	2.58 2.	2.98 77.03	3 14.26	32.10

>	65.47	92.16	35.66	83.64	34.94	85.58	24.05	58.15	45.67	48.45	91.20	51.96	59.22	83.26	29.09	46.61	30.03	17.66	24.33	14.18	18.34	18.89	15.77	32.53	41.34	18.88	15.69	84.36	53.06	71.74	60.97	57.90	123.91	72.91	63.36	51.03	150.95	74.43	143.11	61.33	73.90	80.70	97.84
Ξ	3961.8	4554.2	2661.0	4707.9	2718.4	3005.5	7 7771	3203.7	3099.4	2685.8	4802.1	3068.8	4534.3	4769.1	3629.7	3368.8	7322.3	1788.1	1817.3	1770.7	1642.4	1647.0	1410.2	1643.6	2588.3	1350.6	1432.3	5283.8	2993.2	4141.1	4584.9		_	4562.2	4051.3	3033.1	7616.8	9.5099	6906.2	2237.3	3377.1	3114.9	4528.6
NA	13364.2	12191.9	14944.9	11916.0	17807.4	19130.5	18140.3	14978.1	14157.5	14352.1	21456.7	16532.6	15229.6	13077.9	14944.3	9620.4	10032.0	6626.6	6779.1	5396.5	7844.0	5336.2	4411.3	6421.3	15941.0	6267.1	6748.6	9187.6	13551.0	11214.6	8001.9	6291.1	13710.5	14922.7	16383.9	15759.1	14573.3	15530.4	15234.0	16034.4	18882.1	18313.6	21040.5
MN	516.0	1.609	309.6	643.5	320.8		2707		_	4	810.9			530.7	462.6	315.8	390.8	616.9	567.4	743.8	570.9	799.4	730.1	548.0	599.9	603.0	555.7	741.9	322.2	207.7	725.1	437.2	849.4	317.0	813.0	434.6	1134.9	509.5	911.0	979.2	842.2	856.1	793.5
¥	26811.7	25718.0	28594.9	26671.9	29053.3	24990.6	24021.3	36057.6	28501.0	27293.6	24567.2	34822.3	27474.2	23358.9	32794.6	32363.8	31385.6	50267.4	47775.5	38835.2	46987.9	51295.1	41833.9	45567.6	28628.3	50565.2	46421.7	31984.5	30586.1	29330.9	26112.3	21522.4	30451.8	25962.3	24673.0	29556.9	30344.3	23075.4	31612.3	25728.3	25719.4	26116.8	22016.2
DY		7.272	11.304				9 530			+	5.129		12.532					_		10.915	16.259	16.810						_			_	_	_			7.157	868.9	8.247	6.919				4.435
CA	12220.7	11283.7	10584.9	10654.3	12550.1	12169.0	0.00277	8661.3	18739.8	11317.8	15658.2	10659.1	11083.0	18698.4	11457.3		_			9966.3	6202.7	11208.3	12828.3	7062.1	10605.6	8605.2	7933.0			16619.0	17204.2	15131.2	16472.9	11345.0	12699.3	11589.8	13867.3	14004.3	14692.3	30076.5	11225.8	11639.0	16312.9
BA	674.7	715.9	538.9	9.189	1262.4	1397.0	239.9	675.7	1620.9	652.8	741.4	8.768	1482.3	852.3	444.0	546.2	4//.8	135.1	99.2	76.8	7.06	189.5	124.4	131.9	703.1	132.9	204.3	700.9	414.1	622.5			765.8	9.109	1067.8	1195.7	6.806	836.8	995.3	786.1	781.8	708.7	783.1
AL	75455.6	84059.5	79278.1	92064.5	87661.7	87833.9	87703.5	86667.5			98271.8		07102.5	88595.0	74784.1	94007.3	7.2632.0	75612.3	85789.3	81845.3	81110.3	86056.9	85925.2	84894.6	102479.9	78976.0	81086.0	83950.9	79453.1	79230.0	8.90808	80691.4	84547.2	91805.5	94189.4		87936.7	83841.3	85265.4	93118.8	93486.7	89184.7	95253.7
ZR		230.1	195.3	_			188.5	_			199.5		_			.0.				207.6	189.5	241.1	214.7	195.6	1										235.4	169.7			230.0				190.3
NZ	86.5	101.6	92.6	86.1	76.3	64.0	12.0	44.4	59.7	62.9	9.76	89.2	74.8	96.4	91.2	67.1	80.0	76.8	86.8	76.1	9.88	87.7	63.5	83.0	88.4	98.5	81.8	111.5	83.3	84.5	94.4	104.6	0.06	83.3	9.08	6.06	76.2	68.5	107.3	0.06	86.2	92.7	79.5
3 TH	5 27.07		3 19.68	• •			7 10.14						25.30							1 34.56	7 36.12	4 38.72															12.55	5 17.24	l			9 11.18	3 9.97
TA TE	2.9823 1.06	1.7973 1.42	1.8049 2.18	1.6931 1.48		0.6419 0.58	0.8459 1.27 2.2822 0.58				0.9281 0.96	1.9984 1.80	1.7999 2.2						2.1064 1.94	2.2876 1.7	2.1083 1.87	2.6531 2.7	2.5620 1.78	2.1364 1.85			_			_	2.1022 0.92			1.4628 1.51	0.9453 1.31	0.9315 1.04	0.9882 1.0	1.4157 1.15	1.3074 1.20	0.6791 0.65	0.8142 0.73		0.8600 0.83
SR		312.8 1.7	204.2 1.8				112 8 23				442.9 0.9	319.0 1.9	251.9 1.7	_						71.0 2.2	67.7 2.1	67.9 2.6	64.5 2.5	63.8 2.1											208.2 0.9	426.5 0.9	318.6 0.9		595.5 1.3	424.5 0.6			516.1 0.8
SC			9.80 20				10.95			-	10.99	8.65 3	11.50 2		9.59 2				5.72	5.16	5.26	5.09	4.97											13.07	9.93 20	11.08 4.		12.98 2.	16.60 50				10.46 5
SB		0.5143 1		_			0.3109				-	0.3793		_		0.4616	0.4106	0.2946	0.2838	0.2873	0.3040	0.4151	0.3186	0.3413	~			`						0.3375 1				0.5452 1					1.0065 1
RB				_			92.51 103.15						109.51							228.02	288.42	292.54	240.02	300.19											130.63			136.64	146.42				112.50
Z		43.8	24.0			0.0	34.2				30.0	0.0								0.0	0.0	0.0	0.0	0.0	0.0	20.4					_	48.1				0.0	36.3	25.1	68.5				0.0
生	`	9.84		8.91			6.08				7.78	10.56	`							10.80	9.64	11.37	10.88	9.71		1								9.30	8.65		7.94	7.30	8.15				7.18
H	28419.9	42929.3	25840.9	38072.3	18435.1	34078.4	0.08/28	28195.9	20426.5	21114.6	41216.7	28710.1	34253.4	41232.6	29613.4	22538.1	7.76122	12388.6	14462.1	14347.5	12774.2	13819.1		14682.5	20369.9	12842.4	13579.6	42505.5	24341.8	31253.4	31808.8	34200.5	53093.2	41901.5	24521.2	39002.8	30350.8	26736.0	59576.1	28541.4	34746.2	36261.2	39222.7
ED			1.5893	1.7633			2.4464	1.3242	1.6249	_	1.5479	1.5220	1.8941	1.5748	1.2877		1.3/42	0.5745	5.44 0.4992	4.04 0.5171	0.5160	4.78 0.8452	0.5277	0.5245	1.3173	0.6312			1.4037	1.5422			1.9899	2.5758	2.0746	1.5756	1.9706					1.4124	1.4820
CS	6.13	5.61	5.90	6.79	3.78		15.60	4.70	5.69	5.37	_	4.39	5.59	11.17		5.07	5.48	4.96	5.44	4.04	4.77	4.78	3.86	5.49			4.94	9.64	6.71	6.11	9.36	11.48	7.27	3.77	4.63	18.46	4.24	8.14	28.58	26.23	18.74		12.40
ANID	LOA028	LOA030	LOA031	LOA032	LOA034	LOA036	LUAU3/	LOA030	LOA042	LOA043	LOA044	LOA053	LOA058	LOA059	LOA060	LOA061	LUAU62	LOA063	LOA064	LOA065	LOA066	LOA067	LOA068	LOA069	LOA070	LOA073	LOA074	LOA075	LOA076	LOA077	LOA079	LOA080	LOA081	LOA082	LOA084	LOA086	LOA087	LOA088	LOA089	LOA091	LOA092	LOA093	LOA094

ANID	macro grp	o Chem2012	CERAMIC TYPE	MATERIAL	SOURCE	STATE	SITE NAME	SITE NO	AS	ΓA	Π	QN	SM	U YB	B CE	00	CR
LOA096	Group-C1		le III	Pottery	MURR	N N		LA 129463	2.77	_			6.33 1.27	2	82	1	48.47
LOA097	Group-B1	Mimbres-04B	Mimbres B/W Style III	Pottery	MURR	MN	Diamond Creek	LA 129463	1.56	52.20 0	0.5510	39.75 7.	7.39 7.62	52 3.54	4 89.58	3.92	21.22
LOA098	Group-A	Mimbres-03	Indeter. Whiteware	Pottery	MURR	MN	Diamond Creek	LA 129463	2.36	52.93	1.2368 4		12.41 6.0	6.65 10.08	8 105.46	2.65	12.26
LOA099	Group-A	Mimbres-03	Indeter. Whiteware	Pottery	MURR	NM	Diamond Creek	LA 129463	3.38	48.68		47.44 12.		9.18 10.22	l	2.41	10.60
LOA100	Group-B	Unas.		Pottery	MURR	NM	Diamond Creek	LA 129463	5.10				1	94 4.50			42.34
LOA102	Group-B	Unas.	Reserve Indented	Pottery	MURR	MN	Diamond Creek	LA 129463	3.90	47.88 0	0.6737		8.57 5.84	34 4.77	7 80.61	6.25	42.62
LOA103	Group-B	Unas.	Reserve Indented Smudged Pottery	Pottery	MURR	MN	Diamond Creek	LA 129463	4.31	37.74 0	0.5942	34.55 7.	7.81 4.5	4.55 4.40	0 81.25	6.40	35.83
LOA104	Group-B1	Mimbres-05B	Reserve Indented Smudged Pottery	Pottery	MURR	MN	Diamond Creek	LA 129463	4.06	40.30 0	0.6078	34.82 7.	7.34 4.13	13 4.46	6 74.11	5.79	36.73
LOA105	Group-B	Unas.	Reserve Indented Smudged Pottery	Pottery	MURR	MN	Diamond Creek	LA 129463	4.58	37.35 0	0.7282	32.92 8.	8.49 6.12	12 5.45	5 91.63	4.64	34.83
LOA108	Group-B1	Mimbres-05B	Reserve Smudged	Pottery	MURR	MN	Diamond Creek	LA 129463	5.34	47.26 0		38.96 8.	8.39 5.54	54 4.69	97.76	6.75	41.12
LOA109	Group-B1	Mimbres-05B	Alma Incised	Pottery	MURR	MN	Diamond Creek	LA 129463	4.19	0 82.09	0.9111	60.12 12.	12.96 5.2	5.25 6.77	7 90.29	2.60	43.66
LOA110	Group-B	Unas.	San Francisco Red	Pottery	MURR	M	Diamond Creek	LA 129463	4.28	54.12 0	0.7447	51.41 11.	11.90 4.29	29 6.33	3 110.43	7.71	33.10
LOA112	Group-B1	Mimbres-05A	San Francisco Red	Pottery	MURR	MN	Diamond Creek	LA 129463	3.63	47.79 0	0.5731	44.58 8.	8.85 5.39	39 4.28	8 105.82	15.60	66.71
LOA113	Group-B	Unas.	San Francisco Red	Pottery	MURR	MN	Diamond Creek	LA 129463	5.02	48.59 0		44.55 9.	9.48 4.3	4.33 4.85	5 94.88	6.67	45.73
LOA114	Group-B1	Mimbres-05A	San Francisco Red	Pottery	MURR	MN	Diamond Creek	LA 129463	5.48	50.78 0				3.38 4.44	,	13.79	9.69
LOA115	Group-B	Unas.	San Francisco Red	Pottery	MURR	MN	Diamond Creek	LA 129463	2.74	20.67 0	0.7303	45.50 9.	9.84 5.0	5.60 5.59	6 88.77	7.40	47.12
LOA116	Group-C1	Mimbres-24	San Francisco Red	Pottery	MURR	M	Diamond Creek	LA 129463	3.16	38.08 0	0.3944	31.35 6.	6.49 2.0	2.68 2.86	6 75.79	11.33	35.79
LOA119	Group-C1	Mimbres-21	Mimbres B/W Style II	Pottery	MURR	M	Diamond Creek	LA 129463	3.58	36.24 0	0.2780	27.57 5.	5.25 1.0	1.66 2.13	3 73.04	19.6	52.56
LOA121	Group-B1	Mimbres-05B	Alma Plain	Pottery	MURR	M	Main Diamond C	LA 135635	3.10	58.87 0	0.9779	53.87 12.	12.09 5.7	5.13 7.51	1 125.26	19.8	34.69
LOA122	Group-B1	Mimbres-05B	Alma Plain	Pottery	MURR	MN	Main Diamond C	LA 135635	2.44	55.13 0	0.9291	48.76 11.	11.29 4.51	51 6.93	3 126.21	4.08	29.24
LOA123	Group-B1	Mimbres-05B	Alma Plain	Pottery	MURR	M	Main Diamond B	LA 135634	2.24	62.44 0	9866.0	57.68 13.	13.29 4.37	37 7.66	6 142.70	4.75	32.19
LOA126	Group-B1	Mimbres-05B	Corrugated	Pottery	MURR	MN	Main Diamond C	LA 135635	3.33	49.43 0	7 9058.0		9.99 4.5	4.58 6.53	3 110.53	8.43	32.66
L0A127	Group-B1	Mimbres-05B	Corrugated	Pottery	MURR	MN	Main Diamond C	LA 135634	2.16	53.90 0	0.8324	49.57 11.	11.03 4.08		6 106.76		33.46
L0A128	Group-B1	Mimbres-05B	cised	Pottery	MURR	MN	Main Diamond B	LA 135634	4.44	00.99	0.8926	59.35 12.	12.49 4.75	75 6.50	0 120.32	7.85	32.67
LOA131	Group-C2	Unas.	Mimbres B/W Style III	Pottery	MURR	MN	Main Diamond B	LA 135634	2.19	54.55 0	0.5605	52.04 10.	10.39 2.47	17 4.48	8 99.21	9.45	38.78
LOA132	Group-B1	Mimbres-05B		Pottery	MURR	NM	Main Diamond C	LA 135635	2.43			47.21 10.		98 6.56			25.29
LOA133	Group-B1	Mimbres-05B		Pottery	MURR	MN	Main Diamond B	LA 135634	3.68	0 86.09		56.15 11.		35 7.11			34.31
LOA134	Group-B1	Mimbres-05B	Reserve Indented	Pottery	MURR	NM	Main Diamond C	LA 135635	6.33	76.76 0			15.61 4.48	18 7.57	7 156.38	9.71	41.09
LOA135	Group-B1	Mimbres-05B	Reserve Indented	Pottery	MURR	NM	Main Diamond C	LA 135635	2.90							10.44	27.29
LOA136	Group-B1	Mimbres-05B	Reserve Indented Smudged Pottery	Pottery	MURR	NM	Main Diamond C	LA 135635	3.43		0.8605	62.53 12.	12.83 3.9	3.92 6.34		80.6	40.46
LOA138	Group-B1	Mimbres-05B		Pottery	MURR	M	Main Diamond B	LA 135634	2.93			50.61 11.11		4.56 6.56	6 109.37		35.83
LOA140	Group-B	Unas.		Pottery	MURR	MN	Main Diamond B	LA 135634	2.13							_	39.01
LOA141	Group-B1	Mimbres-05B	mudged	Pottery	MURR	M	Main Diamond B	LA 135634	3.89								33.97
LOA143	Group-B1	Mimbres-05B		Pottery	MURR	M	Main Diamond C	LA 135635	2.84					5.03 6.13		1	37.38
LOA144	Group-B1	Mimbres-05B	Alma Plain	Pottery	MURR	M	Main Diamond C	LA 135635	1.83	62.88 1	1.0178 (13.38 4.71	7.93			29.29
LOA145	Group-B	Unas.	Corrugated	Pottery	MURR	NM	Main Diamond C	LA 135635	3.32	55.39 0		55.66 11.	11.25 4.36	36 5.42	2 119.68		29.45
LOA146	Group-B1	Mimbres-05B	Corrugated	Pottery	MURR	NM	Main Diamond C	LA 135635	6.40				15.36 4.43	13 7.7	1 111.72	9.51	49.13
LOA150	Group-B	Unas.		Pottery	MURR	¥	Main Diamond C	LA 135635	4.81		0.7484	57.33 12.	12.24 4.40		6 128.65	10.18	47.03
LOA153	Group-B2	Mimbres-08		Pottery	MURR	NM	Main Diamond B	LA 135634	2.87	36.50 0			4.15 5.69			3.92	25.39
LOA155	Group-B1	Mimbres-04A	=	Pottery	MURR	NM	Main Diamond B	LA 135634	2.93	36.48 0			6.05 4.27		2 71.18	7.10	24.29
LOA157	Group-B1	Mimbres-04A	=	Pottery	MURR	M	Diamond	LA 135634	2.65				6.64 5.14	14 3.28			25.23
LOA158	Group-C1	Mimbres-22		Pottery	MURR	M	Main Diamond B	LA 135634	3.83			33.48 5.		1.46 2.2	1 84.38	8.52	10.06
LOA159	Group-C2	Unas.	Mimbres B/W Style III	Pottery	MURR	MN	Main Diamond B	LA 135634	1.22		0.5501		10.48 3.2	3.29 4.14	4 94.48	10.41	40.54
LOA160	Group-B1	Mimbres-05A	Mimbres B/W Style III	Pottery	MURR	NM	Main Diamond B	LA 135634	3.23	50.72 0	0.7043	48.25 10.	10.66 4.66	5.22	2 111.37	7.18	45.77

>	74.05	41.73	29.18	18.21	45.22	79.79	54.15	46.08	54.87	48.37	53.66	45.90	85.21	61.05	85.70	63.44	72.63	54.55	43.68	35.46	39.24	40.64	44.35	50.79	70.19	40.12	49.68	67.55	55.45	43.12	61.23	62.47	56.85	49.70	34.59	60.37	61.26	83.78	51.98	54.70	50.09	25.84	68.18	84.02
F	3132.1	2671.8	1842.3	1864.2	2676.7	3714.4	2816.8	3021.9	2490.0	3013.6	2853.3	3448.7	4683.9	3522.5	4754.7	4252.5	3724.5	1928.0	2956.4	2497.1	2428.2	2119.2	2548.3	3268.4	4913.1	2446.1	2565.1	4351.7	3381.4	4145.0	4957.9	3824.6	3986.4	3000.8	2758.2	4430.1	3466.7	4206.4	2803.2	4414.1	4503.9	1110.8	5137.3	3922.6
NA	19806.3	11395.9	8386.1	7730.1	12340.7	9306.7	2121.1	10725.7		12227.2	11918.2	10160.2	15288.1	12980.3	11012.2		16941.7	16141.3	14435.8	15034.6	13042.1	13640.4	3657.0		16338.6				14273.5	14278.8				13539.2	13508.5	14409.9	12274.4	13254.9	8482.7	14154.7				15921.0
MN	904.4 19	215.6 11	627.7	638.6 7	380.9 12		455.0 12			544.9 12	471.1	728.3 10	767.4 15	644.6 12	815.2 11	676.2 15		936.1 16	863.9 14	268.6 15	413.1 13	1066.5 13	1296.2 13	604.6 12	578.1 16	`	1198.8 14	١.	549.0 14	549.1 14	`	`		753.8 13	311.7 13	522.1 14	952.9 12	523.4 13		384.0 14	629.1 13			273.6 15
×	26599.4	29727.4	53417.6	57858.8			~			28411.3	29172.2	36003.0	25352.7	34879.9	33161.3	30664.7		27028.9	31117.5	29623.8	29901.9	33957.1 1	30018.4	27373.5	27740.7				31368.2	31483.2			35972.4	30057.7	29158.5	25375.2	24240.0	27836.3	27327.6	2		1		27278.5
DY	3.500 26	5.252 29	14.371 53	14.084 57			•			7.756 28	10.262 29	14.966 36	6.399 25	8.737 34	6.316 33	8.464 30	- 1	3.847 27	10.399 37	9.857 29	12.165 29	8.871 33	9.701 30	10.597 27	- 1		9.203 28		9.956 37	9.385 37				9.346 30	-	8.856 25		9.644 27	3.127 27					9.307 27
CA	13619.0		8075.5 1	8475.7 1						15160.8	8146.9 1	10896.3 1		10040.7	14152.5	10378.8		40687.1	9396.9 1	8009.2	9332.8 1	10789.6	7151.6	11311.3 1				_	10036.4	11277.7				11655.7	9015.7 1	6251.6	16078.0	10924.7						10298.2
BA	902.4	546.3	85.3	82.1	496.6					220.3	204.9	494.5		9.867	737.9	385.6		923.0	490.9	496.0	752.7	733.4	992.3			622.4	467.3		969.4		. 8.2001	1305.3		1085.1	9.958	896.2	1275.2	1203.9	408.2				Ì	487.9
AL	89755.0	85407.2	82143.4	85730.7	81864.2	78736.8	74768.0	74618.8	79374.0	73813.0	83371.8	74657.8	87951.5	75125.1	83643.6	72485.3	82067.4	80900.5	79199.5	76946.9	74928.5	79289.1	77190.8	83651.9	84612.1	69831.6	74963.4	84433.8	76846.3	75942.3	76047.8	81832.7	77138.0	76231.4	73892.1	81061.1	86858.3	9.66567	89393.2	82649.5	79905.6	. 8.09500	89300.0	87794.2
ZR	184.6	171.0	216.7	203.2			173.8	238.4	_	170.1	175.5	218.4	239.6	225.7	215.3	294.1		159.6	216.6	176.9	211.6	185.8	214.6		235.9	188.3	228.8		240.2	254.9	_		245.4	208.6	229.7	217.5	215.1	253.4	_	227.7		_	238.0	226.3
NZ	91.5	51.0	146.8	135.9	94.0	96.1	82.7	82.2	103.8	82.2	0.96	80.8	105.4	87.3	97.2	121.8		79.8	92.4	78.0	89.1	93.8	105.7	99.4	87.0	75.1	6.66	102.0	92.5	89.5	89.9	89.0	83.1	88.0	78.2	9.88	94.7	98.5	52.1	55.3	58.4	100.5	88.2	85.1
3 TH	6 9.71	3 25.55	5 36.53	5 38.19	4 17.10	2 25.04	0 18.54		5 23.11	7 21.19	4 24.37	0 20.15	1 17.84	7 19.65	8 17.29	8 19.91	_	6 8.54	8 20.13	5 21.48	6 20.77	1 18.99	3 17.90	1 21.49					9 19.23	8 18.96	1 18.66				4 21.35	2 15.97	8 21.52	0 18.37	5 29.13				7 13.33	0 17.61
TA TB	0.7653 0.7	.4753 0.93	2.2972 2.15	.5128 2.05	1.1 2899.1	2.2978 1.1	1.9073 1.1	1	2.1598 1.35	1.7160 1.17	1.9430 1.84	1.8125 1.80	1.6240 1.21	1.5938 1.27	1.5338 1.28	1.6380 1.48		0.6204 0.66	247 2.08	2.0698 1.85	1.9933 2.16	1.8955 1.61	2.0615 1.7	2.2584 1.81	1.4575 1.32		001 1.84	1.9468 2.15	1.7666 1.79	465 1.88	1.9819 1.7	`		3.1346 1.58	1.9920 2.14	1.8649 1.52	1.8690 2.28	1.8836 1.70	1.5181 0.65		1.6510 0.86	_		1.3580 1.60
SR	448.5 0.7	131.5 1.4	55.6 2.2	2					_	318.7 1.7	154.1 1.9	470.2 1.8	419.7 1.6	288.7 1.5	527.1 1.5	177.8 1.6		486.1 0.6	162.3 2.0247	146.9 2.0	215.2 1.9	290.4 1.8	197.1 2.0	293.4 2.2						238.7 1.8465				293.0 3.1	221.4 1.9	182.3 1.8	335.2 1.8	474.0 1.8	111.6 1.5			\sim		212.9 1.3
SC	8.56 44	6.79 13	90.9						10.87 27		10.32	7.55 47	12.92 47	8.86 28	11.56 52	10.33		6.93 48	10.12	9.24 14	10.23 27	9.66							9.76 22	11.60 23				10.17	9.53 22	11.14 18	11.12 33	11.95 47	6.89	6.90 23	7.10 23		12.14 33	1.77 2
SB	1.4874	0.3823	0.4846							0.4782	0.4931 1	0.5195	0.4448 1		0.5657 1	0.4549 1		4.0790	0.5066 1	0.3503	0.3603 1	0.4528	0.4493	0.5529 1				1	0.5499	0.5118 1			_			0.3541 1	0.4996 1	0.7322			0.3824			0.8323 1
RB		176.06	310.68								149.49	169.75		144.55	133.16	139.35		115.62	180.37	174.48		171.01	158.68	164.52	115.11				171.37	145.69				141.01		134.56	119.07	136.94						153.26
Z	21.3	0.0	0.0							0.0	0.0	0.0	0.0	0.0	37.8	38.0		0.0	28.2	21.7	0.0	0.0	33.9	0.0			27.3		27.8 1	32.5				0.0	0.0	0.0	0.0	41.3	0.0				0.0	0.0
生	92.9	6.43	10.92	10.99	7.84	9.04	7.77	9.37	7.31	7.29	7.80	8.81	9.31	9.01	9.26	11.76		6.35	19.61	8.21	8.37	8.15	7.92	8.54	9.08	8.25	9.61	_		9.51	8.09	7.99	98.6	8.38	9.29	8.78	8.53	10.00		8.22	08'6	6.37	8.84	9.04
FE	35194.5	20497.1	16159.8	15093.0	28994.1	31413.9	27789.0	28386.6	26664.9	26294.2	27797.9	23536.7	41530.6	30090.1	38013.0	41054.9	29014.2	26827.5	28414.0	21896.2	23567.4	27195.3	27710.7	30415.2	39080.7	21467.2	28833.3	36787.2	29649.9	33466.7	28192.3	30126.4	31616.1	29448.6	21581.9	30680.1	31591.3	34738.0	23419.3	23798.5	24955.9	20251.5	40647.2	21481.3
ED	1.4022	1.2145	0.6922							1.1147	1.5371			1.2081	1.6401	1.2995		1.2653	1.4948	1.2277	1.4628	1.2551	1.4275	1.4385					1.9443	1.9308					1.5252	1.7642		1.9083	0.6707				2.0296	8.38 1.5311
CS	18.82	5.79	5.43								8.38	3.17	7.01	6.46	6.51	5.85		13.78	7.47	6.17	5.41	6.17			3.53				2.69	5.25				5.38	5.42	4.31		5.59	7.79			23.93	3.55	8.38
ANID	LOA096	LOA097	LOA098	LOA099	LOA100	LOA102	LOA103	LOA104	LOA105	LOA108	LOA109	LOA110	LOA112	L0A113	L0A114	LOA115	LOA116	LOA119	L0A121	L0A122	L0A123	LOA126	LOA127	L0A128	LOA131	LOA132	LOA133	LOA134	LOA135	LOA136	LOA138	LOA140	L0A141	LOA143	LOA144	LOA145	LOA146	LOA150	LOA153	LOA155	LOA157	LOA158	LOA159	LOA160

ANID	macro grp	macro grp Chem2012	CERAMIC TYPE	MATERIAL	SOURCE	STATE	SITE NAME	SITE NO	AS	ΓA	ΓΩ	ND S	SM	U YB	3 CE	00	CR
LOA162	Group-B1	Mimbres-04A	rle III	Pottery	MURR		Main Diamond B	LA 135634	1.47	35.84 0.4	0.4439 2	27.69 5.	5.89 4.16	16 3.03	_	7.29	24.24
LOA163	Group-B1	Mimbres-09	Mimbres B/W Style III	Pottery	MURR	ΣN	Main Diamond B	LA 135634	1.06		0.5580 4	48.18 9.	9.86 4.62	52 4.11	1 108.22	2.36	14.76
LOA164	Group-B1	Mimbres-04B	Mimbres B/W Style III	Pottery	MURR	ΣN	Main Diamond B	LA 135634	3.02	49.59 0.5	0.5230 3	37.91 7.	7.30 5.98	3.52	2 87.08	5.02	21.70
LOA165	Group-C1	Mimbres-22	Cibola	Pottery	MURR	ΣN	Main Diamond B	LA 135634	7.09	39.25 0.2	0.2553 2	29.91 5.	5.15 1.6	1.62 2.13	3 75.39	6.36	11.53
LOA166	Group-A	Mimbres-03	Indeter. Whiteware	Pottery	MURR	NM	Diamond Creek	LA 129463						17 7.80			11.89
LOA167	Group-A	Mimbres-03		Pottery	MURR	NN	Diamond Creek	LA 129463			1.2418 4	46.16 12.	12.30 6.00	10.13	l	2.37	9.94
LOA169	Group-C1	Mimbres-22	Indeter. Whiteware	Pottery	MURR	NM	Main Diamond C	LA 135635	9.24	36.94 0.2	0.2825 2		4.68 1.52	52 2.17	7 72.38	6.14	14.32
LOA170	Group-A	Mimbres-03		Pottery	MURR	NM	Diamond Creek	LA 129463	2.62	38.51 1.1	1.1160 3	39.21 9.	9.99 8.01	00.6	0 91.75		8.42
LOA171	Group-B2	Mimbres-02A		Pottery	MURR	NM	Gatton Park	LA 011075			0.5219 2	29.91 5.					34.21
LOA172	Group-A	Mimbres-03	Cibola B/W untyped	Pottery	MURR	MN	East Fork	LA 11074	0.00	35.92 1.0	1.0110 3	31.98 8.	8.57 7.53			2.37	9.20
LOA173	Group-C1	Mimbres-22	Cibola B/W untyped	Pottery	MURR	NM	Diamond Creek	LA 129463	09.6			27.15 4.	4.61 1.36	36 1.89	66.69 6	5.30	6.51
LOA176	Group-B1	Mimbres-04B	Mimbres B/W Style III	Pottery	MURR	NM	East Fork	LA 011074		47.59 0.5	0.5122 3	32.70 6.	6.67 8.27	27 3.15	5 91.75	4.78	23.79
LOA191	Group-A	Mimbres-01	Indeter. Whiteware	Pottery	MURR	MN	XSX	LA 050702	2.51	78.10 0.7	0.7948 4	41.86 7.	7.15 14.53		0 132.32	4.10	7.15
LOA192	Group-A	Mimbres-03	Indeter. Whiteware	Pottery	MURR	MN	XSX	LA 050702	1.30	39.90 1.2	1.2180 3	38.84 10.41	41 6.23	23 8.79	9 95.43	1.97	9:36
LOA193	Group-A	Mimbres-03	Indeter. Whiteware	Pottery	MURR	NM	XSX	LA 050702	3.11	41.88 1.2	1.2074 4	43.46 11.		56 9.22	2 89.71	2.19	12.93
LOA194	Group-A	Mimbres-03		Pottery	MURR	NM	XSX	LA 050702	2.17				8.82 5.85	35 8.13	3 88.85		14.88
LOA195	Group-A	Mimbres-03	Indeter. Whiteware	Pottery	MURR	NM	XSX	LA 050702	3.67			49.41 12.06			5 128.87	2.50	11.68
LOA196	Group-A	Mimbres-03	Indeter. Whiteware	Pottery	MURR	MN	XSX	LA 050702			1.2299 3	34.46 10.58	58 6.34	34 9.26	6 103.43	2.19	9.01
LOA197	Group-A	Mimbres-03	Indeter. Whiteware	Pottery	MURR	MN	XSX	LA 050702	1.84	36.89 1.1	1.1393 3	39.46 9.	9.46 6.04	34 8.11	1 97.37	2.19	9.33
LOA199	Group-A	Mimbres-03	Indeter. Whiteware	Pottery	MURR	MN	XSX	LA 050702		39.52 1.3	1.3743 3		9.79 6.32	32 9.94	113.24	1.98	8.57
LOA200	Group-A	Mimbres-03	Indeter. Whiteware	Pottery	MURR	MN	XSX	LA 050702	3.27	39.64 1.2	1.2748 3	39.82 10.77	77 6.89	39 9.27	7 99.52	2.15	11.45
LOA201	Group-A	Mimbres-03	Indeter. Whiteware	Pottery	MURR	ΣN	XSX	LA 050702	1.99	39.19 1.0	1.0466 3	34.64 9.	9.14 5.82	32 7.74	4 88.67	2.93	11.92
LOA202	Group-A	Mimbres-03	Indeter. Whiteware	Pottery	MURR	ΣN	XSX	LA 050702	1.49	40.40	1.4361 3	39.05 10.59	69.9	59 10.71	1 98.51	2.82	12.37
LOA203	Group-A	Mimbres-03	Indeter. Whiteware	Pottery	MURR	ΣN	XSX	LA 050702		41.49 1.3	1.3053 4	41.33 11.80		13 9.66	6 104.38		8.02
LOA204	Group-A	Mimbres-03	Indeter. Whiteware	Pottery	MURR	NN	XSX	LA 050702		42.26 1.4	1.4955 3	39.52 10.77	77 6.81	31 11.47	7 95.39	2.09	12.80
LOA205	Group-C1	Mimbres-21		Pottery	MURR	NN	XSX	LA 050702		41.59 0.3					2 84.11		47.06
LOA206	Group-C1	Mimbres-21	=	Pottery	MURR	NN	XSX	LA 050702	2.13		0.3516 3	32.73 5.	5.89 1.58			1	80.89
LOA207	Group-C1	Mimbres-21		Pottery	MURR	NM	XSX	LA 050702)2 2.36			34.36
LOA208	Group-B1	Mimbres-09		Pottery	MURR	NN	XSX	LA 050702	2.74	55.83 0.5	0.5704 5	52.97 10.06	06 4.21	21 4.14	4 118.23	2.38	15.06
LOA209	Group-B1	Mimbres-05A		Pottery	MURR	ΣN	XSX	LA 050702	3.80			45.85 9.	9.78 4.45	15 5.02	2 107.31	6.46	47.10
L0A211	Group-C1	Mimbres-21	=	Pottery	MURR	N	XSX	LA 050702								_	78.59
LOA212	Group-A	Mimbres-03		Pottery	MURR	MN	XSX	LA 050702				•	11.50 5.76	1			12.48
LOA213	Group-A	Mimbres-03	'e	Pottery	MURR	Z	XSX	LA 050702	_			1					11.38
LOA214	Group-C1	Mimbres-21	Three Circle R/W	Pottery	MURR	M	XSX	LA 050702									55.19
LOA215	Group-C1	Mimbres-21	deter.	Pottery	MURR	ΣN	XSX	LA 050702	2.01			32.75 5.	5.86 1.75	75 2.50		10.78	68.44
LOA216	Group-B1	Mimbres-09		Pottery	MURR	NM	XSX	LA 050702	2.60		0.5703 5	57.92 10.25		31 4.79	9 111.84		14.78
LOA217	Group-B1	Mimbres-05A		Pottery	MURR	NN	XSX	LA 050702		49.19 0.6	0.6706 4	49.58 10.26		97 5.00	0 104.31	8.52	52.26
LOA218	Group-C1	Mimbres-21	Mimbres B/W Style III	Pottery	MURR	NM	XSX	LA 050702	2.76		0.4301 3	36.04 6.	6.90 1.54	54 3.67		11.45	70.82
LOA219	Group-C1	Mimbres-24	/W Style III	Pottery	MURR	Ž	XSX	LA 050702	3.73	39.71 0.3	0.3999 4	40.25 7.	7.00 2.53	53 3.42	2 79.25	13.71	36.91
LOA220	Group-B1	Mimbres-05B		Pottery	MURR	NM	XSX	LA 050702	5.95	55.04 0.8	0.8338 5	1		58 6.80	0 101.40		39.91
LOA221	Group-B1	Mimbres-04A	Alma Plain	Pottery	MURR	NM	XSX	LA 050702	2.49	51.37 0.6	0.6340 4	40.41 8.	8.56 4.91	91 4.17	7 107.12	7.55	22.08
L0A222	Group-B1	Mimbres-05B		Pottery	MURR	M	XSX	LA 050702				÷			1		38.86
L0A223	Group-B	Unas.		Pottery	MURR	MN	XSX	LA 050702									44.20
LOA224	Group-B	Unas.	Alma Plain	Pottery	MURR	NN	XSX	LA 050702	2.79	42.38 0.4	0.4858 3	37.41 7.	7.59 4.42	12 3.33	3 88.95	13.27	59.33

>	57.09	51.29	44.59	44.62	20.48	29.17	43.20	21.82	61.70	19.94	31.59	48.58	37.02	18.04	27.59	31.80	24.75	16.80	12.97	21.57	18.43	26.82	18.50	22.14	15.07	54.97	55.87	43.61	38.47	74.53	65.37	25.07	11.34	48.90	56.39	40.41	73.08	66.10	93.74	29.67	51.76	52.55	59.73	128.26
F	4158.1	3533.7	3071.9	1311.7	1644.8	1615.8	1515.0	2106.4	3531.5	1904.5	1900.6	3136.9	1979.4	1183.4	1614.0	1048.6	1096.7	1088.6	1416.7	954.7	1789.3	9.069	1474.4	1131.1	1392.2	1423.8	1910.9	1302.7	3078.3	3922.3	2754.8	1312.1	1524.8	1677.0	2476.6	1958.5	3761.8	3501.3	4115.0	2612.9	2558.0	2710.9	2793.8	5153.7
NA	13998.0	18748.2	12057.0	8336.5	5984.1	6752.8	11027.5	5108.7	12581.5	5187.0	10223.5	10317.3	14005.9	69/09	7085.1	6003.4	5199.4	6115.4	5035.6	4894.3	5036.7	6754.9	6017.7	5943.3	5818.2	18911.6	18307.2	18315.9	18237.7	15006.0	17053.2	5855.2	2669.0	17062.3	17638.6	17732.9	13599.4	17197.1	18777.7	12165.5	15060.8	12235.3	10890.4	11322.9
M	387.6	397.4	286.9	720.1	480.3	623.0	803.0	628.9	289.9	643.5	912.8	143.1	226.5	594.8	499.4	577.5	604.1	618.8	632.1	659.3	729.1	550.0	665.5	714.4	562.7	1047.1	1187.0	1056.5	293.4	277.7	912.1	590.3	8.629	961.3	1070.3	478.3	384.6	952.9	726.2	610.7	626.3	652.9	335.5	382.4
¥	29045.5	29154.0	28122.8	34142.3	44016.9	42438.8	29576.4	39904.4	29246.2	43654.0	27946.2	27475.8	34485.4	43677.5	43954.0	45257.9	43876.2	49176.6	42230.5	44548.2	46007.9	45641.1	49156.2	47960.8	43142.5	27755.3	22305.6	25984.9	30231.9	27197.4	27831.1	46941.8	46927.3	25685.4	25448.4	34325.4	25684.6	25255.4	27754.8	30756.7	30111.9	32209.2	34717.6	27136.0
DΥ	4.458 2	7.162 2	5.116 2			10.439 4	3.556 2	12.650 3	4.478 2	11.381 4	3.401 2	4.500	4.848 3	11.692 4	12.658 4	13.758 4	12.419 4	12.664 4	10.351 4	12.031 4	12.843 4	11.007 4	11.773 4	12.848 4		3.290 2											8.047	3.967	4.477 2	9.019	5.652 3			5.964 2
CA	11710.0	10630.3	7614.5			6708.7	31437.3	8294.7	7884.0		42800.3	7659.7	11420.6	7245.1	7604.0	16918.9	39421.7	8938.8	11832.0	8511.8	10823.7		10345.1	11978.1	_	24671.1	13148.1	9604.2	11764.2	10049.1			_	25903.1	13607.2	12506.1	11913.5	15957.1	18053.1	11101.6	14183.5	9.9026	10911.4	14175.6
BA	9.789	1101.9	557.5	940.9	88.0	109.3	954.2	626	443.3	153.2	646.7	529.6	339.2	0.0	99.1	82.5	71.3	89.2	56.1	110.0	61.2	166.3	106.8	144.3	97.3	9.006		1234.6	983.2	462.5	632.9	67.4	117.6			999.2	442.3	659.2	769.5	562.8	780.3	602.6	537.7	6.11.9
AL	77986.4	84970.2	82046.4	94382.7	83154.2	80059.0	92182.6	77184.3	87014.9	80554.7	90300.7	90000.3	17430.8	70916.1	71784.4	77891.4	76202.1	72690.2	74304.6	80330.1	82653.2	73887.9	79176.0	68994.2	79425.2	94526.1	80433.8	77191.8	81045.4	84275.8	80527.3	75106.1	76254.6	79594.3	79496.0	88655.9	83098.7	85899.1	93673.2	71204.2	78030.8	76249.9	86607.1	91538.0
ZR	240.0	241.8	205.0	142.1		186.5	129.5	186.5	194.1	194.2	134.7	169.0	211.2	179.8	168.2	185.4	164.1	155.0	191.2	189.9	206.5	190.4	194.9	168.0	170.2	165.3	1.69.1	178.2	264.8			174.2	177.9			233.8	197.9	192.8	184.6		190.2			215.6
NZ	52.4	75.4		8.06	6'26	77.3	75.7	74.6	53.9	72.6	84.3	53.3	55.8	6.99	9.69	8.07	65.0	26.0	76.3	61.2	84.3	154.0	101.2	62.7	83.8	102.7	5'66	8.06	82.0	9.08	89.4	79.4	99.4	77.2			79.2	8.26	97.6	6'68	79.3	8.06	_	80.4
3 TH	5 18.66	14.72	7			1 44.78	7 9.15	36.77	2 21.20		3 8.79	1 29.85	2 56.29	3 34.80	37.10	1 42.01	50.91	5 36.12	2 35.20	39.86	3 39.49	9 41.17	1 37.25	39.01	(,,	3 9.78						_		2 10.32		3 15.78	16.09	5 11.27	10.90	7 22.11	19.71			5 18.38
TA	1.4970 0.75	1.0051 1.29	1.5545 0.93	0.6119 0.65		2.3079 2.31	0.5375 0.57	2.3942 1.89	1.5343 0.7	2.2682 1.54	0.5469 0.53	1.6362 0.81	2.4106 0.82	2.2108 1.83	2.1527 2.09	2.2142 1.51	2.2156 2.00	2.3000 1.86	2.3594 1.62	2.4562 1.79	2.5659 1.93	2.1715 1.59	2.3788 2.01	2.3404 2.10	2.1607 2.14	0.7348 0.68	0.7587 0.71		_	1.3734 1.55		2.1211 2.11	2.2295 1.72	0.8810 0.7		0.9996 1.23	1.2669 1.42	1.0873 0.86	0.9542 0.84	1.8316 1.57	1.3579 1.07		1.9371 1.13	1.1903 0.96
SR	258.4 1.4	215.2 1.0				58.3 2.3	297.4 0.5	48.7 2.3	278.5 1.5	68.6 2.2	352.6 0.5	120.9 1.6	107.3 2.4	31.5 2.2	36.0 2.1	74.5 2.2	48.3 2.2	30.4 2.3	54.7 2.3	30.1 2.4	44.7 2.5	69.8 2.1	60.8 2.3			395.7 0.7			243.6 1.C						_			290.9 1.0	420.8 0.5		320.0 1.3			281.9 1.1
SC	6.71 2	8.58 2	6.69		5.88		4.54 2	5.09	9.46	5.25	4.09	8.04	5.44	4.57	5.80	6.11	5.41	4.24	4.65	5.24	5.36		5.52	4.62		7.91 3	7.57 3									9.29		9.59 2	10.83 4	7.88 3	7.77 3			14.28 2
SB	0.3970	0.5247	0.3469	4.3040	0.3866	0.4807	3.3385	0.2720	0.4738	0.2618	2.4888	0.4100	0.7466	0.2346	0.5503	0.3447	0.4219	0.2883	0.2834	0.3482	0.5020	0.2916	0.2825	0.3505	0.3183	1.2351	1.6634	2.5235			1.9408	0.3290	0.3242	1.3069	2.2021	0.5806	0.7102	1.3128	0.9022	0.6310	0.3283			0.4588 1
RB	143.23	121.12	164.55	156.52	276.16	274.48	134.21	253.90	166.90	256.07	135.82	155.79	208.90	262.88	261.52	277.58	269.44	270.02	243.94	285.64	280.39	285.81	297.44	273.24	275.40	137.18	126.08	127.57			147.40	274.96	288.95	134.52	125.82	138.46	140.59	137.34	113.51	156.28	126.50	154.35	37.5 139.24	121.23
Z	0.0	31.6	17.6			0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	20.1	0.0		29.7		45.7		45.7								59.4	24.4	30.2	30.2	0.0	37.5	0.0
土	9.71	8.97	7.27	5.83	9.43	10.24	5.76	10.37	7.54	9.91	5.54	6.27	6.91	9.40	8.87	9.94	89.6	9.34	6.67	10.90	11.11	10.27	10.37	9.72	89.6	6.68	7.38	91.9	9.28	9.87	8.37	9.32	9.49	6.95	7.22	9.21	8.73	8.06	7.55	9.54	7.24	9.41	8.09	8.77
FE	24678.4	16993.5	21026.9	19573.9		15503.4		12824.8	21930.7	13076.2	17463.8	23902.7	11751.4	11352.4	13719.7	14913.9	13340.0	11306.7	11983.4		14716.6	13793.1	14202.0	11780.6	14691.1	30615.4	28451.4	22628.4	18101.3	22085.1	33208.2				28971.6	2.1530 22415.2		35125.2	39019.6	25496.4	25937.4	25324.2	31504.4	44960.8
EU	1.1375	2.0900		1.2414	0.5400	4.98 0.6628	1.1018	0.4690	0.9861	4.66 0.4401	1.1875	1.0545	1.0498	4.29 0.5474	4.86 0.5912	0.4931	4.56 0.7598	4.08 0.5670	3.99 0.5116	0.5315	4.70 0.5139	5.46 0.4726	5.25 0.5717	0.6131	5.36 0.5381	1.4497	1.3266					0.6282	0.5220		1.2876	2.1530	1.6016	1.3580	1.5039		1.6107		1.0067	1.4613
CS	4.35	4.11	5.17	30.82	5.54	4.98	22.35	4.36	19.79	4.66	22.59	2.68	19.10	4.29	4.86	4.88	4.56	4.08	3.99	4.76	4.70	5.46	5.25	4.21	5.36	17.35	15.87	17.91	4.41	8.21		5.54	5.08	19.16	15.15	4.47	7.79	15.66	11.41	6.05	4.08	6.07	7.87	4.31
ANID	LOA162	LOA163	LOA164	LOA165	LOA166	LOA167	LOA169	LOA170	L0A171	L0A172	LOA173	LOA176	LOA191	LOA192	LOA193	LOA194	LOA195	LOA196	LOA197	LOA199	LOA200	LOA201	LOA202	LOA203	LOA204	LOA205	LOA206	LOA207	LOA208	LOA209	L0A211	L0A212	LOA213	L0A214	LOA215	LOA216	LOA217	LOA218	LOA219	LOA220	LOA221	LOA222	LOA223	LOA224

ANID	macro_grp	Chem2012	CERAMIC TYPE	MATERIAL	SOURCE	STATE	SITE_NAME	SITE_NO	AS	ΓA	Π	ND	SM	n	YB ()E CO	CR
LOA225	Group-B	Unas.	Reserve Plain Smudged	Pottery	MURR		XSX	LA 050702	4.55	49.82 0	0.6252 4	47.30 9	9.32 4	4.53 5.	5.20 106.68	13.67	63.00
LOA226	Group-B1	Mimbres-05A	Reserve Plain Smudged	Pottery	MURR	(MN	XSX	LA 050702	3.44	49.72 0	0.5203 4	40.08	7.43 4	4.84 3.	3.46 102.27	27 11.62	50.10
LOA227	Group-B	Unas.	Reserve Plain Smudged	Pottery	MURR	MN	XSX	LA 050702	5.11	61.95 0	0.8058 6	64.99	12.12 4	4.69 6.	6.10 129.79	79 13.25	41.56
LOA228	Group-B	Unas.	Reserve Plain Smudged	Pottery	MURR		XSX	LA 050702	4.88		0.5201 4	42.06	7.94 4	4.09 3.	3.52 98.03	03 14.81	
LOA229	Group-B	Unas.	Reserve Plain Smudged	Pottery	MURR		XSX	LA 050702	3.14		0.6414 4	45.70 9	9.56 4	4.89 4.	4.78 102.36		59.82
MPC001	Group-B2	Mimbres-02A	Mimbres B/W Style III	Pottery	SI/NIST		Cameron Creek	LA 000190	2.24	l I	0.4539 2	25.84 5	5.18	8.16 3.	3.18 112.90	90 12.58	
MPC002	Group-C2a	Mimbres-49A	Mimbres B/W Style Indeter. Pottery	Pottery	SI/NIST		Cameron Creek	LA 000190	3.91	46.89 0	0.4473 3			2.08 3.	3.46 96.67	67 15.31	49.65
MPC003	Group-B	Unas.	Mimbres B/W Style Indeter.	Pottery	SI/NIST		Cameron Creek	LA 000190	4.77		0.4790 2			6.41 3.	3.63 111.81		17.94
MPC004	Group-B2	Mimbres-02A	Mimbres B/W Style III	Pottery	SI/NIST		Cameron Creek	LA 000190	1.66	65.22 0	0.4832 3		7.33 2	2.48 3.	3.42 88.61	12.97	36.45
MPC005	Group-A	Mimbres-01	Mimbres B/W Style Indeter. Pottery	Pottery	SI/NIST		Cameron Creek	LA 000190	3.52	75.21 0	0.6287 2	27.63 4	4.79 17	17.61 3.	3.66 119.95	95 12.97	9.48
MPC006	Group-B	Unas.	Mimbres B/W Style III	Pottery	SI/NIST) MN	Cameron Creek	LA 000190	2.25	37.62 0	0.3227 2		5.94 4	4.12 2.	2.94 74.90	90 17.95	26.04
MPC007	Group-B1	Mimbres-04B	Mimbres B/W Style III	Pottery	SI/NIST	MN	Cameron Creek	LA 000190	2.17	47.80 0	0.3996 3	34.72 6	6.49	2.25 3.	3.11 98.51	51 8.75	24.81
MPC008	Group-B	Unas.	Mimbres B/W Style III	Pottery	SI/NIST) MN	Cameron Creek	LA 000190	2.49	42.80 0	0.4573 2	21.95	5.66	3.31 3.	3.03 76.47	47 10.14	21.91
MPC009	Group-B2	Mimbres-02A	Mimbres B/W Style III	Pottery	SI/NIST) MN	Cameron Creek	LA 000190	2.21	45.23 0	0.4891 1	13.85 6	9.68	0.00	4.06 87.39	39 10.62	37.21
MPC010	Group-B	Unas.	Mimbres B/W Style III	Pottery	SI/NIST) MN	Cameron Creek	LA 000190	3.00	55.13 0	0.4188 2	28.54 (6.50	6.84 3.	3.55 87.79	11.61	20.93
MPC011	Group-B	Unas.	Mimbres B/W Style III	Pottery	SI/NIST		Cameron Creek	LA 000190	1.29						2.78 78.97		
MPC012	Group-B1	Mimbres-04A	Mimbres B/W Style III	Pottery	SI/NIST) MN	Cameron Creek	LA 000190	5.30	39.30 0	0.3344 2	20.82	4.76 5	5.26 2.	2.74 72.02	02 11.89	22.63
MPC013	Group-B1	Mimbres-04A	Mimbres B/W Style III	Pottery	SI/NIST	MN	Cameron Creek	LA 000190	3.25	53.02 0	0.5133 4	40.04	7.91	0.00	4.03 103.86	86 14.93	20.12
MPC014	Group-B1	Mimbres-04B	Mimbres B/W Style III	Pottery	SI/NIST	MN	Cameron Creek	LA 000190	2.04	42.70 0	0.3896 2	24.63 5	5.55 7	7.92 2.	2.81 81.18	18 15.10	23.32
MPC015	Group-B1	Mimbres-04A	Mimbres B/W Style III	Pottery	SI/NIST	MN	Cameron Creek	LA 000190	1.79	53.26 0	0.4339 2	23.31 7	7.66	0.00	3.41 103.86	86 10.52	22.42
MPC016	Group-B1	Mimbres-04A	Mimbres B/W Style III	Pottery	SI/NIST	MN	Cameron Creek	LA 000190	1.45	41.15 0	0.4448 3	36.94 6	6.49	3.46 3.	3.31 79.52	52 16.00	24.14
MPC017	Group-B	Unas.	Mimbres B/W Style III	Pottery	SI/NIST	MN	Cameron Creek	LA 000190	1.55	50.75 0	0.3336 2	28.22 E	5.52	7.32 3.	3.39 88.20	20 11.30	27.40
MPC018	Group-B1	Mimbres-04B	Mimbres B/W Style III	Pottery	SI/NIST	MN	Cameron Creek	LA 000190	2.73	54.75 0	0.4715 1	19.70	7.59 4	4.30 3.	3.35 103.86	86 10.62	
MPC019	Group-B2	Mimbres-02A	Mimbres B/W Style III	Pottery	SI/NIST		Cameron Creek	LA 000190	1.98		0.4891	13.57 6	6.43 C	0.00			35.13
MPC020	Group-A	Mimbres-10	Mimbres B/W Style III	Pottery	SI/NIST		Cameron Creek	LA 000190	3.20	95.81 1	1.1119 8	82.89 19	19.32 C	0.00	8.84 191.63	53 13.46	41.18
MPC021	Group-C2	Unas.	Mimbres B/W Style III	Pottery	SI/NIST		Cameron Creek	LA 000190	0.00	53.26 0		11.98	2.77 10	10.78 2.	2.65 83.27	27 15.60	49.85
MPC022	Group-B	Unas.	Mimbres B/W Style III	Pottery	SI/NIST	NM	Cameron Creek	LA 000190	2.32	32.24 0	0.1547	0.00	2.86 C	0.00	1.55 46.18	18 6.43	9.88
MPC023	Group-C1	Mimbres-21	Mimbres B/W Style III	Pottery	SI/NIST		Cameron Creek	LA 000190	1.58								_
MPC024	Group-C1	Unas.	Mimbres B/W Style III	Pottery	SI/NIST		Cameron Creek	LA 000190	6.94						3.09 77.89	1	42.83
MPC025	Group-B	Unas.	Mimbres B/W Style III	Pottery	SI/NIST		Cameron Creek	LA 000190	2.02								
MPG024	Group-B	Unas.	Mimbres B/W Style III	Pottery	SI/NIST		Galaz	LA 000635	7.65	-					1		
MPG026	Group-B	Unas.	Mimbres B/W Style III	Pottery	SINIS		Galaz	LA 000635	1.99							J	
MPG027	Group-B	Unas.	Mimbres B/W Style III	Pottery	SI/NIST		Galaz	LA 000635	1.80						_	_	
MPG029	Group-B	Unas.	Mimbres B/W Style III	Pottery	SI/NIST		Galaz	LA 000635	3.35							1	
MPG036	Group-B2	Mimbres-02A	Mimbres B/W Style III	Pottery	SI/NIST		Galaz	LA 000635	1.97				4.58				
MPG042	Group-B2	Mimbres-02A	Mimbres B/W Style III	Pottery	SI/NIST		Galaz	LA 000635	2.05	47.36 0	0.4899 2		6.68			19 8.93	
MPG046	Group-B	Unas.	Mimbres B/W Style III	Pottery	SI/NIST		Galaz	LA 000635	1.25						3.34 99.19		
MPG047	Group-B	Unas.	Mimbres B/W Style III	Pottery	SI/NIST	NM	Galaz	LA 000635	2.61	42.98 0	0.3795 2	27.35 5	5.33 2	2.76 3.	3.11 77.01		32.60
MPG048	Group-C1	Mimbres-21	Mimbres B/W Style III	Pottery	SI/NIST		Galaz	LA 000635	2.56		Ì	17.16 6	6.03 C	0.00		1	
MPM001	Group-B1	Mimbres-04A	Mimbres B/W Style III	Pottery	SI/NIST		Mattocks	LA 000676	2.45								
MPM002	Group-B	Unas.	Mimbres B/W Style III	Pottery	SI/NIST		Mattocks	LA 000676	1.94		0.4523		5.65 2	2.51 3.		38 10.42	
MPM003	Group-B1	Mimbres-04B	Mimbres B/W Style III	Pottery	SI/NIST		Mattocks	LA 000676	2.83	50.40 0	0.4966 2						
MPM004	Group-B	Unas.	Mimbres B/W Style III	Pottery	SI/NIST		Mattocks	LA 000676	1.31								
MPM005	Group-B1	Mimbres-04C	Mimbres B/W Style III	Pottery	SI/NIST	NM N	Mattocks	LA 000676	4.00	43.79 0	0.4030 2	27.32	5.85	2.41 3.	3.19 87.79	79 13.37	30.18

>	91.97	75.48	92.60	97.14	86.59	55.20	70.06	25.60	56.69	16.80	54.71	47.52	49.54	96.69	44.78	42.22	48.88	44.52	45.31	48.79	65.42	55.91	56.59	64.50	55.58	91.75	18.50	63.62	74.91	55.11	59.30	58.17	51.01	65.41	44.32	68.03	41.70	61.40	70.83	42.90	58.29	43.54	42.53	76.46
=	4862.7	4709.2	4634.1	4656.9	4753.8	3687.0	4350.6	2976.4		991.4	4175.6	2837.5	2791.1	2617.5	3061.2	4117.5	2956.0	1798.9	2601.7	3086.9	3622.6	2815.7	3348.5	3038.0					3321.9	2650.9	2983.7	3142.4	2931.4				1352.6	2413.0	3376.2		4465.8			3490.3
NA	13566.2	13699.4	13747.3		15034.6	12177.1	15319.8	14766.0	13790.8	14862.5	12266.1	11618.5	14699.4	13103.3	12651.6	14290.2	11583.6	15009.5	10383.3	14227.5	13871.3	11433.9	10337.4														14616.1	14595.2	19678.0		15005.8			14189.5
MN	687.1 13		927.9 13		552.2 150	339.7 12	856.1 153	1156.6 14	602.1 13	356.5 148	357.9 12.	247.5 110	426.2 146	231.7 13	315.3 120		322.0 11!	1346.7 150	193.7 103	224.3 14,	464.0 138	296.3 114	251.6 103	538.4 13		,		`	,	_			_			251.4 13	1762.3 146	876.3 14	806.4 196		350.4 150	-		554.3 14
¥	29145.2 68	_	8	28066.2 9	28986.4 5	2	26414.8 8	21444.9 11	27965.7 60	27870.1 3	26607.8	27366.8 2	29590.1 4;	25629.7 2:	29365.7 3	28294.4 29		25848.3 13	27350.0 1	28370.2	29526.9 44	32775.9 29	25976.7	28724.6 5:	30223.3 7.				1		`							22964.5 8			29278.5 3	~	7	25688.5 58
DY	7.016 291	81 29142.	04 27837.		7.165 289	74 28759.	5.484 264	_				_	_				7.669.7												-	- 1	- 1	- 1				-			_			- 1		
CA		.0 5.881	.7 9.704	.5 5.495		.7 5.074		.4 5.847	.3 6.104	.3 5.285		.6 4.511	.9 4.527	.0 5.024	.0 5.260	.1 4.486	.7 3.772	.8 6.243	.4 4.583	.3 5.387	.9 5.127	.3 4.239	.9 5.310	.7 4.530	1											.5 5.410		.2 3.905			.7 4.525			.4 4.502
0	18116.4	18516.0	9075.7	14247.5	15742.9	9010.7	119621	11168.4	14025.3	13097.3	11330.8	9873.6	12583.9	11917.0	10074.0	8654.1	11162.7	12474.8	7847.4	1	9518.9	10816.3	8811.9	13508.7		_				`				1	6415.5			14290.2	`	`	1.90601			12730.4
BA	759.4	1195.1	750.0	1.096	6.099	475.6	1.326	780.5	207.2	642.3	733.3	612.6	739.7	9.783	9.869	1.968	662.0	864.9	528.8	757.0	846.8	656.7	586.0				241.0	938.0	844.6	785.0	818.0	634.4	742.7	420.3	399.7	545.2	533.6	585.7	844.0		806	626.7	869.4	684.6
AL	85134.6	77084.8	79937.2	74640.0	82489.5	90427.3	91212.4	87096.2	82472.0	99643.1	88927.7	90380.1	88872.4	86005.9	82588.6	78459.5	89259.3	87679.3	88194.5	86681.3	81776.8	97804.1	96922.2	83666.2	79594.4	91968.0	92888.3	91892.5	69354.0	82233.8	89349.9	95596.6	90091.0	81914.9	87849.8	92951.7	82587.1	86201.4	95599.2	91228.0	88740.3	88925.0	86941.0	95879.4
ZR	263.9	237.1	270.0	244.9	258.2	272.0	354.0	222.8	195.9	270.0	299.2	200.0	264.2	233.9	255.3	269.8	196.8	204.2	181.1	186.2	328.1	264.2	220.8	193.2		309.7	127.1	221.8	255.9	248.9	188.8	179.9	187.1	147.9	222.8	208.0	227.0	205.0	245.0	212.8	257.0	195.9	195.9	267.3
NZ	113.1	93.0	120.9	89.3	110.2	52.5	91.5	58.6	8.79	47.1	55.8	52.6	91.3	26.0	43.5	42.4	83.1	59.9	9.99	60.3	49.7	57.6	59.2	55.9	8.76	93.4	48.1	86.7	91.5	42.2	62.1	71.2	66.7	68.3	52.4	54.3	0.09	72.6	82.1	48.8	51.4	61.1	55.2	72.4
TH	20.83	17.84		19.61		20.96	13.50		20.00	51.26		28.44	19.54	20.46	24.72		22.54	19.36	26.54	23.23	20.09	25.47	28.57	19.72			7			- 1	19.27	_				21.43		20.86			19.05			19.81
_	1.21	0.94	1.69	0.93	1.28	0.62	0.99	1.18	1.06	0.70	0.84	0.80	0.78	0.97	1.03	99.0	0.58	1.05	0.70	0.92	0.88	0.63	1.02	0.92	2.95		0.38			0.06	٠.					0.96		0.52	0.78	0.75	0.78	0.88		0.76
TA	1.8657	1.6939	1.6681	1.6791	1.9571	1.5000	1.1400	1.5700	1.3000	2.1900	2.3710	1.7220	1.7220	1.4790	2.1380	2.0280	1.4090	1.4190	1.4690	1.4890	1.6290	1.6290	1.6290	1.4390	1.8880	1.0500	1.6410			,		1.6110	1.5600				1.8500	1.2200	0.7160	1.3610	1.4590	1.4490		1.4590
SR	309.6	471.6	218.9	397.4	306.8	252.0	296.0	267.9	558.5	115.0	306.2	182.8	272.3	293.1	238.2	311.2	191.0	287.7	130.9	293.8	330.4	258.2	129.1	417.8	238.2	237.1	71.0	492.0	381.9	212.8	285.8	269.8	295.8	358.9	201.8	308.3	171.0	438.0	418.0	297.2	291.7	167.1	289.7	328.9
SC	13.57	10.09	11.18	9.25	11.74	89.6	10.40	8.07	10.89	4.98	8.07	7.98	7.35	12.00	6.73	11.9	69'L	8.02	7.43	8.32	7.33	8.11	8.95	10.21		_										11.91		8.97	8.97	6.75	7.06	7.38	7.11	8.47
SB	0.5411	0.4063	0.6654	0.4592	0.4372	0.7236	1.0089	0.0000	0.6302	0.8684	0.4143	0.0000	0.5061	0.4664	0.0000	0.3027	0.7972	0.0000	0.3482	0.0000	0.3680	0.6335	0.4491	0.0000	0.8047	0.5218	0.0000	1.4406	0.7104	0.4226	0.0000	0.2605	0.3746	0.4185	0.6798	0.5417	0.4069	0.6690	1.3728	0.0000	0.3862	0.3465	0.0000	0.0000
RB	134.01	123.77	134.79	134.25	138.82	152.60	133.10	78.30	166.00	199.60	125.90	203.20	136.80	149.90	129.40	103.80	171.40	141.90	174.60	137.40	173.00	222.80	175.80	159.60	187.10	211.80	46.10	98.40	153.50	169.40	120.70	174.60	121.60	177.40	170.20	125.90	152.60	168.50	141.90	169.40	146.20	166.00	79.60	149.90
Z	49.0	38.0	0.0	0.0	37.4	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0			0.0	0.0			0.0							0.0	0.0	0.0	0.0	0.0		0.0
生	10.09	8.45	10.17	68.6	9.71	8.47	10.79	7.36	7.31	6.21	9.81	6.19	7.48	7.53	7.77	8.07	6.12	7.24	5.75	7.16	11.08	6.72	7.14	7.88		_	7.27	98.9	6.87	7.19	6.50	99.9	6.65	5.90	9.13	7.32	6.05	6.22	6.72	7.48	10.11	6.03	6.57	8.31
FE	41931.1	30844.9	35650.7	34549.7	37548.9	22300.0	38900.0	26121.6	28774.0	14900.0	25527.0	23878.1	25585.9	26485.0	20701.4	20701.4	27101.9	25822.6	23014.4	23280.9	25118.9	22182.0	26181.8	25822.6	33884.4	39994.5	11587.8	31405.1	32136.6	20701.4	28183.8	30690.2	26915.3	25527.0	19588.4	26181.8	19600.0	27700.0	33300.0	19906.7	25527.0	23388.4	22490.6	33728.7
EN	1.5857	1.3246	2.0534		1.5948	1.0149	1.7302	1.5287	1.3810	0.9379	1.2027	1.1278	1.2227	1.3409	1.2860	1.1172	0.9400	1.4559	1.0033	1.4559	1.2860	1.2227	1.3282	1.3071		1.6458	7.3967	1.4359	_		1.6880							1.1816			1.1922		1.3282	1.1805
CS	5.56	4.73	4.97	4.94	5.66	20.16	7.29	4.62	23.47	16.63	5.40	5.81	5.06	16.73	5.21		5.54 (5.08	5.54	5.06	4.94	13.11	6.22	20.16	10.06	7.40		-							16.92		9.17 (17.44			4.56			5.00
ANID	LOA225	LOA226	L0A227	LOA228	LOA229	MPC001	MPC002	MPC003	MPC004	MPC005	MPC006	MPC007	MPC008	MPC009	MPC010	MPC011	MPC012	MPC013	MPC014	MPC015	MPC016	MPC017	MPC018	MPC019	MPC020	MPC021	MPC022	MPC023	MPC024	MPC025	MPG024	MPG026	MPG027	MPG029	MPG036	MPG042	MPG046	MPG047	MPG048	MPM001	MPM002	MPM003	MPM004	MPM005

ANID	macro_grp	Chem2012	CERAMIC TYPE	MATERIAL	SOURCE	STATE	SITE_NAME	SITE_NO	AS	ΓA	Π	ND	SM	\ N	YB CE	E CO	CR
MPM006	Group-B1	Mimbres-04A		Pottery	SI/NIST	M		LA 000676	89.9	56.55 0	0.5894		0 89.6	0.00 4.48	133.19	7	20.12
MPM007	Group-B1	Mimbres-04A	Mimbres B/W Style III	Pottery	SI/NIST	MN	Mattocks	LA 000676	2.37	34.15 0	0.2817	13.95 4	4.01	3.90 2.85		4 14.42	19.04
MPM008	Group-B2	Mimbres-08	Mimbres B/W Style III	Pottery	SI/NIST	MN	Mattocks	LA 000676	2.41	33.15 0	0.2642	14.81	2.96 4	4.82 2.4	2.45 57.47	7 23.02	22.53
MPM009	Group-B1	Mimbres-04A	Mimbres B/W Style III	Pottery	SI/NIST	MN	Mattocks	LA 000676	2.08	43.60 0	0.3377	20.75 4	4.88 6	6.37 2.55	55 84.07	7 10.14	24.53
MPM011	Group-B1	Mimbres-04A	Mimbres B/W Style III	Pottery	SI/NIST	NM	Mattocks	LA 000676	2.00			30.87 6		7.34 3.25	1	`	
MPM012	Group-B2	Mimbres-08	Mimbres B/W Style III	Pottery	SI/NIST	MM	Mattocks	LA 000676	3.00							1	
MPM013	Group-B1	Mimbres-04A	Mimbres B/W Style III	Pottery	SI/NIST	M	Mattocks	LA 000676	1.99	46.27 0	0.4247	33.95 6	6.73 3	3.32 3.15	15 79.93	3 8.93	26.62
MPM014	Group-B2	Mimbres-08	Mimbres B/W Style III	Pottery	SI/NIST	M	Mattocks	LA 000676	3.75							1	
MPM015	Group-B	Unas.	Mimbres B/W Style III	Pottery	SI/NIST	NM	Mattocks	LA 000676	3.90	-				9.93 2.71			25.52
MPM016	Group-A	Mimbres-01	Mimbres B/W Style III	Pottery	SI/NIST	MN	Mattocks	LA 000676	1.44	46.71 0	0.3194			10.73 2.21	21 68.44	4 7.20	6.16
MPM017	Group-B1	Mimbres-04A	Mimbres B/W Style III	Pottery	SI/NIST	MN	Mattocks	LA 000676	1.80	38.27 0	0.4080	26.78 5	5.90	3.22 3.10	10 77.72	2 9.85	26.02
MPM018	Group-B	Unas.	Mimbres B/W Style III	Pottery	SI/NIST	MN	Mattocks	LA 000676	2.44	33.83 0	0.3586 2	24.33 5	5.38	3.57 2.79	19 63.91	1 11.60	27.32
MPM019	Group-C2	Unas.	Mimbres B/W Style III	Pottery	SI/NIST	MN	Mattocks	LA 000676	2.13		0.2734 2	21.69 6		0.00	98 82.15	5 19.01	67.90
MPM020	Group-B1	Mimbres-04B	Mimbres B/W Style III	Pottery	SI/NIST	MN	Mattocks	LA 000676	2.42	43.59 0	0.3745 2	21.41 6	6.27 4	4.24 3.34	34 79.52	2 16.00	25.51
MPM021	Group-A	Mimbres-01*	Mimbres B/W Style III	Pottery	SI/NIST	MN	Mattocks	LA 000676	60.9	63.59 0	0.5166	25.73 10	10.09	0.95 4.63	53 107.76	06.9	7.92
MPM022	Group-B2	Mimbres-08	Mimbres B/W Style III	Pottery	SI/NIST	MN	Mattocks	LA 000676	2.41	37.45 0	0.4665 1	12.46 3	3.39 6.	6.82 3.20	90'.29 05	6 12.27	22.01
MPM023	Group-A	Mimbres-01	Mimbres B/W Style III	Pottery	SI/NIST	MN	Mattocks	LA 000676	2.80	68.46 0	0.3687	21.85 4	4.78 14	14.58 3.07	114.94	4 20.85	6.50
MPM024	Group-B	Unas.	Mimbres B/W Style III	Pottery	SI/NIST	MN	Mattocks	LA 000676	5.06	44.30 0	0.4096	30.94 6	6.49	6.68 3.35	35 81.75	5 14.42	22.53
MPM025	Group-B1	Mimbres-04B	Mimbres B/W Style III	Pottery	SI/NIST	MN	Mattocks	LA 000676	2.12	66.59	0.5141	34.48 8	8.22	7.24 4.18	18 96.04	4 14.83	24.81
MPM026	Group-A	Mimbres-01	Mimbres B/W Style III	Pottery	SI/NIST	MN	Mattocks	LA 000676	3.81	66.13 0	0.4297	16.43 3	3.63 19	19.13 3.19	96.86	6 7.94	7.69
MPM027	Group-B1	Mimbres-04A	Mimbres B/W Style III	Pottery	SI/NIST	MN	Mattocks	LA 000676	2.68	63.16 0	0.4289	23.58 9	9.35 0	0.00 3.96	96 110.78	8 12.19	18.44
MPM1A	Group-C1	Mimbres-21	Mimbres B/W Style III	Pottery	SI/NIST	MN	Mattocks	LA 000676	3.12		0.2583			0.00 2.50	50 79.34	11.61	21.71
MPM1B	Group-C1	Mimbres-21	Mimbres B/W Style III	Pottery	SI/NIST	MN	Mattocks	LA 000676	2.91	39.03 0	0.2909	33.54 5	5.61	0.00 1.93	17.89	9 9.84	24.25
MPM1C	Group-C1	Unas.	Mimbres B/W Style III	Pottery	SI/NIST	MN	Mattocks	LA 000676	2.98	40.50 0	0.1822	25.73 5	2.69	0.00 2.18	18 80.81	1 25.35	21.61
MPM1D	Group-C1	Mimbres-21	Mimbres B/W Style III	Pottery	SI/NIST	MN	Mattocks	LA 000676	3.03	41.15 0	0.2383 2	20.35 5	5.77 0	0.00 2.03	13 80.81	1 20.56	29.70
MPM2A	Group-B2	Mimbres-08	Mimbres B/W Style III	Pottery	SI/NIST	NM	Mattocks	LA 000676	2.99	33.84 0	0.2859	0.00		3.92 2.14			26.04
MPM2B	Group-B2	Mimbres-08	Mimbres B/W Style III	Pottery	SI/NIST	M	Mattocks	LA 000676	2.41	-							
MPM2C	Group-B2	Mimbres-08	Mimbres B/W Style III	Pottery	SI/NIST	M	Mattocks	LA 000676	3.03		_						
MPM2D	Group-B2	Mimbres-08	Mimbres B/W Style III	Pottery	SI/NIST	M	Mattocks	LA 000676	3.20	_	0.1547	0.00	3.00 5		1.85 58.54		
MPN001	Group-B1	Mimbres-04A	Mimbres B/W Style III	Pottery	SI/NIST	M	NAN	LA 002465	1.88	50.87	0.3578 2	23.10 6	6.92	3.92 3.19	19 95.16	6 12.88	20.36
MPN002	Group-B2	Mimbres-02B	Mimbres B/W Style III	Pottery	SI/NIST	M	NAN	LA 002465	2.92								35.21
MPN003	Group-B	Unas.	Mimbres B/W Style III	Pottery	SI/NIST	MM	NAN	LA 002465	2.34								
MPN004	Group-B1	Mimbres-04B	Mimbres B/W Style III	Pottery	SI/NIST	MM	NAN	LA 002465	2.83							6 18.16	
MPN005	Group-B2	Mimbres-08	Mimbres B/W Style III	Pottery	SI/NIST	NM	NAN	LA 002465	2.87	34.31 0	0.2592	9.07 3	3.05 6	6.29 2.42	12 57.47	7 16.79	24.93
MPN006	Group-B1	Mimbres-04A	Mimbres B/W Style III	Pottery	SI/NIST	NM	NAN	LA 002465	2.39	51.57 0	0.4013 2	21.50 8	8.11 2	2.03 3.19	103.86	6 12.27	20.45
MPN007	Group-B	Unas.	Mimbres B/W Style III	Pottery	SI/NIST	Σ	NAN	LA 002465	1.88	45.23 0	0.3010	19.98 6	6.04 5	5.37 3.15		1 9.75	21.12
MPN008	Group-B	Unas.	Mimbres B/W Style III	Pottery	SI/NIST	MN	NAN	LA 002465	2.71	51.45 0	0.3536	30.31 6	6.62	2.60 2.7	2.76 99.42	2 10.23	27.91
MPN009	Group-B2	Mimbres-02A	Mimbres B/W Style III	Pottery	SI/NIST	MN	NAN	LA 002465	2.49	39.03 0	0.3921 2	22.36 4	4.25 5.	5.13 3.14	14 64.78	8 11.02	36.96
MPN010	Group-B2	Mimbres-11	Mimbres B/W Style III	Pottery	SI/NIST	MN	NAN	LA 002465	3.20	35.43 0	0.3637	19.88 4	4.19	4.87 2.98	98 68.46	6 24.27	40.71
MPN011	Group-B1	Mimbres-04A	Mimbres B/W Style III	Pottery	SI/NIST	MN	NAN	LA 002465	2.19	40.78 0	0.3394	21.95 5	5.28	1.45 2.73	73 70.38	8 10.52	19.94
MPN012	Group-B	Unas.	Mimbres B/W Style III	Pottery	SI/NIST	NM	NAN	LA 002465	2.59	39.30 0	0.4080	23.85 5		4.00 3.27	27 76.29		22.12
MPN014	Group-B	Unas.	Mimbres B/W Style III	Pottery	SI/NIST	M	NAN	LA 002465	3.71								
MPN017	Group-B1	Mimbres-04A	Mimbres B/W Style III	Pottery	SI/NIST	MN	NAN	LA 002465	2.04					2.98 3.37		9 12.59	20.83
MPN021	Group-B	Unas.	Mimbres B/W Style III	Pottery	SI/NIST	MM	NAN	LA 002465	3.14	43.29 0	0.3102	13.85 4	4.94 6.	6.93 2.63	53 75.42	2 10.42	17.25

>	70.27	45.28	48.70	46.81	68.09	38.42	59.97	50.36	70.00	23.03	53.38	46.22	92.95	52.67	31.09	40.95	38.99	58.74	53.48	17.24	45.42	46.90	43.44	48.72	54.87	41.32	36.80	42.11	47.97	53.24	62.50	54.81	50.93	46.19	51.65	44.42	49.90	49.30	48.74	37.14	52.06	49.22	43.62	44.03
I	3178.3	3405.9	2825.8	3852.2	3902.8	2522.6	3653.2	2685.0	3419.3	1242.1	4373.5	2134.7	4330.2	3218.1	940.6	2826.6	1873.5	3833.9	3211.9	1505.3	2606.4	2453.1	1987.8	1875.4	2284.6	2508.6	2531.3	3217.7	3296.1	2848.7	2818.5	4086.8	2830.4	2795.1	2795.5	2704.8	3217.3	3628.6	3444.0	2469.7	3528.9	1624.4	2929.8	2806.1
NA	13965.9	14218.4	10073.8	15022.1	14450.2	9769.5	5455.5	9873.6	0904.5	10522.1	14058.1	11669.2	21010.1	10585.8	19176.7	10592.8	21178.3	16487.1	11704.6	14660.6	14781.4	8.69601	10643.9	10991.7	11179.5	8690.5	8723.2	9704.1	9930.4	16537.3	1970.9	13030.6	13096.1	9522.5	15240.8	16661.0	15387.0	11306.8	11546.4	15891.2	14386.5	11441.7	16355.8	17343.2
MN		200.1	176.5	295.9	1		473.6		168.9	195.9 1	337.0 1	254.7 1	618.2	314.0 1	881.0 1		- 1	9.999	474.8 1	254.8 1	285.4	1242.3	1329.3	1332.9	1203.7				197.1	_	Υ.		$\overline{}$	188.6	397.0	138.3	608.4	176.7	914.4	452.7	1			217.0 1
¥	21536.7	28748.1	30247.6	30251.3	25810.4	30354.9	27646.6	27863.1	28084.4	34050.9	27894.6	30986.0	21071.5	25217.8	31839.4	28434.7	30333.1	30618.6	26672.8	30016.8	31693.6	21661.5	18697.3	23368.9	•	29402.2	27381.3	28742.8	32267.8	27395.7	30568.0	26525.5	28771.1	30213.4	29490.5	29192.5	31093.2	31429.1	27614.1	30754.8	28837.4	20526.8	29660.2	32401.9
DY	7.199 2	3.112 2	2.808 3		,	٠,	5.299 2	•	4.773 2		5.345 2	4.457 3	3.772	4.828 2	3.015 3				6.299	3.583 3	6.815 3	3.832 2	3.467	3.130 2	3.890 2			_	2.537 3	- 1		- 1	- 1	2.772 3	5.094 2	4.453 2	5.073 3				,	- 1	- 1	4.278 3
CA	12636.1	9561.9	6180.5	9154.9	13498.6	6041.3	13422.6	6104.7	7879.5	6291.0	10803.3	11548.9	26972.8	10900.0	18368.4	8261.1	6345.0	14506.7	11127.2	21169.4	10003.9	51402.1	54243.8	54794.6	47360.1	6520.8	5123.5	6277.3	5838.9	15095.1	11213.2	9137.5	9.9266	8.8959	12001.4	12994.7	16784.4	8558.1	9202.9	12206.3	10166.5	19479.9	14468.9	11223.4
BA	991.4	727.6	435.7	957.2	748.6	473.1	848.3	448.7	520.1	394.9	773.0	489.1	871.9	500.2	620.5	459.1	372.4	703.4	650.0	297.7	681.8	662.0	747.9	679.4	819.5	407.6	379.2	437.6	446.4	0.777	397.5	728.6	634.0	440.9	823.5	733.3	959.4	383.0	401.1	704.3	663.3	329.1	761.9	786.6
AL	90101.4	95012.5	79172.8	80693.3	90940.2	80263.4	84927.8	87698.7	90439.7	91241.0	83216.0	82140.8	106669.2	98736.8	123631.3	87091.2	17154.5	84416.2	83554.2	0.64850	87354.1	89393.7	87466.9	89699.1	91872.2	87526.7	88133.1	93547.0	90225.9	86353.3	89418.7	83865.4	76552.3	85777.6	6.76998	86793.3	87048.5	88644.2	75260.0	89847.4	84915.1	76698.8	83956.0	87891.9
ZR		227.0	231.7	352.0			259.0		208.0	157.0	322.0	120.0	92.9	181.1	247.7	222.8	_	261.2	209.9	247.7	314.8	208.0	188.8	_	1.661				231.2		~			188.8	182.0	247.2	258.8	233.9	195.0	217.8	8			199.1
NZ	64.6	8.79	36.0	31.1	60.2	37.0	49.7	46.1	45.8	35.4	48.2	49.9	92.4	59.9	55.3	44.9	42.6	63.6	41.3	44.0	49.7	76.1	78.6	81.3	74.4	39.9	43.8	43.3	42.3	51.8	63.9	53.7	44.3	48.0	52.1	54.6	72.6	55.8	56.3	73.6	50.3	61.4		53.0
3 TH		0 23.01	3 26.79	19.82						3 43.90	5 19.16	5 18.97	9.39	5 25.94	4 56.36			2 17.26	3 26.73	7 52.36	1 22.54	3 9.12	8.77											3 29.71	19.54	4 22.54	3 15.38	2 23.01				9 20.84		4 21.83
TA TB		110 0.50	330 0.48	900 0.64		_	1.4100 0.82		900 0.72	100 0.40	1.6400 0.76	300 0.76	520 0.7	190 0.75	380 0.54	790 0.58		910 0.92	1.23	280 0.47	1.5000 1.21	580 0.7	710 0.69	69.0 09/	180 0.65	710 0.42			1.5600 0.44			210 0.82	390 0.74	190 0.48	510 0.94	190 0.84	98.0 069	390 0.62	1.6710 0.66	300 0.75	06'0 001	1.3490 0.7		590 0.94
SR		231.2 1.6110	102.1 3.1330	316.0 1.4900		٠,	391.0 1.47			124.0 2.2400	301.0 1.64	164.0 1.1300	679.0 0.7620	198.2 1.5490	150.0 2.4380	177.0 1.4790		264.9 1.2910	199.1 1.5490	123.0 2.3280	196.8 1.50	538.3 0.6580	553.4 0.6710	418.8 0.6760	441.6 0.6180			`	0.0 1.56	_	_			195.0 1.5490	285.1 1.3610	358.9 1.3490	406.4 1.1690	٠,	•	264.2 1.7300	`	_		339.6 1.4590
SC		7.00 23	5.72 10		9.20 34		8.49 39		7.62 14	4.16 12	6.81 30	7.36 16	14.90 67	9.00 19	5.26 15			7.21 26	6.95 19	4.59 12	7.13 19	6.62 53	6.47 55			6.53 14		6.65 7	6.19					6.56 19	7.33 28	7.33 35		9.80 20	7.75 22					6.98 33
SB		0.3912 7	0.3283								0.4019	0.3482 7	0.0000	0.3275 9	1.2066			0.0000	0.3862	0.8684	0.0000	1.1652 (0.5582 (0.0000	0.2655 7	1.1255 8		0.6508 7	0.4209 7				0.3812 (
RB			173.00 0								160.50 0	142.80 0	0.00	153.50 0	183.60				157.00 0	197.60 0	146.20 0	107.40	83.20 1						195.00 0						127.60 0	111.70 0	108.10	142.90 0						161.40 0
N	0.0	0.0	0.0	0.0			0.0		0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0		0.0 13	0.0	0.0	0.0	0.0	0.0	0.0										0.0	0.0	0.0	0.0	0.0	0.0	0.0				0.0
H	7.46	7.12	9.05	10.10	97.9	6.62	7.33	7.55	6.74	5.88	9.37	5.69	6.22	6.44	8.01	7.44	7.16	6.67	7.83	7.37	9.13	6.36	5.59	6.26	5.94	7.60	6.44	6.87	7.56	6.33	6.44	10.49	7.34	6.45	6.15	7.65	8.27	8.68	8.29	7.60	6.65	5.79	98.9	6.59
FE	28510.2	24378.1	19186.7	21400.0	27478.9	18706.8	25400.0	22387.2	24200.0	11100.0	21900.0	20400.0	39800.0	25822.6	15995.6	21086.3	14092.9	33265.9	22284.4	13001.7	22387.2	25822.6	25882.1	27101.9	26181.8	21379.6	20797.0	21379.6	20090.9	19319.7			20893.0	22182.0	20701.4	15995.6	26181.8	21086.3	23014.4	23878.1	23823.2	23014.4	23280.9	20701.4
EU	_	0.8577 2	0.6087 1				1.4454 2		1.0761 2	0.4188 1	1.2027 2	1.0867 2	1.6353 3	1.1278 2	0.6615 1				1.5498 2	0.6151 1	1.6342 2	1.4137 2	1.3493 2											0.6341 2	1.4865 2		1.5498 2		0.8978 2	1.1278 2				1.1172 2
CS		4.54	7.12 0							14.92	4.45	6.48	1 99.9	6.05	21.26 0	6.82	19.34 0	3.69	5.24	15.54 0	5.33	18.05	17.76	18.05	18.26		7.81	7.95 0	7.37 0					7.56 0	4.61	4.69		20.35 0	7.30 0					4.52
ANID	MPM006	MPM007	MPM008	MPM009	MPM011	MPM012	MPM013	MPM014	MPM015	MPM016	MPM017	MPM018	MPM019	MPM020	MPM021	MPM022	MPM023	MPM024	MPM025	MPM026	MPM027	MPM1A	MPM1B	MPM1C	MPM1D	MPM2A	MPM2B	MPM2C	MPM2D	MPN001	MPN002	MPN003	MPN004	MPN005	900NAW	MPN007	MPN008	MPN009	MPN010	MPN011	MPN012	MPN014	MPN017	MPN021

ANID	macro_grp	Chem2012	CERAMIC TYPE	MATERIAL	SOURCE	STATE SITE_NAME	ME SITE_NO	AS	LA	Π	ND	SM	Π	YB	CE (00	CR
MPN022	Group-A	Mimbres-01	Mimbres B/W Style III	Pottery	SI/NIST N		LA 002465	0.00	48.24	0.3018	12.72	3.18	11.21	2.54 7	79.15 11.		10.06
MPN023	Group-B2	Mimbres-02A	Mimbres B/W Style III	Pottery		NW NAN	LA 002465	2.09	40.59	0.4230	14.14	5.33	3.25	3.56 6	68.62 17.	17.82 4	41.09
MPN024	Group-B1	Mimbres-04A	Mimbres B/W Style III	Pottery	SI/NIST N	NM NAN	LA 002465	2.89	44.10	0.4247	20.35	5.46	8.14	3.80 8	80.81 11.	11.40	19.44
MPN025	Group-B2	Mimbres-02A	Mimbres B/W Style III	Pottery			LA 002465	1.69		0.4247	26.76	6.52	4.58	3.86		18.24 3	39.78
MPN026	Group-B2	Mimbres-02A	Mimbres B/W Style III	Pottery		NW NAN	LA 002465	1.16	39.12		18.69	5.53	7.43	3.87 7	77.89 11.		39.78
MPP001	Group-B1	Mimbres-05A	Mimbres B/W Style III	Pottery	SI/NIST A	AZ Powers Ranch	anch AZ CC:3:46 ((4 2.79	46.60	0.5225	27.51	9.14	1.73	4.34 10	102.91 15.31		49.40
MPP002	Group-B	Unas.	Mimbres B/W Style III	Pottery	SI/NIST A	AZ Powers Ranch	anch AZ CC:3:46 (<i>i</i>	(4 4.36	86'39	0.7624	52.18	13.49	2.72	6.07 13	137.23 11.	11.30 2	25.22
MPP003	Group-C1	Mimbres-21	Mimbres B/W Style III	Pottery		AZ Powers Ranch		(4 3.54	40.59	0.3486	24.13	6.41	0.00	2.59 8		13.84 6	68.34
MPP004	Group-B1	Mimbres-05A	Mimbres B/W Style III	Pottery	SI/NIST A	VZ Powers Ranch	anch AZ CC:3:46 ((4 3.44	48.46	0.5559	38.33	99.6	2.58	4.33 10	109.76 11.	11.70 5	57.37
MPP005	Group-C1	Mimbres-22	Mimbres B/W Style III	Pottery	SI/NIST A	VZ Powers Ranch	anch AZ CC:3:46 (/	(/ 11.98	40.68	0.2274	26.09	5.20		1.79	78.07	7.74	8.31
MPP006	Group-B	Unas.	Mimbres B/W Style III	Pottery	SI/NIST A	AZ Powers Ranch	anch AZ CC:3:46 ((4 3.30	46.64	0.5894	35.61	8.97	13.33	4.90 10	107.76 11.51		48.83
MPP007	Group-B1	Mimbres-05A	Mimbres B/W Style III	Pottery	SI/NIST A	AZ Powers Ranch	anch AZ CC:3:46 (<i>i</i>	(/ 3.28	58.40	0.4581	25.68	98.6	0.00	3.75 9	١.	11.80 6	62.76
MPP008	Group-B1	Mimbres-05A	Mimbres B/W Style III	Pottery	SI/NIST A	AZ Powers Ranch	anch AZ CC:3:46 ((4 3.20	51.45	0.4957	32.47	9.27	2.55	3.83	99.19 17.	74 6	62.19
MPP010	Group-B1	Mimbres-05A	Mimbres B/W Style III	Pottery	SI/NIST A	AZ Powers Ranch	anch AZ CC:3:46 ((/ 2.54	45.65	0.4648	25.85	9.10	0.00	4.21 9	99.42 24.	24.95 5	51.96
MPP014	Group-A	Unas.	Mimbres B/W Style III	Pottery	SI/NIST A	AZ Powers Ranch	anch AZ CC:3:46 ((4 5.60	31.80	0.7131	23.74	6.75	13.70	4.81 5	57.61 10.	10.52 4	43.52
MPP015	Group-C1	Mimbres-21	Mimbres B/W Style III	Pottery		AZ Powers Ranch		,			17.64	6.82	0.00	2.63 8			72.90
MPP019	Group-C1	Mimbres-21	Mimbres B/W Style III	Pottery	SI/NIST A	AZ Powers Ranch	anch AZ CC:3:46 ((/ 2.98	39.94	0.3511	22.36	00.9	0.00	2.62	81.00 12.	12.00 3	36.45
MPP021	Group-B	Unas.	Mimbres B/W Style III	Pottery	SI/NIST A	AZ Powers Ranch	anch AZ CC:3:46 ((4 5.90	47.80	0.6471	31.59	86.6	2.96	5.12	91.93 6	6.65	34.57
MPP023	Group-B	Unas.	Mimbres B/W Style III	Pottery	SI/NIST A	AZ Powers Ranch	anch AZ CC:3:46 ((4 3.52	48.91	0.5827	31.81	08.6	1.86	4.87 10	106.77 9	9.95	45.78
MPT001	Group-B2	Mimbres-02A	Mimbres B/W Style III	Pottery	SI/NIST N	NM Old Town	LA 001113	2.53	36.34	0.4414	23.96	5.69	7.72	3.49 6	6 89.59	9.33	32.71
MPT003	Group-A	Mimbres-01	Mimbres B/W Style III	Pottery		NM Old Town	LA 001113	1.42	54.25	0.3177	12.84	2.68	13.45	2.50 7	75.24 15.	15.60	3.94
MPT004	Group-B2	Mimbres-02B	Mimbres B/W Style III	Pottery	SI/NIST N	NM Old Town	LA 001113	3.22		0.4280	31.21	5.83	7.69	3.20 7	71.67 14.	14.04	35.39
MPT005	Group-A	Mimbres-01*	Mimbres B/W Style III	Pottery	SI/NIST N	NM Old Town	LA 001113	2.86	57.90	0.3954	18.48	2.67	23.40	2.55 9.	92.13 6	6.46	2.58
MPT006	Group-B2	Mimbres-11	Mimbres B/W Style III	Pottery		NM Old Town		2.48			22.94	4.48		2.83 6	_		42.83
MPT007	Group-A	Mimbres-03	Mimbres B/W Style III	Pottery	N TSIN/IS	NM Old Town	LA 001113	3.72	36.85	0.8945	27.91	7.64	4.55	6.51 6	66.43	7.59 1	10.57
MPT008	Group-C1	Mimbres-21	Mimbres B/W Style III	Pottery		NM Old Town		2.89	39.07	0.2583	17.07	5.75	0.00	2.16 8		14.92 5	53.54
MPT009	Group-B	Unas.	Mimbres B/W Style III	Pottery	_	NM Old Town	LA 001113	2.54		0.2909	21.95	5.04	1.64	2.21 6	64.04 12.	12.08 3	31.67
MPT010	Group-B1	Mimbres-04B	Mimbres B/W Style III	Pottery				3.05			41.87	9.46		l			27.22
MPT011	Group-C1	Unas.	Mimbres B/W Style III	Pottery	_			0.00			17.44	5.52					26.98
MPT012	Group-B	Unas.	Mimbres B/W Style III	Pottery				3.52			18.56	4.40				21.93 4	45.99
MPT013	Group-B	Unas.	Mimbres B/W Style III	Pottery				1.59			18.77	6.52					20.54
MP1015	Group-B2	Mimbres-11	Mimbres B/W Style III	Pottery				3.75			9.90	4.09					43.32
MPT016	Group-C1	Unas.	Mimbres B/W Style III	Pottery				1.93			15.65	6.18					40.52
MPT017	Group-B	Unas.	Mimbres B/W Style III	Pottery				0.00		_	34.08	7.18					22.22
MPT018	Group-B	Unas.	Mimbres B/W Style III	Pottery				1.89			15.36	5.89					22.53
MPT019	Group-B2	Mimbres-08	Mimbres B/W Style III	Pottery	_			2.41		0.3227	0.00	2.90	5.50				21.02
MPT020	Group-B	Unas.	Mimbres B/W Style III	Pottery		NM Old Town		2.64			16.13	6.28					23.05
MPT021	Group-B2	Mimbres-11	Mimbres B/W Style III	Pottery	SI/NIST N	NM Old Town	LA 001113	2.54	34.31	0.3168	9.17	4.35	3.70	2.93	70.87 34.	34.92 4	41.66
MPT022	Group-B2	Mimbres-11	Mimbres B/W Style III	Pottery	N TSIN/IS	NM Old Town		2.70	34.71	0.3770	15.54	4.46	3.36	2.92	77.89 35.	35.89 4	48.61
MPT023	Group-B2	Mimbres-11	Mimbres B/W Style III	Pottery		NM Old Town		2.75			17.16	4.96	3.52	3.11 7			45.99
MPT024	Group-B	Unas.	Mimbres B/W Style III	Pottery	N TSIN/IS	NM Old Town	LA 001113	2.56	80.99	0.6195	39.86	11.09	0.00	5.23 11	118.98 18.	18.84 2	27.33
MPT025	Group-B2	Mimbres-08		Pottery		JM Old Town		1.74			14.71	3.66	6.56	2.71 7	1		21.91
MRM001	Group-B1	Mimbres-04A		Pottery				1.66			41.66	8.83					20.73
MRM002	Group-C1	Mimbres-23	Mimbres B/W Style III	Pottery	MURR	TX Hueco Tanks	nks 41EP00002	3.50	36.86	0.3820	24.55	6.18	3.80	2.60 7	71.82 11.	11.68 4	43.34

>	29.84	63.22	53.18	68.72	63.28	81.44	75.38	66.18	80.42	31.55	83.28	74.13	69.63	80.88	59.12	63.00	51.21	59.13	81.33	53.63	18.68	51.98	17.71	55.48	24.04	59.62	69.57	57.30	71.92	44.96	64.97	54.06	63.72	66.93	32.37	35.29	45.33	60.09	67.04	61.89	60.05	44.17	55.70	81.10
Ξ	1754.7	2876.9	3088.0	3203.3	3330.7	5345.0	3861.5	4124.5	3943.7	2664.6	3795.9	4544.8	4496.4	4744.4	2281.8	3011.6	3150.0	4165.9	4059.2	2984.9	1692.9	2918.2	1186.1	3442.6	1146.4	2338.6	3293.2	3321.7	3004.4	2778.7	2829.3	3217.9	2055.8	2849.5	2777.6	2645.7	2555.7	3473.9	3105.0	3996.3	1961.8	2729.3	2246.9	3689.2
NA	20082.8	13142.2	16895.5	13616.9	14091.8	14054.0	12365.3	20063.7	13101.8	11189.5	13205.5	15806.0	14706.4	14010.0	8647.6	17831.1	12819.0	14395.8	15474.7	12713.3	13910.7	10690.4	20107.0	11687.1	7125.1	17446.7	15647.4	10776.2	11861.8	16596.4	10721.0	11121.2	16466.6	16847.1	15260.5	10496.5	10572.2	11500.6	10667.9	12040.0	10743.3	9291.6	14418.2	11973.9
MN		314.9	194.6	306.3	231.4	664.6					370.9	392.6	775.4	0.666	216.4	946.2	1001.6	205.0		397.1	213.2	454.8	144.0	822.8	584.8	1208.3	659.1	291.6	1807.8	222.8	1036.4	1124.2			367.5	178.6	198.9	778.4	1357.4		638.7		340.9	647.5
¥	27418.9	26019.5	30941.4	24799.9	25055.8	27299.8	30534.2	28743.3	26631.4	37728.8	23535.8	27952.7	21666.4	25721.3	21524.0	31022.2	26824.2	34437.6	27284.6	28283.3	30231.9	30638.0	32199.0	28870.2	39395.5	28494.1	24878.1	25498.0	28060.7	29921.5	31900.2	30286.0	27428.0	27461.9	29754.6	31772.0	29373.1	31332.9	27969.0	29825.2	23944.0	29866.9	29439.5	28881.9
Dγ	2.504	4.491	4.402			_		- 1			8.369	7.058	6.250	7.255		4.845		8.837	8.695	4.964	2.167	4.891	2.498	3.715	9.476										4.392	2.732	4.953	3.350	3.348	4.311				3.744
CA	6975.4	12723.2	13226.2	11020.4	11717.5	10739.3	7051.8	9239.4	13078.4	29509.7	15572.9	14196.3	22576.7	12847.6	7047.6	10368.7	33948.4	7186.7	12380.1	9720.2	7494.1	8554.4	6347.8	9442.7	7885.9	28842.8	13992.4	12509.8	11070.9	12337.9	8835.7	7948.6	22112.3	11452.8	12060.5	5252.0	7895.3	17551.0	9959.2	9915.2	11100.6	8621.8	12231.0	45338.0
BA	275.7	558.7	936.3	609.3	504.8	558.6	622.6	836.7	603.8	848.0	557.9	636.5	686.4	6.269	245.8	859.9	747.1	601.7	604.1	525.7	299.7	627.9	245.9	268.0	85.2	874.8	651.3	622.8	595.3	782.2	477.7	468.9	767.5	866.5	722.7	485.2	525.6	425.0	505.3	478.9	661.4	381.0		662.3
AL	99453.1	93514.1	87722.9	87745.2	89774.8	82771.2	93209.5	94527.4	91269.9	98226.9	87538.5	96057.2	91264.2	85211.5	106460.7	92711.0	92877.8	9.80906	84059.2	88646.2	97502.9	86804.5	15560.3	79018.0	74856.6	94727.9	84015.0	95347.4	81164.3	86365.1	79313.1	85470.1	87070.3	82090.9	80540.9	75554.9	89078.9	74896.8	80041.2	81813.3	97370.3	82408.1	72955.3	78953.9
ZR	164.1	179.1	247.7	115.9 8		~				_	335.7	287.7		252.9	1			306.2	309.7	217.8	187.9	264.0	198.0 1	213.8				_							167.9	227.0	182.8	162.2	182.0 8					138.8
NZ	43.1	61.4	53.6	53.5	54.9	76.8	73.0	82.6	76.7	87.0	76.5	73.6	75.6	86.4	87.6	87.6	81.2	59.1	77.0	53.5	40.3	58.9	48.0	57.7	56.3	96.1	91.5	58.9	81.3	54.6	93.4	55.3	74.2	6.99	49.2	34.4	57.8	49.0	60.5	59.9	58.0	35.5	63.8	73.4
3 TH	8 45.92	4 20.28	6 20.46	9 18.41			6 19.36		3 15.78		8 15.96	3 16.98	9 14.62	0 15.10				6 21.43	6 16.14	8 21.73	8 44.87	9 20.49	0 58.72		ניי			7							0 20.46		5 25.58	4 17.74			1 25.12			6 12.16
TA	2.3390 0.58	1.2910 1.04	1.3300 1.06	1.2390 1.19			1.4590 2.06		1.2790 1.43	0.5510 0.61	1.3090 1.48	1.4790 1.33	1.5600 1.19	2.1880 1.30	2.9510 1.13	0.9350 0.95	0.8450 0.69	1.6290 1.46	1.3490 1.46	1.5890 0.88	2.1380 0.38	1.4000 0.79	2.6000 0.40	1.3800 0.61					0.9570 0.72						2.0000 0.80	3.2140 0.37	1.9190 0.85	2.7930 0.64	2.6920 0.58	3.0480 0.69	2.2180 1.7	2.8970 0.56		1.0631 0.56
SR	130.0 2.3	408.3 1.2	302.7 1.3	269.8 1.2			166.0 1.4		377.6 1.2	309.7 0.5	332.7 1.3	325.1 1.4	436.5 1.5	384.6 2.7				194.1 1.6	306.9 1.3	202.8 1.5	110.9 2.7	252.0 1.4	135.0 2.0	271.0 1.3	0.0				_			_			375.8 2.0	132.1 3.2	167.1 1.9		217.8 2.0	287.7 3.0				569.3
SC	5.07	11.91	7.19					_		4.59	12.71	13.90	13.49 4	11.80		9.23		10.09	11.70	10.21	4.07	8.65	4.24	8.47	5.36				7.57				7.00 4		6.22	5.09	7.43	7.57	8.26	8.93	8.83			10.08
SB	0.4879	0.5111	0.5615	0.5872			_			3.6768		0.5706	0.5657	0.5566		1.8012				0.5987	0.7650	1.2736	0.5516	0.6021	0.4681	1.4803	0.5772	0.4606	1.5225	0.7666	0.4085	0.7369	2.9276	0.0000	0.0000	0.4846	0.4077	0.5442	0.6467	0.5657	0.3746	0.5979		0.7743
RB	251.70	147.20	151.70	138.40	143.90	111.70	205.50	145.60	136.80	169.40	147.20	111.70	135.80	92.20	229.60	119.70	124.20	170.20	140.20	177.40	273.50	199.60	168.50	210.30	245.70			147.20	166.70	187.90	161.40	233.30	158.90	140.90	157.00	260.60	219.30	247.70	250.00	219.70	0.0 178.20	237.10	163.00	166.90
Z	0.0	0.0	0.0						0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0		0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	20.5	0.0
生	6.28	7.36	6.62			_	_			5.83	8.86	8.35		8.58				9.74	8.41	7.41	6.19	6.74	66.9	6.74	8.43										5.84	8.54	6.20	92.9	69.9	7.12	5.54			5.14
H	15995.6	30130.1	21777.1	26607.3	27478.9	29174.3	36141.0	32434.0	31332.8	18706.8	26302.7	30269.1	42461.9	31768.7	32136.6	32508.7		26791.7	23496.3	23878.1	11587.8	22300.0	11200.0	23280.9	12600.0	32600.0	28119.0			26730.1	19010.8	23823.2	24603.7	28119.0	19408.9	16982.4	23120.6	22284.4		24717.2	27478.9			31894.0
EU	0.6457	1.1078	1.2027							1.2143	1.6047	1.8758	1.7713	1.5825	0.7047			1.3937	1.4865	1.0001	0.4368	1.1500	0.5222		0.4653				1.2565						1.2333	1/65.0	1.1383	0.9843						1.2272
CS	20.77	15.72	4.76	14.81	15.94	6.58	8.88	14.11	6.94	32.47	7.88	6.49	6.19	6.45	13.82	15.83	13.91	8.76	7.70	17.93	16.73	39.92	13.61	7.20	4.66	21.27	11.60	5.94	16.73	7.84	4.25	6.97	16.24	3.58	4.35	6.63	6.10	6.77	7.30	7.88	5.98	6.75	5.42	10.46
ANID	MPN022	MPN023	MPN024	MPN025	MPN026	MPP001	MPP002	MPP003	MPP004	MPP005	MPP006	MPP007	MPP008	MPP010	MPP014	MPP015	MPP019	MPP021	MPP023	MPT001	MPT003	MPT004	MPT005	MPT006	MPT007	MPT008	MPT009	MPT010	MPT011	MPT012	MPT013	MPT015	MPT016	MPT017	MPT018	MPT019	MPT020	MPT021	MPT022	MPT023	MPT024	MPT025	MRM001	MRM002

ANID	macro_grp	Chem2012	CERAMIC TYPE	MATERIAL	SOURCE	STATE SITE_	re_name	SITE_NO	AS	ΓA	Π	ND	SM	n	YB C	CE CO	CR
MRM003	Group-B2	Mimbres-11	Mimbres B/W Style III	Pottery	Murr		Hueco Tanks	41EP00002	2.98	35.84 0.	0.4316 2		4.72 4	4.89 2.	2.87 69.02	13.33	38.00
MRM004	Group-A	Mimbres-01	Mimbres B/W Style III	Pottery	Murr .		Hueco Tanks	41EP00002	2.04	69.46 0.	0.5856 5	54.47 4	4.12 11	11.47 2.	2.99 107.22	1.56	3.66
MRM005	Group-B	Unas.	Mimbres B/W Style III	Pottery	MURR	TX Hu	Hueco Tanks	41EP00002	3.11	41.80 0.	0.3803 4	46.54 5	5.97	2.82	2.65 72.08	11.42	32.91
MRM006	Group-B2	Mimbres-11	Mimbres B/W Style II	Pottery	MURR		Hueco Tanks	41EP00002	2.62	38.11 0.	0.5084 2.		5.64 5	5.87 3.	3.30 68.13	13 7.40	37.74
MRM007	Group-B1	Mimbres-04C	Mimbres B/W Style I	Pottery	MURR	TX Hue	Hueco Tanks	41EP00002	1.77	41.87 0.	0.4309 3		6.46 3	3.83 2.	2.95 81.65	99.7 36	32.00
MRM008	Group-A	Mimbres-01	Mimbres B/W Style III	Pottery	Murr	TX Hue	Hueco Tanks	41EP00002	3.64	46.74 0.	0.5074 1	14.92 3	3.77 14	14.50 2.	2.30 80.15	15 2.30	5.81
MRM009	Group-C1	Mimbres-23	Mimbres B/W Style III	Pottery	Murr .	TX Hue	Hueco Tanks	41EP00002	5.26	36.49 0.	0.3426 2	27.08 6	6.07	3.38 2.	2.48 71.54	54 11.29	41.09
MRM010	Group-A	Mimbres-01	Mimbres B/W Style III	Pottery	Murr		Hueco Tanks	41EP00002	1.91	71.29 0.	0.6085 4.		4.33 11	11.88 3.	3.34 111.69	19.1	3.78
MRM011	Group-B	Unas.	Mimbres B/W Style III	Pottery	Murr .	TX Hu	Hueco Tanks	41EP00002	3.50	42.69 0.	0.3755 3	39.31 6	6.04 2	2.89 2.	2.64 74.84	34 11.36	31.82
MRM012	Group-C1	Unas.	Mimbres B/W Style III	Pottery	Murr .		Hueco Tanks	41EP00002	3.68	29.55 0.	0.3044 3	35.16 5	5.06 2	2.68 1.	1.99 57.44	14 8.91	33.40
MRM013	Group-C1	Mimbres-23	Mimbres B/W Style II/III	Pottery	Murr .	TX Hue	Hueco Tanks	41EP00002	4.51	34.97 0.	0.3417 2.	24.74 5	5.76 3	3.30 2.	2.46 67.73	11.17	39.88
MRM014	Group-B2	Mimbres-02C	Mimbres B/W Style III	Pottery	MURR		Hueco Tanks	41EP00002	3.60	30.66			3.50 3	3.56 2.	2.97 63.36	36 3.92	14.56
MRM015	Group-C1	Mimbres-23	Mimbres B/W Style III	Pottery	Murr .	TX Hue	Hueco Tanks	41EP00002	4.47	35.32 0.		24.45 5	5.78 3	3.53 2.	2.38 68.32	32 11.35	39.57
MRM016	Group-C1	Mimbres-23	Mimbres B/W Style III	Pottery	MURR		Hueco Tanks	41EP00002	4.34	33.70 0.		23.25 5	5.37 3	3.40 2.	2.20 64.52	52 10.18	37.52
MRM017	Group-C1	Mimbres-23	Mimbres B/W Style III	Pottery	Murr .	TX Oja	Ojasen	41EP00289	4.44	32.94 0.	0.3941 2.	22.89 5	5.81 4	4.34 2.	2.77 68.99	10.41	51.79
MRM018	Group-B	Unas.	Mimbres B/W Style Indeter.		MURR		Ojasen	41EP00289	2.22		0.4900			5.34 3.	3.27 89.61		78.47
MRM019	Group-B	Unas.	Mimbres B/W Style III	Pottery	MURR	TX Oja	Ojasen	41EP00289	7.54	26.58 0.	0.3517	16.02 3	3.84 6	6.49 2.	2.13 57.14	11.75	34.35
MRM020	Group-C1	Unas.	Mimbres B/W Style III	Pottery	MURR		Gobernadora	41EP00321	1.30	28.59 0.	0.2726 2.	24.33 4	4.80 2	2.89 1.	1.88 56.45	15 7.67	46.76
MRM021	Group-C1	Unas.	Mimbres B/W Style III	Pottery	MURR	TX Gol	Gobernadora	41EP00321	1.94	28.12 0.	0.2706 3	35.93 4	4.83 2	2.73 1.	1.94 54.18	86'6 81	47.92
MRM022	Group-B2	Mimbres-02A	Mimbres B/W Style III	Pottery	Murr		Gobernadora	41EP00321	2.45	33.53 0.	0.4460 4	40.28 5	5.06 5	5.19 2.	2.92 60.64	3.84	
MRM023	Group-B2	Mimbres-02B	Mimbres B/W Style III	Pottery	Murr .		Gobernadora	41EP00321	4.24	40.33 0.	0.5105 2	24.73 6		5.90 3.	3.33 69.81	31 6.70	37.63
MRM024	Group-B2	Mimbres-02A	Mimbres B/W Style III	Pottery	MURR		Gobernadora	41EP00321	2.48	35.77 0.	0.4764 2	20.82 5	5.35 6	6.33 3.	3.12 65.55	55 5.48	
MRM025	Group-B	Unas.	Mimbres B/W Style II/III	Pottery	MURR	TX Nor	North Hills I	41EP00355	2.16	45.04 0.	0.4556 5	51.28 4	4.44	4.60 3.	3.00 75.87	77.4	14.52
MRM026	Group-B2	Mimbres-02A	Mimbres B/W Style III	Pottery	MURR		North Hills I	41EP00355	3.56	51.76 0.			7.23 4	4.31 3.	3.37 92.12	-	36.19
MRM027	Group-B1	Mimbres-04A		Pottery	Murr	TX Nor	North Hills I	41EP00355	2.19	45.48 0.	0.5344 3	35.10 8		5.69 3.	3.82 98.03	13 7.37	23.85
MRM028	Group-B1	Mimbres-04A	Mimbres B/W Style III	Pottery	Murr		North Hills I	41EP00355	2.86			32.54 7	7.99 4	4.60 3.	3.33 84.76	7.16	22.30
MRM029	Group-B	Unas.	Mimbres B/W Style III	Pottery	MURR	TX Nor	North Hills I	41EP00355	3.77	47.89 0.	0.4597 3	39.53 6	6.15 4	4.25 3.	3.66 74.14	14 6.87	30.26
MRM030	Group-A	Mimbres-13		Pottery	MURR		North Hills I	41EP00355	`		L		21.29 8		2		
MRM031	Group-B2	Mimbres-02A		Pottery	MURR		North Hills I	41EP00355	4.49							5.68	
MRM032	Group-B2	Mimbres-02A	Mimbres B/W Style III	Pottery	MURR		North Hills I	41EP00355	2.55		~						
MRM033	Group-B2	Mimbres-02A	Mimbres B/W Style III	Pottery	MURR		North Hills I	41EP00355	2.97	_							
MRM034	Group-C2a	Mimbres-49A	Mimbres B/W Style III	Pottery	MURK		North Hills I	41EP00355	2.83								
MRM035	Group-B2	Mimbres-02A	Mimbres B/W Style III	Pottery	MURR		North Hills I	41EP00355	0.00					_			
MRM036	Group-B2	Mimbres-02A	Mimbres B/W Style III	Pottery			North Hills I	41EP00355	3.08								(•)
MRM037	Group-A	Mimbres-01	Mimbres B/W Style III	Pottery			North Hills I	41EP00355	2.99	56.58 0.	0.5171 3						
MRM038	Group-B	Unas.	Mimbres B/W Style III	Pottery	MURR		North Hills I	41EP00355	1.89	40.06 0.	0.4882 3	38.38 4	4.89 3		3.32 66.97	3.09	16.81
MRM039	Group-B2	Mimbres-02A	Mimbres B/W Style II/III	Pottery	Murr		North Hills I	41EP00355	2.17	45.08 0.			7.28 5				
MRM040	Group-C1	Mimbres-23	Mimbres B/W Style III	Pottery	Murr .		North Hills I	41EP00355	68.9	36.16 0.	0.3541 3	39.33 6	6.11 3	3.36 2.	2.47 72.00	00 11.88	42.78
MRM041	Group-B	Unas.	Mimbres B/W Style III	Pottery	Murr .	TX Nor	North Hills I	41EP00355	3.33	25.51 0.	0.3228	13.60 2	2.89 4	4.78 1.	1.89 38.93	3 2.24	18.91
MRM042	Group-A	Mimbres-01	Mimbres B/W Style III	Pottery	Murr .		North Hills I	41EP00355	1.92	48.52 0.		41.74 4	4.13 7	7.62 2.	73 80.67	57 4.72	
MRM043	Group-B2	Mimbres-02A	Mimbres B/W Style III	Pottery	MURR	TX Nor	North Hills I	41EP00355	0.00	47.25 0.	0.4914 3		7.61 5	5.91 3.	3.47 109.30	30 5.78	37.41
MRM044	Group-B1	Mimbres-04A	Mimbres B/W Style III	Pottery			North Hills I	41EP00355	5.58								
MRM045	Group-C1	Mimbres-23		Pottery		TX	North Hills I	41EP00355	5.95							1	
MRM046	Group-B2	Mimbres-02A	Mimbres B/W Style III	Pottery	MURR	TX	North Hills I	41EP00355	2.83	35.98 0.	0.4442 2.	23.55 4	4.97 5	5.36 2.	2.96 75.39	39 4.71	36.42

>	0	Q	0	0	0	0	0	Q.	0	0	0	0	0	0	0	0	0	0	0	0	0	0	0	Q	0	0	0	0	0	0.	0	0	0	0	0	0	<u>o</u>	0	0,	0,	0	0.	0	0
	53.10	14.60	79.80		61.00	26.10	70.70		72.30	29.00	86.80	37.90	84.90	55.10	184.50		74.20	53.20	56.10	47.30	58.70	63.70	34.20	52.60			50.40		62.90		63.90	96.40						06'66	53.70	36.70	63.80			52.90
⊏	2641.0	1521.6	2975.4	3830.6	3131.5	1410.7	2601.6	1208.0	2949.1	2646.7	3897.4	1128.0	3054.3	2584.5	3486.6	2698.6	3373.3	2649.1	2568.4	3377.2	2795.8	3400.1	1868.9	2903.8	2754.0	2505.4	3315.0	3771.2	2936.5	2848.6	3565.7	4582.1	3414.7	3087.6	1525.3	1994.6	3146.8	3586.4	2856.2	2198.7	3284.9	2659.4	2852.3	3377.2
NA	11052.1	17141.5	13849.4	13135.3	18767.0	11946.2	11867.4	17216.3	13597.2	9530.4	11959.4	10578.9	11712.5	11737.5	15647.9	13060.3	11253.4	0.9009	9.09/5	13079.1	9551.5	11468.0	8591.5	11712.3	15580.0	15005.5	10163.1	20985.0	12892.7	11292.0	13505.6	18022.1	13539.6	13261.3	13783.1	9023.5	13741.6	10534.6	11515.7	10228.8	13297.7	16342.1	12541.5	11650.2
MN	996.4	185.9	865.7	396.8	451.1	156.0	673.4	233.8	0.789	475.9	649.1	613.8	9.899	9.773	449.7	252.8	346.6	267.7	285.9	177.9	430.4	223.8	517.5	395.0	714.3	492.8	653.4		263.1								387.2	2.889	163.4		250.5			204.1
¥	29739.1	29955.8	23860.2	31272.4	25214.6	29318.7	27350.1	31681.7	25884.8	22511.1	27974.6	22012.6	28591.3	28127.8	30232.4	28647.0	25542.6	20545.9	18438.5	29309.6	29036.0	27457.5	40751.7	27854.4	28232.4	26859.5	31541.1	34108.2	26355.7	30495.8	28271.0	23207.6	25505.3	26040.0	30224.6	18170.0	28141.1	27703.4	25217.3	37298.4	26844.0	28075.6	28078.0	30046.8
DΥ	3.321 2	2.246 2	3.109 2	3.737 3	4.062 2	3.001 2	4.239 2	2.850 3	3.391 2	2.951 2	3.324 2	3.102 2	3.918 2	3.776 2	3.846 3	4.061 2	2.601 2	3.005 2	3.324 1	4.034 2	4.473 2		2.324 4	5.126 2	5.905 2		4.760 3	5.565 3	4.985 2		_						5.056 2	4.114 2	2.085 2	2.847 3	5.363 2			4.229 3
CA	9242.5	7409.0	16364.9	12802.0	16100.0	6598.0	62157.7	6772.4	13394.0	43776.0	58063.6	15400.0	63496.0	51816.0	13106.0	7901.0	15358.0	61872.2	82295.3	10796.1	8351.0	8.8096	19294.6	12401.8	10315.0	13504.2	7754.0	14962.2	12018.0	5705.0	11587.1	13301.3	12681.9	14081.2	6899.2	16696.4	12491.2	53642.3	8198.2	5801.0	11512.5	12342.4	63976.9	8526.1
BA	637.7	352.8	499.7	535.9	742.6	477.8	784.5	275.0	651.1	8.599	756.7	409.5	821.1	7.097	622.8	551.9	517.1	2.095	529.3	8.955	590.3	564.0	393.2	601.2	687.4	0.859	556.1	415.4	572.1	365.2	568.3	855.2	584.4	761.5	402.5	279.5	708.0	6.865	504.4	458.1	623.2	983.3	629.8	474.6
AL	78471.9	108260.4	90072.0	84842.4	98719.3	95343.6	71796.8	06794.8	89158.2	66181.3	77879.2	69344.3	78768.2	70264.9	69884.6	89984.9	81418.5	57426.8	58508.3	88419.0	85024.1	91884.0	76177.9	90060.1	91690.1	91064.4	74503.8	82707.4	84370.4	91396.6	91678.0	88836.5	92380.3	88640.5	95329.3	69369.8	88846.4	83490.6	86709.3	90233.3	88909.2	92359.2	79111.4	92213.4
ZR	157.1	154.7 1	137.2	172.2	189.4	166.1	128.9	180.0	129.2	148.5	123.3	91.4	118.9	114.5	167.2	155.1	170.5	94.3	113.6	224.1	165.1	185.8	124.0	150.8	212.4	189.0	162.0	319.2	168.7	209.8	193.6	179.4	163.0	172.7	182.1	105.0	154.8	134.5	139.2	149.0	153.5	187.4	112.0	167.8
NZ	53.5	43.2	75.6	58.2	6.89	40.9	103.0	36.5	71.0	9.99	68.1	47.3	0.76	8.99	22.6	72.7	93.5	0.06	71.1	49.2	61.3		53.9	63.9	54.6	84.3	44.2				60.7						55.8	73.1	62.0	61.2	6.09		74.0	52.4
H	18.36	48.63	17.12	19.98	17.22	47.46	12.08	49.59	16.31	9.18	11.79	29.65	11.63	11.67	11.17	26.92	18.28	8.09	7.73	21.02			29.10	21.20	17.36		20.36	52.35	19.84	22.06	19.84			19.42				12.57	24.10	36.24	19.02	18.70	11.83	20.41
۱ TB	3 1.13	0.78	0.99	1.22	3 1.44	2 0.28	0.84	0.32	3 0.53	3 0.46		3 0.74	1.16	1.28	97.0	3 0.57	5 0.37	1 0.98	3 0.41	1.19	1.35		77.0	5 0.84	3 1.16	3 1.04	0.60		1.57	-			1.65			0.48	1.65	1.09	9 0.25	1 0.48	1.84			0.20
TA	1.5128	2.6145	1.0701		1.1953	2.4252	1.0196		1.0448			1.4713	0.9330	0.9152	1.0832	1.5473	1.4635	0.7314	0.7288	1.6114	1.5064	1.4423	1.7069	1.4396	1.3583	1.2978	1.5414		1.3512			1.0196				1.6377	1.3740	1.0142	1.5459		1.3121		1.0413	1.4339
SR	199.0	116.2	339.5	221.2	331.4	124.0	518.1	98.0	384.8	461.7	562.6	226.5	504.6	539.1	399.4	176.8	384.4	370.1	379.8	262.3	200.6	250.9	243.2	403.2	274.5	300.5	187.5	150.0	290.1	165.6	302.8	483.1	332.7	306.6	119.5	229.2	319.7	617.5	139.3	144.5	294.2	304.3	622.9	207.5
SC	7.33	3.78	10.13	7.69	8.06	3.93	10.80	3.83	9.70	8.01	9.71	6.02	86.6	8.93	10.23	7.66	8.02	8.64	8.88	9.54	9.52	10.31	4.59	10.95	8.16	7.79	6.94	11.14	11.15	6.67	11.00	10.45	12.34	10.84	4.22	6.70	10.97	11.05	2.96	5.88	11.36	7.26	10.14	9.82
SB	0.6501	0.4868	0.5804	0.6335	0.3789	0.7386	0.7635	0.4994	0.5889	0.6179	0.8011	0.3931	0.7509	0.7491	0.7495	0.6059	0.5214	0.4277	0.4356	0.5138	1.0063	0.5064	0.8287	0.4617	0.3834	0.3762	0.9880	0.8836	0.4250	0.5646	0.4524	0.6617	0.3885	0.3750	0.7820	0.4403	0.4270	0.7779	0.4579	0.6265	0.3645	0.3120	0.7948	0.5142
RB	198.40	218.40	161.30	184.20	134.20	219.00	161.70	225.30	158.50	124.80	160.20	180.50	157.80	152.00	159.10	183.60	170.00	105.80	101.60	159.60	222.40	159.10	229.00	159.20	132.90	137.00	233.70	314.80	138.90	181.50	155.40	101.10	155.40	135.10	226.20	187.80	143.50	170.90	133.00	259.00	146.90	137.60	154.00	26.9 159.10
Z	0.0	0.0	26.9	0.0	28.0	0.0	34.5	0.0	0.0	33.4	0.0	0.0	35.2	33.6	29.7	0.0	0.0	30.3	33.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	27.4	0.0	26.0							0.0	33.4	42.6	0.0	0.0	35.7	0.0	26.3	26.9
H	6.70	08.9	9.00	7.75	7.11	6.62	4.81	7.34	5.82	5.26	4.68	5.10	5.40	4.74	7.79	6.19	7.60	3.84	4.38	9.44	6.67	7.92	2.66	7.04	7.17	7.25	7.00	13.15	7.00	8.34	8.82	7.51	6.75	7.24	7.02	5.93	6.84	5.00	6.47	6.25	19.9	7.17	4.77	7.87
FE	21453.5	12570.6	31801.2	20794.9	28293.5	11486.4	30796.1	12799.4	30913.7	23766.3	30507.6	14134.5	30359.4	27582.7	29065.9	24094.3	28709.0	22603.5	25723.5	20575.8	26526.3	24095.4	16883.8	26428.1	26497.9	27019.3	21050.7	41625.0	25292.5	22366.3	27469.9	34585.9	27165.7	25431.7	12459.2	14807.7	25555.3	33468.5	21320.6	17364.4	25857.1	25121.8	1.2488 30737.0	22383.3
EU	6.88 0.8955	0.5236	1.3074	1.0439	1.3461	0.4577	1.2184	0.5339	1.2862	1.0209	1.1481	0.5109	1.1784	1.0795	1.1174	1.0612	0.7708	0.8726	0.8710	0.9322	1.1332		0.7384	1.2301	1.4848	1.4476	1.1517	2.1468	1.3897		1.2192				0.4540	0.7349	1.3446	1.2095	0.5516	0.6848	1.4291	1.3616	1.2488	0.8717
CS	98.9	27.42	17.89	7.44		13.55 (10.58	29.47	17.56	8.33	66.6	20.55 (10.48	8.96	. 10.77	9.34	14.72 (9.32	8.90	17.69 (43.33	22.43	10.95	23.27	4.46	4.40	27.80		17.35							20.92		11.53	8.91	14.34 (15.70			20.89
ANID	MRM003	MRM004	MRM005	MRM006	MRM007	MRM008	MRM009	MRM010	MRM011	MRM012	MRM013	MRM014	MRM015	MRM016	MRM017	MRM018	MRM019	MRM020	MRM021	MRM022	MRM023	MRM024	MRM025	MRM026	MRM027	MRM028	MRM029	MRM030	MRM031	MRM032	MRM033	MRM034	MRM035	MRM036	MRM037	MRM038	MRM039	MRM040	MRM041	MRM042	MRM043	MRM044	MRM045	MRM046

ANID	macro_grp	Chem2012	CERAMIC TYPE	MATERIAL	SOURCE	STATE	SITE_NAME	SITE_NO	AS	ΓĄ	Π	ND	SM	n	YB C	CE CO	CR
MRM047	Group-B2	Mimbres-02A	Mimbres B/W Style III	Pottery	Murr	TX	North Hills I	41EP00355	2.14	35.92 0.	0.4631 2	23.67	5.25	5.39 3.	3.11 78.65	5 5.01	39.46
MRM048	Group-C1	Mimbres-21	Mimbres B/W Style II/III	Pottery	Murr .	, XT	North Hills I	41EP00355	2.61	38.71 0.3	0.3148 3	37.01	5.77	1.52 2.	2.40 81.15	5 12.41	1 57.3
MRM049	Group-B2	Mimbres-02A	Mimbres B/W Style III	Pottery	Murr	ΣL	North Hills I	41EP00355	0.00	37.97 0.	0.4398 2	22.94	4.39	5.77 2.	2.93 60.67	3.96	5 36.22
MRM050	Group-B2	Mimbres-02A		Pottery	Murr	ĭ	North Hills I	41EP00355	0.00	50.90	0.5224 4		7.11	5.08 3.	3.71 83.86	1.13	34.98
MRM051	Group-A	Mimbres-01		Pottery	Murr	ĭ	North Hills I	41EP00355	2.36	79.53 0.	0.7971 2	27.48	5.57 18	18.68 3.	3.41 107.26	1.69	9 2.46
MRM052	Group-B2	Mimbres-02A	Mimbres B/W Style III	Pottery	Murr	TX	North Hills I	41EP00355	2.35	41.62 0.	0.5670 3	33.69	6.62	5.72 3.	3.34 78.27	7.28	37.45
MRM053	Group-B2	Mimbres-02A	Mimbres B/W Style Indeter. Pottery	Pottery	Murr	1X XI	North Hills I	41EP00355	1.48	46.39 0.	0.5428 3	33.78	7.05	4.95 3.	3.37 72.18	8 6.87	36.78
MRM054	Group-B2	Mimbres-02A	Mimbres B/W Style III	Pottery	Murr	Σ	North Hills I	41EP00355	2.52	49.15 0.	0.5993 3	-	7.23 4	4.83 3.	3.88 97.42	7.47	7 36.65
MRM055	Group-A	Mimbres-01	Mimbres B/W Style III	Pottery	Murr	Σ	North Hills I	41EP00355	1.91	56.57 0.	0.6204 2	22.64	4.40 17	11.77 2.	2.92 87.96	1.35	5 8.29
MRM056	Group-A	Mimbres-01	Mimbres B/W Style III	Pottery	Murr	Σ	North Hills I	41EP00355	2.13	54.72 0.	0.5895 1		3.99 12	12.05 2.	2.58 84.31	1.85	5 6.15
MRM057	Group-B1	Mimbres-04A	Mimbres B/W Style III	Pottery	Murr	X	North Hills I	41EP00355	3.81	65.80 0.	0.5334 4	46.69	8.46	3.95 3.	3.80 128.80	6.45	5 20.50
MRM058	Group-A	Mimbres-01	Mimbres B/W Style III	Pottery	Murr	X	North Hills I	41EP00355	2.46	57.31 0.	0.5736 2	21.85	4.20 17	11.56 2.	2.70 93.21	1 2.87	7.9
MRM059	Group-B	Unas.	Mimbres B/W Style III	Pottery	Murr	X	North Hills I	41EP00355	2.43	33.04 0.	0.4979 1	18.65	3.74	3.27 3.	3.23 57.58	3.79	12.14
MRM060	Group-B2	Mimbres-02A	Mimbres B/W Style III	Pottery	Murr	ĭ	North Hills I	41EP00355	2.79	48.59 0.	0.5267 3	36.97	7.10 4	4.42 3.	3.48 86.18	8 7.07	7 40.18
MRM061	Group-B1	Mimbres-04B	Mimbres B/W Style III	Pottery	Murr	ĭ	North Hills I	41EP00355	2.37	65.10 0.	0.5407	37.60	7.21	4.07 3.	3.65 117.96	6 5.92	24.7
MRM062	Group-B2	Mimbres-11		Pottery	Murr	X	North Hills I	41EP00355	2.21	34.70 0.	0.4931 2	24.31	4.80	5.07 2.	2.85 63.23	3 9.51	1 41.9
MRM063	Group-A	Mimbres-01	Mimbres B/W Style III	Pottery	Murr	X	North Hills I	41EP00355	3.03	49.91 0.	0.5346 2	21.24	4.14 17	11.88 2.	2.48 80.16	1.71	1 8.2
MRM064	Group-A	Mimbres-01	Mimbres B/W Style III	Pottery	Murr	X	North Hills I	41EP00355	1.78	58.80 0.	0.6343 2	23.83	4.59 17	11.92 3.	3.02 94.34	1.43	3 8.05
MRM065	Group-A	Mimbres-13	Mimbres B/W Style II	Pottery	Murr] XI	Diablo 1	41HZ0491	13.64	72.80	1.4149 5	57.23 13	12.82	9.18 9.	9.91 151.65	5 8.80	34.57
MRM066	Group-C2a	Mimbres-49B	Mimbres B/W Style I	Pottery	MURR	NM	Conejo	LA 091044	2.46	62.88 0.	0.5064 6	60.79	11.43	2.59 4.	4.01 85.39	12.18	3 57.66
MRM067	Group-C2b	Mimbres-41	Mimbres B/W Style II	Pottery		NM	Conejo	LA 091044	1.90	34.47 0.	0.3352 2	26.30	5.22	2.19 2.	2.30 66.18	8 9.67	7 26.2
MRM068	Group-B1	Mimbres-04C		Pottery	MURR	NM	Conejo	LA 091044	1.92	40.31 0.		29.19	6.01	3.41 3.	3.06 79.85	7.47	7 30.7
MRM069	Group-C2b	Mimbres-41	Mimbres B/W Style II	Pottery	MURR	NM	Conejo	LA 091044	1.61	32.96 0.3	0.3376 2	26.48	5.23	1.96 2.	2.40 65.52	2 9.95	5 26.56
MRM070	Group-C2b	Mimbres-41	_	Pottery			Conejo	LA 091044	1.41	32.86 0.	0.3445 2	27.91	5.19	1.99 2.	2.41 64.73	3 9.62	26.15
MRM071	Group-C2b	Mimbres-41	Mimbres B/W Style II	Pottery	Murr		Conejo	LA 091044	1.77		0.3468 2	25.68	5.26	2.26 2.	2.27 71.96	11.47	
MRM072	Group-C2a	Mimbres-49A	Mimbres B/W Style II	Pottery			Conejo	LA 091044	3.72		0.4062 4	43.30	8.08		3.29 71.69	14.28	3 60.55
MRM073	Group-C2b	Mimbres-41	Mimbres B/W Style II	Pottery	Murr	NM (Conejo	LA 091044	1.35	32.81 0.3	0.3294 2	26.95	5.16	2.50 2.	2.34 63.20	9.43	3 24.67
MRM074	Group-B	Unas.		Pottery			Conejo	LA 091044	1.58		_					5 6.92	
MRM075	Group-B	Unas.	_	Pottery			Conejo	LA 091044	3.22				3.63	2.67 2.			
MRM076	Group-B2	Mimbres-02B	_	Pottery			Divad	LA 096687	3.27								co
MRM077	Group-A	Mimbres-01	Mimbres B/W Style III	Pottery			Divad	LA 096687	2.39				_				
MRM0/8	Group-B	Unas.		Pottery			Divad	LA 096687	1.60								
MRM079	Group-A	Mimbres-01		Pottery			Divad	LA 096687	2.85								
MRM080	Group-C1	Mimbres-23		Pottery			Divad	LA 096687	4.52								
MRM081	Group-B2	Mimbres-11		Pottery			Divad	LA 096687	2.09							_	
MRM082	Group-B1	Mimbres-04C		Pottery			Divad	LA 096687	2.87								30.78
MRM083	Group-A	Mimbres-01		Pottery			Divad	LA 096687	2.75					12.04 2.		1.64	
MRM084	Group-C1	Mimbres-23	Mimbres B/W Style III	Pottery	MURR		Divad	LA 096687	3.62		0.3368 2	28.33		3.00 2.	2.33 67.76	6 11.78	3 40.31
MRM085	Group-B	Unas.		Pottery			Divad	LA 096687	1.76	-	0.4581 3	30.81	5.58	5.61 2.		` '	2
MRM086	Group-A	Mimbres-01		Pottery			Divad	LA 096687	1.32				,	13.45 2.	2.59 93.30	1.29	9 4.89
MRM087	Group-B2	Mimbres-02A		Pottery	Murr		Divad	LA 096687	1.94		0.5754 4	48.83	7.87	4.82 4.	4.01 91.10	0 7.71	36.47
MRM088	Group-B	Unas.		Pottery			Divad	LA 096687	1.86					7.47 2.			
MRM089	Group-B2	Mimbres-02C		Pottery			Divad	LA 096687	3.00			15.05		3.65 2.			
MRM090	Group-B2	Mimbres-11	Mimbres B/W Style III	Pottery	MURR	NM W	Divad	LA 096687	5.37	32.30 0.	0.4441 2	21.42	4.35 4	4.46 2.	2.79 77.07	7 25.45	5 51.49

>	57.40	65.00	54.30	27.60	18.50	67.90	73.50	60.10	26.90	24.70	57.80	24.70	35.80	89.60	43.80	45.60	29.20	18.20	99.89	81.20	80.80	90.80	94.70	85.20	75.80	100.00	71.50	29.60	68.90	51.90	16.70	44.80	40.60	80.60	46.50	67.60	18.70	08.69	39.90	24.00	57.80	65.50	27.90	69.90
F	3718.1	3200.6	2955.4	3319.7	1312.2	3319.1	2720.4	3324.0	1522.3	1318.2	2598.9	1208.3	1116.7	3388.8	2006.0	3645.2	1798.7	1945.7	3197.4	4095.8	3855.4	3468.7	4363.5	3305.8			3628.9	2498.6	2571.9	2635.8	1050.8	2286.0	2682.5	3728.1	1992.4	4133.3	1285.7	2858.1	2119.3	1055.6	3125.0	2994.0	1135.6	2268.7
NA	11693.1	18631.1	10839.0	12293.9	20714.4	14013.6	13041.6	12713.0	11466.7	18244.9	13726.3	13145.7	11392.2	14017.8	15081.1	12403.3	9177.9	12251.2	13599.7	17025.8	17296.3	16592.5	17325.5	17019.0	17661.4	18406.1	16835.8	13040.2	11671.0	11264.6	13941.0	11446.9	6422.2	10766.6	11154.5	14868.6	16916.4	13158.4	12882.7	18071.2	12942.0	12214.2	10529.7	8337.7
MN	206.5	983.3	193.4	363.7	144.7	299.1	319.6	356.4	130.8	194.5	518.5	241.6	843.9	351.6	272.4	1087.9	127.4	140.2	330.0	757.5	603.2	377.1	647.8	538.8	8.589	1151.7	613.1	550.9	515.4	531.1	165.4	339.4	148.8	640.0	2330.7	524.6	136.9	640.3	189.1	149.4	533.1	500.4	597.6	1154.9
¥	29411.2	28681.9	32918.3	28577.4	30075.0	26031.6	26778.3	27126.5	32105.9	28287.8	27880.8	34419.9	27033.1	26541.2	27990.6	32646.8	32995.6	35646.6	37404.4	21898.6	22916.2	25405.5	25861.4	25493.3	24715.1	20379.0	25517.9	30316.0	22119.6	28714.4	34742.5	26854.8	37612.2	27754.6	29198.2	26162.3	25841.5	27513.6	30384.3	27219.8	27562.6	29330.5	19845.2	28914.0
DΥ	4.267	3.817 2		5.328 2		5.651 2	5.092	6.015 2	3.283 3	2.631	5.440 2	2.240 3	3.493 2	5.382 2	5.798 2	3.882	2.743 3	3.002	12.968 3	7.433 2	3.171 2	4.494	3.499 2	3.692											2.843 2			5.431 2	3.347 3		6.181 2			2.352 2
CA	9554.0	12162.3	6108.0	11678.6	9557.9	12157.2	12572.2	9758.7	6721.5	8832.6	13487.0	10283.6	22656.7	16626.3	14123.3	10720.0	6297.0	8.69/5	9684.7	16305.5	22272.1	14853.0	19788.0	21165.0	19309.0	17724.0	21322.3	11892.1	13809.7	11438.0	6506.5	7348.1	3580.0	61982.7	7056.0	13232.0	10219.0	52820.0	9922.0	7849.0	12113.0	10260.0	16789.3	8466.0
BA	476.5	943.5	385.2	528.3	112.8	555.1	578.1	575.4	239.1	228.9	6.688	738.0	663.0	616.4	710.6	8.685	296.6	266.8	653.4	892.9	974.7	893.8	861.8	1143.6	1088.7	775.0	971.4	899.2	1179.6	475.0	426.8	413.6	443.7	703.1	520.3	726.9	450.1	832.4	487.4	369.9	605.5	528.6	448.0	441.5
AL	92676.7	6.98886	91860.9	90821.7	111239.3	91975.5	85926.1	96736.5	106890.7	107464.0	88257.6	07234.9	70085.4	98356.7	84930.9	88999.5	96882.9	113823.0	85879.4	92959.8	88366.0	87047.2	89769.1			86280.5	90150.1	77293.4	86849.9	83147.1	04817.4	77630.8	95774.8	75640.4	82583.0	83083.8	92113.8	79484.1	87447.7	98344.0	84035.7	95226.7	8.70069	87990.6
ZR	199.2	163.8	173.0		`	218.3	1.69.1	180.8	174.8 1	173.6	198.5	141.6	6.86	161.2	152.3	142.6	193.4	169.2	345.7	243.0	187.8	230.6	180.8	158.1	164.2	185.6	167.7			158.4	165.7		178.6		120.9		166.5	138.5	174.8	176.9				164.6
NZ	9.99	75.4	63.0	54.8	31.1	60.1	58.8	67.1	44.9	41.5	9.99	52.5	57.4	57.1	49.2	65.8	38.3	43.3	81.9	75.0	58.5	59.8	70.6	55.4	55.3	74.0	50.6	48.6	60.3	55.0	42.0	55.8	41.0	79.9	55.0	64.9	33.6	75.2	47.7	29.4	58.7	65.0	44.8	65.3
TH	21.24	6.55					19.15	20.37	49.39	50.17	21.71	52.21	29.87	19.15			45.68	52.78	57.00	10.92	66'6	16.60	10.68	10.00	_		66.6										46.84	12.34	29.39	49.57	20.01	21.79	29.49	18.98
rA TB	98 0.56	64 0.80	99 0.42	96 1.46		40 0.76	77 0.92	75 1.01	68 0.42	88 0.40		70 0.44	51 0.52	98.0 96	43 0.90	79 0.59	06 0.40	83 0.50	09 2.14	24 1.41	99.0 98		14 0.64	32 0.64	75 0.66	10 0.99	61 0.66	92.0 89	95 0.42		_			70 0.70	78 0.57	45 0.84	64 0.31	99.0 96	48 0.63	87 0.36	22 1.10	05 0.83	42 0.47	65 0.52
7	8 1.6098	7 0.7064		2 1.4296			5 1.3077	4 1.5575	5 2.3868	9 2.3788	0 1.3154	8 2.4670	5 1.6451	5 1.3496	8 1.4643	1 1.5979	8 2.3706	6 2.4683	8 2.2709	8 0.9724	9 0.9936	3 1.2477	8 0.9814		4 0.9975													0.9696	3 1.6348	3 2.5587	0 1.5622	3 1.4305		7 1.6765
SR	224.8	434.7		3		320.9	374.5	348.4	3 52.5	127.9	1 246.0	113.8	3 482.5	316.5	9 243.8	5 265.1	72.8	9.89	8.98	3 486.8	664.9	320.3	3 618.8	644.7		_				(7					3 242.9			9 542.2	3 164.3	110.3	403.0			176.7
3 SC	10.22	9.02				5 11.22	11.33	5 10.93	3 4.68	9 4.40	5 8.21	4.56	7 5.38	12.01	6:29	8.25	4.24	7 5.05	10.58	5 12.43	3 7.75	8.29	7.88	1 7.81	7.77	11.17	7.67		_	8.32				_	5 7.33			61.6 t	8.83	3 3.72	7 10.41			8.99
SE	0.4819	1.5902	0.5313	0.3786	0.7030	0.4195	0.3689	0.4816	0.7138	0.8199	0.2995	0.7172	0.3377	0.3577	0.4960	0.6303	1.0331	0.7667	1.0569	0.3285	0.2583	0.3563	0.3331	0.2844	0.2686	0.4026	0.2622	0.2181	0.3655	0.7801	0.7644	0.4197	0.5822	0.7510	0.6006	0.4021	0.4322	0.6804	0.4758	0.5088	0.4117	0.5379	0.3386	0.9752
RB	169.70	131.40	190.40	151.20	207.30	143.60	143.30	154.70	225.80	231.80	125.50	216.90	117.00	133.10	175.90	188.70	204.70	240.30	355.50	29.5 102.00	92.80	116.20	96.50	91.70	91.30	91.40	93.60	115.20	90.00	181.20	231.70	196.90	239.70	157.50	199.50	140.60	178.50	162.00	194.00	195.20	152.40	187.10	0.0 172.80	189.60
Z	0.0	36.5				0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	7.5	0.0	0.0	29.5	0.0	0.0	0.0	0.0	0.0	0.0	25.0	0.0	0.0	0.0					0.0		0.0	34.4	0.0	0.0	15.6	36.4	0.0	0.0
Ή	8.94	6.48	9.05	7.66	7.21	8.32	6.57	8.18	19.9	6.85	7.24	5.99	5.29	98.9	80.9	7.24	7.13	6.28	14.05	6.85	6.85	96.8	6.41	6.73	6.48	7.04	6.32	92.9	7.62	6.24	6.61	7.00	97.9	5.02	6.52	9.59	6.04	4.98	6.29	6.62	7.65	5.94	5.22	6.82
FE	23101.2	34087.2	20421.6	23844.7	10531.1	26912.5	27363.3	25916.3	11558.7	12584.1	28338.9	11919.8	12135.6	29228.4	20846.5	23520.7	12686.2	12413.6	36001.3	37739.8	29956.7	29053.3	31070.3	29730.9	30249.7	36787.7	29867.8	22567.5	23507.6	22552.1	10530.2	19395.5	17235.3	32364.7	21910.8	32096.2	10560.6	30109.2	18574.9	11083.7	26175.0	28535.2	13968.3	30212.1
EN	0.9136	1.3610		1.2778		l I	1.3789	1.3472	0.5258	0.5029	1.3654	0.5312	0.5466	1.31%	1.2852	0.9496	0.4833	0.5571	1.4175	2.6278	1.3417	1.2381	1.3760	1.3340				1.2232	_		0.4412	0.9674	0.4958			1.3197		1.2092	7.49 0.9497		1.4450			8.28 0.8559
CS	21.67 (18.97	19.24 (14.86	16.71	16.08		17.59 (22.73 (4.66	11.55 (10.04 (15.80	8.78	7.83 (22.37 (19.01	42.97	4.14	3.88	4.70	4.03	3.93							_	8.97	15.24 (10.38	8.49	4.04		6.84	7.49	17.90 (19.48	10.25	19.40 (8.28
ANID	MRM047	MRM048	MRM049	MRM050	MRM051	MRM052	MRM053	MRM054	MRM055	MRM056	MRM057	MRM058	MRM059	MRM060	MRM061	MRM062	MRM063	MRM064	MRM065	MRM066	MRM067	MRM068	MRM069	MRM070	MRM071	MRM072	MRM073	MRM074	MRM075	MRM076	MRM077	MRM078	MRM079	MRM080	MRM081	MRM082	MRM083	MRM084	MRM085	MRM086	MRM087	MRM088	MRM089	MRM090

ANID	macro_grp	Chem2012	CERAMIC TYPE	MATERIAL	SOURCE	STATE S	SITE_NAME	SITE_NO	AS	ΓA	Π	ND	SM	n	VB (CE CO	CR
MRM091	Group-C1	Mimbres-23	Mimbres B/W Style III	Pottery	MURR		Divad	LA 096687	5.31	35.22 0	0.3567 3	32.47 5	5.72 3	3.34 2.	2.36 69.65	55 11.70) 41.97
MRM092	Group-B2	Mimbres-02B	Mimbres B/W Style III	Pottery	Murr	NM D	Divad	LA 096687	29.9	43.36 0	0.5129 3	31.20 6	6.40	5.60 3.	3.48 82.81	31 9.07	37.24
MRM093	Group-A	Mimbres-01	Mimbres B/W Style III	Pottery	MURR	NM D	Divad	LA 096687	2.62	65.07 0	0.5988 2	27.67 4	4.93 15	15.97 2.	2.74 104.67	57 2.29	89.9
MRM094	Group-B2	Mimbres-11	Mimbres B/W Style III	Pottery	Murr		Divad	LA 096687	2.26	34.42 0	0.4507 2	24.91 4	4.93 5	5.37 3.	3.06 71.72	15.71	1 45.52
MRM095	Group-B1	Mimbres-04B	Mimbres B/W Style III	Pottery			Divad	LA 096687	2.97					7.17 3.	3.10 82.22		
MRM096	Group-B1	Mimbres-04A	Mimbres B/W Style I	Pottery	Murr		Hill 100	LA 097088	3.12	39.75 0	0.4203 2	29.34 6	6.09	4.84 2.	2.76 70.86	36 7.59	33.06
MRM097	Group-B1	Mimbres-04A	Mimbres B/W Style I				Hill 100	LA 097088	2.97	40.37 0	0.3923 3	_				94 8.40) 24.83
MRM098	Group-B2	Mimbres-02A	Mimbres B/W Style Indeter.	Pottery			Hill 100	LA 097088	2.13	45.04 0							
MRM099	Group-B2	Mimbres-02A*	Mimbres B/W Style Indeter. Pottery	Pottery	Murr	NM H	Hill 100	LA 097088	1.65	35.78 0	0.3959 2	26.91 4	4.99 3	3.73 2.	2.64 61.57	5.57	7 29.50
MRM100	Group-C1	Mimbres-21	Mimbres B/W Style I/II	Pottery	MURR		Hill 100	LA 097088	4.29	41.56 0	0.4382 3	35.16 7	7.07	2.44 3.	3.33 78.98	11.67	7 81.13
MRM101	Group-B1	Mimbres-04A	Mimbres B/W Style II	Pottery	Murr	X	Furqoise Ridge	41EP00762	2.18	50.18 0	0.5163 5	52.14 6	6.53 3	3.83 3.	3.35 91.46	1.38	3 23.05
MRM102	Group-B1	Mimbres-04C	Mimbres B/W Style II	Pottery	Murr		Furqoise Ridge	41EP00762	1.73	45.36 0	0.4961 3	34.93 7	7.06	3.18 3.	3.06 87.49	67.3	3 40.10
MRM103	Group-C2	Unas.	Mimbres B/W Style I	Pottery	Murr	TX T	Furqoise Ridge	41EP00762	3.66	31.51 0	0.3714 2	26.17 5	5.88	3.38 2.	2.62 64.24	24 6.85	35.25
MRM104	Group-B1	Mimbres-04C	Mimbres B/W Style II	Pottery	Murr	•	Furqoise Ridge	41EP00762	1.67	51.06 0	0.4992 3	36.76	7.13 3	3.50 3.	3.16 93.15	15 9.37	7 41.30
MRM105	Group-B	Unas.	Mimbres B/W Style I	Pottery	Murr	TX T	Turqoise Ridge	41EP00762	2.88	60.64 0	0.5825 4	48.57 9	97.6	3.48 4.	4.22 108.17	l	1 31.67
MRM106	Group-B	Unas.	Mimbres B/W Style I	Pottery	Murr		Furqoise Ridge	41EP00762	3.19	63.64 0			_	3.71 4.	l		
MRM107	Group-C2b	Mimbres-41	Mimbres B/W Style II	Pottery	Murr .	TX T	Furqoise Ridge	41EP00762	16'1	36.42 0	0.3862 2	27.07 5	5.81 2	2.41 2.	2.80 76.59	10.81	1 25.50
MRM108	Group-B1	Mimbres-04C	Mimbres B/W Style I/II	Pottery	Murr		Furqoise Ridge	41EP00762	1.65	45.46 0	0.4791 4	48.37 7	7.03 3		3.02 90.50	90 8.95	5 45.26
MRM109	Group-C2a	Mimbres-49A	Mimbres B/W Style I/II	Pottery	Murr	X	Furqoise Ridge	41EP00762	2.31	20.67	0.4935 4	44.33 9	9.23 2	2.58 3.	3.52 99.96	96 8.38	3 38.7
MRM110	Group-B1	Mimbres-04C	Mimbres B/W Style II	Pottery	Murr	X	Turqoise Ridge	41EP00762	2.25	44.19 0	0.4780 6	63.32	7.05	3.09 2.	2.99 87.87	37 9.23	3 41.54
MRM111	Group-C2b	Mimbres-41	Mimbres B/W Style II	Pottery	Murr .	•	Furqoise Ridge	41EP00762	5.89	37.97 0	0.3698 4	46.05 6	6.07	1.94 2.	2.96 76.34	34 10.25	5 28.03
MRM112	Group-B1	Mimbres-04C	Mimbres B/W Style I/II	Pottery	Murr	X	Turqoise Ridge	41EP00762	2.50	45.88 0	0.4625 3	33.58 7	7.14 3	3.01	3.36 89.18	10.26	5 44.69
MRM113	Group-C1	Mimbres-23	Mimbres B/W Style III	Pottery	Murr		Sandcliffe		4.13	35.81 0		27.70 5	5.86		2.76 71.63	53 12.01	1 45.64
MRM114	Group-B	Unas.	Mimbres B/W Style III	Pottery			Sandcliffe		2.22								2
MRM115	Group-A	Mimbres-01	Mimbres B/W Style III	Pottery			Sandcliffe		2.35				7.26 12		4.39 147.20		
MRM116	Group-B2	Mimbres-11	Mimbres B/W Style III	Pottery			Sandcliffe		5.51				4.78 4		2.94 74.76	_	
MRM117	Group-B2	Mimbres-02A	Mimbres B/W Style III	Pottery	Murr	NM S	Sandcliffe		2.08	47.91 0	0.5739 3	36.95 7	7.65 6	6.28 3.	3.45 90.83	33 6.28	39.46
MRM118	Group-B2	Mimbres-02A	Mimbres B/W Style III	Pottery			Sandcliffe		3.57								
MRM119	Group-B2	Mimbres-02A	Mimbres B/W Style III	Pottery			Sandcliffe		1.94					5.76 2.			
MRM120	Group-B	Unas.	Mimbres B/W Style III	Pottery			Sandcliffe		4.86								
MRM121	Group-B	Unas.	Mimbres B/W Style III	Pottery			Sandcliffe		90.9	_							
MRM122	Group-B2	Mimbres-02A	Mimbres B/W Style III	Pottery			Sandcliffe		3.25						_		
MRM123	Group-B1	Mimbres-04B	Mimbres B/W Style III	Pottery			Temporal	LA 001085	1.83						_		~
MRM124	Group-A	Mimbres-01	Mimbres B/W Style III	Pottery			Femporal	LA 001085	1.45			45.97 4	_				
MRM125	Group-C1	Mimbres-23	Mimbres B/W Style III	Pottery			Temporal	LA 001085	5.28							54 11.37	7 39.81
MRM126	Group-A	Mimbres-01	Mimbres B/W Style III	Pottery			Femporal	LA 001085	4.57	52.24 0	0.5162 1		3.73 12			1.7	1 4.22
MRM127	Group-C2a	Mimbres-49A	Mimbres B/W Style III	Pottery			Femporal	LA 001085	4.50		0.4047 5			3.35 3.			
MRM128	Group-B2	Mimbres-11	Mimbres B/W Style III	Pottery	Murr	L MN	Femporal	LA 001085	2.81	37.89 0	0.4620 2	26.31 4	4.95 4	4.43 2.	2.85 75.43	13.84	1 38.88
MRM129	Group-B	Unas.	Mimbres B/W Style III	Pottery		T	Femporal	LA 001085	3.06				4.34 3		_	18 7.42	31.55
MRM130	Group-A	Mimbres-01	Mimbres B/W Style III	Pottery		J	Femporal	LA 001085	2.17				3.49 12	12.84 2.	2.47 76.86	``	3 7.5
MRM131	Group-A	Mimbres-01	Mimbres B/W Style III	Pottery	Murr		Femporal	LA 001085	5.59	50.57 0	0.5394 1	17.88 3	3.68 12	12.01 2.	2.52 80.17	1.95	5 4.09
MRM132	Group-B2	Mimbres-02A	Mimbres B/W Style III	Pottery		L MN	emporal	LA 001085	0.00				7.66 4				
MRM133	Group-B	Unas.		Pottery			Femporal	LA 001085	0.00	_							3 24.28
MRM134	Group-C2a	Mimbres-49B	Mimbres B/W Style I	Pottery	MURR	L MN	emporal	LA 001085	3.02	65.41 0	0.5519 8	82.80 12	12.93	2.52 4.	4.04 81.91	11.38	3 66.72

>	79.60	57.80	23.40	63.90	52.90	06.89	67.20	63.90	71.70	68.70	58.60	64.00	87.80	67.20	95.80	80.10	88.20	68.10	72.70	96.70	84.80	70.60	77.50	47.20	31.30	09.69	29.60	81.70	57.50	64.10	64.60	28.00	51.20	14.90	86.00	16.60	92.90	73.90	51.80	23.20	25.50	72.00	46.30	94.60
F	3768.0	2871.5	1237.1	4179.5	3091.8	3789.4	3271.8	3524.4	3537.2	2495.2	3969.3	3881.1	3366.5	3917.5	4491.1	4052.7	3533.6	3607.4	3497.5	3592.4	3534.0	3440.7	3253.5	2698.9	1518.6	2991.1	3227.8	3361.8	3478.6	3788.3	3049.8	3153.0	2687.2	1373.0	2698.2	1086.0	4899.3	3284.4	2352.8	1629.4	1565.0	3629.0	2686.6	4665.5
NA	10791.2	9473.4	10891.1	10031.1	9745.9	14489.6	14710.9	12186.5	12185.2	17185.7	15091.6	15366.8	10471.5	16012.0	13811.1	14448.2	16972.0	17394.8	15404.4	15397.5	17007.4	15441.7	15710.4	11649.5	15697.1	10097.7	15202.8	11108.9	12922.0	16067.0	13151.3	12624.2	14393.0	16427.1	10647.7	10316.4	17251.3	11221.8	11564.3	14760.2	14550.3	13195.7	14584.1	15326.5
MM	673.1	676.3	193.6	741.0	257.8	355.3	372.1	361.1	333.7	6.886	393.8	367.2	354.2	389.9	616.3		582.5	395.7	9.059	366.5	550.0	358.2	640.8	382.4	305.2	1384.4	253.1	252.9	242.6	199.4	201.2	177.7	252.7	524.6	616.3	169.5	448.4	2367.0	755.0	152.9	170.5			682.5
¥	27632.8	24749.7	35180.4	32294.9	25693.9	28644.2	30213.5	27442.7	28152.4	27949.2	32916.8	26474.6	23690.6	26199.1	27461.7	28951.7	23427.9	26727.0	23972.3	23687.6	23506.7	24757.2	30851.8	28952.4	30146.2	28946.6	29511.6	26354.9	29077.0	33599.2	32257.6	27292.9	31620.6	32918.3	26509.6	34304.6	22307.4	41467.9	21200.0	28911.8	34161.8	26287.3	32662.2	20080.5
Dλ	3.743	4.828	2.491	3.250	4.473	3.892		5.043	4.856	4.666	3.981	5.214	4.276	4.903	6.834		3.510	5.083	5.910	4.794	3.611	4.611	3.824																3.380	1.926	2.263			7.323
CA	53504.0	8408.0	6828.3	10942.0	12389.1	11398.3	13434.0	11564.0	10587.9	17096.3	11149.9	12962.2	10610.9	13664.2	11513.2	8942.0	22525.9	14521.3	12441.9	12880.5	21595.5	11724.7	45386.2	8010.2	7562.3	10520.0	12883.0	21839.3	10703.9	11901.0	8354.2	14469.5	13195.1	30634.0	65671.5	7540.0	16557.0	10613.0	16935.8	5880.0	7834.5	11953.1	11805.0	16514.9
BA	690.4	501.8	646.9	468.0	465.1	1140.5	1097.9	747.9	889.4	1141.6	922.5	707.8	816.2	714.1	937.0	783.5	1094.6	736.8	937.5	746.2	1120.8	650.5	697.2	532.9	378.4	9.169	644.8	974.8	9:229	9.797	811.6	786.1	812.5	343.7	512.6	263.0	854.0	743.8	417.4	496.9	351.3	555.4	562.0	1088.4
AL	74951.8	90863.0	96643.7	81988.0	97782.0	80654.1	80355.5	91572.5	85678.2	90825.5	6.06098	87288.3	87911.9	89661.9	93240.5	89363.5	94077.8	84150.3	96451.7	83986.5	93087.6	89029.3	79107.9	86074.9	06918.3	83928.5	86156.3	00171.9	94107.2	91988.5	92319.5	87859.4	85943.9	109050.9	73848.7	94300.7	88694.9	88649.5	76086.6	94828.9	93908.4	90425.0	_	93445.1
ZR	124.2	146.5	202.5	165.3	184.9	222.9	203.1	208.5	166.5	176.7	231.5	196.1	150.3	183.8	200.0		170.3	178.0	175.0	188.5	170.7	175.3	138.5	187.0	155.0	161.0		~		155.9	156.9	174.3		_			184.8	159.4	143.2	166.2	146.6	178.5	169.3	177.7
NZ	76.4	74.6	41.9	55.2	1.99	50.2	55.4	58.9	53.2	7.77	8.89	73.2	63.0	82.1	69.1	72.5	48.4	83.1	69.4	73.1	63.0	72.8	73.9	54.6	49.4	59.1	56.1	74.2	54.6	46.5	46.8	55.4	8.69	66.4	53.8	72.9	81.4	41.3	52.4	76.7	48.0	66.2	146.4	92.2
3 TH	12.07	7 21.32	5 51.00		1 28.29	17.47		1 20.37	0 15.70	11.25	1 22.42	1 16.70	3 11.17	3 17.57	14.89	5 17.27	3 11.02	5 16.54	3 13.24	9 16.70	3 11.09	9 16.82	5 12.43				_	_						_			11.14	1 20.87	18.01	2 49.46				1 10.23
TA TB	0.9902 0.70	1.5351 0.77	2.3855 0.46	1.5734 0.61	1.5890 0.81	1.4202 0.69	1.4295 0.65	1.6019 0.91	1.2150 0.70	0.8840 1.04	1.6217 0.51	1.2603 0.81	0.7889 0.88	1.2316 0.98	1.1188 0.84	1.3059 1.25	0.9646 0.48	1.2438 0.56	1.0201 1.68	1.2178 1.49	0.9625 0.48	1.2397 0.59	0.9729 0.45	1.5775 0.90	2.3957 0.71	1.5171 0.39	1.4051 1.21	1.4895 1.21	1.5506 1.09	1.4584 0.66	-		_		0.8992 0.97	2.1766 0.22	1.0686 0.54	1.4887 0.41	1.3397 0.34	2.6239 0.2.	2.2943 0.30			0.9829 1.51
SR	521.9 0.	211.4 1.	141.6 2.	259.5 1.	205.4 1.	446.3 1.	385.3 1.	359.3 1.	251.9 1.	388.6 0.	273.8 1.	276.6 1.	328.4 0.	303.1	319.2 1.	379.1 1.	646.9 0.	387.2 1.	353.6 1.	313.7 1.	746.6 0.	339.2 1.	644.8 0.	148.7 1.							_		_			203.3 2.	444.6 1.	223.4 1.	336.9 1.		108.5 2.			444.5 0.
SC	10.26	9.54	4.08		9.34	. 19.9			8.50	9.43		9.32	08.6	9.40	10.28	10.55	8.33	8.93	10.42	9.15	8.56	9.42	10.26	8.65		8.65			10.75							3.63		7.94				_		13.07
SB		0.8903	0.6470	0.7165	0.4304	0.3087	0.3499	0.4708	0.3845	1.5999	0.4792	0.4227	0.7965	0.4442	0.4648	0.5093	0.3418	0.4127	0.4044	0.3888	0.3063	0.4220	0.7638	0.4374	0.8169	0.8054				0.6962	0.7311	0.4508	0.6434			0.9136	0.7217	0.6849	0.4730	0.6838	0.7150	0.4219		0.3908
RB	160.10	205.80	205.70	197.70	150.70	144.10	151.50	156.00	124.20	135.00	173.60	122.00	115.70	120.40	130.00	140.40	95.20	122.80	120.40	122.20	101.20	121.10	167.70	190.20	240.70	199.20	147.40	153.70	154.10	209.40	224.40	139.90	180.40	250.60	152.40	196.20	102.40	208.30	149.90	220.80	195.10	147.60	180.90	90.30
Z	0.0	0.0	0.0			0.0	0.0	0.0	0.0	41.6	23.5	0.0	0.0	0.0	0.0	0.0	0.0	29.6	45.6	0.0	26.8	26.8	23.4	20.6	0.0	46.4											45.8	30.6	0.0		0.0	0.0		39.0
出	5.20	99:9	92.9	7.17	6.51	88.88		7.59	6.47	7.09	10.79	7.93	5.55	8.34	7.34	7.87	6.88	7.64	7.64	7.73	6.63	8.16	5.81	7.02	6.47	7.31	8.05	6.88	8.46	5.85	6.16	8.04	6.24	7.29		6.59	7.66	7.15	6.55		5.98			6.58
FE	32085.3	26883.4	11678.6	24965.1		30441.7	32361.3	25475.9	19975.9	30221.8	28288.9	30598.5	33088.0	30836.2	38857.8	36390.3	33859.9	35324.1	31530.2	30794.2	34543.1	32882.2	33587.8	22010.8		26446.0				20235.7	21339.2	23459.0	21709.8	11522.1	31137.6		39543.3	24068.7	23696.2	12404.6	10196.3	28366.4	18385.3	40737.6
EU	1.1994	1.1825	0.5125	1.0025	1.0688	1.1482	1.1270	1.2832	0.9302	1.2522	1.2352		1.4183	1.4083	2.0126		1.4733	1.4377	2.0213	1.3643	1.5272	1.4445	1.2437	1.3230		0.9638									1.1775	9.86 0.4334	1.6472	1.0055	11.68 0.7928	0.4216	0.4713			2.6014
CS	10.65	48.37	10.25	7.58	6.31	4.44	4.51	20.12	15.64	14.13	5.37	4.85	5.56	4.84	5.59	6.38	3.69	4.68	4.05	4.95	3.71	4.90	10.68	5.91	23.92	7.88	16.38	29.78	23.12	11.00	11.64				10.28	98.6		8.94	11.68	21.28		15.81	9.13	3.82
ANID	MRM091	MRM092	MRM093	MRM094	MRM095	MRM096	MRM097	MRM098	MRM099	MRM100	MRM101	MRM102	MRM103	MRM104	MRM105	MRM106	MRM107	MRM108	MRM109	MRM110	MRM111	MRM112	MRM113	MRM114	MRM115	MRM116	MRM117	MRM118	MRM119	MRM120	MRM121	MRM122	MRM123	MRM124	MRM125	MRM126	MRM127	MRM128	MRM129	MRM130	MRM131	MRM132	MRM133	MRM134

	CERAINIC LIPE			:	SIIE_INAINE	SILE_NO	2	_							CR
MINDLES-23	Mimbres B/W Style II	Pottery	MURR	M	Temporal	LA 001085	3.94	50.42				3.55 2	_	12.67	42.62
	Mimbres B/W Style III	Pottery	MURR	M	Temporal	LA 001085	3.31			_	5.58		2.81 67.83		
Mimbres-02A N	Mimbres B/W Style III	Pottery	MURR	MN	Temporal	LA 001085	2.60	58.94	0.6158	70.31	8.95	4.50 4			38.77
	Mimbres B/W Style III	Pottery	MURR	MN	Temporal	LA 001085	3.06				3.98 1				5.48
Mimbres-01	Mimbres B/W Style III	Pottery	MURR	MN	Temporal	LA 001085	3.25				4.71 1				96.8
Mimbres-01	Mimbres B/W Style III	Pottery	MURR	NM	Temporal	LA 001085	2.68	63.30			5.83 1			28 2.42	7.13
Mimbres-02A N	Mimbres B/W Style III	Pottery	MURR	¥	Temporal	LA 001085	2.71	40.81	0.5162	39.12	6.39	5.06		78 6.51	38.82
Mimbres-02A N	Mimbres B/W Style III	Pottery	MURR	MN	Temporal	LA 001085	3.07		_	51.93	8.14	4.72 3		91 9.42	41.60
_	Mimbres B/W Style III	Pottery	MURR	MN	Temporal	LA 001085	4.22	38.35		48.95	6.71	4.45			46.43
Mimbres-02B N	Mimbres B/W Style III	Pottery	MURR	M	Temporal	LA 001085	6.70	44.35	0.5929	36.46	7.54	6.43 3			41.14
Mimbres-04C N	Mimbres B/W Style II	Pottery	MURR	MN	Roth	LA 073942	2.23	42.81				3.12			30.39
Mimbres-04A	Mimbres B/W Style II	Pottery	MURR	MN	Roth	LA 073942	2.88	46.87	0.4248	51.41	6.04	3.98			19.7
Mimbres-05A	Mimbres B/W Style II	Pottery	MURR	MN	Roth	LA 073942	2.10	46.68		65.47		3.56 3			45.39
_	Mimbres B/W Style II	Pottery	MURR	MN	Roth	LA 073942	2.61	62.22	0.4998	70.54		2.70 3	_		30.7
_	Mimbres B/W Style I	Pottery	MURR	MN	Roth	LA 073942	2.86	45.49 (56.36	7.19	3.34 3			34.68
Mimbres-03	Mimbres B/W Style II	Pottery	MURR	MN	Roth	LA 073942	1.79	49.35	1.4521	48.41	3.84	7.38 12	<u> </u>		9.46
Mimbres-24	Mimbres B/W Style I	Pottery	MURR	MN	Roth	LA 073942	6.35	39.52		55.97				15 12.47	48.10
	Mimbres B/W Style I	Pottery	MURR	MN	Roth	LA 073942	1.75	39.87	0.3871	33.66	6.54				23.97
Mimbres-05A N	Mimbres B/W Style I	Pottery	MURR	MN	Roth	LA 073942	3.65	46.31		42.49					58.87
Mimbres-04A	Mimbres B/W Style II	Pottery	MURR	MN	Roth	LA 073942	2.01	44.01				3.67			21.63
Mimbres-04B N	Mimbres B/W Style I	Pottery	MURR	M	Roth	LA 073942	1.79	39.64		26.55		5.06 2			23.61
Mimbres-05A N	Mimbres B/W Style II	Pottery	MURR	M	Roth	LA 073942	2.46	46.19		41.33		3.04 3			45.70
Mimbres-04A	Mimbres B/W Style I	Pottery	MURR	MN	Roth	LA 073942	2.24	52.75		44.89	9.04	4.05			25.9
	Mimbres B/W Style I/II	Pottery	MURR	NM	Roth	LA 073942	6.50		0.4600						
Mimbres-04A	Mimbres B/W Style I	Pottery	MURR	MM	Roth	LA 073942	2.30		0.4159						23.22
Ü	Mimbres B/W Style III	Pottery	MURR	NM	Los Tules	LA 016315	2.13			30.34				1	
	Mimbres B/W Style I	Pottery	MURR	M	Los Tules	LA 016315	2.65			38.26					
Ą	Mimbres B/W Style I	Pottery	MURR	MN	Los Tules	LA 016315	2.78								
Mimbres-21	Mimbres B/W Style II	Pottery	MURR	M	Los Tules	LA 016315	2.56								
_	Mimbres B/W Style I	Pottery	MURR	MN	Los Tules	LA 016315	3.14								
	Mimbres B/W Style II	Pottery	MURR	¥.	Los Tules	LA 016315	4.92						1		28.23
	Mimbres B/W Style III	Pottery	MUKK	MN :	Los Iules	LA 016315	1.84			_				_	42.44
	Mimbres B/W Style III	Pottery	MURR	M	Los Tules	LA 016315	4.00								22.38
	Mimbres B/W Style III	Pottery	MURR	M	Los Tules	LA 016315	4.02		0.3672		_				40.61
	Mimbres B/W Style II	Pottery	MURR	MM	Los Tules	LA 016315	1.12	44.87	0.5733		3.45 1			1.17	3.72
Mimbres-01	Mimbres B/W Style III	Pottery	MURR	MN	Los Tules	LA 016315	2.84	23.68	0.5874	20.95	4.04				4.91
Mimbres-13 N	Mimbres B/W Style I	Pottery	MURR	MN	Los Tules	LA 016315	15.56	92.79	1.2789	79.67				38 9.41	38.55
_	Mimbres B/W Style I	Pottery	MURR	MN	Los Tules	LA 016315	5.46	33.50		32.48	6.29				36.36
Mimbres-01	Mimbres B/W Style III	Pottery	MURR	MN	Los Tules	LA 016315	2.72	57.41	0.6216	19.79	4.17 1				7.54
Mimbres-21	Mimbres B/W Style II	Pottery	MURR	MN	Los Tules	LA 016315	2.83	39.94 (0.3809	33.18	6.12	1.63 2		36 11.70	.69.3
Mimbres-23	Mimbres B/W Style II	Pottery	MURR	MN	Los Tules	LA 016315	2.36	36.51	0.3699	28.13	5.88	3.44 2		12.11	45.54
	Mimbres B/W Style I	Pottery	MURR	MN	Los Tules	LA 016315	4.56		0.3726	28.20	2.96				
Mimbres-49A N	Mimbres B/W Style Indete	r. Pottery	MURR	¥	Los Tules	LA 016315	2.21	38.98	0.3388	32.04	6.21	2.01 2		•	58.47
Mimbres-23 N	Mimbres B/W Style II	Pottery	MURR	NM	Los Tules	LA 016315	3.84	34.63	0.3709	27.93	5.70	3.95 2			43.0
- 本 本 本 本 本 本 本 本 本 本 本 本 本			Mimbres BW Style III Mimbres BW Style II Mimbres BW Style III	Mimbres BW Style III Pottery Mimbres BW Style II Pottery Mimbres BW Style III Pottery	Mimbres BW Style III Pottery MURR NM Mimbres BW Style II Pottery Murbres BW	Mimbres BW Style III Pottery MURR NM Mimbres BW Style II Pottery Murbres BW Style II Po	Mimbres BW Style III Pottery MURR NM Temporal Mimbres BW Style III Pottery MURR NM Roth Mimbres BW Style II Pottery MURR NM Los Tules Mimbres BW Style II Pottery MURR NM Los	Minches BMS Syle III Pottery MURR NM Temporal LA 001085 Minches BMS Syle III Pottery MURR NM Temporal LA 001085 Minches BMS Syle III Pottery MURR NM Temporal LA 001085 Minches BMS Syle III Pottery MURR NM Temporal LA 001085 Minches BMS Syle III Pottery MURR NM Temporal LA 001085 Minches BMS Syle III Pottery MURR NM Temporal LA 001085 Minches BMS Syle III Pottery MURR NM Temporal LA 001085 Minches BMS Syle III Pottery MURR NM Roth LA 073942 Minches BMS Syle II Pottery MURR NM Roth LA 073942 Minches BMS Syle II Pottery MURR NM Roth LA 073942 Minches BMS Syle II Pottery MURR NM Roth LA 073942 Minches BMS Syle II Pottery MURR NM Roth LA 073942 Minches BMS Syle II Pottery MURR NM Roth LA 073942 Minches BMS Syle II Pottery MURR NM Roth LA 073942 Minches BMS Syle II Pottery MURR NM Roth LA 073942 Minches BMS Syle II Pottery MURR NM Roth LA 073942 Minches BMS Syle II Pottery MURR NM Roth LA 073942 Minches BMS Syle II Pottery MURR NM Roth LA 073942 Minches BMS Syle II Pottery MURR NM Roth LA 073942 Minches BMS Syle II Pottery MURR NM LOS Tules LA 076315 Minches BMS Syle II Pottery MURR NM LOS Tules LA 076315 Minches BMS Syle II Pottery MURR NM LOS Tules LA 076315 Minches BMS Syle II Pottery MURR NM LOS Tules LA 076315 Minches BMS Syle II Pottery MURR NM LOS Tules LA 076315 Minches BMS Syle II Pottery MURR NM LOS Tules LA 076315 Minches BMS Syle II Pottery MURR NM LOS Tules LA 076315 Minches BMS Syle III Pottery MURR NM LOS Tules LA 076315 Minches BMS Syle II Pottery MURR NM LOS Tules LA 076315 Minches BMS Syle II Pottery MURR NM LOS Tules LA 076315 Minches BMS Syle II Pottery MURR NM LOS Tules LA 076315 Minches BMS Syle II Pottery MURR NM LOS Tules LA 076315 Minches BMS Syle II Pottery MURR NM LOS Tules LA 076315 Minches BMS Syle II Pottery MURR NM LOS Tules LA 076315 Minches BMS Syle II Pottery MURR NM LOS Tules LA 076315 Minches BMS Syle II Pottery MURR NM LOS Tules LA 076315 Minches BMS Syle II Pottery MURR NM LOS Tules LA 076315 Minches BMS Syle II Pottery MURR NM LOS Tules LA 076315 Minches BMS Syle II Pottery MURR	Minchees BW Style III Pottacy MURR NM Temporal IA 001085 3.51 ASSIB Minchees BW Style III Pottacy MURR NM Temporal IA 001085 3.06 63.91 Minchees BW Style III Pottacy MURR NM Temporal IA 001085 2.01 4.08 Minchees BW Style III Pottacy MURR NM Temporal IA 001085 2.01 4.08 Minchees BW Style III Pottacy MURR NM Temporal IA 001085 2.01 4.43 Minchees BW Style II Pottacy MURR NM Temporal IA 001085 2.01 4.43 Minchees BW Style II Pottacy MURR NM Temporal IA 0073942 2.01 4.46 Minchees BW Style II Pottacy MURR NM Roth IA 0773942 2.01 4.46 Minchees BW Style II Pottacy MURR NM Roth IA 0773942 2.01 4.45 Minchees BW Style II	Minchee BW Syle Pottery MURR NM Temporal A 001085 2.66 534 0.6158 Minchee BW Syle Pottery MURR NM Temporal A 001085 2.66 534 0.6158 0.6350 Minchee BW Syle Pottery MURR NM Temporal A 001085 2.66 534 0.6158 0.6350 0.6350 Minchee BW Syle Pottery MURR NM Temporal A 001085 2.66 534 0.6158 0.6350 0.6350 Minchee BW Syle Pottery MURR NM Temporal A 001085 2.21 4.45 0.6158 0.6350 0.6350 Minchee BW Syle Pottery MURR NM Temporal A 001085 2.21 4.45 0.6158 0.6458 Minchee BW Syle Pottery MURR NM Temporal A 001085 2.21 4.45 0.6458 0.6458 Minchee BW Syle Pottery MURR NM Roth A 077942 2.21 4.45 0.6458 0.4458 0.4458 Minchee BW Syle Pottery MURR NM Roth A 077942 2.21 4.45 0.4458 0.44	Minches BMS Syle II	Mintores BW Syle III Pottery Mintore BW Syle III Pottery MINTOR BW Syle III Pottery MI	Minches BW Sybell Polety MAN Temporal JA 000085 2.65 8.94 1.67 3.94 <t< td=""><td> Minches BNW Syle Pottary MURR NM Temporal LA 001066 2.05 3.05 0.51 </td><td> Mintree BW Style Politicy MINRR NM Temporal A D00165 264 0.554 0.557 0.547 354 0.557 0.548 Mintree BW Style Politicy MINRR NM Temporal A D00165 256 0.554 0.556 0.517 0.524 0.057 0.548 Mintree BW Style Politicy MINRR NM Temporal A D00165 256 0.554 0.557 0.518 0.517 0.524 0.057 0.528 0.057 0.0</td></t<>	Minches BNW Syle Pottary MURR NM Temporal LA 001066 2.05 3.05 0.51	Mintree BW Style Politicy MINRR NM Temporal A D00165 264 0.554 0.557 0.547 354 0.557 0.548 Mintree BW Style Politicy MINRR NM Temporal A D00165 256 0.554 0.556 0.517 0.524 0.057 0.548 Mintree BW Style Politicy MINRR NM Temporal A D00165 256 0.554 0.557 0.518 0.517 0.524 0.057 0.528 0.057 0.0

>	79.40	37.60	96.70	16.80	27.30	33.40	71.20	73.80	84.00	98.80	72.40	46.70	107.10	77.20	63.40	12.40	92.00	104.40	74.90	53.30	45.50	102.20	66.10	80.60	50.80	59.00	65.80	44.10	48.40	77.80	50.40	55.10	49.60	76.30	15.70	24.30	83.60	79.00	30.50	61.60	85.30	86.10	84.80	94.60
F	2635.2	2528.6	2933.3	1337.5	2055.3	2100.7	3338.3	3317.0	3179.3	2538.0	3014.2	2175.9	3547.0 1	3110.5	3383.0	1124.7			4784.8	3687.0	2572.4	3988.5	3136.2	4869.5	2831.3	3833.4	3116.5	2457.9	2300.9	3457.2	2988.9	3707.3	3554.2	4029.1	1578.8	1428.4	3548.8	3880.0	1203.0	3094.1	4010.7	3952.8	4588.7	3715.8
NA	12402.2	12706.6	12116.7	. 12870.8						9516.4	16392.1	14601.9	3432.2	12319.2	16586.3	5014.6		17388.4	14855.0	13979.1	13194.0	13636.5	12600.4	8362.8			3047.6		17282.2	14946.9				11915.3	14134.7	. 8'2036	12500.6	7368.6	. 972598	19760.4				12848.9
MN	723.0 12	289.7 12	432.9 12	173.8 12		,	,	`	`	507.8	491.4 16	419.4 14	575.3 13	1130.8 12	586.4 16	535.2 5		803.1 17	402.6 14	431.3 13	170.7 13	615.8 13	300.2 12	660.2 18	331.0 13	_	432.7 13	`	1133.4 17	1090.9 14		`	264.1 12	669.8 11	118.8 14	171.6 9	445.5 12	223.1	205.3 18	1052.7 19				657.0 12
¥	25610.4 7	26616.6	28140.4 4	30856.3 1			26021.3 2			25433.3 5	26584.6 4	32019.8 4	26070.8 5	24423.4 11	30554.7 5			18035.3 8	27903.2 4	31101.2 4	27383.7 1	25002.1 6	27624.4 3	22947.1 6					29788.6 11	22643.5 10			34568.4 2	27162.8 6	30184.5 1	44876.1 1		20978.8 2	26726.3 2	26248.2 10				30657.4 6
DY	3.742 256		6.794 287			- 1				4.984 254	4.449 265	3.743 320	5.018 260	5.286 24	4.988 305	13.461 470		3.535 180	8.503 279	3.418 317	3.603 273	5.112 250	6.091 276		- 1	- 1			3.311 297	6.538 226				3.961 277	1.859 307	2.480 448	13.829 350	4.178 209	2.750 267		1	- 1		3.731 306
CA		9737.9 4.	14812.9 6.	7						8967.5 4.	14422.6 4.	13246.5 3.	5354.6 5.						7997.8 8.	9814.9 3.	8391.5 3.								13293.5 3.						7885.3 1.	6699.7	9662.3 13.	8796.2 4.						_
۷	4 53295.0				1			_	4		Ì	Ì	_	0 15891.3	1	6 8233.1		9 23193.0				7 17712.2	0 10388.2				`	Ì		9 15992.5				2 47085.7							7			4 42701.7
- BA	714.4	2 476.8	418.4				_		5 627.2	5 404.6	9 891.3	0.895.0		9 858.0	728.8	5 540.6		1 767.9	1 558.0	5 693.8	5 672.9	7 910.7	0.046.0				1	1	5 941.6	3 1159.9				1373.2	792.7	7 953.4	3 1109.5	3 1122.3	2 464.5		`	`		1029.4
Al	77420.9	82916.2	89434.4	89068.1	104033.8	103264.8	91323.7	93847.2	80646.5	91760.5	87967.9	78577.0	90888.6	91675.9	86090.7	81366.6	92576.9	93213.4	76837.4	75922.5	84952.6	90023.0	90751.0	92360.6	87876.6	78197.4	93169.2	83442.0	88835.6	87567.3	89360.0	81327.5	94072.3	82082.7	93359.2	108622.7	88435.3	74852.3	110208.2	91971.4	77138.7	73883.5	94285.0	79550.0
ZR	121.2	155.8	183.8	184.2	152.6		164.8			154.9	199.9	197.5	172.2	141.1	186.1	193.3	199.4	116.3	215.1	201.1	151.8	147.8	175.6	172.7	204.9				145.9	229.3	l I		186.3	132.7	178.2	175.4	304.9	161.0	169.0				150.2	131.2
NZ	76.1	68.2	68.4	42.4	99.2	54.9	81.8	74.3	92.1	78.0	70.1	61.6	93.9	276.5	74.8	109.8	8.96	89.5	110.9	73.3	55.4	110.5	73.0	101.9	75.7	61.7	98.5	62.0	9.69	169.9	59.2	47.0	53.7	91.5	38.2	43.5	106.7	0.06	57.1	85.5	84.2	85.6	91.7	77.1
H	13.06	20.25	21.14	52.91			-		19.71	22.57	17.09	20.94	14.68	14.88	17.32	37.51	1	9.70	18.07	22.11	27.40	14.36	20.65	10.42	21.75		18.98	1	9.13	13.31				12.87	50.24	53.23	50.46	10.70		10.12	13.38	_	9.26	12.49
A TB	8 0.94	.2 1.21	5 0.91	6 0.24			6 0.51	5 1.02	0 1.10	3 1.33	8 0.62	0.20	0 1.51	5 1.62	7 0.71	1.77		5 0.92	1.42	1 0.75	9.09	5 1.17	1.24	7 1.03	4 0.72	99.0	0.91	1 0.95	4 0.65	8 1.32	0.92	5 0.63	9.29	4 0.77	0.30	6 0.36	8 2.35	7 0.85	3 0.42	0.80	0.75	0 0.73	6 0.72	5 0.71
	1	5 1.1742	9 1.4145	1 2.5276		` '				5 1.5563	3 1.2858	1.4456	.5 1.0410	5 1.0525	3 1.3617	0 2.3358		0.5695	3 1.8458	1.5641	3 1.5336	3 1.1045	5 1.5080	0.9357	1.5004				5 0.5794	7 1.1128				1.0034	3 2.7209	2 2.5136	1 2.3698	3 0.8327	2 2.2093	1 0.8330	_			5 1.0835
SR	682.7	200.6	395.9	Ì					1106.3	265.6	311.3	241.2	328	361.5	389.3	90.0		515.7	226.8	258.0	210.3	383.8	245.5	334.1	, 223.9				366.6	339.7			, 255.9	669.2	170.8	78.2	105.4	169.3	132.2	385.4	641.7			878.6
3 SC	10.66	7 8.15	3 11.57				5 11.45		10.68	10.05	1 8.63	6.57	13.75	9.47	9.31	5 5.48		5 13.02	3 9.98	3 7.19	3 7.40	13.57		-	5 7.85		1		7 5.54	7 8.42			6.35	10.26	3.30	5 4.23	11.46	9:38	2 4.91		l		_	3 9.78
SE	0.7667	0.4087	0.4323	0.7702	0.8117	0.7046	0.4316	0.4451	0.9104	0.9901	0.3994	0.4000	0.5637	0.5562	0.4453	0.3856		0.3005	0.6103	0.3938	0.3668	0.5304	0.4048	0.6750	0.3766	1.7386	0.4067	0.3100	2.4077	0.5617	4.3714	0.5865	1.6382	0.8380	0.5070	0.7555	1.0491	1.0236	1.1522	1.3819				0.7508
RB	164.40	168.20	158.10	238.70				150.40	185.70	212.30	127.90	180.50	139.40	125.00		289.00	142.20	83.20	166.80	180.50	153.10	135.00	149.90	121.60	167.60				124.20	118.30				166.80	174.50	267.50	329.00	117.10	266.50	127.70		`		175.60
Z	42.0	0.0	0.0	0.0					0.0	0.0	36.1	0.0	0.0	33.4	39.3	0.0		0.0	0.0	0.0	0.0	20.1	0.0	0.0	0.0		0.0		0.0	32.5			0.0	17.9	0.0	0.0	0.0	0.0	0.0	0.0	_		0.0	30.5
生	5.49	6.38	7.14							7.12	8.21	8.45		6.54	7.85	10.36	_	5.20	11.15	8.83	6.51	6.54	6.98		8.89	3 7.03	6.41	6.04	8 6.45	8.65			7.79	5.35	7.07	6.45	12.73	6.35	7.17	3 7.78	7.03			5.27
HE			27589.3	12583.5						27694.5	32627.8	26940.5		37182.9	32171.0		41006.4	50984.7	35816.8	7.26267	24370.2	40882.8	31048.2	42228.7	1.0566 29051.6		27641.9		21483.8	35839.1		22114.9	21774.0	31648.0	2'1961	6846.7	36183.7	28084.0	16112.7	33185.8			37694.0	32672.3
EU	1.2726	1.0892	1.5742	0.5045	0.6654	0.8123	1.2244	1.5360		1.2401	1.3040	1.1892	1.8689	1.8939	1.3561	0.7405	1.5282	1.7010	1.1752	5.60 1.1456	0.9320	1.8547	1.5797				1.3709	1.4123	1.1564	1.9244	1.2469	1.0409	0.7684	1.2273	0.3920	0.4589	1.7230	1.4100	0.5062	1.2914	1.2871		1.5621	10.86 1.1875
S	10.79	7.24	25.63		18.44	15.62	17.89			50.18	4.86	5.27	6.43	5.05				2.79	9.92	2.60	6.20	6.19	6.05	20.11	5.98	_		4.32	17.82	4.40	15.71		9.74	10.78	6.51	16.87		6:36	21.03	17.00	9.42		6.29	10.86
ANID	MRM135	MRM136	MRM137	MRM138	MRM139	MRM140	MRM141	MRM142	MRM143	MRM144	MRM145	MRM146	MRM147	MRM148	MRM149	MRM150	MRM151	MRM152	MRM153	MRM154	MRM155	MRM156	MRM157	MRM158	MRM159	MRM160	MRM161	MRM162	MRM163	MRM164	MRM165	MRM166	MRM167	MRM168	MRM169	MRM170	MRM171	MRM172	MRM173	MRM174	MRM175	MRM176	MRM177	MRM179

ANID	macro grp	Chem2012	CERAMIC TYPE	MATERIAL	SOURCE	STATE	SITE NAME	SITE NO	AS	ΓA	ΓΩ	ND	SM	n	YB	CE CO	CR
MRM180	Group-A		Mimbres B/W Style II/III	Pottery	MURR	MN	Los Tules	LA 016315	12.07	76.86	1.3815	82.43	17.01	7.64	9.45 184.58		9 41.87
MRM181	Group-B2	Mimbres-02C		Pottery	MURR	MN	Los Tules	LA 016315	3.70	32.59	0.5036	17.90	3.97	3.67	117 63.70	70 4.50	16.27
MRM182	Group-B	Unas.	Mimbres B/W Style II	Pottery	MURR	MN	Los Tules	LA 016315	4.21	51.26	0.5074	36.67	7.47	5.10 3	3.28 111.31	31 4.64	4 29.45
MRM183	Group-C2a	Mimbres-49A	Mimbres B/W Style Indeter.	Pottery	MURR	MN	Los Tules	LA 016315	1.72	39.59	0.3391	33.78	6.32	2.58 2	.25 74.69	69 14.41	1 56.9
MRM184	Group-B2		=	Pottery	MURR	NM	Los Tules	LA 016315	3.83		0.5685	34.72			3.57 94.63		
MRM185	Group-C2a	Mimbres-49A		Pottery	MURR	NM	Los Tules	LA 016315	4.30	40.05	0.4667	35.28	7.51	2.93 3	3.12 81.90	90 17.09	91.79
MRM186	Group-B	Unas.	Mimbres B/W Style II	Pottery	MURR	NM	Los Tules	LA 016315	5.03	43.55	0.4595	34.94	69.9	4.39 2	2.88 87.27	27 7.63	3 53.14
MRM187	Group-B1	Mimbres-04C	Mimbres B/W Style II	Pottery	MURR	MN	Los Tules	LA 016315	2.04	43.47	0.4391	34.41	6.40	4.06	3.08 83.51	51 8.50	30.13
MRM188	Group-C2a	Mimbres-49A	Mimbres B/W Style I	Pottery	MURR	MN	Los Tules	LA 016315	1.88	46.10	0.4374	46.23	8.37	3.58 3	3.47 87.46	46 9.23	38.38
MRM189	Group-B	Unas.	Mimbres B/W Style II/III	Pottery	MURR	MΝ	Los Tules	LA 016315	4.66	39.55	0.3960	30.29	5.44	3.87 2	2.50 78.91	91 7.69	31.04
MRM190	Group-B1	Mimbres-04C	Mimbres B/W Style I	Pottery	MURR	MΝ	Los Tules	LA 016315	2.73	43.12	0.4515	35.25	6.70	3.48 3	3.11 84.40	40 8.25	5 29.23
MRM191	Group-B2	Mimbres-08	Mimbres B/W Style II	Pottery	MURR	MN	Los Tules	LA 016315	4.13	30.99	0.3884	16.76	3.48	4.90 2	2.08 51.72	72 3.10	7 21.07
MRM192	Group-C2a	Mimbres-49A	Mimbres B/W Style III	Pottery	MURR	MN	Los Tules	LA 016315	2.99	39.59	0.3460	33.53	6.41	2.93 2	2.38 71.45	45 12.24	4 56.28
MRM193	Group-A	Mimbres-03	Mimbres B/W Style II	Pottery	MURR	MΝ	Los Tules	LA 016315	2.66	42.41	1.1161	41.13	11.28	7.16 8	8.30 92.00	00 2.00	11.41
MRM194	Group-B	Unas.	Mimbres B/W Style II	Pottery	MURR	MN	Los Tules	LA 016315	4.76	38.03	0.4503	24.91	4.73	6.15 2	2.52 76.11	11 7.25	5 26.34
MRM195	Group-B	Unas.	Mimbres B/W Style II	Pottery	MURR	MN	Los Tules	LA 016315	3.35	27.49	0.2805	17.64	3.15	2.19 1	1.94 45.82	82 2.61	13.66
MRM196	Group-B2	Mimbres-02A	Mimbres B/W Style I	Pottery	MURR	MN	Los Tules	LA 016315	00.00	41.04	0.4674	31.90		4.81 2	2.80 78.77	77 7.95	5 37.3
MRM197	Group-C2a	Mimbres-49A	Mimbres B/W Style III	Pottery	MURR	MΝ	Los Tules	LA 016315	4.37	32.47	0.3311	27.41	5.34	3.04 2	2.25 67.05	05 11.31	1 45.84
MRM198	Group-C2a	Mimbres-49A	Mimbres B/W Style II/III	Pottery	MURR	ΣN	Los Tules	LA 016315	3.43	43.36	0.4093	36.31	69.9	3.24 2	2.60 81.54	54 13.48	3 51.43
MRM199	Group-B	Unas.	Mimbres B/W Style II	Pottery	MURR	MΝ	Los Tules	LA 016315	5.83	62.02	0.6323	46.34	8.82	5.91 4	4.18 110.15	15 5.60	34.07
MRM200	Group-C1	Mimbres-21	Mimbres B/W Style I	Pottery	MURR	MΝ	Tortugas	LA 079550	2.58	37.10	0.2980	28.45	5.11	1.03 2	2.12 74.33		7 61.65
MRM201	Group-C2b	Mimbres-41	Mimbres B/W Style I	Pottery	MURR	MN	Tortugas	LA 079550	0.00	37.30	0.3248	30.27	5.70	2.39 2	2.12 68.02		5 26.18
MRM202	Group-B1	Mimbres-04C	Mimbres B/W Style I	Pottery	MURR	MN	Tortugas	LA 079550	1.47	38.37	0.4051	27.18	5.78	2.97	2.59 75.42	42 7.33	3 34.3
MRM203	Group-B1	Mimbres-04C	_	Pottery	MURR	MN	Tortugas	LA 079550	2.04	42.26	0.4337	29.40		3.59 2	2.89 79.60	60 10.25	5 37.53
MRM204	Group-B	Unas.		Pottery	MURR	NM	Tortugas	LA 079550	2.24	45.21	0.5142	32.23	7.59	3.16 3		78 11.81	1 42.86
MRM205	Group-C2b			Pottery	MURR	NM	Roth	LA 073942	2.16		0.3629	27.13			2.52 67.69	69 9.72	2 23.6E
MRM206	Group-C2b		_	Pottery	MURR	NM	Roth	LA 073942	1.44		0.3504	43.27	5.80	2.52 2		1	7
MRM207	Group-A	Mimbres-03	_	Pottery	MURR	MN	Roth	LA 073942	2.63		1.4721		11.71	7.73 12	-		
MRM208	Group-A	Mimbres-03		Pottery	MURR	NM	Roth	LA 073942	3.93		1.2457	34.07	9.17	6.87	9.60 90.72		0 10.23
MRM209	Group-B1	Mimbres-05A	=	Pottery	MURR	M	Roth	LA 073942	2.94	45.56	0.5019	41.37	8.45	3.17 3	3.74 88.33	33 10.99	9 50.38
MRM210	Group-B1	Mimbres-04A	=	Pottery	MURR	M	Roth	LA 073942	2.15	_	0.4441	29.81					(\)
MRM211	Group-A	Mimbres-03		Pottery	MURR	MN	Roth	LA 073942	4.02		1.2898	34.42					
MRM212	Group-C2	Unas.	Mimbres B/W Style II	Pottery	MURR	MN	Roth	LA 073942	2.70		0.5136	60.28			_		
MRM213	Group-B	Unas.	ndeter.	Pottery	MURR	M	Roth	LA 073942	2.13		0.4947	51.36		2.97 3	3.77 85.38		1 42.08
MRM214	Group-B	Unas.	Mimbres B/W Style I	Pottery	MURR	NM	Roth	LA 073942	1.87	47.90	0.3587	34.15	60.9	2.23 2	2.41 86.66	69 6.97	7 28.46
MRM215	Group-A	Mimbres-01		Pottery	MURR	Σ	Rio Vista	LA 001082	1.70	62.47	0.7840	29.99	4.60	8.94	4.25 98.36		
MRM216	Group-C1	Mimbres-23	Mimbres B/W Style III	Pottery	MURR	MΝ	Rio Vista	LA 001082	3.90	36.61	0.3545	27.65	5.83	3.45 2	2.45 73.78	78 12.29	9 45.92
MRM217	Group-A	Mimbres-01		Pottery	MURR	MN	Rio Vista	LA 001082	1.49	06.09	0.6804	22.77	4.92	18.79 2	2.89 100.66	66 1.88	3 8.27
MRM218	Group-A	Mimbres-01	Mimbres B/W Style III	Pottery	MURR	Σ	Rio Vista	LA 001082	2.58	56.31	0.6033	52.14	4.04	9.11 3	3.13 86.99	99 5.32	
MRM219	Group-C2a	Mimbres-49A	Mimbres B/W Style III	Pottery	MURR	MN	Rio Vista	LA 001082	4.53	36.00	0.3629	28.50	5.85	3.92	2.37 73.11	11 11.44	43.08
MRM220	Group-C1	Mimbres-23	Mimbres B/W Style III	Pottery	MURR	NM	Rio Vista	LA 001082	5.13	37.30	0.3818	31.47	5.95	3.54 2	77.57	57 11.46	41.09
MRM221	Group-A	Mimbres-01		Pottery	MURR	NM	Rio Vista	LA 001082	2.96		0.6671	51.94		10.13 3	1		2 10.78
MRM222	Group-B2	Mimbres-02A		Pottery	MURR	NM	Rio Vista	LA 001082	1.43		0.6454	44.54	8.99				
MRM223	Group-B2	Mimbres-02A	Mimbres B/W Style III	Pottery	MURR	NM	Rio Vista	LA 001082	2.35	37.14	0.4880	27.38	2.60	5.32 3	3.16 64.77	77 3.94	4 35.80

>	0	0	0	0	0	0	0	0	0	0	0	0	0	0	0	0	0	0	0	0	0	0	0	0	0	0	0	0	0	0	0	0	0	0	0	0	0	0	0	0	0	0	0	0
	09.69	36.20	26.80	78.60		100.40	97.60	61.40	70.90	51.40	61.10	51.10	84.60	20.90	48.90	29.00	46.50	89.20	30.68	47.60	47.50)9.6/	53.30	40.30	68.20	72.30			16.70	124.80	58.10			73.10	96.09	38.40	85.30	21.50		78.50	78.70			53.20
⊏	3514.9	1742.9	3523.2	4014.7	2799.2	5082.5	4401.0	3076.6	3798.2	3230.4	2883.7	2996.0	5107.9	1755.9	2942.7	1522.4	3058.3	2762.8	3455.9	2661.9	1528.2	3454.0	3639.7	3279.1	3391.4	3659.9	3629.4	1048.5	1672.1	4382.8	2867.8	970.0	3434.5	2934.5	3333.2	1937.9	3534.8	1167.8	1230.5	3438.0	3249.0	1765.3	3610.2	3062.0
NA	12769.5	12297.8	12797.7	20726.5	12589.0	14578.4	11944.9	17559.9	16126.9	15312.5	16900.2	11266.2	19455.7	929999	13599.9	8641.8	15206.8	12111.5	18654.1	11861.3	17612.0	15711.2	17439.3	17414.0	16657.9	15930.9	15244.3	7004.8	5911.6	14238.4	14890.7	6106.9	12872.7	15613.1	15055.6	12662.8	11662.5	13885.7	17370.9	11872.3	10523.7	15478.3	12744.3	11934.3
MN	501.8	741.1	190.6	646.8		981.8	259.9	490.1	733.9	657.3	495.7	183.1	493.0	5.895	453.5	402.2	349.1	631.9	561.0	281.2	1042.9	444.6	380.3	675.3	819.1	486.3	554.0	537.9	0.809	9.809	`			592.2	456.7	260.0	684.8	217.3	307.2	589.3	607.9	. 9	209.5	174.9
¥	36418.6	19931.8	33231.7	23233.1	26568.0	27808.0	27815.9	27827.7	25839.1	30810.9	29154.1	33099.8	21944.2	48569.8	36302.2	21094.7	29210.1	26443.0	25031.0	33045.6	24585.7	21841.4	27524.1	28445.1	26048.4	24187.0	22380.5	50231.8	49309.0	24584.9	31264.6			28462.5	33588.6	35682.8	29431.8	30650.8	28158.3	28542.8	29125.4	27257.7	24997.5	30197.8
DΥ	13.971 36	3.417 19	5.217 33	3.876 23		4.891 27	4.322 27	4.472 27	5.514 25	4.166 30	4.490 29	2.224 33	3.692 21	11.312 48	3.677 36	2.546 21	5.180 29	3.688 26	4.044 25	6.158 33	2.753 24	3.324 21	3.995 27	3.966 28	5.147 26			14.758 50	11.286 49	6.076 24					3.857 33	4.187 35	4.001 29	3.314 30	2.920 28	.702 28	3.852 29		6.775 24	4.533 30
CA	8774.6 13	14476.2 3	11091.7 5	19360.4 3		16554.0 4	12467.5 4	15663.9 4	14549.3 5	12694.5 4	15576.9 4	7733.1 2	19024.2 3	9802.0 11	10026.0 3	9932.0 2	10810.8 5	49678.3 3	16828.3 4	10979.9 6	34222.7 2	22529.1 3	14840.8 3	11336.6 3	13449.7 5	22371.3 3		`		17185.9 6					13310.4 3	8057.5 4	43642.2 4	52031.6 3	28413.1 2	59177.8 3				11359.5 4
A		,		`		Ì					,				,		`							ľ							_													
BA	551.7	255.9	906.4	1249.5		1039.7	892.4	930.3	1024.8	782.3	893.0	712.9	1225.3	420.7	530.2	444.3	501.3	1154.4	867.3	694.1	994.3	862.7	746.6	1019.2	636.9	885.3			582.6	925.1				967.1	1044.1	551.8	9.89.8	117.6	1049.2	935.0	867.7			554.2
AL	91552.9	72064.8	75311.8	91289.4	96700.2	83400.7	86385.6	85002.4	91485.9	74924.1	87361.2	84609.4	94048.5	84261.5	91904.2	89668.3	77010.7	76028.2	84423.2	87297.6	84783.8	97952.1	81965.6	80408.3	7.09077	8.98676	96446.8	78955.5	78855.5	93705.0	96257.4	81492.1	91855.3	82324.6	83405.5	98753.4	82462.1	108729.5	108716.2	76820.4	76773.4	110173.3	91167.6	87715.7
ZR	277.7	106.4	189.1	134.2	177.2	200.7	153.6	201.0	188.9	158.3	147.5	173.0	196.0	162.0	144.0	107.3	166.5	124.0	145.1	197.8	142.3	132.4	148.5	176.9	197.4	143.0	142.7		170.8	148.6	182.8				173.7	168.4	149.1	214.0		131.6	146.0			232.1
NZ	105.3	54.7	60.4	91.8	63.6	105.1	84.1	68.7	79.3	53.1	69.3	52.4	92.4	9.6/	56.3	65.4	7.07	72.8	91.8	74.6	9.08	80.4	69.1	67.3	71.2	72.3	71.0	125.0	168.7	88.1	54.8	162.0	263.6	102.8	50.2	57.8	89.4	53.0	61.7	80.9	86.3	58.5	6.89	62.3
H	56.84	29.41	22.26	6.87	20.97	12.68	17.79	17.66	11.75	16.37	18.01	27.16	6.87	39.14	29.80	17.81	20.05	12.69	13.07	24.77	9.01	10.65	15.18	16.28	16.05	10.20	10.87	34.93	35.80	14.33	19.99	34.23	13.04	17.01	15.88	43.85	13.53	54.71	53.94	12.45	12.60	48.80	19.20	21.85
4 TB	9 2.66	0.20	1.01	4 0.76		5 0.97	4 0.87	3 0.79	2 1.03	0 0.71	6 0.83	2 0.39	4 0.72	4 2.11	99.0 9	7 0.44	5 0.80	4 0.71	5 0.81	1 1.19	5 0.58	0 0.71	3 0.68	2 0.77	1 0.80	8 0.34		5 1.23	9 1.05	2 0.95			9 0.83	8 0.61	4 0.51	2 0.30	6 0.82	2 0.26	9 0.24	9 0.52	7 0.86		1.15	2 0.57
TA	2.3799	1.5559	1.5096	0.8374			1.2554	1.1683	0.9782	1.2790	1.2646	1.8432	0.9104	2.3274	1.6736	1.4057	1.7345	0.9934	0.9005	1.6161	0.6505	0.8860	1.0863	1.2422	1.2981	0.9218			2.3849	1.0312				1.2498	0.8914	2.2392	1.0506	2.2782	2.4129	0.9559	7776.0		1.2339	1.5742
SR	73.1	248.1	282.6	6.109	386.7	330.2	347.3	333.2	343.9	321.5	303.0	151.5	593.2	75.3	154.6	134.9	347.1	548.8	494.9	194.1	390.1	628.9	392.4	404.7	344.3	641.6	9.895	9.07	6.36	326.0	271.2	94.8	302.5	300.4	287.3	201.6	629.6	219.5	138.1	2.163	689.7	192.4	320.4	145.0
SC	_	60'9	6.43	12.20		13.54	9.84	8.10	61.6	6.32	8.14	6.03	12.02	6.07	6.35	6.59	8.80	9.17	11.78	7.90	6.63	8.99	8.23		8.91	8.63				13.90				9.84	6:36	5.16	10.71	5.01	4.55	10.62	10.78		12.30	10.01
SB	1.2696	0.4554	1.6231	0.4952	0.4749	0.7966	1.6665	0.4563	0.3682	0.5540	0.3488	1.6312	0.5660	0.3198	1.1018	0.3808	0.6808	0.6322	0.9149	2.4374	1.4883	0.2173	0.3552	0.3897	0.3672	0.2338	0.2370	0.7307	0.8475	0.4449	0.3615	0.7783	0.4968	0.5626	0.2861	0.5453	0.7812	0.7203	0.6505	0.6519	0.7229	0.8226	0.3261	0.4805
RB	343.80	175.00	218.20	86.10	144.40	131.70	154.60	127.70	106.00	147.80	127.00	197.60	93.30	291.30	208.40	81.90	179.70	130.00	115.40	239.30	115.80	102.20	112.50	133.00	135.70	90.80	106.30	292.00	274.80	132.40	169.80	269.90	116.80	132.00	107.80	267.20	176.80	222.40	239.40	136.80	165.80	249.20	135.90	157.10
Z	0.0	0.0	0.0	0.0		0.0	0.0	0.0	32.4	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	28.8	0.0	0.0	0.0	36.1	24.8	25.1	0.0			0.0	33.7				41.2	0.0	0.0	49.4	0.0	0.0	43.8	47.6	0.0	0.0	0.0
生	12.31	5.74	7.72	6.82	7.66	7.94	6.92	8.57	7.70	7.46	7.25	8.23	7.91	10.09	6.44	7.06	8.02	5.57	90.9	7.44	6.36	5.36	6.28	7.39	8.10	6.22	5.80	10.29	10.39	5.87	8.37	10.35	6.63	8.25	7.56	6.12	5.18	6.47	6.62	4.97	4.72	5.93	6.76	8.24
出	38163.7	15136.9	18886.5	38055.0	26379.1	46130.3	29764.5	29212.2	33391.0	23153.0	30632.5	21115.7	38493.7	15041.7	22985.7	15466.9	24466.3	33847.8	35288.7	21953.1	24753.7	37616.7	28199.6	28302.8	30796.3	34611.4	37732.7	13336.3	14732.4	41111.0	27061.3	13184.9	37244.6	33685.2	24543.1	14777.9	34622.0	12855.0	13329.8	31941.3	31885.6	17726.0	27029.9	20987.2
ED	1.8803	0.6104	1.4561	1.5783		1.6229	1.4701	1.3187	1.8514	1.0905	1.3189	0.6390	1.6273		0.8973	0.5415	1.1788	1.1810	1.5872	1.6719	1.1190	1.4023	1.2237	1.2515	1.4134	1.3330			0.5178	1.8123				1.4043	1.3471	0.7889	1.2433	0.5679	0.6132	1.2476	1.2128			1.0463
SS	47.88	19.86	12.23	6.42		2.97	9.13	4.97		8:38	4.82	8.78	, 88.9	5.74 (9.31	6.57 (14.72	, 16.9	, 83	6.85	14.79	4.59	3.38		4.83	3.72	4.47	4.15 (4.67	6.12				5.95	2.69	19.14 (11.70	21.25 (17.68	7.95	11.43			19.83
ANID	MRM180	MRM181	MRM182	MRM183	MRM184	MRM185	MRM186	MRM187	MRM188	MRM189	MRM190	MRM191	MRM192	MRM193	MRM194	MRM195	MRM196	MRM197	MRM198	MRM199	MRM200	MRM201	MRM202	MRM203	MRM204	MRM205	MRM206	MRM207	MRM208	MRM209	MRM210	MRM211	MRM212	MRM213	MRM214	MRM215	MRM216	MRM217	MRM218	MRM219	MRM220	MRM221	MRM222	MRM223

ANID	macro_grp	Chem2012	CERAMIC TYPE	MATERIAL	SOURCE	STATE S	SITE_NAME	SITE_NO	AS	ΓA	Π	ND	SM	n	YB	CE CO	CR
MRM224	Group-A	Unas.	Mimbres B/W Style III	Pottery	MURR		Rio Vista	LA 001082	9.47	236.27	1.7940 22	226.37 37	37.15	8.10 12.	12.28 298.52	7.82	40.58
MRM225	Group-B	Unas.	Mimbres B/W Style III	Pottery	Murr	NM R	Rio Vista	LA 001082	2.38	70.47	0.6238	62.76	8.43 4	4.35 3.	3.99 126.37		31.74
MRM226	Group-A	Mimbres-01	Mimbres B/W Style III	Pottery	MURR	NM	Rio Vista	LA 001082	2.87	62.58	0.5871	20.11 4	4.16 12	12.82 2.	2.83 94.72	2 2.50	19.9
MRM227	Group-B	Unas.	Mimbres B/W Style III	Pottery	MURR		Rio Vista	LA 001082	3.17	42.98 (0.4551	52.13 4		4.14 2.	2.87 70.97	7 5.81	14.89
MRM228	Group-C1	Mimbres-23	Mimbres B/W Style III	Pottery			Rio Vista	LA 001082	3.03	34.88	0.3703		5.45 3	3.36 2.		11.51	41.91
MRM229	Group-A	Mimbres-01	Mimbres B/W Style III	Pottery	MURR		Rio Vista	LA 001082	2.31	51.25	0.4970	15.83 3	3.63 14	14.70 2.		1.76	4.49
MRM230	Group-C1	Mimbres-23	Mimbres B/W Style III	Pottery			Rio Vista	LA 001082	6.13	-	0.3690	27.63 5	5.65 3		2.34 69.41	1	39.91
MRM231	Group-B	Unas.	Mimbres B/W Style III	Pottery			Rio Vista	LA 001082	3.05		0.4569	26.06 E	5.08	5.92 2.	2.71 87.26	6 5.53	30.86
MRM232	Group-C2a	Mimbres-42	Mimbres B/W Style III	Pottery	Murr		Rio Vista	LA 001082	1.82	38.24 (0.3336	46.58 6	6.10 2	2.48 2.	2.51 77.37	15.66	54.17
MRM233	Group-A	Mimbres-01	Mimbres B/W Style III	Pottery	Murr	NM R	Rio Vista	LA 001082	1.25	25.39 (0.4951	48.94 3	3.50	9.82 2.	2.61 82.66	1.73	4.47
MRM234	Group-B	Unas.	Mimbres B/W Style III	Pottery	MURR	NM	Rio Vista	LA 001082	0.00	59.37	0.6447	36.91	8.00	7.11 3.	3.97 98.16	6 2.13	22.30
MRM235	Group-A	Mimbres-01	Mimbres B/W Style III	Pottery	MURR		Rio Vista	LA 001082	2.05	60.13	0.5523	55.08 4	4.19 11	11.93 2.	2.82 96.67	7 2.60	
MRM236	Group-C1	Mimbres-23	Mimbres B/W Style III	Pottery	Murr	NM R	Rio Vista	LA 001082	4.11	37.31 (0.3766	26.84 5	5.79 4	4.00 2.	2.69 71.37	11.74	40.46
MRM237	Group-C1	Mimbres-23	Mimbres B/W Style III	Pottery	MURR	NM	Rio Vista	LA 001082	5.10	34.04	0.3594	26.25 5	5.35	3.34 2.	2.12 66.60	0 11.66	42.52
MRM238	Group-B2	Mimbres-02C	Mimbres B/W Style III	Pottery	Murr	NM R	Rio Vista	LA 001082	2.97	35.88	0.4807	19.93 3	3.63 2	2.91 2.	2.95 57.32	3.83	16.08
MRM239	Group-A	Mimbres-01	Mimbres B/W Style III	Pottery		J	Rio Vista	LA 001082	3.52				4.02 14		2.49 86.23	3 2.94	
MRM245	Group-A	Mimbres-01	Mimbres B/W Style II	Pottery	MURR	N X	Northgate	41EP00006	3.32	49.85 (0.5575	15.92	3.66 16	16.36 2.	2.17 76.91	1 2.12	4.59
MRM246	Group-B2	Mimbres-11	Mimbres B/W Style III	Pottery	MURR	N XL	Northgate	41EP00006	2.35	37.44 (0.5500	23.55 5	5.24 5	5.49 3.	3.37 73.11	1 8.84	40.06
MRM247	Group-B2	Mimbres-02A	Mimbres B/W Style III	Pottery	MURR	N X	Northgate	41EP00006	2.10	48.04 (0.5557	35.81 6	6.78	5.04 3.	3.69 96.16	80.6 9	34.18
MRM248	Group-C1	Mimbres-23	Mimbres B/W Style III	Pottery	MURR		Northgate	41EP00006	4.43	36.46	0.3758	32.88 6	6.01		2.46 72.53	3 12.48	42.28
MRM249	Group-B2	Mimbres-08	Mimbres B/W Style III	Pottery	MURR -		Northgate	41EP00006	3.63	34.76	0.4169	17.32 3	3.74 5				25.48
MRM250	Group-B	Unas.	Mimbres B/W Style III	Pottery	MURR	X	Northgate	41EP00006	3.52	38.73	0.5314	50.44	4.84	3.35 3.	3.54 68.87	17 4.98	14.74
MRM251	Group-B2	Mimbres-02A	Mimbres B/W Style III	Pottery	MURR	X	Northgate	41EP00006	1.88	45.28 (0.5567	32.11 7	7.18 5	5.44 3.	3.63 87.97	7 6.44	38.44
MRM252	Group-B2	Mimbres-02A	Mimbres B/W Style III	Pottery	MURR		Northgate	41EP00006	2.76	52.93	0.5862		8.43 4	4.70 3.	3.95 85.73		37.60
MRM253	Group-B2	Mimbres-02A	Mimbres B/W Style III	Pottery	MURR		Northgate	41EP00006	2.73	38.49 (
MRM254	Group-B2	Mimbres-02A	Mimbres B/W Style III	Pottery			Northgate	41EP00006	2.58		0.5290		6.87	5.74 3.	3.38 73.39	80.9 6	38.34
MRM255	Group-B	Unas.	Mimbres B/W Style III	Pottery	Murr -	TX	Northgate	41EP00006	4.07	37.82	0.4434	57.59 4	4.83 3	3.43 2.	2.71 66.34	6.90	22.28
MRM256	Group-A	Unas.		Pottery	MURR -		Northgate	41EP00006	0.00	_	-		1				
MRM257	Group-B2	Mimbres-02A		Pottery	MURR		Northgate	41EP00006	2.32				4.69 3				۲,
MRM258	Group-A	Mimbres-01	Mimbres B/W Style III	Pottery	MURR		Northgate	41EP00006	3.12								
MRM259	Group-A	Mimbres-01	Mimbres B/W Style III	Pottery			Northgate	41EP00006	2.07	_					_		
MRM260	Group-B	Unas.	Mimbres B/W Style III	Pottery			Northgate	41EP00006	4.28					3.73 2.			
MRM261	Group-B	Unas.	Mimbres B/W Style II	Pottery	MURR		Northgate	41EP00006	4.38								
MRM262	Group-B	Unas.	Mimbres B/W Style III	Pottery			Northgate	41EP00006	2.06								
MRM263	Group-B	Unas.	Mimbres B/W Style III	Pottery			Northgate	41EP00006	2.63								
MRM264	Group-A	Mimbres-01	Mimbres B/W Style III	Pottery	MURR -		Northgate	41EP00006	2.77				4.58 12	12.04 3.		9 2.60	
MRM265	Group-B2	Mimbres-02A	Mimbres B/W Style III	Pottery			Northgate	41EP00006	1.98				6.66		3.53 122.59		
MRM266	Group-B2	Mimbres-02A	Mimbres B/W Style III	Pottery	MURR -	N XI	Northgate	41EP00006	1.95	49.77 (0.5160	62.23	7.40 4	4.84 3.	3.47 109.16	6 5.36	37.57
MRM267	Group-A	Mimbres-01	Mimbres B/W Style III	Pottery	Murr -		Northgate	41EP00006	3.06	26.76	0.6055	53.54 4	4.09	9.81 3.	3.13 88.98	8 2.36	7.31
MRM268	Group-C1	Mimbres-21	Mimbres B/W Style III	Pottery	Murr -		Northgate	41EP00006	3.14			43.03 6	6.00 1	1.68 2.	74 84.18	8 11.48	41.90
MRM269	Group-B2	Mimbres-02A	Mimbres B/W Style III	Pottery	Murr -	TX N	Northgate	41EP00006	3.16	40.81	0.4797	46.25 5	5.09 4	4.71 3.	3.16 70.06	4.62	30.17
MRM272	Group-C1	Mimbres-21	Mimbres B/W Style II	Pottery			Huesito	41EP02321	4.62					1.72 2.			
MRM273	Group-C1	Mimbres-21	Mimbres B/W Style II/III	Pottery	Murr -	TX H	Huesito	41EP02321	2.45	39.05	0.3183 4	45.32 5	5.59 1	1.61 2.	2.39 84.02	11.36	45.45
MRM276	Group-D	El Paso Core	El Paso Polychrome	Pottery	MURR	X	Hueco Tanks	41EP00002	3.83	99.03	0.7700	76.85 15	15.70 3	3.75 6.	6.13 224.69	9 5.80	19.07

>	84.30	58.10	18.90	41.60	82.00	20.00	81.90	62.60	85.20	28.50	26.00	26.50	19.60	95.20	25.60	38.20	26.90	20.00	49.20	80.00	50.10	27.60	63.80	67.50	52.70	58.80	45.80	12.20	49.30	12.80	29.50	41.90	73.30	39.90	63.10	27.80	49.30	47.60	27.70	64.90	44.20	63.70	70.30	76.50
I	2886.0	2922.6	1375.7	1827.4	3119.5	1500.8	3134.3	2808.2	3948.2	1180.9	2812.3	2019.6	3631.4	3378.6	2064.8	999.1	1136.6	2989.3	3161.1	3435.3	3104.3	1524.5	2809.2	2604.2	2842.8	3889.4	2150.7	780.5	3168.6	1363.7	1724.1	2977.6	3848.8	1965.7	3129.5	1663.0	3118.6	3298.3	1702.0	3021.7	3362.9	3143.5	3037.3	6663.7
NA	20126.3	14807.2	12686.0	8790.8	11541.2	17981.9	12009.0	12513.4	21829.0	16521.6	15471.7	17247.5	11550.1	10071.7	12624.9	24752.2	12447.7	13323.7	12002.5	12146.6	8883.6	10314.6	13808.6	12374.4	10956.3	12879.9	14722.7	17275.1	10760.8	21085.5	15486.2	14751.3	13604.9	11425.4	14561.2	12002.5	11844.2	10873.4	15878.1	19226.1	12291.0	18960.0	19154.0	20914.2
MN	557.4	254.4	283.5	489.8	674.5	140.2	638.0	220.1	709.4	213.8	139.7	236.0	673.8	640.0	482.7	185.6	129.1	375.6	254.8	693.3	230.8	8.999	248.7	473.7	222.6	250.6	573.1	353.1	211.3	226.7	156.5	515.8	340.6	408.8	721.1	225.8	288.3	237.7	278.3	864.2	226.4	8.996	933.0	555.4
\prec	31762.5	28815.5	32295.6	43072.8	29454.6	29774.3	29590.5	28316.6	24723.9	25597.4	33731.8	26904.8	28620.0	27200.1	22497.8	27286.1	27312.1	31688.7	28649.1	27573.2	27423.2	28218.2	26330.6	30332.9	31321.1	28186.6	22555.5	22629.2	32801.8	25389.9	29001.7	25531.7	27079.5	20131.6	25902.3	33840.7	33861.5	31340.8	28564.8	26604.2	34871.8	30383.2	30237.2	43995.1
DY	24.240 3	6.100 2	3.160 3	3.231 4	3.628 2	2.040 2	3.648 2	3.786 2	4.136	2.338 2	6.420 3	2.875 2	3.959 2	4.021	3.379 2	2.902 2	1.746 2	4.201 3	5.460 2	3.819 2	2.691 2	3.945 2	4.801	5.554 3										_				5.207 3	3.123 2		4.526 3			9.006
CA	19388.6	14642.0	9445.3	29310.2	59782.1	5835.0	51085.4	8913.5	22827.8	5222.4	7318.3	9141.8	53646.6	63710.5	17089.2	3914.2	6599.5	8031.7	8256.7	41067.9	5285.1	14115.2	12265.0	12235.3	6877.4	11657.6	14223.6	6566.7	9549.0	4861.7	5761.5	22284.6	12554.5	15230.9	16143.6	9743.8	6945.5	7946.0	18709.0	16031.8	7616.4	26424.4	18053.5	14632.0
BA	1230.3	730.4	487.1	924.8	1322.2	863.7	1036.5	914.8	1401.8	376.8	591.7	1107.2	1142.8	1817.7	835.1	211.0	485.8	447.5	9.809	784.4	551.7	464.0	584.0	777.2	435.0	516.9	409.3	185.8	663.4	320.8	528.5	729.4	725.1	266.3	492.4	679.4	426.7	423.8	370.5	782.0	408.0	7.006	1106.8	1243.9
AL	93698.3	89023.2	106549.5	77135.2	79220.4	105335.1	83378.1	93037.2	02619.8	101142.5	83612.5	0.7957.0	78889.9	76112.9	77462.2	09836.2	93610.2	87360.4	91499.9	77644.4	84824.5	56842.9	89358.8	72850.9	91199.8	86930.0	74126.2	89141.8	86042.8	105523.1	03350.8	78609.8	86482.7	67902.4	82946.1	07660.4	82831.3	90791.2	10752.7	98607.5	76197.9			87639.9
ZR	375.8	212.2	186.9 1	153.1		204.7	157.5	174.9	175.4 1	143.0	199.1	157.7 1	154.1	145.4	106.8	164.2	156.4	191.5	151.8	126.9	136.2	9.86	192.4	187.2		171.3	113.5			173.7	_			107.1		150.0	203.0	160.7	170.3	152.1	174.1			206.0
NZ	101.8	122.1	58.4	53.4	123.2	53.0	64.1	58.0	109.1	57.0	56.9	54.6	78.0	106.7	50.2	63.6	65.7	62.2	58.6	71.0	47.2	51.4	62.6	62.8	64.8	69.4	50.2	84.5	66.2	72.0	38.7	58.6	27.7	42.0	105.8	59.4	54.5	59.6	63.1	97.6	45.9	101.8	106.8	9.99
TH	90.29	25.23	52.64	28.40		53.36		27.26	8.90	50.05	31.87	56.46	12.53	12.36	28.36	52.84	48.98	23.06	20.07	12.84	28.45	32.95	20.16	20.15						53.70		_	_				20.74	21.07	53.73	10.13	~			17.01
TA TB	3.0279 2.33	1.4716 0.71	2.2255 0.25	677 0.29	507 0.33	2.7498 0.14	0.9786 0.66	1.5423 0.72	0.7416 0.75	2.2489 0.19	1.6038 0.68	2.6674 0.22	481 0.36	0.9274 0.31	1.4962 0.39	2.5503 0.18	2.2536 0.15	1.7845 0.81	1.4820 0.63	1.0037 0.68	1.5450 0.23	1.5528 0.79	1.5707 1.17	1.5740 0.62	1.5802 0.65	1.4039 1.04	1.3268 0.29			771 0.35	-					2.2386 0.28	1.6122 0.63	1.5942 0.74	2.5337 0.24	0.7519 0.37	1.6555 0.38		_	2.8338 0.79
SR	148.4 3.0;	221.7 1.4	114.0 2.2.	233.2 1.5677	488.5 0.9507	321.5 2.7		148.6 1.5	620.3 0.7	98.5 2.2		131.4 2.60	637.4 1.0481	536.7 0.92	227.9 1.4		119.9 2.2	312.5 1.78	236.4 1.48	526.6 1.00	200.0 1.5	275.5 1.5!	296.4 1.5	377.7 1.5					216.8 1.6241		_			_				156.8 1.59	116.2 2.5;		195.4 1.6!			304.8 2.8;
SC	13.29 14	7.87	4.50 11	4.40 23		3.74 32		8.09 14	12.80 62	3.81	6.16 12	4.99 13	9.72 63	9.56 53	5.87 22	4.11 8	3.70 11	8.50 31	9.50 23		6.54 20	6.25 27	11.11	10.47 37			6.96 27		9.25 21								8.18 24	9.69 15	4.75 11	9.07 50	7.65 19			9.22 30
SB	1.0122 13	0.5950	0.7237			0.7117	1		0.4204 12	0.4045			0.7482	0.7895	0.3436	0.7489	0.7843		0.4997		0.5997	0.3383 (0.3939 17	1		1												0.5601						0.3989
RB	324.40	176.20		219.60		189.70	163.60		83.20	250.50	196.00	230.30	162.00	144.70	175.00	207.60	197.90	190.00	146.20	156.20	176.50	106.20	142.30	147.70	168.60													165.90		125.60	171.00			99.20
Z	66.2 3	0.0	0.0 251.90	0.0	30.1	0.0	64.0 1	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	27.8 1	0.0	0.0	0.0	0.0	0.0	34.1		0.0												0.0	0.0	0.0		0.0		42.1
土	12.85	97.9	6.39	6.10	4.87	7.34	5.00	6.48	5.94	2.77	09.9	6.57	4.88	5.24	5.42	6.39	5.59	8.75	7.57	2.06	89.9	5.46	8.13	7.91	8.40	7.77	5.52	5.11	8.01	7.12	7.10	6.11	6.36	5.62	5.94	6.46	8.96	7.87	7.74	6.33	8.38	6.41	96.9	17.19
FE	44254.5	24556.0	12717.5	18551.2	31851.2	8.6996	31116.2	26973.4	37593.8	11196.1	13177.4	16963.9	31550.1	32113.1	13339.8	13070.9	11014.5	23387.4	22453.6	29897.9	22238.8	14243.4	26921.2	25036.7	22410.6	26225.5	18804.2	9341.6	21486.4	10683.3	9387.4	24703.8	30043.5	14640.4	25950.2	13663.3	20888.6	23272.3	13712.5	34303.6	17662.4	31683.2		37213.8
EU	3.8672	1.5110	0.5443	0.7483		0.3899		0.9481	1.5823	0.4422		0.5712	1.1599	1.1447	0.6122	0.4978	0.3702	1.0418	1.2048	1.2378	0.6467	0.7096	1.3198	1.3881		1.3174					_							1.1057			0.9313	1.3000	1.3399	2.9639
CS	41.51	9.93	23.80	11.28	10.30	14.35	10.85	10.60	6.02	17.67	8.51	28.35	10.43	80.6	18.75	19.80	14.05	8.03	21.24	9.75	7.79	11.82	16.66		17.53	16.26	16.41	43.23	12.65						17.80			17.73			15.43		31.89	2.60
ANID	MRM224	MRM225	MRM226	MRM227	MRM228	MRM229	MRM230	MRM231	MRM232	MRM233	MRM234	MRM235	MRM236	MRM237	MRM238	MRM239	MRM245	MRM246	MRM247	MRM248	MRM249	MRM250	MRM251	MRM252	MRM253	MRM254	MRM255	MRM256	MRM257	MRM258	MRM259	MRM260	MRM261	MRM262	MRM263	MRM264	MRM265	MRM266	MRM267	MRM268	MRM269	MRM272	MRM273	MRM276

ANID	macro dri	macro arp Chem2012	CERAMIC TYPE	MATERIAL	SOURCE	STATE	SITE NAME	SITE NO	AS	LA	Π	ND	SM	n	YB CE	00	CR
MRM277	G-dno-D	El Paso Core		Pottery	MURR		Hueco Tanks	41EP00002	3.97	79.45	0.5951	_	12.38 4.	4.19 4.91	146	ω	20.56
MRM278	G-dnoJ9	El Paso-2	El Paso Polychrome	Pottery	MURR	X	Hueco Tanks	41EP00002	8.73	53.98	0.6026	10.99	10.09	3.71 4.8	4.88 97.69	10.46	69.63
MRM279	G-dnoJ9	El Paso-2	El Paso Bichrome	Pottery	MURR	ĭ	Hueco Tanks	41EP00002	6.73	43.65	0.5568	52.72	8.20 4.	4.00 3.0	3.66 83.53	8.40	57.06
MRM280	G-dno ₂	El Paso Core	El Paso Polychrome	Pottery	MURR	ĭ	Hueco Tanks	41EP00002	4.15	26.68	0.5252	60.01	9.29 4.	4.16 3.	3.48 117.07	12.02	31.11
MRM281	G-dno.D	El Paso-2	El Paso Brownware	Pottery	MURR	TX	North Hills I	41EP00355	7.46	71.61	0.5077			2.83 3.47			53.01
MRM282	G-dnoJ5	El Paso Core	El Paso Bichrome	Pottery	MURR	ĭ	North Hills I	41EP00355	6.47	70.78	0.6448				5.40 136.34		30.91
MRM283	G-dnoJ5	El Paso Core	El Paso Brownware	Pottery	MURR	ĭ	North Hills I	41EP00355	5.99	66.07	0.6247	89.39 11	11.30 4.	4.45 5.0	5.02 136.11	7.38	30.07
MRM284	G-dnoJ5	El Paso Core	El Paso Bichrome	Pottery	MURR	ĭ	North Hills I	41EP00355	4.86	64.24	0.5854		10.91		_		24.67
MRM285	Group-D	El Paso Core	El Paso Brownware	Pottery	MURR	TX	North Hills I	41EP00355	6.34	49.33	0.4357	57.05		5.38 2.8	2.89 97.03		23.57
MRM286	G-dno19	El Paso Core	El Paso Brownware	Pottery	MURR		Diablo 1	41HZ0491	5.35	52.11	0.4862	61.38	7.74 5.	5.11 3.	3.16 98.24	3.28	15.55
MRM287	G-dno19	El Paso Core	El Paso Brownware	Pottery	MURR	XT	Diablo 1	41HZ0491	11.65	53.64	0.5116	70.78	9.54 4.	4.04 3.	3.70 103.99	6.46	29.95
MRM288	G-dno ₂	El Paso Core	El Paso Brownware	Pottery	MURR	ĭ	Diablo 3	41HZ0493	7.37	61.32	0.5130	71.21	9.09	3.97 3.	3.40 99.99	6.31	29.10
MRM289	G-dno19	El Paso Core	El Paso Brownware	Pottery	MURR		Diablo 3	41HZ0493	6.21	66.04	0.5131	77.37 10		5.59 3.3	3.23 122.04	10.73	27.09
MRM290	G-dno19	El Paso Core	El Paso Brownware	Pottery	MURR	MN	Conejo	LA 091044	68.9	65.31	0.5716	70.85 10	10.89 5.	5.06 4.	4.14 127.02	89.9	27.40
MRM291	Gronp-D	El Paso Core	El Paso Brownware	Pottery	MURR		Conejo	LA 091044	6.67	58.34	0.5299	67.95	10.41 3.	3.91 3.9	3.90 107.68	6.49	29.89
MRM292	Gronp-D	El Paso Core	El Paso Brownware	Pottery	MURR		Conejo	LA 091044	5.70	76.75	0.6508	102.00 13	13.43 4.	4.17 5.3	5.38 152.40	4.34	24.35
MRM293	Gronp-D	El Paso Core	El Paso Brownware	Pottery	MURR		Conejo	LA 091044	5.91	78.38	0.6504		12.03 3.		5.30 143.45	8.14	31.35
MRM294	G-dno ₂ D	El Paso Core	El Paso Brownware	Pottery	MURR	MN	Conejo	LA 091044	7.37	76.29	0.6515		12.07 4.	4.86 4.9	4.51 141.34	19.8	31.69
MRM295	G-dnoJ9	El Paso Core	El Paso Brownware	Pottery	MURR	MN	Hill 100	LA 097088	6.87	60.19	0.5186	72.90 10	10.12 3.	3.70 3.71	71 107.93	5.28	24.60
MRM296	G-dno19	El Paso Core	El Paso Brownware	Pottery	MURR	MN	Hill 100	LA 097088	5.17	70.62	0.5460	80.30	11.42 3.	3.61 3.8	3.85 121.65	5.74	24.92
MRM297	G-dno19	El Paso Core	El Paso Brownware	Pottery	MURR	MN	Hill 100	LA 097088	8.10	76.71	0.5781	68.32 10	10.08 4.	4.03 4.71	71 136.42	6.31	30.61
MRM298	G-dno19	El Paso Core	El Paso Brownware	Pottery	MURR	MN	Hill 100	LA 097088	8.57	58.04	0.5261	63.85	9.45 4.	4.24 3.0	3.68 110.01	6.50	30.49
MRM299	G-dnoJ9	El Paso Core	El Paso Brownware	Pottery	MURR	NM	Hill 100	LA 097088	7.98	25.68							38.13
MRM300	Gronp-D	El Paso Core	El Paso Brownware	Pottery	MURR	XL	Turqoise Ridge	41EP00762	6.35	62.69	0.5432				3.95 121.20		27.96
MRM301	Group-D	El Paso Core	El Paso Brownware	Pottery	MURR	×	Turqoise Ridge	41EP00762	5.82	81.56	0.6017		12.77 4.		5.10 158.04		24.94
MRM302	G-dno.D	El Paso Core	El Paso Brownware	Pottery	MURR	XL	Turqoise Ridge	41EP00762	5.47	71.55	0.5025						22.91
MRM303	Group-D	El Paso Core	El Paso Brownware	Pottery	MURR	×	Turqoise Ridge	41EP00762	7.30	76.55	0.6259				_		27.61
MRM304	Group-D	El Paso Core	El Paso Brownware	Pottery	MURR		Turqoise Ridge	41EP00762	7.84	60.97	0.6035	74.77 10		5.24 4.21			28.63
MRM305	Group-D	El Paso Core	El Paso Brownware	Pottery	MURR		Roth	LA 073942	6.77	84.51	0.6208	101.18 14		4.71 5.	5.10 146.33		23.56
MRM306	Gronp-D	El Paso Core	El Paso Brownware	Pottery	MURR		Roth	LA 073942	6.30	56.57	0.4635					_	24.55
MRM307	G-dnoJ9	El Paso Core	El Paso Brownware	Pottery	MURR		Roth	LA 073942	4.98	73.77	0.6185					_	27.19
MRM308	Group-D	El Paso Core	El Paso Brownware	Pottery	MURR		Roth	LA 073942	3.74	76.84	0.5186	_					25.07
MRM311	G-dnoJ9	El Paso Core	El Paso Brownware	Pottery	MURR	NZ NZ	Los Tules	LA 016315	7.34	65.33	0.5626	_		_	·-		31.18
MRM312	G-dnoJ9	El Paso Core	El Paso Brownware	Pottery	MURR	N N	Los Tules	LA 016315	5.76	47.82	0.3864						22.25
MRM313	Group-D	El Paso Core	El Paso Brownware	Pottery	MURR	MN	Los Tules	LA 016315	6.15	80.64	0.7186		15.42 3.				25.65
MRM314	Group-D	El Paso Core	El Paso Brownware	Pottery	MURR	M	Los Tules	LA 016315	6.91	72.85	0.5512						30.01
MRM315	Group-D	El Paso Core	El Paso Brownware	Pottery	MURR	M	Tortugas	LA 079550	5.34	65.23	0.4661	1		7.09 3.		1	20.99
MRM318	Gronp-D	El Paso Core	El Paso Polychrome	Pottery	MURR	ĭ	Northgate	41EP00006	7.60	58.47	0.5512						28.48
MRM319	Gronp-D	El Paso Core	El Paso Brownware	Pottery	MURR	TX	Northgate	41EP00006	6.23	61.25	0.5649	51.33		3.77 3.9		5.37	24.78
MRM320	Gronp-D	El Paso Core	El Paso Bichrome	Pottery	MURR	TX	Northgate	41EP00006	6.61	55.48		63.31		4.89 3.9	3.52 105.55	5.95	27.12
MRM321	Gronp-D	El Paso Core		Pottery	MURR	XI	Northgate	41EP00006	7.96	64.33	0.5992			4.15 4.			33.86
MRM322	Gronp-D	El Paso Core		Pottery	MURR		Northgate	41EP00006	4.79	84.05		`			-		26.88
MRM323	Gronp-D	El Paso Core		Pottery	MURR		Divad	LA 096687	5.53	64.18	0.5950						26.91
MRM324	Group-D	El Paso Core	El Paso Brownware	Pottery	MURR	NM	Divad	LA 096687	96.98	69.69	0.5805	78.89 11	11.37 4.	4.58 4.0	4.60 141.43	8.88	27.43

1/342.0 6243.7 100.00
32586.0 366.3 11056.0 29752.5 649.5 17542.0
10073.0 5.791 17752.3 6.419
85913.8 828.6 177
7.5 1.9629 0.73 19.60
0.6458 10.93 307.5 0.5562 9.22 322.0
9.61 0.0 151.20 0.6458 14.13 44.3 113.10 0.5562 18 08 0.0 121.00 0.5562
5.06 1.6034 38099.6 9.6 3.56 1.7501 38475.6 14.7 4.05 2.0266 47677.5 18.0
3.56 4.05 3.08

ANID	macro_grp	macro_grp Chem2012	CERAMIC TYPE	MATERIAL	SOURCE	STATE	SITE_NAME	SITE_NO	AS	ΓΑ	ΓΩ	ND	SM	n	YB	CE CO	CR
MRM326	Group-D	El Paso Core	El Paso Bichrome	Pottery	MURR	MZ	Divad	LA 096687	7.57	73.82 0	0.5952	96.35 13	13.79 4	4.48 5.	5.04 142.63	53 6.05	25.99
MRM328	G-dno-D	El Paso Core	El Paso Brownware	Pottery	MURR	ĭ	Huesito	41EP02321	19.6	55.46 0		64.10 9	9.21 4	4.62 3.	3.84 103.72	72 5.08	31.35
MRM329	Group-D	El Paso Core	El Paso Brownware	Pottery	MURR	X	Huesito	41EP02321	9.18	56.53 0	0.5322 (65.34 9	9.45 3	3.82 3.	77 114.14	4 7.83	37.87
MRM330	Group-D	El Paso Core	El Paso Brownware undif.	Pottery	MURR	X	Huesito	41EP02321	10.60		0.5531 (9.76 3	3.63 3.	3.74 110.84		39.87
MRM332	Gronp-D	El Paso Core	El Paso Bichrome	Pottery	MURR	MN	Sandcliffe		12.44			`			3.65 130.23	1	
MRM334	G-dno-D	El Paso Core	El Paso Polychrome	Pottery	MURR	M	Sandcliffe		5.87						_		
MRM340	Group-B	Unas.	Mimbres B/W Style II	Pottery	MURR	ĭ	Milner Farm	41EP03022	3.58	39.43 0			5.44 4		2.81 75.89		
MST061	Group-C2a	Mimbres-49A	Playas Plainware	Pottery	MURR	M	Old Town	LA 001113	2.33								
MST088	Group-C2a	Mimbres-49A	Playas Redware	Pottery	MURR	Σ	Old Town	LA 001113	2.87				9.06		_		
MST100	Group-C2a	Mimbres-49A	Playas Plainware	Pottery	MURR	M	Old Town	LA 001113	5.46	37.76 0						10.06	
MVP0001	Group-B2	Mimbres-08	Mimbres B/W Style III	Pottery	MURR	MN	Rock House	LA 001118	3.34	33.00 0	0.4984	17.35 3	3.44 5	5.32 2.	2.70 66.45	19.08	27.97
MVP0002	Group-B	Unas.	Mimbres Polychrome	Pottery	MURR	M	Pruitt Ranch	LA 001117	1.62	41.43 0	0.5582	26.85 4	4.94 4	4.08 3.	3.39 81.03	3 9.03	31.61
MVP0003	Group-C2a	Mimbres-42	Mimbres B/W Style II	Pottery	MURR	MN	Rock House	LA 001118	1.37	37.88 0	0.2910	29.16	5.79 1	1.52 2.	2.33 79.16	17.37	59.24
MVP0004	Group-B2	Mimbres-02A*	Mimbres B/W Style III	Pottery	MURR	MN	Perrault	LA 018891	6.23	42.14 0	0.5274	27.27 5	5.93 3	3.14 3.	3.56 88.96	11.00	39.16
MVP0005	Group-B	Unas.	Mimbres B/W Style II	Pottery	MURR	M	Goforth	Alum Mt:8:1(C	6.54	60.34 0		46.87	8.66 3	3.18 4.	4.13 113.95	5.15	13.24
MVP0006	Group-B1	Mimbres-04A	Mimbres B/W Style III	Pottery	MURR	M	McSherry	LA 015050	3.46	45.56 0		33.76 6	6.51 4	4.19 3.	3.28 96.67	7 9.16	
MVP0009	Group-B1	Mimbres-04A	Mimbres B/W Style III	Pottery	MURR	M	Ranger Station	LA 005066	2.34				7.44 4				25.88
MVP0011	Group-B	Unas.	Mimbres B/W Style III	Pottery	MURR	MN	Goforth	Alum Mt:8:1(C	2.39	39.12 0	0.4903		4.79 5	5.44 2.	2.82 77.00		21.93
MVP0012	Group-B	Unas.	Mimbres B/W Style III	Pottery	MURR	M	McSherry	LA 015050	2.97	48.77 0	0.5659	37.37	7.34 6	6.40 3.	3.65 85.46	15.39	30.44
MVP0013	Group-A	Mimbres-01	Mimbres B/W Style III	Pottery	MURR	NM	Mitchell	LA 012076	1.79	54.18 0			4.79 9		2.97 97.64		7.91
MVP0014	Group-B2	Mimbres-02A	Mimbres B/W Style III	Pottery	MURR	MN	McSherry	LA 015050	2.80	67.25 0	0.6707	54.05	9.03 3	3.29 5.	5.17 105.35	16.20	40.87
MVP0015	Group-A	Mimbres-01	Mimbres B/W Style III	Pottery	MURR	MN	Ranger Station	LA 005066	1.34	62.29	0.6646	20.40	4.70 11	11.72 3.	3.10 102.70	10.75	8.45
MVP0016	Group-B	Unas.	Mimbres B/W Style III	Pottery	MURR	MN	Mitchell	LA 012076	1.75	43.33 0	0.4825			4.76 3.	3.63 83.17	13.08	29.71
MVP0017	Group-B1	Mimbres-04B	Mimbres B/W Style III	Pottery	MURR	NM	Pruitt Ranch	LA 001117	2.34							1	
MVP0018	Group-B	Unas.	Mimbres B/W Style III	Pottery	MURR	Σ	Mitchell	LA 012076	1.63								
MVP0019	Group-B2	Mimbres-02A	Mimbres B/W Style III	Pottery	MURR	M	Pruitt Ranch	LA 001117	2.68								
MVP0020	Group-B	Unas.	Mimbres B/W Style III	Pottery	MURR	M	Pruitt Ranch	LA 001117	1.43						3.15 91.44		
MVP0021	Group-B1	Mimbres-04A		Pottery	MURR	M	Pruitt Ranch	LA 001117	2.83						_	_	
MVP0022	Group-B1	Mimbres-04A		Pottery	MURR	M	Mitchell	LA 012076	2.31			37.07					
MVP0023	Group-A	Mimbres-01	Mimbres B/W Style III	Pottery	MURR	M	Rock House	LA 001118	1.98				_				
MVP0024	Group-B	Unas.	Mimbres B/W Style II/III	Pottery	MURR	¥	Pruitt Ranch	LA 001117	4.55	_						_	
MVP0025	Group-C2a	Mimbres-49A	Mimbres B/W Style III	Pottery	MURR	Σ	Ranger Station	LA 005066	2.51								
MVP0026	Group-B2	Mimbres-02A		Pottery	MURR	M	McSherry	LA 015050	1.76	41.44 0				5.43 3.		12.72	
MVP0027	Group-B1	Mimbres-04A		Pottery	MURR	M	site uncertain		3.29		<u> </u>				_		
MVP0028	Group-B1	Mimbres-04A	Mimbres B/W Style III	Pottery	MURR	M	McSherry	LA 015050	1.28	31.64 0	0.4171 2	24.93 5	5.06 3	3.63 2.	2.70 68.24	9.55	19.72
MVP0029	Group-B1	Mimbres-04A	Mimbres B/W Style III	Pottery	MURR	M	Pruitt Ranch	LA 001117	3.36		0.5974	43.22 7		4.92 3.	3.69 113.94	9.86	21.31
MVP0030	Group-B1	Mimbres-04B	Mimbres B/W Style III	Pottery	MURR	MN	Pruitt Ranch	LA 001117	2.38	49.45 0	0.5617	36.02 6		6.01 3.	3.48 88.14	13.18	24.99
MVP0031	Group-A	Mimbres-01	Mimbres B/W Style III	Pottery	MURR	MN	McSherry	LA 015050	2.16	48.73 0	0.6433	17.27	3.99 12	12.60 2.	2.95 83.84	84 8.22	8.48
MVP0032	Group-B1	Mimbres-04A	Mimbres B/W Style III	Pottery	MURR	MN	Mitchell	LA 012076	1.44	34.34 0	0.4605 2	28.81	5.32 3	3.58 2.	2.85 76.77	7 10.38	20.70
MVP0033	Group-B	Unas.	Mimbres B/W Style III	Pottery	MURR	NM	McSherry	LA 015050	3.28	58.84 0				3.90 4.	4.60 113.46	17.13	
MVP0034	Group-B2	Mimbres-11	Mimbres B/W Style III	Pottery	MURR	M	Pruitt Ranch	LA 001117	3.52	33.86 0		23.92 4	4.80 5	5.21 3.	3.22 73.53	3 21.75	45.87
MVP0037	Group-C1	Mimbres-21	Mimbres B/W Style II	Pottery	MURR	M	Rock House	LA 001118	1.81								
MVP0038	Group-B	Unas.	Mimbres B/W Style I	Pottery	MURR	M	WS Ranch	LA 003099	3.32								
MVP0039	Group-B	Unas.	Mimbres B/W Style III	Pottery	MURR	MN	Mitchell	LA 012076	1.58	37.76 0	0.4163	31.10	5.75 2	2.82 2.	2.54 79.52	13.66	60.85

V II	.0 95.30	.0 85.60		.7 93.90	.3 136.50	.4 73.50	.6 62.30	.7 61.14	.0 87.93	.5 88.89	.2 36.18	.7 47.34	.9 79.04	.9 68.77	.6 39.07	.6 41.63	.8 55.89	.4 45.69	1.5 47.60	.5 30.03	.9 67.48		90.79 8.	.2 53.14	.3 41.47	6 59.72	.4 49.81				1 62.34				.4 52.06	.5 49.25	7 25.81	.5 41.37		.9 59.81	.7 47.58	F 112 81
A		1 3844.0			8 5932.3	9 4500.4	0 2856.6	5 3327.7	5 6415.0	0 3832.5	5 2986.2	0 3113.7	2 4828.9	0 3324.9	5 2798.6	8 3162.6	0 3418.8	3 3099.4	3 3290.5	3 2033.5	3 2662.9	8 1065.8	8.6168	4 3245.2	3 3093.3						7 2468.7				5 2751.4	5 3145.5	9 1532.7	0 3477.5	8 2801.9	0 3027.9	6 2173.7	A C772 E
NA	1 17022.8	11755.	_		16236.8	0 20754.9	0 14440.0	8 14417.5	7 14847.5	_	6 9720.5	9 13111.0	2 23715.2	8 13146.0	5 19802.5	3 19789.8	8 13413.0	1 11916.3	8 15327.	7 16309.3	8 12815.3		13299.6	2 14198.4	3 14695.3	9 12811.9	٠ ا				4 14470.7 9 16456.4		_		5 15896.5	11980	6 14023.9	8 17281.0		11172.	6 20178.6	,,,,,,,,,,,,,,,,,,,,,,,,,,,,,,,,,,,,,,,
MM	5 465.1		0 487.5	5 520.1	0 505.6	5 396.0	1 415.0	6 474.8	1 730.7	1	5 200.6	6 298.9	8 684.2	8 318.8	7 566.5	9 289.3	5 345.8	3 398.1	0 324.8	0 159.7	9 296.8	7 106.4	5 276.2	3 232.2	5 360.3						5 1248.4	+			5 389.5	9 162.0	5 244.6	4 236.8		0 918.9	7 1155.6	
	30278.5				24659.0	32218.	30111.1	35408.6	29161.1	31122.4		26286.6	25981.8	35388.8	36231.7		26089.5	34388.3	28948.0	35677.0	29883.9	25558.7	28796.6	30477.3	30087.5	27250.4					22388.5				30656.6	31758.9	32048.6	28055.4		34412.0	28914.7	
DY	8.204	5.682		6.345	6.100	4.953	4.393	4.101	6.040	3.884	3.043	3.401	3.765	4.122	5.981	4.922	6.041	3.659	5.343	3.198	7.160	3.081	4.928	4.210	4.812	5.021					3.407				5.539	5.278	2.581	3.943		3.931	3.886	
CA	15751.7	15207.3	12124.7	16279.5	10817.7	11102.0	14022.0	14060.5	16460.0	14601.0	7097.2	11633.9	19593.8	17693.5	10671.1	12219.1	14449.1	8161.3	14027.4	14560.9	15406.9	5114.6	9351.6	10416.9	12939.9	11879.9	14861.7	12919.7	10929.5	8208.9	20055.0	13228.0	12329.2	11968.7	15430.8	9817.8	5869.5	12290.8	11977.5	9605.6	29222.9	1
BA	1082.3	1090.8	915.7	1616.6	698.4	576.9	720.7	797.3	671.9	921.1	445.3	753.3	1037.0	551.1	1398.2	890.1	752.7	667.3	655.1	510.7	604.6	332.3	9.868	498.9	736.2	533.6	1017.4			274.1	430.6	609.3	704.4	_	921.8	763.6	269.2	1080.1	1105.7	484.8	929.4	
AL	87911.0	91335.9	103073.2	95830.5	102037.4	89608.0	73999.0	79154.7	83112.5	86951.7	91265.5	91480.7	98844.0	76249.6	89144.4	78096.6	99544.3	79006.0	89112.1	106020.0	87357.5	100980.5	87510.7	88592.6	88395.4	89229.7	81266.1	87089.5	92950.3	90197.4	74821.7	92229.1	90323.9	89366.8	88965.9	90035.1	96045.5	87725.8	96048.0	83260.1	84355.5	
I ZR	302.6	306.7			385.0	330.4	217.8	176.5	215.9	152.2	3 236.1	159.8	156.8	219.7	255.3	219.4	198.7	1 218.5	186.8	179.9	179.0	3 171.5	230.0	149.9	194.7	184.0			_		125.4				192.0	508.6	154.7	236.4		170.8	148.3	
NZ	88.7	62.1					96.1	87.0	9.66	104.6	48.8	71.9	158.2	70.9	79.2		79.0	45.4	53.7	60.4	79.5	49.8	59.1	63.6	6.09	58.6					58.4					49.2	50.0	57.9		62.5	93.7	
프	3 21.10	23.24			1 29.13	25.14		13.38	10.87	13.00	28.30	31.49	10.6	17.66	17.32	3 22.63	17.83	3 29.35	1797	1 48.17	3 20.46	51.10	3 21.07		19.56						21.12				1 21.61	29.08	8 47.18	19.18		7		
4 TB	5 0.83	3 1.00	5 1.55	8 1.26	5 1.24	99.0 6	1 0.53	6 0.85	9 1.22	2 0.75	9 0.40	4 0.63	69.0 6	6 0.78	8 1.03	5 0.78	6 0.95	0 0.58	1 0.89	9 0.50	1 1.18	9 0.47	3 0.83	4 0.70	0 0.72	7 0.82		5 0.95			8 0.57	_		0.63	1.04	5 0.90	4 0.38	2 0.64		3 0.58	1 0.65	
TA	2.9025	2.6043			2.8125	2.8849	1.3071	1.1306	1.1739	1.0282	1.5679	1.6684	0.7489	1.3486	1.1438	1.4425	1.3206	1.5640	1.8111	2.0729	1.3281	2.4359	1.5043	1.5834	1.3610						1.4238			1.	1.4016	1.5875	2.3224	1.6922		1.6393	0.6501	0000
SR	366.6	373.8	307.4	290.0	228.1	309.9	240.3	402.8	372.4	373.8	117.9	224.0	748.3	315.2	200.0	303.3	220.1	208.0	295.4	216.0	462.0	97.5	261.7	183.2	304.0	323.8	206.4	298.5	221.6	92.3	377.3	391.6	264.9	308.8	319.7	205.5	110.2	347.2	226.7	228.2	486.8	
SC	9.50	60.6	10.41	11.09	11.18	8.40	86.9	9.57	13.45	10.84	19.9	8.28	12.44	7.81	8.65	6.34	9.92	5.84	8.98	4.05	11.86	4.37	8.46	7.42	6.82	10.77	6.17	7.47	8.26	3.77	6.34	10.10	8.27	6.15	7.54	7.18	4.39	6.84	10.37	8.09	5.44	1
SB	0.4127	0.6419	0.8972	0.9447	0.7525	0.4521	0.4845	0.4947	0.4432	0.6202	0.6491	0.4077	0.3629	1.1567	0.5377	1.0003	0.3658	0.4617		0.7488	0.4989	0.8045	0.3872		0.3552	0.4598		0.3900	0.3779		0.4755			0.3009	0.3813		0.5584	0.3134	0.6353	0.7865	0.8876	
RB	107.40	138.40	166.30	130.50	108.50	134.90	153.80	140.50	114.27	110.83	196.72	206.14	84.89	171.34	147.06	157.87	129.45	190.09	166.76	186.11	134.80	197.86	153.45	183.63	141.73	155.87	185.34	138.99	144.02	205.19	166.18	163.68	146.43	139.50	150.02	160.55	236.44	131.06	144.11	209.34	111.95	0,000
Z	0.0	0.0	37.2	26.2	0.0	22.8	29.6	35.4	39.7	39.6	0.0	0.0	78.4	0.0	35.3	18.9	0.0	0.0	0.0	0.0	28.2	0.0	0.0	0.0	0.0	0.0	0.0		0.0	0.0	0.0	0.0		0.0	0.0	0.0	0.0	0.0	0.0	31.7	32.6	0
生	11.64	11.52	10.91	10.34	11.07	12.65	7.18	6.23	9.29	6.48	9.22	7.22	6.40	8.33	10.50	7.91	7.06	9.12	7.50	7.30	6.88	6.58	9.19	98.9	8.81	8.36	6.88	8.24	6.48	7.31	6.57	7.13	7.31	7.76	7.56	7.72	6.47	10.23	9.81	7.46	19.9	000
H	40197.8		44078.9	7	53527.7	37394.7	22891.2	31788.0	45702.0	38746.1	21806.3	22633.9	40617.6	23650.3	22556.9	19377.5	30913.6	19771.6	23210.7	11144.1	29844.9	0.5756 10343.8	28541.7	23286.9	21276.1	24302.1	18251.2	22296.2	26650.1	12918.5	20939.0	24516.1	21469.7	22030.9	22826.4	22341.3	13267.4	23490.0	26092.2	25162.5	23599.8	1000
EN	2.0506		1.7816		2.0020	1.5804	1.1183	1.2113	1.7328	1.2446	0.5805	0.8964	1.5187	1.1307	1.8961	1.2979	1.3529	0.8783	1.2721	0.6596	1.6766).5756	1.2867	1.0262	1.1594	1.2209					0.8078	_			1.5560	1.1822	0.5005	1.0772		0.9136	1.1689	!
CS	3.21		5.87		3.57	4.18	9.30	4.07	6.63	5.04	7.96	7.33	5.50	33.27	3.62	4.06	4.84	6.27	15.47	11.31	18.75	17.63		9.00	5.03	22.24			4.98		16.25 (4.82	4.99	16.53 (5.07		7.71	12.37	1
ANID	MRM326	MRM328	MRM329	MRM330	MRM332	MRM334	MRM340	MST061	MST088	MST100	MVP0001	MVP0002	MVP0003	MVP0004	MVP0005	MVP0006	MVP0009	MVP0011	MVP0012	MVP0013	MVP0014	MVP0015	MVP0016	MVP0017	MVP0018	MVP0019	MVP0020	MVP0021	MVP0022	MVP0023	MVP0024	MVP0026	MVP0027	MVP0028	MVP0029	MVP0030	MVP0031	MVP0032	MVP0033	MVP0034	MVP0037	

ANID	macro_grp	Chem2012	CERAMIC TYPE	MATERIAL	SOURCE	STATE	SITE_NAME	SITE_NO	SY	ΓA	n	QN	SM	n	YB CE	CO =	CR
MVP0040	Group-B2	Mimbres-11	Mimbres B/W Style III	Pottery	MURR		Pruitt Ranch	LA 001117	5.94		0.4757 20	20.51	4.65 4.	4.62 3.9	3.90 68.51	_	44.83
MVP0041	Group-B1	Mimbres-04A	Mimbres B/W Style II	Pottery	MURR	MN	Galaz	LA 000635	1.63	49.61 0.5	0.5878 40	40.17	7.81 4.	4.82 3.0	3.66 97.74	4 9.23	20.28
MVP0042	Group-B	Unas.	Mimbres B/W Style III	Pottery	MURR	MN	Pruitt Ranch	LA 001117	1.87	85.00 0.3	0.3969 3!	35.96 5	5.85 3.	3.56 2.0	2.68 77.54	4 6.74	24.53
MVP0043	Group-B2	Mimbres-08	Mimbres B/W Style III	Pottery	MURR	MN	Galaz	LA 001679	5.26	36.49 0.4	0.4819	18.51	4.08 5.	5.55 2.0	2.61 69.03	3 14.51	24.13
MVP0044	Group-B1	Mimbres-04A	Mimbres B/W Style III	Pottery	MURR	MN	Pruitt Ranch	LA 001117	4.19	48.36 0.5	0.5728 47	42.21	7.95 4.	4.11 3.9	3.95 102.86	6 9.97	20.80
MVP0045	Group-B2	Mimbres-02A	Mimbres B/W Style III	Pottery	MURR	MN	Pruitt Ranch	LA 001117	1.82	41.72 0.5	0.5977 30	30.43 5	5.38 4.	4.69 3.53	53 97.18	8 13.27	39.51
MVP0046	Group-B1	Mimbres-04B	Mimbres B/W Style III	Pottery	MURR	MN	Pruitt Ranch	LA 001117	3.20	57.15 0.0	0.6494 47	42.78 8	8.43 6.	6.20 4.7	4.14 98.73	3 11.48	28.15
MVP0047	Group-B	Unas.	Mimbres B/W Style III	Pottery	MURR	MN	Pruitt Ranch	LA 001117	3.82	32.58 0.3	0.3711 28	28.17 5	5.26 2.	2.92 2.3	2.29 67.10	0 17.25	59.48
MVP0048	Group-C2a	Mimbres-49A	Mimbres B/W Style III	Pottery	MURR	MN	Pruitt Ranch	LA 001117	3.02	43.95 0.4	0.4099 4.	42.68 6	6.72 2.	2.59 2.77	77 78.33	3 17.30	59.75
MVP0049	Group-B	Unas.	Mimbres B/W Style III	Pottery	MURR	MN	Pruitt Ranch	LA 001117	2.59	40.05 0.5	0.5440 28	28.97 5	5.22 6.	6.22 3.0	3.03 90.34	4 13.96	26.27
MVP0050	Group-B	Unas.	Mimbres Corrugated	Pottery	MURR	MN	Pruitt Ranch	LA 001117	1.38	32.35 0.3		20.00	4.36 5.	5.68 2.21	21 69.41	1 15.07	30.19
MVP0051	Group-B	Unas.	Mimbres Corrugated	Pottery	MURR	MN	Pruitt Ranch	LA 001117	2.98	39.29 0.4	0.4087 28	28.39 5	5.07 4.	4.94 2.81	81 73.31	1 8.05	12.58
MVP0053	Group-B	Unas.	Mimbres B/W Style III	Pottery	MURR	MN	Pruitt Ranch	LA 001117	2.41	35.38 0.4	0.4724 2	27.20 5	5.03 3.	3.28 2.8	2.85 71.20	0 6.51	13.05
MVP0054	Group-B1	Mimbres-04A	Mimbres B/W Style III	Pottery	MURR	MN	Pruitt Ranch	LA 001117	3.54	42.00 0.5	0.5279 3	39.06	7.18 4.	4.32 3.2	3.26 97.28	8 23.91	25.79
MVP0055	Group-B2	Mimbres-08	Mimbres B/W Style III	Pottery	MURR	MN	Pruitt Ranch	LA 001117	3.71	34.18 0.3	0.3839 18	18.80	3.75 5.	5.87 2.4	2.45 62.11	1 19.54	23.21
	Group-B1	Mimbres-04B	Mimbres B/W Style III	Pottery	MURR		Pruitt Ranch	LA 001117	3.47				9.25 6.		71 101.57		29.04
	Group-B1	Mimbres-04A	Mimbres B/W Style III	Pottery	MURR		Pruitt Ranch	LA 001117	2.72	48.24 0.5	0.5514 3.	32.55 6		5.98 3.71		0 11.93	28.23
	Group-B2	Mimbres-11	Mimbres B/W Style III	Pottery	MURR		Pruitt Ranch	LA 001117	3.12	33.93 0.4		27.22 4				0 19.79	43.90
	Group-B2	Mimbres-08	Mimbres B/W Style III	Pottery	MURR		Pruitt Ranch	LA 001117	2.28				3.90 5.				21.51
	Group-A	Mimbres-01	Mimbres B/W Style III	Pottery	MURR		Pruitt Ranch	LA 001117	1.94				,	11.06 3.21		_	7.42
	Group-B	Unas.	Mimbres B/W Style III	Pottery	MURR		Mitchell	LA 012076	2.22				7.04 3.	3.68 3.3	3.33 86.02		35.50
	Group-B1	Mimbres-04C	Mimbres B/W Style III	Pottery	MURR		Mitchell	LA 012076	2.70	46.54 0.5	0.5356 3	37.28	7.60 3.		3.44 90.35	5 13.50	30.36
	Group-B	Unas.	Mimbres B/W Style Indeter. Pottery	er. Pottery	MURR		Mitchell	LA 012076	7.20						3.63 100.30	0 11.88	15.95
	Group-B	Unas.	Mimbres B/W Style III	Pottery	MURR		Mitchell	LA 012076	2.06								57.81
	Group-C2a	Mimbres-49A	Mimbres B/W Style III	Pottery	MURR		Mitchell	LA 012076	2.35				_			8 12.13	39.01
	Group-B1	Mimbres-04A	Mimbres Corrugated	Pottery	MURR		Mitchell	LA 012076	1.47								19.93
	Group-C2a	Mimbres-49A	Mimbres B/W Style III	Pottery	MURR		Mitchell	LA 012076	2.84				5.88 2.				54.06
_	Group-A	Mimbres-01	Mimbres B/W Style III	Pottery	MURR		Mitchell	LA 012076	3.58				_				11.18
	Group-B	Unas.	Mimbres B/W Style III	Pottery	MURR		Mitchell	LA 012076	4.06	_			- 1				71.68
	Group-A	Mimbres-01	Mimbres B/W Style III	Pottery	MURR		Mitchell	LA 012076	96.0				1		_		6.21
	Group-C2	Unas.	Mimbres B/W Style III	Pottery	MURR		Mitchell	LA 012076	2.78								49.62
MVP0074	Group-B	Mimbros 04P	Mimbres B/W Style III	Pollery	MURK		Milchell	LA 012076	2.81	40.20 0.4	0.4314 3	30.04	0.09 3.	3.15 2.0	2.08 94.04	0.001	16.10
	Group-B I	Ulhac	Mimbres B/W Style III	Pottery	MIPP		Cow Springs Draw		2.76								20.22
	Group-A	Unas	Mimbres Classic Corrugated Pottery	terPotterv	MIRR		Cow Springs Draw		4.50								18.02
	Group-B2	Mimbres-02A	Mimbres B/W Style III	Pottery	MURR		Ebv	LA 015016	2.41	_							38.05
	Group-A	Mimbres-01	Mimbres B/W Style III	Pottery	MURR		Eby	LA 015016	2.49					12.80 2.8		8 36.47	7.74
MVP0080	Group-B1	Mimbres-04A	Mimbres B/W Style III flare r Pottery	re i Pottery	MURR	MN	Eby	LA 015016	4.61	68.30 0.5	0.5551 5	55.18 10	10.34 4.	4.54 4.77	77 111.49	9 22.07	26.34
	Group-B2	Mimbres-02A	Mimbres B/W Style III	Pottery	MURR		Eby	LA 015016	1.39	46.37 0.4				4.15 3.6		0 12.60	36.81
	Group-C2	Unas.	Mimbres B/W Style III	Pottery	MURR		Eby	LA 015016	1.00				` '				27.92
	Group-C2a	Mimbres-49A	Three Circle R/W	Pottery	MURR		Eby	LA 015016	3.74		0.3093 2		`	1.86 2.27		7 14.92	67.10
	Group-B1	Mimbres-04A	Mimbres B/W Style III	Pottery	MURR		Eby	LA 015016	3.41								18.30
	Group-C2b	Mimbres-41	Mimbres B/W Style III	Pottery	MURR		Eby	LA 015016	1.56							_	24.43
MVP0086	Group-B	Unas.	Mimbres B/W Style III	Pottery	MURR	ΣN	Eby	LA 015016	3.52	57.10 0.5	0.5123 3:	33.67 6	6.47 4.	4.00 3.5	3.54 109.65	5 8.10	31.22

>	46.10	49.24	37.60	52.22	51.79	45.70	50.12	106.16	88.13	52.86	59.78	33.84	28.58	46.03	50.27	58.94	44.35	68.73	46.71	27.00	63.07	62.01	50.17	79.20	82.70	48.50	91.89	12.26	92.26	30.71	64.45	88.90	48.23	32.08	36.13	64.57	24.61	90.99	55.36	70.48	77.21	22.65	75.38	61.68
I	3421.0	3387.8	3010.4	2850.5	2405.9	3479.0	3012.1	5315.5	4321.9	3574.5	2972.3	2102.1	1339.8	4287.7	2591.5	2876.3	3338.1	4169.8	2810.6	1296.8	3883.1	3598.1	3487.5	5101.6	5348.2	2863.1	4581.1	722.6	4898.4	1177.6	4141.7	4917.3	3960.3	3159.4	2956.9	4707.5	4806.9	4492.0	5019.8	4283.0	4761.8	4365.9	4489.1	3270.0
NA	11596.7	18229.9	17106.0	10042.2	15811.8	13283.0	11363.4	15400.7	16464.8	12644.7	13225.6	16520.0	13805.1	14407.1	10935.8	10172.3	13502.2	11714.5	12545.1	19791.0	15618.1	16523.8	17328.2	14040.1	19864.5	18331.7	16053.9	10898.5	14369.4	13407.8	17868.4	16439.2	12192.3	14828.2	1849.8	13657.3	16958.4	12134.0	14941.3	17662.2	15382.3	17848.9	18674.5	15108.2
MN	1257.7	624.1	423.2	211.3	1004.7	279.4	475.0	548.8	910.1	335.1	312.5	433.6	523.6	757.1	307.5	390.0	542.9	614.5	278.8	188.0	322.0	274.9	537.2	432.7	525.8	284.7	707.2	956.2	485.6	182.7	463.7	928.9	416.9	398.4	116.6	257.4	271.2	542.1	229.0	368.3	398.6	365.2	488.7	199.7
¥	30647.7	30376.5	34016.2	31063.9	27230.2	32002.1	30003.3	28244.3	30499.0	30137.9	35360.3	37523.8	38822.8	27013.8	32459.5	26187.2	31488.2	33982.2	33356.4	25141.2	27288.4	29534.8	33896.8	32492.1	22814.2	29871.3	24807.7	34262.1	21039.3	29761.2	27296.5	25743.6	29811.6	23567.6	34258.4	26203.5	28642.1	21611.5	25621.6	22968.7	26220.7	25101.0	25711.1	27328.2
DΥ	3.284			3.319		4.424 3		3.527 2	4.494 3	3.795 3	3.087	4.291	4.216	5.222	2.741 3	6.772 2	5.543 3	3.812	2.912 3	3.218 2	5.669 2	6.220 2	6.094	4.568 3	4.603 2	6.965 2	4.065 2							3.599 2				7.554 2	5.018 2	2.731	3.680 2			4.822 2
CA	16562.9	14108.5	12488.5	6321.5	13686.3	9887.3	10197.2	17370.7	16368.3	12750.9	8135.3	23926.6	9497.2	13307.0	5657.0	12493.9	9207.2	8580.2	8.8699	6736.7	13978.4	12182.7	14132.7	12098.1	13649.0	13856.5	12411.1	7264.8	14574.0	4420.6	15869.8	14129.9	9119.4	14508.9	7334.3	9729.3	16236.1	11430.4	13709.3	19006.3	24459.5	16275.3	22257.3	10371.2
BA	6.899	1001.8	887.0	468.0	792.7	378.5	623.0	751.5	942.7	576.8	534.2	475.1	563.3	1039.9	476.8	487.7	818.9	469.2	535.0	381.4	703.5	852.2	1069.2	732.0	1099.7	952.0	876.4	537.7	790.9	466.3	884.3	953.2	596.9	464.7	2638.6	594.3	271.6	6.693	688.1	848.7	784.5			634.1
AL	75595.8	84849.4	86725.7	78592.8	9.9/988	87221.8	93188.7	88962.5	95693.0	88340.2	83234.8	83076.4	82809.9	86601.4	82968.5	99449.3	85777.1	78888.7	79519.1	01505.7	93057.4	88989.2	92927.8	92657.7	102858.6	83112.8	94530.6	94465.9	9.80600	93191.1	94669.1	93247.6	84073.8	71879.0	_	80786.4	96730.4	92389.5	83327.6	79091.1	78365.1		_	85194.7
ZR	173.5			188.8		192.5	218.3	207.4	197.0	217.4	151.0	136.5	126.5	231.4	210.5	150.4	193.8	177.9	182.2	168.1	227.5	198.6	268.0	217.0	287.6	240.7	195.4		_								186.8	1.891	156.5	177.8	140.0			160.8
NZ	1.69	71.2	64.5	42.6	67.1	63.3	78.2	9.06	121.4	59.9	54.3	7.06	54.8	48.0	39.6	69.4	92.1	65.2	43.0	42.7	70.9	64.5	78.6	26.9	7.06	53.9	75.0	39.5	94.1	38.0	69.5	77.3	0.79	55.8	101.3	60.5	50.7	76.5	0.99	9:59	8.66	65.1	67.2	60.3
H	17.27					21.43		14.23	13.05	25.98	23.09	22.34	18.06	18.84	29.28	26.72	21.28	18.50	26.27	50.56	16.36	16.08	17.26	14.43	12.94	17.14	14.26			46.19					49.04		52.85	21.47	18.48	10.07	9.85	l		25.45
TA TE	1.4880 0.64	1.3105 1.00	621 0.69	_	1.3515 1.03	1.5724 0.71	1.5415 1.16	1.3862 0.59	1.0330 0.79	1.5009 0.57	1.5555 0.47	1.4762 0.59	1.1639 0.63	1.4769 0.76	1.5340 0.38	271 1.05	931 0.88	547 0.51	1.6009 0.44	2.2664 0.42	1.2552 0.81	1.2339 0.92	1.1884 0.89	1.3955 0.78	0.8913 0.85	1.3207 1.06	1.2004 0.67	2.3563 0.47	1.1404 0.64	2.4186 0.27	1.1011 0.80			1.4264 0.58	711 1.42		2.4206 0.45	1.2575 1.36	1.3855 0.93	0.9565 0.66	381 0.75		_	771 0.80
SR	195.7 1.48	265.1 1.3				189.6 1.5	144.3 1.5	361.9 1.38	409.7 1.0:	210.8 1.50	219.4 1.5!	290.3 1.4	147.6 1.10	254.3 1.4	151.8 1.5:	134.0 1.427	175.0 1.3931	176.2 1.6547	137.7 1.60	104.8 2.20	256.0 1.2	273.4 1.2:	209.8 1.18	263.4 1.39	305.2 0.89	299.9 1.3.	300.8 1.20	209.0 2.3						306.6 1.4;	197.0 2.4711			189.1 1.2	268.7 1.38	498.9 0.99	327.0 0.9381			213.0 1.4771
SC	7.32 19	6.94 26			7.82 29	8.66 18		10.34 36	11.40 40	6.75 21	7.26 21	4.73 29	6.10 14	7.32 25	5.73 15	9.38 13	7.63 17	7.68 17	5.28 13	4.32 10	9.75 25	8.84 27	9.02	10.75 26	1.72 30	6.08 29	11.01						7.44 12			10.56 26		9.41 18	10.75 26	7.31 49	11.23 32			7.95 21
SB	0.7905					0.5106	0.4870	0.4181 10	0.5585 1	0.5223	0.3153	0.5150	0.4605	0.3511	0.4827	0.4371	0.5437	0.6810	0.5182	0.8003	0.4259	0.3714	0.5888		0.3097 1	0.3236	0.5367 1		`									0.4347	0.3689 10	0.2385	`			0.5473
RB	186.98					181.50	172.70	108.96	130.03	183.84	225.15	141.60	145.28	138.59	185.66	143.79	160.56	197.52	194.72	213.43	134.29	129.84	142.90		87.62	118.10	120.04	219.88								138.04	207.28	123.68	137.16		97.19			167.64
Z	0.0	14.6				0.0	0.0	0.0	0.0	0.0	32.2	0.0	0.0	0.0	0.0	23.0	25.9	25.4	0.0	0.0	0.0	33.3	0.0	23.8	0.0	24.0 1	24.2							0.0	0.0		0.0	0.0	0.0	0.0	26.4			0.0
生	8.53	6.81	6.04	7.78	7.81	9.05	7.66	89.8	7.25	8.73	6.12	90.9	6.63	96.6	8.75	5.84	6.74	7.74	8.07	6.35	8.62	7.82	10.32	7.98	11.14	9.80	8.14	5.63	8.15	6.29	7.90	10.44	5.98	5.33	4.55	8.77	6.57	6.62	7.36	7.11	5.92	9.11	5.73	6.45
FE	22844.8	22403.6			26468.8	22098.8	26194.8	47632.2	40010.0	23849.3	21814.9	19158.5	17007.5	25232.4	19740.2	27214.0	24781.9	22826.0	18857.1	13383.8	28203.6	27856.4	23398.0	37633.7	41686.3	28236.6	37228.2	14971.1	45839.1	8512.7	34558.9	37353.4	22797.9	17374.4	40583.5	24945.6	10866.6	28881.0	24854.9	27516.6	35182.3	26890.1	26398.0	25511.9
EU	0.8645				1.4352	0.8721	1.4463	1.0512	1.5108	6.84 0.9379	0.9255	0.7109	0.7659	1.3611	0.6678	1.4702	1.2119	0.9553	0.6949	0.5711	1.4280	1.5822	1.6970		1.9923		1.3659			0.3749			1.2584	0.7572	0.7339	1.1160	0.4997	1.7674	1.4116	1.2382		1.4617	1.2853	1.1744
CS	6.63	4.33				18.19	6:36	4.37	5.45	6.84	6.83	11.51	12.54	4.38	6.71	6.22	6.07	7.11	6.31	27.13	6.15	5.11	4.30	4.19	2.93	4.04	4.75							15.10	4.35	15.80	14.34	5.62	13.92	3.11	68.9	4.06		9.78
ANID	MVP0040	MVP0041	MVP0042	MVP0043	MVP0044	MVP0045	MVP0046	MVP0047	MVP0048	MVP0049	MVP0050	MVP0051	MVP0053	MVP0054	MVP0055	MVP0056	MVP0057	MVP0058	MVP0059	MVP0060	MVP0061	MVP0062	MVP0063	MVP0064	MVP0065	MVP0066	MVP0069	MVP0070	MVP0071	MVP0072	MVP0073	MVP0074	MVP0075	MVP0076	MVP0077	MVP0078	MVP0079	MVP0080	MVP0081	MVP0082	MVP0083	MVP0084	MVP0085	MVP0086

Universe of Minches Al Minches Pal Willers Pal Minches Al Minches Al Willers Pal Willers Pa	macro_grp	p Chem2012	CERAMIC TYPE	MATERIAL	SOURCE	STATE	SITE_NAME	SITE_NO	AS	ΓA	ΓN	QN	SM	n	YB CE	CO	CR
Windless AM Minches & W. Sybe III Politicy WURR NM PR. Cummings IA 019709A 211 83 9456 2529 285 131 33 71 34 71	Group-C21		Mimbres B/W Style III	Pottery	MURR	NM	Eby	LA 015016	1.67								25.70
Minches-QAM Minches BW Syge II Postery NURR MA Eby LA 019016 231 4501 4007 540 230 543 740 259 341 740 259 341 740 259 341 740 259 341 740 259 341 740 259 341 740 259 341 740 259 341 740 259 341 740 259 341 740 259 341 740 341 740 259 341 740 341 740 259 341 740 259 341 740 341 740 341 740 341 740 341 740 341 740 341 740 341 740	Group-C2			Pottery	MURR	MN	Eby	LA 015016	1.78							1 15.52	26.16
Winners 40A Minnes BW Sylett Pottery MURR RM RW EDY A 019016 371 33, 43, 90 0134 209 349 25. 259 68. 14 A 10 10 10 10 10 10 10 10 10 10 10 10 10	Group-B2			Pottery	MURR	NM	Ft. Cummings	LA 075994	2.31							7 15.10	37.68
Universes 404 Mimicros Plant Politary MIMPR NA RM Ety LA 019016 2477 3277 0.207 5.61 2.00 6.80 Universe 404 Mimicros Plant Politary MIMPR NA Ety LA 019016 2177 5.01 5.91 5.09 3.75 7.50 Universe ADM Mimicros Plant Politary MIMPR NA Ety LA 019016 5.17 5.01 5.21 5.0	Group-C28		Mimbres B/W Style II	Pottery	MURR	MN	Eby	LA 015016	3.71							7 23.16	90.09
Bitters Minterses BWI Minterses BWI Style III Politaty MINR EN IA 019016 3.31 45.90 2.37 15.06 3.21 6.50 3.21 7.50 Minterses BWI Style III Politaty MINR EN IA 019016 3.31 45.90 2.37 15.06 3.31 45.90 2.37 15.06 3.31 45.90 2.37 15.06 3.31 Minterses BWI Style III Politaty MIRR R MM EDY IA 019016 5.23 3.65 0.37 13.21 7.31 3.01 4.32 3.22 3.02	Group-B		Mimbres B/W Style III	Pottery	MURR	NM	Eby	LA 015016	4.12								
Unass Mintees BNV Syleil Politay MIRR BN WARD EN LA 019016 31 4519 (3396) 33 77 6.67 327 77 5.00 Mintees OLG Untygeld ed on white Politaty MIRR BN WARD EN LA 019016 512 3345 (3406) 517 321 321 77 5.00 Mintees OLG Mintees BNV Syleil Politaty MIRR NA EN EV LA 019016 2.68 50.71 (3426) 517 321 77 5.00 389 95.93 Mintees OLA Mintees BNV Syleil Politaty MIRR NA EV LA 019016 2.68 50.71 (3426) 387 77 3.91 3.21 7.01 37.01 7.01 4.29 7.02 4.84 7.02 <td>Group-C2</td> <td></td> <td>Mimbres Plain</td> <td>Pottery</td> <td>MURR</td> <td>ΣN</td> <td>Eby</td> <td>LA 015016</td> <td>2.47</td> <td>_</td> <td>_</td> <td></td> <td></td> <td></td> <td></td> <td></td> <td>54.46</td>	Group-C2		Mimbres Plain	Pottery	MURR	ΣN	Eby	LA 015016	2.47	_	_						54.46
Minthese ONE Mintheres BWI Syle III Politory MINRR NM Eby LA 019016 175 3345 6378 337 33 33 33 33 33 33 33 33 33 33 34 32 33 34 33 33 34 34 33 34 </td <td>Group-B</td> <td>Unas.</td> <td>Mimbres B/W Style III</td> <td>Pottery</td> <td>MURR</td> <td>M</td> <td>Eby</td> <td>LA 015016</td> <td>3.31</td> <td></td> <td></td> <td></td> <td></td> <td></td> <td></td> <td>0 16.93</td> <td>14.2</td>	Group-B	Unas.	Mimbres B/W Style III	Pottery	MURR	M	Eby	LA 015016	3.31							0 16.93	14.2
Membres-OLA Minches BW/Syle III Pollety MINCHES-OLA MINCHES BW/Syle IIII Pollety MINCHES-OLA MINCHES BW/Syle III Pollety MINCHES-OLA MINCHES-OLA	Group-B1	Mimbres-04C	Untyped red on white	Pottery	MURR	M	Eby	LA 015016	1.91								31.69
Membres-OA Minchee BW Syle III Pollety NAME LA 019016 5.21 3.45 0.1773 3.21 3.21 3.17 1.01 Urass Minchee SW Syle III Pollety MURR RW Eby LA 019016 5.23 3.06 0.379 1.37 3.54 4.18 2.35 1.70 0.04 1.70 1.01 4.79 1.70 1.01 4.79 1.70 1.01 4.79 1.02 1.70 0.04 1.01 4.79 1.02 1.70 0.04 1.01 4.79 1.02 1.00 1.00 2.00 0.03 9.04 1.00 1.00 0.09 1.00 0.09 1.00 0.09 1.00 0.09 1.00 0.09 1.00 0.09 1.00 0.09 1.00 0.09 1.00 0.09 1.00 0.00 0.09 1.00 0.09 1.00 0.09 1.00 0.09 1.00 0.09 1.00 0.09 1.00 0.09 1.00 0.09 1.00	Group-B1	Mimbres-04B	Mimbres B/W Style III	Pottery	MURR	NM	Eby	LA 015016	1.75								24.7
Members-OAA Membres BWW SyleIII Potley MURR MAR EDY LA019016 5.23 6.01 0.4325 7.95 9.23 9.73 Membres-OAA Membres BWW SyleIII Potley MURR MAR EDY LA019016 5.23 6.045 0.3565 3.20 6.07 3.21 4.70 9.04 Unas. Membres BWW SyleIII Potley MURR MM EDY LA019016 1.70 5.20 6.07 3.21 4.01 6.03 9.9 6.33 4.01 1.00 9.9 6.33 9.9 6.33 9.9	Group-B2		Mimbres B/W Style III	Pottery	MURR	MN	Eby	LA 015016	5.72								48.55
Unas. Mimbres BW Syle III Pottery MURR MW Eby LO15016 5.25 ad.66 379 7.64 3.64 4.09 5.55 3.06 379 3.64 4.09 1.05 1.00 4.00 5.26 6.05 3.06 6.37 1.04 4.29 1.25 1.00 0.05 3.06 6.37 1.04 4.20 1.05 1.00 1.0	Group-B1			Pottery	MURR	MN	Eby	LA 015016	2.68							4 14.50	19.45
Hambres-OAD Mimbres BMV Syle III Poletey MURRR MM Eby LA 019016 2.34 44.01 0.66571 3.70 7.64 3.54 4.00 0.6571 1.01 4.20 0.52 1.02 1.02 0.02 1.02 <t< td=""><td>Group-B</td><td>Unas.</td><td>Mimbres B/W Style II</td><td>Pottery</td><td>MURR</td><td>MN</td><td>Eby</td><td>LA 015016</td><td>5.23</td><td>30.65 0.3</td><td></td><td></td><td></td><td></td><td></td><td>0 23.34</td><td>25.85</td></t<>	Group-B	Unas.	Mimbres B/W Style II	Pottery	MURR	MN	Eby	LA 015016	5.23	30.65 0.3						0 23.34	25.85
Unas. Mimbres BM Syle III Poltey MURR MA Eby LA 019016 4.71 31.90 6.471 32.80 6.89 10.43 Unas. Mimbres BM Syle III Poltey MURR RM Eby LA 019016 4.71 31.90 6.471 30.23 8.81 6.88 32.00 9.45 Mimbres BM Syle III Poltey MURR MM Eby LA 019016 2.03 55.50 6.91 5.92 4.81 10.50 Unas. Mimbres BM Syle III Poltey MURR MM Eby LA 019016 2.03 55.50 6.92 3.83 4.91 10.90 6.71 9.93 7.91 5.92 4.91 10.50 9.93 7.91 5.92 4.93 6.83 9.93 7.93 4.83 6.93 7.93 4.83 6.93 7.93 4.83 7.93 8.93 1.93 4.83 7.93 4.83 7.93 4.83 7.93 4.83 7.93 4.83 7.93	Group-B2	Mimbres-02A	Mimbres B/W Style III	Pottery	MURR	MN	Eby	LA 015016	2.36							7 14.54	35.67
Unas. Minchee BW Syle III Potlety MMRR MMR Eby LA 015016 4.77 4.01 4.24 1.83 2.93 6.53 In mas. Minchee BW Syle III Potlety MMRR Eby LA 015016 2.78 6.50 4.24 1.02 6.66 9.23 89.96 Unas. Minchee BW Syle III Potlety MMRR Eby LA 015016 2.81 6.05 6.66 9.23 89.96 Unas. Minchee BW Syle III Potlety MMRR MW Eby LA 015016 2.81 4.02 6.66 9.23 89.96 Minchee SUR Syle III Potlety MMRR MW Eby LA 015016 2.81 6.20 6.66 9.23 89.96 Minchee SUR Syle III Potlety MURR MW Eby LA 015016 2.81 8.74 4.83 1.83 1.83 1.83 1.83 1.83 1.83 1.83 1.83 1.83 1.83 1.83 1.83 1.83	Group-A	Unas.	Mimbres B/W Style III	Pottery	MURR	MN	Eby	LA 015016	1.10							3 16.15	27.80
Unass. Minchee BWN Style III Pottery MURR MURR Eby LA 015016 2.78 46.63 0.491 6.88 3.20 89.47 Unass. Minchees BWN Style II unsilp Pottery MURR IMB Eby LA 015016 2.81 40.61 5.23 4.31 0.52 45.2 4.35 4.39 9.89 Unass. Minchees BWN Style III Pottery MURR IMB Eby LA 015016 2.81 40.60 7.53 4.31 10.25 40.61 5.82 4.31 10.25 40.61 7.83 4.81 10.25 4.31 4.82 4.85 6.60 7.83 4.81 10.55 4.31 4.85 4.35 4.35 4.35 4.35 4.35 4.35 4.35 4.35 4.35 4.35 4.35 4.35 4.83 4.35 4.35 4.35 4.35 4.35 4.35 4.35 4.35 4.35 4.35 4.35 4.35 4.35 4.35 4.35 4.35	Group-B	Unas.	Mimbres B/W Style III	Pottery	MURR	MN	Eby	LA 015016	4.77							3 8.01	31.22
Minthores Offices of Multiple BW Style II unship Pottery MURR BW Style II voilish Pottery MURR BW MR Eby LA 015016 337 3147 04125 24.91 55.9 35.2 58.95 Unass. Minthores BW Style II Pottery MURR R Eby LA 015016 2.81 40.81 7.59 53.2 43.7 28.7 66.6 9.23 89.96 Minthores BW Style III Pottery MURR R IM Eby LA 015016 2.18 51.20 0.5658 3.95.8 3.81 2.81 3.75 2.81 3.75 3.81 6.80 3.85 3.81 6.80 3.83 3.83 6.80 3.83 3.83 3.85 3.83 3.	Group-B	Unas.	Mimbres B/W Style III	Pottery	MURR		Eby	LA 015016	2.78							7 24.45	26.35
Unas. Mimbres BW Syle II Pottley MURR NM Eby LA 015016 2.37 3.47 4.04 5.55 6.0620 4.068 7.59 5.31 2.87 4.30 9.05 4.33 2.81 3.29 4.33 2.81 3.05 Mimbres BW Syle III Pottley MURR RN Eby LA 015016 2.81 6.050 4.06 7.53 5.23 4.33 2.81 7.80 1.05 9.05 4.83 2.81 7.30 9.05 7.83 4.33 2.81 7.30 9.05 4.33 4.33 4.33 7.03 8.23 4.33 4.33 7.30 8.23 4.33 <th< td=""><td>Group-A</td><td>Mimbres-01</td><td>Mimbres B/W Style II uns</td><td>slip Pottery</td><td>MURR</td><td>MN</td><td>Eby</td><td>LA 015016</td><td>1.97</td><td></td><td></td><td></td><td></td><td></td><td></td><td>6 25.27</td><td>11.3(</td></th<>	Group-A	Mimbres-01	Mimbres B/W Style II uns	slip Pottery	MURR	MN	Eby	LA 015016	1.97							6 25.27	11.3(
Unas. Minthes BW Syle III Pottery MURR NM Eby LO 15016 2.03 5.55 6 0.000 0.0484 7.59 5.32 4.13 10.25 Minthese-OAR Minthes BW Syle III Pottery MURR NM Eby LA 015016 2.13 5.10 0.6569 3.93 7.80 4.53 2.33 1.30 3.93 Minthese-OR Minthees-OR Minthees-OR Minthees-OR MINTH Eby LA 015016 3.13 5.01 4.53 2.53 2.93 1.80 3.23 2.93 1.80 3.23 2.93 1.80 3.23 2.93 1.80 3.23 2.93 1.80 3.23 2.93 1.80 3.23 2.93 3.23 2.93 3.2	Group-B	Unas.	Mimbres B/W Style II	Pottery	MURR	MN	Eby	LA 015016	3.37							6 11.83	33.03
Group-BI Mintbres-OLA Mintbres BMS SyleIII Pottery Pottery MURR NAME IMA (1501) 2.8 4.0.0 0.4484 2.5.1 5.2.2 4.35 2.8 3.00 Group-BB (Goup-BB (Mintbres-OLA Mintbres Class). Conquebte (Park Name). LA (1501) 2.13 5.10 1.55 4.35 2.8 4.35 2.8 3.5 4.35 2.8 3.5 4.35 3.5 4.35 4.35 3.5 4.35 4.35 3.5 4.35 4.35 3.5 4.35	Group-B	Unas.	Mimbres B/W Style III	Pottery	MURR	MN	Eby	LA 015016	2.03							17.10	59.49
Group-B2 Mimbres-O2A Mimbres BW Syye III Pottery MURR NA Eby LA 015016 2.15 5.120 0.5659 39.9 7.80 4.33 5.25 1.28	Group-B1	Mimbres-04B		Pottery	MURR		Eby	LA 015016	2.81							9 21.88	71.7
Group-E2b Mmbres A7 Mmbres Classic Corrugate Pottery MURR MM Eby LA 015016 3.82 3.54 0.456.1 7.26 1.28 1.28 1.29 2.51 2.58 1.29 2.51 2.58 1.29 2.51 2.58 1.29 2.51 2.58 1.29 2.51 2.58 1.29 2.51 2.58 1.29 2.51 2.58 1.29 2.51 2.58 1.29 2.51 2.53 3.31 3.50 3.51 3.71	Group-B2			Pottery	MURR		Eby	LA 015016	2.13							5 23.55	37.7
Mimbres-04A Mimbres BW Style III Pottery MURR NA Eby LA 015016 2.40 37.54 0.4261 57.26 5.42 4.37 3.04 Mimbres-04A Mimbres BW Style III Pottery MURR NA Eby LA 015016 5.04 33.01 0.5239 20.26 4.01 3.27 3.01 Unas. Mimbres-02A Mimbres BW Style III Pottery MURR NA Eby LA 015016 5.04 5.02 4.01 3.27 3.31 Unas. Mimbres-BW Style III Pottery MURR NA Eby LA 015016 2.04 5.02 0.747 5.08 1.2.02 7.51 5.37 2.81 3.40 3.42 4.01 3.22 4.01 3.24 4.01 3.24 4.01 3.24 4.01 3.25 4.01 3.24 4.01 3.24 4.01 3.24 4.01 3.24 4.01 3.34 4.01 3.01 6.25 4.01 3.01 6.25	Group-C21		Mimbres Classic Corruga	ated Pottery	MURR		Eby	LA 015016	3.82						1	8 18.55	30.30
Mimbres-04A Mimbres BW Style III Pottety MURR NM Eby LA 015016 3.04 39.03 0.4345 26.06 5.42 4.37 3.04 Mimbres-02A Mimbres BW Style III Pottety MURR NM Eby LA 015016 2.94 33.07 0.5239 3.31 3.31 3.02 4.01 3.25 3.31 3.02 4.01 3.25 3.31 3.02 4.01 3.25 3.31 3.31 3.02 4.01 3.25 3.31 3.31 3.02 4.01 3.31 3.02 3.04 3.31 3.02 3.04 3.31 3.02 3.04 3.31 3.02 3.04 3.31 3.31 3.02 3.04 3.31 3.31 3.02 3.04 3.31 3.04 3.04 3.31 3.04 3.04 3.04 3.04 3.04 3.04 3.04 3.04 3.04 3.04 3.04 3.04 3.04 3.04 3.04 3.04 3.04 3.04 3.04<	Group-B1	Mimbres-04A		Pottery	MURR	MN	Eby	LA 015016	2.40							2 11.94	20.82
Mimbres-02A Mimbres BWW Style III Pottery MMRR IMA Eby IA 015016 1.57 38.11 0.5013 20.25 4.01 5.33 3.31 Unas. Mimbres BWW Style III Pottery MURR IMA Eby IA 015016 2.64 57.02 0.7497 5.02 4.01 3.23 3.81 Mimbres-04C Mimbres BWW Style III Pottery MURR IMA Eby IA 015016 2.64 40.05 0.4720 29.92 5.73 5.13 3.18 Mimbres-04C Mimbres BWW Style III Pottery MURR IMA Eby IA 015016 2.64 40.05 0.4720 29.92 5.73 5.13 3.18 Mimbres-04A Mimbres BWW Style III Pottery MURR IMA Eby IA 015016 2.64 40.05 0.4720 29.92 5.13 3.19 Mimbres-02A Mimbres BW Style III Pottery MURR IMA Eby IA 015016 2.64 40.05 0.4720	Group-B1	Mimbres-04A	Mimbres B/W Style III	Pottery	MURR	MN	Eby	LA 015016	3.04								22.33
Unas. Mimbres BWN Style III Pottery MURR NM Eby LA 015016 5.63 3.307 0.5239 20.25 4.01 3.22 3.81 Unas. Mimbres BWN Style III Pottery MURR NM Eby LA 015016 2.94 57.02 0.7479 5.08 12.02 7.51 3.31 3.10 Mimbres-OdA Mimbres BWN Style III Pottery MURR NM Eby LA 015016 2.94 57.02 0.7470 29.92 5.73 3.13 3.18 </td <td>Group-B2</td> <td>Mimbres-02A</td> <td>Mimbres B/W Style III</td> <td>Pottery</td> <td>MURR</td> <td>M</td> <td>Eby</td> <td>LA 015016</td> <td>1.57</td> <td></td> <td></td> <td></td> <td></td> <td></td> <td></td> <td>0 13.24</td> <td>37.03</td>	Group-B2	Mimbres-02A	Mimbres B/W Style III	Pottery	MURR	M	Eby	LA 015016	1.57							0 13.24	37.03
Unas. Mimbres BW Style II Pottery MURR NM Eby LA 015016 2.94 57.02 0.7497 50.86 1.2.02 7.51 5.37 Mimbres-Odd Mimbres BW Style III Pottery MURR NM Eby LA 015016 2.64 40.05 0.4720 29.92 5.71 5.31 3.18 Mimbres-Odd Mimbres BW Style III Pottery MURR NM Eby LA 015016 2.64 40.05 0.4720 29.92 5.71 5.33 3.49 Mimbres-Odd Mimbres BW Style III Pottery MURR NM Eby LA 015016 2.64 40.05 0.473 3.21 4.71 2.97 5.71 5.33 3.49 1.44 2.99 2.89 3.49 0.7317 2.66 6.01 1.46 4.88 9.12 2.87 5.31 5.71 5.37 5.71 5.37 5.71 5.37 7.14 3.97 7.14 3.97 7.71 3.73 7.74 3.75	Group-B	Unas.	Mimbres B/W Style III	Pottery	MURR		Eby	LA 015016	5.63								21.30
Mimbres-O4C Mimbres BW Style III Pottery MURR IVM Eby IA 015016 3.11 4701 0.4549 34.37 7.14 3.52 3.42 Mimbres-O4A Mimbres BW Style III Pottery MURR IVM Eby IA 015016 2.69 4.005 0.4720 2.992 5.73 5.13 3.18 Mimbres-O2A Mimbres BW Style III Pottery MURR IVM Eby IA 015016 2.64 4.089 0.493 3.2.1 6.48 8.2 3.4 4.8 2.39 0.57 3.2 3.4 9.2 2.89 3.4 9.2 2.89 3.4 9.2 2.89 </td <td>Group-B</td> <td>Unas.</td> <td>Mimbres B/W Style II</td> <td>Pottery</td> <td>MURR</td> <td></td> <td>Eby</td> <td>LA 015016</td> <td>2.94</td> <td></td> <td></td> <td>_</td> <td></td> <td></td> <td>7</td> <td></td> <td>7.89</td>	Group-B	Unas.	Mimbres B/W Style II	Pottery	MURR		Eby	LA 015016	2.94			_			7		7.89
Mimbres-OAA Mimbres BWN Style III Pottery MURR NA Eby LA 015016 2.64 4.055 0.4720 29.29 5.73 5.13 3.18 Mimbres-OAA Mimbres BWN Style III Pottery MURR NM Eby LA 015016 2.64 4.089 0.4731 2.666 5.01 1.160 3.13 a Mimbres-OA Mimbres BWN Style III Pottery MURR NM Eby LA 015016 2.64 4.089 0.473 3.5.50 6.13 1.59 2.39 Luns. Mimbres BWN Style III Pottery MURR NM Eby LA 015016 5.52 53.05 0.4484 46.89 9.12 2.89 2.89 Luns. Mimbres BWN Style III Pottery MURR NM Eby LA 015016 2.24 6.07 3.24 4.09 9.12 2.99 2.89 Luns. Mimbres BWN Style III Pottery MURR NM Eby LA 015016 2.24 6.05 0.478	Group-B1	Mimbres-04C	Mimbres B/W Style III	Pottery	MURR	MN	Eby	LA 015016	3.11							_	30.56
Mimbres-OZA Mimbres BW Style III Pottery MURR NM Eby LA 015016 2.64 4.089 0.4934 32.71 6.48 4.82 3.49 Mimbres-O1 Mimbres-O1 Mimbres BW Style III Pottery MURR NM Eby LA 015016 2.04 0.2781 33.50 6.13 1.59 2.39 Unas. Mimbres BW Style III Pottery MURR NM Eby LA 015016 2.52 53.05 0.4158 4.44 2.99 2.89 Unas. Mimbres BW Style III Pottery MURR NM Eby LA 015016 2.78 46.80 0.4078 3.24 2.89 2.89 Unas. Mimbres BW Style III Pottery MURR NM Eby LA 015016 2.78 46.80 9.12 2.81 3.40 Unas. Mimbres BW Style III Pottery MURR NM Eby LA 015016 2.78 4.05 3.04 4.44 3.72 Unas. Mimbres	Group-B1		Mimbres B/W Style III	Pottery	MURR		Eby	LA 015016	2.69								18.50
wimbres-U Mimbres BM Style III Pottery MURR NM Eby LA 015016 0.1317 26.06 5.01 11.50 2.3.5 a Mimbres-42 Mimbres BM Style III Pottery MURR NM Eby LA 015016 2.48 38.76 0.2781 33.50 6.13 1.59 2.39 Unas. Mimbres BM Style III Pottery MURR NM Eby LA 015016 2.58 46.36 0.4078 30.23 5.09 2.89 2.89 Unas. Mimbres BM Style III Pottery MURR NM Eby LA 015016 2.38 46.36 0.4078 30.23 3.62 1.89 2.89 Unas. Mimbres BM Style III Pottery MURR NM Eby LA 015016 2.73 30.96 5.81 4.44 3.72 Unas. Mimbres BM Style III Pottery MURR NM Eby LA 015016 2.73 30.96 5.81 4.44 3.72 Unas. Mimbres	Group-B2		Mimbres B/W Style III	Pottery	MURR		Eby Fi	LA 015016	2.64	_			7			1 9.78	37.59
Group-Local Mimbres-AZ Mimbres-AZ Mimbres BAW Style III Pottery MURR NM Eby LA 015016 2.48 38.76 0.4281 3.53 0.13 1.39 2.89 Group-B Unas. Mimbres BAW Style III Pottery MURR NM Eby LA 015016 5.52 53.05 0.4484 4.6.80 9.12 2.89 Group-B Unas. Mimbres BAW Style III Pottery MURR NM Eby LA 015016 5.52 53.05 0.4784 4.6.80 9.12 2.89 Group-B Unas. Mimbres BAW Style III Pottery NURR NM Eby LA 015016 2.34 46.80 30.35 3.61 4.34 2.89 Group-B Unas. Mimbres BAW Style III Pottery NUR Eby LA 015016 5.21 5.03 0.599 3.89 3.44 4.37 Group-B Unas. Mimbres BAW Style III Pottery MURR NM Eby LA 015016 2.21 <	Group-A		Mimbres B/W Style III	Pottery	MUKK		Eby	LA 015016	0.00								1.1
Group-B Unas. Mimples B/W Style III Potterly MURR IVM EDy LA 015016 5.24 54.45 0.4136 2.136 4.44 2.59 2.83 Group-B Unas. Mimbres Three Circle Corru Pottery MURR IVM Eby LA 015016 5.52 53.05 0.4484 46.80 9.12 2.87 3.54 Group-B Unas. Mimbres B/W Style III Pottery NURR IVM Eby LA 015016 5.36 0.4078 30.23 5.02 4.84 2.80 Group-B Unas. Mimbres B/W Style III Pottery NURR IVM Eby LA 015016 5.81 3.44 3.72 6.15 3.69 3.81 4.44 3.72 Group-B Unas. Mimbres B/W Style III Pottery NUR Eby LA 015016 2.21 5.03 0.599 3.81 4.44 3.72 Group-B Unas. Mimbres B/W Style III Pottery MURR IM Eby LA 015016 </td <td>Group-Cz.</td> <td></td> <td>Mimbles B/W Style III</td> <td>Pollery</td> <td>MUKK</td> <td></td> <td>EDy</td> <td>LA 015010</td> <td>2.40</td> <td></td> <td></td> <td></td> <td></td> <td></td> <td></td> <td></td> <td>01.00</td>	Group-Cz.		Mimbles B/W Style III	Pollery	MUKK		EDy	LA 015010	2.40								01.00
Unas. Mimbres BW Style III Pottery MURR NM Eby LA 015016 5.52 53.05 0.4484 46.80 9.12 2.81 2.54 Unas. Mimbres-O1 Mimbres BW Style III Pottery MURR NM Eby LA 015016 2.34 68.92 34.61 6.63 1.89 2.80 Unas. Mimbres BW Style III Pottery MURR NM Eby LA 015016 1.80 5.81 3.45 1.63 3.49 4.03 3.40 4.03 3.40 4.03 3.40 4.03 3.40 4.03 3.40 4.03 3.40 4.03 3.40 4.03 3.40 4.03 3.40 4.03 3.40 4.03 3.40 4.03 3.40 4.03 3.40 4.03 3.40 4.03 3.40 4.03 3.40 4.03 3.40 4.03 3.40 4.44 3.72 4.44 3.72 4.44 3.72 4.44 3.72 4.44 3.72 4.44	Group-B	Unas.	Mimbres B/W Style III	Pottery	MUKK	MN.	Eby	LA 015016	3.24								20.74
Unas. Mimbres BW Style III Pottery MURR NM Eby LA 015016 2.58 46.36 0.4078 30.23 5.02 4.84 2.80 Mimbres-01 Mimbres BW Style III Pottery MURR NM Eby LA 015016 1.34 68.92 0.4861 39.21 6.63 1.197 4.03 Unas. Mimbres BW Style III Pottery MURR NM Eby LA 015016 5.81 38.44 0.5457 30.96 5.81 4.44 3.72 Unas. Mimbres BW Style III Pottery MURR NM Eby LA 015016 2.02 5.09 30.62 6.19 8.13 3.58 Unas. Unityper BW Style III Pottery MURR NM Eby LA 015016 2.02 70.90 30.62 6.19 8.13 3.58 3.56 4.39 3.58 3.56 4.39 3.58 3.56 4.39 3.56 4.39 3.51 4.26 3.39 3.66 5.19	Group-B	Unas.	Mimbres I hree Circle Co	orru Pottery	MUKK	NN.	Eby	LA 015016	2.52					_		_	50.32
Group-A Mimbres-01 Mimbres-02 Mimbres-03 Mimbres-03 Mimbres-03 Mimbres-03 Mimbres-03 Mimbres-03 Mimbres-04	Group-B	Unas.	Mimbres B/W Style III	Pottery	MURR	ΣN	Eby	LA 015016	2.58								22.34
Group-B Unas. Mimbres BMX Slyle III Pottery MURR NM Eby LA 015016 5.81 38.44 0.5457 30.96 5.81 3.44 3.72 Group-B Unas. Mimbres BMX Slyle III Pottery MURR NM Eby LA 015016 5.81 38.44 0.5457 30.96 5.81 4.44 3.72 Group-B Unas. Mimbres BMX Slyle III Pottery MURR NM Eby LA 015016 2.02 78.08 0.7838 38.38 7.06 12.02 4.39 Group-B Unas. Untyped red on white Pottery MURR NM Eby LA 015016 1.93 33.90 0.4756 21.95 4.21 3.5 Group-B Mimbres-OZ Mimbres-OZ Mimbres BMX Slyle III Pottery MURR NM Eby LA 015016 1.93 33.90 0.4756 21.95 4.22 2.90 3.06 Group-B Mimbres-OZA Mimbres BMX Slyle III Pottery	Group-A	Mimbres-01	Mimbres B/W Style III	Pottery	MURR	NM	Eby	LA 015016	2.34				,				7.39
Group-B Unas. Mimbres B/W Slyle II Pottery MURR NM Eby LA 015016 5.81 38.44 0.5457 30.96 5.81 4.44 3.72 Group-B Unas. Mimbres B/W Slyle III Pottery MURR NM Eby LA 015016 2.21 50.39 30.65 6.19 8.13 3.58 Group-B Mimbres-O1 Mimbres B/W Slyle III Pottery MURR NM Eby LA 015016 3.66 33.90 0.4756 21.95 4.21 3.51 3.28 Group-B Unimbres-O2C Mimbres B/W Slyle III Pottery MURR NM Eby LA 015016 1.93 33.86 0.4570 25.12 4.22 2.90 3.06 Group-B2 Mimbres-O2A Mimbres-B/W Slyle III Pottery MURR NM Eby LA 015016 1.58 45.29 0.5662 34.27 7.56 4.48 3.97 Group-B2 Mimbres-O4A Mimbres-BW Slyle III Pottery MURR	Group-B	Unas.	Mimbres B/W Style III	Pottery	MURR	MN	Eby	LA 015016	1.80							0 11.39	31.48
Unas. Mimbres BMX Style III Pottery MURR NM Eby LA 015016 2.21 50.39 0.5990 30.62 6.19 8.13 3.58 Mimbres-OZ Mimbres BMX Style III Pottery MURR NM Eby LA 015016 2.02 78.08 0.786 21.95 4.29 4.39 Unas. Unas. Untyped red on white Pottery MURR NM Eby LA 015016 1.93 33.90 0.4756 21.95 4.21 3.51 3.28 Mimbres-OZA Mimbres BMX Style III Pottery MURR NM Eby LA 015016 1.58 45.29 0.5662 34.27 7.56 4.48 3.97 Mimbres-OZA Mimbres-SMX Style III Pottery MURR NM Eby LA 015016 1.58 45.29 0.5662 34.27 7.56 4.48 3.97 Mimbres-SAA Mimbres-SMX Style III Pottery MURR NM Eby LA 015016 2.34 37.89 0.4564 <td>Group-B</td> <td>Unas.</td> <td>Mimbres B/W Style II</td> <td>Pottery</td> <td>MURR</td> <td>MN</td> <td>Eby</td> <td>LA 015016</td> <td>5.81</td> <td></td> <td></td> <td></td> <td></td> <td></td> <td></td> <td>5 15.57</td> <td>37.80</td>	Group-B	Unas.	Mimbres B/W Style II	Pottery	MURR	MN	Eby	LA 015016	5.81							5 15.57	37.80
Mimbres-01 Mimbres BMV Style III Pottery MURR NM Eby LA 015016 2.02 78.08 0.7888 38.38 7.06 12.62 4.39 Unas. Unas. Untyped red on white Pottery MURR NM Eby LA 015016 3.66 33.90 0.4756 21.95 4.21 3.51 3.28 Mimbres-OZA Mimbres BMV Style III Pottery MURR NM Eby LA 015016 1.58 45.29 0.5662 34.27 7.56 4.48 3.97 Mimbres-OZA Mimbres-BMV Style III Pottery MURR NM Eby LA 015016 1.58 45.29 0.5662 34.27 7.56 4.48 3.97 Mimbres-OZA Mimbres-BMV Style III Pottery MURR NM Eby LA 015016 2.34 37.89 0.4564 30.13 5.73 4.87 3.11	Group-B	Unas.	Mimbres B/W Style III	Pottery	MURR	NM	Eby	LA 015016	2.21							0 8.93	23.78
Unas. Untyped red on white Pottery MURR NM Eby LA 015016 3.66 33.90 0.4756 21.95 4.21 3.51 3.28 Mimbres-02C Mimbres BWN Style III Pottery MURR NM Eby LA 015016 1.58 45.29 0.5662 34.27 7.56 4.48 3.97 Mimbres-04A Mimbres BWN Style III Pottery MURR NM Eby LA 015016 2.34 37.89 0.4584 30.13 5.73 4.87 3.11	Group-A	Mimbres-01	Mimbres B/W Style III	Pottery	MURR		Eby	LA 015016	2.02				`				90.9
Mimbres-02C Mimbres BMV Style III Pottery MURR NM Eby LA 015016 1.93 33.86 0.4570 25.12 4.22 2.90 3.06 Mimbres-02A Mimbres BMV Style III Pottery MURR NM Eby LA 015016 1.58 45.29 0.5662 34.27 7.56 4.48 3.97 Mimbres-04A Mimbres BMV Style III Pottery MURR NM Eby LA 015016 2.34 37.89 0.4584 30.13 5.73 4.87 3.11	Group-B	Unas.		Pottery	MURR		Eby	LA 015016	3.66								25.25
Mimbres-02A Mimbres B/W Style II Pottery MURR NM Eby LA 015016 1.58 45.29 0.5662 34.27 7.56 4.48 3.97 3.11 Mimbres-04A Mimbres B/W Style III Pottery MURR NM Eby LA 015016 2.34 37.89 0.4584 30.13 5.73 4.87 3.11	Group-B2	Mimbres-02C		Pottery	MURR	NM	Eby	LA 015016	1.93			7				l	
Mimbres-04A Mimbres BM/ Style III Pottery MURR INM Eby LA 015016 2.34 37.89 0.4584 30.13 5.73 4.87 3.11	Group-B2	Mimbres-02A	Mimbres B/W Style II	Pottery	MURR	ΣN	Eby	LA 015016	1.58						_	4 9.73	37.64
	Group-B1	Mimbres-04A	Mimbres B/W Style III	Pottery	MURR	MN	Eby	LA 015016	2.34							7 12.96	26.59

>	56.14	79.24	62.31	106.63	50.77	73.83	43.79	35.29	48.80	53.72	27.92	59.67	53.20	38.28	44.59	41.89	18.38	38.07	55.37	32.47	67.16	69.32	57.14	40.14	60.27	22.85	31.27	63.32	49.14	52.62	18.24	95.99	45.41	68.66	35.64	31.31	59.49	54.44	36.02	41.67	48.81	27.80	56.28	27.68
F	4408.9	4537.4	5031.2		2033.3	9.9609	3943.2	4581.2	3219.0	5234.8	4504.8	5888.7	4547.8	4164.0	2895.5	3941.5	3050.6	3360.5	4424.7	4125.3	4424.3	3931.6	4260.2	3449.7	4882.3	3239.1	4286.6	5201.9	5202.6	6199.4	2788.7	5965.6	3717.8	7145.6	3127.7	3291.9	4089.3	4487.2	3528.8	3186.3	3588.2	3620.1	4719.3	5958.3
NA	18263.6	18079.6	15435.5	16758.5	15742.7	19742.1	14750.2	17775.5	11270.7	10045.7	17324.9	13687.1	13670.4	14604.6	12700.4	13647.3	5871.9	16237.6	13257.7	12432.5	13426.4	17800.6	17298.4	15726.3	14456.1	10624.9	13152.1	16220.9	16271.9	15205.7	23125.4	21642.2	14971.2	17097.0	5121.3	16989.7	14169.4	9303.2	16040.3	19579.9	12848.2	11825.3	14709.8	13891.5
MN	340.9	423.3	242.3	508.2						1598.5	235.0	156.3	219.9	875.2	404.8	305.0		189.9	231.7	156.3	473.4	251.0	341.1		6.889						- 1	_			165.5			427.8		194.8	`	`	`	335.0
¥	24227.9	24055.5	26790.9	24692.9	20587.9	27389.8	33598.6	26325.7	26042.9	26981.3	27268.3	32824.4	24739.9	26154.1	28955.3	24105.6	46922.4	31087.2	26092.0	31564.8	27238.2	28439.6	27202.5	30494.6	27244.5	_		30312.0	31830.5	25265.5	26523.5	20717.1	23082.5	51430.4	29928.9	35511.7	28965.4	25910.1	30641.6	31493.3	23975.0	20825.9	23396.3	27209.0
DY	3.212	3.205	5.506							2.459	4.867	2.661	5.055	4.505		3.724		3.946	5.386	3.771	6.563	4.064	3.946 2	3.632							_			_	3.545 2	4.858	4.379	4.311	4.092	5.673				4.296
CA	21699.1	19848.5	11997.4	13118.1	18036.8	21953.2	9738.4	13593.8	9111.2	10685.4	18689.2	10254.5	11833.7	9887.2	16241.3	11619.3	9975.7	12401.5	4027.1	7758.3	12346.4	8792.2	10780.7	11676.0	11488.2	18099.0	14696.0	15672.6	9035.2	14257.1	9335.3	17632.1	14072.1	22177.2	9898.4	20555.3	11426.6	15652.3	8622.2	8470.4	17624.0	16724.5	11959.3	10412.5
BA		943.2	577.7	678.5	378.8	768.4	676.2	697.2	510.7	413.8	796.2	522.7	591.2	438.1	333.5	8.9/6	183.5	383.5	728.6	593.6	653.8	767.4	690.5		529.9			744.2	746.0						552.2	475.3	7.889	324.8	500.0	411.4	380.8	226.8	575.1	725.1
AL	82286.0	83792.8	83020.0	87064.6	72723.2	88210.0	79121.2	83793.3	87141.7	75665.4	81218.6	90332.0	77076.1	77328.8	74141.1	0.79088	75934.1	74555.3	89293.3	84007.3	82200.4	92992.4	85870.5	85303.2	86600.4	74821.1	88901.2	85891.2	88995.1	87874.7	02642.0	101489.8	70322.8	82004.1	75408.0	104513.4	84261.2	93083.2	93703.3	11072.9	75949.8	6,64869	86036.1	76086.4
ZR	154.5	147.4	187.7	186.7							157.1	173.7	168.9	187.2	130.0	169.0		137.3	151.9		170.3	143.6	211.6		180.3						٠	_				`	145.4 8	129.4 9		227.4 11				266.4 7
NZ	74.8	9.99	58.8	83.4						62.8	9.99	58.2	55.1	61.7	62.3			46.5	70.4	46.1	61.4	79.5	52.6										_		49.3		55.2	89.3		58.9	64.8			6.77
3 TH	0 9.51	4 9.78	2 18.52	5 11.40			8 24.04		-	2 18.32	9 18.40	2 25.11	1 19.14		19.65	0 24.25		2 20.09	5 24.67		7 20.30	4 10.17	1 19.59						-		7					3 49.18	8 23.90	9 20.63	8 31.27					1 19.82
TA	0.9194 0.60	0.9764 0.64	1.4580 1.0.	1.0738 0.95	1.3090 0.48		1.6945 0.78		1.4998 1.08	1.5113 0.62	1.2755 0.89	1.7379 0.42	1.6284 1.01	2.1072 0.81	1.5994 0.59	1.4548 0.70		1.6128 0.72	1.5690 0.95	1.4406 0.58	1.5260 1.07	0.7203 0.86	1.5413 0.61	1.3909 0.64	1.5296 0.82				1.6065 0.71		_			_	1.4150 0.63	2.2398 0.83	1.5115 0.78	1.3994 0.79	1.6653 0.78	5367 0.96	1.3334 0.60			1.5100 0.81
SR		472.3 0.9	271.8 1.4	389.0 1.0					147.1 1.4	166.9 1.E	260.2 1.2	243.3 1.7	299.1 1.6	124.4 2.1	290.3 1.5			314.1 1.6	193.9 1.5	126.5 1.4	303.0 1.5	403.5 0.7	195.9 1.5						187.5 1.6						193.3 1.4		207.1 1.5	231.9 1.3	279.3 1.6	118.7 2.5				271.9 1.5
SC		7.34		11.82					7.53	8.65	6.16	5.95	10.52	7.14	90.9	7.19		7.66	8.17	6.21	10.59	8.31	6.95	98.9	10.78												7.81	9.76	7.77	4.72				66.9
SB	0.2624	0.2334	0.3667	0.7483	0.4070	0.3812	0.2932	0.3823	0.4071	0.8850	0.3331	1.6251	0.3761	0.4377	0.4183	0.7071	0.2921	0.4797	0.8372	0.4803	0.4339	0.4690	0.3542	0.5928		0.4413	0.3380	0.4386	_		0.7279	0.3605	0.4084	0.7931	0.4956	0.7982	0.5505	0.6451	0.9844	0.6630	0.3995	0.3732	0.3342	0.3939
RB	85.44	94.26	136.89	105.74	147.98	85.47	166.54	106.05	160.64	179.07	129.92	181.08	128.43	176.95	157.97	144.74	254.62	144.04	153.86	159.60	146.89	94.96	127.74	166.76	146.41	149.88	155.65	130.92	165.28	130.92	223.61	76.56	155.33	102.01	171.18	169.95	166.06	155.68	132.84	186.87	144.60	164.30	135.30	145.07
Z	0.0	0.0	26.9	0.0	. 7	0.0	0.0	0.0	0.0	30.4	0.0	0.0	0.0		0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	33.4	31.2	0.0	0.0	0.0	4	0.0	0.0	10.8	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
生	5.93	6.56	7.12						5.80	7.06	97.9	6.65	92.9	6.44	6.22	5.46		6.71	6.16	6.77	7.80	5.08	9.63	9.80	7.88		J								5.53	7.13	6:36		6.73	7.50				9.87
H	27064.2	29808.8	25191.8	38625.4	21591.5	35721.3	20980.5	22376.5		26206.1	16922.0	19999.5	23631.8	22164.9	21004.7	20363.3	13948.4	15848.3	23301.8	18111.9	25950.5	31946.7	25496.3		26369.3	20668.8			22113.3	25246.1	14324.5	40892.7	17898.5	37289.3	17307.1	11070.2	24052.1	29317.4	19080.2	10216.0	23911.9			23989.5
EU	1.2666		1.4474	1.6385					1.3562		1.3730	6/69.0		1.0347	0.6963	1.0427	4.39 0.5880	0.9653	1.3120	0.9261	1.4212	1.9071	1.0068		1.1557	0.6903	2.5328								0.9066			0.9992	1.0002	1.0263				1.1391
CS	3.19	3.23	14.77	9.40	14.29	2.24	3.05	4.07	6.16	8.00	4.04	8.67	12.33	8.91	10.53	6.42	4.39	9.79	10.19	5.92	20.26	4.37	5.31	4.72	16.25	16.33	19.99	3.91	4.14	15.61	14.19				8.00	13.10	68.6	9.42	12.87	18.31	13.92	18.44	13.32	4.76
ANID	MVP0087	MVP0088	MVP0089	MVP0090	MVP0091	MVP0092	MVP0093	MVP0094	MVP0095	MVP0096	MVP0097	MVP0098	MVP0099	MVP0100	MVP0101	MVP0102	MVP0103	MVP0104	MVP0105	MVP0106	MVP0107	MVP0108	MVP0109	MVP0110	MVP0111	MVP0112	MVP0113	MVP0114	MVP0115	MVP0116	MVP0117	MVP0118	MVP0119	MVP0120	MVP0121	MVP0122	MVP0123	MVP0124	MVP0125	MVP0126	MVP0127	MVP0128	MVP0129	MVP0130

ANID	macro_grp	Chem2012	CERAMIC TYPE	MATERIAL	SOURCE	STATE !	SITE_NAME	SITE_NO	AS	ΓA	Π	ND S	SM	U YB	B CE	00	CR
MVP0131	Group-B	Unas.	Mimbres B/W Style III	Pottery	MURR		Eby	LA 015016	2.30	48.26 0.5	0.5660 33	33.68 6.18	18 6.91	3.22	2 90.64	9.40	25.01
MVP0132	Group-C1	Unas.	Mimbres B/W Style II	Pottery	MURR	I WN	Eby	LA 015016	5.10	38.00 0.4	0.4240 31	31.91 6.(6.04 4.45	15 2.77	7 75.39	13.14	56.09
MVP0133	Group-B1	Mimbres-04B	Mimbres B/W Style III	Pottery	MURR	NM E	Eby	LA 015016	3.28	46.75 0.5	0.5405 32	32.63 6.53	53 6.71	71 3.23	3 92.67	10.15	22.85
MVP0134	Group-B2	Mimbres-11	Mimbres B/W Style III	Pottery	MURR		Eby	LA 015016	2.95	33.15 0.5			4.66 4.77	_) 22.69	44.09
MVP0136	Group-B2	Mimbres-02A	Mimbres B/W Style III	Pottery	MURR		Eby	LA 015016	2.77			31.13 6.21	21 6.09			l	36.07
MVP0137	Group-B1	Mimbres-04A	Mimbres B/W Style III flare r Pottery	Pottery	MURR		Eby	LA 015016	1.94	41.47 0.5	0.5366 31	31.14 5.95	95 5.21			6.87	18.97
MVP0138	Group-B2	Mimbres-11	Mimbres B/W Style III	Pottery	MURR		Eby	LA 015016	5.37	31.44 0.5	0.5469 23		_		0 70.05	(~)	46.26
MVP0139	Group-B2	Mimbres-02A	Mimbres B/W Style III	Pottery	MURR		Eby	LA 015016	2.48	36.06 0.5	0.5456 29	29.28 5.81	81 6.83	33 3.30	0 65.19	8.65	37.58
MVP0140	Group-B1	Mimbres-04A	Mimbres B/W Style III seed Pottery	Pottery	MURR	NM H	Eby	LA 015016	1.97	47.29 0.5	0.5120 37	37.69 6.57	57 5.47	17 3.39	71.19	7.66	18.20
MVP0141	Group-B	Unas.	Mimbres B/W Style II unslip Pottery	Pottery	MURR		Eby	LA 015016	2.67	30.55 0.2	0.2718 21	21.74 2.9	2.98 1.79	79 2.03	3 41.10	96.9	8.46
MVP0142	Group-B	Unas.	Mimbres B/W Style III	Pottery	MURR	MM	Eby	LA 015016	3.51	44.00 0.4	0.4194 38	38.75 6.2	6.25 3.74	3.11	1 69.74	15.59	30.51
MVP0143	Group-C2	Unas.	Mimbres plain	Pottery	MURR	MN H	Eby	LA 015016	2.62	32.94 0.2	0.2710 27	27.54 5.1	5.15 1.91	1 2.04	4 64.32	14.86	32.33
MVP0144	Group-B1	Mimbres-04B	Mimbres B/W Style III	Pottery	MURR	MN H	Eby	LA 015016	1.64	48.81 0.5	0.5541 35	35.78 6.5	6.54 6.44	14 3.52	2 86.78	8.33	18.30
MVP0145	Group-B1	Mimbres-04A	Mimbres B/W Style III flare Pottery	Pottery	MURR	NM	Eby	LA 015016	3.27	34.30 0.3	0.3520 26	26.80 5.50	50 3.85	35 2.77	70.69	15.78	23.62
MVP0146	Group-B1	Mimbres-04A		Pottery	MURR	MN H	Eby	LA 015016	2.12	36.52 0.4	0.4615 32	32.13 6.4	6.40 4.81	31 3.18	8 101.15	13.47	27.73
MVP0147	Group-B2	Mimbres-08	Mimbres B/W Style III	Pottery	MURR		Eby	LA 015016	3.68	34.47 0.4	0.4169 21	21.56 3.6	3.68 4.78	78 2.40	0 60.91	11.26	21.37
MVP0148	Group-B2	Mimbres-02A	Mimbres B/W Style III	Pottery	MURR	NM E	Eby	LA 015016	2.37	35.78 0.4	0.4963 25	25.96 5.24	24 4.54	3.11	1 71.34	14.90	34.34
MVP0149	Group-B	Unas.	Mimbres B/W Style II	Pottery	MURR		Eby	LA 015016	3.21	33.74 0.5	0.5158 21	21.74 4.40		35 3.14	4 67.63	3 7.19	27.34
MVP0150	Group-B1	Mimbres-04A	Mimbres B/W Style III	Pottery	MURR	MN H	Eby	LA 015016	1.38	36.00 0.4	0.4673 27	27.92 5.81	81 3.70	70 3.04	4 76.73	14.87	27.09
MVP0151	Group-B1	Mimbres-04C	Mimbres B/W Style II	Pottery	MURR	MM	Eby	LA 015016	1.73	33.29 0.3	0.3810 25	25.06 5.19	19 3.10	10 2.75	5 61.87	8.76	30.34
MVP0152	Group-B2	Mimbres-02A	Mimbres B/W Style III	Pottery	MURR	NM	Eby	LA 015016	1.91	37.68 0.4	0.4590 26	26.76 6.00	00 4.16	3.16	6 63.55	9.38	32.74
MVP0153	Group-A	Mimbres-01	Mimbres B/W Style III	Pottery	MURR	NM	Eby	LA 015016	2.45	56.08 0.7	0.7144 22	22.75 4.10	10 11.62	52 2.74	4 84.83	18.07	6.03
MVP0154	Group-B2	Mimbres-02B	Mimbres B/W Style III	Pottery	MURR	NM	Eby	LA 015016	4.65	45.52 0.5	0.5502 29	29.81 6.02		3.53	3 88.53	11.46	34.19
MVP0155	Group-B2	Mimbres-11	Mimbres B/W Style III	Pottery	MURR		Eby	LA 015016	3.49	38.49 0.4				53 3.40			43.88
MVP0156	Group-B2	Mimbres-11	Mimbres B/W Style II/III	Pottery	MURR		Eby	LA 015016	4.93	31.98 0.4	0.4181 25	25.74 4.37		11 2.81	1 76.37	76.87	44.14
MVP0157	Group-B	Unas.	Mimbres B/W Style III	Pottery	MURR		Eby	LA 015016	2.28	42.00 0.5						10.90	32.21
MVP0158	Group-C2a	Mimbres-49A	Mimbres B/W Style II	Pottery	MURR	NM	Eby	LA 015016	2.88	36.42 0.3	0.3291 32	32.63 5.98	98 2.73	73 2.24	4 66.20	15.44	53.18
MVP0159	Group-B1	Mimbres-04A	Mimbres B/W Style III	Pottery	MURR		Byron	LA 153465	2.20								18.68
MVP0160	Group-B1	Mimbres-04B	Mimbres B/W Style III	Pottery	MURR		Hyatt's Lower Ground		3.47								27.94
MVP0161	Group-B2	Mimbres-08	Mimbres B/W Style III	Pottery	MURR		Hyatt's Lower Ground		2.97							12.52	20.85
MVP0162	Group-B	Unas.	Mimbres B/W Style II	Pottery	MURR				1.50								23.64
MVP0163	Group-B1	Mimbres-04A	Mimbres B/W Style II/III	Pottery	MURR		Hyatt's Lower Ground		2.82						1	1	29.58
MVP0164	Group-B1	Mimbres-04A	Mimbres B/W Style III Effigy Pottery	/Pottery	MURR		2C Cienega		2.73								21.68
MVP0165	Group-C2	Unas.	Obliterated corrugated	Pottery	MURR		2C Cienega		3.58	_							16.42
MVP0166	Group-C2b	Mimbres-47	Mimbres Classic Corrugated Pottery	Pottery	MURR		Dutch Lathum's in Marcho	0	2.88	34.61 0.2							24.59
MVP0167	Group-B2	Mimbres-02A	Mimbres B/W Style II/III	Pottery	MURR		Dutch Lathum's in Marcho	0	1.97								34.68
MVP0168	Group-B	Unas.	Mimbres Classic Corrugated Pottery	Pottery	MURR		Uncle Lewis Plantation		4.37				67 7.33	33 3.25	_	18.46	47.24
MVP0169	Group-B1	Mimbres-04A	Mimbres B/W Style III	Pottery	MURR		Old Town	LA 001113	1.91	33.10 0.3	0.3537 23	23.37 4.39		98 2.48		8.49	20.41
MVP0170	Group-B1	Mimbres-09	Mimbres B/W Style II/III	Pottery	MURR		Old Town	LA 001113	3.27	59.85 0.5	0.5669 53	53.60 11.00	00 4.00	00 4.45	1	4.39	14.88
MVP0171	Group-B1	Mimbres-04A	Mimbres B/W Style III seed Pottery	Pottery	MURR		Old Town	LA 001113	2.07								24.06
MVP0172	Group-B1	Mimbres-04C	Mimbres Plain	Pottery	MURR	M M	Old Town	LA 001113	3.00	40.20 0.5		28.41 5.78	78 5.73	73 3.16			33.78
MVP0173	Group-B2	Mimbres-02A	Mimbres B/W Style III	Pottery	MURR		Old Town	LA 001113	7.83					30 3.33			37.94
MVP0174	Group-B1	Mimbres-04A	Mimbres B/W Style III	Pottery	MURR		Old Town	LA 001113	2.59	53.89 0.5					1	1	20.41
MVP0175	Group-B	Unas.	Mimbres B/W Style III	Pottery	MURR	NM NM	Old Town	LA 001113	1.98	33.66 0.4	0.4598 22	22.90 4.70	3.74	3.07	7 61.44	9.64	24.92

>	55.26	67.57	46.86	64.56	43.30	37.17	52.00	56.04	40.58	20.06	61.03	82.54	45.79	55.35	47.44	40.87	96.09	43.18	47.90	41.41	67.28	17.46	53.62	51.64	25.68	53.78	82.98	42.75	51.98	34.01	36.82	50.65	44.39	72.05	54.07	51.89	66.77	33.62	31.03	49.37	55.89	67.14	30.33	36.37
I	4744.5	4548.7	4036.8	5712.6	4737.3	3068.5	4022.4	5245.4	3426.3	1579.2	6901.4	4575.3	2519.6	5153.6	4595.3	4171.5	3151.9	2900.0	4779.7	5212.3	3815.0	3800.7	4132.1	5628.4	5208.7	5035.7	7.167.7	4595.6	4944.5	4260.0	3886.2	5062.6	3708.8	3900.4	3905.7	4750.7	4093.3	3273.4	3433.2	3304.1	3671.5	3841.1	4082.9	4356.0
NA	13125.1	15609.3	11395.0	10433.2	11664.4	16302.6	9934.3	13174.8	18787.0	8026.5	13384.7	20110.8	11955.4	15657.4	13459.7	11547.4	13565.6	13217.4	14449.9	17476.8	14637.7	13546.7	11843.8	11373.0	11268.7	15105.4	19087.5	18125.0	10710.9	10177.5	15809.1	13826.1	16378.2	15280.2	19241.7	13545.4	13734.4	17822.0	20804.3	15255.6	18120.8	13963.2	15558.4	15093.4
MN	329.6	722.4	421.0	1175.9	218.6	181.8	1908.2	200.6	235.5	396.5	285.3	721.0	570.9	291.3	488.9	189.2	229.4	236.2	306.9	165.1	233.7	157.2	928.9	511.4	1187.8	343.3	486.1	247.9	295.5	166.6	286.7	379.7	279.3	273.9	206.8	415.5	757.1	335.1	422.7	395.1	316.6	198.7	1355.5	574.7
¥	32419.9	26608.6	27849.7	31073.9	29202.0	32912.6	33792.1	30533.7	32167.0	16379.3	28285.7	24375.4	31101.6	31695.6	27699.8	32129.2	28706.6	31022.8	31418.2	29876.3	29801.2	32757.4	29004.6	34128.3	33472.2	32824.0	26224.6	31413.2	24382.9	29646.3	28086.5	27424.2	29321.0	34337.7	36051.8	31365.0	36345.5	32138.5	31479.9	36085.3	34546.6	25631.2	25028.6	25854.3
DY	4.127 3	3.621 2	4.356 2	2.995 3		3.949 3	3.320 3	4.490 3	4.236 3	2.187 1	4.559 2	2.356 2	4.762 3	3.766 3					3.832 3	3.903 2	3.482 2	2.435 3	4.081 2	4.090 3	3.407 3	4.749 3												2.951 3	7.668 3	3.877 3	4.407 3			3.674 2
CA	10816.1	13663.9	7323.5	8816.1	9296.9	10567.8	6469.1	9895.7	12645.5	9474.6	11963.0	16559.4	7153.5	11417.5	10400.6	5983.2	11172.9	15531.7	9301.6	14033.0	11987.9	6160.9	11235.6	8633.8	9918.3	13716.6	15251.7	12034.2	10507.8	6580.5	8933.4	13393.8	13285.6	13842.9	7520.4	10806.4	11167.2	12804.4	12777.1	10502.0	12466.3	12275.8	10993.6	15505.7
BA	730.7	692.9	546.7	367.6	422.9	815.0	461.3	582.9	720.7	262.2	564.3	714.1	8.003	894.5	725.9	626.3	492.4	405.5	804.6	700.4	505.3	216.7	341.7	426.2	471.9	546.6	810.7	813.5	978.9	500.2	369.7	803.9	725.6	9.899	1248.4	570.6	654.4	726.0	1127.6	888.3	734.2	9.809	832.3	402.5
AL	94345.7	79736.4	83083.5	7.96887	88018.3	79867.2	76156.0	88000.0	85176.5	78351.6	80538.6	88307.3	81149.0	79103.9	80141.9	73685.1	86249.5	77926.2	75654.9	90322.8	87342.3	99492.3	83470.7	79044.4	76436.3	77268.7	82923.2	85412.3	93708.6	76885.3	76031.9	91247.1	83844.6	-		83728.0	84671.7	80030.1	85206.4	84055.8	82408.1	88572.8	82112.4	72698.2
ZR	192.1	188.8	208.7	147.5	190.2	251.9	148.4	217.0	202.5	97.2	157.2		171.3	199.3	237.1		179.5	161.4	262.5	191.1	166.5	151.9	132.3	174.7	163.5	223.3		168.6	154.0	204.6	9.091	175.0	190.3	112.1	155.1	201.2		168.3	249.3		191.5	143.8	160.5	184.9
NZ	78.3	79.5	64.9	73.8	53.0	69.3	82.0	74.1	62.6	72.5	62.6	91.6	59.2	39.4	62.1	41.2	64.8	68.3	59.9	1.99	92.9	1.09	81.5	70.5	62.0	54.8	78.3	57.7	70.7	40.3	50.2	67.0	62.6	83.9	9.19	58.3	97.3	20.0	83.7	72.6	88.5	75.1	83.4	47.7
H	25.13	13.71	30.18			19.88	18.65	21.29	19.18	23.36	19.67	8.60	25.82	18.01			20.02	21.23	19.78		19.49	50.80	19.96	19.69		22.67			-					_				17.30	14.42	17.93	19.26			19.11
TA TB	199 0.75	916 0.69	511 0.83	241 0.60	353 0.86	358 0.81	702 0.59	967 0.74	502 0.89	355 0.43	233 0.87	0.66	298 0.85	926 0.72	0.79	731 0.45	1.4026 0.83	372 0.62	105 0.73	1.2198 0.64	203 0.81	558 0.41	1.4385 1.06	77.0 776	1.3956 0.54	1.3359 0.84	529 0.67	1.3093 0.74	347 1.01	1.4419 0.48					510 0.64	36 1.06		182 0.57	99 1.39	148 0.73	1.3365 0.77		740 1.08	1.4073 0.54
SR	200.4 1.5499	469.8 1.1216	133.8 1.6511		214.8 1.5353	253.7 1.3358	211.1 1.5702	240.8 1.6267	293.8 1.3602	82.3 1.3855	379.0 1.3233	586.6 0.7045	139.2 1.5298	314.0 1.3926			281.2 1.40	300.7 1.6372	259.3 1.5105		307.8 1.6203	96.7 2.0558	237.9 1.43	183.4 1.5927	253.6 1.39	347.8 1.33	435.7 0.9629											292.8 1.2182	249.7 0.9699	286.4 1.2448	297.2 1.33			283.5 1.40
SC	7.25 20	8.04 46	6.99	7.60 16	10.18 21	5.67 25	7.85 21	10.17 24	6.04 29	5.22 8	8.28 37	9.74 58	6.19 13	6.34 31			9.84 28	6.45 30	6.64 25		9.15 30	4.25 9	9.23 23	8.36 18	7.42 25	8.27 34	9.72 43											5.39 29	7.89 24	6.24 28	7.17 29			6.13 28
SB	0.6105 7	1.1490 8	0.4615 6			0.3688 5	7677.0	0.4538 10	0.2737 6	0.2541 5	0.4870 8		0.3615 6	0.3525 6	6			0.3699 6	0.3926 6	0.3606	0.3722 9	0.8271 4	0.8191 9	0.6737		_												0.2332 5	0.4938 7	0.2889 6		—		0.3720 6
RB	212.78 (120.83	152.58 (149.80 (183.54 (146.31	145.79 (53.56 (88.73 (98.99	183.48 (126.92			141.41 (170.06 (139.07 (144.31 (208.20	186.87		159.73 (130.44 (121.78 (132.40 (131.47 (137.87
Z	36.8 2	0.0	0.0			0.0	0.0	17.2	0.0	0.0	28.7	0.0	0.0	0.0		0.0		0.0	0.0	0.0	0.0	0.0	0.0	0.0		0.0												0.0	0.0	30.2	0.0			0.0
土	7.12	7.35	6.82	7.24	7.83	8.34	7.47	8.88	7.30	6.11	6.40	5.15	6.42	8.56	9.64	6.54	7.36	6.24	10.04	8.53	7.21	5.55	6.15	6.92	9.60	7.76	8.34	88.9	5.55	8.57	5.99	6.71	7.04	5.17	6.34	7.96	92.9	6.02	00.6	5.81	7.08	6.34	6.53	7.07
FE	20875.1	28333.4	23019.6	24031.6	21650.0	20066.5	24311.2	22714.9	20843.5	7251.5	22389.7	37342.5	19094.1	20267.7	24572.2	16838.0	23237.0	18501.8	21603.9	24050.1	21991.4	12119.5	25392.1	22578.1	23821.3	19957.8	35812.1	20609.6	26309.6	16664.0	17565.0	26082.9	22126.2	36975.5	23630.5	22253.1	29733.5	16965.9	20798.8	19467.2	23699.1	25491.1	24097.5	16997.7
EU	1.1956	1.3201	1.0965	0.8944		1.1818	0.8616		1.3609	0.3657	1.0368	1.3311	1.1281	1.1080		_	0.9817	0.7437	1.1192	1.2064	1.0882	0.4742	1.0601	1.0952	0.8545													1.0054	2.3105	1.0942	1.0792			13.24 0.8461
CS	12.66	7.64	5.37	7.54		4.56	7.18	21.23	4.03	2.77	8.75		5.58	3.44			20.14	10.63	4.53	5.48	17.61	15.07	36.45	7.79		14.98												3.72	3.48	4.47	4.50		4.96	13.24
ANID	MVP0131	MVP0132	MVP0133	MVP0134	MVP0136	MVP0137	MVP0138	MVP0139	MVP0140	MVP0141	MVP0142	MVP0143	MVP0144	MVP0145	MVP0146	MVP0147	MVP0148	MVP0149	MVP0150	MVP0151	MVP0152	MVP0153	MVP0154	MVP0155	MVP0156	MVP0157	MVP0158	MVP0159	MVP0160	MVP0161	MVP0162	MVP0163	MVP0164	MVP0165	MVP0166	MVP0167	MVP0168	MVP0169	MVP0170	MVP0171	MVP0172	MVP0173	MVP0174	MVP0175

ANID	macro grp	Chem2012	CERAMIC TYPE	MATERIAL	SOURCE	STATE	SITE NAME	SITE NO	AS	LA	Π	ND	SM	Λ	YB CE	CO	CR
MVP0176	Group-B	Unas.	Mimbres B/W Style II/III	Pottery	MURR			LA 001113	3.01	40.70	0.4365 2		4.87 5.	5.61 2.79	79 65.08	12	13.79
MVP0177	Group-B1	Mimbres-04B	Mimbres B/W Style III	Pottery	MURR	MN	Old Town	LA 001113	3.57		0.5510 3	33.23 6	6.29 6.	6.96 3.28	28 79.44	4 10.45	20.95
MVP0178	Group-B	Unas.	Mimbres B/W Style III	Pottery	MURR	NM	Old Town	LA 001113	2.13	43.99 0.	0.4885 2	24.95 4	4.24 4.	4.64 2.91	73.70	0 12.88	15.97
MVP0179	Group-C2	Unas.	Mimbres B/W Style III	Pottery	MURR	MN	Old Town	LA 001113	0.00	38.12 0.	0.3477 3	34.80 6	6.67 3.	3.87 2.48	18 74.85	5 16.33	61.47
MVP0180	Group-C1	Mimbres-21	Mimbres B/W Style II	Pottery	MURR	MN	Old Town	LA 001113	1.44								
MVP0181	Group-B1	Mimbres-04A	Mimbres B/W Style III	Pottery	MURR	M	Old Town	LA 001113	2.51						1	·-	
MVP0182	Group-B	Unas.	Mimbres B/W Style III	Pottery	MURR	M	Old Town	LA 001113	2.69								
MVP0183	Group-B2	Mimbres-11	Mimbres B/W Style III	Pottery	MURR	MN	Old Town	LA 001113	4.68								
MVP0184	Group-C2a	Mimbres-49A	Mimbres B/W Style III	Pottery	MURR	M	Mitchell	LA 012076	2.73					2.96 2.81			
MVP0185	Group-B2	Mimbres-11	Mimbres B/W Style II	Pottery	MURR	NM	Perrault	LA 018891	0.00		0.5440 2			4.64 3.30		5 18.87	40.80
MVP0186	Group-B2	Mimbres-02A	Mimbres B/W Style III	Pottery	MURR	NM	Old Town	LA 001113	1.55		0.6074 3	37.08		6.18 3.74	74 85.38	8 10.73	37.01
MVP0187	Group-B2	Mimbres-02A	Mimbres B/W Style III	Pottery	MURR	NM	Eby	LA 015016	3.04	35.97 0.	0.5203 2		5.50 3.	3.09 3.28	28 65.18	8 10.05	36.47
MVP0188	Group-B1	Mimbres-04A	Mimbres B/W Style III	Pottery	MURR	¥	Eby	LA 015016	2.81	40.00 0.			7.00 4.	4.29 3.35	35 80.80		24.05
MVP0189	Group-B1	Mimbres-04B	Mimbres B/W Style III	Pottery	MURR	MN	Eby	LA 015016	1.76	44.19 0.	0.5271 3	32.46 7	7.07	6.75 3.27	27 86.48	8 14.40	21.70
MVP0190	Group-B2	Mimbres-02A	Mimbres B/W Style III	Pottery	MURR	¥	Ft. Cummings	LA 075994	3.14	35.26 0.	0.4948 2		5.57 4.	4.97 3.04	04 69.40	0 13.28	37.45
MVP0191	Group-B2	Mimbres-02A	Mimbres B/W Style III	Pottery	MURR	MN	Eby	LA 015016	2.35	44.34 0.	0.5607 3	35.35 7	7.30 5.	5.18 3.56	95 82.90	0 9.59	34.76
MVP0192	Group-A	Mimbres-01	Mimbres B/W Style III	Pottery	MURR	MN	Eby	LA 015016	2.29	57.30 0.	0.9467 2		4.97 19.	19.63 3.18	18 90.73	3 20.46	4.23
MVP0193	Group-B	Unas.	Mimbres B/W Style III	Pottery	MURR	M	Eby	LA 015016	1.78	40.99 0.	0.5440 2	21.86 4	4.57 6.	6.57 2.91	71 66.75	5 14.15	28.13
MVP0194	Group-A	Mimbres-01	Mimbres B/W Style III	Pottery	MURR	M	Old Town	LA 001113	2.21	45.04 0.	0.6049 2	28.61 5	5.62 7.	7.19 3.18	18 81.07	7 8.72	19.29
MVP0195	Group-B1	Mimbres-04A	Mimbres B/W Style III	Pottery	MURR	MN	Eby	LA 015016	1.74	60.32 0.	0.6906	46.20 8	8.48 6.	6.02 4.11	11 106.46	6 9.30	25.47
MVP0196	Group-B2	Mimbres-02A	Mimbres B/W Style III	Pottery	MURR	MN	Cow Springs Draw		1.85	41.79 0.	0.5593 2	28.97 5	5.87 5.	5.41 3.30	30 86.73	3 8.88	34.90
MVP0197	Group-B2	Mimbres-11	Mimbres B/W Style II	Pottery	MURR	MN	Old Town	LA 001113	2.66	37.17 0.	0.5452 2	27.45 5	5.47 5.	5.06 3.03	3 70.50	0 18.18	39.82
MVP0198	Group-B1	Mimbres-04B	Mimbres B/W Style III	Pottery	MURR	MN	Old Town	LA 001113	4.03	52.79 0.	0.6197 4	40.36 8	8.79 8.	8.71 3.37	37 88.33	3 10.63	25.55
MVP0199	Group-C2	Unas.	Mimbres B/W Style II	Pottery	MURR	MN	Old Town	LA 001113	2.37	43.88 0.	0.3790 4			2.55 2.65		1	64.44
MVP0200	Group-A	Mimbres-01	Mimbres B/W Style III	Pottery	MURR	NM	Old Town	LA 001113	0.00				3.52 6.	6.50 2.42	12 63.33	3 17.16	
MVP0201	Group-C2a	Mimbres-49A	Mimbres B/W Style II	Pottery	MURR	NM	Old Town	LA 001113	4.55			45.89 8		2.48 2.86			51.22
MVP0202	Group-B2	Mimbres-11	Mimbres B/W Style III	Pottery	MURR	M	Old Town	LA 001113	2.92								40.19
MVP0203	Group-B1	Mimbres-04B		Pottery	MURR	MN	Old Town	LA 001113	2.73							1	24.67
MVP0204	Group-B2	Mimbres-02A		Pottery	MURR	M	Old Town	LA 001113	2.06	41.53 0.				5.09 3.22		_	32.52
MVP0205	Group-B2	Mimbres-02A	Mimbres B/W Style III	Pottery	MURR	M	Old Town	LA 001113	2.66								38.32
MVP0206	Group-B1	Mimbres-04A	Mimbres B/W Style III	Pottery	MURR	N	Perrault	LA 018891	3.21						_		
	Group-B2	Mimbres-02B	Mimbres B/W Style III	Pottery	MURR	∑	Perrault	LA 018891	4.08	_							
	Group-B2	Mimbres-11	Mimbres B/W Style III	Pottery	MURR	M	Perrault	LA 018891	4.33							8 24.68	42.07
MVP0210	Group-B	Unas.	Vertical corrugated	Pottery	MURR	M	Perrault	LA 018891	2.94	_	0.4244 4		9.09 2.	2.96 3.45	112.50	0 14.57	36.03
MVP0211	Group-B1	Mimbres-04B	Mimbres B/W Style II/III	Pottery	MURR	NM	Perrault	LA 018891	2.29	54.82 0.	0.6366 4	42.22 8	8.14 8.	8.04 3.89	39 95.42	9.26	26.87
MVP0212	Group-B2	Mimbres-02A	Mimbres B/W Style III	Pottery	MURR	¥	Perrault	LA 018891	1.87	42.92 0.	0.5121 3	31.62 5	5.89 6.	6.16 3.44	14 70.25		38.68
MVP0213	Group-B1	Mimbres-04A	Mimbres plain	Pottery	MURR	M	Perrault	LA 018891	2.02	46.50 0.	0.4835 3	37.28 7	7.01 4.	4.27 3.51	51 88.66	6 17.39	19.73
MVP0214	Group-B	Unas.	Three Circle Corrugated	Pottery	MURR	MN	Perrault	LA 018891	90.9	36.12 0.	0.4904 2	25.11 4	4.72 4.	4.71 3.18	18 65.61	1 24.88	33.82
MVP0215	Group-C2	Unas.	Mimbres B/W Style II	Pottery	MURR	¥	Perrault	LA 018891	3.87	29.61 0.		24.79 4	4.87 2.	2.30 1.8	1.80 58.83	3 15.42	26.96
MVP0216	Group-B1	Mimbres-04B	Mimbres B/W Style III	Pottery	MURR	MN	Perrault	LA 018891	3.22	58.12 0.	0.5646 4	48.46 9	9.29 6.	6.18 3.83	33 101.52	2 14.26	23.98
MVP0217	Group-B2	Mimbres-11	Mimbres B/W Style II/III	Pottery	MURR	NM	Perrault	LA 018891	3.44	34.31 0.	0.4610 2	26.02	4.91 4.	4.48 3.11	11 76.22	2 32.13	43.99
MVP0218	Group-B1	Mimbres-04B		Pottery	MURR	M	Perrault	LA 018891	1.99								22.12
	Group-B1	Mimbres-04C		Pottery	MURR	MN	Perrault	LA 018891	2.47						l	ļ	35.01
MVP0220	Group-B1	Mimbres-04B	Mimbres B/W Style III	Pottery	MURR	MN	Perrault	LA 018891	2.35	52.22 0.	0.5606 3	34.15 6	96.9	6.95 3.62	52 90.15	5 5.66	21.02

>	39.53	40.76	49.62	127.36	54.06	54.26	50.25	64.50	88.45	53.49	66.11	41.83	55.20	43.96	74.81	59.94	25.37	37.01	40.77	66.20	38.70	38.40	52.13	96.78	37.33	72.35	49.95	43.01	45.59	57.52	62.49	90.89	60.09	55.48	54.56	47.86	35.56	43.77	63.77	48.98	58.63	36.02	70.84	45.08
=	4178.1	4802.3	3449.9	5610.3 1	2945.9	4484.1		4894.1	4573.6	9.9909	4276.4	5118.2	4498.9	4290.7	4320.6		2483.6	3640.5	3493.4	3593.4	4785.3	4809.0	3539.7													_	3360.7	4385.1	4534.9		4575.4	3034.5	4795.1	3136 3
NA	14233.7	12319.0	9572.1	16020.5	21410.8	16960.0	12940.3	11812.0	17555.0	14665.4	15535.7	12317.5	14571.4	12409.1	13836.8	15521.2			17750.9	16993.6	12888.6	14763.1	11144.8	14998.3														10897.5	18254.7		10549.1			117077
MN	170.8 14.	270.2 12:	406.0		1025.0 21	869.8 16	313.0 12	766.9 11	819.6	445.4 14	222.5 15	168.3 12	425.1 14	378.0 12	262.7 13			118.9 11	160.5 17	332.4 16	203.4 12	336.1 14	225.5 11	334.7 14						_	_			`				992.7 10	616.8 18.	,				10F 0 11
¥	33372.5 1	30616.8 2	42518.3 4		25378.4 10	30879.0		32548.5 7	25182.5 8	32600.1 4	26203.2 2	28432.8 1	29730.4 4	30770.6	27642.8 2		30052.3 1	33736.6	34424.8 1		31209.5 2	32412.4 3	28147.2 2			_																- 1	_	20000 1
DY	3.172 333	4.233 306	3.243 425	4.109 176	3.263 253	5.103 308	4.946 277	4.113 32E	3.253 251	4.079 326	5.862 262	4.804 284	4.942 297	4.800 307	4.815 276		2.743 300	3.077 337	4.623 344	6.462 27E	4.298 312	3.325 324	5.461 281					- 1										3.228 454	2.626 223					7 000 A
CA	8701.8	17040.0 4		18449.3 4.	14107.8 3				16074.4 3	9813.5 4.0	13426.8 5.		10326.8 4.	7547.4 4.	11832.9 4.8		18855.7 2.	6487.5 3.0	8300.9		8024.4 4	9620.4 3.	8060.6 5.																					2001
A			.0 13820.0	`		.6 11798.1					Ì		Ì				`							1		_							ľ	_				.1 12516.7	`				_	
- BA	5 690.7	5 527.0	350.0		5 833.5	3 905.6	500.0		874.3	5 487.9	3 678.7	9 511.8	3 770.3) 556.2	9 292.8				574.2	708.5	3 525.5	393.8	3 585.4											_				672.1						5217
AL	88626.5	81344.5	77666.0	9.60698	86860.5	90648.3	83080.5	80092.7	86289.8	81943.5	86131.3	84902.9	83788.3	82956.0	6.79896	86017.4	101894.9	89781.9	81591.2	86708.7	85909.3	75621.6	92426.8	83934.2	88899.1	93202.3	71608.3	87175.1	83545.2	88513.4	86687.3	80979.9	77239.4	78955.6	87871.1	90982.6	79165.2	74703.7	95303.6	85714.3	77450.5	84923.0	92762.0	79617 8
ZR	236.1	191.9	140.7	170.3	145.7	190.4	177.1	207.0	266.6	186.7	249.0	235.5	255.0	183.8	179.9	216.0	225.2	233.1	202.4	240.3	174.0	177.8	178.7	160.5	155.9			184.5			128.4	162.3			185.1	191.6	177.2	152.4	193.2	158.2	194.0	185.4	191.0	1756
NZ	57.6	54.7	54.7	84.4	83.1	64.1	79.5	67.5	89.3	63.3	62.2	56.4	56.4	52.2	67.9	7.09	55.4	0.09	40.2	82.1	63.7	82.2	6.99	82.8	53.3	119.0	67.0	75.9	55.9	75.5	73.0	6.69	56.9	147.0	74.5	72.1	65.0	93.9	71.6	55.5	55.2	9.09	67.2	60 2
HL	24.39	27.05	30.42		6.37	21.11		18.82	12.75	19.51	18.17	20.04	18.79		19.14	18.96	51.63	28.18	30.76	19.56		20.20	26.95	61.6			18.74			- 1								20.92	7.94					25 33
TB	0.65	0.77	0.48	0.85	0.67	1.03	0.95	0.71	0.67	0.72	0.95	0.73	0.88	0.88	0.79	1.04	0.45	0.55	0.74	1.28	0.79	99.0	0.99	1.23	0.39		0.67						_	_				0.56	0.51	1.08	0.58			0.85
TA	1.5982	1.5680	1.7745	0.8798	0.7026	1.3578	1.4238	1.5895	1.1683	1.6183	1.3504	1.5144	1.5590	1.6473	1.3077	1.4431	2.5426	1.8204	1.7625	1.3637	1.5332	1.6599	1.5098	0.8812	1.8002	1.0818	1.5526	1.4884	1.5749	1.4650	1.2699	1.5348	1.5093	1.0430	1.4281			1.6380	0.8184	1.5111	1.5638	1.5782	1.2202	1 5296
SR	212.2	179.1	207.5	421.9	411.8	311.0	206.9	227.8	394.9	222.6	290.1	195.6	236.2	147.0	275.2	389.3	148.6	220.4	203.9	304.1	231.8	343.8	176.6	508.1	254.1	400.6	261.0	152.0	241.0	313.1	269.5	214.5	241.1	237.0	170.9	198.1	287.5	297.9	460.9	158.4	226.0	116.4	272.3	165.3
SC	5.78	6.64	4.84	11.34	6.15	7.31			66.6	7.82	10.77	9.57	7.16	6.63	11.32	l	3.84	8.35	5.19	7.84	8.78	7.38	8.71	12.49		_				_				_		1		6.81		7.26	7.60			6.80
SB	0.3313	0.4010	0.7990	0.3431	1.0993	0.3294	0.4515	0.5655	0.4476	0.5454	0.3719	0.4206	0.3495	0.3707	0.4425	0.4025	0.7152	0.4759	0.5361	0.3890	0.4056	0.5623	0.3617	0.4372	0.6436	0.3239	0.6025	0.4558	0.4394	0.4425	0.3710	0.8767	0.6854	0.5433	0.4354	0.5004	0.2322	0.8681	0.3754	0.3390	0.6271	0.4171	0.3656	0.3736
RB	160.12	177.64	230.01	70.97	116.04	130.30	154.06	191.48	115.38	189.54	133.27	140.33	135.87	161.79	141.58	140.71	179.32	206.97	177.97	138.66	162.26	172.50	151.80	74.42	219.36	130.29	200.10	167.87	168.67	147.81	134.64	195.23	190.50	153.53	167.10	170.18	128.06	202.40	92.88	157.05	197.72	174.95	116.10	184.21
Z	0.0	0.0	0.0	26.9	24.0	0.0	0.0	0.0	0.0	0.0	30.3	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	32.4	0.0	0.0	0.0	23.8							47.9			_				0.0	0.0	0.0		29.5		0.0
生	9.03	6.51	5.88	7.25	6.57	6.82	5.87	69'L	10.74	7.26	7.60	8.92	9.05	6.15	70.7	7.74	6.40	8.23	7.51	8.16	86'L	7.37	6.13	2.86	6.19				8.92	7.75	5.82	6.89	7.25	8.66	5.88	8.15	6.54	6.22	5.59	6.12	7.44	7.00		6.42
FE	21078.6	19051.1	18245.2	27938.6	23526.4	25946.9	22871.3	22411.5	37438.5	21245.4	24236.9	18829.8	24189.7	19813.7	25936.1	25789.0	8928.7	18197.3	13331.8	26238.8	20634.6	20273.2	25624.9	29464.6	16812.2	37723.0	21069.8	23317.6	19689.1	25026.3	21924.0	24068.0	22828.6	34020.8	25454.6	22270.0	23160.3	27374.3	31343.7	21555.0	23691.2	20290.0	26307.1	21709.9
ED	0.8894	1.0367	9.60 0.7023	1.4974	1.1063	1.4295			1.2965	1.1213	1.3999	1.0103	1.2724	1.1786	1.0639	1.3923	0.4718	0.6735	0.9227	1.6083		_	1.3067	1.6217	0.5567			1.3010	_									7.00 0.8209			0.9442	1.1667		1,1712
SS	4.00 (5.18	09.6		15.26	4.74		7.32	4.09	6.98	13.91	18.32	4.65	5.50	17.81		11.31		7.57	4.74	17.72 0.9571	5.81 1.0277	6.02	3.53	11.37	4.59		6.16				41.58	6.58		6.21	17.69 0.9421	3.80	7.00 (4.57		7.05	5.62	4.16	5.70
ANID	MVP0176	MVP0177	MVP0178	MVP0179	MVP0180	MVP0181	MVP0182	MVP0183	MVP0184	MVP0185	MVP0186	MVP0187	MVP0188	MVP0189	MVP0190	MVP0191	MVP0192	MVP0193	MVP0194	MVP0195	MVP0196	MVP0197	MVP0198	MVP0199	MVP0200	MVP0201	MVP0202	MVP0203	MVP0204	MVP0205	MVP0206	MVP0207	MVP0208	MVP0210	MVP0211	MVP0212	MVP0213	MVP0214	MVP0215	MVP0216	MVP0217	MVP0218	MVP0219	MVP0220

ANID	macro grp	Chem2012	CERAMIC TYPE	MATERIAL	SOURCE	STATE	SITE NAME	SITE NO	AS	ΓA	ΓΩ	ND SM	U N	YB	CE	00	CR
MVP0221	Group-B1	Mimbres-04B		Pottery	MURR			LA 018891	2.45	47.07 0.5244		33.03 6.67	7 6.52	3.21	83.21	10.84	21.35
MVP0222	Group-B1	Mimbres-04B	Mimbres B/W Style III	Pottery	MURR	NM	Perrault	LA 018891	1.74	59.03 0.5591		38.78 7.63	3 4.46	3.89	94.00 1		21.92
MVP0223	Group-C2a	Mimbres-49A	rugate	Pottery	MURR	NM	Perrault	LA 018891	1.46	47.34 0.4423		45.22 8.47	7 2.27	3.31	106.66 1	12.89	54.72
MVP0224	Group-B1	Mimbres-04A	Mimbres B/W Style III	Pottery	MURR	MN	Pruitt Ranch	LA 001117	3.61	52.06 0.5865		39.79 7.91	1 5.86	3.82	93.18	8.50	24.29
MVP0225	Group-B1	Mimbres-04A		Pottery	MURR	NM	Pruitt Ranch	LA 001117	2.74				_	3.62			21.60
MVP0226	Group-A	Mimbres-01	j	Pottery	MURR	NM	Pruitt Ranch	LA 001117	1.64	47.48 0.3940		17.45 3.92	2 16.27	2.59	74.14 1	17.89	91.9
MVP0227	Group-B	Unas.	_	Pottery	MURR	M	Pruitt Ranch	LA 001117	2.46	34.52 0.3919		31.64 4.95	5 2.88	2.77	67.85 1		33.02
MVP0228	Group-C2a	Mimbres-42	Mimbres B/W Style II	Pottery	MURR	M	Pruitt Ranch	LA 001117					2 2.60				59.03
MVP0229	Group-A	Mimbres-10	ugatec	Pottery	MURR	NM	Pruitt Ranch	LA 001117				1			120.52		33.99
MVP0230	Group-B2	Mimbres-02A	Mimbres B/W Style III	Pottery	MURR	MN	Pruitt Ranch	LA 001117	1.82			31.47 6.52	2 3.20	3.56	79.38 1	19.93	37.39
MVP0231	Group-C2b	Mimbres-47	Mimbres Classic Corrugated Pottery	Pottery	MURR	MN	Pruitt Ranch	LA 001117	3.47	43.72 0.3044		36.05 7.06	5 2.76	2.42	98.36 1	17.37	24.81
MVP0232	Group-B1	Mimbres-04A	Mimbres B/W Style III	Pottery	MURR	MN	Pruitt Ranch	LA 001117	2.53	36.36 0.4241		26.72 5.74	4 4.63	3.00	76.14 1	15.30	25.67
MVP0233	Group-C2	Unas.	ed:	Pottery	MURR	MM	Pruitt Ranch	LA 001117		37.74 0.3704		.67 5.72					24.26
MVP0234	Group-B2	Mimbres-11		Pottery	MURR	MM	Pruitt Ranch	LA 001117		36.06 0.4518			5 3.50	3.27	72.47 2	27.85	48.71
MVP0235	Group-B1	Mimbres-04A		Pottery	MURR	MM	Pruitt Ranch	LA 001117		35.88 0.4006	006 27.41			2.78	67.86 1	15.33	24.91
MVP0236	Group-C2a	Mimbres-49A		Pottery	MURR	MM	Mimbres Peak			38.04 0.3432		31.10 5.88	8 3.30	2.61	75.97	14.64	50.77
MVP0237	Group-B1	Mimbres-04A		Pottery	MURR	MM	Red Mountain					_					19.87
MVP0238	Group-B1	Mimbres-04A	Mimbres B/W Style III	Pottery	MURR	MN	site uncertain		2.01	36.05 0.3769	769 23.71	.71 4.87	7 3.94	2.55	96:39	7.80	23.95
MVP0239	Group-B	Unas.	Mimbres B/W Style III	Pottery	MURR	MN	site uncertain		2.74	33.16 0.4861		20.69 3.96	5 3.04	3.18	50.62	7.95	17.83
MVP0240	Group-B2	Mimbres-08	Mimbres B/W Style III Pottery	Pottery	MURR	MN	2C Cienega		3.14	32.00 0.4016		17.83 3.51		2.39	55.55 2		23.33
MVP0241	Group-B	Unas.	Mimbres Classic Corrugated	Pottery	MURR	MN	2C Cienega		2.57	39.49 0.2980		30.89 5.03	3 2.34	2.24	68.28 1	15.85	29.41
MVP0242	Group-B	Unas.	Mimbres B/W Style III Jar	Pottery	MURR	MN	Perrault	LA 018891	3.97	40.35 0.4986		28.12 5.31	1 5.30	3.14	75.96 2	22.01	31.92
MVP0243	Group-B1	Mimbres-04A	Mimbres B/W Style III	Pottery	MURR	M	2C Cienega		2.41	35.93 0.4125		26.54 5.09	9 3.58		16.09	7.35	25.54
MVP0244	Group-B	Unas.		Pottery	MURR	MN	Perrault	LA 018891		50.16 0.5509		44.42 8.18	8 4.58	3.59	98.79 2		31.06
MVP0245	Group-B1	Mimbres-04A	Mimbres B/W Style III	Pottery	MURR	NM	Mitchell	LA 012076	1.81	56.36 0.6034		50.08 10.08	8 4.93	4.33	105.22		17.64
MVP0246	Group-B1	Mimbres-04A		Pottery	MURR	MN	Eby	LA 015016									20.59
MVP0247	Group-B1	Mimbres-04A	_	Pottery	MURR	M	Ranger Station	LA 005066	_				3.21				20.99
MVP0248	Group-A	Mimbres-01	=	Pottery	MURR	MN	Uncertain							2.84	1		8.92
MVP0249	Group-B1	Mimbres-04C		Pottery	MURR	M	Harris	LA 001867	1.77	39.75 0.4214		33.07 6.05		2.96			34.35
MVP0250	Group-B1	Mimbres-04C	_	Pottery	MURR	MN	Harris	LA 001867									42.90
MVP0251	Group-B1	Mimbres-04C	_	Pottery	MURR	M	Harris	LA 001867		_							38.73
MVP0252	Group-C2b	Mimbres-47		Pottery	MURR	M	Harris	LA 001867						1.34			23.83
MVP0253	Group-C2b	Mimbres-41		Pottery	MURR	M	Harris	LA 001867							-		23.57
MVP0254	Group-B1	Mimbres-04B	_	Pottery	MURR	M	Harris	LA 001867						_			22.04
MVP0255	Group-B1	Mimbres-04C		Pottery	MURR	M	Harris	LA 001867		66.88 0.7359		55.97 11.18		_	_		45.76
MVP0256	Group-B2	Mimbres-08		Pottery	MURR	MM	Stewart Pueblo	Stewart Pueb		31.47 0.3859			8 3.88	2.31			16.79
MVP0257	Group-B1	Mimbres-04C		Pottery	MURR	MN	Pruitt Ranch	LA 001117		47.69 0.4653		43.13 8.28	8 3.20		92.59	6.29	32.96
MVP0258	Group-B2	Mimbres-02A		Pottery	MURR	MM	Pruitt Ranch	LA 001117		43.15 0.5803		27.93 5.55	5 4.92	3.21	68.63	5.02	34.18
MVP0259	Group-B1	Mimbres-04B	Mimbres B/W Style III	Pottery	MURR	¥	Pruitt Ranch	LA 001117	2.37	40.66 0.5015		27.03 5.82	2 5.56	2.90	69.07	4.64	24.29
MVP0260	Group-B1	Mimbres-04B		Pottery	MURR	MM	Pruitt Ranch	LA 001117	5.26	64.36 0.6057		45.54 9.05	5 5.37		103.45	6.72	22.88
MVP0261	Group-B1	Mimbres-04A		Pottery	MURR	MM	Pruitt Ranch	LA 001117	3.71	41.04 0.5710		34.02 6.47	7 7.51	2.95	78.65	5.07	20.69
MVP0262	Group-B2	Mimbres-08		Pottery	MURR	MN	Pruitt Ranch	LA 001117			•		_	2.48			23.92
MVP0263	Group-B2	Mimbres-08		Pottery	MURR	M	Pruitt Ranch	LA 001117						2.27			22.55
MVP0264	Group-B1	Mimbres-04A	Mimbres B/W Style III	Pottery	MURR	MN	Pruitt Ranch	LA 001117	1.82	36.15 0.3973	73 28.21	.21 5.27	7 3.07	2.71	96:39	3.89	21.99

>	41.07	38.76	62.28	53.76	46.67	14.77	36.69	84.67	59.13	65.37	69.34	35.51	97.71	55.69	37.70	76.87	42.00	42.59	31.28	37.96	42.64	54.09	36.41	16.69	49.74	50.81	58.97	31.70	73.00	76.07	76.99	47.73	85.43	46.67	69.32	35.94	63.36	45.43	48.01	61.42	64.79	41.64	38.66	36.20
F	3367.1	3709.6	5717.5	3670.2	3543.5	2326.0	4403.4	4817.8	3426.6	4825.3	4510.7	5585.9	6277.1	5502.2	4704.7	5014.5	5221.9	3391.9	2550.0	3954.2	4055.5	5468.9	3435.3	9.9819	3182.2	4734.3	4311.3	2421.1	5597.9	4123.0	4527.1	3694.8	5003.3	3030.1	4976.5	3106.1	5969.5	5629.5	4563.6	3910.0	6118.2	4098.4	3276.3	3847.2
NA	12165.3	12640.4	13497.9		15921.8	15832.9	16105.3	25267.0	13652.2	14873.7	20355.1	15545.0	20820.8	10929.1			18275.1	17840.0	12094.2	10399.0	15645.0	12611.5	16688.2	15359.5	16770.4		17429.7										18643.1	12823.1	1179.1	11811.8				16476.7
NM	356.0 12	343.0 12	250.6 13	441.5 13	416.8 15	110.1	308.0 16	626.3 25	324.7 13	204.2	214.1 20	558.0 15	347.0 20	799.5 10		543.8 18	218.0 18	271.0 17	546.4 12	155.9 10	263.6 15	890.9 12	331.6 16	466.2 15	1	`	347.9 17		390.9 15			- 1	,	·-				205.4 12	285.2 11	`	211.2			272.6 16
¥	29117.6	33798.3	23354.7 2	28795.7	31300.9	32882.4 1	33547.9 3	28311.8 6	35273.6 3	26744.2 2	36883.9	31003.0 E	38284.8	33711.6			33408.2	31824.3 2	22726.7 5	32303.0	49753.3	34065.6	29242.6	29823.1			28556.5						_					31958.5 2	27837.1 2			~		30830.9
DΥ	4.568 29	5.377 33	5.198 23	5.812 28		1.989 32	3.740 33	2.913 28	9.360 35.	4.828 26	4.397 36	3.948 31	3.612 38	3.616 33		3.556 29	4.616 33	3.741 31	2.792 22	2.506 32	3.274 49	3.868 34	3.398 29.	6.254 29		4.757 39	4.640 28								- 1		- 1	4.733 31						3.560 30
CA	7447.3 4.			10279.7 5.	9758.0 4.	7088.9 1.	15925.9 3.	18048.4 2.	11376.6 9.	13337.1 4.	8924.0 4.	11512.6 3.		8874.8 3.		12435.8 3.	11768.2 4.	13572.4 3.	16639.9 2.	5872.9 2.	12084.9 3.		12485.2 3.	16622.2 6.			11939.3 4.											8540.0 4.	13127.6 3.					13919.3 3.
4		10084.1	5 14083.4	,			ľ					`	_		`	`						7 11092.0								•					•				,		1			`
BA .	511.7	794.0	1045.5			192.7	729.5	1013.6	464.9	608.4	1067.0	852.0	1512.6	565.3			820.9	848.4	293.1	459.6	887.0	414.7	752.6			_	801.2						_				1				774.7			676.5
AL	81651.0	82417.0	92011.9	86151.1	87885.3	97123.9	74728.6	94650.9	106457.8	89341.1	87216.9	79772.3	83531.5	85031.2	83122.3	94491.8	90920.7	87128.7	75293.3	76656.4	91884.3	82937.8	82928.1	90117.5	94622.2	85832.3	93245.2	102536.6	87120.3	90270.9	94466.4	88908.1	95246.0	83497.9	97623.6	71476.7	90055.8	89749.2	94229.5	86957.7	99615.5	84768.6	73681.9	82345.3
ZR	179.8	174.8	214.3	193.8	221.2	203.7	163.9	150.4	267.8	172.7	185.1	225.4	283.0	180.5	149.5	174.7	173.8	174.5	108.2	174.5	152.6	154.8	170.9	235.5	175.1	229.4	176.0	127.7	164.8	228.8	168.7	160.4	197.6	166.8	231.4	199.8	236.4	220.3	121.2	179.8	341.4	166.8	155.7	153.9
NZ	53.6	58.0	9.68	78.9	76.2	49.2	8.09	0.06	126.3	6.69	9:59	61.9	101.2	6.89	64.2	67.5	55.9	62.9	46.3	39.4	67.4	6.09	57.9	71.6	6.99	75.6	69.7	929	87.4	90.2	99.0	131.9	75.9	53.8	87.8	42.9	94.1	76.0	92.2	124.4	86.2	48.6	50.7	50.9
H	23.43	24.05	13.69	21.55	20.72	51.02	16.67	8.24	54.94	17.61	9.21	18.49	12.83	18.39	17.28	13.18	21.73	17.26	24.93	24.74	14.90	20.38	19.08	20.19		19.62	20.09	44.99	15.28	15.59	15.40	7.49			18.55	22.28	13.90	21.66	23.81	24.06	17.06			17.30
TB	0.76	0.98	0.97	1.01	0.83	0.28	0.59	0.56	1.82	0.87	0.80	0.67	0.76	0.65	0.73	99.0	0.82	0.56	0.50	0.39	0.64	0.64	0.62	1.06	1.24	0.81	0.77	0.44	0.78	0.73				0.55		0.40	1.04	0.70	0.69	1.15	0.78			0.62
TA	1.4609	1.5490	1.0672	1.3543	1.4798	2.4918	1.1928	0.7163	2.4418	1.3394	0.7161	1.5414	1.2509	1.5932	1.2173	1.1777	1.3683	1.1733	1.5732	1.4503	0.8626	1.4646	1.2048	2.6052	1.2979	1.2559	1.5191	2.2727	1.0856	1.1468	1.0711	0.5753	0.9221	1.3943	1.2299	1.3874	1.0110	1.5902	1.3813	1.4094	1.4489	1.5233	1.3613	1.2199
SR	134.4	138.5	360.8	171.4	231.6	8.98	310.1	611.3	104.1	279.5	379.3	322.9	450.8	217.9	319.2	292.7	230.1	290.2	263.9	120.4	216.5	201.3	271.1	270.7	246.8	289.5	230.9	195.2	254.1	286.4	310.7	573.8	556.3	159.4	285.2	146.5	240.1	187.4	142.7	156.6	268.2	110.0	97.9	267.3
SC	6.52	6.50	11.72	7.77		3.89		11.81	14.25	10.80	7.03	6.94	7.18	8.46	6.71		7.26	6.07	5.58	5.41	7.43	6.92	6.29				7.35	4.96	8.62					7.13	1		7	8.54		7.54	8.49			5.81
SB	0.3637	0.4195	0.3347	0.4756	0.4832	0.4521	0.5608	0.2495	0.5471	0.3586	0.3956	0.3701	0.3053	0.7512	0.3177	0.4886	0.3641	0.2979	0.3281	0.4426	0.3920	0.7770	0.2800	0.5589	0.2669	0.3019	0.4078	0.6797	0.3491	0.3923	0.3464	0.3298	0.2438	0.3030	0.4349	0.3908	0.5963	0.5484	0.6219	0.4476	0.3241	0.5767	0.8672	0.4864
RB	167.74	166.57	92.19	151.26	162.53	197.57	152.36	71.90	246.66	128.15	113.29	142.95	109.22	194.05	129.65	121.94	150.40	134.25	173.86	177.43	108.21	200.44	138.45	120.37	129.82	123.91	135.72	264.31	105.57	120.46	103.78	76.05	86.92	142.06	126.31	162.10	128.73	166.85	158.47	147.56	130.84	196.16	167.36	131.01
Z	0.0	0.0	30.7	0.0	28.5	0.0	20.9	0.0	41.7	0.0	43.1	0.0	0.0	0.0	40.1	30.7	0.0	25.2	0.0	0.0	0.0	0.0	0.0	0.0		0.0	0.0	0.0			0.0	0.0	0.0			0.0	68.8	51.4	61.2	58.9	87.7			51.9
生	6:36	7.03	8.64	7.01	89.8	89.9	6.58	6.40	10.21	6.70	5.77	9.40	12.19	7.22	6.25	7.11	6.28	6.67	5.56	7.41	7.35	19.9	6.73	06.6	6.34	8.65	6.84	5.73	6.25	8.87	5.84	5.41	6.78	6.05	96.9	7.55	9.47	9.63	5.34	6.05	13.25	7.82	7.27	5.83
H	21329.5	19917.5	33210.1	25740.9	23513.5	10182.9	18892.6	39833.2	37973.0	24817.5	29192.6	23635.0	41440.2	23543.0	21802.3	32134.5	18384.4	18175.3	15662.9	17125.3	24462.0	19700.3	19784.1	36742.4	27216.1	21938.0	25136.1	12474.1	27776.8	32970.7	28322.1	26662.2	29511.5	23605.9	30836.1	15153.7	33032.9	19738.7	23211.5	26562.1	27156.8	19746.7	19597.2	17411.0
EN	1.1238	1.3470	1.7235		1.2587	0.4311	0.9998	1.3905		1.2279	1.7628	1.1204	1.2836	1.0700			1.2995	1.0795	0.6261		1.0421	1.0311	1.1056	1.4623			1.2351					0.9736						0.9062						1.0988
CS	5.06	4.99	3.94	5.53	4.19	16.16	11.80	3.70	15.29	13.02	4.00	4.38	3.04	1.75	4.54	4.43	4.78	4.63	19.24 (6.34 0.6265		9.22	4.99				5.97							2.98	5.54	5.19 0.6320		17.24 (5.51	4.19			4.74
ANID	MVP0221	MVP0222	MVP0223	MVP0224	MVP0225	MVP0226	MVP0227	MVP0228	MVP0229	MVP0230	MVP0231	MVP0232	MVP0233	MVP0234	MVP0235	MVP0236	MVP0237	MVP0238	MVP0239	MVP0240	MVP0241	MVP0242	MVP0243	MVP0244	MVP0245	MVP0246	MVP0247	MVP0248	MVP0249	MVP0250	MVP0251	MVP0252	MVP0253	MVP0254	MVP0255	MVP0256	MVP0257	MVP0258	MVP0259	MVP0260	MVP0261	MVP0262	MVP0263	MVP0264

SOURCE STATE SITE_NAME MURR NM Pruitt Ranch
NM Pruitt Ranch
NM Pruitt Ranch
NN
MURR NM Pruit Ranch
Z
M
M
N
Z :
Z
N
N
M
MURR NM Pruitt Ranch
MURR NM Pruitt Ranch
MURR NM Pruitt Ranch
NN
M
M
M
Z.
NN S
NN
NZ.
Z
MURR NM Ranger Station
MN
MN
M
N N
NIN
N
MURR NM Ranger Station

>	68.51	49.59	44.84	51.88	32.11	53.87	44.07	36.46	55.31	38.50	66.99	34.28	25.12	62.21	38.15	46.42	42.28	44.47	67.82	32.16	51.04	56.27	38.39	40.98	37.04	25.56	43.74	79.09	35.96	39.83	53.28	46.01	43.26	80.08	20.39	53.43	34.69	45.01	38.42	32.07	91.48	79.08	63.00	41.69
F	3992.4	5421.2	3530.1	4443.5	3390.9	4161.8	3357.2	3076.3	3753.6	2878.6	3216.9	3757.7	3251.9	4513.1	3344.7	4581.1	2980.1	3606.7	3768.8	2761.8	3041.5	3787.4	3721.4	6229.5	3761.1	2926.9	4880.3	4841.5	4997.4	3091.3	5087.9	2620.0	3896.4	5036.4	2574.2	5010.7	3601.4	4358.2	4665.1	3498.6	5392.1	5214.6	4304.6	3522.9
NA	18712.4	5795.2	10588.4	_	12879.7	11876.9		7519.9	17106.7	16035.6		11097.4	19797.8	13553.3	1837.6		9061.5	17694.5	17306.8	16303.0	12029.3	14529.1	15141.1	17759.1		2	11822.5		٥.							11935.7	16906.7	14505.9	17549.5		17172.9			19221.0
MN	882.7 18	331.5 15	286.0 10	1130.2 11	606.2 12	905.5 11	_	113.9 7	354.3 17	288.3 16	1699.4	2066.7 11	212.9 19	463.3 13	417.3 11	1	404.5	240.3 17	630.9 17	438.4 16		265.1 14	371.5 15	١.			217.2	`	`	`	`			_			259.9 16	341.4 14	516.4 17		617.9 17	`		305.0 19
¥	26368.9	28140.9	30141.7		32763.8	29075.6		39109.9	30647.2	29924.2	28324.2	26676.4 2	32118.2	26001.6	27482.9		29033.5	30989.0	26923.2	32995.2	26997.3	24151.5	29053.4	26959.8	29159.7		32131.3										30974.8	32367.1	33448.5		25505.3			30124.0
DΥ	3.762 20	4.338 28	2.622 30		2.762 3.	3.185 29	5.093 29	2.602 39	6.993	3.850 29	2.948 28	2.307 20	3.428 3.	5.712 2	5.587 2		2.375 29	4.345 30	4.039 2	3.187 3.	2.755 20	5.890 2	3.575 29	3.909 2		3.383 2	5.094 3.				_	-						4.334 3.	4.630 33	3.938 3	4.052 2			3.979 30
CA	18848.4	14523.4	8216.7	8757.3	15555.5	14782.5		5092.6	13404.4	15225.1	7507.8	12174.4	12628.6	10201.5	10031.6		7486.8	12453.7	20107.1	18568.5	31221.2	13696.2	13654.9				9288.8										14253.9	11437.5	12183.2	7.7889	16329.7			16761.6
BA	739.1	761.5	415.6	403.6	240.9	415.0	515.5	494.0	751.9	8.099	346.6	382.1	347.9	783.3	444.7	453.4	379.0	740.9	683.2	637.1	396.8	832.9	648.8	963.4	437.0	400.8	451.7	714.5	693.9	626.2	705.0	1176.2	839.3	669.4	384.4	624.6	777.4	464.3	1033.1	803.3	824.5	835.5	947.9	585.1
AL	94386.7	92143.2	79661.1	76756.1	70302.2	76383.8	86466.7	81500.6	89825.1	81894.0	75215.1	85111.0	108022.6	86433.7	84021.9	82452.3	86429.3	84626.8	91467.4	80020.2	86956.2	89505.2	83428.3	85539.0	78699.2	76447.3	95854.0	82079.5	80580.7	79683.4	117761.7	88056.9	86416.2	79100.5	98321.0	87273.3	98780.6	80907.1	79941.5	103191.2	90390.9	96076.2	86045.2	85667.4
ZR	141.3	170.3	183.3	137.1	112.6	136.0	176.8	168.4	211.2	139.8	130.8	142.3	180.1	181.4	146.0	156.5	178.2	160.2	141.3	145.9	152.1	174.3	138.3	215.0	173.5	123.9	166.7	173.4	155.3	165.7	172.4	155.9	177.2	228.8	152.0	9.961	176.2	151.0	195.3	171.8	251.8	218.6	129.5	147.3
NZ	108.0	75.3	63.0	53.9	142.3	79.1	76.4	56.1	288.1	72.8	73.9	86.7	60.2	65.8	71.5	71.2	49.1	80.4	104.4	81.5	9.69	64.0	55.2	73.3	50.3	64.2	83.4	102.5	55.3	21.7	70.1	81.0	60.7	84.2	52.8	70.7	55.9	93.3	9:59	44.7	94.1	72.1		63.0
H	9.54	17.03	24.73	18.88	20.86	18.19	25.19	35.33	18.50	16.41		18.25	49.25	20.15	25.14	18.84	26.44	20.63	8.56	15.88	19.71	19.02	17.16	12.36			23.98		18.01								20.23	20.64	18.05	_	11.90			22.04
TB	0.69	0.73	0.41	0.57	0.45	0.67	0.91	0.38	1.19	0.63	0.56	0.49	0.58	0.93	0.99	0.57	0.46	0.71	0.67	0.57	0.47	1.01	09.0	0.69	0.38	0.65	0.95			_					0.40	0.69	0.73	0.62	0.72	0.61	0.78	_	_	0.73
TA	0.6774	1.2788	1.5219	1.5533	1.3061	1.5154	1.4534	2.4439	1.4290	1.1730	1.4732	1.4832	2.2451	1.6282	1.4500	1.6526	1.3935	1.4281	0.6798	1.1015	1.3757	1.3435	1.2237	1.1405	1.5332	1.4356	1.3630	1.3658	1.3108	1.2422	1.4634	1.4698	1.2055	1.2796	2.2983	1.3972	1.3661	1.6733	1.3246	2.6511	1.0514	1.0708	1.0117	1.3821
SR	397.4	267.8	122.2	236.4	258.5	243.9	172.6	93.7	243.0	295.8	185.1	235.0	145.8	233.5	159.2	201.8	111.3	253.3	349.9	310.1	442.8	322.0	271.7	423.1	129.0	210.3	180.2	9.609	244.8	304.4	147.9	202.2	272.3	323.8	88.0	262.6	294.8	233.7	339.6	403.0	398.3	334.1	279.9	402.3
SC	8.84	6.79	5.54	7.39	5.79	7.75	7.60	3.86	7.21	6.22	8.02	8.37	4.48	8.31	7.33	8.20	6.36	6.52	8.28	5.31	9.05	11.97	5.79	7.94	5.87	6.23	7.98	9.84	5.49	5.74	7.93	7.61	8.17	9.18	4.24	8.43	6.75	7.44	6.12	4.67	9.59	10.01	7.84	6.53
SB	1.3037	0.4076	0.6711	0.7454	0.3959	0.7125	0.3947	0.6050	0.3677	0.3233	0.7933	0.8198	0.6735	0.4180	0.5950	0.7328	0.9021	0.4239	0.6098		0.4840	0.5197	0.3458	0.7521	0.5859	0.2872	0.4123			0.2840	0.7764	1.1792	0.4268	0.4889	0.8447	0.5422	0.3833	0.5461	2.0651	0.8439	0.4325	0.4540	14.3895	0.4493
RB	124.48	138.83	187.13	195.82	71.69	174.94	175.84	238.92	128.22	128.31	186.02	189.98	181.62	138.74	166.94	197.41	172.33	148.43	116.53	117.26	148.48	137.24	151.25	110.27	184.60	177.62	133.90	125.36	136.46	141.85	168.46	159.09	127.78	113.01	242.86	145.74	141.54	166.39	125.41	172.55	106.76	114.15		137.12
Z	25.9	74.3	47.8	25.3	0.0	38.0	314.8	88.5	76.8	79.8	113.9	116.2	69.2	68.3	100.7	1001	184.2	28.5	62.6	45.0	0.0	57.2	82.7	99.2	24.7	62.9	46.7	9.89	38.8	35.4	58.7	30.8	50.5	54.1	32.6	0.0	31.8	48.5	35.9	0.0	60.4	57.2	22.5	31.6
生	6.25	60.9	7.86	6.48	4.79	6.51	6.45	6.31	7.64	5.44	98.9	7.09	7.98	8.79	89.9	7.21	9.60	7.05	5.71	6.25	66.9	7.10	5.07	9.37	8.54	5.44	6.24	7.35	6.79	5.85	6.13	6.27	8.33	8.96	6.50	9.30	7.58	7.22	8.67	7.19	10.97	8.71	6.17	6.67
FE	31484.2	21034.3	19430.7	22036.4	17771.1	22348.6	23094.9	11555.1	26282.8	18566.7	26777.0	24570.1	12299.9	26418.5	22345.1	23771.9	21462.5	22122.8	30994.6	17933.2	21590.7	26483.6	18891.2	24606.1	19665.0	17851.4	25286.4	31900.0	16724.4	19119.5	23410.6	22057.7	23616.5	38337.7		26710.1	17771.9	20361.1	22277.4	9226.8	37022.1	34701.5	29022.6	24301.8
EU	1.2735	1.1262	0.6153		0.5359).9115	1.1856	0.4353	1.6616	1.0778	1.8726	0.8670	0.8134	1.4408	1.3168	0.9689	0.5497	1.1828	1.4041	1.0033		1.6438).9494	1.5272).5563	0.8343	1.2549	1.4682	1.1489	0.9722	1.3170	1.3928	1.1133	1.2467	0.4850	1.1213	1.1946	0.9861	1.2183	0.8579	1.3283	1.2844	1.2763	1.0814
CS	18.65 1	5.48	6.84	7.92 (5.13	5.65 0.9115	6.07	12.66	4.25 1	4.72	7.42 0.8726	89.8	16.15	5.28	5.71		7.31	4.11	6.77	3.61	20.88 0.7383	16.06	5.70 0.9494	3.68	7.05 0.5563	5.08	4.66							3.42 1	13.18			6.29	3.77 1		3.52			6.46
ANID	MVP0265	MVP0266	MVP0267	MVP0268	MVP0269	MVP0270	MVP0271	MVP0272	MVP0273	MVP0274	MVP0275	MVP0276	MVP0277	MVP0278	MVP0279	MVP0280	MVP0281	MVP0282	MVP0283	MVP0284	MVP0285	MVP0286	MVP0287	MVP0288	MVP0289	MVP0290	MVP0291	MVP0292	MVP0293	MVP0294	MVP0295	MVP0296	MVP0297	MVP0298	MVP0299	MVP0300	MVP0301	MVP0302	MVP0303	MVP0304	MVP0305	MVP0306	MVP0307	MVP0308

ANID	macro_grp	Chem2012	CERAMIC TYPE	MATERIAL	SOURCE	STATE	SITE_NAME	SITE_NO	AS	ΓA	Π	S QN	SM	U YB	3 CE	00	CR
309		Unas.	Mimbres B/W Style III	Pottery	MURR	MN	Ranger Station	LA 005066	3.00		0.6386 19	19.00 3.	3.68 11.60	50 2.27	7 72.54	1.88	55.99
_		Mimbres-08	Mimbres B/W Style III	Pottery	MURR	NM	Gonzales	LA 001679 [N	1.59							3.43	21.60
MVP0311 Gr	Group-B2	Mimbres-02A	Mimbres B/W Style III	Pottery	MURR	NM	Gonzales	LA 001679 [N	2.41	42.56 0.5	0.5334 34	34.26 6.	6.95 3.89	39 3.39	9 78.63	2.66	35.76
	Group-C1	Mimbres-21	Mimbres B/W Style III	Pottery	MURR	MN	Galaz	LA 000635	3.93	37.57 0.3	0.3830 32	32.88 6	6.27 2.69	59 2.7	2 78.28	12.41	32.59
		Mimbres-04C	Mimbres B/W Style III	Pottery	MURR	MN	Galaz	LA 000635									26.65
		Mimbres-04A	Mimbres B/W Style III	Pottery	MURR	M	Galaz	LA 000635	2.91								17.41
	Group-B1	Mimbres-04A	Mimbres B/W Style II/III	Pottery	MURR	M	Galaz	LA 000635	1.76	43.42 0.4	0.4768 33		6.48 4.57	57 2.98		5.10	20.99
	~	Unas.	Mimbres B/W Style III	Pottery	MURR	M	Galaz	LA 000635	1.71								23.04
		Mimbres-04C		Pottery	MURR	¥	Galaz	LA 000635	2.37							4.57	30.23
MVP0318 Gr	Group-B1	Mimbres-04A		Pottery	MURR	MN	Galaz	LA 000635	2.36		0.6864 43	43.65 9.	9.03 7.83	33 4.05	5 98.39	80.9	20.32
MVP0319 Gr		Mimbres-01	Mimbres B/W Style III	Pottery	MURR	MN	Galaz	LA 000635	3.38	26.05 0.8	0.8063 25	25.21 4.	4.58 12.02	3.23	3 87.73	1.66	8.52
MVP0320 Gr	Group-B1	Mimbres-04A	Mimbres B/W Style III	Pottery	MURR	MN	Galaz	LA 000635	3.24	48.52 0.5	0.5075 37	37.48 7.	7.72 5.32	32 3.43	3 89.53	8.18	24.32
MVP0321 Gr	Group-B1	Mimbres-04A	Mimbres B/W Style II	Pottery	MURR	MN	Galaz	LA 000635	2.12			35.63 7.	7.30 5.02	3.31	1 95.08	33.80	24.16
MVP0322 Gr	Group-B1	Mimbres-04A	Mimbres B/W Style III	Pottery	MURR	M	Galaz	LA 000635	3.10	45.90 0.5	0.5458 37	37.79 7.	7.24 4.40	40 3.55	5 88.63	5.57	18.07
MVP0323 Gr	Group-B1	Mimbres-04C	Mimbres B/W Style II	Pottery	MURR	MN	Galaz	LA 000635	1.90	44.24 0.5	0.5281 35	35.12 7.	7.10 4.01	3.20	0 76.99	4.68	44.89
MVP0324 Gr		Mimbres-01	Mimbres B/W Style III	Pottery	MURR	MN	Gonzales	LA 001679 [N	2.00	54.23 0.3	0.3701 24	24.79 4.	4.61 17.30	30 2.44	4 88.17	2.58	13.71
	Group-C2	Unas.	Mimbres B/W Style II/III	Pottery	MURR	MN	Gonzales	LA 001679 [N	1.90	33.61 0.3	0.3689 27	27.27 5.	5.74 3.03	33 2.32	2 57.07	4.17	18.46
MVP0326 Gr	Group-C1	Mimbres-21	Mimbres B/W Style III	Pottery	MURR	MN	Gonzales	LA 001679 [N	2.42	35.79 0.3	0.3284 28	28.15 5.4	5.69 2.09	2.15	5 73.58	12.02	72.28
MVP0327 Gr	Group-B	Unas.	Mimbres B/W Style III	Pottery	MURR	MN	Gonzales	LA 001679 [N	3.65	63.46 0.5	0.5719 54	54.53 10.	10.66 4.77	77 4.23	3 125.70	22.04	109.33
MVP0328 Gr	Group-C1	Unas.	Mimbres B/W Style III	Pottery	MURR	MN	Goforth	Alum Mt:8:1(C	717	27.73 0.	0.1841 19	19.51 3.	3.56 1.52	52 1.40	0 53.55	4.20	5.72
MVP0329 Gr	Group-C1	Unas.	Mimbres B/W Style III	Pottery	MURR	¥	Goforth	Alum Mt:8:1(C	3.32	37.34 0.3	0.3966 38	38.37 8.	8.73 1.3	1.38 3.21	1 82.73	10.39	38.36
	Group-B1	Mimbres-04B	Mimbres B/W Style III	Pottery	MURR	M	Goforth	Alum Mt:8:1(C	2.92	52.13 0.5	0.5628 36	36.25 7.	7.48 7.82	32 3.42	2 91.54	3.94	22.25
MVP0331 Gr	Group-A	Mimbres-01	Mimbres B/W Style III	Pottery	MURR	M	Goforth	Alum Mt:8:1(C	2.27	47.50 0.5	0.5985 20	20.31 3.	3.56 10.47	47 2.26	6 72.76	2.09	5.11
		Mimbres-04A	Mimbres B/W Style III	Pottery	MURR	M	Goforth	Alum Mt:8:1(C	2.05	56.70 0.6	0.6453 48	48.50 9.		33 4.31	-	5.15	20.46
MVP0333 Gr		Unas.	Mimbres Polychrome	Pottery	MURR	NM	Goforth	Alum Mt:8:1(C	2.85	53.42 0.3	0.3923 41		7.88 2.87	37 2.63	3 101.82	15.37	62.03
		Unas.	Mimbres B/W Style III	Pottery	MURR	MN	Goforth	Alum Mt:8:1 (C	3.05								17.59
		Mimbres-21	Mimbres B/W Style III	Pottery	MURR	M	Goforth	Alum Mt:8:1(C								11.98	56.00
		Mimbres-21	Mimbres B/W Style III	Pottery	MURR	M	Goforth	Alum Mt:8:1(C								1	51.04
		Mimbres-11	Mimbres B/W Style III	Pottery	MURR	M	Goforth	Alum Mt:8:1(C	3.55	44.39 0.0			8.85 4.85		7 92.17		50.37
	Group-B1	Mimbres-04A	Mimbres B/W Style III	Pottery	MURR	M	Goforth	Alum Mt:8:1(C		40.24 0.4	0.4203 29	29.86 6.	6.13 4.22	22 2.86	6 75.49		25.59
	_	Mimbres-21	Mimbres B/W Style III	Pottery	MURR	M	Goforth	Alum Mt:8:1(C		_							43.29
_		Unas.	Mimbres B/W Style III	Pottery	MURR	M	Goforth	Alum Mt:8:1(C				31.38 5.				1	56.89
	Group-A	Mimbres-01	Mimbres Polychrome	Pottery	MURR	¥	Goforth	Alum Mt:8:1(C	3.30	40.37 0.5	0.5475 21	21.77 3.			7 66.59	3.37	12.88
	Group-A	Mimbres-01	Mimbres B/W Style III	Pottery	MURR	¥	Goforth	Alum Mt:8:1(C	2.12	75.76 0.7		29.18 5.	5.54 12.04	3.72	2 105.88	4.26	14.29
		Unas.	Mimbres B/W Style III	Pottery	MURR	MN	Goforth	Alum Mt:8:1(C	3.63	54.77 0.5	0.5107 50	50.66 9.	9.82 3.01	01 4.13	3 116.45	4.65	23.96
MVP0345 Gr	Group-B	Unas.	Mimbres B/W Style I/II	Pottery	MURR	¥	Goforth	Alum Mt:8:1(C	4.55	49.69 0.5	0.5364 36	36.31 8.	8.12 4.90	3.77	7 105.25	10.15	54.24
	Group-B1	Mimbres-04C	Mimbres B/W Style III	Pottery	MURR	M	Goforth	Alum Mt:8:1(C	-0.91	44.76 0.3	0.3984 37	37.84 6.	6.78 2.52	52 2.70	0 92.94	12.43	39.95
MVP0347 Gr	Group-B	Unas.	Mimbres B/W Style III	Pottery	MURR	MN	Goforth	Alum Mt:8:1(C	3.14	55.06 0.5	0.5409 51	51.04 9.	9.34 3.00	3.56	119.34	19.9	21.20
	Group-B1	Mimbres-04B	Mimbres B/W Style III	Pottery	MURR	MN	Goforth	Alum Mt:8:1(C	2.01	52.38 0.5	0.5795 41		8.06 6.14	14 3.57	7 91.75	4.96	20.36
MVP0349 Gr	Group-B	Unas.	Mimbres B/W Style III	Pottery	MURR	MN	Goforth	Alum Mt:8:1(C	2.54	.0 89.89	0.7335 59	59.93 12.27	.27 4.80	30 5.41	1 145.97	2.80	23.36
	Group-B	Unas.	Mimbres B/W Style III	Pottery	MURR	M	Goforth	Alum Mt:8:1(C	2.18	63.22 0.0	0.6022 71	71.65 14.97	.97 3.89	39 4.48	8 148.14	3.14	20.58
		Mimbres-02A		Pottery	MURR	M	Goforth	Alum Mt:8:1(C	5.64								43.07
		Mimbres-11		Pottery	MURR	MN	McSherry	LA 015050	4.79				5.13 3.90	3.74	4 84.57	l	48.07
MVP0353 Gr	Group-B2	Mimbres-02B	Mimbres B/W Style III	Pottery	MURR	MN	McSherry	LA 015050	4.86	45.53 0.5	0.5554 36	36.34 7	7.21 5.93	93 3.79	9 76.78	9.12	41.82

>	18.30	39.85	55.72	78.34	55.16	30.00	51.37	40.86	50.87	42.76	34.52	49.64	46.80	36.24	58.24	27.36	54.61	84.51	78.40	35.65	72.79	53.24	23.37	49.91	87.55	19.64	78.48	66.69	71.78	47.72	69.92	74.51	31.99	22.73	39.39	99.89	57.51	0.00	25.00	35.86	42.02	106.62	46.08	66.95
I	2360.5	3684.5	4060.1	3986.2	4321.0	3582.0	3188.4	3623.0	3710.6	4946.9	2811.8	3143.5	3772.7	2849.9	4357.6	2771.9	4840.3	4890.4	4980.8	2507.5	3719.2	3285.4	2391.5	3404.4	5368.5	3373.8	3332.6	4391.3	5357.5	4406.8	3549.8	4604.0	3355.8	1410.6	3616.4	4455.3	3944.0	3771.9	3804.2	4139.2	3763.2	4562.3	4452.6	3370.8
NA	19299.4	10904.5	13958.2	17864.2	17169.1	18477.0	15935.4	27291.1	15415.7	16574.9	10306.2	16515.9	17287.3	15738.7	16223.2	14318.4	13356.1	19356.3	19294.0	15209.4	19621.8	11670.6	15852.1	16400.3	15043.7	4992.2	21450.7	18935.2	16560.9	13981.1	20020.4	15372.7	8220.8	19485.0	16980.2	12947.4	15150.7	19066.5	12669.3	19869.9	17084.0	3644.9	10686.1	10306.3
M	153.7	163.3	256.1	839.3	862.6	1097.9	282.7	511.5	244.3	323.6	135.8	708.2	985.8	1137.0	263.1	366.6	383.5	889.7	568.3	1079.6	959.5	358.9	172.5	333.9	659.5	486.6	944.6	834.9	360.1	293.5	852.1	425.3	188.4	244.7	475.4	537.1	559.9	596.3	287.7	323.7	381.6	510.6	647.8	679.7
\checkmark	22359.0	33437.7	30800.6	29556.4	26467.5	32522.4	31040.2	23572.9	28757.8	32038.0	33394.6	30014.1	28925.4	29159.0	29224.8	33779.0	35209.7	28214.6	24203.8	37475.4	29553.4	29841.4	35835.4	28376.6	24845.1	39668.2	21936.6	25393.4	30001.9	29520.8	25604.3	21562.8	43916.1	27181.0	28631.3	25229.5	30858.3	32252.0	31523.7	32397.2	29450.7	24912.9	31142.9	28017.1
Dγ	2.313		5.171	4.061		4.155	4.574	3.021	4.717	968.9	3.144	5.211	4.514	5.047	4.907	2.598	6.505	4.307	4.156	3.471	7.006	5.377	1.863								_							6.123	5.427	9.067	8.563			4.916
CA	11311.2	6811.4	13490.9	14002.9	17405.1	12447.8	12860.7	13310.8	12332.8	13429.4	5577.9	13037.6	14025.9	15101.9	11895.8	6107.0	15702.8	17015.3	18004.7	38617.0	15067.3	7839.2	9099.1	12826.3	13288.8	6218.5	10555.1	12707.8	11144.1	9750.3	17247.8	20852.2	4461.2	20956.7	14181.3	11131.8	12855.1	14587.3	8765.7	11946.6	18958.9	29168.9	10627.1	11633.8
BA	208.8	496.2	746.7	770.1	722.2	1070.6	625.4	785.7	626.7	7.897	317.5	806.4	827.5	983.7	697.5	541.8	764.0	954.2	800.7	868.4	827.5	548.1	229.0	821.3	830.2	111.1	679.3	719.3	534.8	763.1	800.0	653.1	513.8	180.9	1115.2	600.2	777.6	887.2	463.3	1064.7	949.7	541.5	449.3	488.7
AL	91447.3	78382.2	82153.7	96639.4	89050.7	81089.3	87649.8	92957.5	87278.1	83595.4	99500.3	78428.8	84572.6	92984.1	91444.4	8.605901	92664.6	95176.2	98765.5	100572.9	91340.4	84593.2	93170.1	87384.7	92921.4	69804.9	90721.8	86642.9	89864.6	79514.4	9.89288	96568.0	84182.2	-		87200.6	84351.3	95740.0	88090.9	87796.9	85915.2	93753.6	77624.0	88635.0
ZR	146.1	164.4	134.6	127.6	220.9	172.8	199.0	122.9	189.0	227.4	148.3	153.2	151.2	134.6	189.1	174.0	92.2	121.4	265.8	107.5	135.2	145.2	115.4	244.1					183.8		140.6	158.0			203.0			251.4	155.2		220.8		150.6	135.8
NZ	71.1	44.5	0.99	113.4	70.9	64.7	68.1	101.2	65.8	83.1	8.79	70.8	65.7	81.2	151.4	72.3	40.7	82.8	141.0	87.9	130.5	58.4	53.7	133.8	94.3	70.5	99.4	107.0	110.4	53.6	138.0	81.0	42.8	63.8	94.2	87.3	111.8	7.86	8.09	105.0	105.9	121.6	61.2	353.7
3 TH	1 44.46		16.90	3 10.54			18.64	99.7	17.62	16.67	3 48.36	17.46	17.39	3 17.56	3 18.16	7 51.06	12.61	9.24	5 19.12	9.90		9 25.89	7 48.02	5 19.28		"			17.02	1						2 19.13		16.24	3 26.11	3 22.73	14.92			3 23.00
TA TE	2.3247 0.34	1.5530 0.48	1.3273 0.80	0.8470 0.78	1.2901 0.96	1.3116 0.71	1.3581 0.79	0.7008 0.56	1.3668 0.80	1.2841 1.04	2.3077 0.48	1.3063 0.97	1.3010 0.81	1.1526 0.93	1.3231 0.93	2.4940 0.37	0.7587 0.69	0.7244 0.67	1.7481 1.25	0.3850 0.38	0.7617 1.25	1.5442 0.89	2.2590 0.27	1.4312 1.15	1.1351 0.80	2.2434 1.27	0.7122 0.60	1.1834 0.94	1.3571 1.2			_		2.2318 0.60	0.9982 1.1		1.0619 0.85	1.0533 1.07	1.5402 0.93	1.3923 1.48	1.0143 1.82		1.5425 0.67	1.5946 0.78
SR	152.8 2.	141.4 1.	257.6 1.	307.5 0.		303.1	220.7 1.	636.7 0.	196.5 1.	267.4 1.	76.9 2.	262.2 1.	294.9 1.	230.5 1.	251.9 1.	79.2 2.	161.4 0.	315.9 0.	663.9 1.		348.8 0.	114.4 1.	137.3 2.	258.5 1.	389.0 1.				237.2 1.								258.6 1.	206.8 1.	180.2 1.	282.5 1.	223.4 1.			266.8 1.
SC	3.64	5.22	76.6	9.15		5.85	6.92	2.98	7.13	6.84	4.51	6.84	7.10	7.17	7.47	4.71	2.67	8.74	18.61	2.98	7.25	7.32	3.97	7.56		5.40		9.12										10.32	6.13	10.83	10.64			9.94
SB	0.5570	0.5371	0.4089	1.4397	0.6213	0.2830	0.3470	0.3988	0.3805	0.4365	1.0305	0.4560	0.5613	0.2900	0.5424	1.2145	0.2970	1.3980	0.7541	1.5835	1.4803	0.4354	0.5172	0.4523		0.7491	1.7738	1.3436	0.8100	0.6065	1.4345	0.5077	0.6434	1.2281	0.6373	1.7488		0.6377	0.3719	0.8586	0.7940	1.1554	1.0479	1.2340
RB	167.46	186.00	133.55	119.05	132.99	122.40	146.80	76.87	143.81	111.17	213.50	132.34	134.15	124.95	139.33	234.26	62.29	114.21	166.81	98.01	112.53	164.33	233.99	137.73	118.96	202.49	118.85	134.37	145.09	141.31	112.52	112.46	226.84	220.55	129.53	162.31	117.17	138.18	164.50	166.02	103.63	151.47	194.46	204.46
Ξ	55.8	30.4	0.0	0.0	41.6	33.7	28.6	50.1	45.1	20.1	44.4	12.1	26.7	56.9	23.4	0.0	0.0	55.7	9.9/	0.0	45.2	38.4	11.2	34.8			35.6		43.7		43.5							43.2	70.3	42.9	38.6			0.0
Ή	6.63	7.86	6.46	6.37	7.88	8.38	7.84	5.04	68.9	9.05	6.26	6.47	7.26	5.57	7.71	6.40	3.52	6.16	13.76	4.94	6.31	5.72	5.29	00.6	8.50	8.67	6.65	7.09	8.98	69.6	6.73	7.83	6.17	6.33	8.51			8.59	6.10	12.95	8.94			6.29
FE	10701.4	17852.3	24025.4	34550.6	27318.7	20877.0	23600.9	25288.1	23478.2	26088.3	13735.7	24072.8	24955.5	23243.4	26387.3	14520.8	17907.3	34233.8	64651.5	12827.2	31119.8	22004.9	11757.8	25035.2	43820.2			34028.3	24303.6	23053.5	33086.9	37910.1	13271.4	13412.3	26032.0	29473.4		28172.3	19286.2	21685.4	19145.4	28745.0		27247.1
EU	0.4343	0.6733	1.3010	1.3095		1.2338	1.1491	1.4390	1.1936	1.5289	0.5236	1.4236	1.3735	1.2929	1.2887	0.4614	1.0618	1.2034	2.3317	0.8307	1.3110	1.2174	0.4067				1.2886		1.2567	1.1598	1.2833	1.2047					1.4817	2.0365	1.3390	2.7706	2.8701			1.2645
CS	12.01	6.48	11.91	13.57	4.75	3.63	4.22	5.23	4.25	3.53	19.85	4.22	4.61	4.49	4.40	14.00	3.31	14.71	92.9	16.93		5.54	15.21				18.06	15.97			16.61				2.68	9.95	4.69	5.26	4.83	5.88	4.62			48.97
ANID	MVP0309	MVP0310	MVP0311	MVP0312	MVP0313	MVP0314	MVP0315	MVP0316	MVP0317	MVP0318	MVP0319	MVP0320	MVP0321	MVP0322	MVP0323	MVP0324	MVP0325	MVP0326	MVP0327	MVP0328	MVP0329	MVP0330	MVP0331	MVP0332	MVP0333	MVP0334	MVP0335	MVP0336	MVP0337	MVP0338	MVP0339	MVP0340	MVP0341	MVP0343	MVP0344	MVP0345	MVP0346	MVP0347	MVP0348	MVP0349	MVP0350	MVP0351	MVP0352	MVP0353

ANID	macro_grp	macro_grp Chem2012	CERAMIC TYPE	MATERIAL	SOURCE	STATE	SITE_NAME	SITE_NO	AS	ГА	21	ND	SM	П	YB	CE CO	O CR
MVP0354	Group-B1	Mimbres-04A	Mimbres B/W Style III	Pottery	MURR	MN	McSherry	LA 015050	3.07	42.18	0.5319	29.59	6.73	3.77	3.79 90	90.29 9.83	3 20.43
MVP0355	Group-B2	Mimbres-02A	Mimbres B/W Style III	Pottery	MURR	MN	McSherry	LA 015050	2.19	51.01	0.6237	39.52	8.42	5.22	4.53 105.62	61.6 29.19	9 37.75
MVP0356	Group-B2	Mimbres-08	Mimbres B/W Style III	Pottery	MURR	NN	McSherry	LA 015050	3.23	38.46	0.4471	22.67	4.34	4.78	2.43 76	76.32 6.19	9 24.58
MVP0357	Group-A	Unas.	Mimbres B/W Style III	Pottery	MURR	MN	McSherry	LA 015050	3.17	41.73	0.5375	24.60	4.95	2.47	3.40 76	76.23 4.74	4 20.07
MVP0358	Group-B1		Mimbres B/W Style III	Pottery	MURR	NM	McSherry	LA 015050	2.27		0.4559	28.36					96.91
MVP0359	Group-C2a		Mimbres B/W Style II	Pottery	MURR	¥	Harris	LA 001867	4.16	38.32	0.4399	39.24				85.02 10.00	0 64.24
MVP0360	Group-C1	Mimbres-22	Mimbres B/W Style I	Pottery	MURR	ΑZ	Nantack Village	AZ W:10:111	2.96	37.01	0.3408	29.29	5.25	1.30	2.09 78	78.02 7.41	1 31.16
MVP0361	Group-C1	Mimbres-21	Mimbres B/W Style I	Pottery	MURR	Σ	Mogollon Village	LA 011568	2.12	_	0.3243						
MVP0362	Group-B2	Mimbres-02A	Mimbres B/W Style III	Pottery	MURR	ΑZ	San Simon Wash	AZ Z:15 (ASN	2.56		0.4681	34.81				76.92 5.78	
MVP0363	Group-A	Unas.	Mimbres B/W Style III	Pottery	MURR	MN	Eaton Ranch	Silver City:2:1	3.52	_	0.4653	18.18				63.23 3.71	
MVP0364	Group-C1	Mimbres-22	Mimbres B/W Style II	Pottery	MURR	NM	Mogollon Village	LA 011568	3.47	44.27	0.3016	36.01	6.03	1.32	2.79 90	90.62 6.80	0 20.67
MVP0365	Group-C1	Mimbres-21	Mimbres B/W Style I	Pottery	MURR	MM	Mogollon Village	LA 011568	4.53	38.21	0.3256	34.96	6.05	1.30	2.26 81.81	.81 6.74	4 25.37
MVP0366	Group-C1	Mimbres-21		Pottery	MURR	MM	Mogollon Village	LA 011568	3.18		0.2947					71.10 9.26	
MVP0367	Group-B	Unas.		Pottery	MURR	MM	Eaton Ranch	Silver City:2:1	2.56		0.6931	42.39		8.93	4.23 103.32		9 25.25
MVP0368	Group-B	Unas.	Mimbres B/W Style III	Pottery	MURR	MM	K Bar Slash Ruin	Silver City:2:3	2.72	46.54	0.4115	32.23	5.93	3.17	3.13 87	87.68 5.56	
MVP0369	Group-B	Unas.	Mimbres B/W Style II/III	Pottery	MURR	MM	Sawmill Ruin	NM S:15/NM	3.30		0.5238	50.14		3.11 4		98.72 4.51	
MVP0370	Group-C1	Unas.	Mimbres B/W Style III	Pottery	MURR	MM	C-F Ranch Ruin No.2	NM Y:7	6.44		0.3359			1.73		82.50 8.78	8 52.75
MVP0371	Group-B	Unas.	Mimbres B/W Style III	Pottery	MURR	MN	C-F Ranch Ruin No.2	NM Y:7	-1.26		0.5945	59.23 1	10.93	4.31	4.20 126.80	.80 2.60	0 20.72
MVP0372	Group-B1	Mimbres-04B	Mimbres Polychrome	Pottery	MURR	M	C-F Ranch Ruin No.2	NM Y:7	2.74	49.22	0.5096	33.29	7.39	5.80	3.18 88	88.55 3.84	4 24.35
MVP0373	Group-C2a	Mimbres-49A	Mimbres B/W Style III	Pottery	MURR	MN	Three Circle Site	LA 000053	2.50	38.62	0.3932	32.68	7.53	3.04	2.73 87	87.52 9.24	
MVP0374	Group-B2	Mimbres-02C	Mimbres B/W Style III	Pottery	MURR	MN	Deming vicinity		3.06	33.05	0.4910	22.93	4.31	2.54	3.15 65	65.45 4.39	6 18.69
MVP0375	Group-B1	Mimbres-04A	Mimbres B/W Style III	Pottery	MURR	MN	Rock House	LA 001118	1.84	33.61	0.3744	26.28	4.85	2.93	2.44 64	64.84 4.21	1 26.97
MVP0376	Group-C2a	Mimbres-49A	Mimbres B/W Style III	Pottery	MURR	NN	Rock House	LA 001118	4.50		0.4319	38.73					
MVP0377	Group-B2	Mimbres-02A	Mimbres B/W Style III	Pottery	MURR	M	Rock House	LA 001118	2.19	45.02	0.5239			3.49	3.42 107.92	.92 10.02	2 40.39
MVP0378	Group-B1	Mimbres-04A	Mimbres B/W Style III	Pottery	MURR	¥	Rock House	LA 001118	1.57		0.4133			3.04		69.56 4.01	1 23.46
MVP0379	Group-B1	Mimbres-04A	Mimbres B/W Style III	Pottery	MURR	M	Rock House	LA 001118	1.68		0.4547					_	
MVP0380	Group-B1	Mimbres-04C	Mimbres B/W Style III	Pottery	MURR	¥	Rock House	LA 001118	1.89	_	0.5410	40.63					
MVP0381	Group-B1		Mimbres B/W Style III	Pottery	MURR	M	Ranger Station	LA 005066	5.45		0.4372	37.32					
MVP0382	Group-C2a	Mimbres-49A	Mimbres B/W Style II	Pottery	MURR	M	Goforth	Alum Mt:8:1(C	4.94	38.10	0.3478	33.43			2.39 128.79		8 55.99
MVP0383	Group-B	Unas.	Mimbres B/W Style III	Pottery	MURR	¥	Galaz	LA 000635	5.56	_	0.4201						
MVP0384	Group-B1	Mimbres-04C	Mimbres B/W Style II/III	Pottery	MURR	¥.	Gonzales	LA 001679 [N	2.42	-+	0.4587					1	
MVP0385	Group-B1	Mimbres-04B	Style III	Pottery	MUKK		Galaz	LA 000635	2.03	_	0.5066	48.44					
MVP0386	Group-B1	Mimbres-04C		Pottery	MURR	Σ	Galaz	LA 000635	3.95		0.5414	31.52				_	
MVP0387	Group-B1	Mimbres-04C	Mimbres Plain	Pottery	MURR	∑	Gonzales	LA 001679 [N	2.58		0.5305	38.35					
MVP0388	Group-B1	Mimbres-05A	Plain smudged	Pottery	MURR	¥	Goforth	Alum Mt:8:1(C	4.36		0.5687	47.52		3.47	3.97 101.52	.52 16.59	9 60.57
MVP0389	Group-B1	Mimbres-05A	Mimbres Plain Smudged	Pottery	MURR	MM	Goforth	Alum Mt:8:1(C	5.52		0.5336	40.01	8.87	2.70	3.95 107.78	.78 15.81	
MVP0390	Group-B1	Mimbres-04C	Alma Plain	Pottery	MURR	NM	Gonzales	LA 001679 [N	1.87		0.4317	38.99			3.04 83	83.74 7.79	9 33.87
MVP0391	Group-B1	Mimbres-04A	Three Circle Corrugated	Pottery	MURR	¥	Harris	LA 001867	2.08	39.04	0.4070	31.40	5.93	3.29	2.68 75	75.43 4.65	5 20.44
MVP0392	Group-B	Unas.	Alma Plain	Pottery	MURR	MM	Harris	LA 001867	4.05		1.2394	37.98	1	1.32 7	7.19 89	89.32 3.19	
MVP0393	Group-B1	Mimbres-04A	Alma Neckbanded	Pottery	MURR	MM	Harris	LA 001867	4.33		0.5180	26.36		3.14	3.27 72	72.66 5.83	3 17.43
MVP0394	Group-C2a	Mimbres-49A		Pottery	MURR	MN	Hamis	LA 001867	3.66		0.4468	35.80				1	
MVP0395	Group-B1	Mimbres-04A		Pottery	MURR	M	Harris	LA 001867	2.92		0.3660	26.81					
MVP0396	Group-B1	Mimbres-04A	g	Pottery	MURR	¥	Harris	LA 001867	2.34		0.3737	27.90					
MVP0397	Group-B1	Mimbres-04A	Reserve Plain Smudged	Pottery	MURR	MN	Mitchell	LA 012076	1.69	44.38	0.4496	35.43	7.08	3.38	3.24 85	85.16 2.96	6 19.56

>	57.31	42.50	42.60	36.49	40.12	76.09	33.92	33.87	59.22	43.34	39.19	40.37	56.43	63.73	46.09	43.08	52.38	33.65	47.49	66.23	34.42	33.61	83.66	71.28	27.02	32.03	59.48	66.34	79.20	130.41	62.59	40.72	57.89	65.39	99.80	65.65	66.53	50.82	50.32	52.98	87.08	51.47	43.95	32.33
F	3972.8	4321.4	3017.7	2351.7	3429.0	5628.4	2726.9	2768.7	3896.3	4212.8	3329.5	2980.6	4333.6	5011.4	3566.1	3610.4	4004.9	3808.5	3464.8	4366.2	3641.1	3598.8	5049.9	4481.3	3135.3	3011.0	5440.6	4240.0			4033.1	3530.0	3880.8	4626.2	2,0076	5210.6	3805.8	3786.7	4109.5	3207.4	3620.1	3692.5	3564.1	4504.1
NA	13460.0	15954.9	10211.0		17245.3	14089.1	13447.7	18305.4	13385.6	10633.1	10199.1	12638.9	20480.3	17161.3	16833.2		18633.1	20209.8	12348.0	16149.9	12135.8	14526.8	15836.1				16235.0											17391.1						17652.7
MN	476.4 13	723.2 15	414.8 10	,	301.7 17	536.6 14	715.5 13	986.8 18	260.0 13	165.8 10		739.9 12	1077.2 20	280.8 17	465.1 16		842.3 18	281.2 20	188.0 12	418.5 16	668.3 12	296.4 14	481.9 15								,		1.	- 1 -		`			`	339.9 18				182.6 17
¥	28242.3	7 28077.5	29432.3			31358.4 5	30397.6		31583.8 2	30451.6	36085.7	34271.8 7	25967.5 10	28615.6 2	30853.6		33574.5 8	32095.9 2	30791.8	24154.5 4	23185.4 6	29302.7	19788.2 4							_				7		`		29051.7	Ì					36267.9 1
DΥ	5.710 28	4.402 28	2.648 29	3.405 21	3.457 32	6.040 31	.967 30	3.338 25	4.541 31		3.228 36	3.570 34	3.476 25	4.266 28	3.529 30		3.726 33	7.270 32	4.862 30	4.732 24		3.252 29	5.040 19			-				- 1		_	_											4.9878 36
CA	12453.6 5	10365.3 4	7401.3 2	7668.9		15524.8 6	13179.5 2	14429.0 3	14955.5 4	6383.0 3		21236.8 3	20138.4 3	11962.1 4	13230.9 3		8927.8 3	14894.3 7	9854.5 4		17151.6 2	12626.3 3	18689.7 5					_			_	-+		_		_		13102.0 3.8						11636.1 4.9
BA	503.7 12	825.8 10	427.8 7		697.1 12	823.8 15	958.7 13	885.6 14	915.3 14	475.2 6	672.9 19		902.7 20		994.6 13	1	8 9.598	1125.2 14	6 0.809			571.4 12	875.4 18			`	`	`			_	7	`	,		, ,				1456.7 19	_		`	808.9 11
AL																1		,										,							_					,	`			
	81735.6	78699.5	81809.2		87022.0	84308.9	83878.3	92500.8	84884.0	82957.9	94783.0	95728.5	91680.6		84289.9		90951.5	88739.0	89424.6	97296.9	72774.9	1.19738	88017.9					83796.4	85332.3	93269.3	72500.3	82217.5	80937.8			89565.4			97023.9	84019.9	76766.7			79962.5
ZR	175.4	163.4	161.8		197.4	184.7	140.8	145.0	160.0	164.7	133.3	128.0	152.2	443.3	278.9	200.4	165.5	221.9	155.5		9.711	141.5	204.8	168.3				170.2														149.1		184.6
NZ	62.9	73.5	87.7	52.8	68.7	114.0	78.2	98.4	48.5	46.1	97.3	87.2	82.8	135.2	51.9	8.96	857.9	113.2	56.7	86.5	49.4	60.5	85.5	71.7	61.8	53.0	74.9	94.9	118.3	85.6	77.7	103.0	80.2	67.70	101.2	120.8	87.4	61.5	89.0	80.0	141.7	64.7	54.7	61.2
H	18.04	21.53	27.10	34.87	22.58	11.01	10.24	9.70	20.10	33.85	10.92	10.57	8.43	22.98	14.43	16.48	10.43	15.65	27.85	13.21	29.39	17.23	11.68	18.05	20.62	18.90	16.84	17.58	11.15	14.72	15.92	26.28	10.03	18.55	14.95	15.58	15.76	19.37	43.75	17.70	13.47	17.48	18.49	19.01
TB	96.0	1.22	0.51	0.59	0.62	1.01	0.58	0.59	0.75	0.45	09.0	0.73	0.62	0.93	0.64	1.12	0.62	1.27	0.79	0.92	0.52	0.58	0.77	0.89	0.60		0.92			0.84				_	_ I,			0.63	1.31	0.70				0.98
TA	1.2529	1.7059	1.4431	1.6011	1.4321	1.3368	0.7291	0.6464	1.3775	1.6181	0.7530	0.7007	0.5891	1.7736	0.9353	0.9889	0.7952	1.0688	1.5768	1.1717	1.5061	1.1774	1.0328	1.2820	1.3422	1.2999	1.2962	1.3309	0.8954	1.0412	1.2336	1.414/	1.3530	1.3035	1.1915	1.1466	1.1748	1.3725	2.8427	1.2546	1.1373	1.2295	1.3768	1.3665
SR	237.0	300.9	145.8	242.5	236.2	343.3	318.6	367.3	457.1	113.5	311.0	325.7	359.1	334.4	304.7	255.0	385.9	244.5	144.5	383.8	266.8	288.5	502.7	353.3	278.9	318.5	241.7	682.89	435.45	470.88	332.54	166.72	702.04	305.67	248.16	349.89	414.02	255.67	56.25	313.50	383.71	258.64	266.14	227.19
SC	6.82	10.76	6.19	19.9	6.04	6.56	5.15	6.01	8.86	6.14	5.37	5.40	6.62	6.63	5.46	10.03	6.51	9.22	7.29	10.52	6.02	00.9	11.82	10.95	6.49	6.22	9.24	9.76	10.92	14.91	7.50	7.05	7.45	7.08	13.44	13.33	8.84	7.24	10.58	6.84	8.26	6.46	6.59	6.64
SB	0.4068	0.4708	0.5674	0.6497	0.3606	1.2659	2.5029	2.3009	0.4023	0.6377	1.7694	1.5928	1.9684	0.4906	0.9174	0.6786	2.9668	0.5883	0.3695	0.4385	0.3354	0.3738	0.7534	0.4652	0.3569	0.3192	0.6913	0.5343	0.4877	0.7592	0.4169	0.565/	0.5016	0.4102	0.8184	0.8671	0.4055	0.3365	0.4963	0.3870	0.5911	0.3525	0.3162	0.3027
RB	132.31	155.62	183.22	169.96	165.48	121.50	132.56	124.21	121.35	182.65	148.78	122.56	110.68	168.69	104.54	133.46	143.43	113.64	153.53	109.64	154.06	132.69	93.38	131.32	137.98	141.85	136.86	118.67	80.72	107.09	97.71	159.72	118.07	131.62	120.34	136.18	98.03	132.32	286.54	145.23	119.71	121.56	126.69	130.54
Z	73.5	0.0	0.0		33.0	0.0	36.3	52.5	131.8	0.0	0.0	43.2	34.8	102.2	0.0	44.5	52.3	0.0	0.0	0.0	0.0	36.9	74.5	43.2	_										_									6.69
生	6.91	7.88	7.24	99.9	8.36	7.71	6.26	6.59	7.30	7.19	6.10	5.83	5.83	18.51	11.93	8.20	7.36	8.99	9.65	86.9	5.56	80.9	7.96	6.49	6.35	6.57			6.79	8.77	7.03	5.65	0.00	8.85	8.00	8.60		6.26	7.32	7.36	7.79	6.18	7.50	2.87
FE	23731.3	26499.7	21723.6	15289.8	21909.9	41061.3	21608.4	24905.7	22210.0	20981.4	22070.3	22055.5	25779.4	33968.7	19563.4	26400.3	29155.7	19269.8	23065.1	34030.3	14622.5	20359.3	39318.0	27538.6	19315.6	21030.0	27155.1	36570.5	40109.7	46679.6	28664.4		_	30121.4	41883.1	40464.3	29421.3	27258.3	31463.8	26020.8	40559.1	23897.0	24298.5	15171.2
EU	1.2885	1.4877	0.7093	0.7186	1.0187	1.3132	0.9945	1.1537	1.1083	0.7088	1.2631	1.2104	1.0872	1.5696	1.2451	1.9497	1.3618	2.3288	1.1545	1.4991			1.6549							_	1.2101							1.1299	0.9072			1.0462		1.3676
CS	4.81	21.48	6.84 0	20.45 0	3.93	8.62	16.78 0	18.82	11.01	7.39 0	23.88	13.45	16.28	4.85	5.38		18.12	4.07	5.25	4.13	16.62 0	4.65 0.9915	8.93					_			_				0.74	10.89 1		4.40				3.84 1	4.00 0	3.56 1
ANID	MVP0354	MVP0355	MVP0356	MVP0357	MVP0358	MVP0359	MVP0360	MVP0361	MVP0362	MVP0363	MVP0364	MVP0365	MVP0366	MVP0367	MVP0368	MVP0369	MVP0370	MVP0371	MVP0372	MVP0373	MVP0374	MVP0375	MVP0376	MVP0377	MVP0378	MVP0379	MVP0380	MVP0381	MVP0382	MVP0383	MVP0384	MVP0385	MVP0386	MVP038/	MIVPUSSS	MVP0389	MVP0390	MVP0391	MVP0392	MVP0393	MVP0394	MVP0395	MVP0396	MVP0397

ANID	macro_grp	Chem2012	CERAMIC TYPE	MATERIAL	SOURCE	STATE	SITE_NAME	SITE_NO	AS	ΓA	ΓΩ	ND	SM	n	YB (CE CO	CR
398	Group-B1	Mimbres-04B	Mimbres B/W Style III	Pottery	MURR	MN	Mitchell	LA 012076	2.11	52.75 0	0.5590	39.50 7	7.71 6	6.18 3.	3.68 91.45	45 4.76	6 25.09
	Group-B	Unas.	Mimbres Plain	Pottery	MURR	M	Mitchell	LA 012076	3.25	53.43 0	0.5537	51.82 10	10.40	3.86 4.	4.68 112.81	81 15.71	1 76.20
MVP0400	Group-B	Unas.	Alma Plain	Pottery	MURR	NM	Mitchell	LA 012076	6.83	40.28 0	0.4304	33.78	7.20 2	2.81 3.	3.39 74.76	76 7.14	4 25.22
	Group-B1	Mimbres-04C	Mimbres B/W Style III	Pottery	MURR	MN	Mitchell	LA 012076	3.80	41.67 0		34.90	6.45 4	4.08 3.	3.26 85.56	56 8.53	3 27.05
	Group-B2	Mimbres-08	Mimbres B/W Style III	Pottery	MURR	NM	Mitchell	LA 012076	1.55						2.80 63.31		
	Group-C2a	Mimbres-49A	Mimbres B/W Style III flare r Pottery	Pottery	MURR	¥	Mitchell	LA 012076	3.71				5.90	3.30 2.	2.68 68.53	53 5.76	5 31.70
	Group-B2	Mimbres-08	Mimbres B/W Style III	Pottery	MURR	¥	Stewart Pueblo		4.29	39.04 0	0.4571	21.16	4.01 5	5.40 2.	2.60 70.99		3 26.88
	Group-B1	Mimbres-04A	Mimbres B/W Style III	Pottery	MURR	¥	Stewart Pueblo		3.56						1		0 24.20
	Group-A	Mimbres-01	Mimbres B/W Style III	Pottery	MURR	MN	Rock House	LA 001118	1.93		0.6727		3.63 11	11.18 2.	2.41 68.03	03 1.37	7 4.40
MVP0407	Group-B	Unas.	Mimbres B/W Style III	Pottery	MURR	MN	Gonzales	LA 001679	3.23	_	0.6855				4.57 91.01	01 8.41	1 27.14
MVP0408	Group-B2	Mimbres-08	Mimbres B/W Style II	Pottery	MURR	MN	Gonzales	LA 001679	4.76	34.81 0	0.4007	19.87	3.84 5	5.59 2.	2.47 60.48	48 5.04	4 22.81
MVP0409	Group-A	Mimbres-01	Mimbres B/W Style III	Pottery	MURR	M	Gonzales	LA 001679	3.66	55.59 0	0.7995	26.76	4.92 11	11.95 4.	4.01 97.56	56 3.58	8 8.44
MVP0410	Group-C2a	Mimbres-49A	Gila Polychrome	Pottery	MURR	MN	McSherry?	LA 015050	6.28	44.46 0	0.5497	41.90		3.75 4.	4.28 99.36	36 12.86	58.87
MVP0411	Group-C2	Unas.	Alma Punctate	Pottery	MURR	M	McSherry	LA 015050	2.29	39.56	0.3269	28.42	5.99 2	2.20 2.	2.78 69.34	34 13.46	6 40.7
MVP0412	Group-B	Unas.	Three Circle Corrugated	Pottery	MURR	MN	McSherry	LA 015050	2.90	30.96	0.3748	22.34	4.34 3	3.63 2.	2.25 57.04	04 6.34	4 32.05
MVP0413	Group-B1	Mimbres-04A	Mimbres B/W Style III	Pottery	MURR	MN	McSherry	LA 015050	2.67	55.77 0	0.6019	39.85	7.77 4	4.70 4.	4.28 94.42	42 11.59	9 30.22
MVP0414	Group-B1	Mimbres-04A	Mimbres B/W Style III	Pottery	MURR	MN	McSherry	LA 015050	2.59	37.92 0	0.4288	28.16	5.91 3	3.38 2.	2.86 65.05	05 4.20	0 23.99
MVP0415	Group-C1	Mimbres-21	Mimbres B/W Style II	Pottery	MURR	MN	McSherry	LA 015050	4.89	39.05 0		34.20	5.99 1	1.69 2.	2.59 77.19	19 10.31	1 45.2
MVP0416	Group-B2	Mimbres-02B	Mimbres B/W Style III	Pottery	MURR	MN	McSherry	LA 015050	3.98	45.68 0	0.5243	32.29	6.37 4	4.33 3.	3.45 73.33	33 7.35	5 31.74
MVP0417	Group-B1	Mimbres-04C	Mimbres B/W Style III	Pottery	MURR	MN	McSherry	LA 015050	2.30	40.44 0	0.4711	31.92	6.13 3	3.94 3.	3.08 75.19	19 7.91	1 27.84
MVP0418	Group-C2a	Mimbres-49A	Reserve Plain Smudged	Pottery	MURR	¥	Mitchell	LA 012076	3.16	42.90 0		40.79	8.55 2	2.72 4.	4.08 92.09	09 11.57	7 57.32
MVP0419	Group-C2a	Mimbres-49A	Mimbres B/W Style III	Pottery	MURR	MN	Mitchell	LA 012076	4.37	39.08	0.3929	34.50	6.75 2	2.15 2.	2.81 59.27	27 11.60	0 55.52
_	Group-C2a	Mimbres-49A	Mimbres B/W Style III	Pottery	MURR	MN	Ranger Station	LA 005066	3.49	43.36 0		36.42	6.89	2.12 2.	2.75 78.16	16 12.86	54.48
	Group-B	Unas.	Mimbres B/W Style III	Pottery	MURR	NM	Rock House	LA 001118	4.66				7.14 4	4.19 4.	4.17 129.70	1	3 17.79
	Group-B	Unas.	Mimbres B/W Style III	Pottery	MURR	¥	Pruitt Ranch	LA 001117	5.99						3.67 103.70		
	Group-B1	Mimbres-04A	Mimbres B/W Style III	Pottery	MURR	¥	Pruitt Ranch	LA 001117	6.47						1		
	Group-C1	Mimbres-21	Mimbres B/W Style III	Pottery	MURR	¥	Mitchell-2	LA 012076	7.81							51 8.07	
	Group-B2	Mimbres-08	Mimbres B/W Style III flare r Pottery	Pottery	MURR	¥	Mitchell	LA 012076	4.20								
	Group-B1	Mimbres-04B	Mimbres B/W Style III flare r Pott	Pottery	MURR	M	Mitchell	LA 012076	2.25			37.62		6.39 3.	3.83 82.39	39 4.50	
	Group-B1	Mimbres-05B	Mimbres B/W Style III	Pottery	MURR	M	Mitchell	LA 012076	5.48						1		
	Group-B1	Mimbres-04A	Mimbres B/W Style III	Pottery	MURR	M	Mitchell	LA 012076	2.76	_							
	Group-B2	Mimbres-08	Mimbres B/W Style III	Pottery	MURR	M	McSherry	LA 015050	3.46								7 21.88
_	Group-B1	Mimbres-04A		Pottery	MURR	M	Stewart Pueblo		3.15	44.58 0	0.5091			3.80 3.			
	Group-C2a	Mimbres-49A	Mimbres B/W Style III	Pottery	MURR	MN	Gonzales	LA 001679	3.01	46.17 0	0.4652	40.73	7.99 2	2.60 3.	3.44 88.03	03 5.53	3 28.69
	Group-C2a	Mimbres-49A	Mimbres B/W Style III flare r	Pottery	MURR	¥	Ranger Station	LA 005066	2.85	37.89 0	0.3734	32.45	6.53 2	2.26 2.	2.74 88.34	34 12.47	7 56.22
MVP0433	Group-B	Unas.	Mimbres B/W Style III	Pottery	MURR	MN	Perrault	LA 018891	2.98	42.05 0	0.4753	29.63	5.94 6		3.01 75.24	24 3.92	2 31.13
	Group-B	Unas.	Mimbres B/W Style III	Pottery	MURR	MN	McSherry	LA 015050	2.44	40.24 0	0.4774	26.49	5.17 5	5.25 2.	2.97 65.46	46 4.49	9 13.88
MVP0436	Group-B1	Mimbres-04B	Mimbres B/W Style III	Pottery	MURR	MN	Gonzales	LA 001679	2.84	46.65 0	0.5055	33.37 (6.52 6	6.06 3.	3.30 85.02	02 5.12	2 19.48
MVP0437	Group-B1	Mimbres-04B	Mimbres Plain	Pottery	MURR	MN	Mitchell	LA 012076	2.98	61.22 0	0.5122	49.13 9	9.75 5	5.90 3.	3.69 96.75	75 5.35	5 27.03
MVP0438	Group-C2a	Mimbres-49A		Pottery	MURR	MN	Mitchell	LA 012076	5.18	33.85 0	0.3390	28.92	5.36 1	1.75 2.	2.57 65.22	22 7.64	4 52.43
	Group-A	Mimbres-01	Mimbres B/W Style III flare Pottery	Pottery	MURR	NN	Mitchell	LA 012076	2.97	58.79 0	0.7333	23.97	4.25 12	12.85 2.	2.94 89.86		
	Group-C2	Unas.	Mimbres B/W Style III	Pottery	MURR	¥	Ranger Station	LA 005066	3.06	_					_		
	Group-B2	Mimbres-02A		Pottery	MURR	MN	Pruitt Ranch	LA 001117	3.21								
MVP0442	Group-B1	Mimbres-04A	Mimbres B/W Style III	Pottery	MURR	MN	Pruitt Ranch	LA 001117	2.28	33.99 0	0.4459	30.92	5.88 4	4.85 3.	3.05 81.98	98 6.33	3 27.62

EU FE
1.3041 24327.0 6.93 75.6 172.62 0.5318
1.6470 45328.7 10.54 0.0 150.38 0.5086 1
1.1322 25349.0 6.37 51.5 137.74
4.30 1.2210 30097.9 8.11 39.3 141.82 0.3333 7.11 11.70 0.6722 16326.4 5.41 0.0 225.46 0.5859 5.48
1.2468 30465.0 6.55 57.6 93.70
8.13 0.6774 24369.4 7.31 43.1 185.13 0.5567 7.13
0.4563 9692.8 6.46 17.6 155.34 0.7857
1.2906 28307.2 7.77 48.1 154.23 0.5725
7.05 19.0
6.02 0.0 174.86
1.4443 36447.5 7.18 29.4 107.65 0.5883 1
1.3796 37687.6 5.00 0.0 76.12 0.4914
0.94// 18/63.1 5.15 0.0 1/9.41 0.282/
1.4413 2/069.1 /./0 3/.5 151.20 0.6042
1.1691 20152.5 7.20 80.3 127.65
1.2541 31015.9 6.95 49.1 119.02 13908
1.1071 21800.3 5.70 44.7 202.14 0.9136
1.2156 29715.3 8.85 109.2 146.09 0.4440
1.5006 31274.3 8.61 36.4 119.69 0.5067
8.03 1.5109 36836.5 7.73 0.0 94.32 0.6275 10.45
33639.9 7.38 56.5 100.00 0.3231
1.3450 23473.1 5.75 68.1 123.30 0.2740
1.7231 20756.6 9.81 40.9 144.66 0.6470
1.4708 25657.1 6.76 41.6 115.38 0.3413
1.2812 24010.7 6.27 37.9 135.93 3.1683
6.97 0.628/ 20951.3 6.47 60.9 183.48 0.5103 6.08 6.34 1.2031 22312.7 6.59 5.80 177.15 0.3549 7.42
1.5313 27963.6 9.62 165.8 176.66 0.9402 1
95.4 123.99
0.6472 21529.6 6.97 217.4
1.2936 26153.8 6.94 95.5 129.35 0.2189
28057.2 7.99 73.2 119.49
1.3788 32863.9 7.89 66.5 99.83 0.3709 1
23715.7 6.22 40.7 157.37 0.9654
4.25 0.9432 19843.1 8.31 69.8 178.00 0.3996 5.07
5.57 1.0686 19882.1 5.41 84.8 173.24 0.3676 6.33
4.77 1.5505 26360.7 6.04 0.0 128.13 0.3559 8.64
7.10 61.4
15.06 0.4495 12792.5 6.22 0.0 197.23 0.4852 4.09
18.22 0.6164 19570.4 5.80 71.7 166.23 0.4116 6.43
4.96 1.1217 23706.0 8.56 47.3 139.87 0.3845 7.79

ANID	macro grp	Chem2012	CERAMIC TYPE	MATERIAL	SOURCE	E STATE	SITE NAME	SITE NO	AS	LA	LU	ND S	SM	\ N	YB CE	00	CR
MVP0443	Group-B	Unas.	Mimbres B/W Style III	Pottery	MURR		Ranger Station	LA 005066	2.39	48.02 0.5	0.5526 4	44.27 8.	8.02 5.0	5.06 4.00	148.74	12	21.89
MVP0444	Group-B	Unas.	Mimbres B/W Style III	Pottery	MURR	MN	Pruitt Ranch	LA 001117	3.18	35.51 0.4	0.4288 25	25.23 5.	5.06 3.5	3.55 2.83			20.69
MVP0445	Group-A	Mimbres-01	Mimbres B/W Style III	Pottery	MURR	N	Gonzales	LA 001679	3.23	59.33 0.9	0.9357 22	22.75 4.	4.94 16.78	78 3.55	5 90.14	1 2.85	4.24
MVP0446	Group-C2a	Mimbres-49A	Mimbres B/W Style III	Pottery	MURR	MN	Mitchell	LA 012076	3.32	37.52 0.3	0.3149 30	30.72 5.	5.75 3.7	3.18 2.24	71.7	11.25	24.73
MVP0447	Group-B	Unas.	Mimbres B/W Style III	Pottery	MURR	MN	McSherry	LA 015050	4.10			1			1		16.20
MVP0448	Group-B	Unas.	Mimbres B/W Style I/II	Pottery	MURR	M	Pruitt Ranch	LA 001117	4.08								8.26
MVP0449	Group-B1	Mimbres-04A	Mimbres B/W Style III	Pottery	MURR	MN	Pruitt Ranch	LA 001117	1.58	43.13 0.4	0.4878 43	43.26 7.	7.00 3.8	3.88 3.39		1 5.81	17.57
MVP0450	Group-B2	Mimbres-08	Mimbres B/W Style III	Pottery	MURR	M	Ranger Station	LA 005066	4.29								21.28
MVP0451	Group-B	Unas.	Mimbres B/W Style II	Pottery	MURR	NM	Rock House	LA 001118	3.52					04 5.77		6.55	22.50
MVP0452	Group-B1	Mimbres-04A	Mimbres B/W Style III	Pottery	MURR	MN	Pruitt Ranch	LA 001117	3.01	54.29 0.5	0.5728 50			82 4.22	107.96	5 7.61	31.82
MVP0453	Group-B1	Mimbres-04B	Mimbres B/W Style III	Pottery	MURR	NN	McSherry	LA 015050	2.52	48.09 0.5	0.5012 36	36.50 6.	6.53 5.9	5.94 3.25	5 89.34	4.56	24.78
MVP0454	Group-B1	Mimbres-04A	Mimbres B/W Style III	Pottery	MURR	NM	Pruitt Ranch	LA 001117	3.64	44.17 0.4	0.4744 47	41.54 6.	6.26 3.27	27 3.56	6 83.73	3 7.35	22.84
MVP0455	Group-A	Mimbres-01		Pottery	MURR	N	Perrault	LA 018891	1.81	57.02 0.5	0.5938 24	24.10 4.	4.60 14.26	26 3.05	91.92		6.01
MVP0456	Group-B1	Mimbres-05B	Mimbres B/W Style III	Pottery	MURR	MN	Perrault	LA 018891	2.02	90 92.99	0.6439 47	47.43 9.	9.84 4.0	4.03 4.64	125.63	3 12.22	37.30
MVP0457	Group-B2	Mimbres-02A	Mimbres B/W Style III	Pottery	MURR	MN	Rock House	LA 001118	1.74	42.10 0.5	0.5019 43	43.94 6.	6.72 5.1	5.15 3.76	74.13	3 5.88	36.68
MVP0458	Group-C2	Unas.	Mimbres B/W Style III	Pottery	MURR	NM	Ranger Station	LA 005066	1.80					2.86 3.23		3 8.55	32.50
MVP0459	Group-B1	Mimbres-04B	Mimbres B/W Style III	Pottery	MURR	NM	Mitchell	LA 012076	2.14	38.03 0.4				3.38 3.18			29.07
MVP0460	Group-B	Unas.	Mimbres B/W Style II/III	Pottery	MURR	MN	Rock House	LA 001118	2.48	54.85 0.6	0.6563 33	33.43 6.	9.88 88.9	8.68 3.94	117.51	1 6.33	22.29
MVP0461	Group-B	Unas.	Mimbres B/W Style III	Pottery	MURR	MN	McSherry	LA 015050	1.80	39.78 0.4	0.4517 33	33.37 5.	5.61 4.4	4.48 2.86	19 69.63	3 3.97	31.22
MVP0462	Group-C2	Unas.	Alma Neckbanded	Pottery	MURR	MN	Harris	LA 001867	4.33	37.52 0.4		33.12 7.	7.16 1.8	1.89 3.03	19 76.65	5 13.57	35.46
MVP0463	Group-C2a	Mimbres-49A	Alma Plain	Pottery	MURR	N	Harris	LA 001867	1.52	49.28 0.4	0.4925 4	41.67 8.	8.91 3.61	61 3.95	94.33	3 9.17	44.73
MVP0464	Group-B	Unas.	Mogollon red on brown	Pottery	MURR	MN	Harris	LA 001867	1.75	62.29 0.6	0.6766 5	54.29 10.	10.84 5.0	5.06 5.00	114.41	1 6.03	40.19
MVP0465	Group-B1	Mimbres-04C	Black on White hatched	Pottery	MURR	MN	Harris	LA 001867	3.07	44.86 0.5	0.5114 42	42.35 7.	7.52 4.5	4.50 3.75	75 91.11	1 5.13	36.24
MVP0466	Group-C1	Mimbres-22		Pottery	MURR	M	Treasure Hill	LA 016241	8.17		0.2965 25			1.48 2.05	15 80.22		9.74
MVP0467	Group-B1	Mimbres-04A	Mimbres B/W Style III	Pottery	MURR	NM	Treasure Hill	LA 016241	2.43	36.87 0.4	0.4490 3	35.57 6.	6.35 4.01	01 3.42		1 8.28	25.87
MVP0468	Group-B2	Mimbres-08	Mimbres B/W Style III	Pottery	MURR	M	Treasure Hill	LA 016241	3.05								23.42
NAM001		El Paso Core		Pottery	MURR	M	Columbus Pueblo	LA 085774	4.99			1		3.74 4.98	1		29.37
NAM002	Group-B2	Mimbres-02A		Pottery	MURR	M	Columbus Pueblo	LA 085774	2.33								42.72
NAM004	Group-B2	Mimbres-11	Mimbres B/W Style Indeter. Pottery	Pottery	MURR	N	Columbus Pueblo	LA 085774	4.23	34.73 0.4		24.81 4.	4.87 3.82	82 3.17	7 77.83	3 21.14	44.70
NAM006	Group-B2	Mimbres-02C	Mimbres B/W Style Indeter. Pottery	Pottery	MURR	MN	Columbus Pueblo	LA 085774	3.95						_		
NAM007	Group-B1	Mimbres-05A	Mimbres Corrugated	Pottery	MURR	N	Columbus Pueblo	LA 085774	4.20							_	
NAM009	Group-B2	Mimbres-02C	Mimbres B/W Style Indeter. Pottery	Pottery	MURR	N	Columbus Pueblo	LA 085774	2.23	_							17.98
NAM010	Clay			Clay	MURR	M	Columbus Pueblo	LA 085774	2.76							5 5.50	24.45
NAM011	Group-B2	Mimbres-02A		Pottery	MURR	M	Columbus Pueblo	LA 085774	1.74								40.04
NAM012	Group-B2	Mimbres-02A	Mimbres B/W Style Indeter. Pottery	Pottery	MURR	M	Columbus Pueblo	LA 085774	2.15			25.07 5.		07 3.37			39.28
NAM013	Group-C1	Mimbres-24	Mimbres B/W Style Indeter. Pottery	Pottery	MURR	N	Columbus Pueblo	LA 085774	4.37	38.79 0.4	0.4637 33	33.18 7.	7.35 2.2	2.28 3.47	7 78.28	3 11.50	42.45
NAM014	Group-B	Unas.	Mimbres B/W Style Indeter. Pottery	Pottery	MURR	M	Columbus Pueblo	LA 085774	3.13	45.55 0.4	0.4570 30	30.15 6.	6.19 4.47	47 3.28	8 67.95	5 4.29	33.44
NAM016	Group-B	Unas.	Mimbres B/W Style Indeter. Pottery	Pottery	MURR	MN	Columbus Pueblo	LA 085774	1.58	42.95 0.4	0.4194 24	24.06 4.	4.95 5.42	42 2.96	93.95	3.49	25.14
NAM017	Group-B2	Mimbres-11	Mimbres B/W Style Indeter. Pottery	Pottery	MURR	NM	Columbus Pueblo	LA 085774	2.69	35.53 0.4	0.4533 23		4.63 4.28	28 3.05	5 59.08		38.71
NAM019	Group-C1	Mimbres-21	Mimbres B/W Style Indeter. Pottery	Pottery	MURR	NM	Columbus Pueblo	LA 085774	3.52		0.3571 33	33.64 6.	6.00 0.92	92 2.23		9.53	26.47
NAM020	Group-B2	Mimbres-02A	Mimbres B/W Style Indeter. Pottery	Pottery	MURR	NM	Columbus Pueblo	LA 085774	2.37	39.49 0.4	0.4620 23	23.18 4.	4.78 4.82	82 3.15	5 66.30	4.73	32.23
OK001	Group-B2	Mimbres-11	Mimbres B/W Style III	Pottery	TAM	M	Old Town	LA 001113	2.08								46.47
OK002	Group-B1	Mimbres-04C		Pottery	TAM	N	Old Town	LA 001113	1.65								
OK003	Group-B1	Mimbres-05A	Mimbres B/W Style I	Pottery	TAM	MN	Old Town	LA 001113	4.61	50.00 0.5	0.5671 5	55.88 9.	9.97 2.6	2.68 4.74	4 165.52	15.89	49.82

>	47.30	40.58	15.84	73.26	50.98	-14.87	44.24	34.70	46.82	98.08	54.43	47.15	22.70	50.20	68.41	43.40	30.94	38.43	53.47	80.49	63.20	75.45	78.06	37.85	56.89	38.28	86.38	73.63	29.66	30.84	66.32	37.77	40.44	71.30	53.77	76.19	62.83	41.18	56.92	55.28	43.47	44.93	64.85	62.39
F	5276.7	4043.6	3467.7	5187.7	4839.5	3584.6	3238.8	3762.9	4539.5	4824.3	4540.0	3277.4	2933.2	4543.2	5825.5	4685.7	4201.1	4551.3	4480.2	6307.1	5123.0	4311.7	5450.5	3561.1	6118.4	3461.8	4685.5	8			5253.4	1819.6	2638.6	3273.2	3397.5	3506.9	3236.2	3627.3	2737.8	2143.4	3106.8			2412.9
NA	16151.4 E	14969.1	22677.5		16356.4	12070.4	6269.3	7728.5	16537.1	13513.7 4	11214.8 4	14361.3	22006.9	13737.5 4	13915.0 E	19713.9	13630.1	16372.9	14353.0 4	17024.9	15858.5	17478.9 4	13855.4	15307.7	13661.3 6		15099.9							14084.9		16479.0	11866.7	14756.4	13255.9	11877.2	11436.1			13648.3
MN	1371.4 16	454.3 149	303.5 226		444.0 163	786.9 120	746.5 162	190.1	378.2 16	441.4 13	231.6 11.	538.0 143	175.0 220	800.5 13	226.1 139	645.2 19.	376.8 136	703.8 163	181.3 143	690.2 170	537.0 158	269.1 174	249.8 138	1053.6 153		305.1 10	577.9 150			1	_	`		`	`	`		176.6 14	744.6 132	1075.1 118	305.7 114	`		793.6 136
¥	27553.4 13	31286.6 4!	28786.5 30		29256.4 4	18977.0	28136.5 7	27469.3	33158.0 3	25869.7 4	28791.6 2:		31756.5 1	29625.8 80	29093.3 2.		28220.3 3	31317.0 70		51555.6 6	39435.0 5.		29928.3 2	41933.2 10					34270.3 118								28661.1 2:	34238.4 1.	33834.8 7					0.0
DY				61 26853.1				•				39 31840.1				85 32534.7	-		96 29608.1			19 31505.1					7.738 32960.1			-				- 1		5.451 316		3.598 342:	3.298 338	3.683 25099.1	87 32669.7	51	66	74
CA I	9.9 5.9869	3.3432	3.3 2.7938		5.0 7.0836	3.7 1.8853	5.2 4.9216	5.7 2.5603	3.0 9.5599	1.4 6.8759	1.3 4.4039	7.7 4.4739	1.1 2.5472	1.1 7.0629	5.0 4.7072		5.3 3.5018	5.4 5.1308	3.9196	7.1 5.8664	1.1 6.7069	1.9 7.8119	1.2 5.0429	3.2 2.8789		7															1.2 3.887			0.0 9.574
	11816.9	13020.1	12068.3		13665.0	10888.7	13925.2	5965.7	13648.0	12974.4	9984.3	12297.7	5221.1	12691.1	10946.0	16124.4	1	9945.4	11955.6	25207.1		14491.9	9504.2	16858.2	_		`	ļ						_		13128.3	11577.6	10589.9	11137.6	28779.1	7121.2			
BA	1019.7	638.2	233.9	835.2	1018.4	287.4	763.0	401.2	923.0	820.8	659.0	569.2	236.2	704.7	519.4	1368.5	513.0	544.5	619.6	1678.7	1019.9	995.3	911.5				1061.6				_			746.6			552.0	766.8	622.6		585.2			852.3
AL	85074.7	86934.9	104344.9	101966.6	89618.0	92081.8	83092.5	84249.9	83316.2	98416.1	91465.9	87955.0	110437.5	90789.7	94251.6	89721.4	94898.2	83404.6	90643.0	86485.8	80608	93409.2	88182.2	102649.8	82618.1	79844.7	85423.6	93584.9	79755.7	72715.8	79443.8	73704.1	58602.9	89968.2	90297.5	88529.1	97379.5	86722.1	84728.8	94427.9	84368.3	77525.8	75355.9	84429.7
ZR	184.9	180.6	219.7	193.3	240.6	120.1	182.9	143.4	189.7	192.7	216.5	206.6	187.8	183.6	162.2	209.0	142.9	9.981	160.0	164.2	178.3	229.9	186.8	145.6	254.3	221.3	315.4	167.5	145.1	125.9	200.4	121.3	168.6	199.3	180.6	198.4	169.3	195.1	150.6	140.5	190.7	177.0	160.0	186.3
NZ	70.8	1116.7	46.9	9.6/	6.3	70.7	75.8	51.5	715.2	76.3	88.4	108.8	61.4	78.0	63.5	83.1	103.0	9.89	64.6	143.9	84.9	79.0	94.7	110.4	62.0	62.4	101.3	73.8	62.8	58.0	90.1	59.4	41.5	62.2	66.7	96.4	62.6	50.5	60.2	8.06	59.0	79.2	94.3	98.1
H	17.96	19.66	54.97	13.04	15.68	22.53	18.25	27.85	16.32	18.04	28.27	20.24	54.57	19.89	20.23	12.73		31.86	24.27	10.63	13.20	17.90	20.63	10.08			18.21					. 7		18.97		11.09	27.77	28.17	20.40	9.81	24.14			18.43
\ TB	1.04	0.62	0.44	0.64	1.18	0.38	0.75	0.54	1.45	96.0	1 0.74	0.69	3 0.33	1.33	0.82	0.81	0.53	0.79	0.57	0.85	0.99	1.21	3 0.80	0.47	0.67	0.32	1.21	96.0	99.0	0.64				0.91		1.03	0.75	3 0.53	0.52	3 0.62	0.63		0.84	1.44
TA	1.3711	1.3739	2.4167		1.0084	1.3916	1.2851	1.4782	1.2283	1.2903	1.4784	1.3531	3.1478	1.4687	1.3864	0.9469	1.4977	2.0994	1.5436	0.8647	0.9487	1.2201	1.4368	0.5916		1.4242	2.5590			_						1.0601	1.7871	1.6808	1.5514	0.6398	1.7252			1.3571
SR	244.18	235.77	108.69	297.38	230.52	225.22	239.04	109.71	462.78	262.69	187.04	255.96	84.99	391.51	262.58	400.21	189.85	171.67	281.78	516.57	328.68	285.14	240.07	369.29	202.13	157.57	373.2	255.0	204.1	265.9	541.3	226.0	356.7	280.9	217.8	-	182.0	6'661	212.5	400.8	162.6	296.9	265.5	215.3
SC	98.9	6.74	3.72	11.42	9.05	5.17	6.45	5.92	8.12	10.25	8.11	7.49	4.20	10.77	11.20	8.76	7.76	6.92	8.88	10.18	10.23	8.23	9.20	4.55	7.17	5.31	9.14	12.83	7.95	6.03	9.91	6.47	4.54	11.86	10.93	9.05	10.06	6.70	7.43	7.05	9.01	8.64	8.52	12.88
SB	0.3052	0.4884	0.7728	0.4720	0.6121	0.2059	0.2237	0.5124	0.5474	0.3513	0.3829	0.6725	0.5947	0.4171	0.3496	1.0243	0.3942	0.4175	0.7063	0.9591	0.3650	0.2787	0.3516	2.4944	0.3725	0.5687	0.5442	0.4552	0.8273	0.3424	0.3938	0.4271	0.3181	0.3737	0.4823	1.4292	1.3761	0.6498	0.6467	1.0973	0.5099	0.6369	0.3569	0.6857
RB	133.34	168.93	187.96	106.47	126.72	39.71	132.25	178.52	108.72	119.54	149.95	159.80	215.33	156.86	151.04	107.64	177.96	186.55	165.31	100.82	90.70	131.53	133.10	145.26	137.77	179.32	118.23	144.62	203.02	176.33	114.16	175.71	130.36	149.50	168.31	139.89	172.20	171.69	196.28	99.38	181.10	194.73	121.88	154.59
Z	48.0	1.99	44.4	65.3	44.3	21.4	48.1	73.9	0.0	64.1	41.5	8.99	71.9	88.2	59.8	51.7	50.9	35.1	52.3	0.0	0.0	9.89	0.0	0.0	45.2	0.0	21.0	0.0	30.8	0.0	31.0	0.0	16.5	0.0	0.0	30.3	0.0	9.6	0.0	0.0	0.0	0.0	0.0	0.0
生	90.9	6.95	6.27	6.58	8.93	6.26	6.64	6.07	7.39	6.28	6.94	7.34	7.37	99.9	98.9	7.32	5.65	6.25	6.48	66.9	6.22	8.26	7.03	5.61	9.64	8.97	12.07	7.22	6.73	5.76	8.28	5.38	6.47	7.29	7.69	7.67	6.44	7.07	6.87	6.17	8.04	7.21	92.9	7.67
丑	23763.5	22887.9	10857.5	37120.8	24269.3	10216.0	22984.6	22190.1	28895.6	31643.3	25445.7	26730.7	11479.1	29282.2	27526.8	26642.4	24176.0	19763.2	24089.0	38948.1	29957.1	30187.0	30558.3	19579.3	25083.5	18334.7	39293.8	30160.3	25552.9	14426.7	35534.4	16175.2	15754.0	27578.1			25121.2	19506.1	22666.8	26630.3	18972.0	23992.1	35785.2	1.7245 32430.0
EU	1.4822	1.0134	0.4993	1.2206	2.0503	0.4352	1.2664		2.2253	1.7491	1.0478	1.1544	0.4935	1.6943	1.2328		0.9111	1.0655	1.0270	1.4737	1.7292	1.8415	1.3614	1.2096			2.0453				1.6112			1.3605	1.0147	1.5429		0.8903	9998.0	1.3743	0.7195		1.2993	1.7245
CS	4.85	4.65	12.61	4.44	4.07	5.02	4.34	7.07	3.30	7.56	5.51	5.25	12.72	24.28	17.34	3.16		8.97	10.68		3.90	5.10	5.46	22.79	4.67		3.71	15.16	7.41						17.53	12.73		9.41	7.16		18.55 (7.82
ANID	MVP0443	MVP0444	MVP0445	MVP0446	MVP0447	MVP0448	MVP0449	MVP0450	MVP0451	MVP0452	MVP0453	MVP0454	MVP0455	MVP0456	MVP0457	MVP0458	MVP0459	MVP0460	MVP0461	MVP0462	MVP0463	MVP0464	MVP0465	MVP0466	MVP0467	MVP0468	NAM001	NAM002	NAM004	NAM006	NAM007	NAM009	NAM010	NAM011	NAM012	NAM013	NAM014	NAM016	NAM017	NAM019	NAM020	OK001	OK002	OK003

ANID	macro_grp	Chem2012	CERAMIC TYPE	MATERIAL	SOURCE	STATE	SITE_NAME	SITE_NO	AS	ΓA	ΠΠ	ND	SM	Π	YB C	CE CO	CR
OK004	Group-C2a	Mimbres-49A	Mimbres B/W Style I	Pottery	TAM		Old Town	LA 001113	4.12	45.11	0.4591	46.77	7.93	2.61 3.	3.14 93.01	13.13	57.56
OK005	Group-C2b	Mimbres-41	Mimbres B/W Style I	Pottery	TAM	MN	Old Town	LA 001113	1.82	37.54	0.2780	35.38	5.28	2.06 2.	2.20 73.98	8 6.38	27.13
OK006	Group-B1	Mimbres-04C	Mimbres B/W Style I	Pottery	TAM	MN	Old Town	LA 001113	2.82	44.68	0.4328	40.36	6.71	3.27 3.	3.89 94.40	6.63	35.67
OK007	Group-C2b	Mimbres-41	Mimbres B/W Style I	Pottery	TAM		Old Town	LA 001113	2.37	39.77	0.3021		5.47	2.53 1.	1.84 78.75	5 11.29	26.03
OK008	Group-B1	Mimbres-04C	Mimbres B/W Style I	Pottery	TAM		Old Town	LA 001113	2.38	46.17	0.4352			3.08 3.			38.48
OK011	Group-B	Unas.	Mimbres B/W Style II	Pottery	TAM		Old Town	LA 001113	0.00	41.14	0.3307	33.94	5.38	2.03 2.	2.89 83.38	3.39	21.11
OK012	Group-C1	Mimbres-21	Mimbres B/W Style II	Pottery	TAM		Old Town	LA 001113	0.00		0.2928		5.27		2.63 75.69		50.74
OK013	Group-B1	Mimbres-04C	Mimbres B/W Style II	Pottery	TAM		Old Town	LA 001113	1.57		0.4054		6.44		3.58 87.19		34.29
OK014	Group-B	Unas.	Mimbres B/W Style II	Pottery	TAM	MN	Old Town	LA 001113	4.48	39.98	0.4013	32.41	5.65	2.93 2.	2.40 74.13	3 8.99	51.14
OK015	Group-B	Unas.	Mimbres B/W Style II	Pottery	TAM		Old Town	LA 001113	3.21	37.34	0.3745	32.29	5.58	2.42 3.	3.41 66.00	90.8	55.69
OK016	Group-B2	Mimbres-02A	Mimbres B/W Style II	Pottery	TAM	MN	Old Town	LA 001113	1.12	37.39	0.3879	32.81	5.30	4.62 2.	2.94 67.58	8 5.05	35.38
OK017	Group-B1	Mimbres-04C	Mimbres B/W Style II	Pottery	TAM	MN	Old Town	LA 001113	1.25	42.39	0.4289	37.28	6.57	2.42 3.	3.54 85.15	5 10.85	25.76
OK018	Group-B1	Mimbres-09	Mimbres B/W Style II	Pottery	TAM	MN	Old Town	LA 001113	2.90	53.61	0.5124	48.60	9.32	2.44 4.	4.04 92.55	5 3.52	17.27
OK019	Group-C1	Mimbres-21	Mimbres B/W Style II	Pottery	TAM	MN	Old Town	LA 001113	2.85	35.58	0.2954	30.64	2.06	1.33 2.	2.34 69.41	1 8.42	48.83
OK022	Group-B2	Mimbres-02A	Mimbres B/W Style II	Pottery	TAM	MN	Old Town	LA 001113	00.00	41.85	0.4585	35.30	7 98.9	4.29 3.	3.53 66.96	6 6.13	34.71
OK023	Group-B2	Mimbres-02A	Mimbres B/W Style II	Pottery	TAM		Old Town	LA 001113	2.23		0.4066						
OK024	Group-B2	Mimbres-08	Mimbres B/W Style III	Pottery	TAM	MN	Old Town	LA 001113	3.83	32.06	0.3794	12.43	3.29	4.34 2.	2.38 56.40	0 6.10	22.00
OK025	Group-B2	Mimbres-11	Mimbres B/W Style III	Pottery	TAM		Old Town	LA 001113	3.29	35.06	0.4819	30.40		4.93 3.	3.10 73.30	16.41	42.79
OK026	Group-B2	Mimbres-11	Mimbres B/W Style III	Pottery	TAM	MN	Old Town	LA 001113	2.90	33.63	0.4168	33.32	4.56	4.20 2.	2.99 74.01	17.31	45.47
OK027	Group-B2	Mimbres-02A	Mimbres B/W Style III	Pottery	TAM		Old Town	LA 001113	1.54	44.50	0.5689	42.38	7.01		3.42 74.51		36.14
OK028	Group-B1	Mimbres-04C	Mimbres B/W Style III	Pottery	TAM	MN	Old Town	LA 001113	1.72	45.44	0.5676	44.82		3.78 3.			28.99
OK029	Group-A	Mimbres-01	Mimbres B/W Style III	Pottery	TAM	MN	Old Town	LA 001113	1.41	52.19	0.6110	27.93	3.94 15	15.39 2.	2.59 84.96	1.20	4.98
OK030	Group-B	Unas.	Mimbres B/W Style III	Pottery	TAM		Old Town	LA 001113	2.71	33.48	0.3076	24.49	3.54	3.70 2.	2.18 58.05		
OK031	Group-B1	Mimbres-05A	Mimbres B/W Style I	Pottery	TAM		Saige-McFarland	LA 005421	4.37		0.5998						50.89
OK032	Group-C1	Mimbres-21	Mimbres B/W Style III	Pottery	TAM		Saige-McFarland	LA 005421	3.08	37.82	0.2740			1.44 2.	2.07 78.83	13 8.90	44.30
OK033	Group-C1	Mimbres-21	Mimbres B/W Style III	Pottery	TAM		Saige-McFarland	LA 005421	1.98		0.3181	38.39		1.60 2.		1	
OK034	Group-C1	Mimbres-22	Mimbres B/W Style III	Pottery	TAM	NM	Saige-McFarland	LA 005421	3.56	39.45	0.2499	41.11	4.97	1.18 1.	1.87 85.40	0 7.85	20.49
OK035	Group-C1	Unas.	Mimbres B/W Style I	Pottery	TAM		Saige-McFarland	LA 005421	1.90		0.2470						46.48
OK037	Group-C1	Unas.	Mimbres B/W Style III	Pottery	TAM		Saige-McFarland	LA 005421	4.11		0.4481	33.11		2.86 3.	3.21 68.66	7.71	44.69
OK038	Group-C1	Mimbres-21	Mimbres B/W Style II	Pottery	TAM		Saige-McFarland	LA 005421	2.44		0.3089					_	
OK039	Group-C1	Mimbres-21	Mimbres B/W Style II	Pottery	TAM		Saige-McFarland	LA 005421	1.73	-	0.2933						66.93
OK040	Group-C1	Mimbres-21	Mimbres B/W Style II	Pottery	TAM		Saige-McFarland	LA 005421	2.42	_	0.3314						42.71
OK041	Group-C1	Mimbres-21	Mimbres B/W Style II	Pottery	TAM		Saige-McFarland	LA 005421	2.41		0.3340					1	
OK042	Group-B1	Mimbres-05A	Mimbres B/W Style III	Pottery	TAM		Saige-McFarland	LA 005421	3.93	_	0.6150						
OK044	Group-C1	Mimbres-21	Mimbres B/W Style I	Pottery	TAM		Saige-McFarland	LA 005421	1.96		0.2898					1	
OK045	Group-C1	Unas.	Mimbres B/W Style III	Pottery	TAM		Saige-McFarland	LA 005421	2.57		0.5271			2.92 3.			
OK047	Group-B	Unas.	Mimbres B/W Style II	Pottery	TAM		Saige-McFarland	LA 005421	2.95		0.3333		Ì	1.67 2.			
OK048	Group-C1	Mimbres-21	Mimbres B/W Style III	Pottery	TAM		Saige-McFarland	LA 005421	1.79	37.13	0.3560	26.53		1.64 2.	2.45 68.04		42.51
OK049	Group-C1	Mimbres-21	Mimbres B/W Style III	Pottery	TAM		Saige-McFarland	LA 005421	1.88	35.34	0.3048				2.00 69.26	8.54	63.04
OK050	Group-C1	Mimbres-24	Mimbres B/W Style III	Pottery	TAM		Saige-McFarland	LA 005421	3.05		0.4913		8.07		4.03 74.67		
OK051	Group-B1	Mimbres-05A	Mimbres B/W Style III	Pottery	TAM	M	Saige-McFarland	LA 005421	4.15	57.58	0.6111	1		4.95 3.	3.72 92.53		
OK052	Group-C1	Mimbres-21	Mimbres B/W Style III	Pottery	TAM		Saige-McFarland	LA 005421	5.52	40.72	0.3972					1	
OK053	Group-B1	Mimbres-04A	Mimbres B/W Style II	Pottery	TAM		Saige-McFarland	LA 005421	2.34		0.4239						
OK054	Group-C1	Mimbres-21	Mimbres B/W Style II	Pottery	TAM	MN	Saige-McFarland	LA 005421	1.45	38.64	0.2838	30.16	5.30	1.10 2.	2.53 75.86	8.55	52.14

>	83.59	67.59	79.83	89.06	60.52	40.47	29.80	59.92	72.51	74.79	41.51	66.01	45.73	40.74	26.60	47.93	48.89	59.14	64.26	56.45	70.71	15.98	44.49	77.59	35.94	72.46	40.61	41.04	65.41	51.69	54.12	48.05	80.16	65.01	49.01	82.56	76.07	44.81	71.86	70.81	87.90	53.03	51.26	51.80
I	4952.5	3614.5	2859.9	3645.6	3811.7	3126.2	2264.6	3172.6	4379.6	4127.3	2944.7	3426.0	2611.5	2604.3	3450.9	3213.1	2759.8	2247.9	3420.6	2938.3	3813.2	0.0	2514.2	4591.0	1096.4	2819.4	1213.0	0.0	3766.1	2767.5	2086.4	2406.6	1.7887	42/8.1	9.1677	4276.5	3372.7	2400.4	3019.2	3894.5	5094.3	2796.7	3997.1	2638.8
NA	12741.0	15861.0	12526.0	16091.4	14793.5	12993.7	17544.5	13536.7	14316.7	13638.3	14716.7	16442.0	14639.3	16431.9	13175.4	10191.9	8.5006	11652.9	10807.6	14749.2	15076.5	22941.1	0.0	15095.3	17842.5	19356.5	14893.7	0.0	11454.9	19152.3	0.0	18418.4	16927.5	13082.2	0.0	13832.5	17129.6	15635.8	19029.6	15229.8	16791.3	17790.7	15256.4	18014.2
M		388.0					933.2	338.9	461.7	422.2	248.8	. 201.3	431.5		. 9.967		219.3	1496.0	. 9.149	247.4	445.3	148.7	175.8			6.088		830.0			921.2			401.8	8/8.9									1081.3
¥	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0						0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0		0.0
DY	5.820	3.644	5.171	2.696	3.854	4.173	2.443	5.043	3.326	3.541	3.029	5.477	6.325	2.643	4.439	3.516	2.415	3.740	3.471	4.921	5.312	1.700	2.945	6.486	3.853	3.189	2.387	2.932	5.172	3.391	2.364	2.545	3.410	0.525	3.424	4.665	4.071	3.634	3.952	6.849	6.895	2.446	4.763	4.359
CA	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0:0	0:0	0.0	0.0	0.0	0.0	0:0	0.0	0.0	0.0	0:0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
BA	1003.4	1048.9	6.797	943.2	704.8	981.5	1258.7	773.5	875.6	993.5	596.2	751.5	929.0	830.2	647.2	373.1	453.7	802.8	564.9	720.8	791.1	482.3	795.8	537.9	931.1	911.4	887.7	0.666	602.3	975.5	903.8	820.4	804.8	432.8	9.088	581.9	0.088	1118.5	1054.8	529.0	296.8	891.0	295.6	884.2
AL	82020.6	89320.5	90103.3	93899.7	83753.5	74841.6	80598.6	83659.2	78333.3	81670.8	78606.0	80400.1	83877.7	77367.4	82156.1	88479.4	77943.3	76312.7	78937.4	82517.4	87294.5	90604.5	70821.1	76868.3	84123.2	91934.3	80978.3	83130.1	69738.6	87626.2	84955.3	83533.0	84561.0	70054.5	7.1528/	76907.3	76704.6	83708.9	81998.2	80021.7	89934.0	88049.3	87282.0	85859.0
ZR		124.4			183.8	145.2	166.2	147.3	171.3	183.7	188.9	212.6	226.7	144.3	219.0	221.3	308.0	192.4	173.0	9.761	239.7	231.2	222.0	279.9								_												191.2
ZN	125.1	91.7			_		81.1	82.4	59.5	63.0	56.7	68.0	70.0	9.6/	45.1	51.7	44.0	62.6	66.2		82.7	43.5	43.0						_															90.6
3 TH	6 14.02	1 11.17		1 10.59	4 17.64	_	7 9.19	7 17.51	4 16.26	6 14.16	7 20.76	6 16.38	9 14.62	7 8.59	9 19.09	2 23.37	5 23.88	0 19.22	9 19.64	7 18.70	9 17.78	2 48.59	2 23.71	1					_					$=$ \downarrow			l				8 16.58		_	9 9.72
TA TI	13 1.06	95 0.61	16 0.89		52 0.74	23 0.66	96 0.67	65 0.87	80 0.74	48 0.66	30 0.67	46 0.86	88 1.09	38 0.67	80 0.79		76 0.35	10 0.60	98 0.59	28 0.87	32 0.89	74 0.32	84 0.42	71 1.19	07 0.64	_						_	_						18 0.66		08 1.18			63 0.59
		0.9195	_		1.2552	6 0.8623	9659.0	1.1265	1.1680	1.1048	1.6730	1.3846	8898.0	0.7138	1.3380		1.5476	3 1.5610	1.8198	5 1.4228	1.3232	3 2.6374	1.3484	1.627								_							$^{\circ}$			_		6 0.6863
SR	324.9	1.687	276.8		445.7	261.6	357.6	287.1	393.6	400.4	319.2	304.4	195.3	406.4	338.5	122.4	133.5	276.8	242.5	348.5	6'11'	127.3	230.7	168.2	448.1	348.4	386.9	516.1	438.0	368.8	341.3	305.1	286.2	165.9	350.6			405.7	533.3	355.9	280.8	360.5	191.7	390.6
SC	13.62	9.21	10.46	8.78	8.74	5.95	7.25	9.55	8.37	8.90	9.25	7.47	9.50	6.17	10.58	9.19	5.62	8.12	8.36	10.89	8.74	3.66	5.34	10.09	6.24	8.40	4.61	5.51	8.66	7.22	7.30	6.11	8.63	7.75	7.75	_		6.29	7.77	9.01	12.59	7.79	6.71	6.86
SB	0.8042	0.2436	0.4721	0.3007	0.4275	0.2232	1.1116	0.4296	1.2985	1.3394	0.6021	0.2947	0.6979	2.9924	0.3587	0.4341	0.5037	0.8378	0.7127	0.4763	0.4239	0.6006	0.5481	0.5984	3.3464	1.6474	6.1460	4.4768	0.6432	1.3156	2.1740	1.9130	1.3321	0.6237	2.0480	0.7025	2.7016	1.4769	1.0478	0.4751	0.4919	2.6074	0.4371	1.7763
RB	148.37	106.76	129.99	101.44	131.90	101.73	122.23	106.26	137.78	122.40	173.31	116.13	128.41	112.03	146.11	178.66	183.98	209.04	213.36	145.83	139.78	221.07	163.17	160.43	133.21	120.12	123.01	108.27	136.85	111.80	124.25	118.43	124.25	148.22	125.48	151.86	117.31	110.30	101.41	102.13	117.13	134.04	141.31	124.96
Z		0.0		0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0		0.0								0.0			0.0	0.0	0.0			0.0
出	99.8	29.5	8.45	29.5	99.9	5.34	6.49	5.63	6.34	6.57	7.36	7.03	7.35	5.46	9.60		9.53	7.17	7.38	7.28	60'6	5.87	7.05	10.15	6.04	6.21	6.54	5.27	7.21	6.04	6.93	6.15	6.19	7.55	7.05	7.27	7.13	5.56	5.74	66.9	7.50	7.07	7.94	6.44
HE	41890.8	35149.9				18852.7			27949.9		19555.8	27982.7	23056.1	22940.2	24256.8		19864.9	25457.4	25449.7	25717.5	34469.0	10692.4	19449.4	31567.5		31919.6	21721.4																	25965.0
EU	1.8639	1.4226	1.4226	1.3823	1.3328	1.1860	1.2394	1.3213	1.2758	1.3033	1.0175	1.3237	1.9343	1.0863	1.2890	0.6506	0.5993	0.9937	1.0172	1.3586	1.3563	14.98 0.4282	0.6790	1.2625		1.3822	1.2535	1.0557	1.2716	1.3743	1.2223	1.2959	1.2530	1.0969	1.2388	1.3407	1.4774	1.1515	1.2229	1.2467	1.6888	1.3905	1.0978	1.2209
CS	8.95	4.45	6.53	4.28	5.50	2.47	18.54	2.09	8.27	8.33	16.10	4.56	4.51	12.25	15.05	17.87	9.30	7.70	7.72	15.73	4.45	14.98	6.01	6.27	19.66	18.55	19.75	14.34	59.05	20.31	18.73			0.40	16.67	21.65	11.39	13.26	12.23	13.99	6.21	16.99	4.72	15.71
ANID	OK004	OK005	OK006	OK007	OK008	OK011	OK012	OK013	OK014	OK015	OK016	OK017	OK018	OK019	OK022	OK023	OK024	OK025	OK026	OK027	OK028	OK029	OK030	OK031	OK032	OK033	OK034	OK035	OK037	OK038	OK039	UK040	UK041	UK042	UK044	OK045	OK047	OK048	OK049	OK050	OK051	OK052	OK053	OK054

ANID	macro_grp	Chem2012	CERAMIC TYPE	MATERIAL	SOURCE	STATE	SITE_NAME	SITE_NO	AS	LA	ΓΩ	ND	SM	n	YB	CE CO	CR
OK055	Group-C1	Mimbres-21	Mimbres B/W Style II	Pottery	TAM		Saige-McFarland	LA 005421	1.40		0.2669 2	29.98 4	4.92	1.24	1.92 70.83	33 10.83	64.05
OK056	Group-B1	Mimbres-05A	Mimbres B/W Style I	Pottery	TAM	MN	Saige-McFarland	LA 005421	3.20		0.7054 4		9.09	4.01 5	5.09 86.41	11 9.02	65.49
OK057	Group-C1	Mimbres-21	Mimbres B/W Style I	Pottery	TAM	MN	Cameron Creek	LA 000190	5.69	36.96	0.2577 3	33.32 5	5.04	1.14 2	2.26 72.19	19 9.03	90.09
OK058	Group-C1	Mimbres-24	Mimbres B/W Style I	Pottery	TAM	MN	Cameron Creek	LA 000190	4.63		0.4153 3	36.82	7.64 0	0.00	3.30 80.05	12.58	
OK059	Group-C2a	Mimbres-49A	Mimbres B/W Style II	Pottery	TAM	MN	Cameron Creek	LA 000190	2.84	49.61 0	0.4665 4	46.36 9	9.10 3	3.38 4	4.06 91.12	10.62	44.78
OK060	Group-C1	Unas.	Mimbres B/W Style II	Pottery	TAM		Cameron Creek	LA 000190	3.99		0.3866 3		69.9	1.90		99 11.03	
OK061	Group-C1	Mimbres-24	Mimbres B/W Style II	Pottery	TAM	NM	Cameron Creek	LA 000190	2.29		0.3479 3			1.44 2		1	
OK062	Group-C1	Mimbres-21	Mimbres B/W Style II	Pottery	TAM		Cameron Creek	LA 000190	1.90	37.25 0	0.3271 2		5.52	1.47 2	2.50 71.99	96.64	
OK063	Group-B	Unas.	Mimbres B/W Style III	Pottery	TAM	MN	Cameron Creek	LA 000190	1.86	50.45 0	0.4031 4		6.93 2	2.68 3	3.17 101.80	30 9.75	31.78
OK064	Group-B2	Mimbres-08	Mimbres B/W Style III	Pottery	TAM		Cameron Creek	LA 000190	2.80	37.44 0	0.3531 2	25.45	3.80 5	5.28 2	2.38 59.36	38.88	20.06
OK065	Group-A	Mimbres-01	Mimbres B/W Style III	Pottery	TAM	MN	Cameron Creek	LA 000190	2.42	69.33 0	0.6418 2		4.84	9.78	3.31 99.61	51 2.95	12.00
OK067	Group-B2	Mimbres-08	Mimbres B/W Style III	Pottery	TAM		Cameron Creek	LA 000190	3.38	37.84 0	0.3925 2	22.19 3	3.95 5	5.03 2	2.38 66.07	3.08	22.78
0K068	Group-B2	Mimbres-11	Mimbres B/W Style III	Pottery	TAM	MN	Cameron Creek	LA 000190	3.15	36.45 0	0.4634 3	35.13 4	4.94 4	4.11 3	3.03 70.62	52 12.60	41.82
0K069	Group-B1	Mimbres-04A	Mimbres B/W Style III	Pottery	TAM	MN	Cameron Creek	LA 000190	1.41	46.35 0	0.4470 5	53.42 6	6.54 4	4.10 3	3.19 96.17		20.04
OK070	Group-A	Mimbres-01	Mimbres B/W Style III	Pottery	TAM	MN	Cameron Creek	LA 000190	2.14	56.36	0.4850 3	32.18 4	4.17 10	10.29 2	2.84 80.80	30 2.54	7.95
OK071	Group-C1	Mimbres-22	Mimbres B/W Style III	Pottery	TAM		Saige-McFarland	LA 005421	6.54	_				1.29 2			
OK072	Group-C1	Unas.	Mimbres B/W Style III	Pottery	TAM		Saige-McFarland	LA 005421	3.11	37.31 0	0.3003 2	29.59 E	5.40	1.56 2	2.74 71.08	38 7.48	32.88
OK073	Group-C1	Mimbres-22	Mimbres B/W Style III	Pottery	TAM	MN	Saige-McFarland	LA 005421	6.16	44.22 0	0.2642 4	43.92	5.29	1.06 2	2.12 78.70	70 5.85	7.85
OK074	Group-C1	Mimbres-22	Mimbres B/W Style III	Pottery	TAM	MN	Saige-McFarland	LA 005421	6.73	39.61 0	0.2150 4	41.13 5	5.09 0	0.96	2.13 73.24	24 6.53	11.59
OK075	Group-A	Mimbres-01	Mimbres B/W Style III	Pottery	TAM		Cameron Creek	LA 000190	2.05	71.97 0	0.6110 3	39.59	5.39 10	10.93	3.57 93.49	19 2.87	11.99
OK076	Group-A	Mimbres-01	Mimbres B/W Style III	Pottery	TAM	MN	Cameron Creek	LA 000190	4.85	76.89 0		30.61	5.18 11	11.93 3	3.18 101.43		7.85
OK077	Group-B1	Mimbres-04A	Mimbres B/W Style III	Pottery	TAM	MN	Cameron Creek	LA 000190	1.66	50.35 0	0.4794 4	46.20	7.33 3	3.87	3.53 108.72	72 4.99	23.45
OK078	Group-A	Mimbres-01	Mimbres B/W Style III	Pottery	TAM		Cameron Creek	LA 000190	1.56	62.89	0.5642 3	33.52 4	4.67		2.95 105.83	33 2.77	13.67
OK079	Group-B1	Mimbres-04A	Mimbres B/W Style II/III	Pottery	TAM		Cameron Creek	LA 000190	2.16	50.31 0	0.4997 4	42.22			3.27 93.98		22.47
0K080	Group-B2	Mimbres-08	Mimbres B/W Style III	Pottery	TAM		Cameron Creek	LA 000190	5.69	36.02 0	0.3649 2	29.17 3	3.81 3	3.87 2	2.22 65.55	55 4.38	23.16
OK082	Group-A	Mimbres-01	Mimbres B/W Style II/III	Pottery	TAM		Cameron Creek	LA 000190	3.21	53.46 0	0.4902 2	28.62 4	4.33 11	11.11 2	2.49 97.96	3.25	
OK083	Group-B2	Mimbres-02A	Mimbres B/W Style III	Pottery	TAM	NM	Cameron Creek	LA 000190	2.20	52.37 0	0.4851 3	36.27 5	5.97	4.77 3	3.03 90.26	26 5.62	36.94
OK084	Group-B1	Mimbres-04A	Mimbres B/W Style III	Pottery	TAM		Cameron Creek	LA 000190	2.74								
OK085	Group-B	Unas.	Mimbres B/W Style III	Pottery	TAM		Cameron Creek	LA 000190	3.96					4.00 3	1		
OK087	Group-C2a	Mimbres-49A	Mimbres B/W Style III	Pottery	TAM		Cameron Creek	LA 000190	2.54					3.16 2			
OK088	Group-C1	Mimbres-21	Mimbres B/W Style I	Pottery	TAM		Cameron Creek	LA 000190	2.46							-	
OK089	Group-C2	Unas.	Mimbres B/W Style II	Pottery	TAM		Cameron Creek	LA 000190	3.62	_							
0K090	Group-A	Mimbres-01	Mimbres B/W Style III	Pottery	TAM		NAN	LA 002465	0.00								
OK091	Group-B1	Mimbres-04B	Mimbres B/W Style III	Pottery	TAM		NAN	LA 002465	0.00								
OK092	Group-C2a	Mimbres-42	Mimbres B/W Style II	Pottery	TAM		NAN	LA 002465	2.38							1	ц)
OK093	Group-A	Mimbres-01	Mimbres B/W Style III	Pottery	TAM		NAN	LA 002465	3.40				1		1		
OK094	Group-B2	Mimbres-11	Mimbres B/W Style III	Pottery	TAM		NAN	LA 002465	3.75							1	4
OK095	Group-A	Mimbres-01	Mimbres B/W Style III	Pottery	TAM		NAN	LA 002465	1.37	51.82 0	0.5043 2	23.11	3.92 9	9.33 2	2.56 75.94	94 2.03	9.17
OK097	Group-B2	Mimbres-02A		Pottery	TAM		NAN	LA 002465	2.61	61.44 0		46.33 7			3.67 85.44	14 8.13	37.45
0K098	Group-B2	Mimbres-02A*		Pottery	TAM		NAN	LA 002465	3.88					_			
OK099	Group-B2	Mimbres-08	Mimbres B/W Style III	Pottery	TAM	M	NAN	LA 002465	3.17					4.27 2	2.28 54.35	35 3.94	25.08
OK100	Group-B	Unas.		Pottery	TAM		NAN	LA 002465	2.36					5.45 3			
OK101	Group-B2	Mimbres-02A		Pottery	TAM		NAN	LA 002465	3.19	_							
OK102	Group-B1	Mimbres-04A	Mimbres B/W Style III	Pottery	TAM	N N	NAN	LA 002465	2.21	34.97 0	0.4250 3	38.11	5.89	3.83	2.63 84.00	00 6.50	28.31

>	49.09	92.68	59.63	90.73	118.37	86.98	84.90	53.90	52.57	36.78	29.34	42.76	62.95	39.98	15.38	39.93	63.21	24.91	32.37	23.72	28.42	34.82	20.83	48.28	42.74	23.89	63.63	54.61	52.44	87.87	63.09	109.63	20.19	51.70	69.34	34.47	61.23	26.54	52.45	70.67	51.28	43.71	71.14	55.37
I		4988.5	3107.7	_	3806.7 17	4074.9			4179.8	2148.2		2990.4	3259.7	3830.2	. 0.1601		1985.3	2021.0	0.0	1442.8	1882.5		1181.4	4071.5			3745.1					_					3776.2	1462.2	2230.9					4191.6
NA																			2.9																									
	8 18598.6	8 15609.2	1		4 14782.2	7 13546.4						3 9541.1	7 12022.0	2 15028.8	6 12201.1	5 9392.7	4 16278.5	2 14499.3	1 10352.	7 13282.0	5 11846.7	3 17671.0	1 13292.1	5 15216.0	8 10752.1	0 11309.2	5 12304.6	٠ ا		,	_							9 12703.5	9 13002.3	L	9 9310.8			7 12972.5
MM	1099.8	553.8	1086.2		548.4	1174.7	879.5	1066.3	620.7	185.5	338.8	187.3	1373.7	194.2	594.6	720.5	552.4	1333.2	876.1	286.7	342.5	200.3	310.1	389.5	276.8	333.0	232.5				_						949.5	134.9	453.9	478.4	195.9			349.7
\sim	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
DΥ	2.987	9.050	2.580	6.694	6.564	4.757	4.439	3.302	4.512	3.332	3.851	2.999	3.512	5.647	2.508	3.239	3.013	4.694	2.948	2.465	3.656	4.919	3.295	4.866	2.377	3.393	5.133	6.937	5.750	4.805	3.754	4.181	2.739	5.015	2.833	3.540	2.804	2.193	6.079	6.081	4.228	4.883	6.241	4.384
CA	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
BA	7.006	9.869	873.3	641.9	780.0	722.1	752.1	780.9	974.3	447.0	479.6	467.2	583.1	942.2	0.677	0.736	9.679	964.4	1058.2	469.0	226.8	1062.4	507.2	786.8	656.2	907.1	557.6	977.2	1224.6	922.5	1027.5	943.8	1036.6	645.2	925.3	360.5	513.0	393.6	530.9	660.2	407.6	774.7	568.4	784.2
AL	90161.2	82239.6	87328.7	94445.2	89817.6	98345.8	90726.8	88464.7	84749.7	75893.5	105693.2	77085.7	84340.9	84741.5	102874.3	100508.3	85620.2	102916.5	97461.0	104223.0	113302.2	86621.5	106311.0	87875.4	76536.5	100232.6	91661.1	88423.2	86444.9	83656.6	89712.8	91989.2	97693.6	85510.9	89521.0	99295.0	79584.6	86618.3	9.79697	85319.3	78659.5	79921.5	94243.0	82569.0
ZR	137.2	200.2	127.3	197.2	156.8	168.1	176.4	171.3	268.2	161.5	220.6	215.4	182.6	247.1	192.0	200.4	152.0	175.4	157.5	184.1	170.8	227.4	211.3	213.3	216.1	219.6	220.5	210.7	250.4	191.0	213.6	177.7	218.8	142.7	191.8	252.8	216.6	191.9	246.6	176.0	207.3	223.4	184.4	257.1
NZ	8.68	85.5	80.4	79.4	91.2	115.3	82.8	74.2	81.8	34.3	48.7	38.8	0.09	57.5	52.7	86.3	90.1	7.67	110.1	49.8	48.1	60.3	51.6	26.7	39.8	48.9	54.8	58.8	60.5	82.6	82.8	9.99	51.2	59.3	79.8	44.3	61.9	51.7	51.8	9.99	43.5	48.3	66.2	50.6
H	8.81	17.23	8.81	10.26	13.74	10.41	10.26	9.17	15.86	25.28	52.43	26.51	19.84	20.46	49.06	10.75	10.22	8.97	9.16	48.68	56.19	21.67	56.32	17.91	24.78	51.05	23.90	19.30	24.05	13.61	9.35	12.06	48.84	26.51	8.87	49.32	18.58	47.40	20.59	20.08	25.53	21.99	20.80	18.32
TB	0.60	1.49	0.61	1.01	1.08	0.82	0.79	99.0	0.00	0.35	0.52	0.46	0.65	0.88	0.45	99.0	69.0	0.52	0.56	0.55	0.58	1.19	0.62	1.04	0.41	0.49	0.83			0.84						0.56	0.52	0.33	1.01	08.0	0.38			0.69
TA	0.6631	1.5643	0.5954	0.9265	1.0164	0.7913	0.9678	0.7767	1.1131	1.5473	2.3192	1.6023	1.5998	1.3504	2.1746	0.6947	9698.0	0.5036	0.5402	2.1171	2.5568	1.5711	2.4499	1.3324	1.6044	2.5192	1.6444	1.2843	1.2453			0.7755	2.4959	1.3946	0.6358	2.2376	1.4993	2.2662	1.4209	1.3699	1.3725	1.3924	1.4632	1.5863
SR	362.7	261.6	398.7	342.6	377.7	487.9	472.7	376.8	318.0	125.5	134.8	118.9	265.3	272.9	137.7	252.6	488.2	390.4	323.4	119.1	126.5	270.4	103.5	204.3	150.7	107.3	247.3	369.7	307.4	343.9	397.6	449.8	145.7	204.6	662.9	106.4	196.5	92.9	409.8	346.6	87.9	244.3	299.4	243.5
SC	7.95	10.44	6.70	68.6	14.12	11.00	9.84	7.51	99.8	4.83	5.22	5.64	8.04	7.08	4.45	5.54	6.20	4.05	4.42	4.87	4.92		5.55	7.75	5.28	4.67	11.21	8.09	8.47	10.13	8.52	10.69			12.33			4.07	9.74	9.30	5.83	5.80	11.93	7.12
SB	1.0304	0.4541	2.0840	0.4407	0.3972	0.5323	0.7850	3.2369	1.1463	0.3884	0.8270	0.4111	0.6954	0.4458	0.6618	3.2876	1.6709	1.8935	2.5861	0.7897	0.9248	0.5146	0.8478	0.3203	0.5563	0.8980	0.5403	0.2999	0.0000	0.5794	2.2471	0.6863	0.6709	0.4425	0.2612	0.9090	0.7608	0.6376	0.3966	0.6052	0.4477	0.3179	0.5393	0.3660
RB	115.06	139.90	121.23	104.08	128.82	132.52	106.85	121.47	137.10	171.96	257.31	180.18	189.17	145.56	203.24	163.38	126.74	118.38	135.50	233.56	234.26	159.23	274.81	129.14	180.11	237.96	156.47	132.36	123.82	136.43	127.85	120.75	243.51	173.93	76.54	224.50	199.26	197.84	132.03	156.11	174.08	148.73	140.94	136.31
Z	0.0	0.0		0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0									0.0	0.0	0.0	0.0	0.0	0.0			0.0
生	5.76	9.45	2.97	7.11	5.82	09.9	6.93	6.03	8.51	6.07	6.62	6.63	6.53	8.01	5.17	66'9	5.71	5.41	5.26	2.90	5.79	6.97	7.05	6.55	7.27	6.03	7.80	6.48	8.29	7.30	6.81	2.97	7.07	5.30	6.24	7.39	6.64	5.51	16.9	68'9	6.25	6.15	6.52	68.6
FE	26563.3	40162.4			37711.6		35969.4	26369.5	27482.7	16535.8	15627.3	18333.9	25885.2	21708.8	12290.6	23204.1	25263.6	18008.2	19383.8	14953.2	13755.8	23314.8	16652.7	25360.3	18198.8	13810.8	24839.5									13804.4	27246.8	11291.7	24665.8	26984.1	20212.5	17687.1		23093.2
EU	1.1997	1.3701	1.1886	1.6083	1.8439	1.6488	1.4437	1.1814	1.4882	0.6262	0.7356	0.6950	1.0178	1.4278	0.5738	1.2338	1.2326	1.2639	1.3043	0.7402	0.6962	1.6403	0.7987	1.4226	0.7369	0.6176	1.2026	1.6473	1.6395	1.4622	1.3110	1.5159	0.6114	1.2503	1.4654	16.05 0.6216	0.8912	0.4965	1.3969	1.1901	0.5493	1.2038	1.4568	1.1667
CS	18.96	2.90		12.05	5.51			17.58	27.03	6.07	19.32 0.7356	09.9	8.22	2.07	21.70	_	17.77	18.57	. 59.92	19.68 0.7402	19.48 0.6962	5.35	20.40	4.12	6.22	14.02	22.96	4.81							5.04	16.05	1.77	18.71	. 16.60	. 25.93	7.47	4.40	26.29	4.79
ANID	OK055	OK056	OK057	OK058	OK059	OK060	OK061	OK062	OK063	OK064	OK065	OK067	OK068	OK069	OK070	OK071	OK072	OK073	OK074	OK075	OK076	OK077	OK078	OK079	OK080	OK082	OK083	OK084	OK085	OK087	OK088	OK089	OK090	OK091	OK092	OK093	OK094	OK095	OK097	OK098	OK099	OK100	OK101	OK102

ANID	macro_grp	Chem2012	CERAMIC TYPE	MATERIAL	SOURCE	STATE	SITE_NAME	SITE_NO	AS	ΓA	Π	ND	SM	U YB	B CE	00	CR
OK104	Group-C2	Unas.	Mimbres B/W Style II	Pottery	TAM	NM	NAN	LA 002465	2.91	32.91 0	0.3758 3	32.32 5	5.66 1.	1.78 2.57		10.83	37.31
OK105	Group-C1	Mimbres-21	Mimbres B/W Style I	Pottery	TAM	MN	NAN	LA 002465	2.19	40.59 0	0.3342 4	40.25 6	6.32	1.30 2.7	2 77.68	11.32	70.52
OK106	Group-C2	Unas.	Mimbres B/W Style III	Pottery	TAM	NM	NAN	LA 002465	0.98	34.84 0	0.3265 3	35.77 5	5.25 1.	1.64 2.43	3 56.11	7.72	29.55
OK107	Group-B1	Mimbres-04A	Mimbres B/W Style III	Pottery	TAM	MN	NAN	LA 002465	3.53	34.36 0	0.3818 3	31.90 3	3.96 4.	4.03 2.21	1 62.62	6.04	20.42
OK108	Group-B	Unas.	Mimbres B/W Style III	Pottery	TAM	MN	NAN	LA 002465	2.42	34.26 0	0.4021 2	24.55 4	4.48 3.	3.49 2.64			26.80
OK109	Group-C2	Unas.	Mimbres B/W Style III	Pottery	TAM	NM	NAN	LA 002465	6.50	36.06 0	_		5.55 1.	1.55 2.08	8 54.34	12.63	50.58
OK110	Group-B	Unas.	Mimbres B/W Style II/III	Pottery	TAM	NM	NAN	LA 002465	8.51	40.13 0	0.3941 3	30.17 5	5.36 4	4.21 2.55	5 68.73	13.36	39.78
OK111	Group-C2b	Mimbres-41	Mimbres B/W Style III	Pottery	TAM	NM	NAN	LA 002465	2.75	34.77 0	0.3231 3	30.16 5	5.30 2	2.22 2.41	1 66.79	11.65	27.57
OK112	Group-C2a		Mimbres B/W Style III	Pottery	TAM	NM	NAN	LA 002465	1.89				6.38 3.				34.27
OK113	Group-B2	Mimbres-02A	Mimbres B/W Style III	Pottery	TAM	MN	NAN	LA 002465	2.01	49.10 0	0.4831 3		6.08 4.	4.77 3.34	4 74.85	5.29	33.24
OK114	Group-B2	Mimbres-02A	Mimbres B/W Style III	Pottery	TAM	MN	NAN	LA 002465	1.86	37.67 0	0.4400	32.40 5	5.86 3.	3.80 2.81	1 67.87	7.62	35.57
OK115	Group-B1	Mimbres-04C	Mimbres B/W Style II/III	Pottery	TAM	MN	NAN	LA 002465	1.59	33.80 0		27.42 4	4.47 2.	2.74 2.59	9 56.25	5.43	32.32
OK116	Group-B2	Mimbres-11	Mimbres B/W Style III	Pottery	TAM	MN	NAN	LA 002465	3.57	32.95 0	0.3919 2			2.39 2.58	8 68.64	17.07	45.86
OK117	Group-B2	Mimbres-02A	Mimbres B/W Style III	Pottery	TAM	MN	NAN	LA 002465	1.61	40.17 0	0.4548 3	32.96 5	5.82 3.0	3.05 2.84	4 73.18	8.61	36.65
OK118	Group-B2	Mimbres-02A	Mimbres B/W Style III	Pottery	TAM	NM	NAN	LA 002465	1.71				5.42 3	3.29 3.51	1 76.53	6.80	33.38
OK119	Group-B	Unas.	Mimbres B/W Style III	Pottery	TAM	NM	NAN	LA 002465	1.92			24.52 3		2.18 2.34			33.31
OK120	Group-B	Unas.	Mimbres B/W Style III	Pottery	TAM	NM	NAN	LA 002465	2.25		0.4848 3		5.96 5.	5.69 3.23		8.88	25.18
OK121	Group-B2	Mimbres-11	Mimbres B/W Style II/III	Pottery	TAM	NM	NAN	LA 002465	3.17	32.51 0	0.4032 2	28.33 4	4.41 3.	3.15 2.68	8 71.56	21.01	48.77
OK123	Group-A	Mimbres-01	Mimbres B/W Style III	Pottery	TAM	MN	Galaz	LA 000635	1.36	68.84 0	0.5342 4	44.10 5	5.42 7.	7.05 3.12	2 102.08	2.52	5.84
OK124	Group-C2a	Mimbres-49A	Mimbres B/W Style I	Pottery	TAM	NM	Galaz	LA 000635	2.18				,	1.81 2.82		15.03	50.45
OK125	Group-B1	Mimbres-04C	Mimbres B/W Style I	Pottery	TAM	¥	Galaz	LA 000635	1.42	43.57 0	0.4835 5	59.15 6	6.81 3.	3.46 3.76	6 89.61	6.65	38.92
OK126	Group-B	Unas.	Mimbres B/W Style I	Pottery	TAM	NN	Galaz	LA 000635	2.91	28.94 0	0.3788 2	28.64 4	4.31 3.	3.14 2.97	7 50.86	4.41	36.90
OK127	Group-B	Unas.	Mimbres B/W Style II	Pottery	TAM	NN	Galaz	LA 000635	6.24	38.85 0	0.7422 5	51.41 7		3.91 5.21			34.77
OK128	Group-B1	Mimbres-04B	Mimbres B/W Style II	Pottery	TAM	NM	Galaz	LA 000635	2.13					41 2.62			29.30
OK129	Group-B1	Mimbres-04A	Mimbres B/W Style II/III	Pottery	TAM	MM	Galaz	LA 000635	6.02	53.93 0	0.5581 6		8.80 3	3.24 4.44	1	69.9	24.59
OK130	Group-B2	Mimbres-11	Mimbres B/W Style II	Pottery	TAM	NM	Galaz	LA 000635	2.44					3.98 2.79		_	39.43
OK131	Group-B1	Mimbres-04A	Mimbres B/W Style III	Pottery	TAM	MM	Galaz	LA 000635	2.04						1		25.69
OK132	Group-B1		Mimbres B/W Style III	Pottery	TAM	NM	Galaz	LA 000635	2.08	~							27.90
OK133	Group-C2a		Mimbres B/W Style III	Pottery	TAM	M	Galaz	LA 000635	2.57		0.4696 5		7.35 3.			6.92	46.35
OK134	Group-B1	Mimbres-04B	Mimbres B/W Style III	Pottery	TAM	NM	Galaz	LA 000635	2.79								23.84
OK135	Group-B1	Mimbres-04A	Mimbres B/W Style III	Pottery	TAM	M	Galaz	LA 000635	2.15								27.39
OK136	Group-B2	Mimbres-11	Mimbres B/W Style II/III	Pottery	TAM	M	Galaz	LA 000635	2.12								36.95
OK137	Group-B1	Mimbres-04A	Mimbres B/W Style II	Pottery	TAM	MN	Galaz	LA 000635	1.50	_							25.69
OK138	Group-B	Unas.	Mimbres B/W Style II	Pottery	TAM	M	Galaz	LA 000635	1.72						_		34.02
OK139	Group-B1	Mimbres-04C	Mimbres B/W Style III	Pottery	TAM	NM	Galaz	LA 000635	3.30					4.54 2.82			37.56
OK140	Group-B1	Mimbres-04A	Mimbres B/W Style III	Pottery	TAM	NM	Galaz	LA 000635	1.36		0.5554 4		8.29 6.1	6.06 4.13	1		24.69
OK141	Group-B1	Mimbres-04C	Mimbres B/W Style II/III	Pottery	TAM	NM	Galaz	LA 000635	1.26	42.66 0	0.4679 4	40.34 6	6.64 5.			8.71	30.80
OK142	Group-B	Unas.	Mimbres B/W Style III	Pottery	TAM	NM	Galaz	LA 000635	2.13		0.4276 4	40.20 6	6.41 5		8 95.47	5.26	26.99
OK144	Group-B2	Mimbres-08	Mimbres B/W Style III	Pottery	TAM	NM	Galaz	LA 000635	3.54	38.59 0	0.4025 4	41.82 4	4.07 5.3	5.30 2.39		4.16	26.22
OK145	Group-B	Unas.	Mimbres B/W Style II	Pottery	TAM	NM	Galaz	LA 000635	1.85	45.92 0		45.92 7	7.07	4.65 3.19	9 92.07	7.71	45.89
OK146	Group-B	Unas.	Mimbres B/W Style I	Pottery	TAM	M	Galaz	LA 000635	1.24		0.3787 3			1.24 2.78		8.22	32.12
OK147	Group-B1	Mimbres-04C	Mimbres B/W Style II	Pottery	TAM	NM	Galaz	LA 000635	1.41								40.32
OK148	Group-C2a	Mimbres-49A	Mimbres B/W Style I	Pottery	TAM	M	Galaz	LA 000635	4.89							_	54.01
OK149	Group-B1	Mimbres-04A	Mimbres B/W Style III	Pottery	TAM	NM	Galaz	LA 000635	1.28	48.86 0	0.5215 4	40.76 7	7.08 2.	2.59 3.40	0 90.03	7.94	21.53

>	70.02	72.96	76.78	39.75	32.50	71.92	75.27	89.48	63.39	55.28	66.84	67.63	60.47	63.10	56.14	41.74	48.22	74.30	23.53	69.40	65.76	64.88	66.38	48.49	53.54	70.05	56.57	51.17	110.74	50.59	41.55	49.03	57.82	00.41	64.02	50.68	52.63	40.66	48.69	102.48	58.07	59.86	108.43	54.54
F	4073.3		3547.2		2258.4	3648.3	3083.8	4425.4	3712.9	3203.4	2660.2	3336.6	3549.9								2992.7		4101.7	2772.9					1															3326.2
NA					6						/		6								9				_	_															4	e 0		
	5 15552.4			3 14632.0	11690.	20131.6	5 12150.4	3 16510.6	5 13746.6	3 13511.5	2 12552.	13635.1	3 9371.			3 11088.6	-	3 8951.1	1 21977.4	5 16450.0	13157.		3 10258.9	3 12314.7				'				`						_			`	~ I		3 16156.3
MN	519.5	1			528.4	0.069	710.6	558.8	726.6	233.8	345.2	348.0	2403.8					2010.0		435.5	397.9		246.8	159.8	l																			654.8
\rightarrow	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
DΥ	4.173	4.586	2.932	3.236	2.889	3.528	3.911	3.034	4.257	4.307	3.724	5.015	2.904	4.407	4.469	4.559	5.250	5.405	3.162	5.708	3.888	2.611	8.650	2.817	7.642	4.145	6.847	5.356	5.314	4.472	3.318	4.220	3.928	7.535	3.868	6.989	5.870	4.251	4.113	6.127	4.044	4.391	4.382	6.539
CA	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
BA	832.4	929.1	842.8	776.5	421.0	1003.2	857.7	911.9	778.2	644.8	591.8	1.999	654.0	9.999	443.2	389.9	623.5	700.4	449.2	842.5	626.5	733.7	430.2	583.7	1013.1	539.6	904.4	857.5	927.6	9.619	8.906	2.009	844.3	784.7	753.6	983.0	942.2	965.5	434.4	638.3	7.086	759.7	800.9	1040.3
AL	94764.4	86682.6	83136.6	88699.3	73550.6	89603.3	80392.5	78443.2	81874.7	83561.2	82770.3	82831.7	86946.9	89644.9	82300.8	82062.3	84376.8	84469.1	100944.6	92614.6	93198.3	99542.7	96372.7	87833.6	86859.5	84533.1	87988.2	76847.9	84446.2	93081.2	81005.9	79206.2	84647.4	88861.4	87137.6	89972.6	89637.2	79125.5	79947.6	102966.4	86079.4	96197.4	78393.2	87942.9
ZR	275.1	164.3	181.3	237.6	123.8	181.2	189.5	207.4	162.4	191.0	216.0	184.8	181.1	236.6	218.5	163.8	156.0	205.2	124.7	191.9	158.7	163.9	215.6	176.5	163.2	204.6	192.6	236.4	244.3	198.6	217.5	151.9	223.8	278.8	230.4	222.5	165.2	227.5			189.4	228.7	202.9	165.6
NZ	74.9				49.1	63.4	51.0	52.5	68.2	51.2	53.5	63.3	57.9			61.8		55.7	40.1	71.7	72.2		83.0	54.0					89.2				_				_					87.2		63.3
H	9.76	9.85	10.01	22.37	23.12	8.53	17.52	6.87	12.59	19.56	17.99	15.94	17.47	18.51	21.11	21.17	22.47	18.77	42.49	10.70	17.21	18.40	19.50	28.21	18.70	18.63	21.43	20.22	12.87	23.85	18.96	20.17	17.37	21.93	16.33	18.72	18.76	19.77	27.55	16.27	13.72	18.30	11.22	17.50
TB			0.55	0.46	0.49	0.55	0.57	0.56	99.0	0.70	0.73	0.70	0.59	0.82		0.53		0.64		0.89	0.93	0.57	1.15	0.72		0.72				0.81	0.79				_						_	_	_	0.98
TA	0.8792	0.8580	0.8982	1.5070	1.5409	0.7852	1.2132	1.0327	0.9973	1.4628	1.2696	1.2840	1.3829	1.2866	1.4468	1.4400	1.5055	1.5316	2.1232	0.9631	1.2134	1.4477	1.7038	1.5359	1.3528	1.6135	1.2724		0.8727	1.3800	1.4925	1.5812	1.3298	1.5315	1.3357	1.2489	1.4990			1.8420	1.0051	1.3871	0.9872	1.3146
SR	413.0	343.9	502.8	253.2	379.1	524.4	160.0	515.9	425.6	282.0	280.9	293.5	195.1	291.9	173.0	255.7	171.9	210.6	144.8	476.9	262.6	252.7	119.4	145.7	280.9	205.5	302.3	214.6	249.3	132.0	217.7	235.8	213.7	294.0	244.5	237.2	264.1	283.0	123.0	178.7	296.1	274.3	232.2	262.5
SC	10.71	8.05	8.10	7.04	6.34	10.76	99.8	7.50	7.65	9.25	10.31	7.74	8.71	10.72	8.18	7.38	6.64	8.71	4.21	11.10	10.64	8.95	10.62	7.76	9.23	8.04	8.75	6.67	11.02	7.85	92.9	7.16	7.03	10.04	8.50	8.58	9.17	7.68	90.9	13.70	7.19	79.67	11.35	6.97
SB	0.4475	1.3388	0.2722	0.5314	0.3549	1.4761	1.4501	0.2098	0.5716	0.3529	0.3576	0.2845	0.8273	0.4244	0.4479	0.5076	0.4908	0.6550	0.4553	0.4372	0.5712	0.5105	1.1250	0.5627	0.3597	0.5484	0.2772	0.3547	0.5809	0.3106	0.3825	0.5437	0.4157	0.4513	0.3732	0.3789	0.3878	0.4321	0.5129	1.2620	0.3233	0.4283	0.9312	0.2575
RB	107.74	122.08	98.77	162.88	158.17	109.68	140.89	93.52	123.50	145.54	143.40	126.32	195.37	147.44	172.82	178.70	202.61	213.32	154.12	89.41	99.64	122.57	174.13	183.31	102.91	169.93	137.56	156.81	114.18	147.90	154.51	160.97	138.15	130.07	136.21	119.94	141.66	141.66	185.85	83.10	113.40	141.67	129.74	123.13
Z	0.0		0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0			0.0		0.0	0.0	0.0	0.0	0.0	0.0	0.0					0.0											0.0				0.0
生	8.34	6.51	6.20	7.99	6.03	5.98	5.75	6.84	6.31	8.20	7.33	6.95	6.40		8.09	6.15	2.06	7.43		7.12	6.63	6.51	9.21	6.41	6.07	6.78	7.81	8.23	8.11	5.49	8.89	7.13	7.82	/0./	8.09	6.91	6.37	7.56		7.98	7.01	7.70	7.42	6.35
FE				23898.6	18768.7	35853.5	32004.1	32647.4	29091.9	22386.9	25804.7	26434.7	26167.3			24057.0		26573.9	l I	33261.3	28137.4	29087.0	29629.5	23801.7					38276.7											24211.5			36552.1	1.3984 25200.0
EU	1.4038	1.2258	1.2421	0.8535	0.7765	1.3172	1.1051	1.3033	1.3665	1.0208	1.1697	1.0147	0.9757	1.2459	0.9974	0.7771	1.0467	0.9910	0.7431	1.7155	1.3946	0.8623	0.8307	1.0026	1.6477	1.0176	1.8278	1.2734	1.6338	1.0668	1.2206	1.0023	1.1683	2.2812	1.1942	1.6317	1.4130	1.3746	0.6851	1.4115	1.4147	1.4451	1.2568	1.3984
CS			3.84	4.70	13.08	7.02	5.36	3.69	4.80	14.77	14.38		7.95	15.93		14.71	10.79		14.53	4.11	5.47		9.92	89.6		7.40	5.44											5.30						4.63
ANID	OK104	OK105	OK106	OK107	OK108	OK109	OK110	OK111	OK112	OK113	OK114	OK115	OK116	OK117	OK118	OK119	OK120	OK121	OK123	OK124	OK125	OK126	OK127	OK128	OK129	OK130	OK131	OK132	OK133	OK134	OK135	OK136	OK137	UK 138	OK139	OK140	OK141	OK142	OK144	OK145	OK146	OK147	OK148	OK149

ANID	macro_grp	macro_grp Chem2012	CERAMIC TYPE	MATERIAL	SOURCE	STATE	SITE_NAME	SITE_NO	AS	ΓA	ΓΩ	ND	SM	Λ	YB CE	00	CR
OK150	Group-B	Unas.	Mimbres B/W Style II/III	Pottery	TAM	MN	Galaz	LA 000635	0.00	34.40 0.	0.3683 2	25.41 4	4.54 2.	2.08 1.80	30 65.16		36.11
OK151	Group-B1	Mimbres-04A	Mimbres B/W Style III	Pottery	TAM	MN	Galaz	LA 000635	2.70	45.74 0.	0.4316	37.68 5		2.47 2.88	38 81.13	9 6.59	22.19
OK152	Group-B1	Mimbres-04B	Mimbres B/W Style III	Pottery	TAM	NM	Galaz	LA 000635	1.74	62.76 0.	0.4846	54.46 8	8.59 3.	3.02 3.78	78 116.31	6.74	30.60
OT033	Group-B	Unas.	Unspec. Textured Rim	Pottery	MURR	MN	Old Town	LA 001113	4.66	60.51 0.	0.5355 4	40.58 8	8.29 3.	3.78 4.07	104.77	8.10	33.27
OT042	Group-D	El Paso-2	El Paso Polychrome	Pottery	MURR	MN	Old Town	LA 001113	99.9							l	61.00
OT043	Group-D	El Paso Core	El Paso Polychrome	Pottery	MURR	MM	Old Town	LA 001113	5.61						_		25.66
OT044	Group-D	El Paso Core	El Paso Polychrome	Pottery	MURR	NM	Old Town	LA 001113	2.00			42.87 8		4.01 3.69		3 5.60	28.53
OT045	Group-D	El Paso Core	El Paso Polychrome	Pottery		NM	Old Town	LA 001113	5.70						_		26.13
OT046	Clay		Clay	Clay, Adobe		MM	Old Town	LA 001113	2.53				_		2.56 59.80		34.77
OT047	Clay		Clay	Clay	MURR	NM	Old Town	LA 001113	4.92	59.05 0.	0.6025			3.48 4.71			41.22
OT048	Group-A	Unas.	Unspec. Plain Smudged	Pottery	MURR	MN	Old Town	LA 001113	3.06	69.26 0.	0.6603	59.19 13	13.83 3.	3.61 5.71	11 142.58	13.51	35.57
OT057	Group-D	El Paso-2	El Paso Polychrome	Pottery	MURR	MN	Old Town	LA 001113	8.28	26.69 0.	0.5368	56.25 10	10.26 3.	3.14 4.45	107.67	12.70	71.14
OT058	Group-D	El Paso Core		Pottery	MURR	MN	Old Town	LA 001113	5.44	55.73 0.	0.5011	39.91 8		5.24 3.38	38 118.72	00.9	23.90
OT059	Group-D	El Paso-2		Pottery	MURR	NN	Old Town	LA 001113	5.89		_		8.89 2.	2.64 4.27	27 93.46	_	70.10
O2000	Group-D	El Paso Core		Pottery	MURR	NM	Old Town	LA 001113	4.91	69.27 0.		53.33 11	11.56 4.	4.39 4.39	39 131.08	3 7.57	27.41
OT061	Group-D	El Paso-2		Pottery	MURR	NM	Old Town	LA 001113	7.02	57.22 0.		48.17 10		4.54 5.03	121.56	1	74.40
OT062	Group-D	El Paso Core		Pottery	MURR		Perrault	LA 018891	4.74			72.91 12	12.16 4.	4.31 4.62		7.89	29.18
OT063	Group-D	El Paso Core	El Paso Polychrome	Pottery	MURR	MN	Perrault	LA 018891	5.03	73.13 0.	0.6189	61.00 11	11.47 3.	3.69 4.81	132.78	8 6.11	25.05
OT070	Group-D	El Paso Core	El Paso Polychrome	Pottery	MURR	MN	LA 018342	LA 018342	4.22	71.68 0.	0.5738 7	71.07	11.01 5.	5.30 4.06	138.18	3 7.83	23.51
0T071	Group-D	El Paso Core	El Paso Polychrome	Pottery	MURR	MN	LA 018342	LA 018342	6.39	48.26 0.	0.4039	33.52		3.39 2.82	32 89.47	88.9	26.33
OT077	Group-D	El Paso Core	El Paso Polychrome	Pottery	MURR	MN	LA 018343	LA 018343	5.73	78.08 0.	0.6435 6	68.18 12	12.89 3.	3.61 5.14	158.20		25.01
OT100	Group-A	Mimbres-01	Mimbres B/W Style III	Pottery	MURR	TX	Hot Wells	41EP00005	3.42	52.68 0.	0.4982	41.97	4.04 10.	0.26 2.47	99.88 21	1.54	8.26
OT101	Group-B	Unas.	Mimbres B/W Style III	Pottery	MURR	MN	LA 018342	LA 018342	2.67	47.46 0.	0.3974	29.57 6	6.30 2.	2.82 2.74	74 91.13		19.45
OT102	Group-B2	Mimbres-08	=	Pottery	MURR		LA 018342	LA 018342	3.65		0.4174	35.56	3.82 5.	5.98 2.41	11 70.61		24.03
OT105	Group-A	Unas.	Playas Corrugated	Pottery	MURR	NN	Old Town	LA 001113	4.06	83.55 0.	0.8522 7	73.43 17.	17.73 4.	4.49 6.95	161.13	12.52	33.79
OT115	Group-A	Mimbres-01	Mimbres B/W Style Indeter. Pottery	Pottery	MURR		Franzoy	LA 002886	2.75				l				4.31
OT116	Group-D	El Paso Core	El Paso Polychrome (Early) Pottery	Pottery	MURR	NM	Franzoy	LA 002886	8.73			37.82 8			1		23.88
OT117	Group-B2	Mimbres-02A	Mimbres B/W Style Indeter. Pottery	Pottery	MURR		Franzoy	LA 002886	3.97							_	31.66
OT119	Group-B	Unas.	Mimbres B/W Style Indeter. Pottery	Pottery	MURR	NN	Dam Site	LA 003635	2.97	43.28 0.	0.5080	27.48 6.		5.70 3.7	3.13 72.43	3 7.74	31.12
OT120	Group-B2	Mimbres-02A*	Mimbres B/W Style Indeter. Pottery	Pottery	MURR	MN	Dam Site	LA 003635	2.73	41.87 0.	0.5270	25.19 5.		5.17 3.38	88 69.83	94.46	26.90
OT121	Group-D	El Paso Core	El Paso Polychrome (Early) Pottery	Pottery	MURR	MN	Dam Site	LA 003635	5.49	_		_					23.45
OT122	Group-D	El Paso Core	El Paso R/Br	Pottery	MURR	M	Dam Site	LA 003635	6.67								29.04
OT128	Clay		Clay	Clay	MURR	MN	Old Town	LA 001113 (C	3.32								48.41
OT129	Clay		Clay	Clay	MURR	M	Walsh Ranch	Raw Clay Loc	5.69	35.74 0.		27.73 5	5.46 3.	3.09 2.52			44.22
OT130	Clay		Clay	Clay	MURR	NM	Old Town	LA 001113 (B	3.88	41.69 0.		27.08 5.	5.65 3.	3.92 2.48	18 78.51	8.78	45.20
OT131B	Clay		Clay	Clay	MURR	NM	Old Town	LA 001113 (C	8.31			44.15 9		3.55 3.96		9.48	45.96
OT131C	Clay		Clay	Clay	MURR	NM	Old Town	LA 001113 (C	11.47				12.89 3.	3.14 4.73	1	14.76	63.02
OT131T	Clay		Clay	Clay	MURR	NM	Old Town	LA 001113 (C	1.08	32.07 0.			6.15 3.	3.58 3.04)4 57.84	1 2.02	15.20
OT132	Group-B	Unas.		Pottery	MURR	NM	Las Animas Village	LA 003949	3.95		0.5063		6.06 5.			6.79	31.58
OT133	Group-A	Mimbres-01		Pottery	MURR	MM	Las Animas Village	LA 003949	3.69				_			1 2.18	6.42
OT134	Group-B	Unas.		Pottery	MURR	MM	Las Animas Village	LA 003949	0.00							8.62	44.42
OT137	Group-A	Mimbres-01	_	Pottery	MURR	NM	Lizard Terrace	LA 037726	1.94								12.01
OT139	G-dno ₂ D	El Paso Core	El Paso Polychrome	Pottery	MURR	NM	Lizard Terrace	LA 037726	7.64					3.98 2.43			31.38
OT140	Group-C2	Unas.	Mimbres- Like Black-on-whi Pott	Pottery	MURR	NM	Lizard Terrace	LA 037726	5.75	38.53 0.	0.3130 4	40.84 6	6.05 1.	1.17 2.32	32 75.80	15.12	48.14

>	71.53	55.32	53.37	72.00	98.50	127.10	85.40	98.09	62.80	77.30	86.90	118.30	99.80	116.30	115.40	113.50	92.00	92.40	105.10	114.20	103.10	25.30	51.50	45.80	79.10	24.40	90.30	58.10	49.20	47.90	105.40	88.40	25.50	05.67	07.20	11.4 80	00.4.00	23.00	51.30	21.80	54.20	21.90	07.70
F	4012.7	3457.1	2268.6		4527.8	6855.0 1.		4012.5	2998.3	3645.9	5436.5	4480.5	2688.8	4856.6 1		1		6099.1	6112.5	5343.8	5364.9 1	1452.2	2763.8		_						_			0.2042									1 2330.4
NA	15922.7 4	15669.5 3	11896.6 2		11363.4 4	18943.9 6	17929.1 5	16868.0 4	13769.5 2	11175.8 3	10663.3 5	10493.7 4	18712.1 5	12403.2 4					18386.6 6	15985.0 5	16696.4 5	12762.0	14033.9 2												0 1						.		14093.7
MN	254.3 159	304.6 156	713.4 118		410.0 113	533.9 189	479.6 179	427.0 168	519.9 137	455.2 111	532.3 106	440.5 104	432.9 187	444.7 124	`				560.2 183	440.7 159	482.0 166	133.2 127	442.9 140			`				`	, ,			210.9 1/3		_	-	Ι,				1 1	442.3 140
¥		0.0	0.0													_	_	4												_													
DY		22			52 27910.5	35 29454.5	99 31472.0	59 32661.3	12 40453.1	78 29694.9	18 28355.0	38 29687.2	34710.6	22 28826.4		_	_		37 30668.8	27040.4	53 29537.1	57 38532.9	78 30514.2											7.87777 CV					- 1			75 35326.4	
CA	0.0 3.272	0.0 4.022	0.0 7.786			.6 4.385	.0 5.499	.5 4.759	.5 2.912		.7 10.218	.3 6.588	.8 5.472	.3 5.822	.1 7.041	·		.0 7.051	.5 6.687	.0 4.609		.5 2.657	.0 4.078		_									700.2 0.									.3 3.423
S	0	0	0	14800.0	16081.8	16109.6		10915.5	47871.5	15688.5	11966.7	11924.3	10754.8	13809.3	16890.1	10500.0	18542.1	11640.0	16330.5	15148.0	15843.1	7160.5	14930.0		_	6716.8	13816.0	13102.5	125/0.9	16174.5	13180.1	10012	18843.9	14412.0	0770	13/05 6	0770	8663.5	88/5.1	8429.0	11058.0	8508.0	0.7701
BA	784.5	892.1	782.2	813.2	892.1	810.2	798.3	871.3	1091.5	598.8	538.5	854.4	1013.3	838.1	3078.0			839.0			1038.3	220.6	918.0			454.1	787.9			588.1	1162.2	1330.2	0/1/0	7.44.2				6/6.0	7,52,7	387.0	7.16.0	306.2	903.0
AL	88803.4	84650.9	92182.0	92193.5	85182.2	96031.4	94942.2	82588.1	75996.3	83749.2	90323.8	91438.3	92646.1	87716.2	89951.8	99133.7	91755.9	93555.5	91717.9	92253.8	93080.7	105066.4	82740.6	83945.4	87677.6	103990.1	91439.4	80176.9	83845.4	76090.6	97159.8	91432.1	800/2.6	4.04401	7 7 003.4	89108.1 111040.8	0.74711	6U3/8.8	8/485.1	9/321.0	90824.3	95/18.1	90463.1
ZR	121.2	254.6	190.9	191.3	265.1	231.3	404.4	315.2	196.2	229.4	335.1	279.3	409.9	285.8	503.0			483.8	369.4	220.7	449.5	149.0	241.1	164.8		`	291.6			151.7	364.6	1.007	6,877	237.8		136.9		730.7	7.171	1/2.7	188.4	180.5	0.122
NZ	82.2	82.2	62.0	63.5	74.7	63.0	55.3	47.4	101.0	65.9	138.5	97.8	53.5	78.9	6.69	94.6	70.6	62.7	70.3	52.8	8.09	37.7	1.99	39.9	119.4	39.6	68.3				82.0	7.13	69.4	C.00	0 70 0.5	136.6	17.4	10.4	59.9	33.3	64.1	49.1	7.10
H	14.73	20.79	24.10		22.82	27.13	19.10	23.56	12.76	20.59	30.22	21.00	28.20	19.07		-			20.17	24.54		50.33	14.84									_		11.11								45.40	
A TB	0.58	0.84	1.24	0.85	1.06	0.55	0.84	1 0.92	0.45	1.18	1.80	1.11	0.75	0.98	1.12	1.13		1.55	0.81	0.54	1.98	0.32	1 0.97		9 2.99						, ,			0.40		5 1.38							0.04
TA	1.2005	1.5445	1.5684	1.5317	2.2977	2.9410	2.8275	2.7054	1.2525	1.2904	1.2312	2.0695	3.2116	1.8937	3.0777	2.2454	2.5720	2.8695	3.4237	2.9255	3.0989	2.3055	1.1181	1.5466	1.2979	2.4797	3.0968	1.5038	1.5/30	1.6285	3.1312	3.2960	1.1624	1.2437									41/1/2
SR	267.0	250.7	180.1	260.7	332.1	500.1	390.3	401.7	883.1	124.0	0.0	244.0	421.0	410.8	862.7	397.1	357.4	278.2	446.8	368.3	345.1	92.9	303.4	130.8	82.0	112.3	547.4	357.3	729.4	328.2	402.0	333.4	207.7	401.7	107.0	176.5	1,0,1	103.0	193.9	125.8	3/3.1	1/5.5	7.400
SC	7.30	7.03	8.65			10.03	9.14	8.29	5.17	10.58	18.77	14.56	8.30	13.78				10.79	9.28	6.07		4.58	7.11		_				92./		l				Ι.	11.04 70.11	-					4.72	
SB	0.4611	0.4489	0.4133	0.4647	0.7212	0.5691	0.4808	0.5196	0.4130	0.7472	0.9355	0.7606	0.4017	0.7253	0.4841	0.7542	0.5072	0.4877	0.4329	0.6453	0.4088	0.7397	1.0765	0.5415	0.8286	0.5095	0.5380	0.4399	0./921	0.6101	0.3665	0.6128	0.4592	0.4323	0.3073	1 2274	0.0507	0.2506	0.4301	0.4/82	0.4615	0.48/6	0.0000
RB	130.31	165.31	157.08	155.60	142.60	94.50	118.50	133.40	107.80	203.10	258.60	142.60	125.10	130.30	94.90	120.60	119.70	115.00	98.00	102.50	100.00	215.80	126.90	198.60	221.10	236.60	101.20	141.10	200.90	181.00	125.00	83.90	120.120	115 40	00.011	194.70	101 40	181.40	07.691	200.50	181.60	204.40	104.70
Z	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	63.0	0.0	0.0	0.0	0.0	0.0	0.0	32.0	0.0	0.0	0.0	40.1	0.0	62.1						0.0	73.7		0.0								0.0	0.0
生	6.22	8.81	6.53		10.75	8.50	14.95	12.71	8.12	9.20	١,	10.68	14.41	10.58				17.79	14.42	9.10	_	5.99	69.6		16.18		`		2.87			٧.		7.87				77.6	9.00	6.39	7.05	1.21	
FE	22956.6	28126.7	29903.9	34696.9	42162.5	50812.2	39511.5	34660.9	21829.1	35213.3	51793.6	47060.7	40942.4	43866.1	52622.2	47060.0	43788.9	43024.2	43822.6	1.3703 47058.7	44460.6	12114.5	24589.6	21620.5	52480.0	11423.0	44304.7	22161.8	21284.4	19281.2	44422.9	44641.1	8.64462	7.10182	1.1333 27.170.3	5/228./ 55715.8	10057	1.26521	23/04.5	11424.4	23644.9	13822.7	1.1032 43233.7
EU	1.1039	1.1708	1.6780		1.5054	1.4634			0.9648	1.5332	1.7645	1.8147	1.6966	1.5869			_		2.3134	.3703	2.7183	0.4806	1.2570	0.7221					_			_		1.2049	1000	1.0825			_		_	0.5504	2001.
CS	4.63	5.47	5.89	5.38	6.13	3.16	4.53	3.90	3.05 0	7.55 1	10.86	5.94		5.28					3.30 2		2.94 2	14.81 0	14.71		9.91									5.37		1 06.7						0 0001	
ANID	OK150	OK151	OK152	OT033	OT042	OT043	OT044	OT045	OT046	OT047	OT048	OT057	OT058	OT059	090TO	OT061	OT062	OT063	01070	OT071	OT077	OT100	OT101	OT102	OT105	OT115	OT116	OT117	01119	OT120	01121	01122	01128	01129	OT131B	OT 1316	O11310	011311	01132	01133	01134	OT 130	01139

ANID	macro_grp	Chem2012	CERAMIC TYPE	MATERIAL	SOURCE	STATE	SITE_NAME	SITE_NO	AS	LA	Π	ND	SM	n	YB C)E CO	CR
OT142	Group-D	El Paso Core	El Paso Polychrome	Pottery	MURR	NM	Lizard Terrace	LA 037726	7.14	75.49 C	0.6091	72.39 11	11.40 4	4.75 4.	4.53 146.00	10.61	1 25.59
OT143	Group-A	Mimbres-01	Mimbres B/W Style III	Pottery	MURR	MN	Lizard Terrace	LA 037726	4.16		0.5775	24.74	4.60 10	10.44 2.	2.96 86.58	58 2.48	3 10.15
OT145	Group-A	Mimbres-01	Mimbres B/W Style III	Pottery	MURR	MN	Lizard Terrace	LA 037726	3.88	51.54 0	0.6338	23.53	3.78 12	12.94 2.	2.89 80.95	95 1.68	3 5.84
OT146	Group-A	Mimbres-01	Mimbres B/W Style III	Pottery	MURR	MΝ	Lizard Terrace	LA 037726	2.67	47.88	0.6009		3.95 11	11.64 3.	3.11 81.25	25 3.98	3 11.46
OT156	G-dno-D	El Paso Core	El Paso Polychrome	Pottery	MURR	MN	Mt. Lion Hamlet	LA 037728	7.92	45.51 (0.4312	43.31		3.87 2.	2.87 86.71		30.80
OT157	Group-B	Unas.	Mimbres B/W Style III	Pottery	MURR	NN	Ronnie Pueblo	LA 045103	4.25	39.19	0.4658	27.90	4.87 5	5.29 2.	2.99 72.08	38 4.96	5 23.12
OT158	Clay		Clay	Clay	MURR	NM	Animas/Seco	Raw Clay Loc		25.40 C				1.69 1.		1	36.41
OT159	Clay		Clay	Clay	MURR		Seco	Raw Clay Loc	4.25	29.23 0	0.3209	27.71	4.87		2.08 47.90		3 142.14
OT160	Clay		Clay	Clay	MURR	MN	Palomas	Raw Clay Loc		27.96	0.4153	9.12	2.16 3	3.35 2.	2.57 65.01	1.92	2 4.19
OT161	Clay		Clay	Clay	MURR		Ash Canyon #2	Raw Clay Loc	1.52	23.98	0.1294	20.23	3.43	1.72 0.	0.93 47.43	43 10.72	2 37.38
OT165	Group-C2a	Mimbres-49A	Clay	Clay	MURR		•	Raw Clay Loc		40.44	0.4045	36.33	6.62	2.87 3.	3.02 81.53	53 14.81	1 59.78
OT166	Group-C2a	Mimbres-49A	Clay	Clay	MURR			Raw Clay Loc	3.70	41.29 0	0.3987	34.98	6.93	2.03 2.	2.81 82.56	56 18.21	1 78.09
OT167	Group-B	Unas.	Mimbres B/W Style II	Pottery	MURR	MN	Old Town	LA 001113	2.71	40.90 C	0.5316	36.73	7.12	3.23 3.	3.99 78.08	38 9.29	9 60.18
OT169	Group-B	Unas.	Three Circle Corrugated	Pottery	MURR	MN	Old Town	LA 001113	3.93	45.36 C	0.5310	31.17	99.9	5.73 3.	3.29 91.51	51 4.99	35.88
OT170	Group-B	Unas.	Three Circle Corrugated	Pottery	MURR	MN	Old Town	LA 001113	3.36	44.56 0	0.5331	32.25	6.61 5		3.55 90.42	42 5.02	36.62
OT171	Group-B1	Mimbres-04C	Three Circle Corrugated	Pottery	MURR	MN	Old Town	LA 001113	3.00	_							
OT172	Group-B	Unas.	Three Circle Corrugated	Pottery	MURR	MN	Old Town	LA 001113	2.56	41.52 0	0.4719	27.61	5.80 5	5.51 2.	2.97 81.99	99 5.21	1 30.20
OT173	Group-B	Unas.	Mimbres B/W Style II	Pottery	MURR	MΝ	Old Town	LA 001113	0.00	49.80		42.17	8.05	3.97 3.	3.80 109.55	55 7.73	35.35
OT174	Group-B2	Mimbres-11	Mimbres B/W Style II	Pottery	MURR	MN	Old Town	LA 001113	2.53	38.48	0.5420	26.80 E	5.64 6	6.10 3.	3.34 72.89	39 8.73	3 37.48
OT175	Group-B1	Mimbres-05A	Mimbres B/W Style II	Pottery	MURR	MN	Old Town	LA 001113	90.9	46.61		42.32	8.30 2		3.74 96.49	49 12.68	3 51.35
OT178	Group-B	Unas.	Mimbres B/W Style I	Pottery	MURR	MN	Old Town	LA 001113	6.63	44.85 (0.5413	38.80	8.43 3	3.04 3.	3.78 99.09	96.94	35.16
OT179	Group-B	Unas.	Mimbres B/W Style I/II	Pottery	MURR	MN	Old Town	LA 001113	08.9	49.62 C	0.5650	48.11 9	9.63	3.04 4.	4.07 109.94	94 7.16	5 39.39
OT180	Group-C2b	Mimbres-41	Mimbres B/W Style I	Pottery	MURR	MN	Old Town	LA 001113	1.59	34.74 0	0.3513 2	28.80	5.48	1.86 2.	2.69 72.00	00 10.95	5 26.92
OT181	Group-A	Unas.	Three Circle Corrugated	Pottery	MURR	MN	Old Town	LA 001113	4.65	111.57 0	0.9636	95.12 20	20.30 12	12.32 6.	6.06 213.62	52 16.80) 94.89
OT182	Group-C2b	Mimbres-41	Three Circle Corrugated	Pottery	MURR	NN	Old Town	LA 001113	1.17	35.52 0	0.3090	29.80			2.26 69.07	01.6 (0.10)) 24.20
OT183	Group-B	Unas.	Three Circle Corrugated	Pottery	MURR	NN	Old Town	LA 001113	3.73	33.61 (0.3395	26.90	5.09 2	2.87 2.	2.39 68.62		9 21.9
OT184	Group-A	Mimbres-10	Three Circle Corrugated	Pottery	MURR	NM	Old Town	LA 001113	3.95	42.44 C	0.7665	30.37	7.23 4	4.88 5.	5.35 62.67	57 2.87	7 26.72
OT185	Group-D	El Paso Core	El Paso Brown	Pottery	MURR	NN	Old Town	LA 001113	8.35						_	1	
OT186	Group-C2b	Mimbres-41	Mimbres B/W Style II	Pottery	MURR	M	Old Town	LA 001113	0.00								
OT187	Group-C1	Mimbres-21	Mimbres B/W Style II	Pottery	MURR	NM	Old Town	LA 001113	2.59	_							
OT189	Group-C1	Mimbres-21	Mimbres B/W Style II	Pottery	MURR	NZ.	Old Town	LA 001113	2.24								
01190	Group-B1	Mimbres-04C	Mimbres B/W Style II	Pottery	MURK	MN	Old Lown	LA 001113	2.22	_		_					
OT191	Group-C2b	Mimbres-41	San Francisco Red	Pottery	MURR	ΣN	Old Town	LA 001113	0.00								
OT193	Group-C2a	Mimbres-49A	San Francisco Red	Pottery	MURR	M	Old Town	LA 001113	4.04								
OT194	Group-C2a	Mimbres-49A	San Francisco Red	Pottery	MURR	NM	Old Town	LA 001113	4.09							1	7
OT195	Group-A	Mimbres-03	Untyped, Unslipped Black-c	Pottery	MURR	M	Old Town	LA 001113	3.08						_		
OT196	Group-A	Mimbres-03	Untyped, Unslipped Black-o Pottery	Pottery	MURR	NM	Old Town	LA 001113	1.63								
OT197	Group-A	Mimbres-03	Untyped, Unslipped Black-o Pott	Pottery	MURR	NM	Old Town	LA 001113	2.32	49.36	1.3989 4	46.93 13	13.35 8	_	1	52 2.18	8.42
OT198	Group-A	Mimbres-03	Untyped, Unslipped Black-o Pottery	Pottery	MURR	NM	Old Town	LA 001113	3.41	38.49				7.39 8.	_	Ì	_
OT199	Group-A	Mimbres-03	Untyped, Unslipped Black-o Pottery	Pottery	MURR	NM	Old Town	LA 001113	2.17	37.77		`		1	_	57 1.95	
OT200	Group-A	Mimbres-03	Untyped, Unslipped Black-o Pottery	Pottery	MURR	M	Old Town	LA 001113	3.59	45.68	1.3143 4	43.35 11	11.86	7.27 9.		2.19	
OT201	Group-B	Unas.	Mimbres B/W Style II	Pottery	MURR	MM	Old Town	LA 001113	0.00				5.06 2				
OT202		Unas.	Mimbres B/W Style II	Pottery	MURR	NM	Old Town	LA 001113	2.06								
OT203	Group-C2b	Mimbres-41	Mimbres B/W Style II	Pottery	MURR	ΣN	Old Town	LA 001113	0.00	34.55 (0.3240	30.03	5.35 2	2.15 2.	2.31 69.22	22 11.77	7 24.13

>	100.70	26.10	13.90	28.40	97.30	45.40	168.50	78.80	27.90	231.60	81.00	08.66	74.60	62.80	65.00	63.50	58.00	89.70	64.70	79.70	26.00	62.80	79.00	100.40	83.00	09.69	50.30	135.30	07.18	50.20	58.00	57.40	83.80	100.40	12.40	12.80	14.70	21.90	16.20	28.20	54.60	28.60
F	7103.4 10	1275.4		1713.9	5565.5	2773.4	3491.5 16	2980.9	732.8	3644.0 23	4331.2	5480.1	4050.4	3282.3	3910.8	3362.8	3443.2	4230.2	3645.2	4077.4	3975.1	3651.9	3415.7	4643.1 10				_		2/65.T			4976.8	3528.5 10	1050.7	1493.8	747.9	787.9		1882.7		2970.2
NA		9925.0 1;		15672.1	13764.1 5	10293.4 2	28770.4 3	843.4 29	10029.4	27958.6 30	12097.5 4:	11977.0 5	15655.4 40	17020.4 3.	14428.7 39		17382.6 3	14504.0 4;	13794.4 30	13196.5 40	12571.5 3	9581.5 30	17723.0 3	16113.3 40		~				7 2.6090			16311.7 49	5273.3 3!	6132.2	6365.2 1	. 2694.4	5914.4		7431.2 18		15194.0 29
MN	607.9 196:	156.6 99.	,	١,	499.4 137		927.3 287	91.0 8	421.0 100;	336.3 279	867.3 120	934.4 119.	698.8 156	295.4 170;	304.3 144.			449.2 1450	338.3 137	671.4 131	430.9 125	422.5 958	521.3 177.	,	`					_ ~			344.9 163.	642.2 152	712.5 61:	667.4 630	672.4 56	537.9 59.	613.6 65	650.8 74:	`	345.0 151
×			7			0.1 247.7											1.7 329.7												,	6.8 TU/3.4									2			
>	8 29345.2	33949.3			5 25461.1	72 29200.1	20 15661.8	00 10271.9	15988.6	13727.6	30 24508.	7 22747.5	75 25383.0	3 27288.6	5 27778.9	36 25073.9	13 32431.7	79 24009.4	9 25202.4	4 30337.8	36024.8	32565.9	5 25325.2	7 30369.1						28 2/466.8			27 29143.2	13 32024.9	14 52396.7	11 50206.0		57 50533.2)4 55831.3	- 1	5 30688.2
A DY	0 6.758	0 3.434	0 2.503	3 2.516	0 4.255	0 3.272	0 1.820	0 3.800	0 2.644	5 1.787	0 5.480	7 4.527	0 6.575	0 4.863	0 5.025		1 4.543	0 6.279	0 4.309	0 6.144	0 6.231	0 7.187	0 3.925	0 12.607						0 3.228			5.127	4 6.043	6 11.304	0 13.741	0 16.398	8 11.757	2 13.974	5 14.704		0 4.815
S	18998.0	6525.0	6390.0	9076.3	17740.0	8503.0	45759.0	187316.0	115054.0	32564.5	29297.0	16203.7	19247.0	14396.0	9123.0	13884.0	12027.1	9858.0	9952.0	11142.0	13268.0	7907.0	17888.0	11755.0	18050.0	15184.0	4433.0	13086.0	47054.0	72264.0	10616.8	20984.0	16449.6	10191.4	9.6928	11840.0	2945.0	8.8608	6840.2	12599.5	16567.5	12412.0
BA	738.5	389.4		369.9	1038.5	464.1	1265.6	132.6	273.5	1404.9	8.0/9	791.9	916.6	659.3	682.4	7.789	908.3	620.1	442.2	864.0	972.0	898.5	1001.9	574.2				721.2	971.0	529.T	7757		562.5	571.3	90.1	101.3	159.7	28.7	172.3	71.9	510.2	573.8
AL	93859.8	96282.5	99136.6	99637.4	91656.8	83045.9	95103.1	52965.2	53972.4	103632.1	86745.4	92923.3	77812.9	88950.1	89929.4	86521.5	87022.6	87804.0	87453.1	92558.1	83072.5	89736.9	91460.8	86404.8	84978.7	88553.6	87660.6	97147.3	90044.4	86251.8	88802.3	87335.0	95680.9	90467.1	79819.9	83876.0	84751.3	80326.7	83104.0	81404.7	92381.9	85478.1
ZR	334.3	186.1	159.7		284.4	197.4	84.8	111.9	84.9	135.2	171.7	166.5	175.5	204.0	171.8	161.3	220.2	197.1	155.4	192.7	229.3	227.5	200.8					327.1	18/.4	146.9	- ~		228.7	212.3	225.6	200.6	206.1	166.8	194.4	185.5	149.5	183.8
NZ	81.6	37.4	40.3	47.0	70.2	48.0	57.3	76.8	24.2	41.5	82.6	80.3	84.8	45.9	50.0		49.1	69.2	49.2	75.6	93.5	106.4	55.2	115.8						6/.5	12.2		72.1	84.2	162.2	70.1	172.7	136.7	74.7	146.4	57.2	46.0
TH	, 22.83	46.85				27.56	3.55	7.33	25.41	3.73	12.21	9.74	14.42	20.57	20.69	16.09	21.57	19.69	21.98	14.47	14.55	15.30	10.64	43.03		_				9.51	7		13.91	12.18		36.03	37.07	32.43	35.75	35.12		21.98
A TB	7 1.37	6 0.48		2 0.46	9 0.82	99.0 6	1 0.43	8 0.65	6 0.38	8 0.31	2 1.08	1 0.86	3 1.11	6 0.87	1 0.89	3 0.91	1 0.81	6 1.02	0.70	5 1.43	2 1.23	7 1.56	4 0.79	9 2.64		_					7 0 75		3 1.07	8 1.22	8 2.02	9 2.24	2 2.55	6 1.88	7 2.49	5 2.42		0.81
TA	3.5767	2.2156	2.3128	2.5162	3.0449	1.5499	0.2981	0.6788	1.2756	0.3998	1.0842	1.0301	1.3923	1.4236	1.4361	1.2283	1.4111	1.6696	1.7889	1.1165	1.0202	1.2017	1.0554	1.4949		1.2526				0.6816			1.2163	1.3828	2.6208	2.4999	2.6312	2.1996	2.4247	2.5085	1.3361	1.6796
SR	471.0	97.5	138.9	154.3	454.6	583.9	1516.5	298.8	517.6	1387.9	406.9	424.2	432.7	329.0	343.1	9'868	414.2	297.6	242.5	347.3	161.2	145.9	674.9	171.1		4	84.7			402.6	400.3		460.4	384.9	42.2		6'82	8.79	48.7	50.1	396.4	359.8
SC	10.35	4.73		4.85	9.44	6.47	8.71	9.80	1.95	8.65	-	12.68	9.45	8.11	8.76	19.8	66.9	10.21	7.99	12.78	10.83	11.15	7.65	14.91				—		69.9			1	9.15		5.12	2.08	5.17		5.52		9.31
SB	0.5061	0.8941	0.7460	0.5468	0.6156	0.5120	0.0000	0.3689	0.2728	0.0000	0.6993	0.5773	0.9257	0.5120	0.4817	0.3909	0.4334	0.3811	0.5524	1.0183	1.2207	1.3197	0.2382	0.3815	0.2619	0.4579	0.5583	0.5176	0.2308	7.4652	0.3829	0.1761	0.3382	1.2923	0.6983	0.3678	0.5773	0.4372	0.3460	0.4098	0.4194	0.7445
RB	109.70	245.20	237.50	213.00	99.10	193.00	30.30	64.40	62.80	40.80	117.70	93.90	136.00	142.50	133.00	103.90	140.90	117.60	191.30	150.90	160.60	174.60	99.50	185.20	79.40	103.10	243.10	101.90	101.30	110.00	135 20	78.20	105.80	127.70	303.50	283.20	290.80	277.70	304.50	329.30	165.70	176.90
Z	0.0	0.0		0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0						0.0			0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0		0.0
生	12.30	6.58	6.29	8.12	11.12	7.75	4.26	3.48	3.15	4.55	6.48	7.50	7.63	7.16	68.9	5.73	7.37	8.03	7.78	8.35	8.78	90.6	7.53	11.10						6.17	0.30	5.57	6.59	8.09	12.68		10.91	6.07	10.72	10.53		7.44
H	45750.3	12862.0	11624.2	13931.2	41879.3	21049.9	28602.3	26371.7	9.6068	28231.5	37007.7	43786.5	34479.6	25332.4	25632.6	27474.1	23891.6	34923.3	22488.6	1.8180 40518.1	30060.2	35572.3	30931.8	48752.4	29894.6	32406.6	24051.2	56105.5	30642.5	243/0.1	24713.1		40672.9	38160.9	12259.3	13484.6	13742.2	13133.7	13920.5	14722.6	27425.0	19843.4
EN	2.2881	0.5697	0.4307	0.5290	1.2696	0.8862	1.2901	0.9424	0.4234	1.1598	1.5063	1.7388	1.2080	1.2461	1.2044	1.2787	1.0849	1.4585	1.0645	1.8180	1.6951	1.9590	1.3578	2.1826						1.1904	1 1618		1.6423	1.5854	0.4841	0.4953	0.6022	5.19 0.4799	0.5394			1.1251
CS	3.60	19.78		11.34	4.36	7.02	2.49	20.45	8.41	3.41	. 96.7	4.56	10.35	4.58	5.75	3.62	4.13	4.84	7.57	8.73	10.36	12.59	3.38							15.48			3.03	9.11	4.21	4.68	4.71	5.19		5.64 (15.02
ANID	OT142	OT143	OT145	OT146	OT156	OT157	OT158	OT159	OT160	OT161	OT165	OT166	OT167	OT169	OT170	07171	OT172	OT173	OT174	OT175	OT178	OT179	OT180	OT181	OT182	OT183	OT184	OT185	01186	0118/	OT 190	OT191	OT193	OT194	OT195	OT196	OT197	OT198	OT199	OT200	OT201	OT202

ANID	macro grp	Chem2012	CERAMIC TYPE	MATERIAL	SOURCE	STATE	SITE NAME	SITE NO	AS	ΓA	Π	ND	SM	n	YB CE	00	CR
OT204	Group-B	Unas.	Mimbres B/W Style II	Pottery	MURR	MN	Old Town	LA 001113	4.01	24.52 0	0.2701	13.89 2	2.32 2.	2.24 1.0	1.63 38.59	1.58	11.54
OT205	Group-C1	Mimbres-21	Mimbres B/W Style II	Pottery	MURR	M	Old Town	LA 001113	3.46	36.69 0	0.3477	29.77 5		1.39 2.64	54 77.74	11.75	88.47
OT206	Group-A	Mimbres-10	Mimbres B/W Style I	Pottery	MURR	MN	Old Town	LA 001113	3.59	61.46	1.2991	59.25 12	12.98 9.	9.49 8.75	75 123.21	4.54	28.95
OT207	Group-B1	Mimbres-05A	Mimbres B/W Style I	Pottery	MURR	NM	Old Town	LA 001113	4.36		0.7249	1		3.26 5.64	1		53.94
OT208	Group-B1	Mimbres-05B	Mimbres B/W Style I/II	Pottery	MURR	MN	Old Town	LA 001113	2.97								37.37
OT209	Group-B1	Mimbres-04C	Mimbres B/W Style I	Pottery	MURR	ΣN	Old Town	LA 001113	0.00							_	32.39
OT210	Group-C2a	Mimbres-49A	San Francisco Red	Pottery	MURR	MN	Old Town	LA 001113	4.55	_				3.01 2.79			55.91
OT211	Group-C2a	Mimbres-49A	Three Circle Corrugated	Pottery	MURR	MN	Old Town	LA 001113	3.78							_	54.59
OT212	Group-A	Mimbres-10	Three Circle Corrugated	Pottery	MURR	M	Old Town	LA 001113	3.73		_	`		_	1		23.97
OT215	Group-C2b	Mimbres-41	Mimbres B/W Style I	Pottery	MURR	NM	Old Town	LA 001113	3.82			27.57 5		3.31 2.40		9.79	24.84
OT216	Group-C2b	Mimbres-41	Plain	Pottery	MURR	MN	Old Town	LA 001113	1.99	33.63 0	0.3080		5.09 2.	2.19 2.14	14 63.38	3 10.14	27.73
OT217	Group-C2b	Mimbres-41	Three Circle Corrugated	Pottery	MURR	MN	Old Town	LA 001113	3.25	35.70 0	0.3320	26.49 5	5.07 2.	2.06 2.15	15 69.79	69.8	22.63
OT218	Group-C2b	Mimbres-41	Three Circle Corrugated	Pottery	MURR	NM	Old Town	LA 001113	2.89	-				1.62 1.91			23.83
OT219	Group-C2a	Mimbres-49A	San Francisco Red	Pottery	MURR	NM	Old Town	LA 001113	7.48				6.25 3.		_	11.68	62.12
OT220	Group-C2a	Mimbres-49A	San Francisco Red	Pottery	MURR	NM	Old Town	LA 001113	2.84	38.55 0				2.05 2.91		10.43	49.57
OT221	Group-B1	Mimbres-04A	Three Circle Corrugated	Pottery	MURR	NM	Old Town	LA 001113	1.89					6.87 3.92	99.83		24.18
OT222	Group-B	Unas.	Mimbres B/W Style I	Pottery	MURR	M	Old Town	LA 001113	1.55								25.25
OT223	Group-C2a	Mimbres-49A	Mimbres B/W Style I/II	Pottery	MURR	NM	Old Town	LA 001113	3.22		0.4494		7.67 2.	2.49 3.75		16.51	62.01
OT224	Group-B1	Mimbres-05A	Mimbres B/W Style II	Pottery	MURR	NM	Old Town	LA 001113	3.88	46.35 0	0.6314		8.72 4.	4.37 5.11	11 88.91	8.76	63.73
OT225	Group-C1	Mimbres-22	Mimbres B/W Style II	Pottery	MURR	NM	Old Town	LA 001113	7.22					1.61 2.42			18.98
OT226	Group-C2b	Mimbres-41	Mimbres B/W Style II	Pottery	MURR	NM	Old Town	LA 001113	2.34	35.85 0		29.98 5		2.90 2.44	14 72.92	10.02	26.99
OT227	Group-B1	Mimbres-04C	Mimbres B/W Style II	Pottery	MURR	NM	Old Town	LA 001113	1.82		0.5013	36.38 7	7.04 3.	3.80 3.30		7.91	44.20
OT228	Group-C1	Mimbres-22	Mimbres B/W Style II	Pottery	MURR	MN	Old Town	LA 001113	3.42	39.67 0	0.3375			1.69 2.51			16.92
OT229	Group-C2a	Mimbres-49A	Plain	Pottery	MURR	NM	Old Town	LA 001113	2.23							13.58	45.72
OT230	Group-A	Mimbres-03	Untyped, Unslipped Black-o Pottery	Pottery	MURR	NM	Old Town	LA 001113	2.05	43.31			10.92 7.	7.12 10.10		2.11	7.53
OT231	Group-A	Mimbres-03	Untyped, Unslipped Black-o Pottery	Pottery	MURR	M	Old Town	LA 001113	2.97						_		10.81
OT232	Group-A	Mimbres-03	Untyped, Unslipped Black-o Pottery	Pottery	MURR	M	Old Town	LA 001113	2.27								9.13
OT233	Group-A	Mimbres-03	Untyped, Unslipped Black-o Pottery	Pottery	MURR	M	Old Town	LA 001113	3.86								10.23
OT234	Group-A	Mimbres-03	Untyped, Unslipped Black-o Pott	Pottery	MURR	Σ	Old Town	LA 001113	2.91	42.15 1		81.22 11	11.14 7.	7.26 10.59	90.10	1.67	7.14
OT235	Group-C1	Mimbres-21	Mimbres B/W Style II	Pottery	MURR	M	Old Town	LA 001113	0.00								34.58
OT236	Group-B	Unas.	Mimbres B/W Style II	Pottery	MURR	Σ	Old Town	LA 001113	3.48	_							19.81
OT237	Group-B1	Mimbres-04A	Three Circle Corrugated	Pottery	MURR	Σ	Old Town	LA 001113	3.28	_							20.73
OT238	Group-C2	Unas.	Sacaton R/Buff	Pottery	MURR	Z	Old Town	LA 001113	4.41					_		1	17.20
OT240	Group-C2b	Mimbres-41	San Francisco Red	Pottery	MURR	N	Old Town	LA 001113	1.65	-							22.38
OT241	Group-C2a	Mimbres-49A		Pottery	MURR	MN	Old Town	LA 001113	3.44							1	52.05
OT243	Group-A	Mimbres-03	Untyped, Unslipped Black-o	Black-o Pottery	MURR	NM	Old Town	LA 001113	1.68		1.3594		11.59 7.	7.00 10.02		1 2.23	09.6
OT244	Group-C2a	Mimbres-49A	San Francisco Red	Pottery	MURR	NM	Old Town	LA 001113	4.39	35.42 0			6.79 2.				34.99
OT246	Group-C2a	Mimbres-49A	San Francisco Red	Pottery	MURR	NM	Old Town	LA 001113	5.73		0.3957		6.63 2.		98 84.30	14.30	59.65
OT247	Group-C2a	Mimbres-49A	San Francisco Red	Pottery	MURR	NM	Old Town	LA 001113	2.48	25.89 0	0.3338		5.78 1.			15.39	36.66
OT248	Group-C2a	Mimbres-49A	Mimbres B/W Style II	Pottery	MURR	NM	Old Town	LA 001113	2.86	40.38 0			6.39 2.	2.55 3.21		12.78	46.94
OT249	Group-B	Unas.	Mimbres B/W Style II	Pottery	MURR	MN	Old Town	LA 001113	2.37						,		23.89
OT250	Group-B	Unas.	Mimbres B/W Style II	Pottery	MURR	M	Old Town	LA 001113	3.48						_	1	52.80
OT251	Group-B1	Mimbres-04C	Mimbres B/W Style I	Pottery	MURR	M	Old Town	LA 001113	0.00	44.12 0						7.19	33.24
OT252	Group-B	Unas.	Mimbres B/W Style I	Pottery	MURR	MN	Old Town	LA 001113	1.51	48.46 0	0.3845	36.48 6	6.36 2.	2.85 2.7	2.75 87.91	6.41	25.86

>	30.20	72.60	45.60	84.80	63.30	61.20	92.50	89.80	37.10	82.40	83.50	82.00	84.10	92.70	78.30	28.60	46.70	102.30	68.40	39.20	88.10	72.20	49.00	101.20	32.80	24.70	14.30	25.60	0.00	41.40	48.00	63.40	00.00	83.10	19 10	72.70	79.30	174.60	85.40	62.80	85.70	26.80	54.40
I	1553.8	2678.9	2000.2	3999.1	3280.8	3414.5	3963.7	4872.9	2323.8	3838.8	3907.9	4784.8	3500.4	4317.8	3906.1	3017.9	3040.8	5555.7	4747.8	1387.1	4162.4	4351.1	2546.9	5567.0	1287.9	2346.3	1288.0	1375.6	1366.1	1752.3	2167.6	3501.2	3373.3	4000.1	1833.8	3476.5	4635.0	4588.7	4214.8	3314.0	4701.9	4330.6	3002.5
NA	6749.5	17982.9	12522.7	14538.0	10160.2	15590.5	16376.0	17119.0	13864.9	16267.6	16239.0	16428.2	17746.5	14919.7	16500.5	13857.0	15205.7	14928.4	15285.0	12517.1	15576.2	13954.9	14774.1	18658.3	5286.8	5841.0	6107.0	6168.0	5441.6	17699.5	12481.9	142021	14392.1	11545 8	40764	14753.3	16276.6	15946.4	14332.0	15316.3	17270.6	17939.3	12922.0
M	373.2	1154.3	329.2	672.6	623.5	340.3	9:059	0.769	282.1	438.2	492.8	363.0	462.8	741.0	436.5	687.2	214.3	869.5	9.999	722.4	491.3	434.4	398.1	759.6	622.0	629.5	651.2	663.1	612.9	1028.2	528.7	504.9	747.7	517 B	604 4	545.6	944.7	629.0	755.4	280.0	576.1	402.4	391.8
¥	17755.5	27214.5	29929.8	28900.3	32139.5	26028.1	33306.8	31105.5	36930.2	20914.0	27971.5	22846.3	24123.8	35604.6	24342.2	26667.7	38077.3	31408.0	28507.6	28581.5	21798.1	22956.0	33342.7	26891.0	45586.0	54092.9	55016.8	51873.8	50065.3	28447.9	18042.6	33518.4	24092.1	23004.1 24974.8	47121 0	34404.7	34460.0	34344.5	26116.1	27820.4	25036.3	27629.1	29229.2
DY	2.280	3.565	13.173	9.142	7.029	4.714	4.494	5.202	15.523	3.752	3.597	3.432	3.864	4.492	4.766	6.559	3.484	2.097	8.237	3.431	4.763	6.087	4.490	4.861	13.123	16.250	12.745	13.426	12.267	3.197	2.175	3.735	3.102	5.200	14 157	5.723	5.129	4.623	4.892	13.208	4.788	4.656	4.159
CA	5001.0	11551.1	0.6099	18849.8	17632.0	11893.0	12113.0	17448.3	6797.4	22192.0	22286.2	21400.6	22075.0	15741.3	17224.3	13087.5	12595.0	15827.8	8.6966	26951.5	22122.9	13087.0	28406.7	22306.5	10766.2	16505.6	6756.0	8745.0	11056.3	14641.0	13934.2	14100.0	14109.0	183310	6363 6	10211.0	11574.0	24832.0	22771.4	12034.0	15815.0	13436.8	13271.0
BA	223.0	993.9	562.1	839.1	851.6	777.0	844.2	813.2	569.4	1018.6	1042.1	924.9	883.5	906.2	6.999	814.9	1015.8	799.3	547.7	746.0	973.3	575.8	1323.2	935.9	178.9	183.0	171.1	261.6	155.5	972.1	408.7	0 107	1122.2	052 F	127.6	582.7	787.2	865.4	743.3	832.9	984.9	733.0	776.4
AL	92961.6	90785.7	89237.6	2.66606	91161.3	89789.3	86951.4	90835.0	81578.9	97104.2	91990.2	89637.4	92651.0	94876.5	91545.3	85280.8	80836.3	83852.2	81562.6	96539.1	100925.1	92657.1	90415.4	74723.9	83245.9	78363.9	83026.5	82384.4	86587.0	89284.8	90999.4	0.067/8	73042.0	91321.4	837099	90590.5	87455.2	85888.5	86459.5	83800.0	106353.1	93892.5	86139.0
ZR	111.3				249.2	149.5	214.8	210.3	250.9	151.2	145.0	110.2	128.2	189.8	196.0	153.6	155.1	169.8	216.4	139.1	148.7	173.8	140.7	299.3							103.5	137.3	100.7					136.0	137.5	234.6		181.9	142.7
NZ		79.4		91.9		80.1		101.9	79.3	94.2	93.0	82.9	63.7	189.9	89.7	83.4	44.3	83.0	93.8	93.8	8.79	117.7	6'66						_		34.1		0.40	,		129.3	167.7	116.5	73.9	68.3		_	69.7
3 TH	_					7 18.56	14.06	3 12.04	5 35.72	10.99	10.19	10.01	4 9.82	3 16.12	11.52	3 18.29	5 13.89	3 12.52	17.77	9.44	5 11.23	17.38	10.68						(~)				10.00				13.24	6.84	1 12.13	21.25			3 14.21
TA TE	2 0.38		5 2.15	1.68	1.39	0.87	16 0.91	1 1.03	6 2.85	5 0.00	0.44	1.14	3 0.44	1.43	4 1.34	1.13	2 0.45	0 1.23	1.29	5 0.44	1 0.56	7 1.20	5 0.54	6 0.65		1.87	1.64						0.40			+-	1.80	9 1.10	1.41	1 1.90		_	1 0.73
						1.2340	1.2189	0.9811	2.5416	0.8815	0.8662	0.8808	0.9273	1.1221	1.0814	1.2061	0.9132	1.1510	1.7152	0.6195	0.9001	1.2375	0.7175							_			0.7030				1.1748	0.6019	1.0353	1.4861			0.8571
SR	63.9	362.0	81.5	223.0	701.5	336.9	407.5	1.794	6'66	526.4	545.2	623.8	626.3	490.3	392.1	265.4	257.6	220.6	190.6	219.9	425.0	246.1	320.2	392.0	90.4	68.2	0.0	57.9	39.4	264.8	190.9	310.6	402.0	500.3 575.8	54.2	443.5	270.8	871.5	247.4	766.6	9.003	350.0	237.9
SC	5.64	8.80	8.70	12.47	98.6	8.76	9.17	11.91	7.29	9.31	8.63	8.37	7.95	10.40	9.59	7.85	60.9	13.85	10.49	4.69	8.97	11.07	5.20	10.08	4.87	4.94	5.23	5.71	4.67	5.60	6.81	0.50	7.20	11 75	5.03	9.00	10.39	18.40	10.41	9.17	10.94	9.28	9.80
SB	0.3435	1.9574	0.4593	0.5812	0.4440	0.3408	0.4360	1.0160	0.4422	0.2448	0.2447	0.2557	0.2526	0.6181	0.2740	0.3321	0.1893	0.7702	0.6313	4.6908	0.3232	0.3597	2.1459	0.2537	0.3937	0.3842	0.5269	0.5229	0.4500	1.5384	0.3446	0.4034	0.3370	0.1002	0.2574	1.1768	0.6610	0.3921	0.4455	0.3189	0.5228	0.3958	0.1864
RB	75.30	131.30	258.60	141.60	162.40	114.70	119.20	115.20	255.30	97.70	72.80	75.40	75.70	121.80	101.00	132.70	115.60	136.20	161.10	145.70	106.60	108.10	147.40	102.70	258.10	281.50	316.70	311.70	286.00	127.90	64.10	131.60	131.00	07.70 05.40	05 996	129.30	125.40	112.90	98.30	137.40	128.70	133.00	108.30
Z								0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	33.0	0.0	67.4	0.0	0.0	0.0	0.0	0.0		0.0				0.0				0.0	0.0			0.0	0.0	0.0	0.0			25.2
Ή	99.9	6.72	7.72	8.14	9.23	5.85	8.31	8.16	8.09	6.42	5.88	5.49	2.69	8.55	8.59	99.9	19.9	7.90	9.33	6.34	5.71	6.73	6.14						,	6.07	7.22	80.7	4.92	00.0	10.34	7.19	7.94	19.9	6.19	7.94	8.75	80.6	99.9
FE	13324.1						37151.2		24199.4	36662.9	36079.8	33775.3	32941.4	38514.2	36556.9		20744.5	43461.5	37065.9	20279.4	37459.1	37464.9	20610.2				12918.5			_	_	2000E 4					38547.9	49699.4					23193.3
EU	0.3628	1.2606	1.2965	1.7669	1.6945	1.2301	1.5376	1.5464	1.5114	1.3159	1.2965	1.3214	1.3127	1.3362	1.3925	1.4334	1.2054	1.7081	1.1636	1.1809	1.3494	1.4275	1.3260	1.4907	4.28 0.5745	4.72 0.8864	0.5702	4.75 0.5601	0.5154			1.0923			4 43 0 5549	1.5327	1.5642	1.6144	1.4693	2.9084	1.4553	1.3643	1.3460
CS		17.85	8.03	7.02	8.04	4.66	3.53	6.79	5.37	4.18	3.01	3.07	2.83	5.49	3.30	4.84	3.22	09.9	9.80	30.33	4.58	5.08	37.54	2.38	4.28	4.72	4.91	4.75	4.53				2.07	3.03	4.43	99.6	4.43	4.52	4.42	5.34	4.01	5.14	2.89
ANID	OT204	OT205	OT206	OT207	OT208	OT209	OT210	0T211	OT212	OT215	OT216	OT217	OT218	OT219	OT220	0T221	OT222	OT223	OT224	OT225	OT226	01227	01228	OT229	OT230	OT231	OT232	OT233	OT234	OT235	01236	U1237	01230	O1240 OT241	OT243	OT244	OT246	OT247	OT248	OT249	OT250	OT251	OT252

ANID	macro_grp	macro_grp Chem2012	CERAMIC TYPE	MATERIAL	SOURCE	STATE	SITE_NAME	SITE_NO	AS	ΓA	n	ND	SM	n	YB (CE CO	CR
OT253	Group-B1	Mimbres-04A	Mimbres B/W Style II	Pottery	MURR	MN	Old Town	LA 001113	2.75	46.83	0.4930	53.87	6.79	4.81 3	3.12 89.06		5 19.45
OT254	Group-C2b	Mimbres-41	Mimbres B/W Style II	Pottery	MURR	MN	Old Town	LA 001113	2.06	35.31	0.3372	31.04	5.40	2.32 2	2.41 65.45		4 27.58
OT255	Group-B1	Mimbres-04C	Mimbres B/W Style II	Pottery	MURR	NM	Old Town	LA 001113	2.23	45.53 (0.5235	48.40	7.22	4.26 3	3.31 96.45	45 6.51	1 37.35
OT256	Group-C2a		Three Circle Corrugated	Pottery	MURR	NM	Old Town	LA 001113	3.03		0.5131	73.41		2.93 3	3.83 105.53	1	
OT257	Group-A	Mimbres-10	Three Circle Corrugated	Pottery	MURR	NN	Old Town	LA 001113	2.34		0.8880				6.46 124.30		
OT258	Group-C1	Unas.	Three Circle Corrugated	Pottery	MURR	M	Old Town	LA 001113	4.54	_					3.17 72.01	_	
OT259	Group-A	Mimbres-10	Three Circle Corrugated	Pottery	MURR	M	Old Town	LA 001113	3.84		`	`	15.65		_		
OT262	Group-C1	Mimbres-21	Mimbres B/W Style II	Pottery	MURR	MN	Old Town	LA 001113	1.97		0.3293						
OT263	Group-C1	Mimbres-22	Mimbres B/W Style II	Pottery	MURR	M	Old Town	LA 001113	7.49		0.2972	43.82	5.35				
OT264	Group-B1	Mimbres-04C	Mimbres B/W Style II	Pottery	MURR	MN	Old Town	LA 001113	2.41		0.4626	47.07		4.33 2	2.85 84.17	17 7.22	
OT265	Group-C2b	Mimbres-41	Mimbres B/W Style II	Pottery	MURR	NM	Old Town	LA 001113	0.00		0.3531	30.44	5.19	2.44 2	2.47 65.94	94 10.11	1 25.76
OT266	Group-C2a	Mimbres-49A	Mimbres B/W Style II	Pottery	MURR	MN	Old Town	LA 001113	3.19	49.25 (0.4119	58.71	8.26	3.43 2	2.97 97.63	63 15.21	1 56.74
OT268	Group-B	Unas.	Three Circle Corrugated	Pottery	MURR	MN	Old Town	LA 001113	2.87		0.3027	_			1.82 69.46		
OT269	Group-A	Unas.	Three Circle Corrugated	Pottery	MURR	MN	Old Town	LA 001113	4.58	89.12	0.7768			5.24 4	4.87 101.75	75 3.54	1 22.1
OT270	Group-D	El Paso Core	El Paso Brown	Pottery	MURR	MN	Old Town	LA 001113	6.78	63.77 (0.5338	65.51	68.6	5.13 3	3.76 112.64		3 25.04
OT272	Group-B	Unas.	Mimbres B/W Style II	Pottery	MURR	MM	Old Town	LA 001113	2.04		0.3006	13.11	2.46		1.89 35.81		
OT273	Group-C2b	Mimbres-41	Mimbres B/W Style II	Pottery	MURR	MM	Old Town	LA 001113	0.00	41.59 (0.3453	38.13			_	47 10.58	
01275	Clay		Clay	Clay	MURR	MN	Old Town	LA 001113	11.27	44.64	0.4270	38.97		3.37 2	2.97 99.98	98 20.21	1 34.53
OT276	Clay		Clay	Clay	MURR	NM	Pruitt Ranch	LA 001117	18.40	42.78	0.4143	39.67	7.58	3.39 3	3.41 109.78	78 10.95	39.78
OT489	Group-A	Mimbres-01	Mimbres B/W Style III	Pottery	MURR	MN	Flying Fish	LA 037767	2.19		0.5560	19.01	3.68 13	13.13 2	2.32 87.28	28 2.16	5 7.18
OT490	Group-B2	Mimbres-02A	Mimbres B/W Style III	Pottery	MURR	MN	Flying Fish	LA 037767	1.61	26.80	0.5543	41.99	8.81	4.65 3	3.91 117.67	67 8.17	7 38.40
OT491	Group-A	Mimbres-01	Mimbres B/W Style III	Pottery	MURR	MN	Flying Fish	LA 037767	2.22	167.97	0.5682	23.20	4.46 10	10.25 2	2.62 112.98	98 5.81	1 5.94
OT492	Group-A	Mimbres-01	Mimbres B/W Style III	Pottery	MURR	NM	Flying Fish	LA 037767	2.16		0.5973						
OT493	Group-A		Mimbres B/W Style III	Pottery	MURR	NM	Flying Fish	LA 037767	2.04		0.6260		4.02	10.75 2	2.78 89.62	62 3.07	
OT494	Group-C2a		Mimbres B/W Style III	Pottery	MURR	M	Flying Fish	LA 037767	1.61		0.3572	33.54				97 15.17	
OT495	Group-A	Mimbres-01	Mimbres B/W Style III	Pottery	MURR	MN	Flying Fish	LA 037767	2.98		0.5079						
OT496	Group-A	Mimbres-01	Mimbres B/W Style III	Pottery	MURR	MN	Flying Fish	LA 037767	1.81		0.6358				_		
OT497	Group-A	Mimbres-01	Mimbres B/W Style III	Pottery	MURR	M	Flying Fish	LA 037767	2.13		0.6639	22.66	_		_		
OT498	Group-B2	Mimbres-08	Mimbres B/W Style III	Pottery	MURR	N N	Flying Fish	LA 037767	2.65		0.4464	19.86	3.97			04 3.57	7 20.37
OT499	Group-B1	Mimbres-04B	Mimbres B/W Style III	Pottery	MURR	N N	Flying Fish	LA 037767	1.47		0.5550						7
01500	Group-A	Mimbres-01	Mimbres B/W Style III	Pottery	MURR		Flying Fish	LA 037767	1.49		0.5138				_		
01501	Group-A	Mimbres-01	Mimbres B/W Style III	Pottery	MUKK	N :	Flying Fish	LA 03//6/	1.87		0.6040						
01502	Group-A	Mimbres-01	Mimbres B/W Style III	Pottery	MURR		Flying Fish	LA 037767	2.20		0.5836	20.44	_				
01503	Group-C1	Mimbres-23	Mimbres B/W Style III	Pottery	MURR		Flying Fish	LA 037767	4.65		0.3797	30.80				_	
01504	Group-B2	Mimbres-08	Mimbres B/W Style III	Pottery	MURR	M	Avilas Canyon Village	LA 045000	3.38		0.4199	22.74					
OT505	Group-B1	Mimbres-04A	Mimbres B/W Style III	Pottery	MURR	Σ	Avilas Canyon Village	LA 045000	2.39		0.5182	36.96					
OT506	Group-B2	Mimbres-08	Mimbres B/W Style III	Pottery	MURR	MN	Avilas Canyon Village	LA 045000	2.46		0.4148	18.47	3.51	4.85 2	2.19 69.23	23 8.32	2 22.73
OT507	Group-A	Mimbres-01	Mimbres B/W Style III	Pottery	MURR	MN	Avilas Canyon Village	LA 045000	1.27	43.80	0.5460	18.03	3.49 10	10.10	2.61 70.87	``	2 11.25
OT508	Group-A	Mimbres-01	Mimbres B/W Style III	Pottery	MURR	MN	Avilas Canyon Village	LA 045000	1.66		0.5611	19.40	4.12 12	12.78 2	2.36 92.68	68 1.97	3.68
OT509	Group-B	Unas.	Mimbres B/W Style III	Pottery	MURR	MN	Avilas Canyon Village	LA 045000	3.25	45.65 (0.4787	24.30			2.72 74.25	25 4.15	5 20.7
OT510	Gronp-B	Unas.	Mimbres B/W Style III	Pottery	MURR	NN	Avilas Canyon Village	LA 045000	2.82		0.4443	23.48	2.09				
OT511	Group-B1	Mimbres-04A	Mimbres B/W Style III	Pottery	MURR	MN	Avilas Canyon Village	LA 045000	1.97		0.4271	31.57					
OT512	Group-B1	Mimbres-04A	Mimbres B/W Style III	Pottery	MURR	MN	Avilas Canyon Village	LA 045000	2.37		0.4780	34.55					
OT513	Group-B1	Mimbres-04A	Mimbres B/W Style III	Pottery	MURR	MN	Avilas Canyon Village	LA 045000	2.20	34.61 (0.4327	27.02	5.44	4.30 2	2.65 70.08	08 5.65	5 25.55

>	20.90	84.50	69.50	92.10	33.00	09.96	40.10	77.80	44.70	58.10	87.00	81.70	00.09	60.50			102.90	69.50	67.20	24.10	59.30	20.40	23.90	24.90			11.70				23.90					45.60	24.10	8.80	36.20	44.70	47.20	0, 77
I	2299.2	3356.4	2888.9		2305.4	3621.2	1632.4	2209.5	1895.6	3007.6	3549.1	4681.1	3026.6	2498.4			3521.7	2855.6	3247.8	1440.6	3821.0	1428.3	1798.5	1409.7		1610.8	1210.1	1293.7	2636.9	2319.6	1330.5			2808.9	2911.1	3193.2	1178.2	880.5	2929.9	2044.3	3629.1	
NA	16037.5	15545.9	12045.0		12831.3	14294.5	14681.1	18511.6	10467.0	18751.5	17396.8	17413.7	19619.2	15718.2	1		16559.5	10224.3	2.6969	15868.5	11406.5	16272.6	13525.1	12720.2						, I,	12500.8	١,			16830.5	10388.0	14690.5	15145.5	13951.3	14470.6	13498.2	
MN	283.0	413.2	248.5		262.8	920.8	369.0	935.9	612.7	361.7	382.0	717.4	102.5	129.0			494.7	2141.4	1587.3	190.5	249.7	225.8	164.5	525.3							114.0				210.9	496.6	266.5	202.4	344.0	377.0	379.2	
×	30693.4	22983.7	20095.9	24973.9	41403.6	28689.9	38805.7	27174.2	35133.2	26245.4	24209.2	22045.7	29032.7	36489.1			22341.9	20236.9	50037.1	29404.5	28067.8	29396.6	33469.5	27026.8						- 1	312/5.0					32884.3	33625.4	30544.8	32112.4	27290.1	26982.0	
DY	4.124	3.551	5.366	6.255	12.352	4.744	12.023	3.503	3.383	4.457	4.227	5.330	3.615	6.926			3.474	4.666	2.696	2.417	2.667	3.022	2.930	2.718		2.199					2.041					3.183	2.493	2.609	3.713	4.321	4.780	
CA	15862.0	21545.0	14443.8	16885.0	7605.0	18751.5	8162.0	36597.0	17590.3	11459.0	22283.1	18196.0	9536.0	5993.8	11934.0	7628.0	22335.0	83346.0	10043.4	5482.4	10450.9	5659.9	8137.0	7205.2	22340.0	5468.7	29623.4	25371.6	6424.5	10246.2	1302.8	4629.0	49605.5	6185.4	10816.3	5973.1	8215.1	2.9609	8477.1	7397.7	9972.8	
BA	926.9	954.8	529.0	1	804.3	1002.4	983.5	850.2	940.0	9.598	953.7	969.5	1035.5	6'806	873.4		1001.4	747.0	426.1	307.8	584.1	723.2	307.9	354.4			260.2	299.4	461.5	583.9	331.5	438.0			941.7	526.2	445.6	722.8	630.3	288.7	922.1	
AL	89446.7	91231.7	94510.4		87607.9	94712.8	93378.6	86247.1	103622.1	84204.8	82468.3	98692.9	99731.8	93174.0	93262.8	93141.8	95529.2	74191.3	78798.4	99641.6	89026.4	101794.7	112431.4	107001.4	98771.8	98052.0	92307.1	112944.8	/6834.9	86957.4	97821.8 104825.0	98327.2	82314.2	84918.5	87361.0	81716.7	97629.2	100679.8	84401.2	90502.2	87969.0	
ZR	170.7	143.1	144.7		158.4	139.0	152.3	135.2	136.1	159.8	171.4	183.8	129.0	190.8			143.3	113.8	110.7	176.4	210.1	144.8	186.1	162.4							202.0				171.2	207.9	139.5	175.2	172.2	176.4	265.5	
NZ	26.8	94.2	63.2	110.0	63.9	129.9	74.5	9.69	7.66	63.0	17.1	76.9	47.8	29.8			74.3	95.3	193.9	38.2	61.9	39.1	47.7	44.2							44.8					37.5	39.9	73.6	46.4	44.6	51.9	
rB TH	8 20.45	69.01		7 12.68	5 32.90	0 10.03	5 40.57	5 8.83	0 10.48	7 17.37	10.21	6 13.48	0 13.41	5 41.06		5 17.53	11.61	4 15.75	11.81	9 50.28	99.61		8 56.63	5 49.87							45.97	_	_			4 26.24	9 41.78	3 52.62	8 32.13	9 21.51	19.10	
TA	527 0.68	403 0.56	651 1.16	0.9408 0.97	851 1.55	369 1.10	671 1.85	972 0.55	317 0.50	1.2572 0.97	348 0.86	960 1.26	356 0.40	962 1.05	232 0.92	1.6766 0.55	230 0.87	547 1.14	691 2.01	2.6252 0.29	741 0.96	625 0.38	621 0.38	1.9769 0.35							703 0.20				_	058 0.34	571 0.29	489 0.33	1.7217 0.48	258 0.69	1.5164 0.78	
SR	249.1 1.3527	520.0 0.9403	200.0 1.1651		200.1 1.9851	702.4 0.7369	241.5 2.0671	345.2 0.5972	303.9 0.6317	282.4 1.2E	470.1 0.9348	481.4 1.0960	417.4 0.7356	0.0 2.3962	366.2 2.8232		550.2 0.9230	357.9 1.0547	173.8 0.9691	86.1 2.62	213.8 1.5741	123.3 2.4625	102.9 2.4621	104.5 1.97							125.6 2.2703				284.2 1.3851	149.7 1.6058	173.0 2.2571	153.7 2.3489	136.7 1.72	207.3 1.1258	257.3 1.51	
SC	6.85 24	8.78 52	11.30 20	10.77 36	7.99 20	11.17 70	8.30 24	7.20 34	5.13 30	8.27 28	7.20 47	10.58 48	7.96 41	6.79	10.16 36		8.83 55	11.01 35	11.78 17	4.00	9.91 21	4.14 12	5.12 10	4.68 10	9						4.11 12					5.55	4.95	3.93	5.75 13	7.31 20	7.44 25	ĺ
SB	0.3691	0.3359	0.4127 1	0.3811 1	0.5478	0.4627 1	0.5359	1.1829	1.9077	0.3274	0.2667	0.4489	0.3378	0.4642			0.2475	0.3330	1.0238	0.6808	0.5120	0.6451	0.7299	0.9174	,	0.7460	0.7526	0.6267	0.4383	0.8002	0.4626	0.5904	1		0.4359	0.5879	0.4519	0.7003	0.4425	0.4220	0.3654	
RB	153.60	102.90	108.50	109.20	245.80	119.10	265.50	125.70	159.90	122.90	92.60	112.50	09.76	278.90	126.90	69.10	108.10	112.60	213.20	221.20	164.40	222.40	250.80	246.70	79.00	226.90	199.70	257.00	210.10	177.20	317.90	218.30	174.20	188.90	146.10	196.30	258.50	198.90	232.20	170.40	150.00	
Z	13.0	0.0	29.3	28.2	0.0	. 70.92	0.0	26.3	0.0	0.0	0.0	33.6	0.0	21.9	0.0		0.0	47.3	0.0	0.0	19.4	0.0	0.0	0.0							0.0		0.0	0.0		0.0	0.0	0.0	0.0	0.0		1
生	7.26	6.57	9.02	8.25	7.21	6.71	6.37	9.92	2.89	9.90	7.40	8.19	4.37	8.92	1		5.75	5.23	4.51	6.52	8.53	80.9	6.42	5.52							5.40					8.41	6.07		6.14	19.9	9.93	
J FE	22926.2	34271.8	31053.5	36240.3	3 24136.9	44232.9	27618.4	27059.5	20951.5	27923.3	30305.2	36954.4	18374.2	31370.0			37576.0	37033.7	34721.1	11056.6	1 24082.1	13252.3	13503.0	15509.8				_			134/9.6				_	18929.9	14102.0	10645.6	17639.5	20971.6	1 24739.0	1
EU	1.3411	1.3553	1.4094	2.3107	1.6728	1.6104	1.6296	1.1859	1.1951	1.2440	1.3587		1.4320	1.3847			1.3442	1.3972	1.5613	15.98 0.4454	1.3564	18.23 0.6163	24.99 0.6468	0.5147	1.5273	0.4007			0.7235		0.7527				1.4045	0.6208	9.48 0.4568	3.55 0.5048	7.43 0.8426	0.9401	1.1504	
CS	4.48	3.84	5.66	3.80	8.28	11.69	10.10	20.06	33.21	4.75	3.04	4.58	4.24	80.6	3.18	8.06	4.03	5.32	12.22	15.98	18.98	18.23	24.99	20.93	6.31	12.73	19.90	22.12	0.60	6.95	15 21	15.51	11.41	7.39	4.32	6.77	9.48	13.55	7.43	9.90	4.74	
ANID	OT253	OT254	OT255	OT256	OT257	OT258	OT259	OT262	OT263	OT264	OT265	OT266	OT268	OT269	OT270	OT272	OT273	OT275	OT276	OT489	OT490	OT491	OT492	OT493	OT494	OT495	OT496	OT497	01498	01499	OT501	OT502	OT503	OT504	OT505	OT506	OT507	OT508	OT509	OT510	OT511	i

ANID	macro grp	macro grp Chem2012	CERAMIC TYPE	MATERIAL	SOURCE	E STATE	SITE NAME	SITE NO	AS	ΓA	Π	ND	SM	n	YB (CE CO	O CR
OT514	Group-B	Unas.	Mimbres B/W Style III	Pottery	MURR	MN	Avilas Canyon Village	LA 045000	1.88	29.41	0.3721	23.14	4.18	3.29 2.	2.23 58.02	02 8.20	0 34.61
OT515	Group-B	Unas.	Mimbres B/W Style III	Pottery	MURR	MN	Avilas Canyon Village	LA 045000	2.22	29.73 (0.3584	24.54	4.38	3.12 2.	2.80 61.37	37 9.10	0 35.38
OT516	Group-B	Unas.	Mimbres B/W Style III	Pottery	MURR	NM	Avilas Canyon Village	LA 045000	4.10	39.62	0.4869	22.95		6.65 2.	2.67 79.85	85 10.77	7 28.34
OT517	Group-A	Mimbres-01	Mimbres B/W Style III	Pottery	MURR	NM	Avilas Canyon Village	LA 045000	1.73	49.43			3.79 12	12.62 2.	2.55 81.06	06 3.11	
OT518	Group-A	Mimbres-01	Mimbres B/W Style III	Pottery	MURR	NN	Avilas Canyon Village	LA 045000	1.58				1				
OT538	Group-C2a	Mimbres-49A	Tularosa Smudged Corruga Pottery	Pottery	MURR	M	Old Town	LA 001113	4.00	35.75 (2.34 2.		66 12.58	
OT544	Group-A	Mimbres-03	Tularosa B/W	Pottery	MURR	M	Old Town	LA 001113	2.66	44.00	1.3437		11.09	7.47 10.	10.00 91.78	78 2.25	
OT548	Group-D	El Paso Core	El Paso Polychrome	Pottery	MURR	ΣN	LA 015062	LA 015062	2.76			1			1		
OT549	Group-D	El Paso Core	El Paso Polychrome	Pottery	MURR	NM	LA 015062	LA 015062	4.65		0.3952		7.55 4			12 7.75	
OT550	Group-D	El Paso Core	El Paso Polychrome	Pottery	MURR	MN	LA 015062	LA 015062	3.80	39.13					3.54 75.45		
OT551	Group-D	El Paso Core	El Paso Polychrome	Pottery	MURR	MN	LA 015062	LA 015062	2.07	54.39 (0.5412	20.69	8.35	3.52 4.	4.04 109.22	22 7.34	4 32.05
OT561	Group-D	El Paso Core	El Paso Polychrome	Pottery	MURR	MN	Simon Ranch	LA 014983	96.3	56.01	0.5726	45.84	9.10	2.72 4.	4.44 95.59	59 5.45	5 27.37
OT562	Group-D	El Paso Core	El Paso Polychrome	Pottery	MURR	MN	Simon Ranch	LA 014983	5.30	76.93	0.7183	58.52	10.37 E	5.21 5.	5.57 152.52	52 6.44	4 30.53
OT564	Clay		Clay	Clay	MURR	MN		EMAP CS-1c	3.01	56.92	0.7239	66.32	10.69	2.75 5.	5.03 36.71	71 1.22	2 2.37
OT565	Clay		Clay	Clay	MURR	MN		EMAP CS-3a	2.76	53.05	0.2890	60.09	7.98	2.71 1.	1.99 43.00	00 7.79	9 42.29
OT566	Clay		Clay	Clay	MURR	Ž		EMAP CS-3b	4.48	34.67	0.4343	36.66	6.21	3.14 2.	2.91 35.54	54 7.44	4 114.80
OT567	Clay		Clay	Clay	MURR	MN		EMAP CS-5	11.16	34.86	0.4415		5.39	3.70 3.	3.05 72.32	32 20.76	
OT568	Clay		Clay	Clay	MURR	MN		EMAP CS-6a	4.34	45.28 (0.2854	53.08	7.10	1.57 2.	2.12 57.71	71 9.57	7 18.14
0T569	Clay		Clay	Clay	MURR	MN		EMAP CS-6b	2.64	47.91 (0.3085	66'19	9.68	1.26 2.	2.29 68.95	95 11.89	9 21.67
OT570	Clay		Clay	Clay	MURR	MN		EMAP CS-7	3.69	44.14 (0.4611	36.00	7.26	3.40 3.	3.42 60.14	14 12.75	5 77.65
OT571	Clay		Clay	Clay	MURR	MN		EMAP CS-8	1.25	37.90	0.3302	30.00	5.80	2.29 2.	2.46 50.34	34 9.83	3 108.88
OT572	Clay		Clay	Clay	MURR	MN		EMAP CS-9	2.82	31.81	0.4274	21.28	5.12	3.74 2.	2.95 37.31	31 14.37	7 118.98
OT573	Clay		Clay	Clay	MURR	M		EMAP CS-10	4.45	36.24	0.3998	28.93	5.50 4	4.09 2.	2.82 76.02	02 16.95	5 91.82
OT574	Clay		Clay	Clay	MURR	MN		EMAP CS-13	7.73	20.50	0.3263	16.56	3.69	1.80 2.	2.39 104.86	86 17.71	1 73.84
01575	Clay		Clay	Clay	MURR	MN		EMAP CS-13I	00'9	33.92	0.3811	26.89	5.53	3.39 2.	2.75 47.69	69 17.73	3 74.86
OT576	Clay		Clay	Clay	MURR	NM		EMAP CS-178	1.35	40.03				2.38 2.		39 9.99	
OT577	Clay		Clay	Clay	MURR	NM		EMAP CS-17I								39 17.12	
OT578	Clay		Clay	Clay	MURR	NM		EMAP CS-18	8.88					1.94 2.			1 119.70
OT579	Clay		Clay	Clay	MURR	M		EMAP CS-20I	7.01	45.60 (22.68	5.77	4.13 2.	2.62 69.89	89 10.60	
OT580	Clay		Clay	Clay	MURR	M		EMAP CS-21I	5.18	25.08 (0.3090	34.46				05 14.87	7 42.56
OT581	Clay		Clay	Clay	MURR	M		EMAP CS-54	2.52								
OT582	Clay	Unas. C2	Clay	Clay	MURR	ĭ	EMAP CS-57	EMAP CS-57	2.02								
OT583	Clay		Clay	Clay	MURR	M		EMAP CS-59	10.68		0.3594	29.10				30 14.64	4 91.69
OT584	Group-C1	Unas.	Mimbres B/W Style Indeter. Pott	Pottery	MURR	ΑZ	Rising	AZ FF:12:48	0.00	37.59	0.3012	26.26	5.25 (0.89 2.	2.40 52.54	54 11.78	8 71.33
OT586	Group-B	Unas.	Mimbres B/W Style Indeter. Pottery	Pottery	MURR	ΑZ	Rising	AZ FF:12:48	2.90		0.5339	45.93	8.57	3.08 3.	3.72 38.59	59 4.49	9 19.05
OT587	Group-C1	Unas.	Mimbres B/W Style III	Pottery	MURR	ΑZ	Rising	AZ FF:12:48	0.00	38.94	0.3355	29.23	5.43	1.24 2.	2.40 48.81	_	1 59.59
OT589	Group-B	Unas.	Mimbres B/W Style Indeter. Pottery	Pottery	MURR	ΑZ	Rising	AZ FF:12:48	0.00	42.60	0.5202	23.28	5.24 E	5.40 3.	3.78 33.18	18 5.30	0 31.7
OT590	Group-C1	Unas.	Mimbres B/W Style III	Pottery	MURR	ΑZ	Rising	AZ FF:12:48	00.00	39.93	0.3168	32.52	5.47 (0.86 2.	2.47 49.54	54 8.69	9 31.69
OT591	Group-B2	Mimbres-11	Mimbres B/W Style III	Pottery	MURR	ΑZ	Rising	AZ FF:12:48	2.08	35.29	0.4357	22.67	4.70 4	4.78 2.	2.91 51.88	88 10.97	7 48.86
OTP01X	Group-D	El Paso-2	El Paso Polychrome	Pottery	MURR	NM	Perrault	LA 018891	4.82	48.92	0.5941	37.85		3.64 4.	4.57 99.07	1	6 71.06
OTP03X	Group-D	El Paso Core	El Paso Polychrome	Pottery	MURR	M	Old Town	LA 001113	6.20				9.39	4.49 3.			8 27.67
OTP04X	Group-D	El Paso Core	El Paso Polychrome	Pottery	MURR	M	Old Town	LA 001113	6.31								_
OTP05X	Group-D	El Paso-2	El Paso Polychrome	Pottery	MURR	M	Old Town	LA 001113	8.96						_	_	
OU0002	Group-B	Unas.	Mimbres B/W Style I	Pottery	MURR	MN	DAP3	LA 153386	2.46	34.74 (0.4882	37.98 1	10.47	7.95 3.	3.33 90.56	56 9.82	2 34.33

837.5 1192A.3 3.490 2343.0 447.1 1624.1 2871.0 76.70 921.1 7330.8 3.440 2813.3 864.7 12041.2 3401.1 65.00 921.1 7330.8 3.460 2813.1 864.7 12041.2 3401.1 65.00 922.2 7785.4 2.69 2716.0 2.20 144.0 30.20 356.6 13299.6 12.95 50440.5 714.9 553.9 140.3 25.0 919.3 13191.6 10.673 2884.7 567.4 1609.6 62.39 72.40 777.4 12791.9 4.024 3.084.3 56.28 95.0.5 95.0.5 96.30 700.0 1283.6 1.046.3 3.0105.1 57.0 16.30 97.0	ZR AL 171.5 92012.4	TB TH ZN ZR AL 0.61 14.44 54.3 171.5 92012.4	8.67 376.5 1.0138 0.61 14.44 54.3 171.5 92012.4	132.90 0.3293 8.67 376.5 1.0138 0.61 14.44 54.3 171.5 92012.4
921.1 7330.8 3.460 28123.1 884.1 12041.2 3401.1 355.4 4931.0 2.903 23487.0 282.0 20409.6 1147.7 355.4 4931.0 2.903 23487.0 282.2 20409.6 1147.7 356.6 17260.0 2.973 2784.3 649.8 1315.5 330.6 919.3 177.4 12791.9 4.460 31054.0 517.4 16716.9 5623.8 720.0 12833.6 4.024 26202.3 515.1 15709.7 5905.5 935.5 10955.5 6.157 30105.1 533.2 13710.8 5172.2 700.1 12833.6 4.024 26202.3 515.1 15709.7 5905.5 935.5 10855.5 6.157 30105.1 533.0 4403.0 3102.0 106.6 9337.4 1441 12509.9 804.4 5905.5 4505.0 107.1 1441 1509.0 1707.0 1707.0 1707.0	142.3	0.47 14.68 56.6 142.3	8.83 408.9 1.1614 0.47 14.68 56.6 142.3	132.60 0.3262 8.83 408.9 1.1614 0.47 14.68 56.6 142.3
35.4 4791.0. 2.703 2746.0. 2040.0. 1147.7 35.4 4791.0. 2.703 2746.0. 222.0. 2040.0. 1147.7 35.6 1795.4 2.667 27167.0 212.7 1877.2 1910.4 356.6 1329.6 12.952 50440.5 714.9 553.48 1403.0 919.3 13191.6 10.673 2984.7 567.4 16609.6 6239.0 777.4 12791.9 4.46 3105.1 533.2 13110.8 517.2 700.1 1283.6 4.024 2620.3 515.7 1570.9 569.5 935.5 1085.5 6.157 30105.1 333.0 1441.1 320.6 623.0 106.6 9937.4 7.14 12509.9 86.4 1893.0 349.5 107.1 1082.4 4.26 4.30 2317.1 306.3 326.6 429.6 107.4 1082.4 4.27 2.048.7 344.1 322.0 4440.1	45.5 186.5 88078.6	0.51 26.41 45.5 186.5	7.37 185.3 1.6666 0.51 26.41 45.5 186.5	185.3 1.6666 0.51 26.41 45.5 186.5
17260.0 4.391 27934.3 649.8 13155.5 3309.6 13299.6 12.952 50440.5 714.9 5534.8 1403.0 13191.6 10.673 29844.7 567.4 16609.6 6239.0 12791.9 4.40 31054.0 517.4 16716.9 5652.8 12833.6 4.04 28020.3 515.7 15709.7 5909.5 10855.5 6.157 30105.1 533.2 13710.8 5172.2 9937.4 7.146 31448.1 254.5 15568.9 3495.0 10882.4 7.80 33345.2 587.6 14641.3 4294.8 1336.3 8.403 38116.3 358.6 6486.7 349.6 45743.2 5.599 8981.3 138.4 66.4 893.0 3449.5 2796.6 4.598 19281.6 35.7 1449.1 322.6 45743.2 5.599 8981.3 313.0 3449.5 2796.6 4.598 1428.7 4		0.34 49.59 49.8	4.51 181.2 2.3831 0.34 49.59 49.8	206.70 0.5192 4.51 181.2 2.3831 0.34 49.59 49.8
82980.0 356.6 13299.6 12.952 50440.5 714.9 5534.8 1403.0 75742.2 919.3 13191.6 10.673 29844.7 567.4 16609.6 6230.0 7742.2 919.3 13191.6 10.673 2984.7 567.6 16609.6 6239.0 97481.2 777.4 12791.9 4.460 31054.0 515.7 1570.9 5995.9 9117.1 720.0 12.855.6 7202.3 515.7 1570.9 5995.9 84524.4 1134.5 10882.4 7.146 3148.1 254.5 1568.9 3495.0 88370.9 206.4 9625.9 3.907 2770.6 20.3 3348.3 3495.0 8870.9 206.4 3520.0 4.748 3828.4 6.44 599.5 4576.9 7994.4 366.6 4.30 3816.4 4.27 20.4 26.7 3449.5 8806.4 36.7 370.4 3828.4 6.44 599.5 457.6		0.80 13.21 96.8	10.37 651.4 1.1617 0.80 13.21 96.8	115.90 0.5843 10.37 651.4 1.1617 0.80 13.21 96.8
97481.2 777.4 12791.9 4.40 31054.0 517.4 1471.0 562.8 83791.1 720.0 12833.6 4.024 26202.3 515.7 15709.7 5909.5 91175.1 935.5 10955.5 6.157 30105.1 533.2 13710.8 5172.2 86366.6 706.6 9937.4 7.146 31448.1 254.5 15568.9 3495.0 84524.4 1134.5 10882.4 7.880 33345.2 587.6 14641.3 4294.8 8370.2 1516.1 1438.3 38116.3 3348.2 14641.3 4294.8 68370.9 206.4 9625.9 3.901 27707.6 203.3 3448.3 2878.8 68370.9 206.4 3828.4 66.4 180.1 4275.7 1769.0 4275.7 1769.0 4275.7 1769.0 4275.0 4275.0 4275.0 4275.0 4275.0 4275.0 4275.0 4275.0 4275.0 4275.0 4275.0 4275.0 4275.0	169.8 1	2.19 34.90 169.8 1 96 21 49 82 4	6.04 83.1 2.2950 2.19 34.90 169.8 9.56 306.2 3.4788 1.96 21.49 82.4	306.2 3.4788 1.96 21.49 82.4
83791.1 720.0 12833.6 4.024 26202.3 515.7 15709.7 5909.5 91175.1 935.5 10955.5 6.157 30105.1 533.2 13710.8 5172.2 86366.6 706.6 9937.4 7.146 31448.1 254.5 15568.9 3495.0 84224.4 1134.5 10882.4 7.880 33345.2 887.6 14641.3 4204.8 83266.6 706.6 9937.4 7.146 31448.1 254.6 346.2 3132.6 68370.9 206.4 9625.9 3.907 27707.6 203.3 3648.3 2878.8 72747.2 107.7 7935.9 4.141 12509.9 86.4 1801.6 4275.0 80624.5 138.7 22796.6 4.59 19281.6 35.7 2048.5 4648.0 77.2 12784.8 4.59 14282.7 479.6 6468.2 4037.0 99227.6 30.0 3702.7 4.59 1444.8 3.850 138.3	72.9	0.86 24.64 72.9	9.32 422.6 2.8278 0.86 24.64 72.9	97.30 0.5496 9.32 422.6 2.8278 0.86 24.64 72.9
91175.1 935.5 10955.5 6.157 30105.1 533.2 13710.8 5172.2 86366.6 706.6 9937.4 7.146 31448.1 254.5 15568.9 3495.0 84224.4 1134.5 10882.4 7.880 33345.2 587.6 14641.3 4294.8 83426.2 1516.1 14336.3 8.403 38116.3 358.6 6486.7 3132.6 68370.9 206.4 9625.9 3.907 27707.6 203.3 3648.3 2878.8 7959.0 210.7 7935.0 4.141 1250.9 86.4 1801. 4275.0 7954.0 17.2 12784.8 4.245 6188.7 261.6 475.9 100170.9 387.1 4598.4 6.48.5 454.0 475.9 484.0 10070.0 387.2 4.743 1722.1 484.0 475.1 474.1 475.0 466.8 403.0 474.1 475.0 466.8 403.0 403.0 474.1 476.0 <	61.5	0.64 22.30 61.5	8.57 374.4 2.7496 0.64 22.30 61.5	89.20 0.5010 8.57 374.4 2.7496 0.64 22.30 61.5
86366.6 706.6 9937.4 7.146 31448.1 254.5 15568.9 3495.0 84524.4 1134.5 10882.4 7.146 31448.1 254.5 1566.1 4641.3 4294.8 84376.2 1516.1 14336.3 8.403 3345.2 587.6 14641.3 4294.8 8370.2 206.4 9625.9 3.907 27707.6 203.3 3648.3 2879.8 79597.0 219.6 35240.6 4.194 3828.4 684.1 801.6 4275.7 7994.4 708.1 6794.6 4.340 23217.1 306.3 7263.6 4297.7 65715.1 381.3 45743.2 5.59 8981.3 1387.3 4149.1 276.7 53480.6 77.2 12784.4 4.25 6198.7 261.6 468.8 497.5 4691.6 475.9 65715.1 381.3 4.52 6198.7 3187.3 4140.1 378.0 474.5 474.5 474.6 473.4 475.6		1.07 18.02 79.5	9.74 216.1 2.3478 1.07 18.02 79.5	109.70 0.5664 9.74 216.1 2.3478 1.07 18.02 79.5
84524.4 1134.5 10882.4 7.880 33345.2 587.6 14641.3 4294.8 83426.2 1516.1 14336.3 8.403 3816.3 386.6 6486.7 3132.6 68370.9 206.4 9625.9 3.907 27707.6 203.3 3648.3 2879.8 72747.2 107.7 79395.9 4.714 12509.9 86.4 1801.6 4275.7 79597.0 219.6 35240.6 4.194 38828.4 6.848.7 5691.6 65715.1 381.3 45743.2 5.59 8981.3 386.7 4293.0 3445.5 53480.6 77.2 12784.4 4.25 6198.7 261.4 2797.6 4293.0 3445.5 53480.6 77.2 12784.4 4.25 6198.7 493.0 3445.5 53480.6 770.6 4.59 19281.6 35.4 493.0 494.5 65715.1 381.3 4.25 1988.7 494.5 494.6 423.0 444.5 <	65.0	1.14 22.17 65.0	7.96 158.7 2.5336 1.14 22.17 65.0	118.30 0.7117 7.96 158.7 2.5336 1.14 22.17 65.0
8346a. 1516.1 14336.3 8.403 88110.3 358.6 0486.7 3142.0 68370.9 206.4 9625.9 3.907 27707.6 203.3 3648.3 2879.8 72747.2 107.7 79395.9 4.714 12509.9 86.4 1801.6 4275.7 79597.0 219.6 35240.6 4.194 38828.4 634.4 599.5 4576.9 79984.4 708.1 67964.6 4.340 23217.1 306.3 7263.6 4293.0 100170.9 354.4 39937.8 6.198.7 261.4 2897.7 5269.6 55406.6 4.59 19281.4 6.29 1449.1 3226.4 55406.6 4.59 19281.4 6.29 1449.5 4293.0 66747.5 138.7 27796.6 4.58 19281.4 6.24 4847.5 80624.5 302.0 46908.9 3.900 37022.7 529.1 4395.0 4284.0 61404.0 474.3 17704.4	82.1	1.38 29.64 82.1	8.18 230.8 3.5151 1.38 29.64 82.1	128.60 0.6958 8.18 230.8 3.5151 1.38 29.64 82.1
08370.7 200.4 9025.9 3.907 1710.0 203.3 3646.3 2874.3 72747.2 107.7 79395.9 4.714 12509.9 86.4 1801.6 4275.7 79597.0 219.6 35240.6 4.149 38828.4 634.4 599.5 4576.9 79984.4 708.1 67964.6 4.340 23217.1 306.3 7263.6 4293.0 100170.9 354.4 39937.8 4.725 6198.7 261.4 2897.7 569.6 65715.1 381.3 45743.2 5.59 8983.3 1349.5 561.6 55340.6 77.2 12784.4 4.579 1928.7 499.6 6468.2 4037.9 6575.6 110.0 1944.8 3.850 1368.3 55.4 1970.0 4526.6 61404.0 47.3 17704.4 1.726 14699.9 156.4 349.5 365.6 667.6 61855.0 111.0 19444.8 3.850 386.3 386.7 <td< td=""><td>1.00</td><td>1.53 22.01</td><td>6.61 960.4 1.3560 1.53 22.01</td><td>16/./0 0.4664 6.61 960.4 1.3560 1.53 22.01</td></td<>	1.00	1.53 22.01	6.61 960.4 1.3560 1.53 22.01	16/./0 0.4664 6.61 960.4 1.3560 1.53 22.01
72/47.2 107.1 7995.9 4.714 1230.9 86.4 1801.0 4275.7 79597.0 219.6 35240.6 4.194 3828.4 634.4 599.5 4576.9 79984.0 2354.6 4.340 23271.1 306.3 7263.6 429.0 100170.9 354.4 39937.8 4.925 6198.7 261.4 2897.7 5676.6 5340.6 77.2 12784.4 5.59 8981.3 1387.3 4149.1 3226.4 5340.6 77.2 12786.6 4.59 19281.6 35.9 2048.5 459.6 5340.6 77.2 12786.4 4.59 19281.6 448.5 4484.5 80624.5 302.0 46908.9 3.900 37022.7 529.1 3736.0 365.8 61404.0 474.3 17704.4 1.726 14699.9 156.4 365.0 4498.8 85801.8 885.8 54524.0 2.75 25014.4 497.2 1449.8 385.8	74.9	0.74 12.19	10.37 85.8 0.9136 0.74 12.19	161.60 0.4141 10.37 85.8 0.9136 0.74 12.19
79597.0 279,6 352,40.6 4.194 38828.4 634.4 599.5 457.6 79984.4 708.1 67964.6 4.340 23217.1 306.3 7263.6 4293.0 100170.9 354.4 39937.8 4.925 6198.7 261.4 2897.7 5691.6 65715.1 381.3 45743.2 5.599 8981.3 1387.3 4149.1 3226.4 53400.6 77.2 127848.4 4.256 4.599.6 5498.5 2449.5 80624.5 330.1 85458.4 4.594 19281.2 529.1 3736.0 3449.5 99227.6 360.4 4.599.8 1.702.7 499.6 6468.2 4840.0 99227.7 30.4 1.726 1469.9 1.56.4 3441.0 370.2 61404.0 4.44.4 1.726 1469.9 1.56.4 3470.0 352.8 61404.0 4.44.4 1.726 1469.9 1.56.4 344.0 370.1 85801.8 885.8	74.0	0.86 11.36	14.04 455.2 1.0744 0.86 11.36	103.00 0.5359 14.04 455.2 1.0744 0.86 11.36
7984.4 708.1 67964.6 4.340 23217.1 306.3 7263.6 4293.0 100170.9 354.4 39937.8 4.925 6198.7 261.4 2897.7 5691.6 65715.1 381.3 45743.2 5.599 8981.3 4149.1 3226.4 53480.6 77.2 127848.4 4.259 19281.6 35.9 2048.5 4844.0 79926.3 303.1 85458.4 4.594 14282.7 499.6 6468.2 4037.9 99227.6 303.0 46908.9 3702.7 529.1 19797.0 3494.0 99227.6 303.1 8545.4 1740.5 156.4 487.0 365.8 484.0 105781.0 1444.8 3.850 136.3 345.2 526.6 4498.8 82636.7 62.7 1469.9 154.4 497.2 14680.0 3170.4 82636.7 62.7 1469.9 154.4 497.2 1444.8 385.8 82636.7 61.4 <td< td=""><td>54.4</td><td>0.67 12.22</td><td>15.82 0.0 1.1890 0.67 12.22</td><td>245.60 0.8097 15.82 0.0 1.1890 0.67 12.22</td></td<>	54.4	0.67 12.22	15.82 0.0 1.1890 0.67 12.22	245.60 0.8097 15.82 0.0 1.1890 0.67 12.22
100170.9 354.4 39937.8 4.925 6198.7 261.4 2897.7 5691.6 65715.1 381.3 45743.2 5.599 8981.3 1387.3 4149.1 3226.4 53480.6 77.2 12784.8 4.275 838.4 66.4 893.0 3449.5 80624.5 138.7 22796.6 4.598 19281.6 35.9 2048.2 4037.9 99227.6 303.1 85458.4 4.549 14282.7 499.6 6468.2 4037.9 99227.6 303.1 85468.4 1.726 14699.9 156.4 3451.5 265.6 85807.7 304.0 2759 2504.4 497.2 14686.0 395.8 8626.6 47.3 3702.0 17440.5 30.4 499.8 365.6 888927.7 580.6 9055.9 4.377 39900.2 260.4 1498.8 105781.0 189.2 20503.4 4.257 10499.3 458.7 836.6 526.0 2	73.6	0.94 8.79	6.86 461.8 0.7427 0.94 8.79	121.40 0.5379 6.86 461.8 0.7427 0.94 8.79
65715.1 381.3 45743.2 5.599 8981.3 1387.3 4149.1 3226.4 53480.6 77.2 177848.4 4.275 8384.4 66.4 893.0 3449.5 80624.5 138.7 22796.6 4.598 19281.6 35.9 2048.5 4840.0 7926.3 303.1 8458.4 4.549 1428.7 499.6 6468.2 4037.9 9927.6 302.0 46908.9 3.900 3702.7 529.1 3736.0 365.2 61404.0 474.3 17704.4 1.280 1368.3 553.4 1977.0 4524.6 82630.7 62.7 31823.3 3.290 1740.5 30.4 2690.6 479.8 82631.7 580.6 9055.9 4.257 10499.3 469.6 401.6 479.8 82634.7 62.7 31823.3 3.290 1740.5 30.4 269.0 4749.8 82634.8 47.5 14699.0 156.4 479.2 1468.0 479.	1.001	1.04 9.24	8.42 390.4 0.8700 1.04 9.24	390.4 0.8700 1.04 9.24
53480.6 77.2 127848.4 4.275 8384.4 66.4 893.0 3449.5 80624.5 138.7 22796.6 4.598 19281.6 35.9 2048.5 484.0 79926.3 333.1 88458.4 4.549 1428.7 499.6 6468.2 4037.9 99277.6 332.0 46608.9 3.900 3702.7 529.1 3736.0 3952.8 61404.0 474.3 177704.4 1.726 14699.9 156.4 3477.0 4524.6 88501.8 885.8 54524.0 2.759 25014.4 497.2 14680.0 3170.4 88921.7 580.6 9055.9 4.257 10499.2 2690.6 4498.8 105781.0 189.2 2060.3 4.257 10499.2 36.7 4749.8 889.1.6 910.9 40394.5 3.682 156.3 460.6 4448.8 880.1.8 34992.9 3.940 15411.3 697.4 4998.8 4997.8 88171.6	1.99	1.02 11.36	11.57 97.6 0.8730 1.02 11.36	1.2877 11.57 97.6 0.8730 1.02 11.36
80624.5 138.7 22796.6 4.598 19281.6 35.9 2048.5 4844.0 79926.3 303.1 85458.4 4.549 14282.7 499.6 6468.2 4037.9 99227.6 302.0 46908.9 3.900 3702.7 529.1 3736.0 3952.8 61855.0 111.0 19444.8 3.850 1368.3 553.4 19797.0 4524.6 61404.0 474.3 17704.4 1.726 14699.9 156.4 3451.5 2656.6 85801.8 885.8 54524.0 2.759 27014.4 497.2 14686.0 3170.4 882636.7 62.7 31823.3 3.290 17440.5 30.4 2690.6 4498.8 88271.7 580.6 9055.9 4.377 3990.2 260.4 1377.7 449.8 105787.0 1892.2 17049.3 458.7 886.6 4788.1 88771.4 910.9 40394.5 3.682 15623.6 160.9 1765.0 3157.7 </td <td>79.4</td> <td>0.83 9.26</td> <td>10.51 241.9 0.8736 0.83 9.26</td> <td>241.9 0.8736 0.83 9.26</td>	79.4	0.83 9.26	10.51 241.9 0.8736 0.83 9.26	241.9 0.8736 0.83 9.26
79926.3 303.1 85458.4 4.549 14282.7 499.6 6468.2 4037.9 99227.6 302.0 46908.9 3.900 37022.7 529.1 3736.0 3952.8 61855.0 111.0 19444.8 3.850 1368.3 553.4 19797.0 4524.6 61404.0 474.3 17704.4 1.726 14699.9 156.4 3451.5 2656.6 85801.8 885.8 54524.0 2.759 25014.4 497.2 14686.0 3170.4 882636.7 62.7 31823.3 3.290 17440.5 30.4 2690.6 4498.8 88921.7 580.6 9055.9 4.377 3990.2 260.4 1357.7 4749.8 105787.0 1897.2 1708.8 681.6 4098.3 3857.8 882.1 8474.6 910.9 40394.5 3.682 1562.3 60.9 14663.9 4015.6 8974.4 991.6 1560.8 3496.5 6.752 1844.9 1750.9 <td>53.8</td> <td>0.76 12.07</td> <td>14.26 83.0 1.2163 0.76 12.07</td> <td>83.0 1.2163 0.76 12.07</td>	53.8	0.76 12.07	14.26 83.0 1.2163 0.76 12.07	83.0 1.2163 0.76 12.07
99227.6 302.0 46908.9 3.900 3702.7 529.1 3736.0 3952.8 61855.0 111.0 19444.8 3.850 1368.3 553.4 19797.0 4524.6 61404.0 474.3 177704.4 1.726 14699.9 156.4 3451.5 2656.6 85801.8 885.8 54524.0 2.759 25014.4 497.2 14686.0 3170.4 82636.7 62.7 31823.3 3.290 17440.5 30.4 2690.6 4498.8 88921.7 580.6 9055.9 4.377 1990.2 260.4 1377.7 1449.8 105787.0 1892.2 2050.3 4.58.7 886.6 488.7 92421.8 806.8 34992.9 3.940 1541.3 690.9 1468.9 94330.6 828.4 8416.3 3.592 1562.3 650.9 1468.9 3157.7 88776.4 991.5 13661.4 3.590.9 1590.9 1408.5 3157.7 88776.4	0.09	0.80 11.09	14.79 461.1 1.2242 0.80 11.09	461.1 1.2242 0.80 11.09
61855.0 111.0 19444.8 3.850 1368.3 553.4 19797.0 4524.6 61404.0 474.3 177704.4 1.726 1469.9 156.4 3451.5 2656.6 85801.8 885.8 54524.0 2.759 25014.4 497.2 14686.0 3170.4 82636.7 62.7 31823.3 3.290 17440.5 30.4 2690.6 4498.8 88921.7 580.6 9055.9 4.377 39900.2 260.4 1357.7 4498.8 105787.0 1892.2 20503.4 4.257 1049.9 3.64 4982.1 92421.8 806.8 34992.9 3.940 1541.3 697.4 9953.3 3857.8 84714.6 910.9 40394.5 3.682 1562.3 60.9 14663.9 4015.6 59043.3 122.0 13661.4 3.599 519.7 1750.9 3157.7 88776.4 991.6 15203.8 3.60 29452.8 965.5 18484.9 2437.6 <td>1.95</td> <td>0.62 10.23</td> <td>15.94 155.8 1.1106 0.62 10.23</td> <td>253.30 1.1671 15.94 155.8 1.1106 0.62 10.23</td>	1.95	0.62 10.23	15.94 155.8 1.1106 0.62 10.23	253.30 1.1671 15.94 155.8 1.1106 0.62 10.23
61404.0 474.3 177704.4 1.726 14699.9 156.4 3451.5 2656.6 85801.8 885.8 54524.0 2.759 25014.4 497.2 14686.0 3170.4 82636.7 62.7 31823.3 3.290 17440.5 30.4 2690.6 4498.8 88271.7 580.6 9055.9 4.377 39900.2 260.4 1357.7 4749.8 105787.0 189.2 20503.4 4.257 10499.3 458.7 886.6 4282.1 92421.8 806.8 34992.9 3.940 15411.3 697.4 9953.3 3857.8 84714.6 910.9 40394.5 3.62 1562.3 60.9 14663.9 4015.6 59043.3 122.0 13661.4 3.599 7708.8 681.6 4098.5 3850.6 93330.6 828.4 8415.3 3.942 22760.6 1240.7 20370.9 2163.0 89716.8 1072.5 13665.2 6.752 3899.9 519.7<	38.6	0.76 9.52	10.78 93.4 1.1795 0.76 9.52	9.00 0.3648 10.78 93.4 1.1795 0.76 9.52
85801.8 885.8 54524.0 2.759 25014.4 497.2 14686.0 3170.4 82636.7 62.7 31823.3 3.290 17440.5 30.4 2600.6 4498.8 88927.7 580.6 9055.9 4.377 39900.2 260.4 1357.7 4749.8 105787.0 189.2 20503.4 4.257 10499.3 458.7 836.6 4282.1 92427.8 806.8 34992.9 3.940 15411.3 697.4 9953.3 3857.8 84714.6 910.9 40394.5 3.62 15623.6 60.9 14085.9 4015.6 59043.3 122.0 136614.4 3.599 7708.8 681.6 4098.5 3850.6 93330.6 828.4 8415.3 3.924 22760.6 1240.7 20370.9 2163.0 89716.8 1072.5 13661.2 8.752 8945.7 1750.9 3157.7 89735.7 4961.1 16806.3 3.444.9 258.5 12650.9 31	41.3	0.38 2.70	6.25 373.0 0.2969 0.38 2.70	46.60 1.9586 6.25 373.0 0.2969 0.38 2.70
82636.7 62.7 31823.3 3.290 17440.5 30.4 2690.6 4498.8 88921.7 580.6 9055.9 4.377 39900.2 260.4 1357.7 4749.8 105787.0 189.2 20503.4 4.257 1049.3 458.7 886.6 4822.1 92427.8 806.8 34992.9 3.940 1541.3 697.4 9953.3 3857.8 84714.6 910.9 40394.5 3.682 15623.6 509.9 14663.9 4015.6 59043.3 122.0 136614.4 3.599 7708.8 681.6 4098.5 3850.6 93330.6 828.4 8415.3 3.924 22760.6 1240.7 20370.9 2163.0 88776.4 991.6 15203.8 3.604 29452.8 965.5 1848.9 2437.6 95515.1 865.9 11185.1 3.70 2859.4 575.1 15765.9 3344.4 95515.1 865.9 14441.9 258.5 156.6 3344.4 <td>58.6</td> <td>0.44 3.22</td> <td>9.13 707.2 0.3462 0.44 3.22</td> <td>74.50 0.6127 9.13 707.2 0.3462 0.44 3.22</td>	58.6	0.44 3.22	9.13 707.2 0.3462 0.44 3.22	74.50 0.6127 9.13 707.2 0.3462 0.44 3.22
88927.7. 580.6 9055.9 4.377 39900.2 260.4 135.7. 4449.8 105787.0 189.2 20503.4 4.257 10499.3 458.7 836.6 4282.1 92421.8 806.8 34992.9 3.940 15411.3 697.4 9953.3 3857.8 84714.6 910.9 40394.5 3.62 15623.6 509.9 14663.9 4015.6 59043.3 122.0 136614.4 3.599 7708.8 681.6 4098.5 3850.6 93330.6 828.4 8415.3 3.924 22760.6 1240.7 20370.9 2163.0 89716.8 1072.5 13665.2 6.752 33909.9 519.7 1750.9 3157.7 88778.4 99.1 15203.8 3.64 9455.1 15484.9 2437.6 95515.1 865.3 11185.1 3.79 28594.5 751.1 15765.9 3344.4 95515.1 865.2 11185.1 3.79 28594.5 156.6 971.	7.79	0.49 11.09	15.49 92.6 1.0635 0.49 11.09	119.20 0.5970 15.49 92.6 1.0635 0.49 11.09
105787.0 1892.2 20503.4 4.257 10499.3 458.7 886.6 4282.1 92421.8 806.8 34992.9 3.940 1541.3 697.4 9953.3 3857.8 84714.6 910.9 40394.5 3.682 15623.6 509.9 14663.9 4015.6 59043.3 122.0 136614.4 3.599 7708.8 681.6 4098.5 3850.6 93330.6 828.4 8415.3 3.924 22760.6 1240.7 20370.9 2163.0 88778.4 991.6 15203.8 3.604 29452.8 965.5 18484.9 2437.6 80415.4 496.1 6806.3 4.346 2945.8 1556.9 3157.7 8935.5 14185.1 3.231 29079.3 1308.5 1353.5 2971.5 8933.7 1463.9 15405.6 5.234 1336.4 5971.5 84705.0 17050.6 5.548 24360.0 323.4 4967.0 95515.1 865.2 1436.	80.2	0.76 13.55	11.79 51.9 1.0694 0.76 13.55	348.50 0.6865 11.79 51.9 1.0694 0.76 13.55
92421.8 806.8 34992.9 3.940 15411.3 697.4 9953.3 3857.8 84714.6 910.9 40394.5 3.682 15623.6 509.9 14663.9 4015.6 59043.3 122.0 136614.4 3.599 7708.8 681.6 4098.5 3850.6 93330.6 828.4 8415.3 3.924 22760.6 1240.7 20370.9 2163.0 89716.8 1072.5 13665.2 6.752 33909.9 519.7 17750.9 3157.7 88778.4 991.6 15203.8 3.604 29452.8 965.5 18484.9 2437.6 80415.4 496.1 6806.3 4.346 34441.9 258.5 12656.9 3344.4 95515.1 852.9 11185.1 3.709 28594.5 751.1 15765.7 2518.2 89835.7 481.8 9431.3 3.21 29079.3 1308.5 11353.5 2971.5 88937.6 1163.9 15405.6 5.548 2436.0 435.5 16590.8 4776.0 94150.4 650.4 15371.5 3.790 27233.9 443.1 15998.1 4867.9 104162.9 746.3 15227.6 6.312 23733.3 76.7 12086.4 4646.2 865.8 4 658.4 656.7 17657.6 4217.7 1507.1 18046.5 3113.0	66.1	0.74 2.66	13.81 268.4 0.3003 0.74 2.66	49.50 0.1977 13.81 268.4 0.3003 0.74 2.66
84714.6 910.9 40394.5 3.682 15623.6 509.9 14663.9 4015.6 59043.3 122.0 136614.4 3.599 7708.8 681.6 4098.5 3850.6 93330.6 828.4 8415.3 3.924 22760.6 1240.7 20370.9 2163.0 89716.8 1072.5 13965.2 6.752 33909.9 519.7 1750.9 3157.7 88778.4 991.6 15203.8 3.604 29452.8 965.5 18484.9 2437.6 95515.1 862.9 11185.1 3.74 34441.9 258.5 12656.9 3157.7 89835.7 481.8 9431.3 3.21 29079.3 1308.5 1314.4 517.1 88935.6 1163.9 15405.6 7.30 25272.8 523.4 1336.4 5414.0 94150.4 560.4 1576.0 5.548 2436.0 435.5 16590.8 4406.0 94150.4 560.4 15227.6 6.272.3 433.1 15	85.5	0.76 11.03	10.36 458.0 1.0877 0.76 11.03	94.10 0.3718 10.36 458.0 1.0877 0.76 11.03
59043.3 122.0 136614.4 3.599 7708.8 681.6 4098.5 3830.6 93330.6 828.4 8415.3 3.924 22760.6 1240.7 20370.9 2163.0 8971.6 1075.5 13965.2 6.752 2760.6 1240.7 20370.9 2163.0 88778.4 991.6 15203.8 3.604 29452.8 965.5 18484.9 2437.6 95515.4 496.1 16806.3 4.346 29452.8 965.5 18484.9 2437.6 95515.4 496.1 16806.3 4.346 29441.9 258.5 12656.9 3157.1 8935.7 481.8 9431.3 3.231 29079.3 1308.5 1353.5 2971.5 88935.7 1163.9 15405.6 5.548 24360.0 435.5 16590.8 4790.0 94150.4 650.4 15371.5 3.70 27233.9 443.1 15998.1 4867.9 86538.4 666.4 1764.6 4.346.2 436.2 <t< td=""><td>75.7</td><td>0.68 9.00</td><td>9.45 627.4 0.8730 0.68 9.00</td><td>80.50 0.3381 9.45 627.4 0.8730 0.68 9.00</td></t<>	75.7	0.68 9.00	9.45 627.4 0.8730 0.68 9.00	80.50 0.3381 9.45 627.4 0.8730 0.68 9.00
9330.6 828.4 8415.3 3.924 22760.6 1240.7 20370.9 2163.0 89776.8 1072.5 13965.2 6.752 3390.9 519.7 17750.9 3157.7 88778.4 991.6 15203.8 3.604 2945.2 896.5 18484.9 2437.6 80415.4 496.1 6806.3 4.346 34441.9 258.5 12656.9 3344.4 95515.1 862.9 11185.1 3.709 28594.5 751.1 1565.9 3344.4 98935.7 481.8 9431.3 3.231 29079.3 1308.5 1715.6 2971.5 88937.6 1163.9 15405.6 5.548 24360.0 435.5 16590.8 4796.0 94150.4 650.4 15371.5 3.790 27233.9 443.1 15998.1 4867.9 8658.8 666.4 1764.6 4504.6 2833.3 461.1 12086.4 44046.2	185.1	0.84 8.80 1	10.31 207.1 0.9796 0.84 8.80 1	53.10 0.9350 10.31 207.1 0.9796 0.84 8.80 1
89716.8 1072.5 13965.2 6.752 33909.9 519.7 17750.9 3157.7 88778.4 991.6 15203.8 3.604 2945.2 965.5 18484.9 2437.6 80415.4 496.1 16806.3 4.346 34441.9 258.5 12656.9 3344.4 95515.1 852.9 11185.1 3.709 28594.5 751.1 15765.7 2518.2 88935.7 481.8 9431.3 3.231 29079.3 1308.5 1336.4 5410.0 84705.0 700.7 17050.6 5.548 24360.0 435.5 16590.8 4796.0 94150.4 460.4 15371.5 3.790 2723.9 435.1 15998.1 4867.9 10416.2 746.3 15227.6 6.312 23733.3 767.1 12086.4 44046.2 8658.8 466.6 7174.6 4676.7 28177.1 592.4 118040.5 4646.2	83.5	0.68 9.34	8.38 377.5 0.7451 0.68 9.34	1.1724 8.38 377.5 0.7451 0.68 9.34
88778.4 991.6 15203.8 3.604 29452.8 965.5 18484.9 2437.6 80415.4 496.1 6806.3 4.346 344119 258.5 12666.9 33444 95515.1 882.9 11185.1 3.709 28594.5 751.1 1576.7 2518.2 89835.7 481.8 9431.3 3.231 29079.3 1308.5 1353.5 2971.5 88937.6 1163.9 15405.6 5.548 5227.8 523.4 11336.4 5414.0 84705.0 7 77050.6 5.548 2350.0 435.5 16590.8 4796.0 94150.4 650.4 15371.5 6.723.2 3733.3 767.1 12086.4 4646.2 8658.8 466.6 1754.5 4.66.7 78177.1 592.4 113046.4 4646.2	75.0	1.35 14.98	9.82 278.5 0.9528 1.35 14.98	131.50 0.6678 9.82 278.5 0.9528 1.35 14.98
80415.4 496.1 6806.3 4.346 3441.9 258.5 12656.9 3344.4 95515.1 852.9 11185.1 3.709 28594.5 751.1 15765.7 2518.2 89835.7 481.8 9431.3 3.231 29079.3 1308.5 11353.5 2971.5 88937.6 1163.9 15405.6 7.130 25272.8 523.4 11336.4 5414.0 84705.0 700.7 7050.6 5.548 24360.0 435.5 16590.8 4796.0 94150.4 650.4 15371.5 3.790 27233.9 443.1 15998.1 4867.9 104162.9 746.3 15227.6 6.312 23733.3 767.1 12086.4 4646.2 865.84 69.6 1754.5 6.312 23733.3 767.1 18040.5 3113.0	88.1	0.80 10.22	7.17 411.8 0.7507 0.80 10.22	411.8 0.7507 0.80 10.22
95515.1 852.9 11185.1 3.709 28594.5 751.1 15765.7 2518.2 89835.7 481.8 9431.3 3.231 29079.3 1308.5 11353.5 2971.5 88937.6 1163.9 15405.6 7.130 25272.8 523.4 11336.4 5414.0 84705.0 700.7 17050.6 5.548 24360.0 435.5 16590.8 4796.0 94150.4 650.4 15371.5 3.790 27233.9 443.1 15998.1 4867.9 104162.9 746.3 15227.6 6.312 23733.3 767.1 12086.4 4646.2 865.8 4 656.6 1754.5 9 4.676, 28177.1 592.4 18040.5 3113.0	47.0	0.74 21.38	7.72 187.2 1.6852 0.74 21.38	187.2 1.6852 0.74 21.38
89835.7 481.8 9431.3 3.231 29079.3 1308.5 11353.5 2971.5 88937.6 1163.9 15405.6 7.130 25272.8 523.4 11336.4 5414.0 84705.0 700.7 17050.6 5.548 24360.0 435.5 16590.8 4796.0 94150.4 650.4 15371.5 3.790 27233.9 443.1 15998.1 4867.9 104162.9 746.3 15227.6 6.312 23733.3 767.1 12086.4 4646.2 865.8 4 656.6 1754.5 9.467.7 78177.1 592.4 1804.6 3113.0	78.6	9.87 8.58 78.6	6.59 393.5 0.6163 0.68 9.58 78.6	393.5 0.6163 0.68 9.58 78.6
88937.6 1163.9 15405.6 7.130 25272.8 523.4 11336.4 5414.0 84705.0 700.7 17050.6 5.548 24360.0 435.5 16590.8 4796.0 94150.4 650.4 15371.5 3.790 27233.9 443.1 15998.1 4867.9 104162.9 746.3 15227.6 6.312 23733.3 767.1 12086.4 4646.2 865.8 4 659.6 1754.5 9 4.676, 28177.1 592.4 1804.0 5 3113.0	. 64.3	0.69 20.32 64.3	8.90 216.8 1.6285 0.69 20.32 64.3	216.8 1.6285 0.69 20.32 64.3
84705.0 700.7 17050.6 5.548 24360.0 435.5 16590.8 4796.0 94150.4 650.4 15371.5 3.790 2723.3 443.1 15998.1 4867.9 104162.9 746.3 15227.6 6.312 23733.3 767.1 12086.4 4646.2 865.8 4 659.6 1754.5 9 4.676, 28177.1 592.4 1804.0 5 3113.0	63.7	1.27 18.05 63.7	15.64 252.7 1.9843 1.27 18.05 63.7	124.80 0.6734 15.64 252.7 1.9843 1.27 18.05 63.7
941504 6504 15371.5 3790 272339 443.1 159981 4867.9 104162.9 746.3 15227.6 6.312 23733.3 767.1 12086.4 4646.2 86538.4 659.6 17545.9 4.626, 28177.1 592.4 18040.5 3113.0		1.01 22.54	8.85 377.3 2.6238 1.01 22.54	84.90 0.5575 8.85 377.3 2.6238 1.01 22.54
104162.9 746.3 15227.6 6.312 23733.3 76.71 12086.4 4646.2 86538.4 659 715.5 4.65 715.5 713.7 159.2 118040.5 313.3	_	0.74 25.43 54.1	8 47 341 0 2 8975 0 74 25 43 54 1	93.30 0.4573 8.47 34.1.0 2.8975 0.74 25.43 54.1
86538 4 659 6 17545 9 4 626 28177 1 592 4 18040 5 3113.0	97.7	1.32 25.43	11 71 413 8 2 7901 1 32 25 87	75.50 0.457.9 0.47 341.0 2.077.9 0.74 25.45
0.51.6 6.51.0 1.7.6 1.7.7 0.50.4 7.51.0 0.7.50 1.00.50.0		0.93 17.56	8.72 326.3 1.2755 0.93 17.56	148.99 0.4613 8.72 326.3 1.2755 0.93 17.56

ANID	macro_grp	Chem2012	CERAMIC TYPE	MATERIAL	SOURCE	STATE	SITE_NAME	SITE_NO	AS	ΓA	nı	ND	SM	n	YB C	CE CO	CR
900000	Group-C1	Mimbres-27	Mimbres B/W Style III	Pottery	MURR		DAP3	LA 153386	4.09	32.69 (0.5951	42.68	8.81	5.91 3.	3.56 92.04	14.53	40.43
800000	Group-A	Mimbres-10		Pottery	MURR	= E	DAP3	LA 153386	4.98	26.87	1.3263 1	100.54 3	33.42	19.79 9.	9.70 196.34	34 8.21	37.34
OU0011	Group-C1	Mimbres-27	Mimbres B/W Style II	Pottery	MURR	MN	DAP3	LA 153386	4.32	31.26 (0.5247	40.53	10.65	7.07	3.60 82.31	12.01	49.51
OU0012	Group-C1	Mimbres-27	=	Pottery	MURR		DAP3	LA 153386	3.39	30.97	0.5008	27.46	8.59	5.44 3.	3.64 58.57		18.03
OU0014	Group-C1	Mimbres-27		Pottery	MURR	MN	DAP3	LA 153386	4.57	37.34 (41.34		10.22 4.	4.73 89.99	99 13.53	42.83
OU0015	Group-C1	Mimbres-27	Mimbres B/W Style I	Pottery	MURR		DAP3	LA 153386	6.74	40.00	0.5190	39.23 1	11.50	7.14 4.	4.36 86.80	30 15.45	40.79
OU0017	Group-A	Mimbres-10	Corrugated	Pottery	MURR		DAP3	LA 153386	7.56	80.02	0.9194	60.69	29.82	11.93 6.	6.42 123.71	7.14	35.15
OU0018	Group-B	Unas.	Three Circle R/W	Pottery	MURR	- N	DAP3	LA 153386	3.86	54.52	0.6338	40.12	14.00 1	14.52 4.	4.93 82.23	23 17.70	52.85
OU0019	Group-A	Mimbres-01*	Mimbres B/W Style III	Pottery	MURR		DAP5	LA 153388	3.08	113.73 (0.4604	48.61 3	34.02 20	20.93 3.	3.16 85.66	56 6.02	10.18
OU0020	Group-A	Unas.	Mimbres Brown Ware	Pottery	MURR		DAP5	LA 153388	4.76	73.03	1.2030	92.24 4	46.52 27	21.27 8.	8.90 121.89	39 8.16	29.20
OU0021	Group-A	Unas.	Mimbres B/W Style III	Pottery	MURR	- N	DAP5	LA 153388	3.39	126.10 (0.5393	41.78 2	25.35 27	21.22	3.64 86.64	54 10.31	26.40
OU0022	Group-C2	Unas.	Mimbres B/W Style III	Pottery	MURR	MN	DAP5	LA 153388	2.93	43.84 (0.4388	33.46	12.72 (0.00	3.12 70.54	54 12.27	26.06
OU0023	Group-C1	Mimbres-27	Mimbres B/W Style III	Pottery	MURR	MN	DAP5	LA 153388	4.67	49.85	0.4581	40.37	14.73 (0.00	3.34 92.36	36 14.95	31.46
OU0025	Group-C1	Mimbres-24	Three Circle R/W	Pottery	MURR	MN	DAP5	LA 153388	4.79	36.42	0.4438	30.99	6.32	1.99 3.	3.23 72.44	14 8.31	36.80
OU0026	Group-C2a	Mimbres-46	Three Circle R/W	Pottery	MURR	MN	DAP5	LA 153388	2.99	41.81	0.3892	33.11		1.56 2.	2.93 86.02	24.85	93.89
OU0027	Group-A	Mimbres-10	Plain	Pottery	MURR		LA 050180	LA 050180							5.00 88.27	27 13.14	
OU0028	Group-A	Mimbres-10	Incised	Pottery	MURR	MN	LA 050180	LA 050180	3.99	107.82	1.2610	88.84 2	20.40	9.06 10.	10.32 189.71	71 5.62	34.96
OU0029	Group-C1	Mimbres-24	Mogollon R/B	Pottery	MURR	MN	LA 050180	LA 050180	4.36		0.4459		6.75	1.88 3.	3.49 73.11	11 13.83	28.23
OU0031	Group-A	Mimbres-10	Red Ware	Pottery	MURR	MN	LA 050180	LA 050180	3.50	37.41 (0.2927	37.02	6.93	2.72 2.	2.22 76.89	39 10.15	26.03
OU0032	Group-A	Mimbres-10	Red Ware	Pottery	MURR		LA 050180	LA 050180	2.74	107.55 (0.9840	82.06	16.91		8.26 172.90	3.84	28.11
OU0033	Group-C1	Mimbres-24	Mogollon R/B	Pottery	MURR	MN	LA 050180	LA 050180	4.28	38.96	0.4178	38.21	7.17	1.82 3.	3.12 79.42	17.35	31.07
OU0034	Group-C1	Mimbres-24		Pottery	MURR	- N	LA 050180	LA 050180	4.38	45.20 (0.5760	46.37	9.38	2.13 4.	4.50 94.96	36 14.19	40.33
OU0035	Group-B2	Mimbres-02A	Mimbres B/W Style II	Pottery	MURR	- N	LA 050122	LA 050122	1.66	43.55 (0.4710	35.17	2.96	4.32 3.	3.10 76.14	14 6.55	35.96
OU0037	Group-B2	Mimbres-02A	Mimbres B/W Style II	Pottery	MURR		LA 050122	LA 050122	2.59	44.30	0.4388	32.04			2.86 74.74	7.76	
OU0039	Group-B2	Mimbres-11		Pottery	MURR		LA 050122	LA 050122	1.98	37.70 (0.4855				3.73 73.23	23 13.96	41.52
ON0040	Group-B2	Mimbres-11	Mimbres B/W Style III	Pottery	MURR		LA 050122	LA 050122	3.00				5.33		3.68 71.87	37 14.70	40.41
OU0042	Group-A	Mimbres-10		Pottery	MURR		DAP 13	LA 153396	4.68				12.15	3.27 8.		54 17.04	
OU0043	Group-A	Mimbres-10		Pottery	MURR		DAP 13	LA 153396	6.71								
OU0044	Group-B1	Mimbres-04C	res B/W Style I	Pottery	MURR		DAP 13	LA 153396	2.87	_							
ON0045	Group-A	Mimbres-10		Pottery	MURR		DAP 13	LA 153396	4.29								
OU0046	Group-A	Mimbres-10		Pottery	MURR		DAP 13	LA 153396									
OU0047	Group-A	Mimbres-10	es	Pottery	MURR		DAP 13	LA 153396							. 7		
OU0049	Group-A	Mimbres-10	/B	Pottery	MURR		DAP 13	LA 153396	3.04								
ON0050	Group-A	Mimbres-10		Pottery	MURR		LA 050122	LA 050122	4.85	44.06			_		6.76 82.51		
OU0051	Group-B1	Mimbres-04C	ı	Pottery	MURR		DAP 13	LA 153396	2.16	47.18 (
OU0052	Group-B1	Mimbres-04C	Mimbres B/W Style I	Pottery	MURR	MN	DAP 13	LA 153396	2.74	48.48	0.5019	37.05	7.21	3.38 3.	3.50 92.16	16 8.87	32.52
OU0053	Group-A		Clay	Clay	MURR	MN			2.96		1.0433	76.27		3.71 7.	7.57 194.81		3.40
OU0054	Clay		Clay	Clay	MURR	MN			0.00	49.32	0.6543	39.80	6.90	1.85 4.	4.86 78.69	59 7.71	14.13
OU0055	Group-A		Clay	Clay Fired @	MURR	MN			4.28	73.67	0.9262	59.85	10.74	5.64 6	6.20 169.62		2.70
OU0056	Clay		Clay	Clay Fired @	MURR	MN			1.76	48.67	0.6256	41.81	7.39	2.34 5.	5.01 101.13	13 7.59	15.63
PDR001	G-dno ₂ D	El Paso Core	Jornada Brown	Pottery	MURR	MN	LA 121837	LA 121837	19.9	76.35	0.6529	67.33	14.18	5.20 4.	4.87 149.73	73 6.73	22.46
PDR003	Group-D	El Paso Core	El Paso Brown	Pottery	MURR		LA 121833	LA 121833	4.84					4.15 3.	·		
PDR004	Group-B	Unas.	Mimbres B/W Style Indeter. Pottery	Pottery	MURR		Pinon Apache	LA 121828	4.77	43.93	0.4500	37.36	7 86.9	4.01 2.	2.88 85.72	72 10.43	44.30
PDR005	G-dno-D	El Paso Core	Jornada Brown	Pottery	MURR	_ ⊠	Pinon Apache	LA 121828	9.16	96.89	0.6086	52.48	10.48	3.98 4.	4.03 139.22	8.19	39.76

>	69.96	55.51	83.04	58.82	59.13	76.91	57.91	86.26	34.53	55.61	53.79	83.15	76.26	69.94	150.37	91.58	62.32	77.74	50.03	36.51	81.39	96.96	41.67	33.00	60.35	63.45	53.82	62.14	51.21	44.90	55.62	52.30	53.20	58.40	60.53	56.87	28.64	47.77	38.20	56.84	98.95	103.37	67.93	111.71
F	3410.8	3206.5	4354.8	2956.5	3900.0	3580.3	3565.3	4322.9	1549.6	1746.8		2979.1	4116.6	4076.0	5395.7 1		2999.9	3669.9	2622.2	2390.5	4345.4	4701.9	3034.4	3120.3	3393.6	3351.0	2873.9									3008.4		1840.6			4565.8	_		5813.7 1
NA	19125.1	28471.1	19608.5	12102.5	15665.9	18521.4	12703.2	14619.2	10869.3	12291.0	13808.1	17131.9	18266.3	11723.3	16794.2		12824.2	20394.2	16312.7	14107.0	19598.9	19499.5	15741.5	15297.0	12871.2	12906.4	10390.4							3				8948.4	6062.6		15871.5			11474.4
MN	655.4 19	284.0 28	432.6 19	568.0 12	475.9 15	506.3 18	316.0 12	678.8 14	179.5 10	408.0 12	293.2 13	929.8	660.4 18	354.5 11	1185.3 16		180.2 12	442.6 20	211.3 16	138.6 14	460.9 19	663.9	288.0 15	298.1 15	724.1 12	823.8 12	248.3 10		`		`	`		`	_	_		8.777	594.8 6		501.8 15	`		692.9 11
¥	24755.7	13447.4	79309.6	25365.7	25412.4	23703.8	31236.9	21230.0	31818.1	35113.0	26133.9	20424.0	23779.9	26489.7	29211.8 1	26821.3	33808.9	21474.8	26405.0	38591.8	20450.9	23864.8	27869.0		28990.2	30612.5	35177.4					_					17604.3	10494.6						27781.9
DY	6.742 24	12.568 13	5.671 26	5.096 25	6.417 25	6.416 23		7.400 27	3.095 37	12.191 35	4.641 26	4.425 20	5.073 23	4.885 26	4.465 29	7.557 26	19.148 33	5.653 27	3.774 26	14.223 38	5.380 20		3.732 27	3.775 28	4.137 28	4.270 30	10.857 35		- 1				- 1		٠,	٠,		5.629 10	,	,		- 1	- 1	6.912 27
CA	16389.6	8004.8	16641.4	12544.2	14255.9	20766.7	7492.2	25384.1	12355.3	9711.1	10643.8	17048.4	12491.2	15477.8	18368.7	30739.6	5090.0	21037.3	13872.6	10040.6	24479.8	17052.5	12431.6		8.9586	13200.9	8862.7			~	_	1				15467.8		71047.6	18158.5		17400.4			18960.9
BA	7.077	318.3	544.1	650.7	739.7	778.5	618.5	880.3	512.1	874.6	681.4	8.986	817.9	1368.1	848.8	854.7	559.2	0.607	1288.7	1113.7	1295.8	792.0	450.4	430.6	547.0	475.6	871.7	2069.7	1022.6	1160.0	1186.5	1165.5	1439.6	6.999	866.3	828.7	158.6	983.4	182.8	1197.2	1292.7	879.0	876.1	894.7
AL	87539.8	78121.9	91338.8	97175.3	84412.1	87885.2	88531.2	83172.6	90719.0	95298.7	89014.0	94052.5	97155.4	89470.3	88318.2	81603.4	99649.3	97599.4	94545.9	89618.5	92609.7	95260.7	83016.8	79029.7	80533.1	78468.5	77141.8	_			`	`		96176.7	87523.3	86943.0	75234.8	66591.0	81016.5	73863.5	94015.1	92307.8	71330.9	92555.2
ZR	238.7	424.7	212.4	137.6	196.7	164.0	396.2	199.2	148.8	210.0	212.3	161.1	192.7	181.7	176.8	237.8	223.0	176.3	123.9	202.5	190.2	167.2	186.3	210.4	175.3	183.1	309.7									177.5	181.8	168.1	205.1					445.6
NZ	115.4	70.2	101.0	93.4	100.4	102.9	109.0	105.6	62.6	134.8	49.6	377.4	106.0	69.1	97.4		94.5	101.5	72.7	94.1	92.2	109.1	0.79	67.1	74.8	73.2	62.2					3						57.3	73.8					7.76
H	11.23	39.31	11.44	8.50	12.72	11.54	32.89	14.90	42.28	46.01	30.16	10.14	10.67	11.02	11.45	17.18	48.72	10.34	9.17	36.63	9.33	_	19.47	19.53	19.49	19.13	41.01											12.59	35.48	14.61	21.25			28.04
TB	1.28	2.77	1.25	0.95	1.42	1.24	1.91	1.43	0.54	2.10	0.79	0.89	1.07	0.91	0.95	1.30	3.68	1.03	0.78	2.81	1.06	1.57	0.76	0.77	0.71	0.74	2.02		0.89							0.97	1.90	1.06	1.63	1.17	1.32	_		0.93
TA	1.0370	2.2899	1.0299	0.7570	1.1662	0.9680	1.3927	1.4883	2.0183	1.7907	1.8019	0.7081	0.9126	1.1060	0.8107	1.4298	2.2890	0.8384	0.8502	2.3024	0.7772	1.0960	1.6231	1.5439	1.5987	1.5641	1.5861	1.4772	1.2522	2.1809	1.8211	3.1353	1.5201	2.2294	1.2762	1.3565	2.9411	0.9963	3.3215	1.1550	3.3836	2.9173	1.3705	2.6558
SR	410.6	118.9	416.8	253.5	367.1	339.0	66.7	267.8	121.2	129.2	214.9	353.3	397.0	474.2	524.6	322.8	99.2	446.3	439.5	164.4	530.6	356.6	333.4	304.8	266.1	282.3	183.4			184.7	242.9	111.4	265.3	240.4	341.8	365.7		1074.2	1459.9	1286.6		416.4		248.3
SC	10.88	12.08	11.68	86.6	11.08	11.41	12.53	11.30	4.59	10.72	89.8	10.74	11.53	8.47	16.05	11.71	11.57	10.53	7.20	8.38	10.38	11.65	8.78	8.65	8.18	8.02	8.83	7.77	8.74	7.53	10.10	14.25	7.57	11.22	8.75	8.78	3.77	6.73	4.38	7.51	9.76	10.04	8.19	12.24
SB	0.6907	0.5377	0.7400	0.3658	0.6277	0.8104	0.6483	0.6173	0.8210	0.4819	0.5119	0.4076	1.6815	1.2118	0.3412	0.6052	0.6344	0.6329	0.3541	0.5110	0.4780	0.5964	0.5808	0.6217	0.6421	0.6639	0.3772	0.5275	0.4136	0.6955	0.5945	0.4939	0.6205	0.5659	0.3911	0.3531	0.3193	0.1240	0.2782	0.1891	0.4541	0.4730	1.0462	0.8355
RB	135.88	71.68	131.82	125.82	113.34	120.53	237.96	136.87	219.53	253.01	184.13	96.52	117.85	115.39	142.53	144.30	269.04	124.16	95.95	233.67	98.59	122.24	179.67	180.30	178.20	172.62	198.91	180.72	150.31	255.98	228.09	216.82	200.17	212.98	144.56	145.96	167.34	45.59	184.03	54.91	99.82	113.28	178.06	99.75
Z	. 76.0	38.1	0.0	15.8	0.0	0.0	21.6	28.1	0.0	0.0	0.0	0.0	0.0	0.0	78.0	38.1	0.0	34.5	0.0	0.0	0.0	0.0	0.0		. 79.8	27.9	0.0		52.1					0.0	27.6	0.0		0.0	0.0	0.0				0.0
生	9.70	17.76	90.8	6.27	8.47	7.45	16.75	8.44	5.79	9.52	8.27	6.01	7.37	7.39	7.46	10.48	7.18	6.93	2.00	7.54	7.54	7.84	8.03	8.17	7.62	7.86	14.35	6.18	8.86	8.84	6.78	11.48	5.47	6.23	8.46	7.76	8.48	7.16	9.56	8.41	15.73	11.16	8.11	16.82
FE	43399.8	40870.5	39289.3	37151.2	37205.0	37541.7	39030.5	38473.8	13041.9	34105.9	20968.9	45949.8	40044.3	34333.0	56513.9		33441.3	37019.9	31549.7	25266.6	40045.0	42234.2	19646.6	19590.0	23129.6	22974.9	26092.0	26306.9	32906.5	28296.4	_	_	16479.5	32647.0	32713.0	32843.2	9581.9	19175.3	11259.2					2.1609 51552.9
EU	1.6930	1.9989	1.5821		1.5925	1.6986	1.6655	1.3749	0.6154	1.4243	1.0201	1.6102	1.7721	1.3244	1.8416		2.4894	1.6190	1.7407		1.6699	1.7764	1.1157		1.0504	1.0521	1.0477									1.4251		1.3120			4882	.9646	.4065	1609
CS	18.99	3.63		13.75 1	9.03	18.16	9.12	10.11	16.78 0	10.96	14.78	3.08	13.55 1	12.94	4.70		13.72 2	26.27 1	4.02	9.12 2.0921	14.21	25.90	14.64	13.95	7.15	6.91	4.03	-					11.60	10.63 0	5.64	5.73	37.98	3.70	48.89 1.2894	4.40	3.46 2.4882			4.94 2
ANID	9000NO	8000NO	OU0011	OU0012	OU0014	OU0015	OU0017	OU0018	OU0019	OU0020	OU0021	OU0022	OU0023	OU0025	OU0026	OU0027	OU0028	OU0029	OU0031	OU0032	OU0033	OU0034	OU0035	OU0037	OU0039	OU0040	OU0042	OU0043	OU0044	OU0045	OU0046	OU0047	OU0049	O00020	OU0051	OU0052	OU0053	OU0054	OU0055	OU0056	PDR001	PDR003	PDR004	PDR005

ANID	macro gr	macro grp Chem2012	CERAMIC TYPE	MATERIAL	SOURCE	STATE	SITE NAME	SITE NO	AS	ΓA	Π	ND	NS N	YB	CE	00	CR
PDR007	G-dno-D	El Paso Core	El Paso Brown	Pottery	MURR	MN	Pinon Apache	LA 121828	4.99	75.14 0.	0.5600	60.74 11.55	55 4.05	3.62	132.21	7.37	26.97
PDR008	G-dno ₂ D	El Paso Core	Jornada Brown	Pottery	MURR	MN	Pinon Apache	LA 121828	3.38	64.40 0.	0.4967	60.30 11.02	12 4.04	3.50	128.68	06.6	20.05
PDR013	Group-D	El Paso Core	El Paso Brown	Pottery	MURR	NM	LA 107601	LA 107601	5.17	74.67 0.	0.5248	55.39 11.17	7 3.63	4.31	131.53	6.72	25.64
PDR014	G-dno ₂ D	El Paso Core	El Paso Brown	Pottery	MURR	NM	LA 107601	LA 107601	6.47	74.07 0.	0.5322	55.21 11.93	3 3.56	4.62	126.60	6.53	26.04
PDR016	Gronp-D	El Paso Core		Pottery	MURR	NM	LA 107601	LA 107601	5.94					4.65			25.84
PDR017	G-dno-D	El Paso Core		Pottery	MURR	M	LA 107601	LA 107601	6.05	_				3.58			25.93
PDR018	G-dno ₂ D	El Paso Core		Pottery	MURR	NM	LA 107601	LA 107601	5.91	77.62 0.				4.93		6.45	24.26
PDR019	G-dnoJ9	El Paso Core		Pottery	MURR	M	LA 107601	LA 107601	2.67					4.63			25.40
PDR020	Group-D	El Paso Core		Pottery	MURR	NM	LA 121836	LA 121836	4.29		0.5354 4		3.03	3.55		5.91	24.64
PDR021	G-dno ₂ D	El Paso Core	El Paso Brown	Pottery	MURR	¥	LA 121836	LA 121836	8.16	77.50 0.	0.7370	62.31 12.97	3.45	6.05	162.82	10.57	34.98
PDR022	G-dno ₂ D	El Paso Core	Jornada Brown	Pottery	MURR	NN	LA 121836	LA 121836	2.40	65.26 0.	0.5421	43.34 10.05	5.01	4.18	128.36	7.61	26.29
PDR024	G-dno ₂ D	El Paso Core	El Paso Brown	Pottery	MURR	MN	LA 121836	LA 121836	6.41	55.72 0.	0.4734	40.72 8.78	78 5.88	2.80	105.73 1	11.11	24.57
PDR025	G-dno ₂ D	El Paso Core	Jornada Brown	Pottery	MURR	NN	LA 121836	LA 121836	1.93	76.02 0.	0.5525	62.37 13.42	12 4.24	4.55 1		6.12	21.46
PDR026	G-dno ₂ D	El Paso Core	El Paso Brown	Pottery	MURR	MN	LA 121836	LA 121836	6.83	54.16 0.	0.4468	42.38 8.45	15 5.20	2.53	102.45 1	12.11	23.85
PDR027	G-dno ₂ D	El Paso Core	El Paso Bichrome or Polych Pottery	Pottery	MURR	MN	LA 121836	LA 121836	7.26	61.38 0.	0.6629	56.28 12.11	1 4.27	5.82	129.82	6.20	27.45
PDR029	Group-D	El Paso Core	El Paso Brown	Pottery	MURR	NM	LA 121836	LA 121836	5.81	50.80 0.			7 3.89	3.03			32.92
PDR030	Group-D	El Paso Core	El Paso Brown	Pottery	MURR	NM	LA 121836	LA 121836				57.30 10.61		4.70			27.12
PDR031	G-dno ₂ D	El Paso Core	Jornada Brown	Pottery	MURR	NM	LA 121836	LA 121836	3.73	67.94 0.	0.5765	46.17 9.99	67.79	4.30	129.30	8.58	26.80
PDR033	Group-A	Mimbres-10	Alma Plain	Pottery	MURR	NM	LA 121824	LA 121824	5.29	85.45 1.	1.1454 8	86.50 18.67	57 2.68	10.6	174.73	4.87	29.13
PDR037	Group-A	Mimbres-10	Mimbres undif.	Pottery	MURR	NM	LA 121824	LA 121824	7.33			77.60 17.66	3.75	6.21	151.71		29.49
PDR055	G-dno ₂ D	El Paso Core	El Paso Brown	Pottery	MURR	¥	Conejo	LA 091044	5.82	84.60 0.	0.6742	69.01 12.60	5.01	4.72	157.69	8.02	31.58
PDR056	Group-D	El Paso Core	El Paso Brown	Pottery	MURR	NM	Conejo	LA 091044	6.28	82.64 0.	0.6287	62.91 11.69	3.89	4.40	148.20	4.44	20.42
PDR057	G-dno-D	El Paso Core		Pottery	MURR	NM	Conejo	LA 091044	4.19	81.95 0.			8 2.98	4.64			30.03
PDR058	Group-D	El Paso Core		Pottery	MURR	NM	Conejo	LA 091044	7.10			54.27 10.38					17.88
PDR060	G-dnoJ9	El Paso Core		Pottery	MURR	MM	Conejo	LA 091044	6.63	81.58 0.		_		4.05		4.18	23.96
PDR061	G-dno ₂ D	El Paso Core		Pottery	MURR	NM	Conejo	LA 091044							124.98		25.94
PDR062	G-dno ₂ D	El Paso Core		Pottery	MURR	M	Conejo	LA 091044				7		4.89	145.86		29.98
PDR063	G-dnoJ9	El Paso Core		Pottery	MURR	M	Conejo	LA 091044	4.23					2.73			18.77
PDR064	G-dno ₂ D	El Paso Core		Pottery	MURR	ΤX	Tres Casitas	41EP00628	6.18			51.78 9.67	3.86	3.96	103.53	3.80	19.38
PDR066	G-dno-D	El Paso Core		Pottery	MURR	TX	Tres Casitas	41EP00628	3.87			_					24.64
PDR067	G-dnoJ9	El Paso Core		Pottery	MURR	×	Tres Casitas	41EP00628	6.23					\rightarrow			18.50
PDR069	G-dno-D	El Paso Core		Pottery	MURR	X	Tres Casitas	41EP00628									25.16
PDR070	G-dno-D	El Paso Core		Pottery	MURR	X	Tres Casitas	41EP00628						4.06 1			18.70
PDR071	G-dno _{-D}	El Paso Core		Pottery	MURR	TX	Tres Casitas	41EP00628				_		4.72			19.97
PDR073	G-dno ₂ D	El Paso Core		Pottery	MURR	ΤX	Tres Casitas	41EP00628		54.58 0.		41.02 7.28	4.85	2.99		2.88	14.19
PDR074	Group-D	El Paso Core		Pottery	MURR	TX	Tres Casitas	41EP00628		82.75 0.	0.6121 (66.66 11.95	5.16	4.19 1			26.77
PDR075	Group-D	El Paso Core		Pottery	MURR	TX	Tres Casitas	41EP00628				64.08 11.53	3 4.63	4.25		8.56	28.22
PDR076	Group-D	El Paso Core	El Paso Brown	Pottery	MURR	TX	Tres Casitas	41EP00628				47.83 8.90	90 4.48	3.34	113.81	3.41	18.48
PDR077	Group-D	El Paso Core		Pottery	MURR	TX	Tres Casitas	41EP00628	6.54	58.37 0.		48.78 9.72		4.02		3.98	18.37
PDR078	Group-D	El Paso Core		Pottery	MURR	TX	Tres Casitas	41EP00628	5.73		0.5919	63.38 11.53	5.40	4.18	132.51		24.45
PDR079	Gronp-D	El Paso Core	El Paso Brown	Pottery	MURR	TX	El Arenal	41EP03175	87.9			1	00 6.49				41.02
PDR082	G-dno-D	El Paso Core	El Paso Brown	Pottery	MURR	TX	El Arenal	41EP03175						4.05			29.26
PDR086	G-dno ₂ D	El Paso Core		Pottery	MURR	ΤX	El Arenal	41EP03175		_				5.40			43.56
PDR087	G-dno-D	El Paso Core	El Paso Brown	Pottery	MURR	X	El Arenal	41EP03175	7.27	68.17 0.	0.7291	58.04 10.81	1 5.99	5.06	150.44 1	10.74	43.36

>	101.10	100.56	88.11	96.56	83.45	85.66	76.50	98.04	68.85	97.70	95.46	127.17	92.70	103.32	86.41	81.11	83.32	96.53	67.93	70.75	95.99	75.45	69.84	62.95	73.77	71.55	86.01	35.34	53.07	105.96	47.55	79.88	68.33	52.10	52.94	92.04	87.46	46.72	49.71	92.58	89.59	63.65	82.65	78.61
I	5513.3	6388.5	5105.7		5734.3	5342.5	5292.1		5911.3	5340.2	4523.5	4684.0 1	4755.9	5626.8 1	5382.4	4052.9	5924.5	6732.8	3058.0	3097.2	5570.0	4985.6	4941.3	5351.5	5519.2	4482.1	5720.1			1											3378.9			5458.3
NA	15496.6 5	25353.5 6	16560.8 5	_	15533.1 5	16250.6 5	15738.7 5		16629.0 5	11230.6 5	23585.7 4		25533.9 4	12627.8 5	14949.4 5	15770.4 4	14719.5 5	21993.4 6	10987.8 3	11346.4 3	14662.1 5			722.1 5		15701.3 4	13770.9 5											18906.3 3	16846.8 3					13575.6 5
MN	580.1 154	504.5 253	540.2 165	`	510.0 158	530.6 162	452.6 157	446.6 158	536.7 166	518.7 112	529.7 235	1052.1 182	626.3 255	552.9 126	576.1 149	498.8 157	589.6 147	543.5 219	305.9 109		533.2 146	460.2 192	441.3 165	447.8 17.	507.9 180	442.5 157	710.7 13.7			,	_				•			323.8 189	440.4 168	514.9 167	813.6 133	`		1089.1 135
¥	28689.4 58	20894.4 50	9		30276.0 5	34071.3 53	32595.4 4	28662.4 4	28755.9 53	28116.0 5	25751.4 52	27241.2 105		_	28470.0 5	25931.3 49	29963.6 58	/				2	32255.4 4	30248.8 44	27909.3 50	32357.3 4	28402.9 7						_				9	9	9	4	1	ľ		30934.5 108
DY			54 32194.					7.104 286					97 31632.1	06 32785.7		_		42 26778.	96 30570.7	77 28709.7	10 33224.7	45 31297.					_							- 1				65 29387.		28 24103.				
CA	.2 7.168	.1 6.659		8 5.689	.2 6.860	.5 7.088	.8 7.810	17	6.998	.5 9.303	7 6.904	.6 4.317	.3 6.897	.9 5.106	.3 8.835	.2 5.807	.3 6.041	.6 5.542	.6 12.996	.6 13.127	.1 8.210			6.880	.5 7.382	.0 7.612	.8 6.527											.3 4.565	.0 6.601	.6 7.128	.7 6.895			.5 8.255
S	28326.2	24001.1	17772.9	24733.8	23193.2	20380.5	31779.8	17560.6	15723.9	14905.5	13032.7	14646.6	16364.3	16407.9	16874.3	12421.2	18658.3	15029.6	12889.6	11012.6	20092.1	12586.7	14049.7	14436.9	14741.5	17900.0	26443.8	11693.2	16560.6	16902.9	15584.2	18972.5	14044.1	14431.1	12987.8	16636.2	18730.6	12938.3	13678.0	18357.6	8306.7	13528.5	8192.9	8677.5
BA	1314.6	895.0	1103.2	964.1	1120.4	1183.1	963.0	1241.3	905.8	1302.0	1050.4	1341.8	1319.7	1167.4	1158.9	902.6	1335.3	911.3	923.1	745.5	1591.1	1631.7	997.0	1915.1	1181.1	1211.0	2069.6	1524.8	1188.1	977.0	1189.6	1121.5	987.3	997.5	1008.1	1016.7	1530.7	1234.2	1378.8	1255.1			961.0	913.3
AL	92029.2	101347.3	90730.2	82105.6	85652.3	88892.4	88817.3	85451.2	87214.1	96343.5	91306.4	86715.1	92379.6	93664.2	90613.8	86628.3	88378.8	90801.0	82645.4	84536.9	92791.8	88479.5	85288.5	80874.5	88351.5	84507.7	82587.8	84742.5	87143.9	93945.2	86052.6	88141.2	85337.1	90266.3	86510.6	90709.1	94162.9	87472.4	85543.5	92233.8	74546.7	90025.4	73274.8	76356.3
ZR	299.5	241.2	348.4	339.1	480.4	321.7	378.4	308.6	291.5	338.1	319.9	250.5	363.4	220.7	379.5	303.4	373.5	367.4	288.4	301.5	311.3	376.2	319.2	308.0	342.5	419.5	678.2	260.2	252.9	329.7	279.6	314.4	257.3	377.3	238.9	396.5	281.9	263.7	232.0	311.9	456.8	281.1	454.1	425.7
NZ	9.62	63.6	88.3	101.3	93.7	100.6	113.4	101.2	6.06	112.2	99.3	130.5	96.3	126.6	99.2	103.2	114.2	122.5	8.06	6.06	9.96	79.3	77.5		91.4	76.7	87.9		70.5	76.5	0.69	78.3	63.3	67.3	49.8	89.4		57.5	64.2	85.2	9.88	76.6	87.4	87.7
Ŧ	19.37	13.28	18.64	18.12	19.73	17.93	17.96	17.53	21.26	23.22	15.98	30.23	19.80	23.52	23.22	20.09	18.04	17.28	43.06	41.01	29.02	26.53	18.48	21.74	23.25	16.46	18.10		24.25	19.20	23.19							22.74	23.49	24.64				21.62
TB	0.97	1.14	1.29	1.37	1.26	1.37	1.81	1.36	1.18	1.71	1.28	1.03	1.54	96.0	1.56	0.94	1.21	1.19	2.39	2.20	1.48		1.51	1.23	1.22	1.28	1.51	0.65	1.11	1.49	`	•	· -		0.76		1.29	0.98	1.17	1.35	1.34	-		1.34
TA	2.2696	2.9303	2.2151	2.3280	2.2790	2.2496	2.8659	2.4806	3.1653	3.4531	3.2549	2.7203	3.0579	2.6164	3.5005	2.8092	2.3281	3.3774	1.7501	1.9045	2.8161	2.7329	2.4621	2.9504	2.3314	2.3479	2.6536					3.5380				2.8517	2.9231	2.6979	2.7646	3.3452	3.2545			3.1292
SR	321.5	664.8	301.2	367.9	313.6	299.7	205.1	255.2	237.3	327.4	375.3	346.0	351.2	328.7	314.5	275.5	278.1	497.4	112.3	115.9	368.0	279.7	265.9	313.3	289.1	323.1	365.0	285.4	387.2	371.9	332.4	378.1	297.7	280.2	322.3	375.3	440.4	291.3	292.1	364.7	224.0	280.6	207.3	197.8
SC	10.41	9.42	10.22	68'6	10.07	10.00	9.83	10.05	8.57	10.46		10.71	11.61	10.23	10.46		9.93	10.20	10.22	10.27	11.02		9.54	8.16	11.22	9.04	9.78			Ď,							1	7.81		11.51				8.05
SB	0.4851	0.5883	0.5167	0.5276	0.5525	0.5062	0.4799	0.5453	0.4121	0.7106	0.5229	0.6335	0.4483	0.5613	0.4882	0.5993	0.4343	0.5537	0.5146	0.5420	0.4865	0.4532	0.4956	0.4634	0.4507	0.4076	0.5104	0.3491	0.4750	0.3758	0.4305	0.3966	0.4542	0.4488	0.3274	0.4930	0.4516	0.4744	0.4949	0.4521	0.7498	0.6293	0.7427	0.7373
RB	104.22	88.28	106.54	102.71	98.57	107.61	100.05	104.61	107.19	104.51	91.50	106.42	101.56	104.51	114.07	118.61	91.26	119.96	204.65	198.57	105.24	125.50	131.98	120.53	94.03	118.89	93.47	127.34	129.21	112.52	126.22	106.53	128.68	135.21	130.69	114.98	108.44	119.14	129.17	88.98	150.04	129.96	144.15	144.50
Z	0.0	0.0	32.7	0.0	0.0	0.0	30.5	0.0	0.0	0.0	61.0	0.0	51.5	0.0	0.0	0.0	38.5	0.0	0.0	0.0	0.0	25.5	25.2	20.8	28.9	21.6	36.2									26.5		0.0	21.6	23.3	19.4			25.7
生	12.20	8.69	13.08	12.66	16.95	11.79	12.60	10.78	12.41	13.39	11.30	10.42	12.11	9.01	15.78	12.55	13.61	13.28	13.69	12.82	10.90	12.91	11.77	11.59	11.23	14.18	21.94	10.23	9.14	12.93	9.58	10.77	10.10	13.57	8.79	14.06	9.37	9.54	8.96	10.80	17.16	11.41	16.74	16.44
FE	43525.0	35284.4	39091.8	37608.2	37833.1	38150.0		39187.6	37085.4	44466.8	38750.6	48452.3	27550.5	46688.5	44302.1	41156.7	39401.7	34581.1	29787.5	30176.9	43727.8	40640.3	34794.5	38236.8		34187.5	43157.2	-			34586.4	-	-	35844.7			47125.3	36733.3	34612.8	44489.7			33221.0	33568.6 16.44
EN	2.3912	2.8067		2.4123	2.3585	2.4331		2.3972	1.8492	2.2016	2.4753	1.8184	3.1813	1.7628	2.0522	1.6855	2.1800	2.3874	1.3683	1.3389	2.3385	2.4220	2.3922		2.5710	2.1687	2.4834								1.3346	3456		1.5794	1.8149		1.5386			1.5341
CS	3.42	4.23	3.25 2	3.30 2		3.19 2		3.27 2	3.82	4.45	4.22 2	3.50	5.02	3.33	4.02	4.70 1	3.28	4.03 2	5.00	4.94	3.53 2	4.05	3.74	2.99 2	3.32	2.99 2	3.35 2								3.35	3.14		2.81						4.83 1
ANID	PDR007	PDR008	PDR013	PDR014	PDR016	PDR017	PDR018	PDR019	PDR020	PDR021	PDR022	PDR024	PDR025	PDR026	PDR027	PDR029	PDR030	PDR031	PDR033	PDR037	PDR055	PDR056	PDR057	PDR058	PDR060	PDR061	PDR062	PDR063	PDR064	PDR066	PDR067	PDR069	PDR070	PDR071	PDR073	PDR074	PDR075	PDR076	PDR077	PDR078	PDR079	PDR082	PDR086	PDR087

ANID	macro arp	Chem2012	CERAMIC TYPE	MATERIAL	SOURCE	STATE	SITE NAME	SITE NO	AS	Υ	n1	S QN	NS N	YB	CE	00	CR
RLB001	Group-B1	Mimbres-04A	Mimbres B/W Style III		TAM	NM	NAN	LA 002465		45.24 0.4	0.4420 33	35.34 6.20	20 4.21	~	86.22	5.93	19.59
RLB002	Group-B2	Mimbres-11	Mimbres Polychrome	Pottery	TAM	NM	NAN	LA 002465	3.15	32.76 0.4	0.4158 2	24.75 4.25	25 3.31	3.11	64.36	16.02	39.88
RLB003	Group-B1	Mimbres-04A	Mimbres B/W Style III	Pottery	TAM	NM	NAN	LA 002465	1.84	30.60 0.3	0.3928 2	27.26 4.9	4.98 3.45	2.93	62.36	7.04	23.04
RLB005	Group-C2a	Mimbres-49A	Mimbres B/W Style II	Pottery	TAM	MN	NAN	LA 002465	2.91	47.16 0.3	0.3381 3	39.96 7.41	11 1.91	2.77	85.89	16.88	50.95
RLB006	Group-B	Unas.	Mimbres B/W Style II	Pottery	TAM	NM	NAN	LA 002465			0.4104 3		6.76 3.00		76.55	8.52	49.35
RLB007	Group-B2	Mimbres-02A	Mimbres B/W Style III	Pottery	TAM	NM	NAN	LA 002465	1.90	43.48 0.4	0.4641 34	34.56 6.14	14 4.78	3.23	86.66	4.62	36.00
RLB008	Group-B	Unas.	Mimbres B/W Style I	Pottery	TAM	NM	NAN	LA 002465	2.19	23.08 0.2	0.2111 1;	13.21 2.7	2.14 1.40	1.44	36.88	1.31	8.88
RLB010	Group-B	Unas.	Mimbres B/W Style II	Pottery	TAM	NM	NAN	LA 002465	2.57	38.60 0.4	0.4000 3	34.68 5.69	59 4.20	2.93	63.10	5.23	37.61
RLB011	Group-C1		Mimbres B/W Style I	Pottery	TAM	NM	NAN	LA 002465	1.95		0.3091 34		21 1.39	2.32		10.19	65.63
RLB014	Group-C2b	Mimbres-41	Mimbres B/W Style II	Pottery	TAM	MN	NAN	LA 002465	1.03	34.22 0.3	0.3172 3	37.86 5.23	23 2.16	2.16	85.69	10.43	27.25
RLB016	Group-B2		Mimbres B/W Style III	Pottery	TAM	MN	NAN	LA 002465	2.33	45.43 0.4	0.4777 4	45.45 6.67	57 3.68	3.11	73.51	2.68	37.07
RLB017	Group-B1	Mimbres-05A	Mimbres B/W Style I	Pottery	TAM	MN	Saige-McFarland	LA 005421	2.17	43.14 0.5	0.5550 4	47.45 9.02	2.74	4.69	84.10	80.6	57.10
RLB018	Group-C1	Mimbres-24	Mimbres B/W Style I	Pottery	TAM	MN	Saige-McFarland	LA 005421	2.15	43.71 0.4	0.4963 4	44.67 8.67	57 2.06	4.01	75.81		33.84
RLB019	Group-C2	Unas.	Mimbres B/W Style I	Pottery	TAM	NM	Saige-McFarland	LA 005421	5.19	40.44 0.5	0.5692 40	40.73 10.94	94 2.05	4.82	87.45	28.20	50.32
RLB020	Group-C1	Unas.	Mimbres B/W Style I	Pottery	TAM	NM	Saige-McFarland	LA 005421	1.78	34.90 0.2		33.93 5.64	54 1.24	2.40	66.21	7.52	23.88
RLB021	Group-C1	Mimbres-21	Mimbres B/W Style I	Pottery	TAM	NM	Saige-McFarland	LA 005421	6.78		0.3507 4	41.27 6.25	25 1.39	3.06	77.27	8.17	27.74
RLB022	Group-C1	Unas.	Mimbres B/W Style I	Pottery	TAM	NM	Saige-McFarland	LA 005421	6.31	37.33 0.5	0.5488 6.	63.85 10.62			81.49	9.80	47.70
RLB023	Group-C1	Mimbres-24	Mimbres B/W Style I	Pottery	TAM	MN	Saige-McFarland	LA 005421		41.03 0.4	0.4221 4	41.40 7.57	57 1.19	3.52	80.25	14.44	28.92
RLB024	Group-C1	Unas.	Mimbres B/W Style I	Pottery	TAM	NM	Saige-McFarland	LA 005421	3.51	37.38 0.4	0.4207 4	45.50 6.23	23 2.03	3.16	69.64	8.33	54.76
RLB025	Group-C1	Unas.	Mimbres B/W Style I	Pottery	TAM	MN	Saige-McFarland	LA 005421	2.37	37.48 0.4	0.4370 3	36.81 6.4	6.43 2.49	3.58	71.29	9.56	60.17
RLB026	Group-C1	Unas.	Mimbres B/W Style I	Pottery	TAM	MN	Saige-McFarland	LA 005421	2.70	35.97 0.4	0.4169 4.	43.18 6.58	58 3.17	3.41	75.99	9.41	34.22
RLB027	Group-C1	Mimbres-21	Mimbres B/W Style II	Pottery	TAM	MN	Saige-McFarland	LA 005421	2.87	37.45 0.3	0.3129 4.	42.12 5.41	1.22	2.65	78.75	12.68	60.31
RLB028	Group-A	Mimbres-03	Mimbres B/W Style II	Pottery	TAM	NM	Saige-McFarland	LA 005421				55.00 9.72	,		82.39	2.42	12.23
RLB029	Group-C1	Mimbres-21	Mimbres B/W Style II	Pottery	TAM	NM	Saige-McFarland	LA 005421								8.45	39.04
RLB030	Group-C1	Mimbres-21	Mimbres B/W Style II	Pottery	TAM	NM	Saige-McFarland	LA 005421	1.58			42.54 5.51	51 1.25			10.77	69.10
RLB031	Group-C1	Unas.	Mimbres B/W Style II	Pottery	TAM	NM	Saige-McFarland	LA 005421								7.00	24.29
RLB032	Group-C1	Mimbres-21	Mimbres B/W Style II	Pottery	TAM	NM	Saige-McFarland	LA 005421								10.40	64.58
RLB033	Group-C1	Mimbres-21	Mimbres B/W Style II	Pottery	TAM	NM	Saige-McFarland	LA 005421								10.81	55.55
RLB034	Group-C1	Mimbres-21	Mimbres B/W Style II	Pottery	TAM	NM	Saige-McFarland	LA 005421								10.25	68.89
RLB035	Group-C1	Mimbres-21	Mimbres B/W Style II	Pottery	TAM	M	Saige-McFarland	LA 005421								9.49	56.51
RLB036	Group-C1	Mimbres-21	Mimbres B/W Style II	Pottery	TAM	WN :	Saige-McFarland	LA 005421								10.94	64.73
RLB037	Group-C1	Mimbres-24	Mimbres B/W Style III	Pottery	TAM	M	Saige-McFarland	LA 005421								14.45	35.61
RLB038	Group-C1	Mimbres-21	Mimbres B/W Style III	Pottery	TAM	M	Saige-McFarland	LA 005421								10.93	60.20
RLB040	Group-C1	Mimbres-21	Mimbres B/W Style III	Pottery	TAM	M	Saige-McFarland	LA 005421								89.8	38.79
RLB041	Group-B1	Mimbres-05A	Mimbres B/W Style III	Pottery	TAM	NM	Saige-McFarland	LA 005421						3.41		10.65	51.99
RLB042	Group-C1	Mimbres-22	Mimbres B/W Style III	Pottery	TAM	NM	Saige-McFarland	LA 005421	3.24		0.2268 4	44.95 4.79		1.79	73.55	5.34	6.07
RLB043	Group-C1	Mimbres-21	Mimbres B/W Style III	Pottery	TAM	NM	Saige-McFarland	LA 005421		39.59 0.3		46.50 6.24	24 1.59	2.83		11.61	69.80
RLB044	Group-C1	Mimbres-21	Mimbres B/W Style III	Pottery	TAM	NM	Saige-McFarland	LA 005421	3.39	41.72 0.3	0.3043 3		25 1.10	2.52	79.76	11.07	44.07
RLB045	Group-C1	Mimbres-21	Mimbres B/W Style III	Pottery	TAM	¥	Saige-McFarland	LA 005421	2.41	40.41 0.3	0.3324 30	36.82 5.98	98 1.30	2.76	75.28	11.95	67.12
RLB046	Group-B1	Mimbres-05A	Mimbres B/W Style III	Pottery	TAM	NM	Saige-McFarland	LA 005421		47.44 0.5		51.02 9.70	70 2.93	4.65	92.86	6.87	54.77
RLB052	Group-A	Mimbres-10	Mimbres Corrugated	Pottery	TAM	AZ	CC:10:65/SS19	CC:10:65/SS7	3.55			1	14 4.78	5.33	105.48	6.17	25.23
RLB055	Group-C1	Unas.	Mimbres B/W Style Indeter. Pottery	Pottery	TAM	AZ	04-23/FS208	04-23/FS208							95.85	17.35	51.24
RLB056	Group-C1	Unas.	Mimbres B/W Style Indeter.	Pottery	TAM	AZ	04-23/FS208	04-23/FS208		28.98 0.4						4.82	20.89
RLB057	Group-C1	Unas.	Mimbres B/W Style III	Pottery	TAM	AZ	CC:10:52/FS141/SS5	CC:10:52/FS1	6.19	40.06 0.3	0.2659 3	37.59 5.27	27 1.02	2.13	83.28	10.00	22.91

>	49.41	60.29	49.12	74.41	92.99	48.53	19.02	54.90	48.43	95.10	54.90	60.29	70.88	156.57	44.61	55.20	86.67	80.00	58.73	59.51	54.80	76.76	29.31	49.41	58.33	41.27	51.96	58.82	62.94	49.51	51.27	79.90	66.57	47.55	82.84	37.65	64.90	55.59	72.25	77.55	34.71	94.02	43.43	45.59
Ξ	2981.9	2892.5	3467.7	3484.8	3395.9	3109.0	1831.8	3346.8	1968.0	3591.4	3127.5	4178.9	3399.6	9.8899	1703.9	2682.7	4497.9	4635.6	3748.8	3512.6	2813.1	3149.3	1562.8	2863.4	2800.5	1709.5	2927.3	2043.8	2202.7	1361.7	2195.5	4109.4	4129.2	2768.8	4215.8	919.5	3219.4	2869.3	2430.7	4407.5	3233.4	3888.2	2138.7	2145.0
NA	14601.2	10956.1	13000.7	15320.8	13574.8	11282.3	7570.5	14413.1	19721.2	14755.8	13029.9	15108.2	18046.6	12711.0	11132.0	11389.7	14910.0	19975.3	15832.5	16409.7	15986.7	19692.7	63629	18028.3	18580.2	13625.8	18907.6	17725.0	16476.7	17579.3	19895.6	182/8.6	18310.6	15691.8	13896.8	11532.7	18390.8	15721.5	17579.7	11888.2	13964.6	15266.3	10459.7	9950.8
MN	356.5	8.669	322.6	939.7	2999	203.0	282.1	273.8	1045.6	430.0	254.8	8.969	445.2	950.1	576.4	629.2	9.087	268.0	714.2	731.0	630.3	1026.8	9.969	897.3	1058.5	804.3	1032.3	1009.1	1051.5	1078.4	1041.6	839.3	958.0	932.5	632.5	663.3	1011.4	1026.2	893.5	586.4	378.6	761.9	251.0	987.6
¥	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
D	4.332	2.271	3.671	3.734	5.045	4.511	1.489	3.823	3.517	3.286	4.363	8.489	5.293	8.344	3.942	3.923	8.661	3.632	4.606	4.801	4.837	3.446	10.904	4.624	3.379	2.651	3.490	3.680	2.520	3.640	2.809	4.391	4.195	3.035	5.010	2.486	4.289	4.669	4.438	7.222	9.146	6.838	4.612	2.955
CA	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
BA	945.0	510.8	887.9	1035.2	1124.5	516.1	234.5	876.3	9.896	1024.1	8.659	8.999	650.1	711.6	0.968	826.9	700.1	1001.4	734.1	591.6	692.6	887.5	285.6	749.3	808.3	718.2	807.3	854.0	875.9	792.7	893.5	789.3	859.6	847.3	724.0	847.2	920.8	9.868	0.806	624.1	968.2	893.4	9.089	1069.8
AL	78590.1	74024.1	74189.5	93775.5	79188.3	78872.1	80677.9	84420.5	77991.5	81771.9	82091.8	79633.0	90380.2	88270.4	84337.2	91164.8	81775.5	81136.0	0.99987	72744.8	78971.6	85064.1	72960.9	81744.5	81561.8	91144.4	85307.9	8.69967	86827.4	82899.0	79725.1	90488.0	86918.9	92293.9	88388.0	89718.0	83798.0	93804.2	88479.3	87539.8	76473.0	82006.2	80403.4	85500.4
ZR	310.4	222.8	348.8	284.5	230.2	240.7	140.1	222.7	220.1	234.3	224.2	218.7	164.4	194.6	123.2	151.0	192.4	157.1	110.1	224.0	193.7	188.0	253.1	150.0	180.9	149.8	223.5			176.5	158.4			127.6				151.4	190.1	224.5	143.0	112.9	91.4	141.5
NZ	45.2	45.0	46.4	626	57.0	47.3	46.1	26.0	77.5	58.9	50.3	80.9	73.8	92.8	73.6		1.79	76.4	70.2	70.1	96.4	91.6	171.4	71.5	77.2	74.3	76.5	8'59	71.0	63.4	76.3	72.4	71.5	75.3	75.5	80.5		9'88	9'98	93.7	73.3			88.2
TH S	19.83	17.00	17.92	11.72	14.42	20.42	15.27	1	9.44	11.17	19.42	14.95	10.60	10.60	9.31		10.76	9.43	12.24	12.68	12.51	9.31	32.37			9.33	9.64								_			9.46	68.6	15.59			_	9.50
4 TB	1 0.84	89.0 8	3 0.76	3 0.89		0.82	5 0.27	4 0.77	9 0.65		3 0.95	1.28	3 1.09	1.62	9 0.74	89.0	3 1.79	5 1.06	08.0	2 0.91	1.04	3 0.80	5 1.93	4 0.83	0.79	3 0.57	9 0.75	2 0.83									5 0.74	5 0.67	09.0	2 1.13	1.49			5 0.64
TA	1.4421	1.5218	1.5128			1.5960	1.4666	1.3444	0.7689	1.0053	1.3583	1.5050	0.9403	1.3134	0.6499		1.4243	0.8946	1.1179	1.2652	1.4350	0.7098	2.3256		0.8397	0.6473	0.8279											0.6895	0.8590		1.1130			0.5895
SR	222.3	172.0	254.8	443.9		230.3	106.9	305.9	387.9	567.3	318.5	272.5	304.5	346.5	330.2	262.4	321.8	448.6	358.7	298.8	302.7	387.7	86.0	344.9	334.1	281.5	318.7	397.5	353.2	332.2	496.9	496.6	362.3	319.8	284.1	315.5	294.4	434.7	374.6	241.8	152.4	462.0	108.0	572.8
SC	99.9	7.44	6.72	11.24	8.76	9.35	5.19	9.20	7.90	8.32	11.50	10.59	10.15	19.71	5.20	98.9	8.99	9.41	8.08	8.94	8.80	8.76	5.45	6.49	7.71	5.56	7.84	7.88	7.38	7.00	7.35	11.02	7.93	99.9	11.68	4.15	9.11	8.73	9.49	11.28	7.61	14.91	7.97	69.9
SB	0.4506	0.6547	0.3957	0.5012	1.3078	0.6807	0.3063	0.3178	0.9994	0.3042	0.3427	0.5840	0.6125	0.4652	2.6997	2.1686	0.6614	0.5655	0.7640	0.8837	0.6870	1.4439	0.5619	1.8860	1.8066	2.6576	1.9686	1.2972	2.0863	1.8252	1.2397	1.0000	2.2676	2.5812	0.6511	2.4305	1.8009	1.4079	1.3461	0.8159	0.0000	0.7305	0.9069	0.9260
RB	145.30	186.60	149.10	112.40	124.00	158.70	65.40	145.80	133.00	106.20	158.00	145.80	115.60	99.20	140.60	167.90	130.60	98.50	140.90	139.70	154.90	129.20	302.20	134.10	128.60	143.00	133.00	125.40	124.30	124.80	109.30	118.80	139.70	145.00	147.20	145.20	135.40	129.70	135.50	148.50	206.60	156.70	246.60	82.40
Z	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0			0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
生	9.05	68.9	9.16	7.48		8.56	6.53	7.34	6.62	7.13	7.09	8.64	7.32	8.31	4.92		7.97	7.04	7.38	8.56	6.84	7.67	11.04	6.13	6.30		7.34											6.24		8.53	6.20			9.00
FE	23033.2	22241.1	23696.0	37985.0		22090.7	10703.1		27439.9	33876.6	27146.2	33104.7	35294.5	61135.1	20651.1		36408.8	39803.0	28453.2	29767.0	33210.4	34341.7		23640.1	27981.4	21013.8		27641.4						_				32125.3			24365.5			26081.8
EU	1.2698	0.9235	1.0819	1.7599	1.4973	1.1473	0.3417	1.2517	1.1501	1.4013	1.4203	1.3876	1.6098	1.8240	1.1827		1.6632	1.7211	1.1295	1.1892	1.5894	1.3359	0.5768	1.2404	1.3209	1.2118	1.3153											1.5325	1.3131	1.5889	1.3894			1.3628
CS	4.35	6.41	4.39	4.69	8.25	18.24	5.54	4.97	14.95	3.79	15.26	99.6	19.58	2.60	21.04	26.03	11.24	11.88	11.03	11.45	12.37	18.05	4.85	17.90	16.10	25.07	17.73	14.73	18.36	17.01	16.76	14.00	16.09	20.85	7.16	27.36	15.80	21.20	18.10	10.19	4.96	15.06	22.80	13.35
ANID	RLB001	RLB002	RLB003	RLB005	RLB006	RLB007	RLB008	RLB010	RLB011	RLB014	RLB016	RLB017	RLB018	RLB019	RLB020	RLB021	RLB022	RLB023	RLB024	RLB025	RLB026	RLB027	RLB028	RLB029	RLB030	RLB031	RLB032	RLB033	RLB034	RLB035	RLB036	RLB037	RLB038	RLB040	RLB041	RLB042	RLB043	RLB044	RLB045	RLB046	RLB052	RLB055	RLB056	RLB057

ANID	macro grp	macro grp Chem2012	CERAMIC TYPE	MATERIAL	SOURCE	STATE	SITE NAME	SITE NO	AS	ΓA	Π	ND	SM	n	YB	CE CO	CR
RLB058	Group-C1	Mimbres-21	Mimbres B/W Style II	Pottery	TAM		CC:7:33/FS1138/SS71	CC:7:33/FS11	3.06	38.90	0.2771	40.80	5.26	0.92	2.23 78.78	78 10.37	70.98
RLB059	Group-C1	Mimbres-22	Mimbres B/W Style III	Pottery	TAM	ΑZ	04-174/FS253/SS35	04-174/FS253	2.53	38.41	0.2400	33.99	4.80	0.90	1.78 74.94	94 6.81	7.54
RLB060	Group-B1	Mimbres-05A	Mimbres B/W Style III?	Pottery	TAM	ΑZ	CC:10:61/FS89/SS15	CC:10:61/FS8	8.77	48.49	0.6192	1 29.09	10.13	3.03 4	4.73 104.23	23 7.86	44.28
RLB061	Group-C1	Mimbres-21	Mimbres B/W Style II/III	Pottery	TAM	AZ	CC:10:64/FS97/SS18	CC:10:64/FS9	2.55	39.26	0.3613	39.88	5.80	1.39 2	.73 77.19	92.6 61	42.04
RLB062	Group-B1	Mimbres-04B	Mimbres B/W Style III	Pottery	TAM	AZ	CC:7:34/SF1049/SS72	CC:7:34/SF10	1.72		0.5047					55 3.89	
RLB063	Group-B1	Mimbres-09	Mimbres B/W Style II/III	Pottery	TAM	AZ	CC:10:64/FS97/SS18	CC:10:64/FS9	2.38	60.03	0.4684	65.79	10.02	2.02	4.24 103.86	36 5.11	20.02
RLB064	Group-B	Unas.	Mimbres B/W Style II/III	Pottery	TAM	AZ	CC:10:62/FS55/SS16	CC:10:62/FSE	3.42	39.83	0.4165	41.09	6.21	3.73 2	2.85 78.82	32 8.66	35.82
RLB065	Group-C1	Mimbres-22	Mimbres B/W Style III	Pottery	TAM	AZ	CC:7:27/FS359/SS49	CC:7:27/FS35	2.88	44.23	0.3276	46.32	5.52	1.25 2	2.34 83.77		18.84
RLB066	Group-B1	Mimbres-05A	Mimbres B/W Style III	Pottery	TAM	AZ	04-22/FS212	04-22/FS212	6.00		0.5413	67.56	8.25			96 10.59	
RLB067	Group-B1	Mimbres-05A	Mimbres B/W Style III	Pottery	TAM	MN	M&M Brown #1	LA 002282	3.63	47.56	0.5483	51.69			3.89 97.00	00 12.32	7
RLB068	Group-C1	Mimbres-22	Mimbres B/W Style III	Pottery	TAM	MN	M&M Brown #1	LA 002282	1.91	45.73	0.3042	58.02	5.74	1.37	2.26 96.19	19 7.43	86.9
RLB069	Group-C1	Unas.	Mimbres B/W Style III	Pottery	TAM	MN	M&M Brown #1	LA 002282	11.62	38.74	0.3237	50.51	2.90	1.31	2.10 81.71	11.11	39.38
RLB070	Group-B1	Mimbres-05A	Mimbres B/W Style III	Pottery	TAM	MN	M&M Brown #1	LA 002282	3.01		0.5477	02.69		3.80 4	4.15 89.80	30 7.65	53.63
RLB071	Group-C1	Mimbres-22	Mimbres B/W Style III	Pottery	TAM	MN	M&M Brown #1	LA 002282	2.93	41.50	0.2772	49.81	5.20	1.27	1.86 83.72	12 6.91	10.42
RLB072	Clay		Clay	Clay	TAM	MN			7.87	17.46	0.5296	43.79	4.67	2.46 3	3.79 60.56	56 4.79	2.39
RLB075	Clay		Clay	Clay	TAM	¥		LA 071877	2.00	39.03	0.4201	49.17	6.79	2.23 2	2.88 87.01	14.94	42.43
RLB076	Clay		Clay	Clay	TAM	NM			3.38		0.3465	34.82	6.11			38 22.63	
RLB077	Clay		Clay	Clay	TAM	MN			2.46	39.54	0.4110	48.74	6.74	1.96 3	3.25 87.06	13.03	30.50
RLB078	Group-C2a	Mimbres-49A	Clay	Clay	TAM	MN		LA 073863	7.27	34.85	0.3745	22.96	5.39	2.29 2	2.69 66.43	11.77	40.98
RLB079	Clay		Clay	Clay	TAM	MN		LA 015058	1.49	33.48	0.3530	28.67	5.52	1.33 2	2.45 63.44	17.00	66.29
RLB080	Clay		Clay	Clay	TAM	MN		LA 000190	3.13	28.40	0.3393	26.14	2.90	1.78 2	2.29 58.81	31 22.54	35.47
RLB081	Clay		Clay	Clay	TAM	MN			2.75	40.78	0.3978	27.77	6.62	1.57	2.78 77.13	13 15.44	71.18
RLB082	Clay		Clay	Clay	TAM	MN		LA 015055	3.82	42.78	0.4161	38.18	08.9		2.86 75.37	37 11.34	52.76
RLB083	Group-C2a	Mimbres-49A	Clay	Clay	TAM	MN	NAN	LA 002465	4.45	_	0.3925	35.11	6.01		2.36 70.02		95.07
RLB084	Clay		Clay	Clay	TAM	NM	Raw Clay Locality-RLB084	84	3.33	37.91	0.2771	34.96	7.41		1.91 75.60	50 23.89	19.99
RLB085	Group-C1	Mimbres-21	Mimbres B/W Style III	Pottery	TAM	NN	Red Rock #2	LA 008706	2.71		0.3441		5.80				
RLB086	Group-C1	Mimbres-21	Mimbres B/W Style III	Pottery	TAM	M	Red Rock #2	LA 008706	3.08		0.3255		5.79			1	
RLB087	Group-C1	Mimbres-21	Mimbres B/W Style II	Pottery	TAM	MN	Red Rock #2	LA 008706	2.35		0.2967	34.61	5.46				
RLB088	Group-C1		Mimbres B/W Style III	Pottery	TAM	M	Red Rock #2	LA 008706	1.71		0.3355	37.93	5.93	1.45 2	2.54 79.02	9.99	
RLB089	Group-C2b	-1	Corrugated	Pottery	TAM	Z	Red Rock #2	LA 008706	4.55		0.2474	27.87					
RLB090	Group-B1	Mimbres-05A	Mimbres B/W Style III	Pottery	TAM	N N	Red Rock #2	LA 008706	2.95	_	0.5354				_		
RLB091	Group-B1	Mimbres-04A	Mimbres B/W Style III	Pottery	TAM	N N	Cameron Creek	LA 000190	3.56		0.4447					_	
RLB092	Group-B2	Mimbres-11	Mimbres B/W Style III	Pottery	TAM	Z	Cameron Creek	LA 000190	3.33		0.4572	21.89				_	
RLB093	Group-B1	Mimbres-04A	Mimbres B/W Style III	Pottery	TAM	N N	Cameron Creek	LA 000190	2.58	_	0.4745	29.75					_
RLB094	Group-A	Mimbres-01	Mimbres B/W Style III	Pottery	TAM	M	Cameron Creek	LA 000190	2.20		0.4539	24.22	3.88				
RLB095	Group-B1	Mimbres-04B	Mimbres B/W Style III	Pottery	TAM	M	Cameron Creek	LA 000190	2.71	_	0.5044	35.70					
RLB096	Group-B1	Mimbres-04A	Mimbres B/W Style III	Pottery	TAM	NM	Cameron Creek	LA 000190	2.46		0.3871	28.27			2.54 72.87		
RLB097	Group-B2	Mimbres-02A	Mimbres B/W Style III	Pottery	TAM	NM	Cameron Creek	LA 000190	2.30	52.57	0.5839	47.97		3.72 4	4.13 119.18	11.30	39.41
RLB098	Group-C2b		Mimbres B/W Style III	Pottery	TAM	NM	Cameron Creek	LA 000190	1.90		0.4714	45.86	6.58	2.77 2		25 11.38	23.69
RLB099	Group-B1	Mimbres-04B	Mimbres B/W Style III	Pottery	TAM	NM	Cameron Creek	LA 000190	0.00	49.72	0.4443	48.93		5.78 3	3.48 85.83	33 4.75	
RLB100	Group-C2b	Mimbres-43	Mimbres B/W Style III	Pottery	TAM	NM	Cameron Creek	LA 000190	2.03	30.60	0.1847	33.55	4.56	1.34	1.41 55.50	50 7.15	25.82
RLB101	Group-A		Mimbres B/W Style III	Pottery	TAM	MN	Cameron Creek	LA 000190	3.93		0.4786	28.12	1				
RLB102	Group-C2b		Mimbres B/W Style III	Pottery	TAM	M	Cameron Creek	LA 000190	0.00		0.3153	49.34		2.99 2		1	
RLB103	Group-B2	Mimbres-02A	Mimbres B/W Style III	Pottery	TAM	MN	Cameron Creek	LA 000190	2.39	38.80	0.4712	46.93	5.78	4.77 3	3.02 64.34	34 4.25	37.35

>	55.59	41.18	71.47	55.69	46.18	61.37	55.88	40.29	88.06	70.39	39.71	50.10	85.59	36.76	35.59	83.92	125.00	72.25	81.18	132.25	90.59	142.94	93.04	96.47	123.73	74.12	62.75	54.71	48.53	57.35	75.69	40.78	58.73	46.18	23.14	44.71	52.35	67.45	94.02	35.00	57.35	34.51	119.61	61.67
I	3118.7	2932.0				4066.1			4737.0	4485.7	1949.0	2573.9	3684.1	1858.8	875.3	5092.5	5041.8	3486.5	4084.7	4932.1	4762.3	5460.7	4133.0	6130.9		3748.5	2828.3								1271.7	2803.3		3525.4	3208.2	2458.2	2570.6			3408.8
NA	16765.0 3	9114.8 2			13079.7 2	13655.5 4		12882.5 1	14523.2 4	13121.4 4	5581.6	20679.6	17172.7	12166.9 1	2325.0	10043.1 5	12291.0 5	5028.9	18292.8 4	13861.6 4	11130.2 4	14059.8 5	13246.1 4	18699.4 6	10429.8 6	17872.3 3	16890.9 2		16688.6						8265.5		11523.2 4	10828.6 3	19349.0	11066.7 2	18953.7 2			11316.2 3
MN	,	.6 6.707	_	`	191.6 130	٠ ا	421.4 129	854.5 128	403.4 14	617.5 13	541.2 5	658.2 200	335.8 17	1154.2 12	521.7 2:	761.5 100		906.2 50	705.4 18;	719.0 138	3014.1 11	763.4 140	439.2 13.				984.0 168		`					_	192.5 8;	482.7 118	441.9 11!	356.5 108	872.9 193	309.8 110	440.2 18			182.4 11:
×		0.0						0.0	0.0	0.0	0.0	9 0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0 30	0.0	0.0	9 0.0		0.0	0.0								0.0		0.0	0.0	0.0	0.0	0.0			0.0
DY	2.812	2.579	8.778	3.579	5.421	9.905	3.816	2.606	7.337	6.717	4.402	2.505	6.482	2.858	6.322	4.396	4.315	4.329	4.224	3.923	3.486	3.890	3.995	4.005	4.409	4.377	2.640	4.326	4.443	4.031	8.015	4.643	3.919	4.858	2.476	6.254	4.199	6.023	3.636	4.795	2.624	2.500	3.512	4.732
CA	0.0	0.0	0.0			0.0	0.0	0.0	0.0	.9 0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0		0.0	0.0								0.0	0.0	0.0	0.0	0.0	0.0	0.0			0.0
A	2	6	6	8	3	8	8	3	4	4	∞.	0	0	3	9	2	9:	0	9	2	6	4	8	6	6	0	4	1	_	4	9	4	23	0	7	4	7	3	7	8	6	9	-1	7
BA	953.2	862.9	615.9			1152.8	569.8	1323.3	643.4	880.4	8.806	1021.0	759.0	1087.3	426.6	852.5	702.6	0.688	9.898	709.5	767.9	750.4	532.8	832.9	608.9		876.4			845.4	576.6				559.2	657.4	775.7	565.3	841.7	633.8	796.9		743.1	474.7
AL	79575.9	91975.1	82476.8	84233.5	83312.8	83001.7	78833.1	97715.7	83860.2	77257.1	95899.1	79028.4	85681.3	92051.2	65181.0	78797.6	92939.3	72995.5	79936.6	77883.6	62975.9	80991.9	89535.5	86614.0	96362.4	88132.5	89642.1	87504.7	78583.5	92953.6	86234.3	86066.1	77641.2	86908.6	95414.5	79953.1	82200.5	91262.7	90758.4	81365.6	91902.4	94824.0	92392.1	86523.0
ZR	178.9	166.0	206.6	211.3	280.1	222.9	175.8	142.6	165.0	216.8	152.6	154.1	156.2	152.6	82.2	194.7	206.8	177.0	229.7	228.8	158.7	236.5	205.8	292.9	209.5	201.5	236.2	226.4	190.5	158.9	228.4	164.1	204.0	254.5	171.3	173.8	260.6	210.6	155.1	142.0	112.1	188.2	163.4	178.5
NZ	78.1	83.9	70.9		53.1	73.8			9.89	65.0			1.99	71.5	35.2	70.5	70.5	84.2	64.8	82.0	136.0	120.2	102.1			7.06	102.4								39.6	37.8	22.7	68.5	85.1	60.2	86.7			58.4
H	9.23	80.6	15.54	10.08	25.00	14.16	17.33	10.03	17.37	14.08	11.00	9.95	16.54	9.92	28.43	15.49	7.02	14.41	10.89	8.75	8.42	10.35	14.41	10.33	6.07	9.85	9.95	69.6	10.50	7.90	16.67	21.44	17.65	20.91	48.05	22.51	19.20	22.00	9.76	27.18	7.36	41.65	10.09	22.51
TB	0.65	0.53	1.42	0.70	98.0	1.08	0.70	0.62	1.08	1.30	0.76	0.72	1.14	0.51	0.87	0.87	0.65	0.94	0.67	0.67	0.74	0.87	0.88	0.79	1.04	0.84	0.74	0.70	0.81	0.64	1.46	0.76	0.55	0.70	0.38	0.87	0.72	98.0	0.85	0.81	0.54	0.39	0.83	0.77
TA	0.6948	0.5881	1.2443	0.8721	1.7034	1.0069	1.6699	0.5931	1.3835	1.1876	0.5993	0.8243	1.2109	0.5987	2.1950	1.1849	0.6435	1.1454	0.9165	0.8926	0.5209	1.0105	1.1342	1.0405	0.6832	0.8859	0.7492	0.6221	0.9297	0.7201	1.2860	1.4807	1.4890	1.4177	1.9475	1.3361	1.4830	1.4374	0.5624	1.5780	0.5414	2.1622	0.6422	1.5023
SR	467.6	266.8	260.3	310.3	177.2		171.7	255.4	186.8	381.1	231.9	417.1	300.7	274.1	0.0	641.5	426.1	743.1	507.1	437.2	485.2		344.6	484.7	565.1	393.6	383.3				348.6			272.7	102.8	159.2	213.9	327.9	588.2	194.9	368.8	_		244.1
SC	7.18	4.50	1	7.04				5.20	11.16	11.61	4.45	8.19	12.25	4.64	2.42	10.75	15.54	10.40	8.38	12.03	14.35		11.92	12.60		10.40	9.12				_			6.40	4.46			11.95	11.53	6.64	7.10			11.72
SB	1.6125	4.2792	0.7395	1.1901	0.7705	0.7310	0.4518	2.2627	0.8459	0.5490	3.2412	1.6353	0.5666	3.1677	0.0000	0.6831	0.0000	0.9424	0.3915	0.4588	0.5321	0.5554	0.6154	0.4937	0.2598	1.8365	1.5954	1.0441	2.2318	0.2961	0.7974	0.3498	0.6750	0.3527	0.7860	0.5073	0.3776	0.3994	0.4529	0.3971	0.5321	0.3505	0.3175	0.4630
RB	118.30	158.20	132.80	134.30	164.40	121.10	143.50	138.70	134.20	112.80	187.90	117.40	137.60	147.60	71.30	126.40	71.10	135.00	06.66	80.30	108.40	91.50	137.30	97.30	72.30	138.40	125.20	111.40	146.30	88.80	135.80	148.00	193.80	160.00	283.70	148.10	143.70	153.40	65.70	179.40	100.90	234.00	71.40	153.10
Z	0.0	0.0			0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0			0.0				0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0			0.0
土	6.19	5.38	7.99		8.39	7.33	7.04	5.92	7.42	8.31	6.70	9.65	7.50	5.75	5.99	7.25	5.77	6.02	8.12	89.8	4.55	7.75	8.29	9.40	7.66	6.71	7.25	68.9	6.62	4.75	8.95	5.47	6.72	7.41	5.02	5.73	7.75	7.41	5.46	5.59	4.15	7.30	5.44	8.58
FE	27391.9	18768.9	23570.0	25967.9	20719.2	26614.6	30390.0	25344.2	31155.0	30760.9	21028.3	32283.6	29501.8	18948.6	7757.9	35107.7	50031.9	31819.9	32828.7	1.3865 53724.9	44502.0	55969.2	42157.3	45794.7	57827.4	35010.8	34531.2	25278.9	27329.6	26498.8	25690.8	20737.6	21915.7	19156.3	11914.8	20441.0	25884.6	28273.4	45120.1	20306.8	28222.2	17417.2	49504.0	25630.0
EN	1.2580	1.2482				2.0792			1.5104	1.6685		1.3902	1.6637	1.2218	0.2632	1.4498	1.6255	1.3194	1.3369	.3865	1.4111	1.6322	1.3875		2.0044	1.5236	1.4321								0.5172	1.2765	1.1544	1.5096	1.6246	1.1323	1.2056			1.1512
CS	17.94	39.83				5.58 2		23.92	6.47	5.98	34.60 1	12.40	6.16	24.38 1	0.84 0		2.75	10.41	3.43	3.08	4.98	3.51	5.82	3.42	4.97	16.88 1									17.17 0	4.75	5.31	26.44	4.82	5.95	5.35	9.63 0		23.38 1
ANID	RLB058	RLB059	RLB060	RLB061	RLB062	RLB063	RLB064	RLB065	RLB066	RLB067	RLB068	RLB069	RLB070	RLB071	RLB072	RLB075	RLB076	RLB077	RLB078	RLB079	RLB080	RLB081	RLB082	RLB083	RLB084	RLB085	RLB086	RLB087	RLB088	RLB089	RLB090	RLB091	RLB092	RLB093	RLB094	RLB095	RLB096	RLB097	RLB098	RLB099	RLB100	RLB101	RLB102	RLB103

ANID	macro grp	Chem2012	CERAMIC TYPE	MATERIAL	SOURCE	STATE	SITE NAME	SITE NO	AS	ΓA	ΠΠ	ND	SM	'n	YB CE	00	CR
RLB104	Group-B	Unas.	Mimbres B/W Style III	Pottery	TAM	MN	Cameron Creek	LA 000190	3.21	39.84	0.3470	37.78	4.78 4.	4.28 1.85	35 76.19	9 5.32	29.07
RLB105	Group-B2	Mimbres-11	Mimbres B/W Style III	Pottery	TAM	MN	Cameron Creek	LA 000190	2.34	34.03	0.5088	28.72 4	4.60 5.	5.80 2.94		18.92	42.73
RLB106	Group-B1	Mimbres-04A	Mimbres B/W Style III	Pottery	TAM	MN	Cameron Creek	LA 000190	4.27	42.51	0.4553	46.08 6	6.63 4.	4.52 2.97	7 80.92	2 6.73	23.02
RLB107	Group-A	Mimbres-01	Mimbres B/W Style III	Pottery	TAM	MN	Cameron Creek	LA 000190	0.00	56.49 C	0.6124	32.14 4	4.35 15.	5.04 3.09	90.19	9 4.16	6.28
RLB108	Group-C1	Mimbres-21	Mimbres B/W Style III	Pottery	TAM	NM	Cameron Creek	LA 000190	0.00								63.30
RLB109	Group-C2b	Mimbres-44	Mimbres B/W Style II	Pottery	TAM	NM	Cameron Creek	LA 000190	3.29	40.79 C	0.3004		6.49 3.	3.85 2.39	13.64	10.87	22.51
RLB110	Group-B	Unas.	Mimbres B/W Style II	Pottery	TAM	M	Woodrow	LA 002454	0.00	36.60		39.26 E	5.29 1.	1.49 2.21	75.69		49.20
RLB111	Group-C1	Mimbres-21	Mimbres B/W Style III ?	Pottery	TAM	M	Woodrow	LA 002454	0.00						68.01		47.53
RLB112	Group-C1	Mimbres-22	Unslipped	Pottery	TAM	NM	Woodrow	LA 002454	0.00		0.2354		5.18 2.	2.14 1.92			34.21
RLB113	Group-C1	Mimbres-21	Mimbres B/W Style II	Pottery	TAM	MN	Woodrow	LA 002454	3.64	40.50	0.3203	33.41 5	5.87 1.	1.18 2.26			49.00
RLB114	Group-C1	Mimbres-21	Mimbres B/W Style III	Pottery	TAM	MN	Woodrow	LA 002454	0.00	44.30	0.3667	33.04 6	6.18 1.	1.79 2.61	91.99	12.94	81.80
RLB115	Group-C1	Mimbres-21	Mimbres B/W Style Indeter.	Pottery	TAM	MN	Woodrow	LA 002454	2.52	44.45	0.3808	36.46 6	6.61 2.	2.16 2.55	5 82.39	9 9.30	42.49
RLB116	Group-A	Mimbres-01	Mimbres B/W Style III	Pottery	TAM	MN	Woodrow	LA 002454	3.37	64.78	0.6991	43.58 4	4.42 14.	14.15 3.71	71 94.33	3 2.43	4.76
RLB117	Group-C1	Mimbres-21	Mimbres B/W Style II	Pottery	TAM	NM	Woodrow	LA 002454	0.00	38.61	0.2987		5.67 1.	1.32 2.02	12 82.24	11.67	44.57
RLB118	Group-C1	Mimbres-21	Mimbres B/W Style II ?	Pottery	TAM	NM	Woodrow	LA 002454	0.00	37.94 0	0.2533	29.45 5	5.17 1.	1.36 2.01	10.74	10.08	37.93
RLB119	Group-C1	Mimbres-21	Mimbres B/W Style III	Pottery	TAM	NM	Woodrow	LA 002454	1.73		0.4083		6.39 1.	1.95 2.88		7 10.51	59.87
RLB120	Group-C1	Mimbres-21	Mimbres B/W Style III	Pottery	TAM	NM	Woodrow	LA 002454	6.04	41.38			5.70 0.			5 9.72	35.46
RLB121	Group-C1	Mimbres-22	Unslipped B/W	Pottery	TAM	MN	Woodrow	LA 002454	00.00	41.30	0.3335	34.37 5	5.11 1.	1.24 2.00	00 75.26	6.14	7.43
RLB122	Group-C1	Mimbres-21	Mimbres B/W Style II	Pottery	TAM	NM	Woodrow	LA 002454	3.37	40.91 C	0.3140	27.84 5	5.29 1.	1.40 1.97	77.58	3 7.71	41.12
RLB123	Group-C1	Mimbres-21	Mimbres Polychrome ?	Pottery	TAM	MN	Woodrow	LA 002454	00.00	37.76	0.3373		5.29 1.	1.77 2.28	11.69 89	1 9.28	38.98
RLB124	Group-C1	Mimbres-22	Mimbres B/W Style III	Pottery	TAM	MN	Woodrow	LA 002454	00.00	44.89	0.3600	30.67	5.51 1.	1.44 1.68	82.08	8 6.87	16.33
RLB125	Group-C1	Mimbres-21	Mimbres B/W Style III	Pottery	TAM	MN	Woodrow	LA 002454	3.23	40.48	0.3695	30.00	6.21 1.	1.51 3.13	3 75.84	11.17	43.57
RLB126	Group-C1	Mimbres-21	Mimbres B/W Style I?	Pottery	TAM	MN	Woodrow	LA 002454	00.00	36.39	0.3095	34.73 5		1.33 2.09	13.39	8.75	45.13
RLB127	Group-C1	Mimbres-21	Mimbres B/W Style III	Pottery	TAM	NM	Woodrow	LA 002454	2.54					1.20 2.77			46.03
RLB128	Group-C1	Mimbres-21	Mimbres B/W Style III	Pottery	TAM	M	Woodrow	LA 002454	2.77	41.82				1.80 2.78		3 12.04	81.21
RLB129	Group-C1	Mimbres-21	Mimbres B/W Style III	Pottery	TAM	M	Woodrow	LA 002454	4.51								71.52
RLB130	Group-C1	Mimbres-21	Mimbres B/W Style III	Pottery	TAM	M	Woodrow	LA 002454	1.73					1.86 2.49			70.98
RLB131	Group-C1	Mimbres-21	Mimbres B/W Style II	Pottery	TAM	M	Woodrow	LA 002454	5.52			_					43.50
RLB132	Group-C1	Mimbres-21	Mimbres B/W Style III	Pottery	TAM	M	Woodrow	LA 002454	0.00				6.50 2.	2.02 2.55	1	5 10.38	49.30
RLB133	Group-C1	Mimbres-21	Mimbres B/W Style II	Pottery	TAM	NM	Woodrow	LA 002454	0.00							_	40.24
RLB134	Group-B	Unas.	Mimbres B/W Style III	Pottery	TAM	Σ	Woodrow	LA 002454	0.00	-							23.14
RLB135	Group-C1	Mimbres-22	Mimbres B/W Style III	Pottery	TAM	M	Woodrow	LA 002454	0.00	_							7.77
RLB136	Group-C1	Mimbres-21	Mimbres B/W Style II	Pottery	TAM	MN	Woodrow	LA 002454	1.86								40.63
RLB137	Group-C1	Mimbres-21	Mimbres B/W Style III	Pottery	TAM	M	Woodrow	LA 002454	0.00			22.29	5.45 1.	1.30 1.72	72 80.02		29.38
RLB138	Group-C1	Mimbres-21	Mimbres B/W Style III	Pottery	TAM	NM	Woodrow	LA 002454	0.00	38.51	0.3026	21.03 5	5.62 1.	1.20 2.63	3 77.79	10.39	51.75
RLB140	Group-C1	Mimbres-21	Mimbres B/W Style III ?	Pottery	TAM	NM	Woodrow	LA 002454	0.00		~					1	73.22
RLB141	Group-A	Mimbres-01	Mimbres B/W Style III	Pottery	TAM	NM	Woodrow	LA 002454	0.00	25.56 C			4.35 10.	10.52 2.92	92.09	9 2.09	6.36
RLB142	Group-C1	Mimbres-21	Mimbres B/W Style II?	Pottery	TAM	NM	Woodrow	LA 002454	0.00	36.41	0.2334		5.20 1.	1.15 2.21	21 80.72	2 8.01	41.13
RLB143	Group-C1	Unas.	Smudged Corrugated	Pottery	TAM	NM	Woodrow	LA 002454	0.00		0.2527		5.63 1.	1.23 2.55		9.15	28.67
RLB144	Group-C1	Mimbres-21	Mimbres B/W Style II	Pottery	TAM	NM	Woodrow	LA 002454	3.05	39.06	0.2695		5.62 1.	1.30 2.08	73.26	5 8.94	42.86
RLB145	Group-C1	Mimbres-21	Mimbres B/W Style II	Pottery	TAM	M	Woodrow	LA 002454	1.91				4.78 1.	1.14 1.69			34.40
RLB146	Group-C1	Mimbres-21	Mimbres B/W Style III	Pottery	TAM	NM	Woodrow	LA 002454	2.51			_				_	50.94
RLB153	Group-B1	Mimbres-04A	Mimbres B/W Style III	Pottery	TAM	M	Treasure Hill	LA 016241	1.93								19.99
RLB154	Group-B1	Mimbres-04A	Mimbres B/W Style III	Pottery	TAM	NM	Treasure Hill	LA 016241	2.12	47.84 C	0.4402	42.99 6	6.45 3.	3.58 3.33	83 86.89	9 5.45	18.06

>	53.53	53.63	86.09	21.37	70.20	96.57	50.59	62.45	42.25	62.55	68.92	59.61	0.00	59.31	52.84	76.37	65.88	39.90	0.00	57.84	42.84	71.47	0.00	57.94	70.20	52.06	52.35	61.18	60.49	0.00	0.00	0.00	52.25	74.22	61.57	68.92	13.82	45.88	0.00	55.20	44.02	69.31	58.92	39.31
Ξ	3276.2	2779.8	4238.5	1600.2	2506.2	3260.9	2562.9	2220.7	1891.6	2556.4	2868.5	2172.3	1625.3	3447.5	2543.7	2680.9	2585.2	1684.5	2165.7	2075.5	1709.8	3033.5	1802.4	3050.4	3224.8	2048.9	3098.8	3201.1	2579.0	2545.5	2251.9	2088.4	2660.3	2665.2	2722.1	3027.1	0.0	1999.4	3809.2	2282.7	2045.9	3303.3	3029.9	3385.4
NA	14014.6	9646.4	14303.4	15172.6	15889.8	18414.6	18682.2	16581.4	14433.7	15337.1	16734.6	15851.9	23056.4	16469.0	12566.5	15003.1	13518.7	11094.9	15173.5	16466.3	12662.8	14492.3	16010.3	19409.1	21193.1	19724.8	21119.8	19541.4	23226.6	18280.8	15282.6	12203.1	14803.7	10206.9	14426.1	14801.7	16572.5	12047.6	13805.1	16721.8	17509.3	17891.4	15201.2	15499.5
MN	171.4	1358.9	521.0	196.3	952.3	8.678	1146.3	912.6	865.3	897.0	1021.9	963.7	199.4	943.2	864.3	93.6	881.2	1036.3	6.886	979.4	7.677	729.1	1062.1	936.8	995.0	926.1	890.5	1058.2	0.896	895.0	165.4	859.9	945.8	870.1	1107.6	971.3	473.9	1095.4	436.1	971.8	1031.6	871.1	318.2	554.5
~	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
Dγ	3.196	4.669	4.167	3.453	2.630	5.018	3.238	3.561	3.129	5.969	3.551	4.065	2.548	3.818	3.290	4.484	3.664	3.134	3.237	3.749	5.013	4.006	3.609	2.753	5.630	4.409	3.860	4.154	3.809	2.748	4.860	3.428	3.281	2.952	4.362	3.619	1.712	2.729	3.967	3.936	3.293	4.153	5.124	3.888
CA	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0:0	0.0	0.0	0.0
BA	601.1	621.4	894.0	480.8	955.0	882.3	2295.8	903.8	1110.9	934.8	1109.6	9.668	334.1	1006.0	893.5	872.6	836.9	855.1	914.9	843.9	983.2	803.3	7.197	1396.1	873.2	1011.4	923.9	1016.0	936.6	935.2	676.5	622.1	915.9	773.4	786.1	1001.0	630.9	1530.4	973.3	784.5	0.789	1010.5	710.2	839.9
AL	84475.5	76904.9	81345.5	98910.1	88798.4	86249.5	81034.3	88743.1	86508.0	90168.5	81374.4	84555.6	106946.1	88780.5	84394.7	9:0/658	92746.5	90205.7	78988.5	81060.9	90483.3	92432.2	80445.2	84143.7	83880.3	88114.7	83648.8	89138.9	83426.3	87275.9	80981.0	01452.7	82552.7	91028.2	87287.6	85055.1	98480.6	80181.6	91793.7	88207.2	79263.9	85850.2	87797.4	80221.6
ZR	189.7	136.9	215.1	168.6	112.9	125.6	152.7	169.0	144.2	168.3	248.6	169.2	228.4	148.1		141.9	141.2	118.9	129.5	140.4	143.3	151.9	140.0	183.2	175.3	193.2	213.4				'	_		166.2	204.9			205.3	205.8		133.9	196.2	230.8	158.8
NZ		56.2		47.1	80.7		74.3	70.0	71.7	83.9	92.3	7.67	42.7	83.3			77.1	76.1	69.1		84.2	87.0	79.5		91.5	9.06	79.0	93.1	85.6		_		86.5	90.7	92.5				89.7	74.1				60.4
3 TH		7 18.16		Ľζ			13.39	1 8.61	9 9.21	7 9.39	2 11.25	7 10.50	3 56.80	1 9.34		10.18	8.98	9.13	7 8.80				8.89	5 10.09		7 11.81			_			_						1			_	_		1 20.09
A TE	4 0.58	5 0.57	8 0.69		69.0 9	8 0.73	1 0.70	9 0.61	8 0.59	6 0.77	8 0.82	0 0.77	3 0.38	0 0.74	5 0.58	1 0.84	6 0.63	2 0.60	6 0.57	7 0.63	0 0.58	9 0.73	5 0.58	4 0.65		8 0.67	3 0.71				_	_					0 0.48	5 0.71						9 0.84
TA	,	1.4285	_		0.6756	l I	0.8251	0.7129	0.6508	0.8426	0.8488	0.9050	2.8013	0.8100			0.6136	0.5682	0.6196	0.6407	0.7050	0.8809	0.6255	0.7544	٠ ا					_														1.2839
SR	236.5	186.7	286.5	94.2	381.0	522.5	397.7	378.9	359.8	331.9	378.0	346.7	109.4	468.9	489.2	310.0	373.0	447.8	403.9	431.9	304.5	351.6	396.7	391.7	292.7	315.9	335.6	369.0	420.2	405.5	155.6	254.0	393.1	378.5	393.7	416.9	147.5	371.6	336.3	315.8	445.4	381.5	251.1	273.0
SC	8.04	8.18	8.30	4.38	8.11	10.78	6.94	68.9	4.93	7.40	8.17	6.62	4.11	7.45	6.29	8.47	8.00	4.20	5.86	96.98	4.99	9.23	6.37	8.39	9.42	9.91	8.45	7.82	8.08	7.81	6.94	4.78	7.01	7.07	7.61	8.60	4.63	6.54	8.67	7.32	5.53	8.52	7.51	6.36
SB	0.6863	0.7134	0.3283	0.8270	3.0562	0.2633	1.2649	0.9762	1.4304	1.2229	1.5031	1.2063	0.6062	1.6721	1.2849	1.5777	1.4342	2.0838	1.1879	1.1203	2.0842	1.5384	0.9987	1.3777	1.8150	1.8249	1.7601	1.9279	1.1891	1.1675	0.9655	1.6434	1.2613	1.2530	1.4010	1.4878	0.8081	1.1267	0.6479	1.0615	1.0320	1.6530	0.0000	0.3369
RB	155.60	199.30	135.00	228.80	133.70	73.90	124.00	111.70	112.60	120.80	115.40	137.20	221.00	114.40	09.66	124.60	105.90	113.50	110.10	104.80	123.10	114.90	112.00	128.30	144.50	153.70	147.90	128.70	131.00	121.80	197.20	144.20	123.70	108.20	128.00	121.80	205.00	126.10	109.30	120.40	119.70	126.60	130.70	134.00
Z	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0			0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
生	7.00	6.30			6.03	5.39		5.92	5.72	92.9		6.50	7.35	91.9			5.76	5.63	5.98	6.03		6.05	6.18			7.81	7.25	6.22	6.95	6.19	6.11							6.31			2.67			5.99
FE	29924.8	25968.4			27058.9	44274.4	25219.3	28353.1	21898.4	31086.6	35065.4	27054.3	16611.0	30964.3		29112.9	30380.4	19165.5	22355.0	26285.6	21694.4	33299.0	23511.8	31730.0						30904.0								22986.9	36411.8	26841.3	21161.1			22348.3
EU		0.9515				1.6174	1.2970	1.2818	1.1810	1.3633	1.3712	1.3817	0.6240	1.4729			1.3671	1.2624	1.1295	1.1585	1.3320	1.3444	1.0651	1.4384												1.2884		1.2537	`		1.2323			1.3188
CS	6.63	7.49	5.43	20.66	16.24	3.04	16.46	17.31	12.53	19.64	12.58	16.45	20.81	21.12	23.61	14.50	24.72	24.56	18.48	17.21	23.02	17.55	17.26	18.78	13.98	18.29	14.43	18.60	16.70	17.54	8.24	21.31	17.04	17.85	17.45	20.09	15.44	17.40	12.55	18.45	18.54	17.23	4.08	4.66
ANID	RLB104	RLB105	RLB106	RLB107	RLB108	RLB109	RLB110	RLB111	RLB112	RLB113	RLB114	RLB115	RLB116	RLB117	RLB118	RLB119	RLB120	RLB121	RLB122	RLB123	RLB124	RLB125	RLB126	RLB127	RLB128	RLB129	RLB130	RLB131	RLB132	RLB133	RLB134	RLB135	RLB136	RLB137	RLB138	RLB140	RLB141	RLB142	RLB143	RLB144	RLB145	RLB146	RLB153	RLB154

ANID	macro grp	macro grp Chem2012	CERAMIC TYPE	MATERIAL	SOURCE	STATE	SITE NAME	SITE NO	AS	ΓA	In	ND SM	Π	YB	CE	00	CR
RLB155	Group-B1	Mimbres-05A	Mimbres B/W Style III	Pottery	TAM		Treasure Hill	LA 016241		58.38 0.4941	941 60.02	10.08	3 4.05	3.74	119.73	12.81	49.90
RLB157	Group-C1	Unas.	Mimbres B/W Style III	Pottery	TAM	MN	Treasure Hill	LA 016241	3.19	41.26 0.497	977 45.74	74 7.84	1.77	3.76	83.97	9.81	57.92
RLB159	Group-C2b		Mimbres B/W Style II?	Pottery	TAM	NM	Cameron Creek	LA 000190	4.17	32.82 0.2	0.2949 26.75	75 4.75	5 1.56	1.74	69.69	9.83	22.08
RLB161	Group-C2	Unas.	Three Circle Corrugated	Pottery	TAM	NM	Cameron Creek	LA 000190	3.47	33.37 0.3.	0.3296 31.51	51 5.74	1 2.41	2.25	97.31	14.72	30.29
RLB163	Group-B1	Mimbres-04A	Mimbres B/W Style III	Pottery	TAM	NM	Cameron Creek	LA 000190						2.99	92.83	4.92	20.02
RLB164	Group-C2	Unas.	Alma Neckbanded	Pottery	TAM	MM	Cameron Creek	LA 000190						1.56	45.74	7.12	14.82
RLB165	Group-C2	Unas.	Mimbres B/W Style III	Pottery	TAM	M	Cameron Creek	LA 000190		33.71 0.2	0.2336 25.52		3 1.06	1.37	57.12	8.29	33.93
RLB166	Group-C2b		Mimbres B/W Style III	Pottery	TAM	M	Cameron Creek	LA 000190						2.59	85.90	12.07	27.47
RLB168	Group-C2	Unas.	Mimbres B/W Style III	Pottery	TAM	NM	Cameron Creek	LA 000190							43.92	4.41	8.62
RLB175	Group-B	Unas.	Mimbres B/W Style III	Pottery	TAM	MN	Cameron Creek	LA 000190		54.77 0.5700		51 9.94	4.01		105.93	2.98	11.31
RLB176	Group-B1	Mimbres-04A	Mimbres B/W Style III	Pottery	TAM	MN	Cameron Creek	LA 000190	7.55	47.32 0.4564	564 56.94	94 7.42	3.16	3.38	87.49	6.41	20.08
RLB178	Group-A	Mimbres-10	Plain, Polished	Pottery	TAM	MN	Cameron Creek	LA 000190	2.47	54.94 0.9	0.9506 66.46	46 9.96	6.09	6.81	105.85	7.02	33.07
RLB189	Group-B1	Mimbres-04A	Mimbres B/W Style III	Pottery	TAM	MN	Cameron Creek	LA 000190		50.44 0.6	0.6385 57.67	57 9.20	7.51		108.90	6.32	18.90
RLB190	Group-A	Mimbres-01*	Corrugated	Pottery	TAM	NM	Cameron Creek	LA 000190	0.00		0.8646 75.82	32 11.21	1 6.79	5.35	97.59	2.16	11.94
RLB191	Group-C2b	Mimbres-43	Mimbres Polychrome	Pottery	TAM	NM	Treasure Hill	LA 016241	2.15				3 1.43	1.48	26.66	8.11	28.25
RLB192	Group-C2b		Mimbres Polychrome	Pottery	TAM	NM	Treasure Hill	LA 016241	0.00			08 4.79		2.02	56.99	7.89	27.95
RLB193	Group-C2b	Mimbres-43	Mimbres Polychrome	Pottery	TAM	NM	Treasure Hill	LA 016241			33.66		4 0.95	1.67	56.73	7.97	28.72
RLB194	Group-C1	Unas.	Mimbres Polychrome	Pottery	TAM	MN	Treasure Hill	LA 016241		29.03 0.1972	31.17		5 1.15	1.71	55.02	7.84	28.50
RLB195	Group-C1	Mimbres-21	Mimbres B/W Style Indeter. Pottery	. Pottery	TAM	MN	Treasure Hill	LA 016241	3.99	40.15 0.3171	171 38.39	39 5.84	1.17	2.67	79.51	11.15	52.00
RLB196	Group-C2a	Mimbres-42	Mimbres B/W Style III	Pottery	TAM	MN	Treasure Hill	LA 016241	3.70	39.25 0.3311	311 42.86	36 5.92	2 1.42	1.76	72.27	16.21	58.16
RLB197	Group-B	Unas.	Mimbres B/W Style III	Pottery	TAM	MN	Treasure Hill	LA 016241	7.03	46.17 0.3589	589 33.79	79 4.54	4.96	2.54	19.89	4.28	11.51
RLB198	Group-B1	Mimbres-04B	Mimbres B/W Style III	Pottery	TAM	MN	Treasure Hill	LA 016241	1.64	55.24 0.4225	225 51.38	38 7.41	1 6.12	3.57	91.22	4.53	20.50
RLB199	Group-B1	Mimbres-04A	Mimbres B/W Style III	Pottery	TAM	NM	Treasure Hill	LA 016241							73.46	6.95	18.98
RLB200	Group-B1	Mimbres-04A	Mimbres B/W Style III	Pottery	TAM	MN	Treasure Hill	LA 016241			0.5756 74.21	_	4 5.30	4.27	117.21	7.09	21.92
RLB201	Group-B1	Mimbres-05A	Mimbres B/W Style III	Pottery	TAM	NM	Treasure Hill	LA 016241		52.80 0.5729			5 4.08	3.69	89.71	5.95	53.82
RLB202	Group-B1	Mimbres-04B	Mimbres B/W Style Indeter. Pottery	. Pottery	TAM	NM	Treasure Hill	LA 016241		55.15 0.4501				2.95	100.23	5.33	25.47
RLB203	Group-A	Mimbres-01	Mimbres B/W Style III	Pottery	TAM	M	Treasure Hill	LA 016241						2.16	68.83	2.87	6.59
RLB204	Group-C1	Mimbres-21	Mimbres B/W Style II	Pottery	TAM	MN	Treasure Hill	LA 016241						1.76	80.23	8.41	36.95
RLB205	Group-B2	Mimbres-02A	Mimbres B/W Style III	Pottery	TAM	M	Treasure Hill	LA 016241	0.00					2.86	10.99	4.23	33.23
RLB206	Group-C1	Mimbres-21	Mimbres B/W Style III	Pottery	TAM	MN	Treasure Hill	LA 016241						_	75.33	8.19	50.99
RLB207	Group-B1	Mimbres-04B	Mimbres B/W Style III	Pottery	TAM	N N	Treasure Hill	LA 016241						\rightarrow	107.15	11.33	25.37
RLB208	Group-B	Unas.	Mimbres B/W Style III	Pottery	TAM	Z	Treasure Hill	LA 016241							92.12	5.94	30.42
RLB209	Group-B	Unas.	Mimbres B/W Style II	Pottery	TAM	M	Treasure Hill	LA 016241							107.97	2.78	16.82
RLB210	Group-B	Unas.	Mimbres B/W Style III	Pottery	TAM	MN	Treasure Hill	LA 016241								3.35	28.58
RLB211	Group-B2	Mimbres-02A*	Mimbres B/W Style III	Pottery	TAM	M	Treasure Hill	LA 016241					5.93	5.10		14.93	34.15
RLB212	Group-C1	Mimbres-21	Mimbres B/W Style III	Pottery	TAM	NM	Treasure Hill	LA 016241		37.33 0.2812		34 5.70	1.03	2.16	74.17	13.07	56.56
RLB213	Group-C1	Mimbres-22	Mimbres B/W Style III?	Pottery	TAM	MN	Treasure Hill	LA 016241	7 00'0	40.05 0.2921	921 43.47	47 4.77	1.06	2.11	80.35	88.9	8.77
RLB214	Group-B	Unas.	Mimbres B/W Style III	Pottery	TAM	NM	Treasure Hill	LA 016241	1.70	43.01 0.4021	121 41.32		3 4.35	2.55	69.89	4.24	31.53
RLB215	Group-B1	Mimbres-04A	Mimbres B/W Style II	Pottery	TAM	NM	Treasure Hill	LA 016241					1 4.86		101.89	5.20	18.06
RLB216	Group-B1	Mimbres-09	Mimbres B/W Style III	Pottery	TAM	NM	Treasure Hill	LA 016241		55.83 0.5	0.5226 53.12	12 10.23	3 3.27	4.20	111.17	2.26	16.49
RLB217	Group-B2	Mimbres-02A	Mimbres B/W Style III	Pottery	TAM	NM	Treasure Hill	LA 016241	7.83	40.26 0.4487	187 29.97	90.9 /6	5 4.61	3.18	09.99	5.40	35.31
RLB218	Group-B1	Mimbres-04B	Mimbres B/W Style III?	Pottery	TAM	M	Treasure Hill	LA 016241						3.21	87.23	5.47	20.77
RLB219	Group-B	Unas.	Mimbres B/W Style III	Pottery	TAM	MN	Treasure Hill	LA 016241						3.41	98.94	7.01	29.07
RLB220	Group-A	Mimbres-01	Mimbres B/W Style III	Pottery	TAM	NM	Treasure Hill	LA 016241	2.30	78.69 0.6105	105 34.66	56 5.31	1 9.95	3.47	100.54	2.04	8.28

>	78.92	19.99	73.24	82.16	48.92	81.08	75.49	98.63	45.59	36.57	61.67	47.06	46.96	28.53	65.20	70.39	58.33	69.09	63.14	84.71	51.18	42.45	26.08	50.39	77.94	51.37	27.45	49.12	40.69	45.20	46.76	60.09	30.08	75 20	62.52	35.78	58 43	40.10	48.73	68.24	55.00	50.00	24.31
F	3752.0	3497.9	3622.8	2932.4	3046.5	3191.3	2057.0	3530.0	2151.4	2596.4	2351.7	4214.6	2679.3	1238.9	1840.5	2705.2	2611.0	2218.4	2631.7	3622.3	2483.9	2544.4	2984.4	2898.2	4073.6	1754.2	1929.2	1850.4	3138.7	2789.2	3325.2	0.000	3039.2	2301.0	282/10	1214.7	2539 5	3121.5	3013.2	2494.9	2362.1	3467.6	1894.8
NA	11370.8	16350.7	17253.3	18118.8	12903.4	2909.0	12994.7	15392.6	24903.2	17948.6	15849.1	17722.1	14356.6	5963.4	16152.4	16358.6	15978.0	16677.5	18062.3	22554.7	12463.2	10468.9	16257.4	14908.0	14489.9	9453.1	7229.8	17182.8	10484.3	17163.0	9585.4	14/08.0	116600	17306.0	106000	10514.2	112180	16046.1	16835.1	13592.3	11855.6	18311.4	10317.0
MN	602.0	764.7	468.6	1305.6	253.7	376.6	533.2	872.5	175.5	454.4	321.8	872.9	278.1	749.2	542.1	503.8	490.4	486.8	0.968	670.1	249.6	290.5	508.8	327.2	256.7	205.4	206.0	993.1	189.4	933.7	530.3	271.2	100 7	100.7 7 7 7 7 7 7 7 7 7 7 7 7 7 7 7 7 7 7 7	1045.1	763.5	211.8	408.4	281.0	249.5	404.1	2.909	278.8
~	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
DY	5.991	7.730	3.249	3.646	5.368	1.843	2.070	5.260	1.867	7.353	6.540	9.262	6.954	7.325	2.441	3.561	2.655	2.935	3.395	2.826	3.381	5.294	5.157	6.645	6.363	5.520	1.758	2.331	3.925	3.691	6.568	4.949	5.703	6.037	3 166	2.528	4 427	4.312	6.925	3.523	5.222	4.885	3.255
CA	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
BA	532.4	749.8	1019.8	1014.2	872.4	906.2	1123.5	831.7	714.4	1161.2	917.5	624.4	835.6	97.29	652.2	705.2	694.5	763.4	854.4	1180.3	509.4	630.4	927.6	863.2	784.1	685.9	7.907	1051.5	460.3	1265.8	787.8	844.5	1.001.7	541.3	041.3	863.7	621.7	908.4	1125.7	542.6	614.6	1044.0	554.0
AL	87148.8	78875.3	84378.0	77682.1	82844.2	88678.3	9.85016	94520.3	92080.3	81018.4	82703.6	82823.2	83546.8	84164.4	93792.7	97848.9	92044.6	9.50868	85138.1	95457.7	94186.4	84132.9	80092.6	81882.6	88854.0	87579.8	83025.4	9.70708	83682.1	80035.5	85373.1	1,4454.0	03332.I	8106F 1	986/17	93643.6	89159 4	80002.9	86212.6	86802.0	79638.4	79963.7	104207.2
ZR		192.4	176.2			131.3	93.0	166.6	103.7	256.3		269.5	211.7	174.2	97.2			144.9	133.2			165.9	181.1	197.1									244.3							174.3	178.2	316.0	164.5
NZ	73.6	83.4					94.0	1	53.2	76.3	58.4	107.3	72.5	64.9	102.8				88.1		54.4	58.8	54.4	11.6		, 56.5							0.00								43.4		48.7
B T	17.26	8 12.98				3 10.58	7.64	0 10.25	8 5.30	14.07	3 17.78	9 37.21	0 18.26		8 7.31	3 7.56		3 7.50	89.6	9 8.75		8 26.54	2 16.92				7		(7			_	7 19.10							19.01	9 28.20		7 52.99
TA T	1.26	1.1828 1.18	58 0.55	31 0.63		99 0.33	83 0.66	37 0.90	10 0.38	1.26		87 1.59	1.20	1.46	02 0.58	05 0.63	76 0.56	87 0.53	29 0.78	69.0 86	67 0.54	1.08	181 0.82	34 1.32		1.5506 0.98							09 0.99					_		_	00 0.99		07 0.57
	`	,	3 0.9058	_		4 0.7399	4 0.5783		7 0.3710	1.0862	9 1.3459	5 2.0487	03621.3	8 1.8981	0 0.5302			3 0.5087	2 0.7129	8699.0 8	7 1.4467	7 1.4909	3 1.1981	3 1.3134	,	`		_		_			0 1.2/09					Ι.	1	7 1.3747	0095.1		7 2.2307
SR	254.7	283.9				342.4	475.4	572.6	650.7	248.1		285.5	316.6	65.8	296.0			353.3	336.2	540.8	175.7	115.7	306.3	240.3									10.07								9.96		124.7
SC	11.83	8.65		8.32	7.60	7.15	8.33	13.07	4.12	8.46		8.75	7.71	7.88	7.57	7.76		7.84	8.41	1	6.59	7.49	6.37	8.57	l					~			0 10				,			1	7.03		5.00
SB	0.4992	1.7248	0.3105	0.5122	0.3986	0.4630	0.3246	0.3980	0.2070	0.5891	0.2794	0.5134	0.3366	0.4536	0.5051	0.6117	0.6553	0.6406	1.2950	0.4094	0.4607	0.4543	0.3310	0.0000	0.6380	0.3364	0.4844	1.4776	0.4186	1.4166	0.4759	0.5365	1 1422	0.3425	1 5666	3.4016	0.8195	0.2574	0.7413	0.0000	0.5027	0.7351	0.5913
RB	119.80	134.00	89.20	113.40	140.40	94.20	104.50	77.40	49.10	118.00	136.10	189.90	112.20	297.10	107.70	109.30	103.10	102.30	111.40	77.90	239.00	183.40	130.40	124.50	137.40	153.90	259.00	130.40	176.20	126.40	179.00	152.40	170 50	1/5/10	125.00	152.90	164 40	143.20	117.60	139.60	165.20	132.50	276.10
Z	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0		0.0	0.0	0.0	0.0	0.0	0.0			0.0	0.0	0.0	0.0	0.0	0.0		0.0
±	7.27	8.01	6.21			5.20	4.05	5.56	3.79	9.11	6.44	11.12	6.94	4.70	3.91	4.52	4.31	4.27	6.28	5.63	90.9	5.53	6.18	7.50	7.87	5.94	5.93			6.40	6.82	0.84	10.01			6.77	7.20	8.70			5.88		6.03
H	34356.1	31409.8				35671.6	34829.5	49280.2	19682.4	20349.7	24654.0	31848.1	27192.9	26393.2	30836.0			30723.6	32075.8	41119.4	19239.4	22088.0	23741.2					_	_		_		24111.8										14485.9
ED	1.7434	1.4037			1.4485	0.8937	1.3573	1.8028	1.1364	2.1322		1.3064	1.6590	1.2609	1.1805	1.2135		1.1941	1.2381	1.5400	0.9211	1.3201	1.2862	1.8588	1.6522								1.7444							1.2079	1.3686	1.7453	0.7606
CS	7.15	12.46	2.95	5.80	4.94	2.71	4.81	3.85	1.59	3.63	3.83	3.69	4.62	12.28	6.02	6.31	6.64	8.86	17.29	2.68	14.67	6.34	3.92	4.62	7.52	5.90	35.55	20.52	17.81	19.85	6.30	4.48	4.31	0.10	15.32	24.29	13.12	4.07	4.78	16.49	5.26	18.05	15.67
ANID	RLB155	RLB157	RLB159	RLB161	RLB163	RLB164	RLB165	RLB166	RLB168	RLB175	RLB176	RLB178	RLB189	RLB190	RLB191	RLB192	RLB193	RLB194	RLB195	RLB196	RLB197	RLB198	RLB199	RLB200	RLB201	RLB202	RLB203	RLB204	RLB205	RLB206	RLB207	KLB208	KL5209	PI R211	PI R717	RLB213	RI R714	RLB215	RLB216	RLB217	RLB218	RLB219	RLB220

ANID	macro_grp	Chem2012	CERAMIC TYPE	MATERIAL	SOURCE	STATE 8	SITE_NAME	SITE_NO	AS	LA	Π	ND	SM	Π	YB	CE CO	CR
RLB221	Group-B1	Mimbres-09	Mimbres B/W Style III	Pottery	TAM	•	Treasure Hill	LA 016241	3.28	26.90	0.5149	47.29	6.79		4.01 108.50		
RLB222	Group-C2a	Mimbres-42	Mimbres B/W Style III	Pottery	TAM	MN N	Treasure Hill	LA 016241	2.41	37.82	0.3127	31.56	5.76	1.36	2.12 79.	79.84 18.53	3 63.60
RLB223	Group-B1	Mimbres-04B	Mimbres B/W Style III?	Pottery	TAM	MN	Treasure Hill	LA 016241	3.21	58.62	0.5189	61.50	99.8	6.29	3.51 104.28	.28 5.58	3 22.37
RLB224	Group-B	Unas.	Mimbres B/W Style III ?	Pottery	TAM	MN	Treasure Hill	LA 016241	1.41		0.4241	41.97	7.91	1.99	3.02 95.05	.05 4.77	7 22.16
RLB225	Group-C1	Mimbres-21	Mimbres B/W Style II	Pottery	TAM		Treasure Hill	LA 016241	2.48	39.59	0.3238	48.50	5.82		2.51 87.	87.22 14.41	1 65.34
RLB226	Group-B2	Mimbres-02A	Mimbres B/W Style III	Pottery	TAM	•	Treasure Hill	LA 016241	1.53	38.23	0.4678	32.49	4.88	5.36 3	3.08 65.47	.47 3.92	37.20
RLB227	Group-A	Unas.	Mimbres B/W Style III	Pottery	TAM	L MN	Treasure Hill	LA 016241	1.80		0.5677	51.30	3.55 1	10.46 3	3.03 78.	78.68 1.7	5 1.78
RLB229	Group-B2	Mimbres-02A	Mimbres B/W Style III	Pottery	TAM		Treasure Hill	LA 016241	2.69	36.80	0.4362	35.64	5.32	3.70 2	2.97 64.	64.76 5.91	1 34.35
RLB230	Group-B2	Mimbres-02A	Mimbres B/W Style III	Pottery	TAM	MN	Treasure Hill	LA 016241	0.00	40.39	0.4450	25.17	5.19	3.38	3.08 79.	79.40 7.73	3 32.16
RLB231	Group-B2	Mimbres-02A	Mimbres B/W Style III	Pottery	TAM		Treasure Hill	LA 016241	1.67	40.51	0.4545	32.71	6.24	4.39	3.11 73.	73.93 6.91	34.24
RLB232	Group-B1	Mimbres-04A	Mimbres B/W Style III	Pottery	TAM	MN	Treasure Hill	LA 016241	2.42	51.79	0.5212	57.91	8.00	5.55	4.03 96.	96.43 4.26	5 18.52
RLB233	Group-B2	Mimbres-02A	Mimbres B/W Style III	Pottery	TAM	MN	Treasure Hill	LA 016241	2.57	43.28	0.4739	32.52		5.68	3.32 72.41	.41 6.05	37.99
RLB234	Group-B1	Mimbres-09	Mimbres B/W Style III	Pottery	TAM	L MN	Treasure Hill	LA 016241	2.16	62.25	0.5284	65.26	12.43	2.92	4.39 140.43	.43 2.67	12.96
RLB235	Group-C1	Mimbres-21	Mimbres B/W Style III	Pottery	TAM	MN	Treasure Hill	LA 016241	2.10	38.41	0.2754	20.77	5.33	1.04	2.45 75.	75.46 9.26	5 37.89
RLB236	Group-C1	Mimbres-21	Mimbres B/W Style III	Pottery	TAM	MN	Treasure Hill	LA 016241	0.00	38.66	0.3229	28.64	5.57	1.36 2	2.53 73.	73.48 10.35	5 66.7
RLB237	Group-B2	Mimbres-02A	Mimbres B/W Style III	Pottery	TAM		Treasure Hill	LA 016241	3.39		0.6293	37.64		6.62 3	3.90 75.		
RLB238	Group-B	Unas.	Mimbres B/W Style III	Pottery	TAM	MN	Treasure Hill	LA 016241	2.60	40.58	0.4291	34.68	6.26	4.10	3.27 72.	72.25 3.89	9 20.06
RLB239	Group-C1	Mimbres-21	Mimbres B/W Style III	Pottery	TAM	MN	Treasure Hill	LA 016241	2.23	41.56	0.3077	47.66	60.9	0.98	2.55 80.	80.82 11.20	0 40.35
RLB240	Group-C1	Mimbres-21	Mimbres B/W Style III	Pottery	TAM	MN	Treasure Hill	LA 016241	3.22	41.99	0.4034	32.82	6.35	1.32	3.04 79.	79.15 11.22	2 35.47
RLB241	Group-B2	Mimbres-02A	Mimbres B/W Style III	Pottery	TAM		Treasure Hill	LA 016241	2.61	48.64		48.19	6.83		3.65 78.	78.04 6.67	7 32.99
RLB242	Group-B	Unas.	Mimbres B/W Style III	Pottery	TAM	L MN	Treasure Hill	LA 016241	2.26	51.21	0.4843	49.74	6.29	5.10 3	3.09 87.	87.10 5.67	18.08
RLB243	Group-C1	Mimbres-22	Mimbres B/W Style III	Pottery	TAM	MN	Treasure Hill	LA 016241	1.82	38.26	0.2360	33.62	4.68	0.86	1.72 72.		6.94
RLB244	Group-C2b	Mimbres-44	Mimbres Polychrome	Pottery	TAM	L MN	Treasure Hill	LA 016241	1.11	42.20	0.3654	32.70	6.55	1.02	2.69 78.	l	5 23.19
RLB245	Group-A	Unas.	Mimbres Polychrome	Pottery	TAM	_	Treasure Hill	LA 016241	5.79		0.3986	45.79	3.33	3.79 2		59.85 3.53	
RLB246	Group-B	Unas.	Mimbres B/W Style III	Pottery	TAM		Treasure Hill	LA 016241	1.41			24.54	3.38	4.17		60.89 4.41	13.54
RLB247	Group-B1	Mimbres-04B	Mimbres Polychrome	Pottery	TAM		Treasure Hill	LA 016241	1.39		0.5065	45.20					5 24.85
RLB248	Group-A	Mimbres-01	Mimbres B/W Style III	Pottery	TAM	NM	Treasure Hill	LA 016241	1.82	56.90	0.6420	35.61	3.98	9.22 3	3.30 87.56	.56 1.72	6.76
RLB249	Group-A	Mimbres-01	Mimbres B/W Style III	Pottery	TAM		Treasure Hill	LA 016241	1.82		0.4948	30.35					
RLB250	Clay		Clay	Clay	TAM	NM			1.64		0.6491	57.75	9.28		5.04 113.53	.53 0.54	
RLB252	Clay		Adobe plaster	Clay	TAM		Agape Acres	LA 019165	1.64			25.50				1	
RLB253	Clay		Clay	Clay	TAM		Horse Camp Mil	LA 010983	1.19			9.55					
RLB254	Clay		Clay	Clay	TAM		Cameron Creek	LA 000190	1.00		0.3474	23.06	3.40				
RLB255	Clay		Adobe plaster	Clay	TAM		Agape Acres	LA 019165	0.78			27.97	5.28				
RLB256	Clay		Adobe plaster	Clay	TAM		Agape Acres	LA 019165	2.69			24.11	4.72			59.74 15.30	
RLB262	Group-B		Redware	Pottery	TAM		Treasure Hill	LA 016241	0.89			45.49	7.56				_
RLB267	Group-C2a	Mimbres-49A	Mimbres B/W Style III	Pottery	TAM		Treasure Hill	LA 016241	2.10			31.46	6.95			1	
RLB268	Group-B1	Mimbres-04A	Mimbres B/W Style III	Pottery	TAM		Treasure Hill	LA 016241	2.36	54.55		46.53	7.57	3.56 3			
RLB269	Group-C2	Unas.	Mimbres B/W Style III	Pottery	TAM		Treasure Hill	LA 016241	1.89	34.60	0.4148	32.37	8.44	2.48 3	3.25 87.54	.54 31.32	2 75.15
SRS007	Group-D	El Paso Core	El Paso Polychrome	Pottery	MURR		Millington	41PS00014	5.33	93.32	0.6520	76.06	13.71	3.96	5.06 179.08		3 26.79
SRS008	Group-D	El Paso Core	El Paso Polychrome	Pottery	MURR		Millington	41PS00014	5.17		0.5741	64.49	11.79		4.41 154.95	1	
SRS009	Group-D	El Paso Core	El Paso Polychrome	Pottery	MURR		Millington	41PS00014	6.84	69.24	0.6307		10.77	5.39 4	4.36 127.22	.22 6.88	
SRS010	Group-D	El Paso Core	El Paso Polychrome	Pottery	MURR		Millington	41PS00014	7.64		0.5548		10.89		`		
SRS011	Group-D	El Paso-2	El Paso Polychrome	Pottery	MURR	×	Millington	41PS00014	6.92		0.5715		10.11	3.93 4		.30 10.64	
SWC003	Group-D	El Paso Core	El Paso Brown	Pottery	MURR	XI	Samalayuca	41EP03038	10.46	83.60	0.7532	77.95	14.65	4.14 6	6.34 156.07	.07 7.66	34.1

>	47.75	79.96	47.45	57.25	74.71	49.41	16.08	58.43	48.24	59.22	39.22	69.31	28.04	53.24	58.73	51.67	46.86	69.51	06.69	57.16	70.20	32.16	107.94	31.76	38.73	59.61	18.04	22.75	18.33	92.35	28.04	108.43	90.24	57.65	92.75	49.61	184.02	82.50	89.60	92.00	92.80	85.70	81.57
I	2721.2	4544.6	2572.4	2393.5	3427.4	2406.0	1287.5	3038.9	2928.9	2315.9	2165.6	2971.2	3079.8	2934.9	1762.5	3857.9	3015.8	3342.0	2910.7	2509.4	3120.6	883.1	3021.0	2188.4	2550.2	2624.7	1374.3	2258.1	1253.9	4330.9	0.0	5094.0	4/00.0	4071.0	3999 7	3211.1	5243.7	5219.4	6308.4	4590.1	5565.7	4223.5	6642.3
NA	19981.8	21398.3	10299.1	13482.4	18550.3	10265.5	12059.3	12482.7	12212.7	12416.8	17979.6	10843.6	15856.2	17854.0	16734.8	15066.8	15773.5	20408.1	19954.9	13078.1	16840.6	12275.3	18972.6	12178.7	11771.3	9829.3	11920.2	7335.5	5437.6	18080.4	3135.7	47/76	10220.4	82256	164392	16783.7	16768.1	14358.7	20593.3	16666.9	20124.5	11133.9	16409.7
MN	456.6	688.5	454.2	475.0	984.9	168.9	237.7	257.4	349.2	275.5	176.4	239.4	318.3	803.4	1069.4	250.7	402.2	9.896	834.7	436.2	297.7	9.626	901.0	228.8	278.2	308.2	164.2	127.7	751.6	762.6	1198.8	60.08	74.2.0	0.207	587.2	593.7	1317.4	6.099	545.4	462.5	521.6	385.5	603.0
\prec	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	27122.0	33086.9	33128.2	35201.5	30538.5	27268.0
DY	6.650	3.822	5.603	7.346	3.553	4.456	1.967	3.959	4.581	4.771	4.691	4.936	6.747	3.927	2.764	4.563	4.319	2.397	3.056	4.330	3.425	2.680	4.051	2.340	2.212	5.371	3.202	2.759	7.180	3.023	0.000	2.917	2.172	5.122	4 276	5.234	4.849	7.880	7.662	6.801	6.949	7.005	9.778
CA	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0:0	0.0	15382.5	14654.0	12998.9	14677.5	13811.5	17247.8
BA	1035.9	1195.9	615.8	864.8	947.1	475.1	372.8	629.7	488.0	485.2	9222.6	517.0	1001.2	784.2	788.8	8.909	883.3	8.986	941.8	638.1	1022.6	729.6	950.0	505.3	538.4	618.1	6.099	399.6	167.6	943.5	544.9	294.1	707	712 5	836.8	933.1	930.5	1033.4	995.3	752.2	925.9	1770.3	1402.0
AL	84114.5	89785.1	81059.3	78244.2	87967.0	84089.3	85837.8	83208.3	79227.1	84104.1	82020.3	88322.9	81835.7	90013.9	85562.5	84757.1	82378.2	88592.9	87658.6	84672.3	85716.7	95522.1	83105.1	86241.0	86849.1	87510.3	92064.7	98242.0	81874.1	76658.2	13820.5	119831.4	0.01/0/	78520.9	92356 4	82286.5	84795.8	83405.0	95588.0	84871.4	92190.3	87316.8	99016.6
ZR	230.3	149.3	162.1			213.9	158.2	169.8	181.1	146.4	205.2	147.1	197.3	141.6	132.2		258.5	215.0	205.0	187.9	250.4	114.5	131.3	117.8						14		1703							215.4	322.6			405.4
NZ	82.0	81.9	54.3				38.1	46.8	47.8	52.2	54.9	55.2	71.7	74.5	74.5		78.9	83.2	89.1	51.8	61.0	87.5	85.0	46.0	49.6							3/.0			1		_		77.2	81.7			80.2
3 TH	_	9.40	7	14.50		24.29	5 48.69		3 19.27	3 19.11	3 24.69	1 22.36	1 14.55	8.75	5 9.23	5 19.25	7 14.97	0.03	5 10.41	3 21.97	1 25.75	0.17	99.6	3 35.10	33.50				7		_	11.07		-	_			+	7 20.78	5 19.65			3 22.26
4 TE	3 1.18	2 0.66	1.03	1.10	5 0.81	0.70	1 0.36	5 0.70	8 0.63	0 0.88	1 1.03	4 0.94	3 1.54	09.0	2 0.66	3 0.85	0.77	1 0.60	2 0.65	7 0.88	2 0.84	9.00	2 0.80	5 0.33			6 0.46					3 U.44	_	_			_	3 1.11	1.17	9 0.95			8 1.53
TA	1.0383	0.8952	1.5774	0.9194		1.8522	2.4401	1.4235	1.5578	1.4840	1.4811	1.5604	1.0793	0.7080	0.7282	1.3753	1.0719	0.7331	0.9022	1.4887	1.5152	0.5325	0.7792	1.9725								0.0052					0.5732	_	3.1746	2.4949			3.2088
SR	212.2	551.9	144.6	208.3	386.8	166.0	107.9	311.5	227.2	274.2	296.5	274.3	216.5	358.1	299.0	276.9	273.8	375.8	365.2	250.8	258.1	276.4	455.5	152.4	155.4	108.7	0.0	0.0	86.6	734.8	1934.8	8.671	000.2	540.9	487.5	366.9	612.4	344.1	423.9	284.7		_	372.9
SC	9.78	14.03	7.77	9.70	9.85	10.01	3.52	10.75	8.74	11.01	7.16	12.15	8.97	6.83	8.24	10.96	9.02	7.52	8.48	11.62	7.53	4.51	10.63	5.23	5.95	7.93	4.50	4.92	6.25	9.33	2.14	10.01	0.00	0.73	10.03	6.87	25.86	10.20	69.6	10.84	69.6	12.36	12.25
SB	0.5912	0.3643	0.4031	0.6135	1.6009	0.5164	0.5765	0.3411	0.5315	0.3742	0.5367	0.4597	0.6527	1.4529	1.7672	0.3553	0.6933	1.5367	1.5279	0.4086	0.0000	2.2244	0.4506	0.5745	0.6019	0.4756	0.8600	0.7695	0.2627	0.3148	0.1777	1.4598	0.4031	0.2717	0.3936	0.4337	0.0000	0.4819	0.3708	0.4308	0.4174	0.6410	0.5196
RB	142.70	90.80	150.80	121.40	126.00	188.50	288.10	152.00	156.20	142.50	135.00	153.00	123.60	114.20	129.40	126.40	115.90	111.40	115.10	148.40	202.50	148.90	83.40	229.10	238.70	159.40	247.40	281.50	12.90	73.80	21.50	00.76	90.00	129 40	98.80	115.30	140.40	92.99	100.25	92.45	101.45	114.17	109.73
Z	0.0	0.0	0.0	0.0		0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0				0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0				0.0	0.0			35.8
H	8.01	6.55	5.77	7.60		9.42		68.9	7.46	7.28	9.60	6.73	7.57	6.45	6.34	7.11	7.62	60.9	6.23	6.37	9.24	2.60	6.02	5.39		5.32	7.00	5.52	9.26	5.72	1.17	70°C	0.70	8.79	7.90	167	5.68	13.51	11.18	18.95	11.34	11.27	13.30
FE	23368.4	45037.8	23792.4		37468.0	21242.8	9.8966	26418.7	22044.7	26351.1	19235.2	27409.6	17442.2	27772.2	28750.1		24536.8	32490.4	32163.7	26747.8	31754.4	17956.8	47279.7		18241.9							13/11/8					68379.7			45527.3			50617.0
EU	2.2146	1.6642	1.5325	1.8863	1.4784	0.9247	0.5014	1.1530	0.9426	1.2994	1.5397	1.2704	2.4838	1.2648	1.2759		1.5115	1.3585	1.3454	1.2418	1.3002	1.2776	1.6788	0.6469	0.6684	1.2649	22.94 0.5203			1.4124		1 2442		1.3007				2.7159	2.5504	2.1926	2.3468	1.7769	2.6248
CS	4.60	5.88	5.54	7.60	19.19	19.46	25.98	16.70	17.93	17.80	4.51	22.57	3.80	17.42	17.15	15.03	8.09	18.32	18.14	18.23	8.65	26.82	2.87	12.19	11.81	6.30	22.94	23.61		2.69	0.80	71.11	2.03	3.78	3.86	3.94		3.08	3.11	3.51	3.38	5.25	3.16
ANID	RLB221	RLB222	RLB223	RLB224	RLB225	RLB226	RLB227	RLB229	RLB230	RLB231	RLB232	RLB233	RLB234	RLB235	RLB236	RLB237	RLB238	RLB239	RLB240	RLB241	RLB242	RLB243	RLB244	RLB245	RLB246	RLB247	RLB248	RLB249	RLB250	RLB252	RLB253	KLB254	KLD233	RL B250	RI B267	RLB268	RLB269	SRS007	SRS008	SRS009	SRS010	SRS011	SWC003

ANID	macro grp	macro_grp Chem2012	CERAMIC TYPE	MATERIAL	SOURCE	STATE	SITE_NAME	SITE_NO	AS	ΓA	Π	ND	SM	n	YB CE	00	CR
SWC004	G-dno-D	El Paso Core	El Paso Brown	Pottery	MURR	X	Samalayuca	41EP03038	7.76	52.85 0	0.5899	47.05	9.11 3.	3.64 4.0	4.06 104.71	9.30	33.27
SWC006	G-dno-D	El Paso Core	El Paso Brown	Pottery	MURR	TX	Samalayuca	41EP03038	8.33	63.40 0			10.97 3.	3.61 5.06	135.02	19.9	32.52
SWC007	Gronp-D	El Paso Core	Jornada Brown	Pottery	MURR	TX	Samalayuca	41EP03038	3.73	34.24 0	0.3284	25.34 4	4.72 4.	4.67 2.3	2.38 64.20	5.44	22.69
SWC008	G-dno _{-D}	El Paso Core	El Paso Brown	Pottery	MURR	ΤX	Samalayuca	41EP03038	7.09	28.90 0	0.6599	56.02 10	10.75 3.	3.71 5.4	5.43 133.67	6.73	33.21
SWC011	Group-D	El Paso Core	El Paso Brown	Pottery	MURR	TX	Samalayuca	41EP03038	7.35								28.12
SWC012	Group-D	El Paso-2	Jornada Brown	Pottery	MURR	ĭ	Samalayuca	41EP03038	8.59		0.5738				_	1	48.89
SWC013	Group-D	El Paso Core	El Paso Brown	Pottery	MURR	ĭ	Samalayuca	41EP03038	5.20	49.46 0	0.4171	35.84 6	6.99	3.92 3.3	3.35 79.86		26.36
SWC014	Group-D	El Paso-2	Jornada Brown	Pottery	MURR	ĭ	Samalayuca	41EP03038	7.15								55.64
SWC017	Group-D	El Paso Core	Jornada Brown	Pottery	MURR	TX	Samalayuca	41EP03038	7.09		0.5010					9.30	39.52
SWC018	G-dno ₂ D	El Paso Core	Jornada Brown	Pottery	MURR	ΤX	Samalayuca	41EP03038	4.74		0.6021	56.68 10		2.99 4.5	4.55 126.74	7.13	23.43
SWC019	G-dno ₂ D	El Paso-2	Jornada Brown	Pottery	MURR	ΤX	Samalayuca	41EP03038	6.95	87.83 0	0.7781	74.13 13	13.99 4.	4.26 5.55	55 152.32	1.67	51.79
SWC020	G-dno ₋ D	El Paso Core	El Paso Brown	Pottery	MURR	ĭ	Samalayuca	41EP03038	6.05	65.59 0	0.5549	55.03 9	9.97 2.	2.97 3.82	32 116.83	7.73	26.43
SWC031	Group-A	Mimbres-01	Mimbres B/W Style III	Pottery	MURR	MN	Rio Vista	LA 001082	2.44	74.21 0		35.62 6		10.83 4.00		3.89	5.13
SWC032	Group-B	Unas.	Mimbres B/W Style III	Pottery	MURR	MN	Rio Vista	LA 001082	2.77	61.86 0	0.6270	39.13 7	7.99 5.	5.67 4.18	107.75	5.12	29.92
SWC033	Group-B	Unas.	Mimbres B/W Style III	Pottery	MURR	NM	Rio Vista	LA 001082	1.97				4.83 5.	5.09 2.86	36 76.74	3.84	23.84
SWC034	Group-B2	Mimbres-02A	Mimbres B/W Style II/III	Pottery	MURR	NM	Rio Vista	LA 001082	1.79	37.33 0		_				5.11	39.57
SWC035	Group-B	Unas.	Mimbres B/W Style III	Pottery	MURR	NM	Hatch Site	LA 057481	3.97	50.64 0							27.29
SWC036	Group-B2	Mimbres-02A	Mimbres B/W Style II	Pottery	MURR	MN	Hatch Site	LA 057481	2.36	49.23 0	0.5885	36.87 7	7.30 4.	4.88 3.84	34 98.05	7.94	38.49
SWC037	Group-B2	Mimbres-02A*	Mimbres B/W Style III	Pottery	MURR	MN	Hatch Site	LA 057481	5.69	67.12 0	0.6358	45.48 8	8.31 3.	3.65 4.45	15 79.78	8.70	38.39
SWC038	Group-B2	Mimbres-02A	Mimbres B/W Style III	Pottery	MURR	MN	Hatch Site	LA 057481	2.43	43.67 0	0.5353	31.49 6	6.30 4.	4.11 3.57	57 74.03	88.9	37.54
SWC039	Group-B2	Mimbres-11	Mimbres B/W Style III	Pottery	MURR	MN	Bruton Bead Site	LA 030645	3.21	34.22 0	0.4926	24.38 4	4.96 3.	3.49 3.12	12 71.33	15.82	46.22
SWC040	Group-B2	Mimbres-11	Mimbres B/W Style II	Pottery	MURR	MN	Bruton Bead Site	LA 030645	2.72	36.84 0	0.5269	25.60 5	5.57 5.	5.24 3.4	3.49 70.98	11.49	44.48
SWC041	Group-A	Mimbres-01	Mimbres B/W Style II	Pottery	MURR	NM	Bruton Bead Site	LA 030645	0.75				l		3.25 82.34		3.54
SWC042	Group-B2	Mimbres-02A	Mimbres B/W Style III	Pottery	MURR	NM	Bruton Bead Site	LA 030645	3.92	44.33 0				3.86 3.0			38.33
SWC043	Group-C1	Mimbres-23	Mimbres B/W Style II	Pottery	MURR	M	Jaggedy Site	LA 139863	5.94		0.3964				2.64 73.07	1	40.27
SWC044	Group-B	Unas.	Mimbres B/W Style II	Pottery	MURR	M	Jaggedy Site	LA 139863	4.15								21.85
SWC045	Group-C1	Mimbres-23	Mimbres B/W Style III	Pottery	MURR	M	Jaggedy Site	LA 139863	4.04							_	43.45
SWC046	Group-B1		Mimbres B/W Style III	Pottery	MURR	M	Jaggedy Site	LA 139863	2.53								20.55
SWC047	Group-C2a	Mimbres-42	Mimbres B/W Style II/III	Pottery	MURR	M	Fleck Mimbres Site	LA 035392	2.97	37.51 0			5.87 1.	1.75 2.14			59.08
SWC048	Group-C2	Unas.	Mimbres B/W Style III	Pottery	MURR	M	Fleck Mimbres Site	LA 035392	6.49							_	53.19
SWC049	Group-B2	Mimbres-02A	Mimbres B/W Style III	Pottery	MURR	MZ :	Fleck Mimbres Site	LA 035392	2.30	_							39.76
SWC050	Group-A	Mimbres-01	Mimbres B/W Style II	Pottery	MURR	MN :	Fleck Mimbres Site	LA 035392	1.56	_					_		4.12
SWC051	G-dno-D	El Paso Core	El Paso Brown	Pottery	MURR	¥	FB 565	LA 091552	6.41	_					-		24.98
SWC052	Group-D	El Paso Core	El Paso Brown	Pottery	MURR	₩ N	FB 572	LA 091559	6.18		_						22.11
SWC053	Group-D	El Paso Core	El Paso Brown	Pottery	MURR	MM	FB 576	LA 091563	2.77								31.23
SWC055	G-dno-D	El Paso Core	El Paso Brown	Pottery	MURR	M	FB 3028	LA 093993	6.35								21.93
SWC056	G-dnos9	El Paso Core	El Paso Brown	Pottery	MURR	M	FB 3035	LA 094000	3.55	_				1.53 3.9	_		24.95
SWC057	G-dnos9	El Paso-2	El Paso Brown	Pottery	MURR	M	FB 3075	LA 094040	11.42							1	59.71
SWC058	Group-D	El Paso Core	El Paso Brown	Pottery	MURR	NM	FB 3076	LA 094041	6.19			73.85 10	10.66 1.	1.92 5.12	143.02	9.11	29.83
SWC059	Group-D	El Paso Core	El Paso Brown	Pottery	MURR	NM	FB 3080	LA 094045	90.9	54.66	0.5553		8.23 3.	3.87 4.61			31.28
SWC060	Gronp-D	El Paso Core	El Paso Brown	Pottery	MURR	MN	FB 3550	LA 094512	90.8				7.42 3.	3.38 4.14			23.53
SWC061	Gronp-D	El Paso-2	El Paso Brown	Pottery	MURR	M	FB 3574	LA 094536	7.22						`	1	76.57
SWC062	G-dno-D	El Paso Core	El Paso Brown	Pottery	MURR		FB 3582	LA 094544	7.38								32.33
SWC063	Gronp-D	El Paso-2	El Paso Brown	Pottery	MURR	NM	FB 3598	LA 094560	08.9	65.76 0	0.6706	57.80 10	10.03 4.	4.98 5.0	5.02 141.63	13.79	72.62

>	60.99	71.36	60.95	77.23	86.33	100.01	77.46	82.88	95.19	71.25	85.82	89.79	31.36	58.31	51.70	61.06	39.20	67.68	62.99	64.05	78.04	58.02	11.65	49.15	70.90	41.07	77.39	51.18	95.03	69.26	66.51	67.07	71 19	66.50	66.19	92.25	106.22	68.39	63.07	90.99	121.21	106.11	108.60
I	3829.3	4815.3	5058.1	4248.7	4566.5	4062.6	4372.6	3729.6	4445.9	4833.8	3829.8	5685.2	2191.4	2907.5	2348.8	2884.3	2472.2	2603.1	2639.5	2762.5	3511.6	3898.5	1847.4	3245.5	3274.6	2025.0	3378.3	3627.8	4171.8	3593.4	3401.4	1020.0	3990.9 4450.0	4106.9	4192.3	5914.2	4282.7	5141.5	4407.8	4099.6			4029.6
NA	12607.6	15149.9	13157.9	15119.9	16284.3	12087.9	12117.8	11215.6	14758.4	14924.5	11132.9	18179.7	18483.4	12315.7	14385.9	11622.8	13754.4	13702.1	13470.1	12341.6	12269.8	12875.2	21465.2	12005.8	12853.7	11522.8	12139.0	14407.2	23873.9	18543.6	10273.3	15003.0	14900.0	11796.4	15983.6	17108.8	8542.9	14037.8	12209.9	15994.2	10089.3	14312.8	11068.3
MN	440.7	442.5	402.2		419.3	451.9	345.2	403.3	413.3	499.7	349.7	507.3	228.7	225.6	١.	192.8	545.5	342.1	451.3	335.4	, 6.899	450.9	181.8	423.4		758.7	, 0.449	_	_				200.7	1.			417.7	594.2	426.4	390.5			832.1
¥	27226.9	25602.9	29671.1	25611.2	28998.2	27175.3	24833.5	27038.5	29064.6	29700.1	27245.1	31027.0	31021.1	27356.4	31271.5	27754.5	25979.1	28549.4	27952.2	26802.6	32636.1	31095.4	28816.5	27173.8	29166.9	21692.4	29510.9	26132.4	22548.7	25359.5	26287.3	308/1.9	25/0/.0	27873 9	28141.1	30295.1	25524.8	25569.4	26201.9	30396.2	26284.6	27856.3	28547.2
DΑ	5.829	7.129	3.067	7.251	4.595	5.933	4.734	7.109	5.620	6.543	9.020	5.855	5.382	6.134	3.643	4.021	6.016	2.690	9.660	4.297	3.482	3.752	2.787	5.172						3.596	5.190	3.169				6.111	7.962	7.307	6.410	5.379	6.663	6.581	8.497
CA	14775.0	12667.0	11399.5	11517.9	15422.2	29469.8	12368.1	13618.0	22590.9	14486.3	15005.5	15891.6	14754.3	13972.5	13424.8	10453.0	13646.7	11019.6	16311.4	12896.2	10473.7	11184.0	5382.4	12861.0	42942.0	21589.7	50437.8	13610.8	19027.6	15122.0	10513.2	0203.8	1/255 2	7 6746	16309.2	18978.8	16072.3	17938.7	18308.5	13288.1	16385.3	17976.8	15095.8
BA	1530.9	1359.2	1043.2	1242.5	1747.5	1026.2	1121.4	1491.0	1015.5	1527.0	1725.0	1379.9	940.2	1407.6	704.0	0.779	523.8	750.5	1152.5	782.8	543.0	524.1	0.0	9.599	755.0	345.0	647.6	757.0	1206.7	9.666	565.7	7,502	1108 0	1241 2	1438.4	1526.5	1050.3	1130.7	1320.3	1310.0	1242.3	1946.1	1417.1
AL	88037.6		84470.5	79583.6	86769.2	92667.8	81029.6	83504.8	88087.2	85204.3	84277.4	88310.1	117553.9	90974.5	90614.1	90554.6	81773.4	90253.8	91139.3	92896.1	8.69887	83307.9	103070.0	90663.5	78892.4	77217.0	76757.9	87605.4	95784.7	89205.3	92652.0	101137.8	90323.0		+_	_	92901.5	81166.6	85277.1	92973.7			86170.9
J ZR	328.4	434.4	7 295.1		375.2	3 292.9		3 350.4	5 294.9	7 358.0	7 352.7	365.7	5 210.0	202.7	9.161.8	9 202.1	154.1	7 207.0	176.5	9 201.5	5 202.4	9.681	, 6.9/1	1 201.2						-	243.5	0.112	7,002			390.8	269.2	5 484.7		3 298.8			335.1
NZ	71.2	75.6	60.7		64.9	102.8	69.5	115.3	80.5	74.7	109.7	71.9	47.6	66.2	48.6	6.99	53.1	26.7	66.4	61.9	9.19	62.6	37.4	56.4			78.2						100 1.4			_	92.2	100.5		83.3			153.1
B TF	7 17.55				2 19.67	5 18.66	2 22.08	9 23.97	6 18.04	7 19.08	8 29.45	6 20.49	4 52.45	1 27.09	6 30.83	9 22.39	7 23.39	9 21.91	3 20.71	1 22.57	0 17.80	9 19.38	9 54.27	7 20.44				_				3 55.59						0 21.18	19.61	5 20.02			4 23.74
TA TI	68 0.97	06 1.15	24 0.48	27 1.22	95 0.82	96 0.95	70 0.72	18 1.09	03 0.86	59 1.17	64 1.48	47 0.96	62 0.74	1.01	50 0.56	39 0.59	38 0.87	04 0.89	73 1.13	90 0.81	76 0.60	64 0.69	29 0.39	45 0.97			02 0.85						07 1.14			_	61 1.15	30 1.40	45 1.06	14 0.95	27 1.10		20 1.34
	3 2.5468	1 2.9006	2 2.8624		7 2.6295	8 2.1196		0 2.5218	5 1.9603	3 2.4259	9 2.8164	2 2.8347	3 2.3662	5 1.6467	7 1.6450	8 1.5939	3 1.5838	7 1.5404	4 1.3673	8 1.5990	4 1.5376	8 1.5464	9 2.5929	6 1.5145	٠ ا			_		_			7			3 2.3171	1.9261	8 2.7130	1 2.3845	5 2.3914			6 2.5020
SR	230.3	274.1	344.2		588.7	358.8	260.8	300.0	282.5	250.3	317.9	472.2	135.3	178.5	193.7	213.8	337.3	336.7	565.4	310.8	218.4	250.8	86.9			286.8						107.6	305.1			455.3	236.0	350.8	249.1		459.2		268.6
SC	8.82	90.6	7.45	9.00	9.40	12.59	8.44	11.18	10.98	11.05	11.16	9.62	4.66	8.22	6.43	11.04	8.46	11.04	11.58	11.47	8.31	8.70	3.99	10.66	10.14		_				_	4.25				10.43	13.39	9.87	8.61	7.99	16.27		13.18
SB	0.6970	0.5971	0.5766	0.5900	0.4107	0.8652	0.5936	0.6755	0.6889	0.4062	0.6406	0.4410	0.6541	0.8924	0.5719	0.5237	0.3607	0.3921	0.4418	0.5110	0.6584	0.5947	0.3618	0.4696	0.7935	0.4193	0.6879	0.3442	0.3126	1.5365	0.4612	0.3752	0.3012	0.556	0.5280	0.5034	1.0174	0.5938	0.6492	0.5901	0.7741	0.6560	0.6168
RB	126.28	99.21	119.37	101.26	106.72	129.10	92.34	137.74	125.91	119.06	136.46	108.25	178.10	169.16	181.57	165.11	154.55	157.11	123.48	162.48	185.19	194.34	279.32	145.22	176.43	174.57	161.51	127.50	81.31	116.38	156.36	121 11	115 40	122 58	117.62	116.93	132.77	115.74	125.29	154.29	133.96	118.52	154.30
Z	0.0	24.4	0.0	0.0	0.0	0.0	26.7	33.4	0.0	0.0	40.3	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	19.2	30.9	0.0	0.0	26.5	0.0	41.6	0.0	46.8	0.0	24.4	0.0	0.0	0.00	31.5	0.0	46.9	33.3	0.0	0.0	39.7	0.0	50.4
Ή	10.78		11.78	13.20	13.94	10.17	12.52	12.19	10.10	12.43	11.76	12.27	7.55	6.42	7.56		6.52	7.99	6.79	7.33	7.60	7.28	6.73	7.89	5.46	5.83	5.03			6.54	7.85		12.40	11 40	10.63	12.02	9.75	15.33	10.91	9.84	11.76	10.67	11.20
34	37425.5	37715.3	39231.4	38196.4	44714.8	40654.4	37200.1	42934.1	38425.7	41633.2	41791.3	45103.1	9816.3	23068.0	19358.9	24070.0	20603.8	25348.0	28638.6	25467.2	24762.7	23329.2	10732.4								25811.4	9.007.6					47426.2	43626.1	36562.1	36793.7			45626.9
EU	1.6785	1.7033	1.0892	1.6563	1.7609	1.7427	1.2745	1.5150	1.6463	1.9860	2.0429	2.0340	0.9724	1.4284	0.8340	0.8854	1.0679	1.3429	1.5495	1.1453	1.0457	1.1273	0.4935	1.2380	1.2183		1.2570	1.4444	1.5094			1 0055	1 9870	1 6848			1.6872	2.2917	1.6709	1.6397	1.8234		1.7860
CS	4.17	3.71	2.91	3.77	3.42	7.79	3.08	6.13	6.44	3.01	5.28	3.13	15.59	8.06	9.44	18.69	18.38	22.40	15.96	26.19	7.05	7.63	21.81	19.18	11.16		10.94	4.81	4.94	7.60			0.00	4.64	3.74	3.28	6.62	4.35	4.20	3.91	6.74	3.85	7.48
ANID	SWC004	900DMS	SWC007	SWC008	SWC011	SWC012	SWC013	SWC014	SWC017	SWC018	SWC019	SWC020	SWC031	SWC032	SWC033	SWC034	SWC035	SWC036	SWC037	SWC038	SWC039	SWC040	SWC041	SWC042	SWC043	SWC044	SWC045	SWC046	SWC047	SWC048	SWC049	SWC050	SWC031	SWC053	SWC055	SWC056	SWC057	SWC058	SWC059	SWC060	SWC061	SWC062	SWC063

ANID	macro_grp	Chem2012	CERAMIC TYPE	MATERIAL	SOURCE	STATE	SITE_NAME	SITE_NO	AS	ΓA	n	ND	SM	Π	VB (CE CO	CR
SWC066	Group-D	El Paso Core	El Paso Brown	Pottery	MURR		FB 3947	LA 094907	5.76	45.11	0.4541	34.26	5.30	3.38 3	3.45 76.20	20 4.76	22.60
SWC067	Group-D	El Paso Core	El Paso Brown	Pottery	MURR	MN	FB 3952	LA 094912	80.9		0.5693	47.54	7.38	5.21 4	4.27 104.42		31.24
SWC068	G-dno-D	El Paso Core	El Paso Brown	Pottery	MURR	MN	FB 3958	LA 094918	99.5	85.50	0.6481	72.68	11.30	5.62 5	5.16 164.10	10 8.79	26.94
SWC071	G-dno-D	El Paso Core	El Paso Brown	Pottery	MURR		FB 4386	LA 095343	8.37	67.01	0.7111		10.84	2.05 5	5.59 128.45		35.97
SWR001	Group-B2	Mimbres-08	Mimbres B/W Style III	Pottery	MURR	MN	Swarts	LA 001691	3.87	32.80	0.3883	13.98	3.57	6.41 2	2.38 54.23	23 3.57	722.1
SWR002	Group-B2	Mimbres-02A	Mimbres B/W Style III	Pottery	MURR		Swarts	LA 001691	1.38	43.03	0.5753	38.57	7.16	4.79 4	4.13 84.55	55 7.19	38.74
SWR003	Group-B	Unas.	Mimbres B/W Style III	Pottery	MURR		Swarts	LA 001691	3.66	48.30	0.4509	39.35	7.54	2.16 3	3.31 113.57	57 14.02	81.65
SWR004	Group-B1	Mimbres-04C	Mimbres B/W Style III	Pottery	MURR	M	Swarts	LA 001691	2.81	42.33	0.5109	32.00	6.23	3.66	3.60 87.45	45 11.65	33.86
SWR005	Group-B1	Mimbres-04B	Mimbres B/W Style III	Pottery	MURR		Swarts	LA 001691	2.55	62.94	0.6826	45.95	8.36	7.75 4	4.38 90.65	65 5.92	21.89
SWR006	Group-B	Unas.	Mimbres B/W Style III	Pottery	MURR		Swarts	LA 001691	2.85	45.38	0.5042	29.90	6.46	5.60 3	3.39 82.54	54 4.25	20.44
SWR007	Group-B1	Mimbres-04B	Mimbres B/W Style III	Pottery	MURR	MN	Swarts	LA 001691	2.30	43.26	0.4180	27.67	5.57	6.19	2.74 88.47	47 4.67	23.58
SWR008	Group-A	Mimbres-01	Mimbres B/W Style III	Pottery	MURR	MN	Swarts	LA 001691	4.48	63.22	0.6929	26.07	4.18	12.52 3	3.08 98.13	13 7.37	3.1
SWR009	Group-B1	Mimbres-04A	Mimbres B/W Style III	Pottery	MURR	MN	Swarts	LA 001691	4.36	57.31	0.5648	45.93	8.49	4.12 3	3.95 117.71	71 7.11	24.65
SWR010	Group-B1	Mimbres-04A	Mimbres B/W Style III	Pottery	MURR	MN	Swarts	LA 001691	4.17	52.26	0.5592	45.35	7.40	5.39 3	3.85 86.61	61 10.66	25.79
SWR011	Group-B2	Mimbres-11	Mimbres B/W Style III	Pottery	MURR	MN	Swarts	LA 001691	3.40	36.97	0.5195	28.53	5.31	5.79 3	3.41 70.71	71 17.37	38.99
SWR012	Group-A	Mimbres-01*	Mimbres B/W Style III	Pottery	MURR		Swarts	LA 001691	4.50		0.7120	28.15	l		3.63 113.56		
SWR013	Group-B2	Mimbres-02A	Mimbres B/W Style III	Pottery	MURR	MN	Swarts	LA 001691	2.28	38.45	0.5081	28.22	6.39	4.28 4	4.52 71.63	63 12.72	39.07
SWR014	Group-C1	Unas.	Mimbres B/W Style III	Pottery	MURR	MN	Swarts	LA 001691	3.72	35.86	0.3655	25.32	5.64	3.38 2	2.39 71.64	64 16.18	39.5
SWR015	Group-B2	Mimbres-08	Mimbres B/W Style III	Pottery	MURR	M	Swarts	LA 001691	2.94	35.24	0.4175	21.39	3.61	6.12 2	2.52 62.75	75 12.20	21.06
SWR016	Group-B2	Mimbres-02A	Mimbres B/W Style III	Pottery	MURR		Swarts	LA 001691	0.00	58.40	0.6393	47.44	8.67		4.33 82.28	28 13.18	7
SWR017	Group-A	Mimbres-01	Mimbres B/W Style III	Pottery	MURR	MN	Swarts	LA 001691	2.75		0.5776	21.22	4.08		2.95 85.64	64 14.67	8.35
SWR018	Group-B1	Mimbres-04B	Mimbres B/W Style III	Pottery	MURR	M	Swarts	LA 001691	4.23	55.93	0.5189	47.56	8.26		4.00 111.53	53 16.53	23.40
SWR019	Group-B	Unas.	Mimbres B/W Style III	Pottery	MURR		Swarts	LA 001691	2.31	33.71	0.4438	25.85	5.49		3.10 64.01	01 15.82	30.86
SWR020	Group-B2	Mimbres-02A	Mimbres B/W Style III	Pottery	MURR		Swarts	LA 001691	1.75	42.55	0.4391	30.30					
SWR021	Group-B2	Mimbres-08	Mimbres B/W Style III	Pottery	MURR		Swarts	LA 001691	4.26	32.40	0.3672	14.46		4.75 2	2.25 69.92		
SWR022	Group-B1	Mimbres-04C	Mimbres B/W Style III	Pottery	MURR	NM	Swarts	LA 001691	2.94	41.44	0.4603	30.43			3.75 84.61	13.91	30.7
SWR023	Group-A	Mimbres-01	Mimbres B/W Style III	Pottery	MURR	MM	Swarts	LA 001691	2.50	54.36	0.6943	24.73		12.93 3	3.11 93.36	36 25.11	7.4
SWR024	Group-B1	Mimbres-04A	Mimbres B/W Style III	Pottery	MURR		Swarts	LA 001691	4.86		0.6027	45.57					24.14
SWR025	Group-B2	Mimbres-02A	Mimbres B/W Style III	Pottery	MURR		Swarts	LA 001691	2.45	38.42	0.4818	28.29			3.43 68.09	09 13.83	4
SWR026	Group-A	Mimbres-01	Mimbres B/W Style III	Pottery	MURR		Swarts	LA 001691	2.31		0.5781	22.22					
SWR027	Group-B2	Mimbres-08	Mimbres B/W Style III	Pottery	MURR		Swarts	LA 001691	2.89		0.4547	23.11				_	
SWR028	Group-B	Unas.	Mimbres B/W Style III	Pottery	MURR		Swarts	LA 001691	2.30		0.4615	27.05					
SWR029	Group-B	Unas.	Mimbres B/W Style III	Pottery	MURR		Swarts	LA 001691	0.00		0.5227	25.30					
SWR030	Group-B2	Mimbres-02A	Mimbres B/W Style III	Pottery	MURR		Swarts	LA 001691	1.46		0.5325	31.69			_		34.80
SWR031	Group-A	Mimbres-01*	Mimbres B/W Style III	Pottery	MURR		Swarts	LA 001691	0.00	50.93	0.6543	18.27	3.80	13.57 2			6.32
SWR032	Group-B1	Mimbres-04B	Mimbres B/W Style III	Pottery	MURR		Swarts	LA 001691	0.00	38.54	0.4592	24.35	4.69	6.00 2			
SWR033	Group-B1	Mimbres-04B	Mimbres B/W Style III	Pottery	MURR		Swarts	LA 001691	3.27		0.6352						
SWR034	Group-B2	Mimbres-11	Mimbres B/W Style II/III	Pottery	MURR		Swarts	LA 001691	2.92	36.10	0.4612	26.04				84 25.26	40.40
SWR035	Group-B2	Mimbres-11	Mimbres B/W Style III	Pottery	MURR		Swarts	LA 001691	0.00	38.48	0.5827	30.07	5.76	5.73 3	3.59 74.53	53 34.69	
SWR036	Group-B2	Mimbres-02A	Mimbres B/W Style III	Pottery	MURR		Swarts	LA 001691	2.99		0.5601	34.72		4.06 3	3.57 93.26		
SWR036X	Group-B2	Mimbres-02A	Mimbres B/W Style III	Pottery	MURR	MN	Swarts	LA 001691	3.11	50.58	0.5256	38.41	7.54	5.71 3	3.96 109.18	18 10.91	36.02
SWR037	Group-B	Unas.	Mimbres B/W Style III	Pottery	MURR		Swarts	LA 001691	1.81	45.88	0.4434	32.41	6.59	4.15 3			18.80
SWR038	Group-B	Unas.	Mimbres B/W Style III	Pottery	MURR		Swarts	LA 001691	1.53	33.75	0.4939	20.28	4.71	6.42 2	2.99 59.22	22 26.35	
SWR039	Group-B1	Mimbres-04B	Mimbres B/W Style III	Pottery	MURR	M	Swarts	LA 001691	0.00	56.95	0.6691	48.39	8.57	7.05 4	4.56 100.88	88 20.15	25.93

>	56.28	53.56	109.17	84.77	35.40	53.10	77.80	62.50	43.00	35.90	49.70	12.10	51.00	55.30	43.40	0.00	55.70	80.70	38.90	78.00	28.70	48.20	42.10	46.90	39.40	63.10	13.20	40.80	64.90	15.40	31.70	55.00	41.40	45.30	15.00	49.00	52.50	42.30	54.10	56.59	25.70	55.90	4/ 00
I	4006.5	3932.3	6725.7 1	5105.0	2971.9	3379.3	3845.5	2962.2	2191.6	2602.8	2488.9	1490.8	3423.3	3717.1	3871.6		4029.2	3070.1	3038.7	3799.1	1684.5	3314.3	3548.0				1233.5			1655.0	3191.5			1222 1	_								1 1 1 1
NA	12107.1	16098.3		10778.9	11029.8	14440.1		15917.9	12265.2	11224.8	11515.9	22173.2	15510.7	12356.3	3302.6		11907.2	16566.7	10592.6	13505.6	10886.7	11618.8	12165.4	13963.7	٥.									, 6.16421						11940.2			. 0000
MN	286.3 12	440.2 160	592.7 173		203.3 110	343.3 14	738.3 159	899.1 15	491.0 12.	202.7 113	255.9 11!	325.3 22.	555.2 158	424.8 123	427.5 133	2470.7 93		684.5 16	254.9 105	232.4 13	131.5 108	457.9 110	297.3 12	238.6 139						, ,	,	1.	١,	387.2 12,71	1.	1.	1.	Ι,	1.	513.4 119	132.1 10	1273.2 98	10 1101
¥	27615.8 28	30777.0 4	28750.9 5	25569.1 4	28799.1 20	27321.8 3.		24175.5 89	28308.4 4	29677.6	24126.4 2	30854.8 3.	26314.1 5	31611.0 4.		3	7	24364.9 68	4	24624.7 2:	35990.9 1:		26440.3 24	29145.9 2:										29413.4 30						24568.9 5			
DY	3.764 276	5.645 307	7.273 287		2.976 287	5.470 273	-	3.728 241	6.087 283	5.012 296	3.889 241	2.546 308			51 30621.7	2.214 283	5.134 29598.7	3.409 243	2.644 32114.	6.041 246	2.797 359	5.705 28031.7	3.654 264	4.056 291					-1	_				5.332 294 707 270 C	· ·					5.643 245	1		L 417 747E7 A
CA													9.8 5.841	3.8 5.187	0.2 4.151																						1						
	11257.2	10431.6	18198.8	16700.2	6172.8	14961.2	16831.7	11420.5	8248.8	9741.5	8881.1	7372.4	12709.8	10463.8	9690.2		12865.4	l	5599.5	14340.6	7107.9	10758.9	13728.8	12787.9		_			_				1	12031.5		ļ	ľ			Ľ			0106 /
BA	1115.4	1044.4	1273.9	_	455.2	553.9			583.1	570.7	480.3	196.8	867.3	6.079	553.0	185.2		836.4	454.3	561.2	337.0	643.5	692.6											210.7						479.7	463.2		157.0
Al	86369.8	79962.1	90283.2	95108.0	79555.6	85918.1	80545.6	82325.5	80981.4	80172.6	86930.7	107185.1	86859.4	81069.3	78776.4	83473.0	91598.4	86146.4	73593.2	92706.9	100588.5	93441.1	79352.9	79485.4	77391.9	75954.3	95310.4	84933.9	8875/.4	105359.2	83489.4	84931.4	93358.0	82024.8	91489 0	923297	81127 3	81791.5	83528.8	88891.1	53034.7	71909.7	02221 0
ZR	256.3	432.5	349.3	372.9	163.2	183.8	250.9	257.0	1.69.1	161.7	156.9	207.2	193.0	161.7	173.1	188.0	218.1	136.6	177.6	201.6	153.5	137.3	217.5											1,141						142.1		199.5	1157
NZ	67.4	83.5	122.5	82.7		5'06		106.9	56.1	117.0	0.86	50.4	0.98	0.66	121.3	22.7	115.2	1.78	57.6	62.0	64.2	83.5	74.0	72.4			52.6	64.1			62.8	68.6	60	7 071	140.7	79.8	81.1	97.8	77.2	90.5	57.9	85.4	7 00
3 H	28.78	5 19.21	1 25.67	4 25.66	3 26.48	3 19.79	3 16.28	1 16.48	3 24.25	9 23.30		2 57.08	1 20.90	5 22.28	9 19.29		7 22.44	5 12.73	5 25.82	20.32	1 47.59	3 26.61	7 20.05		_		5 51.08							7 20.43						7 20.99			76 36 1
TA TB	116 0.62	96.0 889	1.31	79 1.24	373 0.38	346 0.78	1.1368 0.88	1.2945 0.7	29 1.08	330 0.79	64 0.65	962 0.42	1.01	718 0.95	0.69	325 0.57	1.07	512 0.66	95 0.46	45 0.92	20 0.41	64 0.98	20 0.57	1.4360 0.62	330 0.41		0.45			_				06 0 08						1.3925 0.87		1.5375 0.53	111
SR	284.2 2.6016	256.0 4.1583	457.5 3.3429	694.0 3.0679	160.2 1.4373	268.3 1.4846	476.4 1.13	324.4 1.29	210.1 1.5129	138.6 1.3830	133.8 1.4564	83.5 2.5962	317.0 1.3187	177.3 1.5718	289.2 1.6026	64.8 2.1825	161.3 1.5461	463.6 0.9512	126.7 1.5092	324.8 1.4745	87.3 2.3120	152.7 1.5664	297.5 1.5120	375.9 1.43			120.8 2.3089			, , ,				79C7 C Z 7111						,	265.9 1.3371		120 0 1 2071
SC	7.73 28	7.05 25	10.94 45	10.92 69	5.54 16	10.72 26		7.99 32	6.58 21	6.30 13		4.00 8	8.46 31	7.05 17	7.93 28		11.25 16		4.98 12	12.29 32	4.37 8	7.43 15	8.39 29	9.16 37			4.27 12			ľ	` \			2 72 11						10.84 38			213 13
SB	0.5074 7	0.8383 7	0.4714 10		0.4148 5	0.3660 10	1.3591 10	0.4239 7	0.3404 6	0.4098 6	0.3721	0.5342 4	0.3920 8	0.5364 7	0.5849 7			0.5227 9	0.6431 4	0.3582 12	0.6434 4	0.3990 7	0.4650 8	0.3779 9				,					~	0.4305 10					1	1			0.1281 8
RB	120.02 0.	122.50 0.			178.90 0.	141.30 0.			169.70 0.	155.60 0.	154.10 0.	178.50 0.	145.20 0.	176.60 0.	196.20 0.				204.20 0.	148.60 0.	231.40 0.	166.90 0.	152.40 0.											100 00 001									160 40 0
Z	0.0	0.0	0.0 103	33.8 128	0.0	0.0 14	36.7 13.	0.0	0.0	0.0 15	0.0	0.0	0.0 14	0.0	0.0	0.0 21	0.0 156	0.0 142	0.0 20	0.0	0.0 23	0.0	0.0 15	14.2 153										0.0						0.0			0.0
生	9.28	14.43	10.17	13.36	7.74	8.26		10.51	7.42	9.65	89.9	7.43	8.36	6.71	7.37	6.03	8.24	6.15	8.00	7.51	6.85	6.15	9.48		8.09	9.22	6.57	8.08	06./	96.98	6.38	11.30	7.07	7.07	437	6.17	7.38	7.99	6.43	7.01	7.26	9.13	5 31
H	33539.9	31324.9		45997.3	18109.5	25782.1		29530.2	20875.5	19914.7	23593.9	11077.7	24116.8	25230.1	22232.8	12515.5	24808.7	32506.0	17529.0	29009.4	13640.8	22774.7	25982.5	21356.8	20361.4	29083.2	13509.6	25819.4	7./91/7	11729.0		_	2.09602	11776 4	21514.0	24518.1	214291	22327.0	24263.1	25715.2	19181.3	20665.5	25105 A
EN	1.0209 33	1.5118 3	2.4136 49	1.9752 4	0.6451 18	1.3877 25		1.2655 29	1.4929 20	1.1214 19	1.0017 23	0.5228 17	1.6016 24	1.3896 2	1.0822 22			1.3689 33	0.6674	1.6441 29			1.1013 2						_			_		71 1697 0					_	1.3347 2	1.3171 19	0.7578 20	1 1051 2
SS	3.04	4.25 1.	3.07 2.	4.99 1.	0.99.9	16.47		5.48 1.	5.31	4.46		10.03 0.	5.13 1.	5.89	7.44 1.			12.54 1.	6.34 0.	17.58 1.	25.19 0.5228	5.74 1.3924	5.48 1.	18.88 1.	6.56 0.			_					20.03 0.	20.4δ I.	8 40 0 8602	6.20	6.61					17.61 0.	4 50 1
ANID	SWC066	SWC067	SWC068	SWC071	SWR001		SWR003	SWR004	SWR005	SWR006	SWR007	SWR008	SWR009	SWR010	SWR011		SWR013		SWR015	SWR016	SWR017	SWR018	SWR019		SWR021						SWR027			SWR030		SWR032	SWR034	SWR035		×			CMDNO

ANID	macro arn	Chem2012	CERAMIC TYPE	MATERIAI	SOURCE	STATE	SITE NAME	SITE NO	AS	٨	=	NS		ΛR	J.	C	CR
SWR040	Group-B2	Mimbres-11	Mimbres B/W Style III	ery		1	Swarts	LA 001691		_		ц,	8 5.73	3	67.61	37.06	38.33
SWR042	Group-B2	Mimbres-11	Mimbres B/W Style III	Pottery	MURR		Swarts	LA 001691		_		25.59 5.01			77.28	37.61	46.77
SWR043	Group-B1	Mimbres-04B	Mimbres B/W Style III	Pottery	MURR		Swarts	LA 001691		_			_		89.94	8.15	19.67
SWR044	Group-B1	Mimbres-04B	Mimbres B/W Style III	Pottery	MURR	MN	Swarts	LA 001691			0.5742 43	43.65 8.69	9 7.62	3.90	92.09	16.90	22.03
SWR045	Group-B1	Mimbres-04A	Mimbres B/W Style III	Pottery	MURR	MN	Swarts	LA 001691	00.00	40.36 0.5	0.5194 33	33.63 5.51	1 4.34	3.09	73.88	6.95	19.20
SWR046	Group-B1	Mimbres-04B	Mimbres B/W Style III	Pottery	MURR		Swarts	LA 001691							90.55	6.02	21.42
SWR047	Group-B2	Mimbres-02A	Mimbres B/W Style III	Pottery	MURR		Swarts	LA 001691	2.19		0.4783 32	32.58 6.13	3 6.17	3.53	69.85	22.74	37.38
SWR048	Group-B	Unas.	Mimbres Corrugated	Pottery	MURR		Swarts	LA 001691	4.18	41.53 0.4677	,	34.51 6.44	4 4.21	3.16	82.32	18.85	25.57
SWR049	Group-B1	Mimbres-04A	Mimbres B/W Style III				Swarts	LA 001691		43.98 0.4;		39.18 6.61		3.00	87.90	16.26	25.39
SWR050	Group-C2	Unas.	Mimbres Plain		MURR		Swarts	LA 001691	6.19	35.46 0.3;	0.3202 34	34.47 6.69	9 2.58	2.42	74.86	21.86	97.38
SWR051	Group-B1	Mimbres-04B	Mimbres B/W Style III	Pottery		MM	Swarts	LA 001691	4.18 E	50.69 0.5291		49.76 7.76	6 6.25	3.28	95.41	24.05	25.68
SWR052	Group-B	Unas.	Mimbres Corrugated	Pottery	MURR		Swarts	LA 001691	3.64	26.51 0.3	0.3119 24	24.37 3.86	6 3.51	1.47	51.50	28.92	50.74
SWR053	Group-B1	Mimbres-04A	Mimbres B/W Style III	Pottery	MURR	NN S	Swarts	LA 001691	2.25	39.81 0.4707		35.45 6.04	4 4.60	3.30	96.08	19.41	25.14
SWR054	Group-B2	Mimbres-08	Mimbres B/W Style III	Pottery	MURR	MM	Swarts	LA 001691	2.83	33.76 0.4	0.4655 23.11	.11 3.96	6 5.42	2.66	61.36	24.74	23.77
SWR055	Group-B2	Mimbres-02A	Mimbres B/W Style III	Pottery		NM S	Swarts	LA 001691	5.45	34.59 0.5		31.24 5.69		3.41	61.99	37.56	37.24
SWR056	Group-B1	Mimbres-04B	Mimbres B/W Style III	Pottery	MURR	MN	Swarts	LA 001691	2.05	9.0 91.77	0.6558 57	57.07 10.70	0 7.82	4.70	113.47	38.70	25.11
SWR057	Group-A	Unas.	Plain brownware olla (non-N Pottery	Pottery	MURR	NM S	Swarts	LA 001691	0.00	27.20 0.477	_	47.51 5.67	7 7.85	3.25	129.45	22.12	102.37
SWR058	Group-B	Unas.	Corrugated	Pottery	MURR	MN	Swarts	LA 001691	1.92	41.51 0.4	0.4986 25	25.90 5.50	0 5.50	2.88	84.73	18.81	50.96
SWR059	Group-B1	Mimbres-04B	Plain	Pottery	MURR	MN	Swarts	LA 001691	4.13	78.79 0.63	0.6265 55	55.97 10.38	8 4.36	4.65	117.03	21.74	26.55
SWR060	Group-B	Unas.	Mimbres B/W Style III	Pottery	MURR	MN	Swarts	LA 001691	00.00	31.94 0.4		24.47 4.80		3.01	55.53	16.46	30.46
SWR061	Group-A	Mimbres-01	Mimbres B/W Style III		MURR	MN	Swarts	LA 001691	00.00	54.88 0.6673		27.36 4.59	9 13.38	3.03	89.48	20.84	8.79
SWR062	Group-B2	Mimbres-11	Mimbres B/W Style III	Pottery	MURR		Swarts	LA 001691	4.95	36.29 0.4	0.4679 35	35.53 5.62	2 4.51	3.11	80.69	40.27	44.78
SWR063	Group-B1	Mimbres-04B	Mimbres B/W Style III	Pottery	MURR	MM	Swarts	LA 001691	4.51	71.31 0.711		62.13 10.63	3 6.14	5.35	119.12	27.54	27.38
SWR064	Group-B	Unas.	Mimbres B/W Style III	Pottery	MURR	NM S	Swarts	LA 001691	4.36	37.13 0.5	0.5293 27.07	.07 4.37	7 2.08	3.31	83.21	19.27	20.91
SWR065	Group-B2	Mimbres-11	Mimbres B/W Style III	Pottery	MURR	NN S	Swarts	LA 001691	3.69	31.46 0.4607		19.81 4.31	1 4.40	2.99	67.84	28.91	48.62
SWR066	Group-B2	Mimbres-02A	Mimbres B/W Style III	Pottery			Swarts	LA 001691	0.00			39.93 6.74	4 4.47		70.33	10.89	35.68
SWR067	Group-B2	Mimbres-02A*	Mimbres B/W Style III	Pottery	MURR		Swarts	LA 001691	10.71	45.27 0.5752		40.66 7.20	0 5.47	3.26	95.54	26.84	38.36
SWR068	Group-B	Unas.	Mimbres B/W Style III	Pottery	MURR		Swarts	LA 001691							50.69	11.34	26.92
SWR069	Group-B	Unas.	Mimbres B/W Style III	Pottery	MURR		Swarts	LA 001691		34.96 0.5				3.64	56.59	21.07	21.41
SWR070	Group-B	Unas.	Mimbres B/W Style III	Pottery	MURR		Swarts	LA 001691		51.42 0.5;	0.5364 50			4.19	98.89	27.95	35.57
SWR071	Group-B1	Mimbres-04A	Mimbres B/W Style III	Pottery			Swarts	LA 001691		32.81 0.4		32.94 5.39		2.90	65.15	26.37	26.11
SWR072	Group-B	Unas.	Mimbres B/W Style III	Pottery			Swarts	LA 001691							110.49	28.23	30.53
SWR073	Group-B2	Mimbres-08	Mimbres B/W Style III	Pottery	MURR		Swarts	LA 001691							61.50	20.63	22.71
SWR074	Group-B	Unas.	Mimbres B/W Style III	Pottery			Swarts	LA 001691					4 8.89		101.89	39.79	32.77
SWR075	Group-B1	Mimbres-04A	Mimbres B/W Style III	Pottery			Swarts	LA 001691	0.00			41.80 7.67	7 6.42	3.82	94.77	13.23	24.83
SWR076	Group-B2	Mimbres-02A	Mimbres B/W Style III	Pottery			Swarts	LA 001691			0.4849 33	33.91 5.34		3.38	74.93	21.32	38.45
SWR077	Group-B	Unas.	Mimbres B/W Style II	Pottery			Swarts	LA 001691							84.18	33.55	50.49
SWR078	Group-B2	Mimbres-02A	Mimbres B/W Style III	Pottery	MURR	NN S	Swarts	LA 001691	3.90	43.98 0.5731		32.08 6.78	8 4.05	3.90	90.23	17.39	34.32
SWR079	Group-B2	Mimbres-11	Mimbres B/W Style III	Pottery	MURR	NN S	Swarts	LA 001691	2.97	32.86 0.50	0.5016 19	19.06 4.78	8 4.57	3.16	80.50	37.87	48.84
SWR080	Group-B2	Mimbres-02A	Mimbres B/W Style III	Pottery	MURR		Swarts	LA 001691	3.19	63.64 0.6	0.6488 47	47.98 8.42	2 2.90	4.58	92.71	21.58	42.64
SWR081	Group-B1	Mimbres-04B	Mimbres B/W Style III	Pottery			Swarts	LA 001691	1.68	62.81 0.6	0.6724 40				85.22	22.98	26.18
SWR082	Group-B2	Mimbres-08	Mimbres Corrugated	Pottery			Swarts	LA 001691							68.82	17.02	23.63
SWR083	Group-A		Mimbres B/W Style III	Pottery	MURR		Swarts	LA 001691		68.06 0.7671			1		97.34	30.00	7.65
SWR084	Group-C2a	Mimbres-49A	Mimbres B/W Style II	Pottery	MURR	MN	Swarts	LA 001691	5.42	44.16 0.50	0.5070 38	38.39 7.55	5 2.99	3.37	156.10	27.29	54.33

>	41.70	50.70	38.50	44.60	35.30	34.30	47.10	52.90	54.40	88.30	60.20	88.60	60.10	34.20	71.80	96.10	90.80	73.70	53.00	51.60	22.10	65.40	54.70	45.40	46.70	96.70	82.00	47.40	37.80	62.00	50.50	29.80	36.60	62.50	41.40	63.30	62.40	49.40	71.70	78.20	43.30	38.20	34.10	99.10
⊨	3290.6	3950.4	2277.2	2847.7	2029.1	2666.4	3066.3	3055.5	3851.0	8.8899	3009.5	4976.8	3371.3	3321.7			3724.4	2164.2	2496.1	2907.8	1948.8	4011.2	2855.0	1707.8		2877.6	3415.4 8											3913.0						5797.0
NA			3			9					2																																	
_	13374.5	10718.4	10850.	11619.0	16965.1	11372.	12278.3	15288.0	15194.9	12835.1	10257.	11855.5	13813.2	10035.7	11762.6	11451.7	9321.5	10986.9	11061.3	13163.5	9953.7	12338.2	9850.2	11105.3	9397.2		14751.7	`		1						12216.8		12972.0	`		_			16569.8
MM	358.7	667.4	257.5		241.5	227.1	582.2	650.0	343.6	861.8	210.2	435.9	179.2	164.8	273.2	470.7	491.6	464.7	381.1	908.7	188.9	430.2	759.2	1213.3	1014.7	211.3	530.8	801.5	1337.8	466.0	584.4	420.8	229.4	1528.9	550.3	211.5	1209.4	368.3	1486.6	566.6	236.2	163.4	261.4	972.9
¥	31580.9	30617.6	29883.7	27127.4	29412.5	30686.8	25257.3	34704.5	30927.2	28757.5	29446.4	31701.8	27968.7	28959.2	32183.2	28921.0	29690.8	38181.3	27654.5	32061.9	39028.0	27646.9	25443.0	20662.3	28064.8	27379.9	28115.4	23109.2	20000.2	23394.0	30825.8	31558.9	31317.9	32138.5	27731.7	28944.8	31464.0	29373.0	27730.4	26237.4	27867.7	32800.5	30278.4	24674.1
DΥ	3.887	4.144	5.520	5.789	3.752	5.081	4.638	3.908	3.841	4.082	4.968	2.860	4.695	3.043	4.438	8.099	4.106	3.289	7.886	3.735	3.388	4.046	7.532	2.719	2.613	4.637	5.596	2.378	3.267	5.965	3.832	7.074	3.026	6.437	4.497	4.417	3.580	5.907	3.747	6.069	5.792	2.992	5.311	5.119
CA	9938.3	9054.4	8819.7	10206.3	17487.6	7688.8	10301.3	8903.0	12613.0	19560.8	8880.2	10876.3	12930.3	7524.8	13798.7	9656.4	8922.7	15337.2	11800.9	32363.9	6549.1	10390.1	9293.3	16428.6	8423.2	13663.2	19149.0	17218.2	17720.7	14281.2	9942.3	11138.4	2666.9	12494.3	9869.5	10429.6	11105.0	11655.6	10269.1	14167.0	10497.1	6261.9	16578.3	24102.1
BA	419.2	361.6	488.1	8.609	789.1	457.5	503.4	791.9	766.2	855.4	476.6	673.4	785.6	405.4	534.1	588.1	534.1	542.5	8.659	743.8	584.0	550.4	672.4	226.7	401.2	618.8	652.6	313.3	350.2	493.4	713.0	545.2	511.9	740.5	464.0	346.3	491.3	640.2	547.1	617.1	551.5	434.3	462.6	704.8
AL	79833.8	74263.1	81361.0	8.99918	82788.6	85977.4	92120.2	77835.5	83835.3	83530.6	90081.1	92336.1	91940.7	85188.8	87138.2	87838.3	9.87668	75284.7	90614.2	70757.0	99431.1	82280.2	93546.2	77944.0	77491.2	85876.2	94206.8	77845.6	81727.9	85710.1	81465.9	88894.9	76211.5	93247.3	88515.6	95245.8	86445.3	83744.0	86467.4	91822.4	83602.6	82618.1	0.0	92637.2
ZR	156.1	114.1	131.3	188.0	230.0	178.0	220.0	207.6	154.0	198.4	105.1	103.3	220.3	173.9	135.8	1.791	176.9	196.8	165.9	167.0		192.0	134.8	100.9		238.5	173.3	187.0	87.0	138.4	314.7					206.6		193.7	168.8		195.3		176.3	0.0
NZ		78.2	70.0			59.4	106.2	283.3	64.0	163.9	72.1	86.4	9.98	85.2	107.1		0.96	172.0	90.1	131.0	61.8	61.4	73.9	78.1			84.5		188.2									92.0			67.3			74.8
H	20.71	18.51	26.37	27.57	19.09	26.45	21.16	20.77	22.04	7.74	27.13	14.44	20.85	26.95	21.71	24.71	59.48	23.80	25.17	16.85	49.74	18.12	25.33	26.96	19.07	18.63	20.02	21.49	26.09	20.00	17.85	23.91	24.64	21.48	22.74	20.51	17.07	19.24	18.43	19.39	26.47	27.41	46.24	11.82
TB	0.64	0.61	0.94	1.12	0.74	0.97	0.85	0.92	0.80	0.78	0.97	0.47	0.70	0.51	0.77	1.62	0.73	69.0	1.48	0.73	0.46	0.74	1.59	0.59	0.58	0.90	0.91	0.49				1.16		1.20	1.06	0.61		0.95		0.88	0.87		_	0.71
TA	1.6329	1.4805	1.5013	1.5154	1.2393	1.4838	1.4542	1.3667	1.4535	9989.0	1.4428	0.9291	1.4142	1.5727	1.5621	1.3654	1.3188	1.2184	1.3941	1.3786	2.2743	1.5539	1.4381	1.4490	1.5027	1.3642	1.3770	1.4402	1.5482	1.4559	1.3640	1.4204	1.4542	1.2426	1.3942	1.5163	1.4751	1.5409	1.6081	1.4136	1.5370	1.5445	2.0127	1.1763
SR	185.6	220.8	112.2	154.2	264.2	139.6	183.9	274.7	290.4	1.998		347.7	222.9	102.5	293.6	163.0	188.0	282.8	189.8	401.8	73.5	242.2	224.7	249.6			348.4				230.1					269.1	0.0	341.1		3325.7				440.1
SC	7.53	7.96	88.9	7.52	6.33	68.9	10.40	7.06	7.10	10.57	7.69	9.29	7.90	6.04	10.49	7.27	11.39	8.18	8.08	7.47	4.29	8.23	9.02	6.48	8.17	10.95	11.23	6.45	92.9	9.73	6.72	8.70	5.25	8.78	7.54	10.33	8.06	9.95	8.15		6.93	5.78	4.59	11.35
SB	0.5391	0.6334	0.3801	0.3367	0.3631	0.3588	0.4907	0.3724	0.3869	0.4645	0.3692	0.3067	0.4188	0.6159	0.4636	0.4957	0.4136	0.4798	0.4668	0.2991	0.8948	0.6436	0.4626	0.4800	0.8004	0.3331	0.6665	0.5299	0.6092	0.5416	0.4831	0.5521	0.5013	0.6917	0.4114	0.5858	0.8757	0.5825	0.6936	0.4846	0.7270	0.6165	0.7360	0.9365
RB	193.10	202.10	183.20	158.50	149.90	179.20	143.70	164.60	147.80	75.40	140.90	117.00	138.80	182.50	144.70	163.60	172.20	183.60	158.10	149.20	257.30	189.00	145.10	185.00	201.40	144.50	128.00	167.70	170.80	147.70	129.80	121.10	177.30	148.10	148.00	152.90	165.70	142.30	194.60	157.50	167.40	186.30	192.30	80.70
Z	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	65.4	0.0	0.0	0.0	0.0	0.0	0.0		0.0	0.0									0.0		0.0	0.0	0.0				0.0
生	7.41	7.45	6.12	7.38	9.70	5.87	7.37	7.84	7.40	9.34	5.32	5.50	10.49	7.51	7.70	5.74	7.22	6.59	6.03	7.37	6.75	7.27	5.91	5.86		6.84	7.27	6.50	5.48	6.74	10.26	7.88	7.65	7.32	8.98	7.93	7.69	9.13	7.23	7.57	7.03	7.73	96.9	98.9
FE	21164.5	24243.8	20503.4	21622.7	17213.0	19754.9	23073.7	26137.6	22141.7	46916.5	23832.7	41347.1	28142.4	19102.9	23383.5	23947.9	37023.6	29571.2	23976.4	22971.6	12573.9	23285.1	28148.0	23178.9	24103.3	24941.9	29765.7	20000.1	18415.1	25311.8	23680.3	25245.9			24604.2	24981.6	25301.5	23922.0	26033.9	31917.5	18704.8	19838.8	12878.2	1.7325 39313.2
EU	0.9659	0.9631	1.1826	1.4259	1.1733	1.2198	1.1627	1.3110	1.2604	1.5748	1.1961	0.7990	1.1431	0.6654	0.9984	1.8476	1.0337	1.0593	1.8134	7.83 0.9892	0.5491	7.50 1.1185	1.7929		7.48 0.8556		1.2698	0.6495			1.0370					0.8772	0.9613	1.2137	0.9852	1.6096	1.3658	0.7090	1.0934	1.7325
CS	7.21	7.40 (6.10	29.9	4.40	2.66	21.43	5.93	4.49	3.65	5.61	9.30	2.55	7.54 (15.52		5.31	10.68	2.66	7.83	28.23 0.5491	7.50	6.25	21.00 (7.48		16.26				_	4.61		6.94	2.90		8.01	17.65			7.24	7.16 (9.05
ANID	SWR040	SWR042	SWR043	SWR044	SWR045	SWR046	SWR047	SWR048	SWR049	SWR050	SWR051	SWR052	SWR053	SWR054	SWR055	SWR056	SWR057	SWR058	SWR059	SWR060	SWR061	SWR062	SWR063	SWR064	SWR065	SWR066	SWR067	SWR068	SWR069	SWR070	SWR071	SWR072	SWR073	SWR074	SWR075	SWR076	SWR077	SWR078	SWR079	SWR080	SWR081	SWR082	SWR083	SWR084

ANID	macro_grp	Chem2012	CERAMIC TYPE	MATERIAL	SOURCE	STATE	SITE_NAME	SITE_NO	AS	ΓA	Π	QN	SM	U YB	3 CE	00	CR
SWR085	Group-B1	Mimbres-04B	Mimbres B/W Style III	Pottery	MURR		Swarts	LA 001691		_	0.6963 (10.03 6.20		9 103.19	22.37	22.80
SWR086	Group-B2	Mimbres-02A	Mimbres B/W Style III	Pottery	MURR	MN	Swarts	LA 001691	4.08	41.27 0	0.5292	35.15 6	6.19 4.57	57 3.29	9 71.78	24.44	36.73
SWR087	Group-C2a	Mimbres-42	Mimbres B/W Style III	Pottery	MURR	NM	Swarts	LA 001691	2.40	37.83 0	0.3163	33.10 5	5.93 1.6	1.69 2.25	5 74.39	21.23	58.13
SWR088	Group-B	Unas.	Mimbres B/W Style III	Pottery	MURR	MN	Swarts	LA 001691	3.33	50.45 0	0.6411	38.16 7.	7.67 4.01	3.62	2 107.00	14.77	23.81
SWR089	Group-B2	Mimbres-02A*	Mimbres B/W Style III	Pottery	MURR	NM	Swarts	LA 001691							9 85.25		35.33
SWR090	Group-B2	Mimbres-11	Mimbres B/W Style III	Pottery	MURR	M	Swarts	LA 001691	2.35				4.55 5.26				30.72
SWR091	Group-B1	Mimbres-04B	Mimbres B/W Style III	Pottery	MURR	M	Swarts	LA 001691	4.60	55.57 0	0.6932	43.10 8	8.20 7.4	7.49 3.94	4 103.67	14.84	28.50
SWR092	Group-C1	Unas.	Mimbres B/W Style III	Pottery	MURR	M	Swarts	LA 001691	3.61							"	37.90
SWR093	Group-B1	Mimbres-04A	Mimbres B/W Style III	Pottery	MURR	NM	Swarts	LA 001691	2.09	45.05 0							21.11
SWR094	Group-B2	Mimbres-02A	Mimbres B/W Style III	Pottery	MURR	MN	Swarts	LA 001691	00.00	40.77 0	0.5197	31.53 6	6.22 4.24	24 3.35	5 75.88		42.51
SWR095	Group-B2	Mimbres-02A	Mimbres B/W Style III	Pottery	MURR	MN	Swarts	LA 001691	0.00	42.16 0	0.5477	32.66 6	6.64 3.90	3.88	8 77.90	13.79	41.08
SWR096	Group-B2	Mimbres-02A	Mimbres B/W Style III	Pottery	MURR	MN	Swarts	LA 001691	2.64	35.28 0	0.5557	28.00 5	5.36 4.71	71 3.03	3 67.49	13.59	36.27
SWR097	Group-B2	Mimbres-11	Mimbres B/W Style III	Pottery	MURR	MN	Swarts	LA 001691	3.70	33.99 0	0.5794		4.45 3.50	50 2.90	0 74.71	35.91	41.11
SWR098	Group-B	Unas.	Mimbres B/W Style III	Pottery	MURR	MN	Swarts	LA 001691	2.89	40.93 0	0.3783	27.36 3.	3.55 3.61	51 2.36	88.75	6.18	12.46
SWR099	Group-B2	Mimbres-08	Mimbres B/W Style III	Pottery	MURR	NM	Swarts	LA 001691			0.4294	16.10 3	3.52 5.6	5.68 2.49	9 56.26		18.01
SWR100	Group-B	Unas.	Mimbres B/W Style III	Pottery	MURR		Swarts	LA 001691	5.52				4.62 4.67	57 3.42			28.05
SWR101	Group-B1	Mimbres-04C	Mimbres B/W Style III	Pottery	MURR	NM	Swarts	LA 001691	2.77	38.81 0	0.5259						31.25
SWR102	Group-B	Unas.	Mimbres B/W Style III	Pottery	MURR	MN	Swarts	LA 001691	2.58	28.69 0		20.44 3.	3.35 2.28	28 2.34	4 54.96	12.63	19.48
SWR103	Group-B2	Mimbres-02A	Mimbres B/W Style III	Pottery	MURR	MN	Swarts	LA 001691	0.00	42.15 0	0.5959	46.08 6	6.64 5.19	19 3.50	0 84.95	34.57	44.64
SWR104	Group-B	Unas.	Mimbres B/W Style III	Pottery	MURR	MN	Swarts	LA 001691						50 2.69		17.75	22.94
SWR105	Group-B2	Mimbres-02B	Mimbres B/W Style III	Pottery	MURR	₽	Swarts	LA 001691	4.23	47.42 0	0.5664	37.89 6	6.95 5.76	76 3.63	3 81.05	16.15	38.68
SWR106	Group-B1	Mimbres-04B	Mimbres B/W Style III	Pottery	MURR	MN	Swarts	LA 001691	3.76	57.61 0	0.6981	44.66	9.01 8.18	18 3.84	4 87.88	22.25	24.34
SWR107	Group-B2	Mimbres-02A	Mimbres B/W Style III	Pottery	MURR	MN	Swarts	LA 001691					9.79 4.31				43.91
SWR108	Group-B	Unas.	Mimbres B/W Style III	Pottery	MURR	MN	Swarts	LA 001691						46 2.98		7	30.64
SWR109	Group-B	Unas.	Mimbres B/W Style III	Pottery	MURR	M	Swarts	LA 001691			_	24.88 3		33 3.14			18.52
SWR110	Group-B2	Mimbres-02A	Mimbres B/W Style III	Pottery	MURR	NM	Swarts	LA 001691									38.07
SWR111	Group-B2	Mimbres-02A	Mimbres B/W Style III	Pottery	MURR	NM	Swarts	LA 001691								,	40.45
SWR112	Group-A		Mimbres B/W Style III	Pottery	MURR	M	Swarts	LA 001691					1				4.02
SWR113	Group-C2a		Mimbres B/W Style II/III	Pottery	MURR	M	Swarts	LA 001691	0.00	38.60 0					0 73.64		56.17
SWR114	Group-C2a		Mimbres B/W Style III	Pottery	MURR	M	Swarts	LA 001691	4.19								69.49
SWR115	Group-B2	Mimbres-11	Mimbres B/W Style II	Pottery	MURR	N S	Swarts	LA 001691		_							43.35
SWR116	Group-B1	Mimbres-04A	Mimbres B/W Style III	Pottery	MURR	MN :	Swarts	LA 001691		_							25.27
SWR117	Group-B2	Mimbres-08	Mimbres B/W Style III	Pottery	MURR	N S	Swarts	LA 001691	5.61								24.78
SWR118	Group-B2	Mimbres-02A*	Mimbres B/W Style III	Pottery	MUKK	N N	Swarts	LA 001691	4.64						_		31.97
SWR119	Group-B1	Mimbres-04C	Mimbres B/W Style II	Pottery	MURR	M	Swarts	LA 001691	4.58							_	39.96
SWR120	Group-B1	Mimbres-09	Mimbres B/W Style II	Pottery	MURR	M	Swarts	LA 001691	4.66					1.78 4.66	1		17.17
SWR121	Group-B2	Mimbres-08	Mimbres B/W Style III	Pottery	MURR	NM	Swarts	LA 001691	1.42	33.09 0						9.86	20.64
SWR122	Group-B2	Mimbres-02A	Mimbres B/W Style III	Pottery	MURR	NM	Swarts	LA 001691	2.48		0.5269					16.13	36.85
SWR123	Group-B	Unas.	Mimbres B/W Style III	Pottery	MURR	Σ	Swarts	LA 001691	2.15	42.58 0	0.4317	25.09 4	4.97 5.98	98 2.89	9 85.39	15.03	22.65
SWR124	Group-B	Unas.	Mimbres B/W Style III	Pottery	MURR	MN	Swarts	LA 001691	3.46	34.92 0	0.5234			25 3.40	0 64.34	08.6	19.60
SWR125	Group-C2	Unas.	Mimbres B/W Style III	Pottery	MURR	NM	Swarts	LA 001691	3.96	32.47 0	0.3839	29.13 5	5.87 1.87	37 2.87	7 66.36	17.78	84.96
SWR126	Group-B	Unas.	Mimbres B/W Style II	Pottery	MURR	M	Swarts	LA 001691	2.23								36.22
SWR127	Group-B1	Mimbres-09	Mimbres B/W Style III	Pottery	MURR		Swarts	LA 001691	0.00	_		62.37 13					18.65
SWR128	Group-A	Unas.	Mimbres B/W Style III	Pottery	MURR	NM	Swarts	LA 001691	16.11	133.07 1	1.3799 17	111.18 20	20.70 10.93	93 11.36	6 226.89	40.09	68.66

>	38.60	61.80	73.10	46.60	90.99	37.10	47.30	89.00	52.60	77.00	61.80	55.70	71.90	30.60	56.30	56.30	59.50	49.90	64.20	38.10	53.30	53.10	75.70	53.30	33.10	58.50	43.20	22.00	87.10	75.70	52.60	50.30	61.90	28.70	42.00	51.70	31.90	54.90	39.90	40.70	84.80	65.50	51.20	77.20
I	3979.2	3001.0	5070.1	3596.0	3159.6	3592.0	3019.0	4374.6	2585.8	3284.6	2869.3	3363.9	3503.0	1579.4	2832.3	1483.4	3132.7	2151.8	4515.2	2587.9	2456.0	2768.7	3981.5	2696.4	1645.1	3014.2	4078.8	1202.8	4161.3	4801.5	3559.1	2907.9	2555.5	3080.4	3377.0	2770.6	2805.8	3363.9	2237.1	2323.6	4114.5	3035.8	3065.4	2504.9
NA	11859.0	12421.6	22410.8	15120.1	14289.4	14538.3	12050.4	17267.7	17321.8	14304.8	14357.8	13626.8	11303.0	13652.6	10314.6	12850.1	16713.6	13410.1	15195.3	14046.1	12256.3	11988.7	14488.5	14611.9	15904.8	12685.8	12126.6	16419.1	23094.8	15990.5	13300.5	12360.5	9423.5	11/95.9	13556.3	16057.5	11156.9	14034.6	10277.1	14200.2	14612.1	14772.3	16817.3	10967.1
M	492.6	262.5	622.0	475.2	381.5	563.3	582.9	816.3	273.6	261.5	237.6	230.7	785.3	418.1	227.5	413.1	325.5	614.8	331.7	213.9	483.2	291.2	292.8	342.1	388.5	329.3	269.0	240.8	582.5	553.0	635.8	326.5	182.9	553.6	314.6	649.3	177.1	256.0	173.8	752.1	655.2	464.0	434.0	275.0
¥	29128.1	28864.7	20261.7	29535.0	28767.3	32406.6	29621.6	22720.3	30282.7	27381.2	27793.3	28888.2	31739.9	28876.4	30154.7	27700.9	22651.9	23080.6	27378.2	30955.0	28841.0	27082.3	23967.7	29216.9	29899.1	27378.4	27743.9	29235.7	24749.3	23557.7	28682.2	29/06.6	31/1/.1	26958.3	29172.6	30050.6	32599.8	29247.0	29010.6	26914.9	27210.0	23358.0	26235.5	25743.8
DΑ	7.233	5.231	3.310	4.988	5.532	4.146	6.053	4.653	4.020	5.232	4.482	3.930	3.702	2.554	2.240	3.910	4.721	2.837	5.127	2.991	5.732	6.472	7.251	4.594	2.888	4.154	2.067	1.860	3.848	8.739	4.204	5.090	2.947	6.205	3.900	7.094	2.811	4.856	3.316	3.254	3.250	3.471	7.803	6.080
CA	9835.3	9171.2	19564.4	4614.1	17333.7	9078.0	11103.6	17625.8	10405.0	12872.8	12708.3	11663.7	8298.5	11702.3	4632.8	16214.4	13295.2	18573.2	16348.4	7157.7	10628.8	8932.4	17879.6	8618.4	9862.4	12463.1	9443.6	8492.2	21940.3	20091.0	10673.9	11890.9	6397.3	14293.0	10488.3	13572.3	6932.9	12867.7	7482.4	15028.2	18936.3	17723.3	17742.7	14276.2
BA	265.7	527.2	869.2	800.5	441.6	379.8	564.7	902.0	721.8	713.0	6.199	603.0	353.4	148.0	426.9	288.5	785.2	329.1	267.0	433.4	1.664	628.5	736.4	662.3	261.3	519.8	532.1	145.5	964.4	724.7	476.9	1./19	401.0	532.0	9.189	1019.8	543.8	551.8	476.0	438.8	756.8	475.0	936.9	670.0
AL	98820.9	84055.3	95152.5	89118.6	78445.6	83890.7	90472.9	92688.6	87416.3	86735.3	91518.5	88267.7	75522.9	64874.7	80504.6	75527.0	90351.7	77420.3	0.0	86644.7	84537.4	92108.9	99425.1	89445.5	90589.0	82134.8	84968.7	96801.3	96352.2	89047.0	75975.3	82822.8	93290.5	9.2590.8	75133.0	77525.2	75455.4	79339.1	75310.2	71114.0	78102.7	88673.2	86466.4	96534.3
ZR	189.6	158.0	144.8	227.1	230.8	l I	271.3	216.9	160.3	181.5	168.3	158.5	133.5	136.8	168.2	135.4	212.8	104.5	107.7	124.1	136.4	174.7	232.4	294.2		290.3												279.7	286.4	134.3	179.5			598.0
NZ	82.4	74.3	113.0		81.2	73.5	71.4	85.4	54.1	77.0	68.5	73.9	68.1	80.4	42.5	72.4	74.0	114.5	115.1	125.7	8.79	689	76.8	292.9		130.1				` '	_				`	132.4		59.2	84.1	104.2				221.7
3 1	3 25.87	4 19.25	1 8.15		5 19.79	9 20.75	-	4 11.94	7 21.13	7 18.06	0 18.51	3 21.17	0 18.49	0 28.35	0 27.41	7 21.61	6 15.74	8 20.33	5 17.53	7 30.17	4 20.34	3 30.18		0 28.70	8 32.12	8 20.42		7				_	_			_		3 19.39	8 25.47	1 23.77	2 9.34			9 53.61
TA TE	1.43	95 0.84	76 0.81	1 0.66	79 1.05	0.49		3 0.64	71.0 68	88 0.77	0.70	35 0.63	71 0.50	34 0.40	09.0 7	99 0.57	51 0.76	2 0.38	37 0.75	1 0.57	18 0.74	11.13	22 0.98	5 0.70	0.48	0.78			_							3 1.37		14 0.93	3 0.58	0.71	32 0.72			3.09
	1.3143	1.5895	0.7276	1.2911	1.4879	1.8462		1.0133	1.4239	1.2788	1.3405	1.5385	1.6071	1.7034	1.5327		1.2251	1.4912	1.3687	1.7451	1.7248	1.5241	1.7122	1.6825	`					`							•	1.5644	1.6013		0.9332			3.3427
SR	0.0	0.0	630.2	189.6	364.6	0.0	177.6	396.7	292.0	242.8	233.4	304.1	192.6	334.5	0.0	256.4	0.0	298.4	0.0	0.0	822.8	0.0	402.0	0.0		323.4	205.8	162.5	774.8	556.0	315.1	716.7	0.0	41/.6	348.8	275.0	123.7	348.4	170.6	337.2	529.4	370.5	237.9	826.9
SC	8.38	10.12	13.64	8.23	9.67	6.84	8.60	10.48	7.45	10.96	11.47	9.96	7.18	4.89	5.28	6.77	8.85	5.88	11.33	98.9	8.58	8.06	12.14	7.13	6.02	10.26	9.39	4.00	12.54	12.02	7.59	7.64	6.21	10.80	7.96	9.57	4.99	9.36	5.71	7.08	10.50	7.88	9.88	31.05
SB	0.3373	0.0000	0.3535	0.5140	0.5033	0.5062	0.5592	0.6063	0.0000	0.0000	0.3255	0.4110	0.6727	0.3368	0.6063	0.4087	0.4852	0.4261	0.0000	0.4467	0.8067	0.0000	0.4444	0.0000	0.3943	0.4955	0.3635	0.4512	0.3183	0.5246	0.6123	0.4014	0.7415	0.3551	0.6615	0.5661	0.5049	0.4266	0.5325	0.3732	0.2965	0.4098	0.6483	1.0733
RB	141.50	152.90	90.60	129.30	138.40	178.90	172.40	124.70	138.90	139.30	141.40	157.00	197.80	08.69	187.30	160.80	118.20	133.60	155.40	197.20	189.40	176.60	120.70	164.20	167.00	158.60	164.00	254.90	72.80	118.20	181.60	151.10	189.10	16/.40	146.30	130.80	192.60	150.50	182.40	144.90	85.40	158.80	113.80	305.90
Z	0.0	0.0	0.0	0.0		0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0		0.0												0.0	0.0	0.0	0.0			0.0
土	6.48	8.19	6.82	8.35	8.40	7.67	6.33	6.43	8.28	8.89	8.40	8.50	7.47	5.45	7.67	97.9	8.50	6.27	8.06			7.37	8.53				9.57			8.24	7.81							8.03	9.30	5.73	6.83			16.24
H	25482.8	24994.1	40787.7	23682.3		19800.2	26235.6		21000.3	26400.7	26844.5	23645.5	23594.3	14450.0	18727.9	19870.6	26626.3	19106.6	27776.4		25422.6	25152.2	29647.5			23807.5		_						_			15492.3	22770.1		19567.9	40077.0			75564.6
EU	1.7169	1.0815	1.5337	1.5137		0.8572		1.5232	1.2588	1.2725	1.2727	1.0128	0.8486	0.4952	0.6657		1.3135	0.6357	1.3718	7.73 0.8525	1.1449	1.5793	1.8397	0.9968	7.20 0.5683	1.0801	1.0732					1.1593			1.1121	4.64 2.1049		1.1917	6.87 0.8787	0.8875	1.4386		2.5606	47.20 3.4848
CS	6.32	15.66	5.65	5.56	18.22	7.40	6.60	12.99	4.68	13.88	13.80	21.05	69.9	7.37	6.92	11.09	5.18	12.28	15.16	7.73	39.77	6.12	18.38	7.66	7.20	15.60	17.89	17.40	4.89	4.34	6.64	5.39	1.75	23.78	5.10	4.64	6.04	17.43	6.87	13.10	2.24	9.93	4.74	47.20
ANID	SWR085	SWR086	SWR087	SWR088	SWR089	SWR090	SWR091	SWR092	SWR093	SWR094	SWR095	SWR096	SWR097	SWR098	SWR099	SWR100	SWR101	SWR102	SWR103	SWR104	SWR105	SWR106	SWR107	SWR108	SWR109	SWR110	SWR111	SWR112	SWR113	SWR114	SWR115	SWR116	SWRII/	SWR118	SWR119	SWR120	SWR121	SWR122	SWR123	SWR124	SWR125	SWR126	SWR127	SWR128

ANID	macro_grp	Chem2012	CERAMIC TYPE	MATERIAL	SOURCE	STATE	SITE_NAME	SITE_NO	AS	ГА	Π	QN	SM	n	YB C	CE CO	CR
SWR129	Group-B2	Mimbres-02A		Pottery	MURR		Swarts	LA 001691	0.00	48.98 0.	0.5918 3	36.80	7.65 4.	4.39 4.86	86 81.07	7 10.47	40.13
SWR130	Group-B1	Mimbres-04A	Mimbres B/W Style III	Pottery	MURR		Swarts	LA 001691	7.07		0.6536 5.		9.99 5.	5.62 4.73	1		
SWR131	Group-B2	Mimbres-08	Mimbres B/W Style III	Pottery	MURR	MN	Swarts	LA 001691	3.47	37.29 0.	0.4788 2	20.85 4	4.05 6.	6.25 2.7	2.75 71.50	0 11.96	25.85
SWR132	Group-B2	Mimbres-02A	Mimbres B/W Style III	Pottery	MURR		Swarts	LA 001691	0.00				4.70 5.	5.12 3.8	3.80 67.87	7 10.85	
SWR133	Group-B	Unas.	Mimbres B/W Style III	Pottery	MURR		Swarts	LA 001691	2.23				7.34 4.		3.89 87.29	9 11.14	26.89
SWR134	Group-A	Mimbres-01	Mimbres B/W Style III	Pottery	MURR		Swarts	LA 001691	3.04	58.52 0.	0.6395 3	33.17 5	5.72 12.	12.80 3.41	41 103.72	2 10.70	7.02
SWR135	Group-B2	Mimbres-02A		Pottery	MURR		Swarts	LA 001691	0.00	50.87 0.					4.15 109.23	3 10.80	
SWR136	Group-B1	Mimbres-04A	Mimbres B/W Style III	Pottery	MURR		Swarts	LA 001691	3.64	44.08 0.	0.5193 3	39.92 6	6.97 3.	3.92 3.71	71 93.69	11.47	25.40
SWR137	Group-B2	Mimbres-02B	Mimbres B/W Style III	Pottery	MURR		Swarts	LA 001691	5.04	38.52 0.	0.5991 3	31.43 6	6.03 5.	5.12 4.21	21 69.97	7 13.70	38.42
SWR138	Group-B2	Mimbres-02A	Mimbres B/W Style III	Pottery	MURR		Swarts	LA 001691	0.00	44.64 0.	0.6092	35.64	7.42 6.	6.76 3.8	3.86 81.68	8 11.44	37.83
SWR139	Group-A	Mimbres-01	Mimbres B/W Style III	Pottery	MURR	MN	Swarts	LA 001691	3.25	50.22 0.	0.5596 2.	24.34 4	4.30 11.	11.84 2.4	2.45 80.16	6 12.32	9.10
SWR140	Group-B2	Mimbres-02A	Mimbres B/W Style III	Pottery	MURR	MN	Swarts	LA 001691	1.70	36.89 0.		34.97 5	5.70 3.	3.40 3.4	3.45 67.95	5 12.32	35.58
SWR141	Group-B	Unas.	Mimbres B/W Style III	Pottery	MURR	MN	Swarts	LA 001691	4.25	38.73 0.	0.3326 2	28.14 5	5.45 3.	3.07 2.5	2.53 75.41	1 16.11	59.75
SWR142	Group-B2	Mimbres-08	Mimbres B/W Style III	Pottery	MURR	MN	Swarts	LA 001691	4.41	31.81 0.	0.3880 2	20.56 3	3.50 5.	5.95 2.3	2.33 64.76	9.756	24.57
SWR143	Group-B	Unas.	Mimbres B/W Style III	Pottery	MURR	MN	Swarts	LA 001691	0.00	41.34 0.	0.3808 4	44.77 6	6.08 5.	5.03 3.2	3.24 79.69	13.70	25.28
SWR144	Group-B	Unas.	Mimbres B/W Style III	Pottery	MURR		Swarts	LA 001691	3.39				5.04 4.	4.46 2.34			
SWR145	Group-B1	Mimbres-04B	Mimbres B/W Style III	Pottery	MURR	MN	Swarts	LA 001691	4.21	48.83 0.	0.5513 3	39.01	8.05 9.	9.46 3.41	41 80.34	4 10.75	23.49
SWR146	Group-B2	Mimbres-11	Mimbres B/W Style II	Pottery	MURR	MN	Swarts	LA 001691	0.00	37.13 0.	0.6028	31.07 5	5.55 5.	5.55 3.5	3.58 70.75	5 21.57	41.45
SWR147	Group-A	Mimbres-01	Mimbres B/W Style III	Pottery	MURR	M	Swarts	LA 001691	0.00	54.46 0.	0.6469 2	24.51 5	5.67 13.	13.68 3.4	3.40 95.42	.2 9.58	5.21
SWR148	Group-B1	Mimbres-04A	Mimbres B/W Style III	Pottery	MURR	M	Swarts	LA 001691	1.85	44.68 0.	0.4951 3	33.30 6	6.55 3.	3.61 3.4	3.46 92.48	8 14.06	21.89
SWR149	Group-C2a	Mimbres-49A	Mimbres B/W Style III	Pottery	MURR	MN	Swarts	LA 001691	0.00		0.3140 3	34.60 6	6.73 2.	2.20 2.3	2.38 80.23	3 17.96	51.63
SWR150	Group-B2	Mimbres-08	Mimbres B/W Style III	Pottery	MURR	M	Swarts	LA 001691	3.45	33.91 0.	0.3240 2.	22.63 4	4.00 4.	4.91 2.4	2.40 72.42	2 34.13	27.16
SWR151	Group-B1	Mimbres-04B	Mimbres B/W Style III	Pottery	MURR	M	Swarts	LA 001691	0.00	54.86 0.	0.5723 5	53.37	9.46 9.	9.82 3.3	3.30 88.23	3 12.30	29.48
SWR152	Group-B2	Mimbres-08	Mimbres B/W Style III	Pottery	MURR		Swarts	LA 001691	3.49	33.86 0.		22.02		4.29 2.81			22.78
SWR153	Group-B	Unas.	Mimbres B/W Style III	Pottery	MURR		Swarts	LA 001691	3.43	44.67 0.					4.09 110.59	12.09	42.99
SWR154	Group-B2	Mimbres-02A		Pottery	MURR		Swarts	LA 001691	0.00					5.08 3.5		1 8.52	
SWR155	Group-B1	Mimbres-04B	Mimbres B/W Style III	Pottery	MURR	MM	Swarts	LA 001691	2.46	59.92 0.	0.6852 4	49.18 9	9.80 6.	6.65 4.8	4.86 107.49	9 7.11	24.87
SWR156	Group-B	Unas.		Pottery	MURR		Swarts	LA 001691	4.41	-						7	
SWR157	Group-B1	Mimbres-04A		Pottery	MURR		Swarts	LA 001691	0.00	51.51 0.							
SWR158	Group-B	Unas.	Mimbres B/W Style III	Pottery	MURR		Swarts	LA 001691	4.42							`	
SWR159	Group-B	Unas.	Mimbres B/W Style III	Pottery	MURR		Swarts	LA 001691	1.31	_						1	
SWR160	Group-B1	Mimbres-04B		Pottery	MURK		Swarts	LA 001691	1.62								
SWR161	Group-B1	Mimbres-04A		Pottery	MURR		Swarts	LA 001691	2.46								
SWR162	Group-B1	Mimbres-04A	Mimbres B/W Style III	Pottery	MURR		Swarts	LA 001691	0.00								
SWR163	Group-B	Unas.	Mimbres B/W Style III	Pottery	MURR		Swarts	LA 001691	2.73								
SWR164	Group-B	Unas.	Mimbres B/W Style II	Pottery	MURR		Swarts	LA 001691	2.76				6.24 3.				
SWR165	Group-B	Unas.	Mimbres B/W Style III	Pottery	MURR		Swarts	LA 001691	3.52							1	
SWR166	Group-B1	Mimbres-04C	Mimbres B/W Style III	Pottery	MURR	MN	Swarts	LA 001691	2.56	46.98 0.	0.5389 3	37.30	7.31 5.	5.23 4.07	07 103.21	1 9.73	27.64
SWR167	Group-B2	Mimbres-08	Mimbres B/W Style III	Pottery	MURR		Swarts	LA 001691	3.34	35.42 0.		19.05	4.05 4.	4.53 2.9	2.90 81.85	5 10.86	25.14
SWR168	Group-B	Unas.	Mimbres B/W Style III	Pottery	MURR		Swarts	LA 001691	2.82	_			8.42 3.	3.50 3.9	3.98 96.64		26.43
SWR169	Group-B2	Mimbres-08	Mimbres B/W Style III	Pottery	MURR		Swarts	LA 001691	4.53	32.07 0.	0.3926 1		3.43 4.	4.75 2.37	37 59.09	9 9.27	24.73
SWR170	Group-C2a	Mimbres-42	Mimbres B/W Style III	Pottery	MURR		Swarts	LA 001691	3.43							1	
SWR171	Group-B2	Mimbres-08		Pottery	MURR		Swarts	LA 001691	4.30					6.09 2.7			
SWR172	Group-B1	Mimbres-04A	Mimbres B/W Style III	Pottery	MURR	Σ Z	Swarts	LA 001691	2.78	46.37 0.	0.4257 3	30.82 6	6.55 4.	4.14 3.3	3.38 90.47	69.9	18.60

>	63.10	46.80	47.00	49.50	39.20	29.80	34.50	55.30	72.00	55.30	28.40	51.00	92.70	44.80	06.69	38.90	47.00	55.50	32.40	40.90	85.70	38.00	29.00	38.10	00.69	42.60	54.80	36.30	49.00	53.60	67.30	45.90	40.20	47.90	38.90	54.70	77.80	50.40	38.80	50.70	46.00	77.20	42.90	46.00
I	2590.1	1890.1	2798.8	3069.0	2711.7	2035.5	3097.9	3647.8	3113.2	3344.0	2269.3	3033.8	4990.7	2576.2	3306.5	2595.7	2859.3	3147.9	2270.8	3171.6	4995.1	2566.5	2996.0	2228.5	2345.7	3301.1	2974.5	2078.8	2221.4	1917.5	3565.2	3130.9	0.1677	3461.5	1147.5	3127.6	2974.8	2364.8	2578.3	2984.7	3300.9	3864.6	2727.6	2794.9
NA	11941.9	13450.0	8334.8	10656.4	10545.6	15734.0	12382.4	14668.0	10151.0	13596.1	17323.9	12034.8	14896.7	9176.8	15913.1	15312.8	11328.8	13392.5	17518.1	15033.7	17237.8	10639.3	8927.1	11242.7	9717.3	14432.7	10540.4	10936.1	15507.5	13796.3	17403.5	12683.8	18141.5	15557.2	12520.8	15551.0	13786.9	15699.9	10506.4	15965.8	11063.3	17073.4	10489.1	17226.1
MN	228.4	685.3	169.5	190.5	386.3	253.0	232.6	498.5	733.6	281.8	197.5	240.6	459.5	324.6	415.9	683.3	246.4	482.4	193.8	443.4	480.0	315.3	187.4	556.9	1048.0	351.1	439.6	1623.6	478.2	921.6	268.0	400.7	1.879	316.7	1011.6	297.2	664.2	662.0	419.4	504.5	195.7	586.7	182.5	292.3
¥	22459.1	26137.3	27164.7	33368.1	26773.5	33881.4	33813.7	27532.3	30250.6	27239.1	32824.6	26405.1	24833.5	28839.0	29049.5	24674.9	26193.3	30300.8	34981.9	27605.4	24993.6	29646.8	22170.9	30538.2	25205.6	28927.0	24488.8	29079.6	27872.5	19945.6	28605.7	282/6.6	31110.9	31300.8	25050.9	29046.6	29124.6	28070.7	29453.6	31747.7	30878.4	19030.3	29905.5	30031.3
DY	5.127	6.033	2.809	3.777	5.206	3.375	4.619	4.682	4.865	5.497	2.522	4.283	3.907	2.493	4.043	2.757	5.284	4.110	3.810	4.160	4.205	2.699	5.750	3.014	4.331	4.484	7.079	1.796	5.062	2.682	4.494	4.708	4.353	4.911	2.910	4.241	4.159	4.799	2.771	4.958	2.708	3.656	2.675	4.125
CA	12081.7	15601.5	7032.7	7439.4	10214.3	8418.2	8822.0	14686.8	12262.0	15659.6	9317.8	10434.1	13805.9	6467.6	13459.2	18353.0	8565.3	8899.2	7207.8	11337.8	19001.7	6501.7	8294.8	7941.3	10356.4	12952.4	8746.5	8588.2	14129.3	16476.9	13638.1	87//8	14111.4	10963.5	15501.3	12645.4	10482.8	12523.4	6754.0	13131.8	6252.7	17979.3	5408.8	11129.7
BA	528.3	695.2	303.9	323.6	510.8	438.1	448.5	697.5	528.9	544.1	337.1	463.0	774.8	382.5	827.6	539.9	548.7	499.9	440.0	0.707	715.0	372.1	398.7	520.2	342.3	481.8	492.9	332.5	504.7	314.4	787.0	2.755	/35.8	626.8	179.9	691.2	405.6	640.1	416.5	824.1	510.7	879.2	378.1	734.1
AL	76787.4	80583.5	85637.9	81616.6	77765.6	97615.0	84934.0	82698.5	86793.3	85822.8	6.08876	85139.6	0.0	86404.3	92852.5	74991.7	91088.7	87728.3	0.0	84009.2	6.68786	83470.8	0.0	74080.5	87894.1	79569.4	97955.9	81114.7	81039.0	80599.4	81703.4	85281.5	1.717	91496.8	72713.1	80473.5	89714.0	82656.9	81353.0	86397.0	78423.1	93886.1	84882.6	78925.2
ZR	252.8	221.2				237.0		346.6	241.8	230.8	274.6		305.8	255.1	332.1	205.6	215.8	180.0	258.9	223.7	234.4	234.7	184.6		274.5	277.1		229.3									125.9	179.8	169.9	153.1	158.7			143.7
NZ	63.1	165.4	70.4	81.5	104.6	67.3	75.6	119.1	101.8	124.1	57.6	91.5	138.2	100.5	115.2	96.1	126.7	107.9	51.9	72.8	117.4	72.1	137.1	89.5	81.2	91.7	135.7	71.5	131.8	105.0	101.1	116.2	108.3	105.7	92.4	58.6	92.7	105.2	72.7	146.3	46.1	9.96	54.9	72.3
H	19.47	18.32		23.52	22.16	46.06	21.05	18.27	21.07	20.08	40.67	20.67	16.38	26.79	17.26	19.74	26.76	20.37	42.62	19.84	11.68	26.51	27.19	25.76		19.82										17.03		17.96	26.30	15.74	25.98		_	20.25
A TB	7 1.03	3 1.34	3 0.46	9 0.75	6 1.13	8 0.61		0.87	9 0.74	4 1.09	9 0.40	9 0.82	6 0.57	0 0.58	1 0.81	99.0 8	2 1.06	6 0.63	99.0 /	2 0.89	2 0.76	7 0.54	0 1.14	3 0.51		5 0.78					-+					5 0.73		4 0.85	6 0.53	7 0.94	9 0.44			8 0.67
TA	1.3287	1.2123	1.4953	1.6629	1.4106	٠,	1.5219	1.3419	1.5099	1.4634	2.0789	1.5159	1.1826	1.5690	1.2501	1.2538	1.5012	1.6966	2.1077		0.9992	1.5917	1.4990	1.5373	1.5186	1.5275		`										1.2684	1.5676	0.9727	1.5649	_		1.2588
SR	304.8	363.0	138.5	193.0	188.2	286.9	319.4	6'667	237.1	364.6	122.2	244.7	369.4	183.6	367.2	9'609	0.0	243.0	202.2	290.1	203.5	150.0	122.0	329.1	726.7	467.3	205.7	288.6	317.9	364.3	568.2	243.6			334.9	608.2	328.9	272.4	9'688	194.3	105.3	550.8	94.2	266.5
SC	12.05	8.70	6.72	9.15	7.57	4.47	8.58	7.88	8.86	10.91	4.86	6.97	12.15	6.55	8.09	7.63	8.03	8.23	3.61	7.09	10.52	6.13	10.35	5.58	10.15	9.58	8.72	89.8	6.82	6.77	6.32	6.34	6.54	7.38	6.09	7.19	9.12	8.29	6.11	10.33	5.86	14.38	5.95	6.57
SB	0.4035	0.2987	0.5826	0.4634	0.5405	0.5696	0.4899	0.3109	1.0293	0.3690	0.5901	0.4776	0.4400	0.6571	0.2772	0.4320	0.3155	0.6247	0.5780	0.4783	0.3747	0.5218	0.4564	0.5299	0.9337	0.7103	0.4871	0.8475	0.3647	0.4301	0.2621	0.4053	0.2708	0.5501	0.3453	1.4763	0.4248	0.3489	0.5579	0.5989	0.5257	0.3455	0.4747	0.2905
RB	137.70	119.70	187.20	188.60	160.90	182.80	173.20	140.80	181.60	145.10	236.20	159.40	121.50	195.30	121.40	142.10	142.70	189.10	182.80	131.80	113.60	187.80	129.70	190.70	210.20	168.70	161.20	187.10	133.40	163.80	131.80	164.10	132.80	176.10	160.50	154.00	206.10	116.00	180.60	129.40	186.30	83.80	187.40	144.00
Z	0.0	0.0		0.0		0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0		0.0		0.0										0.0	0.0	0.0	0.0			0.0
出	7.36	99.9	7.50	9.00	9.90	7.71	8.79	8.40	7.03	7.90	6.28	7.69	8.21	8.35	9.01		6.30	7.63	7.83	6.84	86.9	7.17	5.86	8.99	7.13	7.97	5.77	7.63	8.07	6.36	7.59	6.89	7.88	9.24	6.56	7.03	9.90	6.92	98.6	8.96	8.47	6.34	7.91	7.33
FE	26350.1	27632.3				9.08/6	21070.5	29594.1	25384.5	25885.1	13804.3		39008.3	22490.0	28427.1		23225.2	22243.3	9133.9	20720.4	37829.9	19841.3	29718.3	17488.8		25483.8								_				28782.5	21375.4	28973.6	21073.7			20532.0
ED	1.4653	1.6423		0.7497		0.8252		1.2339	1.0497	1.3436	0.6278	1.0301	1.1999	0.5637	1.1938		1.2594	1.0011	0.8068	1.2535	1.5704	0.6664	1.3724	0.7150		1.1497					1.3154			1.2261				1.3623	0.7068	1.8510	0.6595			1.3648
CS	15.06	4.56	7.84	17.64	5.74	14.02	15.16	4.61	30.62	16.15	20.13	21.03	5.53	8.07	3.67	11.58	2.68	7.85	17.31	4.94	3.69	7.32	6.32	6.30	43.81	14.55	6.15	7.97	3.74	17.22	2.97	5.21	4.18	4.72		7.94	10.61	4.65	6.84	5.04	6.97		7.26	4.36
ANID	SWR129	SWR130	SWR131	SWR132	SWR133	SWR134	SWR135	SWR136	SWR137	SWR138	SWR139	SWR140	SWR141	SWR142	SWR143	SWR144	SWR145	SWR146	SWR147	SWR148	SWR149	SWR150	SWR151	SWR152	SWR153	SWR154	SWR155	SWR156	SWR157	SWR158	SWR159	SWR160	SWK161	SWR162	SWR163	SWR164	SWR165	SWR166	SWR167	SWR168	SWR169	SWR170	SWR171	SWR172

ANID	macro_grp	Chem2012	CERAMIC TYPE	MATERIAL	SOURCE	STATE	SITE_NAME	SITE_NO	AS	ГА	Π	ND	SM	U YB	B CE	00	CR
SWR173	Group-B	Unas.	Mimbres B/W Style II	Pottery	MURR	NM	Swarts	LA 001691	2.72	39.32 0				4.05 2.84		10.39	32.15
SWR174	Group-B	Unas.	Mimbres B/W Style III	Pottery	MURR	MN	Swarts	LA 001691	3.07	47.73 0	0.5544	34.87 6	6.56 4.	4.76 4.06	16 86.37	10.26	30.19
SWR175	Group-B	Unas.	Mimbres B/W Style III	Pottery	MURR	NM	Swarts	LA 001691	1.95	34.66 0	0.4217	22.67 4	4.66 3.	3.48 3.06	6 67.85	16.96	39.34
SWR176	Group-B2	Mimbres-08	Mimbres B/W Style III	Pottery	MURR	MN	Swarts	LA 001691	2.34	32.68 0	0.3988	20.22 3	3.42 4.47	47 2.56	6 60.26	10.40	23.27
SWR177	Group-B2	Mimbres-08	Mimbres B/W Style III	Pottery	MURR	NM	Swarts	LA 001691	3.06					4.70 2.53			25.29
SWR179	Group-B2	Mimbres-02A	Mimbres B/W Style III	Pottery	MURR	M	Swarts	LA 001691	1.73		0.4461		6.50 4.	4.64 3.55	5 85.74	14.04	35.14
SWR180	Group-A	Mimbres-03	Mimbres B/W Style III	Pottery	MURR	NM	Swarts	LA 001691	2.96	45.81	1.4688	57.00 14	14.73 5.	5.55 11.82	_	11.65	12.16
SWR181	Group-B2	Mimbres-02A	Mimbres B/W Style III	Pottery	MURR	M	Swarts	LA 001691	2.82				6.40 4.8			12.06	41.97
SWR182	Group-B2	Mimbres-02A	Mimbres B/W Style III	Pottery	MURR	NM	Swarts	LA 001691	0.00	41.60 0						11.66	38.83
SWR183	Group-B2	Mimbres-02A	Mimbres B/W Style III	Pottery	MURR	MN	Swarts	LA 001691	3.87		0.5356	27.39 5	5.94 5.21	21 3.56	6 67.04	10.33	31.54
SWR184	Group-B1	Mimbres-04B	Mimbres B/W Style III	Pottery	MURR	MN	NAN	LA 002465	2.16	42.84 0	0.4628	26.17 5	5.06 5.	5.60 3.02	19.64	18.94	31.16
SWR185	Group-B2	Mimbres-11	Mimbres B/W Style III	Pottery	MURR	MN	NAN	LA 002465	00.0	34.12 0	0.4909	23.76 4	4.73 5.	5.64 3.10	0 64.47	20.95	36.82
SWR187	Group-A	Mimbres-01	Mimbres B/W Style III	Pottery	MURR	NM	Swarts	LA 001691	3.10				7.22 12.87	87 4.47	. 1		9.70
SWR188	Group-B1	Mimbres-04B	Mimbres B/W Style III	Pottery	MURR	NM	Swarts	LA 001691	0.00		0.6386	_	7.11 5.	5.56 4.22	2 96.69	11.20	28.84
SWR189	Group-B	Unas.	Mimbres B/W Style III	Pottery	MURR	NM	Swarts	LA 001691	2.40	55.44 0	0.5469		8.16 7.8	7.82 3.90	0 101.50	7.66	24.13
SWR190	Group-B2	Mimbres-02A	Mimbres B/W Style III	Pottery	MURR	NM	Swarts	LA 001691	1.71						5 71.22	11.56	37.65
SWR191	Group-B1	Mimbres-04B	Mimbres B/W Style III	Pottery	MURR	Σ	Swarts	LA 001691	2.11	51.91 0	0.5373		6.84 5.	5.99 3.80	0 98.26	19.10	25.74
SWR192	Group-B1	Mimbres-04A	Mimbres B/W Style III	Pottery	MURR	MN	Swarts	LA 001691	2.49	65.69 0	0.7245		11.04 4.	4.46 5.24	116.98	13.11	25.08
SWR193	Group-B2	Mimbres-02A	Mimbres B/W Style III	Pottery	MURR	NM	Swarts	LA 001691	0.00	44.84 0	0.6058	38.48 7	7.49 4.:	4.38 3.98	8 85.49	10.77	42.77
SWR194	Group-B1	Mimbres-04A	Mimbres B/W Style III	Pottery	MURR	MN	Swarts	LA 001691	3.54	35.70 0	0.4217		4.80 4.	4.64 2.85		7.15	17.74
SWR195	Group-B1	Mimbres-04B	Mimbres B/W Style III	Pottery	MURR	MN	Swarts	LA 001691	2.88	49.84 0	0.4944	35.43 6	.9 06.9	6.53 3.58	8 89.16	4.87	21.24
SWR196	Group-B2	Mimbres-02C	Mimbres B/W Style III	Pottery	MURR	MN	Swarts	LA 001691	2.86	37.25 0	0.6023	21.86 4	4.37 3.	3.18 3.82	2 68.18	9.69	17.54
SWR197	Group-B2	Mimbres-02A	Mimbres B/W Style III	Pottery	MURR	MN	Swarts	LA 001691	1.66	43.61 0	0.5573			5.90 3.89			37.74
SWR198	Group-B	Unas.	Mimbres B/W Style III	Pottery	MURR	NM	Swarts	LA 001691	3.60				_			1	16.24
SWR199	Group-A	Mimbres-01*	Mimbres B/W Style III	Pottery	MURR	NM	Swarts	LA 001691	0.00	42.71 0	0.4134	19.90 4	4.21 10.38	38 2.78	8 82.10	9.56	15.08
SWR200	Group-B1	Mimbres-09	Mimbres B/W Style III	Pottery	MURR	M	Ft. Bayard	LA 018372	1.68						Υ		15.31
SWR201	Group-B2	Mimbres-02C	Mimbres B/W Style III	Pottery	MURR	M	Swarts	LA 001691	3.81					2.85 3.12			15.49
SWR202	Group-B1	Mimbres-04A	Mimbres B/W Style III	Pottery	MURR	MM	Swarts	LA 001691	2.31								19.06
SWR203	Group-B1	Mimbres-04A	Mimbres B/W Style III	Pottery	MURR	M	Swarts	LA 001691	3.69					5.65 3.03			20.47
SWR204	Group-B2	Mimbres-02A	Mimbres B/W Style III	Pottery	MURR	M	Swarts	LA 001691	0.00								30.30
SWR210	Clay		Clay	Clay	MURR	ΣN	Swarts	LA 001691	2.16	_							35.85
SWR211	Clay		Clay	Clay	MURR	M	Swarts	LA 001691	2.09								45.89
SWR212	Clay		Clay	Clay	MURR	MM	Swarts	LA 001691	2.57				5.94 3.			10.16	53.53
SWR213	Clay		Clay	Clay	MURR	M	Swarts	LA 001691	1.62	40.34 0		32.75 6		3.38 2.91		1	46.59
SWR214	Group-B1	Mimbres-04B	Mimbres B/W Style I	Pottery	MURR	NM	Swarts	LA 001691	2.43	46.15 0	0.4251		5.59 5.	5.39 2.76		4.50	27.61
SWR215	Group-C1	Mimbres-24	Mimbres B/W Style I	Pottery	MURR	NM	Swarts	LA 001691	4.95					2.84 3.68		_	54.90
SWR216	Group-B	Unas.	Mimbres B/W Style I	Pottery	MURR	NM	Swarts	LA 001691	4.01					4.19 3.34			33.34
SWR217	Group-B	Unas.	Reserve B/W?	Pottery	MURR	Σ	Swarts	LA 001691	4.50	40.31 0	0.4764	26.77 5	5.58 5.	5.79 3.38	8 87.97	7.91	36.60
SWR218	Group-C2		Mimbres B/W Style I	Pottery	MURR	NM	Swarts	LA 001691	2.03		0.4566				1	15.02	43.60
SWR219	Group-C2a	Mimbres-49A	Mimbres B/W Style II?	Pottery	MURR	NM	Swarts	LA 001691	2.76					2.84 2.58		10.24	57.53
SWR220	Group-B1	Mimbres-04C	Mimbres B/W Style I	Pottery	MURR	M	Swarts	LA 001691	1.73				6.53 3.81				35.97
SWR221	Group-B1	Mimbres-04C	Mimbres B/W Style I	Pottery	MURR	M	Swarts	LA 001691	1.09					_			33.54
SWR222	Group-C2	Unas.	Mimbres B/W Style I	Pottery	MURR	M	Swarts	LA 001691	4.36						1	_	36.10
SWR223	Group-B1	Mimbres-04A	Mimbres B/W Style I	Pottery	MURR	MM	Swarts	LA 001691	2.11	33.58 0	0.4284	24.69 4		5.09 2.88	8 72.98	9.06	22.97

>	52.20	59.80	63.80	34.60	46.00	46.20	29.20	55.00	20.60	51.30	44.90	49.70	33.60	43.30	42.80	26.90	41.90	68.30	64.90	42.70	35.10	32.70	63.40	35.90	30.00	34.70	37.02	36.84	44.17	46.08	50.21	67.79	08.70	45.97	04 10	58.00	E2 82	25.35 66.28	75.58	58.75	87.86	70.55	55.53
I	2704.6	2917.5	2832.0	2212.2	2140.6	2753.5	1874.3	3627.8	3496.4	2663.7	2534.7	2277.6	1737.3	2423.4	2734.7	3144.7	2633.0	2476.1	3614.1	2602.6	2396.7	1693.6	3002.9	498.4	1282.2	2684.1	1498.0	2877.0	2659.0	3242.4	2722.7	0.6077	4133.0	5230.7	1001	7,967	26.02.2	3006 5	4074.8	3365.5	4119.2	3584.4	3077.6
NA	15804.8	12147.2	12270.7	10946.6	9929.3	13579.9	5242.9	11319.0	13031.2	13769.9	12581.8	12702.3	15309.7	12896.3	10352.6	14476.0	13307.7	14061.5	12967.3	14891.1	10172.9	12584.8	13237.3	10642.2	14521.1	15965.3	12912.2	17486.7	15917.9	14226.7	18556.8	16050.6	18241.1	12226.0	105250.7	135881	1/0571	18047 5	14208.9	15550.4	14746.2	15293.2	15176.7
M	701.9	652.8	785.3	216.3	335.4	422.1	612.8	165.9	220.5	280.8	182.9	1409.9	1052.7	711.3	235.7	235.0	210.1	296.2	227.5	201.5	242.4	794.9	282.3	2194.5	1776.4	572.7	567.4	212.0	216.2	480.3	682.0	530.9	1.186	0.470	7 027	244.4	221 g	1518.8	341.7	327.4	685.3	137.9	880.0
¥	27846.2	27579.6	30058.3	32813.9	30985.1	27160.9	45639.7	23871.3	24375.4	24651.7	27677.2	26294.3	28333.7	28123.8	26522.1	27282.7	28417.4	25415.5	25761.4	31746.3	27746.3	24482.6	25347.4	19994.0	32861.2	28919.3	22806.0	29782.8	27781.2	26029.4	30169.0	29485.3	C.02002	0.02082	20110.0	2874.4	7007 5	27027.3 25519.8	23802.1	26106.5	25534.8	22012.4	31794.8
DY	3.099	4.905	3.080	2.726	3.194	5.090	17.307	4.690	4.236	4.254	3.387	2.396	4.417	4.845	5.502	4.258	5.310	8.126	5.683	3.896	5.296	3.534	4.771	2.394	2.167	7.502	3.421	4.787	4.564	4.461	3.783	4.086	3.001	4.180	4.271	4 4 79	/ 103	5 837	4.719	5.020	5.121	4.184	3.968
CA	9129.3	10851.6	9412.3	6354.9	7305.1	11759.9	9952.3	10162.7	10442.0	11770.0	8134.0	7951.7	7667.2	10062.2	14194.6	11645.8	10196.5	11664.8	11043.7	9163.0	7243.7	12664.5	10703.7	15071.5	7578.1	13779.5	14851.0	11283.9	11508.9	13624.1	22436.3	17305.0	7 00010	0522 2	17260 0	16/10/13	15//8 0	14980 3	17291.6	12233.0	12802.4	9841.3	9752.5
BA	605.2	596.1	573.9	344.7	420.2	517.0	72.5	596.2	514.5	493.6	586.1	468.4	321.7	725.8	612.2	502.6	577.5	645.2	484.9	726.7	516.4	227.2	9.899	227.1	247.6	944.1	241.7	823.2	9.009	444.8	707.5	505.1	041.7	0.010	7 009	536.0	560.0	12771	695.4	704.7	693.3	723.6	756.6
AL	69002.6	79097.4	73411.2	80283.0	84937.5	82082.1	81056.2	88338.3	87065.1	78794.6	84640.3	76443.8	103250.8	88346.3	86227.2	85302.8	72114.7	89879.0	88442.2	91280.9	81589.3	78857.0	85194.7	64437.5	93148.3	88195.8	68374.2	84175.4	82145.2	80142.0	7,1991.8	710207	700007	022/20	73243.0	827610	91402 2	91343.0	99769.2	84675.7	85518.6	103356.4	89252.1
ZR	150.7	132.1	141.6	153.1	142.5	141.4	153.3	225.7	232.8	200.1	183.0	209.0	198.6	149.4	219.6	208.4	187.0		182.3	9.761	189.6	129.4	1.791									231.8	0.477	1747	107.5			228.8	189.7		186.4	152.0	231.2
NZ	79.8	126.3	61.3	48.8	112.0	79.4	166.0	70.6	63.9	93.8	75.2	70.0	88.4	85.4	100.6	57.6	47.7	8.96	112.5	94.2	78.0	81.5	80.7	112.5	54.6	105.8	70.6	53.2	53.6	55.6	79.4	119.4	98.4	60.3	101 E	6.101	77.6	81.0	109.2	93.5	94.7	88.5	75.4
H I	16.38	1 21.27		1 26.48		5 20.30	43.35	21.15	19.88	22.38	3 26.20	20.55	49.82	26.56	5 25.40	19.09	3 26.91		19.32	3 22.35	26.06	1 27.64	18.09									16.06		00.13		_					18.88		22.19
TA TE	2 0.76	1 0.84	09.0 /	0 0.44		9 0.75	0 2.62	0 1.00	8 0.79	6 0.82	6 0.63	8 0.56	7 0.89	9 0.95	1.15	4 0.92	2 0.93	2 1.50	3 1.01	5 0.58	06'0 0	3 0.64	2 0.90	7 0.54	_	0 1.53			_	_	_	0.81		0.76						1 -	96.0 6	8 0.74	1 0.57
	1.2772				1.4537	1.4499	` '	1.5250	1.5808	1.5376	1.5916		2.3217	1.5909	1.5436		1.5952	1.3232	1.4523	1.4895	1.5050	1.6143	1.3682							`				1.5505		١,				1.	1.5409		1.5101
SR	304.0	158.2	219.5	0.0	0.0	2'667	0.0	320.2	282.7	283.1	174.2	206.7	152.3	214.8	212.2	794.1	173.4	240.4	343.2	210.2	157.8	240.1	295.2	239.4			247.4	280.0	260.0	329.2			7000	390.7	2.012			405.6	306.4	302.9	267.8		205.9
SC	6.18	8.39	7.50	5.50	6.45	9.71	5.90	11.53	11.11	9.58	7.65	7.16	4.97	8.01	8.06	11.36	6.24	10.14	12.24	6.67	7.18	6.67	11.27	6.42	5.17	9.25	5.72	6.22	7.65	9.28	7.83	8.30	0.13	8.3U	0.23	8.02	7 63	0.07	11.90	9.49	9.26	9.78	6.94
SB	0.5215	0.5984	0.7053	0.5302	0.5093	0.4182	0.4599	0.4812	0.4239	0.3774	0.5430	0.5938	0.7588	0.8402	1.3889	0.3672	0.5612	0.3531	0.4472	0.3660	0.3853	0.3460	0.3798	0.3730	0.5559	0.6303	0.3913	0.3160	0.3387	0.2928	0.2994	0.3836	C108.0	0.3427	0.3013	0.0947	0.1787	0.3207	0.4520	0.3729	0.3469	0.4684	0.3520
RB	139.30	145.40	191.50	195.80	175.40	150.50	256.00	145.70	149.30	158.40	172.70	200.50	196.70	164.90	167.10	145.30	177.80	131.60	142.10	171.10	180.80	165.70	139.80	175.90	202.60	120.30	157.87	138.94	135.73	130.27	122.36	145.62	1340.17	162 40	125 42	161 10	155 22	117.57	126.93	120.92	116.84	117.08	178.61
Z	0.0	0.0		0.0		0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	40.7	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0				24.1			20.6			37.7					0.0	19.7	13.0	28.1	0.0
Ή	7.71	7.02	7.70	8.15	7.40	9.05	9.95	7.78	8.87	7.70	6.73	8.39	7.85	6.12	7.07	7.85	7.06	6.34	6.92	7.95	6.17	5.57				7.86	2.67	7.82	6.45	7.27	6.44	11.05	13.79	17.6							7.16		9.47
H	20881.4	26924.8	27682.2	18134.5	23236.3	24348.8	15228.0	26085.3	25904.9	22832.1	25165.2		12402.3	24151.6	23839.6		18981.2	34271.4	28462.6	23458.1	22124.9	16768.8				24672.2				22041.5	28416.2			31808.3						26400.6	40085.3		28542.0
EU	1.1010		0.9979	0.6164	0.7461	1.2406	0.7630	1.1964	1.1768	1.0277	0.9097	0.8994	1.0262	1.3109	1.3351		1.2129	1.9030	1.4371	4.28 0.9352	1.1144	16.72 0.6262	1.3443	0.6385	12.66 0.6330	3.03 2.3017					1.2611			0.0430	1 400E			1 9246	1.4267	1.3281	1.3167	1.7854	0.9193
CS	8.21				7.01	18.63	5.11	22.45	15.95	17.09	9.76	7.16	19.48	7.94	6.14	15.59	7.01	6.12	16.93	4.28	5.74	16.72	14.96	20.01	12.66	3.03	16.30	4.06	4.83	14.05	3.12	4.50	3.22		14.07			3.87	4.79	5.32	4.47	5.91	5.30
ANID	SWR173	SWR174	SWR175	SWR176	SWR177	SWR179	SWR180	SWR181	SWR182	SWR183	SWR184	SWR185	SWR187	SWR188	SWR189	SWR190	SWR191	SWR192	SWR193	SWR194	SWR195	SWR196	SWR197	SWR198	SWR199	SWR200	SWR201	SWR202	SWR203	SWR204	SWR210	SWKZII	SWKZ12	SWK213	SWK214	SWRZ13	SWD217	SWR217	SWR219	SWR220	SWR221	SWR222	SWR223

ANID	macro_grp Chem2012	Chem2012	CERAMIC TYPE	MATERIAL	SOURCE	STATE	SITE_NAME	SITE_NO	AS	LA	Π	QN	SM	n	YBC	CE CO	CR
Ğ	Group-B2 N	Mimbres-02A	Mimbres Polychrome	Pottery	TAM	MN	NAN	LA 002465	1.52	40.28	0.3920	38.01	6 00.9	9.60	.72 69.15	5 5.53	36.79
Ğ	Group-B1 N	Mimbres-04B	Mimbres Polychrome	Pottery	TAM	MN	NAN	LA 002465	1.80	54.15	0.4013	51.54	7.92	4.87 4.	4.45 89.02	2 5.09	28.1
Ğ	Group-B1	Mimbres-04B	Mimbres Polychrome	Pottery	TAM	MN	NAN	LA 002465	1.69	59.94	0.5133	90.50	8.21	8.87 3.	3.71 103.01	1 8.56	27.36
Ğ	Group-B1 N	Mimbres-04B	Mimbres Polychrome	Pottery	TAM	MN	NAN	LA 002465	1.90	61.70	0.5040	20.65	8.30 10	10.74 4.	4.42 99.21	1 6.82	27.89
	Group-B2	Mimbres-02A	Mimbres Polychrome	Pottery	TAM	MN	NAN	LA 002465	1.71	_	0.3267		2.00	8.17 3.	3.60 69.57		37.7
TAM006 Gr		Mimbres-02A	Mimbres Polychrome	Pottery	TAM	MN	NAN	LA 002465	0.00		0.3640			6.77 2.	2.95 57.79		
Ō		Mimbres-04A	Mimbres Polychrome	Pottery	TAM	M	NAN	LA 002465	1.64	42.55	0.4107	41.16	6.38	6.02 3.	3.07 87.33	3 4.59	25.67
		Mimbres-11	Mimbres Polychrome	Pottery	TAM	M	NAN	LA 002465	3.05		0.3733		_			3 14.46	
		Mimbres-02A	Mimbres Polychrome	Pottery	TAM	NM	NAN	LA 002465	1.92		0.4947			5.01 3.	3.38 70.79		
	Group-B2	Mimbres-02A	Mimbres Polychrome	Pottery	TAM	MN	NAN	LA 002465	2.54	39.70	0.4480		5.95	5.71 3.	3.96 62.83		
FAM011 Gr	Group-D E	El Paso Core	El Paso Polychrome	Pottery	TAM	MN	NAN	LA 002465	5.46	80.75	0.4947	67.95	10.57	5.32 4.	4.52 147.25	5 4.54	26.88
TAM012 Gr	Group-D E	El Paso Core	El Paso Polychrome	Pottery	TAM	MN	NAN	LA 002465	7.18	90.55	0.4107	54.87	7.95	2.26 3.	3.91 98.52		27.53
-AM013 Gr	Group-D E	El Paso Core	El Paso Polychrome	Pottery	TAM	M	NAN	LA 002465	3.36	59.05	0.3733	54.94	8.87	4.77 3.	3.26 106.03	3 5.94	23.30
FAM014 Gr	Group-D E	El Paso Core	El Paso Polychrome	Pottery	TAM	M	NAN	LA 002465	3.66	63.46	0.4387	62.53	9.47	2.37 3.	3.80 144.91	1 9.68	27.03
AM015 Gr	Group-D E	El Paso Core	El Paso Polychrome	Pottery	TAM	MN	NAN	LA 002465	5.20	55.91	0.4573	63.99	9.01	4.06 4.	4.05 107.88	8 4.78	24.57
FAM016 Gr	Group-D E	El Paso Core	El Paso Polychrome	Pottery	TAM	MN	NAN	LA 002465	4.80		0.4107	69.89	9.81	2.06 4.	4.01 118.92	2 4.80	28.86
FAM017 Gr	Group-D E	El Paso Core	El Paso Polychrome	Pottery	TAM	MN	NAN	LA 002465	6.97	75.45	0.5693	94.77 1	11.07	5.92 4.	4.36 145.26	11.95	20.98
FAM018 Gr	Group-D E	El Paso Core	El Paso Polychrome	Pottery	TAM	MN	NAN	LA 002465	2.97	44.06	0.3640	41.77	5.81 4	4.27 2.	2.79 75.15	5 7.86	30.96
-AM019 Gr	Group-D E	El Paso Core	El Paso Polychrome	Pottery	TAM	M	NAN	LA 002465	6.23	70.15	0.4853	70.03	10.03 E	5.07 3.	3.99 120.43	3 9.69	18.62
		El Paso Core	El Paso Polychrome	Pottery	TAM	NM	NAN	LA 002465	5.73		0.4107	54.83					
TAM022 Gr	Group-C2a 🛚 🗈	Mimbres-49A	Smudged	Pottery	TAM	MN	NAN	LA 002465	2.21	33.65	0.3733	44.01	5.59	2.21 3.	3.02 77.58	8 19.53	53.47
FAM023 Gr		Mimbres-49A	Smudged	Pottery	TAM	MN	NAN	LA 002465	2.41		0.4387	48.37	7.41	3.74 3.	3.31 102.96	6 9.97	58.7
TAM024 Gr	Group-C2a N	Mimbres-49A	Smudged	Pottery	TAM	M	NAN	LA 002465	3.76	42.59	0.3640	46.68	7.23	3.78 2.	2.23 86.01	13.60	
	<u>2</u> a	Mimbres-49A	Smudged	Pottery	TAM	NM	NAN	LA 002465	2.33		0.3733		6.56			_	
TAM026 Gr	Group-B	Unas.	Smudged	Pottery	TAM	NM	NAN	LA 002465	6.01	46.38	0.4200	52.54	6.17	2.24 3.	3.49 85.63	3 6.30	39.64
		Mimbres-41	Reserve smudged	Pottery	TAM	MN	NAN	LA 002465	0.00		0.3080						25.36
	В	Mimbres-49A	Smudged	Pottery	TAM	M	NAN	LA 002465	1.92		0.2893						78.70
		Mimbres-05A	Corrugated	Pottery	TAM	MN	West Fork	LA 008675	3.92		0.6067						58.40
		Mimbres-05B	Corrugated	Pottery	TAM	M	West Fork	LA 008675	5.56	78.14	1.1107				9.13 132.14	4 11.47	45.87
		Mimbres-05B	Corrugated	Pottery	TAM	Σ	West Fork	LA 008675	3.82	_	0.6720	- 1					
		Mimbres-05B	Corrugated	Pottery	TAM	N S	West Fork	LA 008675	2.96	-+	0.7000				_		
		Mimbres-05B	Corrugated	Pottery	IAM		West Fork	LA 008675	4.44			_					
		Mimbres-05B	Corrugated	Pottery	TAM	Σ	West Fork	LA 008675	3.11	_	_				_		
		Mimbres-05B	Corrugated	Pottery	TAM	M	West Fork	LA 008675	4.66		0.8867				_		45.96
	Group-B1 N	Mimbres-05B	Corrugated	Pottery	TAM	M	West Fork	LA 008675	1.90	52.17	0.6627	20.98	9.88	5.44 5.	5.98 94.84	4 11.72	36.83
TAM042 Gr	Group-B1 N	Mimbres-05B	Corrugated	Pottery	TAM	Σ	West Fork	LA 008675	5.35	66.31	0.9147	68.10	15.42	3.66 8.	8.02 96.06		36.2
		Unas.	Incised corrugated	Pottery	TAM	NM	West Fork	LA 008675	2.97	44.24	0.5600		9.17			2 9.50	51.13
	Group-B1 N	Mimbres-05B	Incised corrugated	Pottery	TAM	NM	West Fork	LA 008675	5.08		0.9053	70.37	14.76	2.85 7.	7.88 96.15	5 7.14	41.33
	Group-B1 N	Mimbres-05A	Smudged	Pottery	TAM	NM	West Fork	LA 008675	4.29		0.6440		11.47	2.47 6.	6.08 119.81	-	
		Mimbres-05B	Smudged corrugated	Pottery	TAM	NM	West Fork	LA 008675	5.00	49.72	0.8027	49.67	10.08	4.58 6.	6.21 102.46	6 7.84	
FAM051 Gr	Group-B1 N	Mimbres-05B	Smudged	Pottery	TAM	NM	West Fork	LA 008675	5.28	54.92	0.7747	60.27	12.55	3.71 7.	7.26 106.33	3 7.48	44.30
	1	Mimbres-05B	Smudged	Pottery	TAM	NM	West Fork	LA 008675	5.45		0.8213		12.72	- 1			
		Unas.		Pottery	TAM	MN	West Fork	LA 008675	4.04	41.94	0.4947		7 29			8.34	52.1
TAM054 Gr	Group-B1 N	Mimbres-05B	Smudged	Pottery	TAM	M	West Fork	LA 008675	2.97	40.17	0.6720	38.55	7.35	3.59 4.	4.87 84.86	6 6.64	32.04
	1		П	•				=		1			l		1	1	

>	54.22	47.35	47.06	46.27	53.33	47.16	61.08	61.96	48.82	90.09	91.37	81.67	101.67	90.10	66.47	82.88	121.96	109.61	127.25	82.88	131.57	86.18	89.90	89.31	66.27	69.12	102.16	64.02	67.94	42.55	55.59	67.25	58.14	63.63	59.71	49.22	54.71	50.39	72.55	49.22	57.45	57.06	75.98	42.75
I	3377.7	2611.1	2195.6	2522.0	2867.0	3336.6	3430.1	4061.3	3445.6	3252.9	5367.6	4285.7	5929.3	5372.6	4421.0	8.1899	. 8.7799	5362.1	6186.1	5944.8	6313.2	4476.7	4608.6	4561.5	3662.4		4813.9	5147.1	4124.3	3050.5	4126.3	3511.1	3426.8	4042.5	3971.9	2890.4	3531.3	3033.3	4601.6	3829.7	3579.2	2745.0	4459.7	2895.1
NA	12384.1	10653.9	11517.1	11410.4	12666.0	11057.4	15137.5	10837.5	12254.5	10730.5	17026.9	11586.6	18060.6	17086.5	17454.0	17249.8	14009.4	17513.4	13125.8	14530.2	15006.6	14007.6	16870.7	13911.0	9894.7	16037.1	15144.2	9813.2	12481.1	8341.6	8515.1	11423.5	10912.9	12243.4	12277.9	11585.7	9423.9	12223.4	11044.3	13332.8	11443.9	9489.1	11912.4	13152.4
MN		384.5	675.2	590.7	236.2	178.0	120.9	1328.9	299.9	193.3	615.2	436.6	595.8	561.7	503.0	712.8	431.4	443.3	423.2	400.4	1105.9	262.2	622.0	718.2	384.3	417.0	0.089	7.677	727.5	599.4	631.0	575.4	465.9	459.4	915.8	421.8	588.4	526.5	619.7	568.1	544.9	546.4	386.5	566.1
¥	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
Dγ	4.960	6.346	6.250	5.448	3.852	3.288	4.836	3.383	4.224	4.941	6.881	5.581	5.591	7.044	6.126	6.499	7.044	3.584	6.747	5.381	3.995	4.779	3.909	4.186	5.046	3.460	3.316	7.933	13.829	8.946	9.940	10.169	10.159	13.782	8.659	11.899	7.025	13.982	10.532	9.175	10.331	10.790	4.798	7.120
CA	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0				0.0	0.0	0.0		0.0	0.0	0.0	0.0	0.0	0.0	0.0
BA	563.2	601.3	772.2	718.9	544.8	480.5	6.998	519.3	549.3	573.2	939.8	907.2	1075.0	978.2	1043.9	1007.5	928.6	613.2	895.7	961.9	1084.4	9.106	936.2	1176.2	8.078	0.076	859.5	651.0	525.7	629.8	229.0	452.6	503.9	402.4	591.0	441.7	603.5	448.4	684.9	455.7	382.7	463.6	600.4	484.0
AL	81286.8	86451.2	86568.0	86771.9	83137.4	83893.5	91892.0	80822.2	81457.5	88521.0	92408.8	7.77606	88045.9	88628.7	86672.0	93251.5	94734.4	92822.8	93025.2	90650.3	81100.4	97193.2	90327.2	82765.1	103319.0	81709.1	81687.2	74763.3	79842.0	68459.3	76878.8	77671.8	82939.0	81783.2	79663.5	81067.1	74595.2	76750.2	72960.9	76378.9	84612.8	82261.1	85136.1	71358.7
ZR	272.2	216.3				288.6	316.6	210.7	246.3	227.0	458.9	301.0	324.0	349.2	303.1	363.8	406.1	298.7	324.6	273.9	182.5	213.2	173.2	206.0			197.7				176.7	161.2						198.8	219.8		221.7		252.9	241.6
NZ	49.8	61.8	58.0	58.1	54.3	26.8	65.3	63.4	50.9	53.7	73.2	74.8	66.5	71.1	70.5	78.6	0.96	58.9	64.6	64.4	72.4	71.4	82.8	70.0	79.0	71.6	88.0	122.5	115.1	59.3	61.1	65.2	82.1	67.2	57.6	80.1	57.0	54.3	74.8	77.1	82.0	117.0	82.9	64.5
H	19.63	25.67	25.45			20.97		16.92	19.86	21.86		21.30	16.31	21.01	23.54	19.71	27.90	23.11	21.76	20.56	13.06	13.36	11.65		$\overline{}$		12.12											20.54	18.28	20.33	23.83		20.67	19.62
TA TB	00 0.95	00 1.15	00 1.11	00 1.09		00 0.57	00 0.97	00 0.65	99.0 00	00 0.85		00 1.00	00 1.09	00 1.32	00 1.17	00 1.36	00 1.55	00 0.67	00 1.16	1.01	00 0.70	00 0.91	98.0 00	00 0.80			00 0.55			00 1.82						00 2.22	00 1.36	00 2.46	00 1.82	00 1.42	00 1.75			00 1.22
SR	0.0 1.5100	0.0 1.5300	0.0 1.6700		0.0 1.7300	0.0 1.6800	0.0 1.3000	0.0 1.4900	0.0 1.4700	0.0 1.4700	0.0 3.3700	0.0 2.5300	0.0 2.6700	0.0 2.7800	0.0 2.5000	0.0 3.3800	0.0 3.1500	0.0 2.6700	0.0 2.5100	0.0 2.5600	0.0 1.1400	0.0 1.0900	0.0 1.1000	0.0 1.0200		0.0 0.9000	0.0 1.0700										0.0 1.5500	0.0 1.7500	0.0 1.9100	0.0 1.7200	0.0 1.8700			0.0 1.7200
s sc																																												
SB S	64 9.54	25 7.70			1		89 7.85	33 7.66	35 8.78	08 11.11	23 10.23	15 9.60	16 8.48	64 10.03	49 8.83	47 10.34	68 12.13	79 9.74	64 10.97	64 9.07	99 11.98	84 11.76	64 11.84	69 10.95	48 9.92	75 7.66	1		05 10.33					_		_		17 9.99	61 10.13	76 8.81	44 10.91		_	35 7.59
8		0.3925				0.5632		0.8533	0.5035				0.2816	0.4864		0.5547	0.7168	0.4779	0.4864	0.4864	0.3499	0.3584	0.4864				0.3157											0.5717	0.5461	0.5376				0.5035
RB	145.00	148.00				160.70	131.50	173.60	153.90	146.40	87.30	126.80	114.00	112.10	128.50	95.30	82.80		77.00	133.20	125.10	94.60	95.00	95.70	_		95.70											132.30	155.50		148.40			141.50
N	9.0	5 0.0				2 0.0	3 0.0	3 0.0	0.0	0.0		1 0.0	5 0.0	5 0.0	0.0	0.0	3 0.0	0.0	0.0	5 0.0	0.0	0.0	3 0.0	3 0.0		5 0.0	5 0.0											3 0.0	0.0	3 0.0	9 0.0			3 0.0
H	0.7 0	7 5.55		2	7	0 8.52		4 6.38	8.10	1 7.56	2 13.96	3 10.54	5 11.25	7 10.95	5 10.99	3 12.10	13.23	0 10.69	79.6 C	0 10.75	3 7.77	5 8.31	7.23	5 8.33	4 8.15		3 8.95		_									9 7.83	3 9.37	5 9.43	7 8.89	3 7.58		8.18
FE	21713.0	22806.7				19131.0	24608.5	23671.4	22484.6	24806.1	45947.2	42682.8	44113.5	44274.7	38179.5	48037.3	56071.0	48665.0	51366.0	40592.0	45507.8	38139.6	38273.0	35987.5		28599.5	42737.8	34409.5	31790.5	22617.6	28484.5	27549.8	28481.7					28056.9		25713.5	29706.7			22389.6
ED	1.2021	1.4108	1.4505	1.4406	0.9438	0.7153	1.2816	0.9041	0.9339	1.1326	2.4043	1.5896	2.1162	1.9671	1.8181	2.3049	2.3944	1.2220	2.2354	1.6194	1.3412	1.5697	1.5797	1.5896	1.1425	1.2717	1.3412	1.5499	2.3149	1.2220	1.4207	1.6492	1.7982	2.0367	1.4505			1.7784	1.3909	1.3313	1.5300	1.6691	1.1326	4.69 0.9538
CS	20.72	5.52				17.33		7.80	18.30	23.32	3.92	4.23	2.49	3.58	3.83		2.59	3.85	2.30	3.89		3.53	4.23	2.91			2.50									96.9		6.25	4.31	6.50	9.95		2.68	4.69
ANID	TAM001	TAM002	TAM003	TAM004	TAM005	TAM006	TAM007	TAM008	TAM009	TAM010	TAM011	TAM012	TAM013	TAM014	TAM015	TAM016	TAM017	TAM018	TAM019	TAM020	TAM022	TAM023	TAM024	TAM025	TAM026	TAM028	TAM029	TAM031	TAM032	TAM033	TAM034	TAM035	TAM037	TAM038	TAM040	TAM042	TAM044	TAM045	TAM047	TAM049	TAM051	TAM052	TAM053	TAM054

ANID	macro_grp	macro_grp Chem2012	CERAMIC TYPE	MATERIAL	SOURCE	E STATE	SITE_NAME	SITE_NO	AS	ΓA	ΓΩ	S QN	SM	U YB	3 CE	00	CR
TAM055	Group-B1	Mimbres-05B	Smudged	Pottery	TAM	ΣN	West Fork	LA 008675	4.28	44.56 0.7	0.7280 4.		9.06 3.17	7 5.47		7.14	38.82
TAM056	Group-A	Mimbres-03	Mimbres B/W Style III	Pottery	TAM	ΣN	West Fork	LA 008675	2.49		1.0827 4.	43.70 10.75	75 6.00	80.8		2.46	15.49
TAM057	Group-C1	Mimbres-21	Mimbres B/W Style III	Pottery	TAM	MN	West Fork	LA 008675	3.55	39.76 0.2	0.2893 3	39.28 5.	5.52 1.29	9 2.16	81.50	10.27	31.29
TAM058	Group-B1	Mimbres-09	Mimbres B/W Style I	Pottery	TAM	MN	West Fork	LA 008675	3.14	54.45 0.5	0.5040 4	48.77 9.	9.56 2.29	3.66	5 100.44	4.16	19.16
TAM059	Group-A	Mimbres-03	Mimbres B/W Style II	Pottery	TAM	ΣN	West Fork	LA 008675			1.0920 4	47.50 9.17	17 4.46	8.20	86.27	3.06	20.07
TAM060	Group-A	Mimbres-03	Mimbres B/W Style I	Pottery	TAM	NN	West Fork	LA 008675				33.78 7			3 70.05	2.61	16.53
TAM061	Group-B	Unas.	Mimbres B/W Style III	Pottery	TAM	ΣN	West Fork	LA 008675	4.24	92.27 1.3	1.3067 8	81.90 18.56	56 11.20	0 8.96	5 144.25	10.78	49.29
TAM062	Group-B1	Mimbres-05A	Mimbres B/W Style II	Pottery	TAM	NM	West Fork	LA 008675	2.02	47.85 0.5	0.5507 3	39.24 8	8.22 4.98	4.04	1 85.64	89.9	53.12
TAM063	Group-A	Mimbres-03	Mimbres B/W Style II	Pottery	TAM	NM	West Fork	LA 008675		41.88 1.0		47.96 10.14	14 4.25	5 7.55		2.37	12.67
TAM064	Group-A	Mimbres-03	Mimbres B/W Style II	Pottery	TAM	MN	West Fork	LA 008675		37.16 1.1	1.1573 3	36.46 8.	8.93 3.73			2.02	15.34
TAM065	Group-C1	Mimbres-24	Mimbres B/W Style II	Pottery	TAM	MN	West Fork	LA 008675	3.84	36.60 0.4	0.4013 4	46.48 6.	6.83 1.18	8 3.29	75.99	14.10	32.94
TAM066	Group-A	Mimbres-03	Mimbres B/W Style I	Pottery	TAM	MN	West Fork	LA 008675	2.42	44.75 1.5	1.5307 4	49.07 12.42	42 5.40	12.67	98.64	2.26	14.59
TAM067	Group-C1	Mimbres-21	Mimbres B/W Style III	Pottery	TAM	Z	West Fork	LA 008675		38.15 0.3	0.3827 3		6.46 2.02			10.10	45.20
TAM068	Group-C1	Mimbres-22	Mimbres B/W Style III	Pottery	TAM	NM	West Fork	LA 008675			0.2520 2	29.87 4.8	4.88 1.30	1.96			13.04
TAM069	Group-C1	Mimbres-24	Mimbres B/W Style III	Pottery	TAM	NM	West Fork	LA 008675		39.99 0.4	0.4573 3	36.76 7	7.35 1.80	3.60	74.39	12.93	33.96
TAM070	Group-B2	Mimbres-02A*		Pottery	TAM	NM	West Fork	LA 008675		49.14 0.4	0.4013 5		6.65 2.23	3 3.19	96.02	9.57	39.03
TAM071	Group-B1	Mimbres-05A	Mimbres B/W Style II	Pottery	TAM	NM	West Fork	LA 008675					9.07 3.34	4.67	_		51.19
TAM072	Group-C1	Mimbres-21	Mimbres B/W Style II	Pottery	TAM	MN	West Fork	LA 008675	0.00	37.87 0.3	0.3080 4.	42.72 5.	5.75 1.02	12 2.7	19.88	10.21	44.38
TAM073	Group-B1	Mimbres-05A	Mimbres B/W Style I	Pottery	TAM	MN	West Fork	LA 008675	5.49	49.06 0.5	0.5227 6	64.75 10.28	28 2.59	4.56	100.79	10.93	64.38
TAM074	Group-A	Mimbres-03	Mimbres B/W Style I	Pottery	TAM	Z	West Fork	LA 008675		40.00 0.9	0.9613 5	57.84 9.	9.96 4.86	1.70	80.54	2.20	13.04
TAM075	Group-B	Unas.	Mimbres B/W Style I	Pottery	TAM	MN	West Fork	LA 008675	4.88	40.08 0.5	0.5133 6	66.31 7.	7.89 3.08	18 4.31	78.47	9.19	55.45
TAM076	Group-A	Mimbres-03	Whiteware	Pottery	TAM	MN	West Fork	LA 008675	1.79	39.97 1.0	1.0920 5	51.20 9.	9.45 5.48	90.8	92.86	2.91	12.06
TAM077	Group-A	Mimbres-03	Whiteware	Pottery	TAM	MN	West Fork	LA 008675	3.18	39.28 1.1	1.1573 6	68.40 10.49	49 4.42		7 90.37		14.62
TAM078	Group-A	Mimbres-03	Whiteware	Pottery	TAM	ΣN	West Fork	LA 008675	2.73		1.6427 5	58.89 15.50	50 8.44	1	_		14.11
TAM079	Group-A	Mimbres-03	Whiteware	Pottery	TAM	NM	West Fork	LA 008675	2.15	33.97 1.1	1.1387 3	36.08 10.14	14 4.93	3 9.50		1.87	10.23
TAM080	Group-A	Mimbres-03	Whiteware	Pottery	TAM	NM	West Fork	LA 008675		40.98 1.2		41.85 9.		1			6.97
TAM081	Group-A	Mimbres-03	Whiteware	Pottery	TAM	NM	West Fork	LA 008675			1.1853 5			0.29		2.52	11.50
TAM082	Group-A	Mimbres-03	Whiteware	Pottery	TAM	NM	West Fork	LA 008675				54.81 14.32		`	ļ	2.49	13.25
TAM083	Group-A	Mimbres-03	Whiteware	Pottery	TAM	NM	West Fork	LA 008675	2.46	42.88 1.2	1.2320 3	39.22 10.95	95 6.52		3 96.46	3.13	19.88
TAM084	Group-A	Mimbres-03	Whiteware	Pottery	TAM	ΣN	West Fork	LA 008675	1.38		1.0453 3	38.17 9.	9.12 6.08	7.97			14.56
TAM085	Group-A	Mimbres-03	Whiteware	Pottery	TAM	MN	West Fork	LA 008675						_			14.76
TAM086	Group-A	Mimbres-03	Whiteware	Pottery	TAM	M	West Fork	LA 008675									14.40
TAM087	Group-A	Mimbres-03	Whiteware	Pottery	TAM	MN	West Fork	LA 008675			_		81 4.98	10.63		2.34	12.57
TAM088	Group-A	Mimbres-03	Whiteware	Pottery	TAM	NM	West Fork	LA 008675	1.77	54.13 1.2	1.2227 5	58.33 13.86	86 4.49	69.6	111.58	3.18	13.21
TAM089	Group-A	Mimbres-03	Whiteware	Pottery	TAM	NM	West Fork	LA 008675	1.86	44.06 1.3	1.3627 6	60.49 12.30	30 5.81	11.70	105.84	2.97	15.55
TAM091	Group-D	Loop 375	El Paso Polychrome	Pottery	TAM	ΤX	Ojasen	41EP00289	9.04	78.87 1.3		75.13 14.78	`	3 11.51	126.49		40.38
TAM092	Gronp-D	El Paso Core	El Paso Polychrome	Pottery	TAM	XX	Ojasen	41EP00289				66.81 11.50	50 1.95	5 4.30	124.47	5.93	33.34
TAM094	Group-D	El Paso Core	El Paso Polychrome	Pottery	TAM	X	Ojasen	41EP00289	8.85			72.12 11.67	67 2.08	18 4.43	140.67	5.72	32.97
TAM095	Group-D	El Paso Core	El Paso Polychrome	Pottery	TAM	ĭ	Ojasen	41EP00289	6.24	57.31 0.5		50.79 8.	8.62 2.44	3.87	7 115.35	6.55	32.21
TAM097	Gronp-D	El Paso Core	El Paso Polychrome	Pottery	TAM	XX	Ojasen	41EP00289	7.00	69.41 0.5		68.83 11.50	50 1.93	3 4.38	143.06	8.51	36.30
TAM098	Group-D	El Paso Core		Pottery	TAM	X	Ojasen	41EP00289	8.32	58.80 0.5	0.5600 5	59.57 9.	9.63 2.48	3.62	2 118.40	7.79	38.46
TAM099	Group-D	El Paso Core		Pottery	TAM	×	Ojasen	41EP00289									34.39
TAM102	Group-D	El Paso Core		Pottery	TAM	ĭ	Ojasen	41EP00289				53.77 9.	9.10 2.11				27.22
TAM103	Group-D	El Paso Core	Jornada Bichrome	Pottery	TAM	×	Ojasen	41EP00289	7.00	80.99 0.7	0.7280 8	86.19 14.70	70 2.73	'3 6.04	180.75	8.31	35.22

>	50.39	21.47	80.78	45.29	29.90	36.57	59.41	87.75	24.22	28.04	88.43	21.37	63.33	38.33	88.06	67.45	103.92	63.53	109.02	19.31	77.94	25.10	14.61	21.76	23.73	16.37	16.37	13.92	24.31	16.47	24.51	23.63	24.02	14.61	15.88	76.37	79.71	81.27	60.10	85.29	79.22	79.90	72.45	90.29
I	3570.3	2002.8	2557.8	2810.4	1570.5	1624.5	3993.3	4094.3	1598.2	1684.5	4053.0	1442.4	3640.1	1147.9	4173.5			3257.5	2376.5	1009.8	4406.5	1982.0	1065.2	1614.9	1806.1	1658.3	1430.9	1712.0	2253.1	1254.2	1496.6	728.7	1631.2	1092.8	1297.7	2935.0	6129.2	5163.6	3638.6	5907.0	4451.4	4217.4	5691.0	5728.1
NA	12682.1	4914.4	18186.1	16408.9	5716.5	7007.3	15354.6	13928.1	5321.3	6913.5	18098.9	5032.4	14275.2	12835.4	17435.1	16360.8	16405.2	18214.4	14004.2	6541.2	14848.8	4441.3	5146.5	4548.1	5439.9	5193.1	4439.0	4612.2	7605.5	5498.8	4498.8	10358.9	5935.3	4931.9	9.8989	9476.9	13747.8	15903.5	12384.3	14115.2	11152.7	11781.5	15871.0	15184.5
M	9.2/9	544.2	6.998	518.2	495.9	534.3	676.3	299.1	586.2	502.4	682.5	548.6	882.4	1053.1	753.2	588.8	224.0	8.896	470.6	523.5	432.5	667.4	537.2	683.5	646.2	757.1	575.5	690.7	556.9	520.8	521.1	593.3	592.1	426.1	508.0	221.0	508.8	582.8	417.2	573.1	396.1	412.1	535.1	717.1
¥	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
DY	7.340	10.790	2.953	6.728	10.475	8.487	16.601	6.633	11.650	12.367	5.868	17.079	4.798	2.819	4.865	4.626	7.598	3.183	6.575	10.427	2.868	10.188	11.497	18.360	12.625	11.736	12.931	14.422	12.979	10.914	12.855	13.332	14.871	13.170	15.311	13.610	7.780	7.617	5.572	9.000	2.668	6.833	908.9	8.640
CA	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0			0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
BA	530.5	146.0	872.4	1023.7	167.2	293.3	564.4	627.4	260.5	155.5	7.007	136.7	822.8	874.9	788.0	1107.1	731.5	974.4	692.6	203.0	689.4	233.6	203.1	311.2	127.5	248.6	167.9	228.0	219.8	156.0	133.3	228.5	143.1	161.3	201.3	1354.6	1927.4	1572.9	1705.7	1773.4	1385.5	1974.3	1501.4	1308.9
AL	74462.1	85311.4	92637.1	85279.4	81705.3	82193.4	82736.3	86194.2	77419.6	85237.1	98037.0	79471.9	85057.0	95066.5	93370.1	87154.4	86113.8	87662.6	87848.6	82084.8	85150.0	7.8887.7	79330.9	87189.4	74492.5	78593.6	75308.8	80284.2	81045.4	71351.6	82200.5	77108.1	73722.7	74923.6	72561.4	75847.2	83704.0	94003.5	79350.5	86885.7	90228.6	83909.9	88460.7	82623.8
ZR	200.2	191.9	183.0					177.6	171.3	162.7	169.0	165.3	243.1	118.0	190.6			157.0	205.8	199.2	268.5		213.0		245.0		203.9				167.4							673.2						662.6
NZ	68.4	71.1	9.78	102.1	89.4	9:59	77.6	56.7	88.2	73.4	114.9	97.1	9.78	93.2	107.6	83.2	53.1	93.5	83.2	89.4	87.5	0.09	91.8	121.3	71.7	241.8	64.7	166.5	152.1	147.5	2.09	115.7	55.0	6.68	73.3			89.0	73.4	90.2	79.6			75.6
3 IH	2 19.82	7 37.88	7 9.33	14.51		38.00	3 24.17	3 16.23	37.95	5 35.50	5 9.37	1 35.79	3 12.39	5 9.18	5 10.69	3 14.31	_		15.62	36.41	5 14.71	39.86	7 36.05	9 40.98		1 36.35	37.17											3 18.40	24.47				2 15.13	3 17.17
TA TE	1.52	300 1.7	100 0.67	700 1.2	1.89	500 1.29	900 2.98	00.98	700 1.89	200 1.66		000 2.54	00.88	500 0.55	1.0500 0.95	700 0.83	1.29	100 0.69	500 1.34	300 1.83	1.16	1.70	500 2.07	000 2.99	t00 2.09		300 2.12	000 2.49	2.14							200 2.24		500 1.58	700 1.22	,	200 1.13			500 1.78
SR	0.0 1.6400	0.0 2.0300	0.0 0.6100	0.0 0.9700	0.0 2.1000	0.0 1.8600	0.0 1.8900	0.0 1.1700	0.0 2.1700	0.0 2.0200	0.00 0.9000	0.0 2.1000	0.0 1.1700	0.0 0.5600	0.0 1.05	0.0 0.9700		0.0 0.7400	0.0 1.2500	0.0 2.1800	0.0 1.3100	0.0 2.3000	0.0 2.2500	0.0 2.5000		0.0 2.4500	0.0 2.1800										0.0 3.1600	0.0 3.7600	0.0 2.9700	0.0 3.0900	0.0 2.5900			0.0 3.6500
SC	8.48	9.02	7.16 (9.20			8.47		5.72	5.88	10.83	5.85		4.52 (10.82	00.6	13.05		11.84 (5.59	11.42	5.39	5.93	9.05	4.61		4.99	4.81	6.47							10.43	11.49	10.12						9.42
SB	0.4864 8	0.4437 6	1.8859 7				0.6741 8	0.5461 12		0.2901 5	_		2.0053 7	2.4747 4	~		٠ ا		0.7595 11		0.6400 11	0.4437 5	0.2645 5				0.4352 4			_								0.6741 10		_		_		0.6400 9
RB							154.40 0.0										122.30 0.8																											93.80 0.6
Z	0.0 139.90	0.0 258.30	0.0 128.30	0.0 129.80		0.0 238.70	0.0 154	0.0 126.90	0.0 271.70	0.0 246.90	0.0 112.10	0.0 266.20	0.0 153.00	0.0 137.40	0.0 115.60	0.0 126.20		0.0 112.60	0.0 134.30	0.0 271.90	0.0 142.00	0.0 242.70	0.0 276.20	0.0 225.50	0.0 271.20	0.0 263.60	0.0 221.40											0.0 100.30	0.0 134.40	0.0 126.00				0.0
生	8.19	8.62	00.9			8.05	10.85	88.9	61.6	8.99	6.58	8.50	9.27	5.55	6.62	8.31		6.31	7.93	9.46	8.67	10.00	10.16	11.02		10.09	9.33											19.64						23.36
FE	25291.3	14855.8	33000.9	24919.3	17720.2	16278.7	30201.7	23634.7	14502.1	14611.4	37597.7	14779.4	29461.1	18546.6	38856.5		20916.6	30431.0	40649.8	14216.5	38090.7	13956.2	14798.4	16218.3	12108.2		12530.3											46104.3 1			46321.9 1.			45254.8 2
EU	1.1922 2	0.5464 1	1.3611 3	2.0069 2					0.6060 1	0.4570 1	1.7088 3		1.4008 2	1.2518 1	1.4704 3				1.6194 4	0.5266 1	1.4505 3		0.5464 1				0.7551 1											2.5235 4						2.9408 4
CS	6.39	5.64 0	19.94	4.31				6.71	5.21 0	5.38 0	23.40	5.56 0	17.69 1	23.48	12.70			17.67	6.89		13.00	4.69 0.5862	5.56 0		4.30 0	4.19 0	3.97 0					4.60 0	3.86 0				3.39 2	4.47					3.22 2	3.98 2
ANID	TAM055	TAM056	TAM057	TAM058	TAM059	TAM060	TAM061	TAM062	TAM063	TAM064	TAM065	TAM066	TAM067	TAM068	TAM069	TAM070	TAM071	TAM072	TAM073	TAM074	TAM075	TAM076	TAM077	TAM078	TAM079	TAM080	TAM081	TAM082	TAM083	TAM084	TAM085	TAM086	TAM087	TAM088	TAM089	TAM091	TAM092	TAM094	TAM095	TAM097	TAM098	TAM099	TAM102	TAM103

ANID	macro grp	o Chem2012	CERAMIC TYPE	MATERIAL	SOURCE	STATE	SITE NAME	SITE NO	AS	ΓA	Π	ND	NS I	J YB	CE	00	CR
TAM104	Group-D	El Paso Core	е	Pottery	TAM	×	Ojasen	41EP00289	4.57	48.70 0.	0.4480 4	44.20 7.	7.53 2.52	2 3.38	98.01	4.69	25.18
TAM105	G-dno-D	El Paso Core	Jornada Bichrome	Pottery	TAM	ĭ	Ojasen	41EP00289	4.92	49.28 0.	0.4387 5	52.44 7.	7.94 2.47	7 3.62	97.80	5.28	27.27
TAM107	G-dno-D	El Paso Core	Jornada Bichrome	Pottery	TAM	ĭ	Ojasen	41EP00289	8.94	73.19 0.	0.7280 7	72.76 11.	11.75 2.16	6 5.95	143.10	7.69	35.20
TAM108	G-dno ₂ D	El Paso Core	Jornada Bichrome	Pottery	TAM	XI	Ojasen	41EP00289	80.8	54.33 0.	0.5973 5	53.26 9.	9.17 2.78	8 4.16	108.70	7.00	33.00
TAM109	G-dno-D	El Paso Core		Pottery	TAM	X	Ojasen	41EP00289	7.38			1			`	7.52	27.70
TAM110	Gronp-D	El Paso Core	Jornada Bichrome	Pottery	TAM	X	Ojasen	41EP00289	6.64	57.96 0.			8.61 3.39	9 3.53	111.08	6.70	31.22
TAM111	Group-B	Unas.	Mimbres B/W Style Indeter. Pott	Pottery	TAM	ĭ	Ojasen	41EP00289	4.71	44.64 0.	0.5413 4	43.79 7.	7.15 5.36	3.45	95.07	14.58	41.77
TAM112	Group-B2	Mimbres-02B	Mimbres B/W Style Indeter. Pottery	Pottery	TAM	ĭ	Ojasen	41EP00289	4.01							7.85	36.75
TAM113	Group-B2	Mimbres-08	Mimbres B/W Style Indeter. Pottery	Pottery	TAM	X	Ojasen	41EP00289	4.09	34.78 0.			3.59 4.00	0 2.38	63.28	6.49	26.76
TAM114	Group-B2	Mimbres-08	Mimbres B/W Style Indeter. Pottery	Pottery	TAM	XT	Ojasen	41EP00289	4.22		0.4480 3	32.56 4.	4.21 4.52	2 2.60	06'.29	6.87	28.23
TAM115	Group-B2	Mimbres-02B	Mimbres B/W Style Indeter. Pott	Pottery	TAM	XT	Ojasen	41EP00289	3.89	46.32 0.	0.5693 4	46.30 7.	7.03 5.35	5 3.63	82.01	8.52	38.48
TAM116	Group-A	Mimbres-01	Mimbres B/W Style Indeter. Pottery	Pottery	TAM	ĭ	Ojasen	41EP00289	0.00	53.20 0.	0.5320 4	47.42 3.	3.54 8.92	2 2.61	74.99	2.31	10.83
TAM117	Group-A	Mimbres-01	Mimbres B/W Style Indeter.	Pottery	TAM	ĭ	Ojasen	41EP00289	2.33	51.09 0.	0.5413 4	41.27 4.	4.48 11.57	7 2.53	76.63	3.06	18.53
TAM118	Group-B2	Mimbres-02B	Mimbres B/W Style Indeter. Pottery	Pottery	TAM	XT	Ojasen	41EP00289	5.04	42.13 0.	0.5320 5	50.91 7.	7.27 5.95	5 3.64	81.17	9.32	37.93
TAM119	Group-B2	Mimbres-02B	Mimbres B/W Style Indeter. Pottery	Pottery	TAM	XT	Ojasen	41EP00289	5.11	42.84 0.		42.31 6.	6.62 4.90	3.66	82.74	7.72	38.37
TAM120	Group-B2	Mimbres-02B	Mimbres B/W Style Indeter.	Pottery	TAM	X	Ojasen	41EP00289	2.76	42.20 0.	0.5507 4		6.30 4.80	0 3.25		7.40	38.62
TAM171	Group-D	El Paso Core	5	Pottery	TAM	X	Gobernadora	41EP00321	5.87	56.61 0.				9 4.45		5.63	30.86
TAM172	G-dno ₂ D	El Paso Core	El Paso Brownware ?	Pottery	TAM	XI	Gobernadora	41EP00321	4.39	56.48 0.	0.4853 6	.8 08.89	8.79 2.58	8 3.67	99.04	5.13	28.31
TAM173	G-dno-D	El Paso Core	El Paso Brownware?	Pottery	TAM	XI	Gobernadora	41EP00321	6.97	57.75 0.	0.4107 5	57.63 9.	9.02 2.26	3.41	107.19	2.98	28.39
TAM174	G-dno-D	El Paso Core	El Paso Brownware ?	Pottery	TAM	XT	Gobernadora	41EP00321	6.40	57.11 0.	0.5507 6	69.15 9.	9.07 2.80	0 4.13		6.67	38.04
TAM175	G-dno-D	El Paso Core	El Paso Brownware ?	Pottery	TAM	×	Gobernadora	41EP00321	5.02	57.99 0.	0.5693 7	79.01 9.	9.51 2.56	4.46	108.70	7.51	37.35
TAM176	G-dno-D	El Paso Core	خ خ	Pottery	TAM	XT	Gobernadora	41EP00321	4.84	52.02 0.	0.4480 6	68.45 8.	8.05 3.43	3 3.16	103.89	2.60	28.67
TAM177	G-dno-D	El Paso Core	El Paso Brownware?	Pottery	TAM	ĭ	Gobernadora	41EP00321	7.74	54.32 0.		71.26 8.	8.65 2.50	0 4.13	104.81	5.79	34.64
TAM178	Gronp-D	El Paso Core	?	Pottery	TAM	ΤX	Gobernadora	41EP00321	7.98						ļ	2.68	31.99
TAM179	Group-D	El Paso Core	?	Pottery	TAM	ĭ	Gobernadora	41EP00321	7.94	56.68 0.				0 3.51	95.62	6.63	36.19
TAM180	Group-D	El Paso Core	۲.	Pottery	TAM	ĭ	Gobernadora	41EP00321	7.37						·-	5.13	27.75
TAM181	Group-D	El Paso Core		Pottery	TAM	ĭ	Gobernadora	41EP00321	68.9				8.55 6.53			7.05	33.51
TAM182	Group-D	El Paso Core		Pottery	TAM	ĭ	Gobernadora	41EP00321	7.60							2.86	31.58
TAM183	G-dno-D	El Paso Core		Pottery	TAM	ĭ	Gobernadora	41EP00321	6.44				8.90 6.96	6 3.83		5.73	31.70
TAM184	G-dno-D	El Paso Core		Pottery	TAM	ĭ	Gobernadora	41EP00321	8.43						-	6.44	37.45
TAM185	G-dno-D	El Paso Core		Pottery	TAM	×	Gobernadora	41EP00321	7.46	_					_	7.16	30.06
TAM187	G-dno-D	El Paso Core		Pottery	TAM	×	Gobernadora	41EP00321	6.01						_	5.73	29.93
TAM188	G-dno-D	El Paso Core		Pottery	TAM	×	Gobernadora	41EP00321	8.78				_			6.62	35.09
TAM189	Group-D	El Paso Core		Pottery	TAM	×	Gobernadora	41EP00321	7.05							19.9	33.15
TAM190	G-dno-D	El Paso Core	ne	Pottery	TAM	×	Gobernadora	41EP00321	6.24							6.15	28.48
TAM191	Group-D	El Paso Core		Pottery	TAM	ĭ	Gobernadora	41EP00321	7.56							6.34	40.87
TAM192	Group-D	El Paso Core		Pottery	TAM	ĭ	Gobernadora	41EP00321	7.18	60.20 0.			8.94 3.19			5.30	28.20
TAM193	Group-D	El Paso Core		Pottery	TAM	ĭ	Gobernadora	41EP00321	5.99							6.41	35.70
TAM194	Group-D	El Paso Core		Pottery	TAM	X	Gobernadora	41EP00321	7.16	64.75 0.	0.5133 4		9.08 4.39	9 4.14	115.03	7.38	41.04
TAM195	Group-D	El Paso Core		Pottery	TAM	X	Gobernadora	41EP00321	5.28		0.4573 4		8.14 3.45	5 3.05	106.21	6.70	34.80
TAM196	Group-D	El Paso Core		Pottery	TAM	X	Gobernadora	41EP00321	8.55	58.02 0.	0.4760 5	58.03 9.	9.32 5.16	6 4.02	110.60	6.97	38.78
TAM197	G-dno-D	El Paso Core		Pottery	TAM	ĭ	Gobernadora	41EP00321	7.65							5.88	34.63
TAM198	Group-D	El Paso Core		Pottery	TAM	X	Gobernadora	41EP00321	8.61				8.75 2.95	5 3.23	104.98	7.54	38.53
TAM199	Group-D	El Paso Core	El Paso Bichrome	Pottery	TAM	ĭ	Gobernadora	41EP00321	6.18	60.55 0.	0.5320 4	44.62 9.	9.73 2.19	9 4.65	111.72	7.10	37.38

>	51.18	61.76	88.73	72.16	101.27	70.39	66.67	50.10	28.04	40.00	53.43	22.94	29.12	54.90	65.00	52.45	61.37	69.71	110.78	81.27	80.39	70.39	62.94	98.96	83.43	64.12	80.10	71.57	70.00	88.53	83.43	06.69	71.57	71.47	67.35	72.84	72.06	76.27	77.75	62.94	75.10	69.51	73.82	71.76
Ξ	3207.1	3890.5	5005.7			4151.5	2774.3	2218.3	2726.7	2726.6	2983.8	1087.8	2299.4	3050.8	3079.2	2217.7	3824.0	3619.6	6425.6	4218.7	4116.7	4320.2	3884.2	4907.4	4073.5	4042.1	3387.2	4209.3	4597.2	5485.1	4470.9	4237.7	3900.0	4538.6	4006.7	4227.2	4679.1	3802.5	4530.5	4212.8	4313.0	3627.6	4212.5	4660.0
NA	15172.5	16360.4	12278.3	10875.1	15039.7	12359.7	10588.2	12197.4	10133.0	10668.2	9751.7	8700.2	12045.5	10267.4	10940.9	10644.4	15536.6	14500.4	14308.4	14473.6	15013.3	20515.1	16430.8	15865.4	10324.0	14102.7	12072.7	12814.8	12356.4	10224.6	12813.3	13178.2	16618.3	13361.0	14258.9	11384.8	12859.1	10865.6	10813.8	12279.7	11148.3	11115.9	11662.6	10858.5
MN	326.2	361.5				400.3	844.2	472.9	296.8	304.5		188.8	260.1	269.7	516.7	481.1	329.6	392.4	643.0	416.2	512.7		414.8	549.9				395.8			498.5	386.9	444.8					370.6	420.1	494.0	427.6	390.2	402.0	382.5
¥	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
DY	4.588	5.543	8.114	6.461	7.646	690.9	4.960	5.180	2.972	2.896	4.912	2.905	2.552	5.343	5.276	5.199	6.317	6.423	6.317	6.184	6.604	6.145	5.438	6.862	5.926	5.247	5.954	5.390	6.040	6.279	7.579	069.9	5.648	5.448	6.270	5.801	5.620	6.795	5.429	6.346	5.448	6.528	980.9	6.126
CA	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
BA	1458.1	819.1	1874.8	1805.5	1565.9	1715.5	612.5	636.0	9.32.9	570.1	488.6	706.1	545.6	592.6	8.089	537.9	1054.2	980.5	1109.4	888.8	1064.8	1127.1	1165.3	1212.2	1257.7	1301.4	1256.5	1219.0	1096.8	1321.5	1143.8	1091.4	1101.2	1353.9	1231.1	1085.6	1247.5	1266.1	1285.0	1170.2	1461.9	1030.0	1178.1	1093.9
AL	80223.0	86038.7	86311.7	89181.6	82893.8	83725.1	84687.0	80084.6	77089.9	77344.0	86052.3	99544.7	92318.4	82277.8	87959.9	89045.7	86332.4	85767.0	100571.3	90326.6	87831.4	90846.1	85192.3	86061.5	92487.2	88059.4	88137.4	84639.4	86220.4	91849.3	84093.9	87512.0	89607.3	86841.0	83064.2	84090.4	85397.9	93265.5	88813.1	84407.9	88662.0	83082.9	90818.4	91994.5
ZN ZR	.9 262.8						.3 159.8	97.0 141.9	.4 206.4	78.4 218.0		.7 129.2	51.0 203.6	66.5 178.0	.1 182.9		86.6 352.1	77.9 229.0	73.5 311.5	.2 305.5	92.6 343.1	65.9 322.8	74.0 293.3			70.6 349.9	60.4 295.1											.1 352.3	.1 348.7	.3 337.8	84.6 345.8			73.0 407.2
Z H						5 108.7			1 65.4			51.7			4 81.1					9 86.2																		108.1	2 62.1					
TB T	0.96 21.86	0.99 22.95	1.33 21.64	1.31 23.11	1.48 18.97	1.05 20.05	0.92 21.33	0.89 21.14	0.43 25.81	0.41 29.27		0.26 48.36	0.34 41.31	0.69 21.57	0.63 20.54	0.80 20.94	0.94 20.87	0.76 19.89	0.96 13.72	1.05 23.89	1.02 20.29	0.81 19.38	1.03 21.30	1.07 16.70		0.80 24.03	0.89 19.44	0.83 19.35	17 19.62				0.86 20.06		1.18 19.04	1.16 19.48	1.16 19.81	1.10 26.39	1.01 19.92	0.95 18.40	12 20.31			1.09 21.35
TA	2.6000 0.	2.8400 0.				2.3900 1.	1.6600 0.	1.6600 0.	1.6400 0.	1.5900 0.	1.5600 0.	1.7500 0.	2.0700 0.	1.5100 0.	1.4600 0.	1.5300 0.	2.2700 0.	2.4400 0.	2.3600 0.	2.6700 1.	2.9400 1.	2.6000 0.	2.4800 1.	2.7900 1.					3.1100 1.									2.3500 1.	2.2800 1.		2.7900 1.			2.4800 1.
SR	0.0	0.0	0.0		0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0		0.0											0.0	0.0	0.0	0.0	0.0			0.0
SC	7.62	8.27	10.97	9.95	10.48	9.35	9.50	8.23	5.95	6.13	9.35	4.72	5.51	9.29	9.13	9.23	8.59	8.54	8.51	10.50	10.12	8.72	9.26	8.60	9.83	8.98	9.52	8.87	9.41	10.10	8.77	8.78	9.93	9.43	7.83	9.64	8.62	10.39	9.93	96.8	10.45	8.81	6.59	10.45
SB	0.4693	0.5461	0.5205	0.5717	0.6144	0.5717	0.8277	0.6741	0.5632	0.6229	0.9984	0.6571	0.8192	0.8619	0.8875	0.8107	0.5547	0.5888	0.6144	0.7424	0.5120	0.6571	0.6400	0.5205	0.7936	0.5376	0.6571	0.6571	0.7083	0.6656	0.5973	0.5632	0.5376	0.7339	0.5803	0.5461	0.6400	0.7424	0.5888	0.6059	0.5973	0.6485		0.7509
RB	126.50	141.50	95.40	118.50	85.70	111.40	193.10	196.30	162.50	170.80	200.30	247.20	222.50	200.80	195.40	194.00	119.90	111.00	84.80	131.00	118.30	113.70	130.70	94.20	104.90	118.70	122.30	117.40	125.20	116.90	112.30	102.90	123.80	117.50	109.80	133.40	125.90	130.80	115.40	115.30	119.50	114.00	117.90	113.10
Z	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0		0.0												0.0	0.0	0.0	0.0			0.0
生	10.41	9.73	15.74	10.91	17.35	11.49	6.22	6.15	8.28	8.38	5.77	4.66	6.01	5.86	6.54	5.94	10.39	89.8	11.70	12.25	14.66	12.77	12.56	20.09	10.38	12.37	11.57	11.81	15.21	13.25	11.30	11.36	10.74	8.97	13.18	15.80	11.14	12.65	11.83	11.10	14.36	11.10	11.06	13.44
FE	33961.4	38589.6	48041.1	44426.7	49606.0	41085.5	27218.4	23907.8	22010.1	23093.8	26871.2	15492.4	14894.8	26088.4	26224.6	26290.2	38150.6	36841.2	43884.6	44033.6	42715.3	39526.4	39314.0	43205.8	41896.1	40247.9	38833.2	39341.5	40326.9	43300.6	41805.7			39809.2			36832.2	43896.1	41559.1	38591.9	43588.2			43788.0
EU	1.4207	1.4903	2.2851			1.7486		1.2121	0.6855	0.7451	1.2021	0.4868	0.6358	1.3114	1.2121	1.2220	1.6691	1.5201	2.1758	1.7883	1.6989	1.7486	1.7188	2.2354	1.6790	1.7188	1.4704	1.4406	1.7188	1.5896	1.5797	1.5995	1.6095	1.7287	1.7287		1.6095	1.6691	1.7486	1.5499	1.7784	1.7188		1.7982
CS	3.37	4.74	3.57	4.76	3.62	4.37	43.63	38.44	6.51	91.9	46.86	14.91	26.92	43.26	40.04	42.43	4.04	3.92	3.22	5.45	4.73	3.87	3.93	3.41		4.09	4.48	4.31	4.84	4.36	3.84	3.76	4.18	3.98	3.58			5.37	4.41	3.89	4.33	3.95	3.95	5.02
ANID	TAM104	TAM105	TAM107	TAM108	TAM109	TAM110	TAM111	TAM112	TAM113	TAM114	TAM115	TAM116	TAM117	TAM118	TAM119	TAM120	TAM171	TAM172	TAM173	TAM174	TAM175	TAM176	TAM177	TAM178	TAM179	TAM180	TAM181	TAM182	TAM183	TAM184	TAM185	TAM187	TAM188	TAM189	TAM190	TAM191	TAM192	TAM193	TAM194	TAM195	TAM196	TAM197	TAM198	TAM199

ANID	macro grp	Chem2012	CERAMIC TYPE	MATERIAL	SOURCE	CE STATE	E SITE NAME	SITE NO	AS	ΓA	ΓΩ	ND	SM	n	YBC	CE CO	CR
TAM200	G-dno-D	El Paso Core		Pottery	TAM		Gobernadora	41EP00321	3.97	52.19 0	0.4667 4		7.88	3.98 3.9	3.99 99.42	ц,	32.85
TAM201	Group-B2	Mimbres-02A	Mimbres B/W Style III	Pottery	TAM	X	Gobernadora	41EP00321	2.39		0.4107 2	23.99 4		3.37 3.57			38.99
TAM202	Group-B	Unas.	Mimbres B/W Style III	Pottery	TAM	XX	Gobernadora	41EP00321	6.34	26.88 0	0.3547 2	20.21 3	3.98 4	4.62 1.8	1.86 57.70	0 11.90	39.53
TAM205	Group-B2	Mimbres-02A	Mimbres B/W Style III	Pottery	TAM	X	Gobernadora	41EP00321	2.70	57.83 0	0.5320 4	40.92	7.76 4	4.28 4.3	4.33 89.95	99.6	42.23
TAM206	Group-C1	Unas.	Mimbres B/W Style III	Pottery	TAM	X	Gobernadora	41EP00321	2.43					2.14 1.0			
TAM207	Group-C1	Unas.	Mimbres B/W Style III	Pottery	TAM	×	Gobernadora	41EP00321	5.42		0.2427 3		5.50 2			5 10.50	
TAM208	Group-A	Mimbres-01	Mimbres B/W Style III	Pottery	TAM	ĭ	Gobernadora	41EP00321	2.01		0.6253 4		6.10	9.29 3.0	3.08 103.01	1 3.01	15.31
TAM209	Group-B2	Mimbres-02A	Mimbres B/W Style III	Pottery	TAM	ĭ	Gobernadora	41EP00321	2.94								
TAM210	Group-B2	Mimbres-02B	Mimbres B/W Style III	Pottery	TAM	X	Gobernadora	41EP00321	3.58							0 7.88	
TAM211	Group-B1	Mimbres-04B	Mimbres Polychrome	Pottery	TAM	MN	Old Town	LA 001113	1.92		0.4947 3	36.53 7	7.38 6		3.64 91.41	1 6.92	28.09
TAM212	Group-B2	Mimbres-11	Mimbres B/W Style III	Pottery	TAM	MN	Pruitt Ranch	LA 001117	2.86	31.92 0	0.4107 3	34.36 4	4.20 3.	3.25 2.97	97 63.39	9 12.08	46.75
TAM213	Group-B2	Mimbres-02A	Mimbres B/W Style III	Pottery	TAM	MN	Pruitt Ranch	LA 001117	0.00	42.25 0	0.4013 3	36.31 6	6.79	5.57 3.31	31 70.73	3 5.98	41.89
TAM214	Group-B2	Mimbres-02A	Mimbres B/W Style III	Pottery	TAM	MN	Pruitt Ranch	LA 001117	2.05	38.13 0				4.74 2.8	2.88 60.67	7 4.13	
TAM215	Group-B2	Mimbres-02A	Mimbres B/W Style III	Pottery	TAM	MN	Pruitt Ranch	LA 001117	2.06	44.20 0	0.4387 3	33.32 6	6.35 4	4.70 3.2	3.23 84.46	91.1	38.50
TAM216	Group-B2	Mimbres-02A	Mimbres B/W Style III	Pottery	TAM	NM	Pruitt Ranch	LA 001117	0.00				7.41 4	4.67 3.47		8 7.40	42.79
TAM217	Group-B1	Mimbres-04B	Mimbres B/W Style III	Pottery	TAM	MN	Pruitt Ranch	LA 001117	3.52	42.92 0	0.4853 2	25.03 6	6.12	4.78 3.3	3.33 84.84	4 5.99	27.14
TAM218	Group-A	Unas.	Mimbres B/W Style III	Pottery	TAM	MN	Pruitt Ranch	LA 001117	0.00	62.12 0	0.6347 2		4.07 5		3.10 89.43	3 2.36	11.52
TAM219	Group-C2a	Mimbres-49A	Mimbres Polychrome	Pottery	TAM	N	Old Town	LA 001113	0.00		0.3080 2	23.43 5	5.35	1.85 2.	2.12 66.12	2 12.48	67.40
TAM220	Group-B1	Mimbres-04B	Mimbres Polychrome	Pottery	TAM	M	Old Town	LA 001113	3.27	78.92 0	0.7093 5	56.52 10	10.81	7.18 4.8	4.83 110.04	4 6.79	32.44
TAM221	Group-B	Unas.	Mimbres Polychrome	Pottery	TAM	ΝN	Old Town	LA 001113	0.00	53.50 0		34.25 7	7.17	5.88 4.3	4.23 98.17	7 4.92	33.96
TAM222	Group-B2	Mimbres-08	Mimbres Polychrome	Pottery	TAM	MN	Old Town	LA 001113	3.56	34.49 0	0.4013 2	28.22 3	3.58	3.36 2.3	2.33 60.67	7 3.26	27.37
TAM223	Group-B2	Mimbres-02A	Mimbres Polychrome	Pottery	TAM	ΝN	Old Town	LA 001113	2.87	48.17 0	0.6440	37.74	7.75 4	4.46 4.	4.53 99.27	17.7	42.54
TAM224	Group-B1	Mimbres-04B	Mimbres Polychrome	Pottery	TAM	MN	Old Town	LA 001113	2.35	51.24 0	0.4947 3	36.25 7	7.20 5.	5.74 2.9	2.98 88.34	4 4.04	27.97
TAM225	Group-B2	Mimbres-02A	Mimbres B/W Style III	Pottery	TAM	Ν	Pruitt Ranch	LA 001117	1.82	41.39 0			6.04		2.93 72.88	8 6.65	40.68
TAM226	Group-B2	Mimbres-02A	Mimbres B/W Style III	Pottery	TAM	NM	Old Town	LA 001113	1.99	34.42 0	0.4573 2	23.94 4	4.16 3.	3.82 2.9	2.99 57.11	1 4.64	37.04
TAM227	Group-B2	Mimbres-02A	Mimbres B/W Style III	Pottery	TAM	NM	Old Town	LA 001113	2.73	35.20 0				4.13 3.41			40.11
TAM228	Group-B1	Mimbres-04C	Mimbres B/W Style III	Pottery	TAM	NM	Old Town	LA 001113	1.92	44.77 0				3.35 3.27		4 3.82	34.78
TAM229	Group-B1	Mimbres-04C	Mimbres B/W Style III	Pottery	TAM	NM	Old Town	LA 001113	1.33		(33.95
TAM230	Group-B	Unas.	Mimbres B/W Style III	Pottery	TAM	NM	Old Town	LA 001113	2.14	0 68.89		47.91 9		6.97 4.51		7.51	32.92
TAM231	Group-B	Unas.	Mimbres B/W Style III	Pottery	TAM	M	Old Town	LA 001113	2.43		0.5787 6		9.56 3	3.92 4.	4.52 104.09		33.32
TAM232	Group-B2	Mimbres-02A	Mimbres B/W Style III	Pottery	TAM	M	Old Town	LA 001113	2.29								
TAM233	Group-C1	Mimbres-21	Mimbres B/W Style III	Pottery	TAM	MN	Old Town	LA 001113	3.54					1.36 2.11		1	
TAM234	Group-B1	Mimbres-04B	Mimbres B/W Style III	Pottery	TAM	M	Old Town	LA 001113	1.70				_			1 5.53	25.34
TAM235	Group-B2	Mimbres-02A	Mimbres B/W Style III	Pottery	TAM	NM	Old Town	LA 001113	1.97	37.36 0	0.3733 3	34.70 5	5.16 9.	9.56 3.07	07 68.40	0 5.11	42.28
TAM236	Group-A	Mimbres-01	Mimbres B/W Style III	Pottery	TAM	NM	Old Town	LA 001113	0.00	62.65 0	0.4947 2	27.37 4	4.09 13	13.42 2.9	2.94 95.25	5 2.75	9.28
TAM237	Group-B1	Mimbres-04A	Mimbres B/W Style III	Pottery	TAM	NM	Old Town	LA 001113	2.91	36.70 0	0.3547 3		5.14 5.	5.01 3.17			24.17
TAM238	Group-B1	Mimbres-04A	Mimbres B/W Style III	Pottery	TAM	MN	Old Town	LA 001113	2.67	40.78 0	0.3733 3	33.50 5		5.64 2.0	2.67 82.02	2 6.38	23.78
TAM239	Group-A	Mimbres-01	Mimbres B/W Style III	Pottery	TAM	MN	Old Town	LA 001113	1.88	60.05 0	0.5600	54.81 5	5.55 13	13.55 2.0	2.66 103.32	2 2.12	86.8
TAM240	Group-A	Mimbres-01	Mimbres B/W Style III	Pottery	TAM	Z	Old Town	LA 001113	1.90	60.52 0	0.6160 2		5.36	7.71 3.	3.16 102.59	9 2.10	9.84
TAM241	Group-B2	Mimbres-02A	Mimbres B/W Style III	Pottery	TAM	NM	Old Town	LA 001113	3.11		0.4293 4	_	5.93 6	6.29 3.4	3.45 65.69	9 5.43	
TAM242	Group-B2	Mimbres-02A	Mimbres B/W Style III	Pottery	TAM	NM	Old Town	LA 001113	2.86	39.50 0	0.4667 3	35.11 6	6.14 6	6.15 2.	2.76 68.69	9 5.74	37.79
TAM243	Group-B2	Mimbres-02A	Mimbres B/W Style III	Pottery	TAM	M	Old Town	LA 001113	0.00				_		_		
TAM244	Group-B2	Mimbres-02A	Mimbres B/W Style III	Pottery	TAM	N	Old Town	LA 001113	1.93				5.11 3		_		
TAM245	Group-B	Unas.	Mimbres B/W Style III	Pottery	TAM	M	Old Town	LA 001113	2.93	49.03 0	0.4387 3	33.44 7	7.77 4.	4.24 2.9	2.59 93.08	8 3.48	21.22

>	62.55	43.24	76.86	57.84	41.37	159.71	30.10	54.02	60.29	48.24	53.82	64.31	49.41	67.16	67.35	49.90	17.94	93.63	56.18	57.75	49.90	65.49	50.20	57.25	48.73	46.57	52.55	53.14	67.84	49.61	46.27	89.41	44.90	51.18	22.25	44.61	46.67	31.67	31.67	72.25	74.12	61.08	59.02	43.92
F	3139.2	3058.4	3356.2	2779.2	2673.3	3534.3 1			3240.8	1952.8			3260.6	2741.2				3997.9	3089.3	3442.5	2383.2	3034.7	2538.5							~							3278.3	2131.1	2309.5	3718.4	4076.8			3242.8
NA																()																												
	5 12683.2	0 11040.5	8 10584.3	8 11564.9	4 5111.7	6 14867.7		3 13050.1	9 10993.0	4 11553.5	3 10055.9	1 14168.0	6 10850.2	8 11689.2		9 11135.5	13513.7	5 16002.9	9 9524.7	3 10677.2	8 8955.4	8 11011.7	1 11271.9	0 11812.6							٠				-		12799.6	5 13714.3	6 13826.5					8 13459.3
MN	337.5	214.0	322.8		233.4	399.6	163.4	496.3	480.9	583.4	835.3		9.661	259.8				326.5	519.9	246.3	182.8	297.8	185.1															157.5	128.6	244.6	251.0			462.8
\sim	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
Dγ	5.648	4.071	2.389	6.403	3.039	3.565	4.559	6.757	4.148	5.486	3.966	4.979	3.641	4.979	5.075	4.196	2.714	3.766	8.630	5.362	2.743	5.448	4.463	4.454	3.259	3.039	5.056	4.540	7.827	6.862	3.689	3.632	5.639	4.616	2.112	3.488	3.049	4.435	3.259	4.826	5.295	4.874	4.234	5.639
CA	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0
BA	1240.0	442.3	613.2	564.3	534.7	7.097	642.7	602.7	8.799	682.3	612.5	692.1	439.6	651.1	641.6	2.695	339.6	735.5	762.7	695.7	598.1	624.5	695.4	682.8	547.5	639.7	908.5	815.1	1041.6	937.9	467.8	9/1.1	617.0	546.7	349.0	728.8	712.0	289.7	602.5	695.5	592.1	558.0	588.5	988.7
AL	82404.9	83277.6	78629.4	80367.8	49017.8	69813.7	97734.1	81652.4	82422.8	83402.3	77066.1	84611.7	89731.1	90340.5	86193.6	83787.0	91406.3	82382.0	93756.2	92075.1	78727.0	90683.8	86772.4	94348.0	85159.0	84200.5	87178.3	89028.6	88662.3	92033.8	85298.6	93283.9	87127.8	84873.2	95245.4	87254.8	86585.3	122139.9	103531.4	102417.8	102433.3	100602.5	82066.0	85171.8
ZR	318.7	218.6	219.4	220.2	103.2	149.7	229.9	175.1	201.1	213.9	217.3	221.5	292.3	193.8	296.8	219.3	156.3	134.2	158.7	272.2	210.3	186.9	184.8	148.4	156.1	180.8	169.4	169.0	216.6	154.4	226.5	141.4	168.4	171.1	158.5	164.3	9.961	182.3	2292	183.9	153.5	191.4	215.4	212.5
NZ	51.2	48.8	80.3	59.2	93.6	72.7	40.2	47.1	44.2	53.1	49.0	53.6	46.2	299	56.5	51.2	71.0	87.5	54.3	68.5	42.3	57.5	38.1	45.8	52.9	61.3	61.8	22.6	49.2	8.09	60.7	17.0	33.7	53.0	37.8	69.1	72.4	32.1	41.3	47.1	54.4	52.3	63.3	44.5
Ŧ	24.83	19.80	17.92	19.17	7.50	11.02	43.81	20.16	22.25	23.88	18.95	19.69	24.60	21.05	20.04	25.52	45.43	10.61	25.56	25.35	28.09	21.66	27.75	21.19	21.87	23.64	15.95			21.67	21.51	9.64	28.14	20.85	51.26	20.93	21.00	47.86	48.45	20.68	20.94	20.43	20.48	15.07
TB	1.03	0.57	0.52	1.06	09.0	0.75	0.65	1.01	0.76	96.0	0.58	96.0	0.61	0.89	1.04	0.76	0.53	0.78	1.51	0.00	0.41	1.11	0.79	0.73	0.56	0.62		_							0.40	0.60		0.54	0.52	0.63	0.71			0.84
TA	2.4300	1.5400	1.4700	1.4000	0.6800	1.1100	2.1100	1.4100	1.5700	1.5600	1.5600	1.5300	1.7500	1.5200	1.4700	1.5200	2.2400	0.8500	1.5300	1.5200	1.4800	1.5900	1.5700	1.5000	1.5800	1.7700	1.3000	1.3000	1.4700	1.3300	1.5900	0.8900	1.5500	1.4900	2.3100	1.4100	1.3200	2.2900	2.4000	1.4900	1.4900	1.5600	1.6100	0.9600
SR	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0				0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0		0.0
SC	8.91	8.48	8.26	10.80	7.88	9.82	3.88	10.01	8.49	7.42	8.20	11.54	10.70	11.41	12.15	7.59	4.00	11.69	9.29	8.70	6.25	11.60	7.06	11.01	6.36	10.06	8.82	8.94	8.25	8.07	99.6	10.21	7.21	10.09	3.88	7.23	7.18	4.29	4.45	10.53	10.22	9.47	10.22	9.54
SB	0.5120	0.5461	0.5291	0.5035	0.3584	0.7339	0.5888	0.5120	0.9045	0.4011	0.8107	0.3499	0.7168	0.4523	0.4352	0.5205	0.5803	0.7595	0.3413	0.5461	0.4608	0.4949	0.4096	0.4949	0.5205	0.4949	0.3328	0.4181	0.3840	0.3584	0.5461	1.81/6	0.3755	0.5291	0.7083	0.5888	0.6485	0.5803	0.6400	0.4779	0.5035	0.3840	0.5291	0.5717
RB	109.30	159.60	162.10	150.90	90.50	146.70	175.00	156.50	210.40	174.00	199.60	155.80	185.00	141.40	148.60	165.90	202.10	105.30	143.50	210.30	187.30	148.70	142.70	151.50	172.00	186.10	137.40	138.50	153.40	123.70	154.90	107.90	147.50	137.80	162.70	145.40	143.20	196.70	197.70	145.10	144.30	160.30	158.80	129.80
Z	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0		0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0		0.0											0.0	0.0	0.0		0.0			0.0
土	10.56	8.29	7.76	7.09	4.20	6.01	7.19	7.47	6.18	6.05	7.18	8.09	8.90	7.27	8.04	8.03	5.06	5.42	5.16	6.29	7.27	7.40	5.89	6.63	8.26		7.28			60.9	8.34	6.10	6.16	7.67	5.93	5.87	69.9	89.9	9.24	7.59	6.53	8.21	7.14	7.69
FE	2.69998	19465.6	29358.6	26992.4	21786.8	28774.0		24425.6	25920.8	23216.6	24654.9	27677.7	22781.7	26587.5	-		10612.1	35042.7	27472.3	20672.4	20613.8	26594.7	21489.0	24851.2	20020.0						23208.9			23119.2	10616.1		` '	9503.2	9532.9	24743.3	24213.0	22662.6		24375.1
EU	1.5399	0.8047	0.8147	1.5201	0.7948	1.1227	0.8842	1.3909	1.1624	1.2319	0.8842	1.3611	0.7352	1.2618	1.4605	1.0134	0.6656	1.3015	1.8777	1.4903	0.6458	1.4306	1.2518	1.0730	0.7054	0.7650	1.5598	1.5697	1.7883	1.7486	0.8445	1.4306	1.4406	0.9736	11.75 0.5365	1.0332	1.0730	0.8047	0.7749	1.0929	1.1127	0.8743	0.9339	1.7585
CS	4.07	16.67	14.75	24.57	7.42	10.48		22.25	35.77	6.18	7.51	16.79	20.13	24.95			72.96	7.53	6.42	12.31	7.13	23.69	4.99	24.38	17.83									16.09	11.75		4.93	16.69	16.65	22.19	21.27			5.94
ANID	TAM200	TAM201	TAM202	TAM205	TAM206	TAM207	TAM208	TAM209	TAM210	TAM211	TAM212	TAM213	TAM214	TAM215	TAM216	TAM217	TAM218	TAM219	TAM220	TAM221	TAM222	TAM223	TAM224	TAM225	TAM226	TAM227	TAM228	TAM229	TAM230	TAM231	TAM232	I AM233	TAM234	TAM235	TAM236	TAM237	TAM238	TAM239	TAM240	TAM241	TAM242	TAM243	TAM244	TAM245

ANID	macro_grp	Chem2012	CERAMIC TYPE	MATERIAL	SOURCE	E STATE	SITE_NAME	SITE_NO	AS	ΓΑ	Π	ND	SM	<u> </u>	YB	CE CO	CR
TAM246	Group-B	Unas.	Mimbres B/W Style III	Pottery	TAM	M	Old Town	LA 001113	1.59	47.11	0.4947	43.87	7.66 2	2.81 3.	3.28 87.02	3.35	20.48
TAM247	Group-B2	Mimbres-02A		Pottery	TAM	NM	McSherry	LA 015050	3.36						3.35 69.12		
TAM248	Group-B	Unas.		Pottery	TAM	NM	McSherry	LA 015050	2.35		0.4013	25.44	5.00 5	5.30 2.	2.45 80.32		33.28
TAM249	Group-B2	Mimbres-02A	Mimbres B/W Style Indeter. Pottery	Pottery	TAM	MN	McSherry	LA 015050	0.00	42.43	0.5693		5.85 6			0 5.95	
TAM250	Group-C2	Unas.	Mimbres Polychrome	Pottery	TAM	MN	Treasure Hill	LA 016241	4.44	32.73							
TAM251	Group-A	Unas.		Pottery	TAM	M	Treasure Hill	LA 016241	0.00	50.43	0.4853		4.05 6	6.96 2.	2.53 67.00	3.52	
TAM252	Group-C2b	Mimbres-44	Mimbres Polychrome	Pottery	TAM	NM	Treasure Hill	LA 016241	0.00	45.18	0.4760	39.00	7.04	1.57 2.	2.74 82.31	12.77	27.66
TAM253	Group-B	Unas.	Mimbres B/W Style III	Pottery	TAM	MN	Pruitt Ranch	LA 001117	0.00	44.34	0.4760	33.04	5.68 2	2.61 3.	3.31 75.31	1 4.53	
TAM254	Group-B2	Mimbres-02A	Mimbres B/W Style III	Pottery	TAM	MN	Pruitt Ranch	LA 001117	1.61	44.07	0.5320	32.74	5.80 4	4.92 3.	3.83 77.56	5.14	40.12
TRC002	Group-D	El Paso Core	El Paso Brownware	Pottery	MURR	MN	LA 117704	LA 117704	7.61	44.27	0.4123	31.80	6.50 5	5.36 3.	3.01 74.64		
TRC003	Group-D	El Paso Core	El Paso Brownware	Pottery	MURR	M	LA 117704	LA 117704	6.37	73.16	0.6738	56.34 11	11.41 5	5.27 5.	5.07 137.86	9.65	30.01
TRC006	Group-D	El Paso Core	El Paso Brownware	Pottery	MURR	MN	LA 117713	LA 117713	8.67	55.22	0.6374	45.73	9.82 4	4.82 4.	4.58 119.79	09.7 6	30.8
UT00415	G-dno-D	El Paso Core	El Paso Polychrome Transit Pottery	t Pottery	MURR	ĭ	Hueco Tanks (CA2)	41EP00002	9.28	70.31	0.6733	53.77 9	9.78 5	5.38 4.	4.67 130.72	72 6.81	32.65
UT00416	Group-D	El Paso Core	El Paso Brown	Pottery	MURR	ΙX	Hueco Tanks (CA2)	41EP00002	4.61	50.41			7.50 2	2.57 3.	3.06 97.54		
UT00418	Group-D	El Paso-2	El Paso Polychrome Classic	Pottery	MURR	ĭ	Hueco Tanks (CA7)	41EP00002	6.36			47.49		3.72 4.	4.38 101.39	9 9.30	56.81
UT00419	G-dno-D	El Paso-2	El Paso Polychrome Pottery	Pottery	MURR	ĭ	Hueco Tanks (CA7)	41EP00002	8.46	53.04	0.5789	48.70	9.32 3	3.02 4.	4.31 99.11	1 14.05	. 66.7
UT00421	Group-D	El Paso-2	El Paso Polychrome	Pottery	MURR	XI	Hueco Tanks (NW1)	41EP00002	19.9	38.67	0.6210	32.00	6.93 3		4.29 78.33	13 8.91	60.45
UT00422	G-dno-D	El Paso Core	El Paso Polychrome Classid Pottery	Pottery	MURR	ĭ	Hueco Tanks (NW1)	41EP00002	7.61	54.61		45.15	8.64 3	3.97 5.	5.18 103.42	12 6.35	34.56
UT00424	G-dno-D	El Paso Core	El Paso Brown	Pottery	MURR	ĭ	Hueco Tanks (NW1)	41EP00002	6.63	72.86	0.7994	60.51 11	11.69 4	4.84 4.	4.97 155.91	10.66	32.87
UT00425	Group-D	El Paso-2	El Paso Polychrome Transit Pottery	t Pottery	MURR	ĭ	Hueco Tanks (NW2)	41EP00002	7.06		0.5391	42.38	8.25 2	2.26 3.	3.85 95.21	9.76	72.13
UT00426	G-dno-D	El Paso Core		Pottery	MURR	ĭ	Hueco Tanks (SB1)	41EP00002	5.86	83.97	0.6415	61.19	11.18 3	3.06 4.	4.43 135.98	80.8	27.30
UT00427	Group-D	El Paso Core	El Paso Brown	Pottery	MURR	ĭ	Hueco Tanks (SB2)	41EP00002	7.36	60.89	0.6359	59.51 11	11.39 4	4.79 4.	4.70 139.09	99.8 60	34.97
UT00428	Group-D	El Paso Core		Pottery	MURR	XI	Hueco Tanks (SB4)	41EP00002	6.67					4.73 3.	3.10 118.18		23.56
UT00430	Group-D	El Paso-2	El Paso Polychrome Classid Pottery	Pottery	MURR	ĭ	Hueco Tanks (SB4)	41EP00002	6.12	52.80	0.6057	45.81	9.22 3	3.13 4.	4.02 95.24	11.56	61.2
UT00431	Group-D	Loop 375	El Paso Polychrome	Pottery	MURR	ĭ	Hueco Tanks (SB5)	41EP00002	10.02	89.10	1.5373	78.87	15.81 4	4.06 10.	10.65 141.65	55 8.91	40.93
UT00434	Group-D	El Paso Core	El Paso Polychrome Classid Pottery	Pottery	MURR	ΤX	Hueco Tanks (SB6)	41EP00002	7.14								
UT00437	Group-D	Loop 375	El Paso Polychrome Classid Pottery	Pottery	MURR	ΤX	Hueco Tanks (WS1)	41EP00002	14.20	85.53		78.60 16	16.84 2	2.89 10.		86 8.73	
UT00438	Group-D	El Paso Core	El Paso Polychrome Classid Pott	Pottery	MURR	ĭ	Hueco Tanks (WS2)	41EP00002	2.89		~					72 8.25	
UT00446	Group-B1	Mimbres-04A		Pottery	MURR	M	Turkey Knob Pueblo	LA 120756	2.36	_					_		_
UT00447	Group-B1	Mimbres-04A		Pottery	MURR	M	Turkey Knob Pueblo	LA 120756	2.36		_	_	6.70 3	3.88 3.			26.14
UT00450	Group-B2	Mimbres-02A	Mimbres B/W Style III	Pottery	MURR	M	Turkey Knob Pueblo	LA 120756	2.40				7.09 4			34 5.80	
UT00451	Group-A	Mimbres-10	Mimbres Corrugated	Pottery	MURR	M	Turkey Knob Pueblo	LA 120756	4.10				16.45 7		_		30.46
UT00452	Group-B	Unas.	Mimbres B/W Style III	Pottery	MURR	Z	Turkey Knob Pueblo	LA 120756	3.42								_
UT00454	Group-A	Mimbres-01	Mimbres B/W Style III	Pottery	MURR	Z	Gap Village	LA 125819	2.51				1				
UT00455	Group-A	Mimbres-10	Three Circle Corrugated	Pottery	MURR	¥	Gap Village	LA 125819	4.68						5.47 80.63	3 4.07	25.40
UT00456	Group-B1	Mimbres-09	Mimbres B/W Style III	Pottery	MURR	¥	Gap Village	LA 125819	3.64	-					_		
UT00457	Group-B	Unas.		Pottery	MURR	MN	Gap Village	LA 125819	3.93				6.58 3	3.63 3.		7.99	
UT00458	Group-C2a	Mimbres-49A		Pottery	MURR	MN	Gap Village	LA 125819	2.68		0.4162			2.79 2.		8.64	
UT00459	Group-C1	Mimbres-21	=	Pottery	MURR	¥	Gap Village	LA 125819	2.60					1.26 2.		1	_
UT00460	Group-B1	Mimbres-04A		Pottery	MURR	M	Gap Village	LA 125819	6.95			50.80		4.71 4.	4.80 130.85	85 8.26	21.62
UT00461	Group-B	Unas.	Mimbres Corrugated	Pottery	MURR	M	Gap Village	LA 125819	2.16			`	11.89 10		1		
UT00462	Group-C2	Unas.	Mimbres B/W Style I	Pottery	MURR	M	Gap Village	LA 125819	0.00	_			6.14	1.35 2.	2.85 73.68	12.29	
UT00463	Group-B	Unas.	Mimbres Corrugated	Pottery	MURR	M	Oops Village	LA 132649	5.92	43.87	0.4632		7.41 4	4.23 3.	3.18 85.50	50 12.70	30.88
UT00464	Group-A	Mimbres-10	Plain (possible corrugated)	Pottery	MURR	MN	Oops Village	LA 132649	2.77	. 10.99	1.3643	58.87 12	12.77 6	6.46 9.	9.72 165.28	28 5.85	26.62

>	53.33	54.90	28.73	48.14	65.20	30.10	82.75	34.71	41.18	85.94	96.93	73.50	63.10	71.90	06.86	101.10	100.20	48.60	88.40	90.10	58.10	87.70	78.50	103.80	70.20	48.90	80.70	69.50	61.80	63.40	64.70	50.90	47.90	31.70	53.20	50.90	66.40	76.40	67.00	53.90	55.00	102.40	96.90	50.40
I	4259.6	3339.8	2297.4	3154.9	2286.1	2063.3	2884.8	2373.2	2820.9	4243.4	5385.5	4786.9	4358.1	4707.9	4636.1	4769.7	3965.1	3529.3	4936.4	4101.9	3648.8	5104.4	5714.3	4573.3	3303.0	2934.3	3571.3	4931.5	3033.1	3132.1	3695.0	2416.1	2825.7	1773.1	2736.9	2923.9	3529.6	3964.3	2813.5	3069.9	2814.2	3645.2	3342.2	2775.8
NA	13586.7	11761.4	15437.2	13125.1		14597.7		17587.2	12802.0	12007.3	14948.2	13548.3	15040.3	16139.8	10034.7	8413.2	10002.1	18261.6	13822.7	9028.8	12231.6	13764.5	20163.4	9844.9		15052.9		٠ ا		13740.9	14194.1					$\overline{}$	0.6696	16556.8	19005.4	14821.7	10640.9		٠ .	13948.3
MN	548.7	271.4	191.6	204.7	529.1	175.8	840.5	192.8	234.1	357.6	613.4	559.9	478.5	431.7	593.0	611.4	337.7	449.2	561.0	374.3	333.0	494.5	616.0	439.4	369.1	430.5	240.8	598.0	911.8	259.1	272.3	366.2	327.8	153.0	177.0	462.6	397.7	327.9	1179.1	1184.9	733.4	1297.5	705.8	429.3
¥	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	30227.4	25805.7	27644.6	28506.9	28156.1	25979.3	17804.9	25938.9	25576.1	21640.7	23805.9	30636.7	26977.2	23651.3	23503.5	22075.5	22152.6	19910.2	26688.7	20038.7	25232.9	26169.4	31215.1	29367.7	33525.1	36729.6	31512.3	26282.5	26798.6	27366.5	25744.2	38321.0	18296.0	31113.6	35161.1
DY	4.769	4.473	3.364	3.326	3.259	1.883	4.597	2.772	3.632	4.031	7.495	6.631	6.283	4.283	6.773	6.294	4.766	6.189	088.9	5.873	99.9		4.619	6.335	14.502					_			_					3.948			9.520			12.555
CA	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	12128.9	16124.2	13070.2	9549.7	14424.1	16774.4	19442.3	14622.5	9619.9	14117.0	16787.5	13739.3	16097.2	18767.2	30873.0	18652.3	26428.5	21540.9	13994.1	11872.9	12734.2	13254.4	11281.5	14360.5	7569.0	6956.2	11920.3	13151.1	13080.2	14010.1	13553.9	8329.4	19024.2	31662.7	6831.1
BA	0.789	9.765	687.4	454.5	736.2	9.779	1028.8	7.196	446.6	1075.6	1241.1	1065.8	6.689	945.8	1267.3	1209.1	922.4	290.8	705.5	1066.5	1030.3	783.1	896.1	1298.1	721.4	601.7	799.4	823.7	557.7	9.799	644.0	883.6	0.688	412.7	818.0	1102.0	770.9	1012.1	938.1	820.1	921.4	926.5	1157.4	629.1
AL	99336.0	103919.6	69941.5	74300.0	97301.9	76247.9	75199.6	98893.0	71565.4		90574.8	90016.3	76422.6	73559.4	0.96667	78356.3	82823.0	77948.3	74948.1	87185.5	78672.6	81819.1	77897.3	75908.2	7.4307.7	72038.4	85469.0	76782.2	74692.8	87136.4	88152.0	85276.2	84297.5	108619.3	89568.2	94365.3		93304.0	86857.3	93678.2	81160.1	93477.9	82252.8	84528.9
ZR	172.2	165.9	`	_		99.2		110.0	145.1	196.0	320.0	306.8	476.3	358.9	326.8	302.6	318.6	369.0	465.7	271.9	251.4	453.2		271.7	414.4	361.4							260.4	207.8		251.4	161.0	190.5	201.5	200.2	265.5			228.0
ZN	63.9	52.3	46.8	54.1	78.9	46.9	83.9	59.4	56.2	64.5	79.4	85.6	122.4	72.1	97.6	73.7	80.7	74.7	87.5	82.0	79.9	8.98	98.1	79.8	77.9	79.0	87.6	93.4	83.2	69.7	58.5	94.0	61.9	58.5	111.0	84.2	86.0	8.89	92.4	71.5	74.0	71.0	75.9	72.7
TH	14.47		32.08	7				18.52	24.88	32.42	25.22	24.02	21.59	19.44	21.02	20.44	20.76	16.70	24.64	21.07	26.00	23.63		18.42		20.60					-							13.10			7			37.06
TA TE	0.9900 0.78	1.5300 0.59	1.6100 0.65			1.9900 0.47	0.7500 0.87	1.3200 0.67	1.7000 0.69	2.9342 0.73	2.8102 1.28	2.7677 1.22	3.7047 1.25	2.5394 0.97	2.5658 1.40	2.0564 1.30	2.1494 0.92	3.4069 1.16	3.3226 1.46	2.2270 1.01	2.5056 1.39	3.2387 1.34	4.7262 1.04	2.2358 1.19	2.4816 2.47	3.3480 1.41	2.2221 2.86	2.4251 1.93				_				1.0410 1.36	1.3725 0.78	1.2283 0.82	0.6836 0.75	1.3829 1.31	2.1018 1.60			2.7243 2.05
SR	0.0	0.0				0.0		0.0	0.0	362.7 2.	343.0 2.	302.7 2.	211.4 3.	369.7 2.	277.7 2.	207.9 2.0	288.7 2.	297.4 3.	259.3 3.	213.1 2.	360.0 2.	348.5 3.	579.4 4.	344.9 2.	257.1 2.	334.0 3.						_				201.6 1.0		390.9 1	304.4 0.	-				89.1 2.
SC	8.95	10.37	6.82	10.76	8.16	5.79	11.66	6.77	10.25	8.52	10.77	9.64	7.74	8.35	13.72	13.87	13.58	7.33	9.61	13.16	8.25		8.40	13.57	8.81	7.40				8.34							11.16	9.65	10.58					7.96
SB	0.6741				0.5803	0.6741		0.3925	0.6912	0.6602	0.4869	0.6778	0.8210	0.4304	0.6839	0.6369	0.6469	0.6213	0.7355	0.7843	0.6826		0.5996	0.5859	0.7487	0.7135			0.3733	0.4067	_		1.1213	0.8803				0.3781		0.3455			0.5870	0.4895
RB	129.00	150.10	193.50	174.20	111.10	239.10	73.90	132.60	168.80	130.91	99.04	140.21	137.40	115.90	122.90	06.66	141.10	108.20	135.90	118.60	124.50		95.40	116.20	131.70	100.40	117.70	103.00	128.80	139.70	149.10	216.70	115.70	254.00	234.70	138.10	168.00	98.70	126.60	124.00	236.00	91.70	118.00	285.10
Z	0.0					0.0		0.0	0.0	0.0	0.0	0.0	0.0	0.0	29.5	0.0	0.0	34.1	0.0	31.7	0.0	0.0	0.0	47.3	0.0	41.2											11.7	0.0	43.0					23.7
生	7.93	7.10	6.59	8.35	4.32	6.81	6.50	6.43	7.68	8.94	14.11	14.23	17.32	11.59	11.13	11.06	11.17	14.21	17.15	10.18	9.50	15.61	11.27	9.37	16.60	12.70	16.19	12.74	7.90	6.79	7.31	7.75	9.83	7.94	6.44	8.60	6.34	8.11	6.73	7.53	9.02	5.58	8.32	7.99
FE	23769.8	24169.1	22140.1	23217.2		17089.7	47647.3	18893.3	22184.1	41375.5	48663.3	40222.8	40200.7	38640.8	47187.8	46344.4	42118.1	31220.1	46966.7	41657.2	35962.6	46333.8	43661.5	41500.7	34494.5				34371.3	30320.6	26167.8	27378.8	21428.5	12635.7	23038.5	23617.8		34484.0	33115.6	28362.7	27669.6			23816.6
EU	1.6790				1.2220	0.6955		1.1525	0.9438	1.1231	2.1252	1.7674	1.6485	1.5210	1.7356	1.6097	1.2648	1.5229	2.3028	1.5305	2.0012	2.1811	2.0467	1.7805	1.8878	1.5932	1.9988						1.2632	0.5633				1.3920	1.3449	1.7480				1.4187
CS	6.26	22.40	11.09	19.03	6.37	12.83	2.97	4.43	19.90	4.44	3.28	5.14	4.92	3.64	5.11	5.36	2.69	4.51	5.01	5.40	3.58	4.53	3.96	5.15	4.64	4.27	5.75	3.30	4.53	4.72	15.79	8.98	6.42	23.19	9.20	5.46	7.69	3.66	20.28	5.02	5.53	2.88	4.08	7.34
ANID	TAM246	TAM247	TAM248	TAM249	TAM250	TAM251	TAM252	TAM253	TAM254	TRC002	TRC003	TRC006	UT00415	UT00416	UT00418	UT00419	UT00421	UT00422	UT00424	UT00425	UT00426	UT00427	UT00428	UT00430	UT00431	UT00434	UT00437	UT00438	UT00446	UT00447	UT00450	UT00451	UT00452	UT00454	UT00455	UT00456	UT00457	UT00458	UT00459	UT00460	UT00461	UT00462	UT00463	UT00464

ANID	macro_grp	Chem2012	CERAMIC TYPE	MATERIAL	SOURCE	STATE	SITE_NAME	SITE_NO	AS	ΓA	Π	ND	SM	n	YB C	CE CO	CR
UT00465	Group-A	Unas.	Mimbres Corrugated	Pottery	MURR	MN	Oops Village	LA 132649	3.36	163.17 1.	1.4113 14			5.31 11.	11.05 177.07	3.33	_
UT00466	Group-A	Mimbres-01	Mimbres B/W Style III	Pottery	MURR	NM	Oops Village	LA 132649	1.62	61.15 0.	0.4622 2			13.12 2.	2.88 98.57		4.87
UT00468	Group-A	Mimbres-10	Mimbres Corrugated	Pottery	MURR	MN	Oops Village	LA 132649	5.43		1.4988 7	73.06 15	15.93 5	5.16 10.54	54 119.14	3.77	31.71
UT00469	Group-C1	Mimbres-21	Mimbres B/W Style II/III	Pottery	MURR	MN	Oops Village	LA 132649	3.78	39.05 0.	0.3397 3		5.70	1.10 2.		10.63	
UT00477	Group-C1	Mimbres-21	Mimbres B/W Style III	Pottery	MURR	MN	Oops Village	LA 132649	6.10	41.29 0.	0.4448 3	37.64 6	6.44	1.98 3.	3.37 85.76	10.41	58.21
UT00478	Group-B1	Mimbres-04B	Mimbres B/W Style III	Pottery	MURR	NM	Oops Village	LA 132649	1.85	55.27 0.	0.6633 4	47.36 8	8.65	9.23 4.	4.00 97.42	12 4.13	27.30
UT00479	Group-B	Unas.	Mimbres Corrugated	Pottery	MURR	MN	Gap Village	LA 125819	4.31	49.40 0.	0.7925 5	51.77 9	9.18	5.49 5.	5.38 89.30	80 6.37	20.75
UT00480	Group-A	Mimbres-10	Mimbres Corrugated	Pottery	MURR	MN	Gap Village	LA 125819	2.82	41.31	1.1202 3	35.26 7	7.85 5	5.07 7.	7.70 70.21	21 3.86	25.45
UT00481	Group-A	Mimbres-10	Mimbres Corrugated	Pottery	MURR	MN	Gap Village	LA 125819	2.67	65.62 0.	0.6600 5	54.47 9	9.72	3.51 4.	4.55 126.81	31 4.64	23.46
UT00482	Group-B	Unas.	Mimbres Corrugated	Pottery	MURR	MN	Gap Village	LA 125819	3.21	46.47 0.	0.7906 4	42.35 8	8.83	5.06 5.	5.33 82.87	37 3.98	1 21.26
UT00483	Group-B1	Mimbres-04B	Mimbres B/W Style II	Pottery	MURR	MN	Gap Village	LA 125819	3.65	53.72 0.	0.6372 4	43.50 7	7.75 6	6.05 3.	3.99 93.98	7.34	7.97
UT00484	Group-C1	Mimbres-22	Mimbres B/W Style II	Pottery	MURR	MN	Gap Village	LA 125819	2.62	41.59 0.	0.2965 3	35.21 5	5.50	1.40 2.	2.23 82.23	23 6.75	12.93
UT00485	Group-A	Mimbres-10	Three Circle Corrugated	Pottery	MURR	MN	Gap Village	LA 125819	4.97	37.68 0.	0.8172 2	25.56 5	5.64 4	4.97 5.	5.33 79.76	4.44	31.39
UT00486	Group-A	Mimbres-10	Three Circle Corrugated	Pottery	MURR	¥	Gap Village	LA 125819	2.98	102.52 1.	1.3740 9	91.74 17	17.38 5	5.73 10.	10.45 137.49	3.60	16.36
UT00489	Group-A	Mimbres-10	Mimbres Corrugated	Pottery	MURR	MN	Turkey Knob Pueblo	LA 120756	3.48	113.30 1.	1.0283 10	101.89 19	19.03	7.75 7.	7.13 188.29	06.9 6	34.03
UT00490	Group-B1	Mimbres-04B		Pottery	MURR	MN	Turkey Knob Pueblo	LA 120756	00.00					7.63 4.	_		23.55
UT00491	Group-C1	Mimbres-21	Mimbres B/W Style III	Pottery	MURR	MN	Turkey Knob Pueblo	LA 120756	2.42	39.60 0	0.3301 3	37.62 5	5.79	1.76 2.	2.54 80.86	9.14	34.91
UT00493	Group-A	Unas.	Plain	Pottery	MURR	MN	Turkey Knob Pueblo	LA 120756	6.09	204.02	1.5933 17	175.13 30	30.00	10.03 10.87	87 280.93	7.11	21.97
UT00547	Group-D	El Paso Core	El Paso Plain	Pottery	MURR	ĭ	41PS00003 (45C5-6)	41PS00003	7.46	49.27 0.	0.5191 3	35.35 7	7.02	3.35 3.	3.43 85.22	6.69	38.61
UT00548	Group-D	El Paso Core	El Paso Plain	Pottery	MURR	ĭ	41PS00003 (45C5-6)	41PS00003	4.97	66.33 0.	0.6261 5	52.24 10	10.25	3.37 4.	4.31 131.10	10.51	28.30
UT00549	Group-D	El Paso Core	El Paso Polychrome	Pottery	MURR	XX	41PS00003 (45C5-6)	41PS00003	6.55	60.12 0.		48.30 9		4.41 4.	4.89 114.10	10 5.44	29.06
UT00550	Group-D	El Paso Core	El Paso Polychrome	Pottery	MURR	ĭ	41PS00003 (45C5-6)	41PS00003	8.71	57.10 0.	0.5596 4	48.12 9	9.32	4.51 4.	4.64 110.12	12 5.73	30.90
UT00551	Group-D	El Paso Core	El Paso Polychrome	Pottery	MURR	ĭ	41PS00003 (45C5-6)	41PS00003	3.63	120.58 0.	0.7850 8	84.14 14	14.17	3.52 6.	6.41 201.06	10.29	24.61
UT00555	G-dno-D	El Paso Core	El Paso Polychrome	Pottery	MURR	Ϋ́	41PS00005 (45C2-2)	41PS00005	5.83	70.46 0.	0.6415 5	57.66 10		4.34 4.	4.49 144.03	3 10.49	
UT00562	Group-D	El Paso Core	El Paso Polychrome	Pottery	MURR	TX	41PS00007 (45C8-1)	41PS00007	2.52	63.21 0.	0.4562 5		9.22 4		3.30 103.20	50 6.83	28.63
UT00566	Group-D	El Paso Core	El Paso Polychrome	Pottery	MURR	XX	41PS00008 (45C5-10)	41PS00008	4.31	63.21 0.		50.64 8		3.94 3.	3.33 109.80		27.30
UT00567	Group-D	El Paso Core	El Paso Plain	Pottery	MURR	TX	41PS00008 (45C5-10)	41PS00008	6.59	72.45 0.	0.6381 6	64.09 11	11.58 3.	3.34 5.	5.58 135.06	8.92	25.85
UT00573	G-dno-D	El Paso Core		Pottery	MURR	Ϋ́		41PS00011	4.91			_					
UT00577	Group-D	El Paso Core	chrome	Pottery	MURR	ĭ	41PS00012 (57D2-2)	41PS00012	5.41						5.85 139.25	1	
UT00582	Group-D	El Paso Core	El Paso Plain	Pottery	MURR	Ϋ́	Millington	41PS00014	6.81						4.11 131.84		
UT00583	Group-D	El Paso Core	El Paso Plain	Pottery	MURR	ĭ	Millington	41PS00014	5.54						_		
UT00584	Group-D	El Paso Core	El Paso Polychrome	Pottery	MURR	ĭ	Millington	41PS00014	7.52						3.10 89.14		
UT00585	Group-D	El Paso Core	El Paso Polychrome	Pottery	MURR	ĭ	Millington	41PS00014	8.15								25.97
UT00639	Group-D	El Paso Core	El Paso Polychrome	Pottery	MURR	ĭ	Millington	41PS00014	4.67			64.87 11				99.9	
UT00640	Group-D	El Paso Core	El Paso Polychrome	Pottery	MURR	ΤX	Millington	41PS00014	7.66		0.7097 6			4.73 4.	4.89 153.72		
UT00644	Group-D	El Paso-2	El Paso Plain	Pottery	MURR	TX	41PS00005 (45C2-2)	41PS00005	97.9			_			1		57.07
UT00758	Group-C1	Mimbres-21	Mimbres B/W Style III	Pottery	MURR	NM	Old Town	LA 001113	1.74					1.53 2.		11.81	
UT00759	Group-B1	Mimbres-04A	Mimbres B/W Style II	Pottery	MURR	NM	Old Town	LA 001113	2.59	57.59 0.	0.6107 4	48.38 9	9.50 6	6.67 4.	4.99 120.87	37 10.18	22.22
UT00762	Group-C1	Unas.	Reserve Smudged Corrugal Pottery	(Pottery	MURR	NM	Old Town	LA 001113	3.29	45.35 0.	0.5718 3		7.72 3.	3.51 4.	4.48 83.55	55 11.74	1
UT00775	Group-A	Mimbres-01	Mimbres B/W Style II	Pottery	MURR	M	Old Town	LA 001113	0.00			21.37 4		14.44 2.			
UT00776	Group-B2	Mimbres-02A	Mimbres B/W Style III	Pottery	MURR	NM	Old Town	LA 001113	1.58		0.5608 3	36.66 7	7.22 5.	5.43 3.	3.70 86.90	90 8.11	39.27
UT00778	Group-D	El Paso Core		Pottery	MURR	MM	Old Town	LA 001113	5.37						1		
UT00779	Group-C2a	Mimbres-49A		Pottery	MURR	M	Old Town	LA 001113	4.21	_						_	
UT00785	Group-B1	Mimbres-04C	Three Circle Corrugated	Pottery	MURR	M	Old Town	LA 001113	1.95	38.07 0.	0.4565 3	30.81 6	6.02	2.93 3.	3.17 75.61	9.69	29.21

519 202.4 114936.4 6A6.3 6A29.5 2958 37776.7 2775 12134.4 1265.7 745 2406 88237.9 15.640 3589 264110 1317.1 17096.9 80.9 179.7 97337.1 10070.4 650.9 15.26 2827.9 14.27 2847.9 14.27 2847.9 14.27 2847.9 14.27 2847.9 14.27 2847.9 14.27 2847.9 14.27 2847.9 14.27 2847.9 14.27 14.27 2847.9 14.27 14.27 2847.9 14.27 14.27 14.27 14.27 14.28 14.27 14.28 14.27 14.28 14.27 14.28 14.27 14.28 14.24 <th>CS EU FE HF NI RB SB SC SR TA TB TB TH 793 3.2194 33859.8 12.72 0.0 280.40 0.3002 12.05 90.5 2.0035 4.25 56.08</th> <th>FE HF NI RB SB SC SR TA TB 33859.8 12.72 0.0 280.40 0.3002 12.05 90.5 2.0035 4.25</th> <th>HF NI RB SB SC SR TA TB 12.72 0.0 280.40 0.3002 12.05 90.5 2.0035 4.25</th> <th>NI RB SB SC SR TA TB 0.0 280.40 0.3002 12.05 90.5 2.0035 4.25</th> <th>RB SG SR TA TB TB 280.40 0.3002 12.05 90.5 2.0035 4.25</th> <th>SB SC SR TA TB TB 0.3002 12.05 90.5 2.0035 4.25</th> <th>SC SR TA TB 12.05 90.5 2.0035 4.25</th> <th>SR TA TB 90.5 2.0035 4.25</th> <th>TA TB 2.0035 4.25</th> <th>TB 4.25</th> <th></th> <th>56.0</th> <th>王 8</th> <th>NZ 6.96</th> <th>ZR 359.1</th> <th>AL 88870.0</th> <th>BA 590.4</th> <th>CA 4948.5</th> <th>DY 23.256</th> <th>K 34459.7</th> <th>MN 118.4</th> <th>NA 10487.7</th> <th>TI 2690.3</th> <th>V 34.40</th>	CS EU FE HF NI RB SB SC SR TA TB TB TH 793 3.2194 33859.8 12.72 0.0 280.40 0.3002 12.05 90.5 2.0035 4.25 56.08	FE HF NI RB SB SC SR TA TB 33859.8 12.72 0.0 280.40 0.3002 12.05 90.5 2.0035 4.25	HF NI RB SB SC SR TA TB 12.72 0.0 280.40 0.3002 12.05 90.5 2.0035 4.25	NI RB SB SC SR TA TB 0.0 280.40 0.3002 12.05 90.5 2.0035 4.25	RB SG SR TA TB TB 280.40 0.3002 12.05 90.5 2.0035 4.25	SB SC SR TA TB TB 0.3002 12.05 90.5 2.0035 4.25	SC SR TA TB 12.05 90.5 2.0035 4.25	SR TA TB 90.5 2.0035 4.25	TA TB 2.0035 4.25	TB 4.25		56.0	王 8	NZ 6.96	ZR 359.1	AL 88870.0	BA 590.4	CA 4948.5	DY 23.256	K 34459.7	MN 118.4	NA 10487.7	TI 2690.3	V 34.40
2.48 4.66 7.45 2.40 6.838.37 684.9 6.60.39 15.640 338.34 10.04 2.24 4.66 7.45 2.40 6.80.3 17.04 13.0 9.0 17.0 9.0 97.0 97.0 1 2.66 19.1 13.3 80.9 17.0 9.88.7 1.0 1.20 1.0 1.20 80.9 17.0 9.88.7 1.24 1.20 1.1 1.0 1.0 1.20 8.0 17.0 9.0 1.0	0.5237 11794.8 6.99 0.0 278.30 0.6572 4.62 99.4	11794.8 6.99 0.0 278.30 0.6572 4.62 99.4	6.99 0.0 278.30 0.6572 4.62 99.4	0.0 278.30 0.6572 4.62 99.4	278.30 0.6572 4.62 99.4	0.6572 4.62 99.4	4.62 99.4	99.4		2.58		0.40	56.84		202.4	114936.4	676.3	6429.5	2.958	37776.7	277.5	13174.4	1265.5	20.20
0.82 1.13 8.8.6 9.74.31 1.8.5 9.74.31 1.8.5 9.74.31 1.8.5 9.74.31 1.10.00 9.7.8.7 1.10 28.30 66.6 1.91.2 10.024.0 48.7.7 9.48 1.43.9 301.6 1.097.2 327.8 1.13 24.41 95.1 18.2.2 10.234.0 1.34.3 1.73.0 28.5 1.04	1.7398 28491.8 8.46 0.0 279.40 0.6112 9.14 140.3	28491.8 8.46 0.0 279.40 0.6112 9.14 140.3	8.46 0.0 279.40 0.6112 9.14 140.3	0.0 279.40 0.6112 9.14 140.3	279.40 0.6112 9.14 140.3	0.6112 9.14 140.3	9.14 140.3	140.3		2.734			46.67		240.6	88383.7	684.9	6203.9	15.640	33394.1	215.7	12484.7	2963.3	53.00
1.10 28.30 6.66 1915 100704 66.09 8427.9 64.55 28787.8 253.4 1097.2 328.9 146.9 13.2 24.4 199.1 100736.0 13.3 13.4 64.1 199.1 10036.0 13.3 13.4 64.1 199.1 10036.0 13.3 13.4 64.1 199.1 8936.1 13.3 189.2 10.236.0 13.3 13.4 64.1 199.1 8936.1 20.2 15.2 33.9 95.0 38.2 10.6 10.0 28.2 10.6 97.2 10.0	14.99 1.2753 2/625.3 6.56 0.0 116.80 1.3542 7.31 417.8 0.6372 19.43 1.4261 28698.7 7.87 32.0 157.70 2.6327 8.00 362.8 0.9605	2/625.3 6.56 0.0 116.80 1.5342 7.31 417.8 28698.7 7.87 32.0 157.70 2.6327 8.00 362.8	0.50 0.0 116.80 1.3342 7.31 417.8 7.87 32.0 157.70 2.6327 8.00 362.8	32.0 157.70 2.6327 8.00 362.8	157.70 2.6327 8.00 362.8	2.6327 8.00 362.8	8.00 362.8	362.8).960!).960!			11.39		179.7	93837.9	847.7	9498.1	4.379	30916.3	950.3	17291.1	2972.8	53.20
1.31 2.44 96.1 182.2 10.264.0 14.33 16.33 9 13.80 38.0 166.10 314.6 1.31 2.1.34 6.1 182.1 182.2 10.264.0 18.33 1.7 20.53 36.0 10.0 20.20 1.8 10.0 20.20 1.8 10.0 20.20 1.8 10.0 20.20 1.8 10.0 20.20 1.8 10.0 20.0 <td>1.4574 24874.9 6.68 0.0 175.90 0.4461 8.95 165.4</td> <td>24874.9 6.68 0.0 175.90 0.4461 8.95 165.4</td> <td>6.68 0.0 175.90 0.4461 8.95 165.4</td> <td>0.0 175.90 0.4461 8.95 165.4</td> <td>175.90 0.4461 8.95 165.4</td> <td>0.4461 8.95 165.4</td> <td>8.95 165.4</td> <td>165.4</td> <td></td> <td>1.5608</td> <td></td> <td></td> <td>28.30</td> <td></td> <td>191.5</td> <td>100770.4</td> <td>620.9</td> <td>8427.9</td> <td>6.455</td> <td>28787.8</td> <td>253.4</td> <td>10972.7</td> <td>3278.9</td> <td>54.90</td>	1.4574 24874.9 6.68 0.0 175.90 0.4461 8.95 165.4	24874.9 6.68 0.0 175.90 0.4461 8.95 165.4	6.68 0.0 175.90 0.4461 8.95 165.4	0.0 175.90 0.4461 8.95 165.4	175.90 0.4461 8.95 165.4	0.4461 8.95 165.4	8.95 165.4	165.4		1.5608			28.30		191.5	100770.4	620.9	8427.9	6.455	28787.8	253.4	10972.7	3278.9	54.90
1.33 46.1 199.1 8936.1.5 70.3 31.94 41.1 1308.0. 210.1 1.21 51.30 86.3 20.4 929.24.6 93.3 889.4.3 71.4 71.1 71.2 72.93 859.5.0 71.8 71.1 71.2 72.3 31.9 72.3 31.9 72.3 31.9 72.3 31.9 72.3 31.9 72.2 32.3 19.8 10.8 92.3 10.8 92.3 10.8 92.3 10.8 92.3 10.8 92.3 10.8 92.3 10.8 92.3 10.8 92.3 10.8 92.3 10.8 92.3 10.8 10.3 10.8 10	1.6012 36473.0 6.81 0.0 147.60 0.6541 10.20 301.0	36473.0 6.81 0.0 147.60 0.6541 10.20 301.0	6.81 0.0 147.60 0.6541 10.20 301.0	0.0 147.60 0.6541 10.20 301.0	147.60 0.6541 10.20 301.0	0.6541 10.20 301.0	10.20 301.0	301.0		2.195	0	_	24.41	_	182.2	102364.0	1343.3	16733.6	7.316	32870.0	398.0	16610.9	3146.9	52.30
1.21 51.30 85.3 207.6 92924.6 931.3 881.27 7.320 37199.7 229.3 959.6 1.318.8 1.27 2.23.3 95.1 97.6 96.5 96.93.8 3.191 234.7 1.08.0 22.8 1.08.0 1.27 2.23.3 95.1 19.5 99.6 3.99.7 1.08.0 99.6 3.99.7 1.08.0 99.6 3.99.7 1.08.0 99.7 1.08.0 99.6 3.99.7 1.08.0 99.7 1.08.0 99.6 99.6 3.99.7 1.09.9 97.1 1.08.0 99.7 4.0.9 1.09.7 1.09.0 97.1 4.0.0 1.09.9 97.1 4.0.0 1.09.8 4.0.0 1.00.0 99.0 4.0.0 99.0 4.0.0 99.0 4.0.0 99.0 4.0.0 99.0 4.0.0 99.0 4.0.0 99.0 4.0.0 99.0 4.0.0 99.0 4.0.0 99.0 4.0.0 99.0 4.0.0 99.0 4.0.0 99.0 4.0.0	0.9661 24629.2 7.66 0.0 298.50 0.4643 8.16 114.1	24629.2 7.66 0.0 298.50 0.4643 8.16 114.1	7.66 0.0 298.50 0.4643 8.16 114.1	0.0 298.50 0.4643 8.16 114.1	298.50 0.4643 8.16 114.1	0.4643 8.16 114.1	8.16 114.1	114.1		2.221	9		31.34		199.1	89361.5	703.3	5894.3	9.154	35287.4	174.1	13087.0	2102.1	46.10
1.27 2.5.3 9.9.5 19.19 97866.5 861.5 1395.8 1.046 2856.9 27.21 10481.5 27.31 10.0 25.73 10.0 25.73 10.0 25.73 10.0 25.73 10.0 25.73 10.0 26.0 36226.8 27.31 11889.4 1780.1 20.34 27.34 10.0 97.34 0.0 3622.8 22.37 11807.0 2093.6 20.0 3622.8 22.37 11807.0 2093.6 27.34 20.0 362.8 23.34 47.1 1307.0 219.3 2.69 56.0 7.0 1199.3 816.11.9 967.6 6376.2 16.42 36.8 47.1 1307.0 217.7 23.0 21.3 10.0 217.7 24.0 10.0 22.1 10.0 20.3 24.2 26.3 10.1 24.0 10.0 20.0 26.2 10.0 21.0 20.0 20.0 20.0 20.0 20.0 20.0 20.0 20.0 20.0	0.9899 30707.4 9.78 0.0 230.20 0.3952 10.03 176.7	30707.4 9.78 0.0 230.20 0.3952 10.03 176.7	9.78 0.0 230.20 0.3952 10.03 176.7	0.0 230.20 0.3952 10.03 176.7	230.20 0.3952 10.03 176.7	0.3952 10.03 176.7	10.03 176.7	176.7		1.210		_	51.30		207.6	92924.6	931.3	8812.7	7.320	37199.7	229.3	9595.0	2137.8	55.80
1.06 25.74 745 1495 94930.7 623.5 6.100 28390.0 492.7 1886.6 2734.3 0.66 9.71 80.0 158.6 92931.9 996.6 36392.8 3.191 223.2 13.3 13091.0 2175.7 2.69 56.92 70.4 199.3 87611.9 96.6 6376.2 16.642 36581.2 163.3 13091.0 2175.7 2.69 56.92 70.4 199.3 87611.9 96.6 6376.2 16.642 36581.2 13331.3 13091.0 2175.7 2.69 56.92 70.4 199.3 87611.9 96.6 6376.2 16.647 36581.0 1370.9 177.7	1.4869 25687.0 8.61 0.0 165.70 0.4228 8.56 270.0	25687.0 8.61 0.0 165.70 0.4228 8.56 270.0	8.61 0.0 165.70 0.4228 8.56 270.0	0.0 165.70 0.4228 8.56 270.0	165.70 0.4228 8.56 270.0	0.4228 8.56 270.0	8.56 270.0	270.0		2.012			22.53		191.9	97866.5	861.5	13957.8	7.646	28556.9	292.8	16481.5	2281.3	45.60
0.69 9.71 80.0 158.6 29291.9 996.6 36939.8 3.191 32434.7 745.9 11899.4 1780.1 0.97 3.42.0 96.0 115.2 91230.1 1080.0 165.2 36826.2 23.2 11807.0 2093.6 2.97 3.42.0 96.0 115.2 91230.1 1080.0 15.283 31090.0 2274.6 18.9 3150.0 26.0 313.3 3100.0 2074.6 89.0 3150.0 447.1 1303.0 250.7 20.0 20.0 20.0 20.0 20.0 20.0 20.0 20.0 20.0 310.0	1.3701 25137.7 6.61 0.0 184.20 0.4611 8.45 157.3	25137.7 6.61 0.0 184.20 0.4611 8.45 157.3	6.61 0.0 184.20 0.4611 8.45 157.3	0.0 184.20 0.4611 8.45 157.3	184.20 0.4611 8.45 157.3	0.4611 8.45 157.3	8.45 157.3	157.3		1.437			25.74		149.5	94930.7	623.5	9639.3	6.100	28390.0	492.7	10896.6	2734.3	48.10
0.97 34.20 95.0 115.2 9120.1 1080.0 7996.7 6.099 36226.8 22.3 7 1807.0 2795.7 2.69 56.52 70.4 4.99 3 10113.4 77.01 10594.9 15.642 36857.2 16.3 31091.0 2775.7 1.18 26.58 4.11 1303.2 943.4 56.3 3179.1 147.1 1303.9 2571.3 1.8 26.58 4.11 1303.2 943.4 56.6 3175.0 447.1 1309.10 2175.7 1.8 26.58 4.10.9 92714.6 814.7 31645.9 3379.2 147.1 1300.9 2774.6 814.7 31645.9 3271.4 4865.5 2082.1 447.1 1260.9 32714.6 814.7 31645.9 3271.4 4865.5 2082.5 862.1 170.4 1260.0 3337.7 401.6 883.6 437.7 401.6 883.7 401.6 883.7 401.6 883.6 431.6 444.1 144.4 1	1.2951 19787.8 6.22 14.5 157.30 4.8950 4.78 304.8	19787.8 6.22 14.5 157.30 4.8950 4.78 304.8	6.22 14.5 157.30 4.8950 4.78 304.8	14.5 157.30 4.8950 4.78 304.8	157.30 4.8950 4.78 304.8	4.8950 4.78 304.8	4.78 304.8	304.8).599(9.71		158.6	92931.9	9.966	36939.8	3.191	32434.7	745.9	11889.4	1780.1	50.10
2.69 56.22 70.4 1993 876119 967.6 6376.2 16.42 33681.2 16.33 130910 2775.7 2.49 42.29 111.9 188.3 101137 470.1 10594.9 15.283 31083.6 447.1 13703.9 2570.3 0.68 10.69 66.4 103.2 92714.6 814.7 3146.5 86.8 10.61 1250.2 1272.1 1250.2 1175.0 447.1 13703.9 2570.3 0.68 10.69 66.4 1009.1 1167.9 1278.6 126.2 1054.4 13913.1 249.9 1.15 23.2 71.2 393.4 970.6 1147.9 1278.4 4865.2 106.1 107.8 107.1 1279.4 1479.5 107.2	0.8064 26674.7 5.50 0.0 239.40 0.5036 9.58 167.0	26674.7 5.50 0.0 239.40 0.5036 9.58 167.0	5.50 0.0 239.40 0.5036 9.58 167.0	0.0 239.40 0.5036 9.58 167.0	239.40 0.5036 9.58 167.0	0.5036 9.58 167.0	9.58 167.0	167.0		2.1006	-+		34.20		115.2	91230.1	1080.0	7996.7	6.009	36226.8	223.7	11807.0	2093.6	53.50
2.49 42.91 111.9 188.3 101137.4 770.1 10594.9 15.283 31083.6 447.1 1370.3 251.0 1.18 26.58 49.4 133.2 943.4 15.283 347.4 6.66 3175.10 48.4 1250.6 95.7 0.68 10.24 190.9 2714.6 184.7 1865.2 895.1 7125.6 48.4 1250.6 95.7 3.84 69.2 11.2 387.9 10.6 17.9 49.8 1447.9 1221.8 14.65.2 17.0 48.4 1250.6 48.4 1250.6 17.0 48.4 1250.6 17.1 48.4 1250.6 17.1 48.4 1250.6 13.8 38.0 17.1 14.9 18.6 19.3 17.1 14.4 17.0 14.4 14.1 18.1 18.2 17.0 48.4 1250.6 17.0 17.1 17.1 17.1 18.2 17.0 17.0 17.0 17.0 17.0 17.0 17.0	1.4896 28380.0 9.65 0.0 254.50 0.3005 9.52 114.5	28380.0 9.65 0.0 254.50 0.3005 9.52 114.5	9.65 0.0 254.50 0.3005 9.52 114.5	0.0 254.50 0.3005 9.52 114.5	254.50 0.3005 9.52 114.5	0.3005 9.52 114.5	9.52 114.5	114.5		4.3917	_		56.92		199.3	87611.9	9.796	6376.2	16.642	36587.2	163.3	13091.0	2175.7	40.50
1.18 2.6.58 49.4 133.2 9143.6.4 59.3 943.7.4 6.667 31751.0 48.4.4 150.6.9 285.7 0.68 10.69 69.4 190.9 92714.6 814.7 31645.9 3.919 27229.8 105.4.4 1393.13 2429.9 3.84 10.69 10.21 10.21 12.22.6.5 895.1 712.6.2 289.1 1.15 23.92 91.5 377.9 86435.2 130.16 380.5.5 6.72 2102.7 724.7 19480.6 737.4 1.16 22.37 7.45 281.5 9900.0 1229.5 1569.4 6.02 2102.1 488.1 168.1 1.17 18.29 86.3 490.6 1927.7 124.1 48.4 188.3 17.1 17.1 17.1 17.1 17.1 17.2 18.2 17.1 18.2 17.1 17.1 17.1 17.1 18.9 86.3 18.0 17.1 17.1 17.1 17.1 17.1	1.8550 35706.7 7.21 0.0 244.20 0.5397 12.22 121.2	35706.7 7.21 0.0 244.20 0.5397 12.22 121.2	7.21 0.0 244.20 0.5397 12.22 121.2	0.0 244.20 0.5397 12.22 121.2	244.20 0.5397 12.22 121.2	0.5397 12.22 121.2	12.22 121.2	121.2	٠,	3.2527			42.91		188.3	101137.4	770.1	10594.9	15.283	31083.6	447.1	13703.9	2510.3	51.40
0.68 69.4 190.9 92774.6 814.7 31645.9 3.919 27229.8 1054.4 13913.1 2429.9 3.84 69.22 112.8 289.1 110981.4 1051.9 8226.5 20.821 46852.5 895.1 7126.4 2420.6 1.0.8 19.34 77.9 393.4 9256.4 1147.9 1221.8 4862.5 885.1 7126.4 2841.6 1.16 20.28 91.5 318.3 87021.8 1188.9 1541.9 6.72.9 1002.7 724.7 19480.6 7101.4 1.16 20.39 90.7 318.3 87021.8 1188.9 1641.9 6.02.0 1002.7 724.7 19480.6 710.1 1.17 18.99 86.3 400.6 83970.9 1072.7 1267.8 16941.0 687.0 1448.8 16445.4 420.5 1.13 21.59 88.4 1087.7 1046.6 2400.0 148.8 1464.1 1470.6 1470.6 1470.0 <td< td=""><td>1.4523 23226.2 5.89 25.6 180.00 0.4066 7.81 140.3</td><td>23226.2 5.89 25.6 180.00 0.4066 7.81 140.3</td><td>5.89 25.6 180.00 0.4066 7.81 140.3</td><td>25.6 180.00 0.4066 7.81 140.3</td><td>180.00 0.4066 7.81 140.3</td><td>0.4066 7.81 140.3</td><td>7.81 140.3</td><td>140.3</td><td>`</td><td>1.5203</td><td></td><td></td><td>26.58</td><td></td><td>133.2</td><td>91436.4</td><td>593.3</td><td>9437.4</td><td>6.667</td><td>31751.0</td><td>484.4</td><td>12506.9</td><td>2857.7</td><td>50.40</td></td<>	1.4523 23226.2 5.89 25.6 180.00 0.4066 7.81 140.3	23226.2 5.89 25.6 180.00 0.4066 7.81 140.3	5.89 25.6 180.00 0.4066 7.81 140.3	25.6 180.00 0.4066 7.81 140.3	180.00 0.4066 7.81 140.3	0.4066 7.81 140.3	7.81 140.3	140.3	`	1.5203			26.58		133.2	91436.4	593.3	9437.4	6.667	31751.0	484.4	12506.9	2857.7	50.40
3.84 69.22 112.8 289.1 110981.4 1051.9 8226.5 20.821 4685.2.5 895.1 7125.4 2841.6 0.85 19.34 77.9 393.4 92960.4 147.9 12218.4 4.865 3337.9 401.6 18356.8 4327.9 1.15 23.32 91.5 377.9 8543.2 1931.6 486.5 1837.9 41.1 1938.1 426.4 1843.1 426.1 1.10 20.37 74.5 281.5 90900.6 1229.5 1564.1 6.612 24002.1 448.1 1681.4 426.1 1905.4 825.0 1.13 21.59 88.4 400.6 18370.9 16.612 24002.1 4645.4 1841.4 4240.5 1.09 1.20 19081.4 6.612 24002.1 4645.4 1841.4 4240.5 1.00 1.20 1902.2 12841.1 16.612 2400.0 16.412.4 1400.5 1400.5 1400.6 1400.7 1400.1	15.70 1.3247 27209.0 6.67 0.0 124.50 1.1676 7.09 358.0 0.7996	27209.0 6.67 0.0 124.50 1.1676 7.09 358.0	6.67 0.0 124.50 1.1676 7.09 358.0	0.0 124.50 1.1676 7.09 358.0	124.50 1.1676 7.09 358.0	1.1676 7.09 358.0	7.09 358.0	358.0		3.7996			10.69		190.9	92714.6	814.7	31645.9	3.919	27229.8	1054.4	13913.1	2429.9	61.10
0.85 19.34 77.9 393.4 92960.4 1147.9 12218.4 4.856 3377.9 401.6 1835.6.8 4327.9 1.15 23.92 91.5 377.9 85435.2 1391.6 38705.5 6.729 1002.7 724.7 19480.6 7191.4 1 1.08 20.58 69.7 318.3 87021.8 1188.9 15419.9 6.801 23188.1 426.4 18431.7 426.5 1.71 18.99 86.3 490.6 89970.9 1072.7 12672.8 10.046 2940.0 664.8 16445.4 520.4 1.71 18.99 86.3 1094.9 1072.7 12672.8 1094.0 1095.4 148.8 1465.0 1095.4 14445.4 520.4 4005.5 1097.5 1445.8 1445.8 1445.8 1445.8 1445.8 1445.8 1445.8 1445.8 1445.8 1445.8 1445.8 1445.8 1445.8 1445.9 1445.9 1445.8 1445.9 1445.9 1445.9 </td <td>17.72 2.6009 32976.5 10.74 0.0 337.00 0.9240 11.27 140.9 2.4246</td> <td>32976.5 10.74 0.0 337.00 0.9240 11.27 140.9</td> <td>10.74 0.0 337.00 0.9240 11.27 140.9</td> <td>0.0 337.00 0.9240 11.27 140.9</td> <td>337.00 0.9240 11.27 140.9</td> <td>0.9240 11.27 140.9</td> <td>11.27 140.9</td> <td>140.9</td> <td></td> <td>2.4246</td> <td></td> <td></td> <td>69.22</td> <td></td> <td>289.1</td> <td>110981.4</td> <td>1051.9</td> <td>8226.5</td> <td>20.821</td> <td>46852.5</td> <td>895.1</td> <td>7125.4</td> <td>2841.6</td> <td>59.10</td>	17.72 2.6009 32976.5 10.74 0.0 337.00 0.9240 11.27 140.9 2.4246	32976.5 10.74 0.0 337.00 0.9240 11.27 140.9	10.74 0.0 337.00 0.9240 11.27 140.9	0.0 337.00 0.9240 11.27 140.9	337.00 0.9240 11.27 140.9	0.9240 11.27 140.9	11.27 140.9	140.9		2.4246			69.22		289.1	110981.4	1051.9	8226.5	20.821	46852.5	895.1	7125.4	2841.6	59.10
1.15 23.92 91.5 377.9 85435.2 1391.6 38705.5 6.729 21002.7 724.7 19480.6 7191.4 1.08 20.58 69.7 318.3 87021.8 1188.9 15419.9 6.801 23188.1 426.4 18431.7 420.5 1.10 22.37 74.5 281.5 90900.6 1229.5 15694.1 6.612 24002.1 448.8 16445.4 520.4 1.71 18.99 86.3 490.6 83870.9 1072.7 1660.4 2409.0 657.8 16445.4 5270.4 1.71 18.99 86.3 490.6 83870.9 1072.7 1660.4 2409.0 657.8 1848.4 1820.7 96.6 19055.4 6820.0 1820.0 19055.4 1820.0 1820.0 19055.4 1820.0 1820.0 1820.0 1820.0 1820.0 1820.0 1820.0 1820.0 1820.0 1820.0 1820.0 1820.0 1820.0 1820.0 1820.0 1820.0 182	3.87 1.4843 36448.0 14.22 0.0 117.37 0.5989 9.07 313.9 3.1975	36448.0 14.22 0.0 117.37 0.5989 9.07 313.9	14.22 0.0 117.37 0.5989 9.07 313.9	0.0 117.37 0.5989 9.07 313.9	117.37 0.5989 9.07 313.9	0.5989 9.07 313.9	9.07 313.9	313.9		3.1975			19.34		393.4	92960.4	1147.9	12218.4	4.856	33377.9	401.6	18356.8	4327.9	83.94
20.58 69.7 318.3 87021.8 1188.9 15419.9 6.801 2318.1 426.4 18431.7 4261.5 22.37 74.5 281.5 90900.6 1229.5 15694.1 6.612 2400.1 448.8 16814.4 4240.5 18.99 86.3 490.6 83970.9 1072.7 12672.8 10.046 2940.0 654.8 16445.4 5270.4 21.59 88.4 408.7 86887.9 1087.5 19541.1 6.61.2 19055.4 6825.0 18.24 72.4 2825.8 1488.3 10819.9 5.65 2818.4 34.0 19796.1 5186.0 18.28 72.4 92829.4 1187.2 24036.9 5.98 28338.1 60.3.9 19586.2 1839.0 18.78 71.4 332.9 92829.4 1169.0 20896.5 8333.2 60.3.9 19586.2 1839.0 17.96 83.2 264.4 9056.9 1769.0 2344.4 786.4 19529.1	3.58 2.0044 45752.7 15.15 35.5 104.90 0.5089 9.99 976.8 3.8248	45752.7 15.15 35.5 104.90 0.5089 9.99 976.8	15.15 35.5 104.90 0.5089 9.99 976.8	35.5 104.90 0.5089 9.99 976.8	104.90 0.5089 9.99 976.8	0.5089 9.99 976.8	8.976 99.9	8.9/6		3.8248	i .		23.92		377.9	85435.2	1391.6	38705.5	6.729	21002.7	724.7	19480.6		108.61
1.16 22.37 74.5 281.5 9090.06 1229.5 15694.1 6.612 2400.0 448.8 16814.4 4240.5 1.71 18.99 86.3 490.6 83370.9 1072.7 12672.8 10.046 2940.0 654.8 16445.4 5270.4 1.13 21.59 88.4 408.7 1087.5 1767.1 67.6 19055.4 682.0 0.97 15.74 88.7 1087.5 168.3 10819.9 5.66 2818.4 349.0 19796.1 580.0 0.97 18.74 72.4 282.5 844.5 10819.9 5.66 2818.4 349.0 1490.5 580.0 19796.1 580.0 19796.1 5180.0 19796.1 5180.0 19796.1 5180.0 19796.1 5180.0 19796.1 5180.0 5180.0 5180.0 5180.0 5180.0 5180.0 5180.0 5180.0 5180.0 5180.0 5180.0 5180.0 5180.0 5180.0 5180.0 5180.0 5180.0 <td>3.66 1.7870 38491.1 13.29 22.4 108.59 0.5790 9.04 506.4 2.6849</td> <td>38491.1 13.29 22.4 108.59 0.5790 9.04 506.4</td> <td>13.29 22.4 108.59 0.5790 9.04 506.4</td> <td>22.4 108.59 0.5790 9.04 506.4</td> <td>108.59 0.5790 9.04 506.4</td> <td>0.5790 9.04 506.4</td> <td>9.04 506.4</td> <td>506.4</td> <td></td> <td>2.6849</td> <td></td> <td></td> <td>20.58</td> <td></td> <td>318.3</td> <td>87021.8</td> <td>1188.9</td> <td>15419.9</td> <td>6.801</td> <td>23188.1</td> <td>426.4</td> <td>18431.7</td> <td>4261.6</td> <td>70.76</td>	3.66 1.7870 38491.1 13.29 22.4 108.59 0.5790 9.04 506.4 2.6849	38491.1 13.29 22.4 108.59 0.5790 9.04 506.4	13.29 22.4 108.59 0.5790 9.04 506.4	22.4 108.59 0.5790 9.04 506.4	108.59 0.5790 9.04 506.4	0.5790 9.04 506.4	9.04 506.4	506.4		2.6849			20.58		318.3	87021.8	1188.9	15419.9	6.801	23188.1	426.4	18431.7	4261.6	70.76
1.71 18.99 86.3 490.6 83970.9 1072.7 12672.8 10.046 29409.0 654.8 16445.4 5270.4 1.13 21.59 88.4 408.7 86987.9 1087.5 19541.1 6.571 29077.9 667.6 19055.4 6825.0 0.97 15.74 78.7 269.4 408.7 1087.5 19541.1 6.571 29077.9 667.6 19796.1 5186.0 0.92 18.24 72.4 282.5 84242.0 1289.4 18790.3 5.61.9 1713.6 6420.7 1732.6 171.1 18791.6 6420.7 19796.1 5180.0 19796.1 5180.0 19796.1 5180.0 19796.1 5180.0 19796.1 5180.0 19796.1 5180.0 19796.1 19796.1 5180.0 19796.1 19796.1 5180.0 19796.1 19796.1 19796.1 19796.1 19796.1 19796.1 19796.1 19796.1 19796.1 19796.1 19796.1 19796.1 19796.1 19796.1	3.69 1.7505 40339.4 11.02 0.0 110.88 0.6141 9.39 578.2 2.8253	40339.4 11.02 0.0 110.88 0.6141 9.39 578.2	11.02 0.0 110.88 0.6141 9.39 578.2	0.0 110.88 0.6141 9.39 578.2	110.88 0.6141 9.39 578.2	0.6141 9.39 578.2	9.39 578.2	578.2		2.8253			22.37		281.5	9.00606	1229.5	15694.1	6.612	24002.1	448.8	16814.4	4240.5	78.53
1.13 21.59 88.4 408.7 86987.9 1087.5 19541.1 6.571 29077.9 667.6 19055.4 6825.0 0.97 15.74 78.7 269.4 93245.8 848.3 10819.9 5.605 28184.4 349.0 19796.1 5186.0 0.97 18.24 72.4 282.5 84242.0 1289.4 18790.3 5.380 27039.2 611.1 18791.6 6420.7 1.32 18.02 94.8 445.8 84165.0 1289.4 18790.3 5.380 27039.2 611.1 18791.6 6420.7 1.03 18.78 34165.0 1289.4 18790.3 5.380 27039.2 611.1 18791.6 6420.7 1.03 18.78 84165.0 1289.4 18713.0 5.985 1862.0 19786.1 1879.1 6420.7 17139.6 6420.7 17139.6 6420.7 17140.0 6825.8 28338.1 66.40.9 17139.6 653.0 19128.0 1805.0 19128.0	2.87 2.9897 3772.9 17.36 38.5 98.01 0.5200 10.79 321.4 2.2197	37772.9 17.36 38.5 98.01 0.5200 10.79 321.4	17.36 38.5 98.01 0.5200 10.79 321.4	38.5 98.01 0.5200 10.79 321.4	98.01 0.5200 10.79 321.4	0.5200 10.79 321.4	10.79 321.4	321.4		2.2197		1.71	18.99		490.6	83970.9	1072.7	12672.8	10.046	29409.0	654.8	16445.4	5270.4	99.68
0.97 15.74 78.7 269.4 93245.8 848.3 10819.9 5.605 28184.4 349.0 19796.1 5186.0 0.92 18.24 72.4 282.5 84242.0 1289.4 18790.3 5.380 27039.2 611.1 18791.6 6420.7 1.32 18.02 94.8 445.8 84165.0 1298.4 28781.5 7.433 2313.6 651.9 17139.6 5639.0 1.03 18.78 71.4 332.9 92829.4 1157.2 24036.9 5.885 28338.1 603.9 19586.2 5839.0 1.128 21.94 95.8 434.9 86753.7 1169.0 20896.5 8.343 29414.6 786.4 19529.1 8359.1 1.108 21.33 76.9 422.0 90433.2 788.3 12442.2 6.09 31318.0 458.1 1765.3 4001.6 0.75 13.77 889 176.0 1744.2 6.09 31318.0 458.1 1765.3 4	2.0327 44645.4 14.08 30.5 102.25 0.6198 9.59 366.1	44645.4 14.08 30.5 102.25 0.6198 9.59 366.1	14.08 30.5 102.25 0.6198 9.59 366.1	30.5 102.25 0.6198 9.59 366.1	102.25 0.6198 9.59 366.1	0.6198 9.59 366.1	9.59 366.1	366.1		3.3597			21.59		408.7	86987.9	1087.5	19541.1	6.571	29077.9	9.799	19055.4	6825.0	88.39
0.92 18.24 72.4 282.5 84242.0 1289.4 18790.3 5.380 27039.2 611.1 18791.6 6420.7 1.32 18.02 94.8 445.8 84165.0 1298.4 28781.5 7.433 32132.6 561.9 17139.6 5639.0 1.03 18.78 71.4 332.9 92829.4 1157.2 24036.9 5.985 28338.1 603.9 19586.2 5895.0 1.28 21.94 95.8 434.9 86753.7 1169.0 20896.5 8.343 29414.6 786.4 19529.1 8359.1 1.21 17.96 832.2 264.4 9056.6 1075.0 13413.0 6.429 37126.7 586.0 19128.6 5765.8 1.08 21.37 76.8 860.7 13413.0 6.429 37126.7 586.0 19128.6 5765.8 1.08 21.37 76.8 1760.8 1764.8 9.063 3138.0 467.1 1765.3 4001.6 1.	2.1848 30323.0 9.63 27.7 110.90 0.4865 10.25 535.6	30323.0 9.63 27.7 110.90 0.4865 10.25 535.6	9.63 27.7 110.90 0.4865 10.25 535.6	27.7 110.90 0.4865 10.25 535.6	110.90 0.4865 10.25 535.6	0.4865 10.25 535.6	10.25 535.6	535.6		2.5279			15.74		269.4	93245.8	848.3	10819.9	2.605	28184.4	349.0	19796.1	5186.0	92.27
1.32 18.02 94.8 445.8 84165.0 1298.4 28781.5 7.433 3213.2 561.9 17139.6 5639.0 1.03 18.78 71.4 332.9 92829.4 1157.2 24036.9 5.985 28338.1 603.9 19586.2 5805.9 1.28 21.94 95.8 434.9 86753.7 1169.0 20896.5 8.343 29414.6 786.4 19529.1 8359.1 1.21 17.96 83.2 264.4 9056.6 1075.0 13413.0 6.429 39126.7 586.0 19128.6 5765.8 1.08 21.33 76.9 422.0 90433.2 788.3 12442.2 6.090 31318.0 458.1 17665.3 4001.6 0.75 1.37 388.9 86027.4 681.9 5684.0 45.4 3138.0 469.4 1760.8 45.4 300.1 16989.5 103.7 1140.0 103.3 1140.2 103.4 1140.2 103.4 1140.2 103.4 <t< td=""><td>1.9031 48190.1 10.73 0.0 97.73 0.4430 9.92 504.3</td><td>48190.1 10.73 0.0 97.73 0.4430 9.92 504.3</td><td>10.73 0.0 97.73 0.4430 9.92 504.3</td><td>0.0 97.73 0.4430 9.92 504.3</td><td>97.73 0.4430 9.92 504.3</td><td>0.4430 9.92 504.3</td><td>9.92 504.3</td><td>504.3</td><td></td><td>2.8906</td><td></td><td></td><td>18.24</td><td></td><td>282.5</td><td>84242.0</td><td>1289.4</td><td>18790.3</td><td>5.380</td><td>27039.2</td><td>611.1</td><td>18791.6</td><td></td><td>100.09</td></t<>	1.9031 48190.1 10.73 0.0 97.73 0.4430 9.92 504.3	48190.1 10.73 0.0 97.73 0.4430 9.92 504.3	10.73 0.0 97.73 0.4430 9.92 504.3	0.0 97.73 0.4430 9.92 504.3	97.73 0.4430 9.92 504.3	0.4430 9.92 504.3	9.92 504.3	504.3		2.8906			18.24		282.5	84242.0	1289.4	18790.3	5.380	27039.2	611.1	18791.6		100.09
1.03 18.78 71.4 332.9 92829.4 1157.2 24036.9 5.985 28338.1 603.9 19586.2 5805.0 1.28 21.94 95.8 434.9 86753.7 1169.0 20896.5 8.343 29414.6 786.4 19529.1 8359.1 1.21 17.96 83.2 264.4 9056.9 1075.0 13413.0 6.429 39126.7 586.0 19128.6 5765.8 1.08 21.33 76.9 422.0 90433.2 788.3 12442.2 6.090 31318.0 458.1 17665.3 4901.6 0.75 13.77 388.9 86027.4 681.9 5684.0 4.546 31152.3 407.1 22488.0 4024.7 1.42 22.03 93.6 397.8 89160.2 96.4 17440.8 9.03 31289.6 586.9 19524.4 710.2 1.74 22.03 897.6 1740.8 7.39 256.8 19524.4 710.2 1.74 21.49 <td>3.21 2.2615 40398.7 15.98 0.0 131.56 0.5569 8.86 449.6 2.8571</td> <td>40398.7 15.98 0.0 131.56 0.5569 8.86 449.6</td> <td>15.98 0.0 131.56 0.5569 8.86 449.6</td> <td>0.0 131.56 0.5569 8.86 449.6</td> <td>131.56 0.5569 8.86 449.6</td> <td>0.5569 8.86 449.6</td> <td>8.86 449.6</td> <td>449.6</td> <td></td> <td>2.8571</td> <td></td> <td></td> <td>18.02</td> <td></td> <td>445.8</td> <td>84165.0</td> <td>1298.4</td> <td>28781.5</td> <td>7.433</td> <td>32132.6</td> <td>561.9</td> <td>17139.6</td> <td>5639.0</td> <td>78.87</td>	3.21 2.2615 40398.7 15.98 0.0 131.56 0.5569 8.86 449.6 2.8571	40398.7 15.98 0.0 131.56 0.5569 8.86 449.6	15.98 0.0 131.56 0.5569 8.86 449.6	0.0 131.56 0.5569 8.86 449.6	131.56 0.5569 8.86 449.6	0.5569 8.86 449.6	8.86 449.6	449.6		2.8571			18.02		445.8	84165.0	1298.4	28781.5	7.433	32132.6	561.9	17139.6	5639.0	78.87
1.28 21.94 95.8 434.9 86753.7 1169.0 20896.5 8.343 29414.6 786.4 19529.1 8359.1 1.21 17.96 83.2 264.4 90566.9 1075.0 13413.0 6.429 39126.7 586.0 19128.6 5765.8 1.08 21.33 76.9 422.0 90433.2 788.3 12442.2 6.090 31318.0 458.1 17665.3 4901.6 0.75 13.77 388.9 86027.4 681.9 5684.0 4.546 31152.3 407.1 22458.0 4024.7 1.42 22.03 93.6 397.8 89160.2 96.4 17640.8 9.03 32289.6 586.9 19526.4 6043.7 1.27 22.81 83.9 330.4 92704.3 727.8 12689.6 7.389 313.3 4619.0 1.27 22.81 891.0 7274.7 7.718 2569.8 40.1.4 11248.5 4190.0 1.30 1.31 1.41.4 <td>1.9023 44633.2 13.44 0.0 109.99 0.4574 9.24 505.6</td> <td>44633.2 13.44 0.0 109.99 0.4574 9.24 505.6</td> <td>13.44 0.0 109.99 0.4574 9.24 505.6</td> <td>0.0 109.99 0.4574 9.24 505.6</td> <td>109.99 0.4574 9.24 505.6</td> <td>0.4574 9.24 505.6</td> <td>9.24 505.6</td> <td>902.6</td> <td></td> <td>2.832</td> <td></td> <td></td> <td>18.78</td> <td></td> <td>332.9</td> <td>92829.4</td> <td>1157.2</td> <td>24036.9</td> <td>5.985</td> <td>28338.1</td> <td>603.9</td> <td>19586.2</td> <td></td> <td>95.10</td>	1.9023 44633.2 13.44 0.0 109.99 0.4574 9.24 505.6	44633.2 13.44 0.0 109.99 0.4574 9.24 505.6	13.44 0.0 109.99 0.4574 9.24 505.6	0.0 109.99 0.4574 9.24 505.6	109.99 0.4574 9.24 505.6	0.4574 9.24 505.6	9.24 505.6	902.6		2.832			18.78		332.9	92829.4	1157.2	24036.9	5.985	28338.1	603.9	19586.2		95.10
1.21 17.96 83.2 264.4 90566.9 1075.0 13413.0 6.429 39126.7 585.0 19128.6 576.8 1 1.08 21.33 76.9 422.0 90433.2 788.3 12442.2 6.090 31318.0 458.1 17665.3 4901.6 1 0.75 13.72 77.7 388.9 86027.4 681.9 5684.0 4.546 38152.3 407.1 12458.0 4004.4 1.42 22.03 93.6 397.8 89160.2 96.4 17640.8 9.063 32289.6 56.9 19526.4 6043.7 1.27 22.81 83.9 330.4 92704.3 1724.8 17.89 13.54 509.0 16889.5 7103.9 1 1.28 22.41 94273.1 700.7 12741.7 7.71 200.8 401.4 1702.2 1 100.2 1 100.0 13.440.0 100.0 100.0 100.0 100.0 100.0 100.0 100.0 100.	2.1917 48874.7 16.40 0.0 112.93 0.4780 10.17 428.7	48874.7 16.40 0.0 112.93 0.4780 10.17 428.7	16.40 0.0 112.93 0.4780 10.17 428.7	0.0 112.93 0.4780 10.17 428.7	112.93 0.4780 10.17 428.7	0.4780 10.17 428.7	10.17 428.7	428.7		4.067			21.94		434.9	86753.7	1169.0	20896.5	8.343	29414.6	786.4	19529.1		109.95
1.08 21.33 76.9 422.0 90433.2 788.3 12442.2 6.090 31318.0 458.1 17665.3 4901.6 1 0.75 13.72 77.7 388.9 86027.4 681.9 5684.0 4.546 38152.3 407.1 22458.0 4024.7 1.42 22.03 93.6 397.8 89160.2 96.4 17640.8 9.063 32289.6 56.9 19526.4 6043.7 1.27 22.81 83.9 330.4 92704.3 727.8 12689.6 7.389 3135.4 609.0 16889.5 7103.9 1 1.29 21.75 892.2 421.4 94273.1 700.7 12741.7 7.718 29568.1 633.4 1790.2 1 100.2 <	2.1103 42485.6 10.80 0.0 122.05 0.4538 8.78 330.8	42485.6 10.80 0.0 122.05 0.4538 8.78 330.8	10.80 0.0 122.05 0.4538 8.78 330.8	0.0 122.05 0.4538 8.78 330.8	122.05 0.4538 8.78 330.8	0.4538 8.78 330.8	8.78 330.8	330.8		3.0672		_	17.96		264.4	90566.9	1075.0	13413.0	6.429	39126.7	585.0	19128.6		102.40
0.75 13.72 77.7 388.9 86027.4 681.9 5684.0 4.546 3812.3 407.1 22458.0 4024.7 1.42 22.03 93.6 397.8 89160.2 996.4 17640.8 9.063 32289.6 586.9 19526.4 6043.7 1.27 22.81 83.9 330.4 92704.3 727.8 12689.6 7.389 3135.4 509.0 16989.5 7103.9 1 1.29 21.75 89.2 427.4 94273.1 700.7 12741.7 7.718 29568.1 633.4 16234.4 7190.2 1 0.77 10.17 10.17 10.31 191.4 91378.5 1826.4 3.799 25432.2 866.6 1840.0 2770.0 1.30 18.70 85.8 17.8 16856.4 3.799 25432.3 18551.2 3910.5 1.30 18.70 86.1 166.7 2759.2 269.2 23.3 15551.2 3910.5 1.30	1.9604 46169.9 15.90 0.0 117.27 0.4655 10.52 317.4	46169.9 15.90 0.0 117.27 0.4655 10.52 317.4	15.90 0.0 117.27 0.4655 10.52 317.4	0.0 117.27 0.4655 10.52 317.4	117.27 0.4655 10.52 317.4	0.4655 10.52 317.4	10.52 317.4	317.4		2.8339			21.33		422.0	90433.2	788.3	12442.2	060.9	31318.0	458.1	17665.3	4901.6	106.10
1.42 22.03 93.6 397.8 89160.2 996.4 17640.8 9.063 32289.6 586.9 1926.4 6043.7 1.27 22.81 83.9 330.4 92704.3 727.8 1289.6 7.389 31135.4 509.0 16899.5 7103.9 1 1.29 21.75 892.2 421.4 94273.1 700.7 12741.7 7.718 29568.1 633.4 16234.4 7102.2 1 0.77 10.17 10.31 191.4 91378.5 782.6 18496.4 3.799 25432.2 866.6 18410.0 2770.0 1.30 18.70 85.8 242.6 84420.5 18496.4 3.799 25432.3 866.6 18410.0 2770.0 1.30 18.70 86.8 18.2 16.6 17.5 18496.4 3.799 25432.3 18551.2 3970.5 1.30 18.70 86.8 18.2 1.06.9 972.5 8871.8 3970.5 1381.4 <	1.5012 29377.1 15.01 0.0 109.90 0.5331 5.30 246.3	29377.1 15.01 0.0 109.90 0.5331 5.30 246.3	15.01 0.0 109.90 0.5331 5.30 246.3	0.0 109.90 0.5331 5.30 246.3	109.90 0.5331 5.30 246.3	0.5331 5.30 246.3	5.30 246.3	246.3		3.6220			13.72		388.9	86027.4	681.9	5684.0	4.546	38152.3	407.1	22458.0	4024.7	58.20
1.27 2.2 81 83.9 330.4 92704.3 727.8 12689.6 7.389 3135.4 590.0 16689.5 7103.9 1 1.29 2.7.75 892 471.4 94273.1 700.7 12741.7 7.718 295.68.1 633.4 16234.4 7190.2 1 1.46 2.1.49 85.2 244.2 9539.5.5 1157.9 16856.4 7.372 26008.8 401.4 11248.5 4619.0 0.77 10.17 10.31 191.4 91378.5 782.6 18496.4 3.799 2543.2 866.6 18410.0 2707.0 1.30 18.70 85.2 242.6 84420.5 813.0 11679.1 6.621 27259.2 523.3 15551.2 3910.5 1.30 12.87 81.8 99045.5 804.4 10612.6 5.969 29801.2 988.8 15815.0 3926.8 0.82 13.72 8681.3 554.0 12857.4 5.12 2696.8 281.0 1381.4	2.0558 43079.6 15.12 48.0 106.16 0.4974 10.28 373.6	43079.6 15.12 48.0 106.16 0.4974 10.28 373.6	15.12 48.0 106.16 0.4974 10.28 373.6	48.0 106.16 0.4974 10.28 373.6	106.16 0.4974 10.28 373.6	0.4974 10.28 373.6	10.28 373.6	373.6		3.1393			22.03		397.8	89160.2	996.4	17640.8	9.063	32289.6	586.9	19526.4	6043.7	94.41
1.29 21.75 89.2 421.4 94273.1 700.7 12741.7 7.718 29568.1 633.4 16234.4 7190.2 1 1.46 21.49 85.2 244.2 95395.5 1157.9 18856.4 7.372 26008.8 401.4 11248.5 4619.0 0.77 10.17 103.1 191.4 91378.5 782.6 18496.4 3.79 25432.2 866.6 18440.0 2707.0 1.30 18.70 85.8 242.6 84420.5 813.0 11679.1 6.621 27259.2 283.3 15551.2 3910.5 1.30 12.87 81.9 87.8 106.2 2726.1 3926.8 0.35 51.56 40.4 160.8 92729.3 222.6 8271.9 2.431 22390.1 106.2 2762.1 1381.4 0.82 18.72 86813.8 554.0 12857.4 5.12 26968.8 281.0 16338.1 653.3 143.3 0.70 10.44	2.1617 48397.2 12.37 50.1 117.93 0.4999 10.80 254.2	48397.2 12.37 50.1 117.93 0.4999 10.80 254.2	12.37 50.1 117.93 0.4999 10.80 254.2	50.1 117.93 0.4999 10.80 254.2	117.93 0.4999 10.80 254.2	0.4999 10.80 254.2	10.80 254.2	254.2		3.3407			22.81		330.4	92704.3	727.8	12689.6	7.389	31135.4	206.0	16989.5		110.07
1.46 21.49 85.2 244.2 95395.5 1157.9 16856.4 7.372 26008.8 401.4 11248.5 4619.0 0.77 10.17 103.1 191.4 91378.5 782.6 18496.4 3.799 25433.2 866.6 18140.0 2707.0 1.30 18.70 85.8 242.6 84420.5 813.0 11679.1 6621 2729.2 253.3 1551.2 3910.5 1.30 12.87 81.9 187.8 99045.5 804.4 1061.2 5.969 29801.2 988.8 15815.0 3926.8 0.82 51.56 40.4 160.8 92729.3 222.6 8271.9 2.431 22390.1 106.2 2276.1 1381.4 0.82 18.72 86813.8 554.0 12857.4 5.12 2696.8 281.0 1435.2 3148.3 1.15 19.10 88.8 294.2 85952.1 785.6 15748.2 7.27 30489.4 60.0 16398.1 653.3<	2.3859 47746.1 15.89 0.0 102.20 0.5320 10.98 237.2	47746.1 15.89 0.0 102.20 0.5320 10.98 237.2	15.89 0.0 102.20 0.5320 10.98 237.2	0.0 102.20 0.5320 10.98 237.2	102.20 0.5320 10.98 237.2	0.5320 10.98 237.2	10.98 237.2	237.2		3.2522			21.75		421.4	94273.1	700.7	12741.7	7.718	29568.1	633.4	16234.4		100.52
0.77 10.17 103.1 191.4 91378.5 782.6 18496.4 3.799 25433.2 866.6 18140.0 2707.0 1.30 18.70 85.8 242.6 84420.5 813.0 11679.1 6.621 27259.2 523.3 15551.2 3910.5 1.30 12.87 81.9 187.8 99045.5 804.4 10612.6 5.969 29801.2 988.8 15615.0 3926.8 0.35 51.56 40.4 160.8 29729.3 222.6 8271.9 2.431 22390.1 106.2 22762.1 1381.4 0.82 18.72 86813.8 554.0 12857.4 5.12 26968.8 281.0 13455.2 3148.3 1.15 19.10 88.8 1782 8555.1 785.4 5.12 20489.4 606.0 16398.1 6534.3 0.60 10.44 93.1 31.9 31.7 16343.2 231.3	1.9410 43209.8 10.12 49.3 111.90 0.6951 13.72	43209.8 10.12 49.3 111.90 0.6951 13.72 296.4	10.12 49.3 111.90 0.6951 13.72 296.4	49.3 111.90 0.6951 13.72 296.4	111.90 0.6951 13.72 296.4	0.6951 13.72 296.4	13.72 296.4	296.4		2.3090			21.49		244.2	95395.5	1157.9	16856.4	7.372	26008.8	401.4	11248.5	4619.0	98.66
1.30 18.70 85.8 242.6 84420.5 813.0 11679.1 6.621 27259.2 523.3 15551.2 3910.5 1.30 12.87 81.9 187.8 99045.5 804.4 10612.6 5.969 29801.2 988.8 15815.0 3926.8 0.35 51.56 40.4 160.8 92729.3 222.6 8271.9 2.431 22390.1 106.2 22762.1 1381.4 0.82 18.72 58.8 178.2 86813.8 554.0 12857.4 5.120 26968.8 281.0 13455.2 3148.3 1.15 19.10 88.8 294.2 85952.1 785.6 15748.2 7.275 30489.4 606.0 16398.1 6534.3 0.70 10.44 93.1 133.4 8062.2 756.3 18692.1 4.239 23978.0 371.7 16343.2 4371.3 0.60 14.90 46.7 107.2 2066.8 713.1 146.4 4337.3 3373.4 4377.	17.99 1.2752 29879.2 7.38 47.0 133.31 1.2612 7.75 422.6 0.7470	29879.2 7.38 47.0 133.31 1.2612 7.75 422.6	7.38 47.0 133.31 1.2612 7.75 422.6	47.0 133.31 1.2612 7.75 422.6	133.31 1.2612 7.75 422.6	1.2612 7.75 422.6	7.75 422.6	422.6		0.7470			10.17		191.4	91378.5	782.6	18496.4	3.799	25433.2	9.998	18140.0	2707.0	65.14
12.87 81.9 187.8 99045.5 804.4 10612.6 5.969 29801.2 988.8 15815.0 3926.8 51.56 40.4 160.8 92729.3 222.6 8271.9 2.43 22390.1 106.2 22762.1 1381.4 18.72 58.8 178.2 86813.8 554.0 12857.4 5.120 2696.8 281.0 13455.2 3148.3 19.10 88.8 294.2 85952.1 785.6 15748.2 7.275 30489.4 606.0 16398.1 6534.3 10.44 93.1 133.4 84062.2 756.3 18692.1 4.239 23978.0 371.7 16543.2 4371.3 46, 71 107.7 7050.8 713.1 145.44 327 3923.1 356.5 14567.4 3432 365.7 365.7 3432.8 3432.4 3432 356.7 345.7 3432.4 3432 356.7 3432.4 3432 365.7 3432.4 3432 365.7 345.7 3432	4.76 1.7018 26021.5 8.59 0.0 129.77 0.3072 7.77 308.4 1.3085	26021.5 8.59 0.0 129.77 0.3072 7.77 308.4	8.59 0.0 129.77 0.3072 7.77 308.4	0.0 129.77 0.3072 7.77 308.4	129.77 0.3072 7.77 308.4	0.3072 7.77 308.4	7.77 308.4	308.4		1.3085	i .		18.70		242.6	84420.5	813.0	11679.1	6.621	27259.2	523.3	15551.2	3910.5	55.04
51.56 40.4 160.8 92729.3 222.6 8271.9 2.431 22390.1 106.2 22762.1 1381.4 18.72 58.8 178.2 86813.8 554.0 12857.4 5.120 26968.8 281.0 13455.2 3148.3 19.10 88.8 294.2 85952.1 785.6 15748.2 7.275 30489.4 606.0 16398.1 6534.3 10.44 93.1 133.4 84062.2 756.3 18692.1 4.239 23978.0 371.7 16543.2 4371.3 14, 20 64.7 107.2 7056.8 713.1 145.44 327 3923.1 36.5 14657.4 3438.4	13.84 1.8101 39382.5 7.53 0.0 187.92 0.4978 11.54 197.8 0.9434	39382.5 7.53 0.0 187.92 0.4978 11.54 197.8	7.53 0.0 187.92 0.4978 11.54 197.8	0.0 187.92 0.4978 11.54 197.8	187.92 0.4978 11.54 197.8	0.4978 11.54 197.8	11.54 197.8	197.8		7.9434	1		12.87		187.8	99045.5	804.4	10612.6	5.969	29801.2	8.886	15815.0	3926.8	88.91
0.82 18.72 58.8 178.2 86813.8 554.0 12857.4 5.120 26968.8 281.0 13455.2 3148.3 1.15 19.10 88.8 294.2 85952.1 785.6 15748.2 7.275 30489.4 606.0 16398.1 6534.3 0.70 10.44 93.1 133.4 84062.2 756.3 18692.1 4.239 23978.0 371.7 16343.2 4371.3 0.60 14.29 423.7 3237 28237.8 373.8 3438.4	11.77 0.4496 10537.8 5.75 0.0 206.61 0.4984 4.08 157.6 2.2984	10537.8 5.75 0.0 206.61 0.4984 4.08 157.6	5.75 0.0 206.61 0.4984 4.08 157.6	0.0 206.61 0.4984 4.08 157.6	206.61 0.4984 4.08 157.6	0.4984 4.08 157.6	4.08 157.6	157.6		2.2984	1		51.56		160.8	92729.3	222.6	8271.9	2.431	22390.1	106.2	22762.1	1381.4	19.86
1.15 19.10 88.8 294.2 85952.1 785.6 15748.2 7.275 30489.4 606.0 16398.1 6534.3 0.70 10.44 93.1 133.4 84062.2 756.3 18692.1 4.239 23978.0 371.7 16343.2 4371.3 0.70 16.90 64.7 107.2 70050.8 713.1 146.4 4.237 2823.1 876.5 16057.4 2438.4	15.84 1.4404 27723.8 7.15 0.0 138.66 0.3414 11.51 325.8 1.3548	27723.8 7.15 0.0 138.66 0.3414 11.51 325.8	7.15 0.0 138.66 0.3414 11.51 325.8	0.0 138.66 0.3414 11.51 325.8	138.66 0.3414 11.51 325.8	0.3414 11.51 325.8	11.51 325.8	325.8		1.3548			18.72		178.2	86813.8	554.0	12857.4	5.120	26968.8	281.0	13455.2	3148.3	67.98
0.70 10.44 93.1 133.4 8406.2.2 756.3 18692.1 4.239 23978.0 371.7 16343.2 4371.3 0.60 14.20 44.7 107.7 70050.8 713.1 1455.4 4.337 2823.1 855.4 14657.4 3.438.4	3.77 2.1251 46737.4 11.98 0.0 116.54 0.4672 9.87 354.9 3.0368	46737.4 11.98 0.0 116.54 0.4672 9.87 354.9	11.98 0.0 116.54 0.4672 9.87 354.9	0.0 116.54 0.4672 9.87 354.9	116.54 0.4672 9.87 354.9	0.4672 9.87 354.9	9.87 354.9	354.9		3.0368			19.10		294.2	85952.1	785.6	15748.2	7.275	30489.4	0.909	16398.1	6534.3	94.86
16.20 66.7 107.2 70050.8 712.1 11654.4 4.337 2823.1 5.55.6 16057.4 3438.4	7.40 1.3968 35435.5 6.42 0.0 106.92 0.7645 11.61 320.9 0.9306	35435.5 6.42 0.0 106.92 0.7645 11.61 320.9	6.42 0.0 106.92 0.7645 11.61 320.9	0.0 106.92 0.7645 11.61 320.9	106.92 0.7645 11.61 320.9	0.7645 11.61 320.9	11.61 320.9	320.9		3.9306			10.44		133.4	84062.2	756.3	18692.1	4.239	23978.0	371.7	16343.2	4371.3	88.92
0.09 10.29 00.1 197.2 797.37.0 11.01 4.4 4.337 202.1.0 303.0 10937.4 3430.4	3.25 1.1941 27002.0 8.99 0.0 96.47 0.3042 7.47 348.3 1.2087	27002.0 8.99 0.0 96.47 0.3042 7.47 348.3	8.99 0.0 96.47 0.3042 7.47 348.3	0.0 96.47 0.3042 7.47 348.3	96.47 0.3042 7.47 348.3	0.3042 7.47 348.3	7.47 348.3	348.3		1.2087	-	. 69.0	16.29	1.99	197.2	79959.8	713.1	11654.4	4.337	28231.5	355.6	16957.4	3438.4	61.23

ANID	macro_grp	Chem2012	macro_grp Chem2012 CERAMIC TYPE	MATERIAL	SOURCE	STATE	STATE SITE_NAME	SITE_NO	AS	ΓA	Π	ND	SM	Π	YB	CE	00	CR
UT00787	T00787 Group-C2 Unas.	Unas.	Three Circle Corrugated	Pottery	MURR	MN	Old Town	LA 001113		33.21 0.3518		28.92	5.57	1.64 2	2.62 101.85	1.85 1	18.79	19.27
WCRM001	Group-C2a	Mimbres-49A	VCRM001 Group-C2a Mimbres-49A Mimbres B/W Style III	Pottery	MURR	MΝ	Badger Ruin	LA 111395	1.82	37.14 0.	3095	25.90	5.63	3.27 2	2.69	73.16 12	12.16	59.27
WCRM002	Group-C2a	Mimbres-49A	VCRM002 Group-C2a Mimbres-49A Mimbres B/W Style II	Pottery	MURR	MN	Badger Ruin	LA 111395	2.75	36.04 0.	3210	28.98			2.11 7	71.29 13		59.48
WCRM003	Group-B1	Mimbres-04A	WCRM003 Group-B1 Mimbres-04A Mimbres B/W Style III	Pottery	MURR	MN	Badger Ruin	LA 111395	2.70	40.27 0.	4292	29.05					4.23	19.52
WCRM004	Group-B1	Mimbres-04B	VCRM004 Group-B1 Mimbres-04B Mimbres B/W Style III	Pottery	MURR	MN	Badger Ruin	LA 111395	2.65	56.79 0.	9909	39.06	7.97		3.81	98.26	4.53	24.21
WCRM005	Group-C2a	Mimbres-49A	WCRM005 Group-C2a Mimbres-49A Mimbres B/W Style III	Pottery	MURR	MN W	Jackson Fraction	LA 111413		41.98 0.	3473	31.26			l	88.42 14	14.40	66.92
WCRM006	Group-C2a	Mimbres-49A	WCRM006 Group-C2a Mimbres-49A Mimbres B/W Style III	Pottery	MURR	MN W	Jackson Fraction	LA 111413	3.17	41.21 0.5078	.5078	37.12			3.88	85.58 12	12.86	55.56
WCRM007	Group-B2	Mimbres-11	WCRM007 Group-B2 Mimbres-11 Mimbres B/W Style III	Pottery	MURR	MN	Jackson Fraction	LA 111413		34.03 0		24.71			2.62	65.46 14	14.56	48.69
WCRM008	Group-C2a	Mimbres-49A	WCRM008 Group-C2a Mimbres-49A Mimbres B/W Style II	Pottery	MURR	MN	Jackson Fraction	LA 111413		40.33 0.5009		38.17		3.03			12.96	57.42
WCRM009	Group-B1	Mimbres-09	WCRM009 Group-B1 Mimbres-09 Mimbres B/W Style III	Pottery	MURR	MN	Jackson Fraction	LA 111413		59.78 0.5936		61.95 12.50					2.43	13.24
WCRM010	Group-B2	Mimbres-08	WCRM010 Group-B2 Mimbres-08 Mimbres B/W Style III	Pottery	MURR	MN W	Jackson Fraction	LA 111413		33.91 0.3845		27.30			2.99 6	67.40	8.01	23.66
WCRM011 Clay	Clay		Clay	Clay	MURR	MN	Badger Ruin	LA 111395	3.96	37.34 0.		28.43	6.01	3.12 2		7.87	19.91	93.02
WCRM012 Clay	Clay		Clay	Clay	MURR	MN	Badger Ruin	LA 111395		35.12 0.4770		34.69			3.41 6	68.79 17	17.31	54.06
WCRM013 Clay	Clay		Clay	Clay	MURR	MN	Badger Ruin	LA 111395	69.9	40.66 0.5372		34.80	7.74 4	4.33 3	3.69	82.52 29	29.40	67.70

>	34	03	66	80	69	18	27	72	44	20	30	44	68	88
	106.34	۰.98	. 67	3 42.80	99.99	3 88.18	5 110.27	3 71.72	96.44	34.70	(43.30	114.44	124.89	1 96.88
T	3251.4	4329.9	3630.9	2947.8	2657.9	4857.8	4395.5	5896.8	4282.2	2368.2	2194.0	5844.0	5079.9	4757.1
NA	20317.4	17336.5	16773.2	15785.7	11420.5	16843.4	15133.7	12152.3	14573.1	16587.6	9526.9	1833.8	9455.8	5930.6
MN	1590.8	537.2	574.3	248.0	376.4	674.5	8.099	1663.0	638.9	339.9	329.5	1029.5	1331.5	1122.7
X	23549.4	23899.8	24978.9	28237.8	29314.3	22758.1	28835.2	31072.5	23626.7	28737.0	31364.2	29787.6	22425.5	32691.3
DΥ	2.939	3.603	3.886	3.969	9.079	3.656	5.646	3.736	5.623	8.206	2.471	4.869	4.746	5.109
CA	14716.2	15030.0	19099.0	10094.0	129908.0	18858.0	13583.0	10744.0	13080.0	13512.0	7429.0	16335.5	22416.5	22975.1
BA	840.6	797.3	737.0	799.8	583.4	686.5	9.098	584.3	8.996	1117.9	471.1	337.5	457.1	754.1
AL	88111.0	95893.8	100916.0	83549.4	89863.6	8.77966	89219.4	90171.0	84965.2	95663.0	80741.4	93719.9	93733.7	86995.3
ZR	107.9	165.2	167.2	167.6	1.69.1	219.8	201.8	59.6 135.6	196.4	207.0	174.9	152.4	146.0	189.4
NZ	63.6	64.8	75.3	48.1	81.2	83.7	125.5		142.2	62.3	41.0	128.9	381.0	230.8
TH	9.24	12.67	12.65	18.59	27.18	13.67	13.10	17.52	12.09	14.12	27.49	13.34	9.94	12.66
TB	0.62	0.45	0.43	1.05	0.72	0.45	0.95	0.65	0.89	1.19	0.33	0.88	0.68	1.68
TA	0.5863 0.62	1.0430	1.022	1.3028	1.5504 0.72 27.18	1.1718 0.45 13.67	0.9081 0.95 13.10	1.4173 0.65 17.52	0.9650 0.89 12.09	0.9880 1.19 14.12	112.4 1.6107 0.33	1.2274 0.88	0.8148 0.68	225.0 1.0744 1.68 12.66
SR	673.0	275.7	360.9	248.8	233.9	329.4	283.7	253.3	323.4	131.2	112.4	62.2	277.6	225.0
SC	10.88	11.01	11.47	99.9	7.71	11.45	13.43	9.01	13.63	9.84	5.52	17.20	15.28	14.39
SB	0.4031	0.4658	0.4073	0.2862	0.4205	0.4576	0.7782	0.7691	0.7520	0.5149	0.6042	0.7434	0.7919	1.0016
RB	71.50	0.0 105.31	0.0 110.34	0.0 140.33	0.0 177.44	0.0 112.30	8.78 0.0 138.53	174.14	0.0 145.25	0.0 124.20	0.0 199.48	0.0 177.44	0.0 114.91	127.30
Z	0.0						0.0	40.4	0.0	0.0		0.0	0.0	49.8
H	5.15	7.79	7.43	6.70	7.02	11.31		92.9	8.38	8.08	7.58	5.81	90.9	7.53
FE	2.15 1.3759 48354.5	35862.9	4.80 1.2940 39007.0 7.43	4.23 1.1410 22759.1	5.88 1.3733 23661.9 7.02	42743.4	8.04 1.6828 39652.0	27733.0	8.28 1.6815 40230.5	17627.9	20340.8	49556.4	68517.5	49023.4
EU	1.3759	4.56 1.3788	1.2940	1.1410	1.3733	1.2924	1.6828	0.9848	1.6815	2.4544	0.6099	1.1466	1.7146	1.6432
CS	2.15			4.23		4.47	8.04	7.50	8.28	4.43	7.04	11.91	6.24	5.36
ANID	UT00787	WCRM001	WCRM002	WCRM003	WCRM004	WCRM005 4.47 1.2924 42743.4 11.31	WCRM006	WCRM007 7.50 0.9848 27733.0 6.56 40.4 174.14	WCRM008	WCRM009 4.43 2.4544 17627.9 8.08	WCRM010 7.04 0.6099 20340.8 7.58	WCRM011 11.91 1.1466 49556.4	WCRM012 6.24 1.7146 68517.5 6.00	WCRM013 5.36 1.6432 49023.4 7.53 49.8 127.30